

Assessment Report

**BC Geological Survey
Assessment Report
31245**

**Diamond Drilling Report
on the
Mt. Dunn Property**

Skeena Mining Division

104B/07E, 10E

**UTM Zone 09 NAD83
399100E 6260300N**

**56⁰ 29' North Latitude
130⁰ 38' West Longitude**

For

Paget Minerals Corporation

By

**John Bradford
P.Geo**

December 2009

Table of Contents

1. Introduction.....	3
2. Location and Access	3
3. Physiography, Climate and Vegetation.....	3
4. Claims and Ownership.....	3
5. Exploration History.....	7
6. Regional Geological Setting	8
7. Property Geology	10
8. Diamond Drill Program 2009	10
8.1 Drill Hole Locations and Sampling Procedures.....	10
8.2 Results.....	14
9. Conclusions and Recommendations	15
References.....	17
Appendix A Drill Logs and Assays	18
Appendix B Author's Certificate	19
Appendix C Statement of Costs.....	20
Appendix D Analytical Certificates.....	21

List of Figures

- | | |
|----------|--------------------------------|
| Figure 1 | Location Map |
| Figure 2 | Claim Map |
| Figure 3 | Regional Geology |
| Figure 4 | Drill Hole Locations (1:5,000) |
| Figure 5 | Long section (1:5,000) |

List of Tables

- | | |
|-----------|---------------------------------------------------------------|
| Table 4.1 | Claim Status |
| Table 5.1 | Historical exploration work in the Mt. Dunn Property area. |
| Table 8.1 | Mt Dunn Project 2009 Diamond Drill Hole Locations and Samples |
| Table 8.2 | Summary of intersections, 2009 drilling Mt. Dunn Project |

Diamond Drilling Report on the Mt. Dunn Property 2009

1. Introduction

Paget Resources Corp. (Paget Minerals Corp.'s predecessor company) conducted an initial reconnaissance survey of the Mt. Dunn Property on August 23 and 28, 2007 (Marsden, 2007). Follow up diamond drill testing of the project was conducted between August 21 and September 2, 2009. The purpose of the drill program was to test the grade of a mineralized porphyry system which is exposed over a strike length of over three kilometers. This report summarizes the results of this drill program. All work including report writing was completed at a cost of \$444,486.03.

2. Location and Access

The Mt. Dunn Property is located 70 kilometres northwest of Stewart in the Coast Mountain of northwestern B.C. The property is located in NTS 104B/07 and 104B/10, latitude 56°29'N, longitude 130°38'W. The property is situated west of the Unuk River about 20 kilometres southwest of the Eskay Creek mine site, which is presently accessible by gravel road from B.C. Highway 37. General access to the property is by helicopter from Stewart B.C. or Bob Quinn Lake. During the 2009 drill program, a drill camp was established at UTM 399550E, 6259760N and accessed by helicopter from Kilometer 54 on Eskay Creek mine road.

3. Physiography, Climate and Vegetation

The Mt. Dunn property extends for 7 kilometres north-south from Fewright Creek in the south across King Creek, to Terwilligen Creek in the north. Elevations range from 250 metres on Fewright Creek to over 1500 metres on the ridges between the creeks. Climate is typical of the north coastal region of B.C., with cold winters with substantial snow accumulations, and short, wet summers. Treeline lies at about 1100 metres elevation; hemlock and subalpine fir dominating at lower elevations.

4. Claims and Ownership


The Mt. Dunn Property consists of two contiguous claims which total 1822.7 hectares, as indicated on Figure 2. They are owned 100% by Paget Minerals Corporation (BCE ID


number 213190) of 11600-1040 W. Georgia St., Vancouver, BC. The claims are currently valid until September 30, 2015.

Table 4.1: Claim Status

Tenure	Owner	Good To Date	Status	Area
501297	213190 (100%)	2015/Sept30	GOOD	1286.292
501315	213190 (100%)	2015/Sept30	GOOD	536.447

PAGET RESOURCES CORP.
Mt. Dunn Project
Figure 1 - Location





5. Exploration History

Table 2 summarizes historical exploration in the Mt. Dunn property, as recorded in ten assessment reports available on the B.C. Ministry of Mines ARIS website (<http://www.aris.empr.gov.bc.ca/>).

Table 5.1 Historical exploration work in the Mt. Dunn Property area.


Report #	Year Work Done	Company	Work Done
5616	1975	Great Plains Development	Geological mapping, 186 soils, 36 rocks
6234	1977	Great Plains Development	27 soils, 28 rocks; ground IP, magnetics, spectrometry
10474	1981	Du Pont	6 silts, 201 soils, 18 rocks; ground VLF/magnetics
11673	1983	Placer/Skyline	4 heavy minerals, 3 silts, 90 soils, 7 rocks
16316	1987	Crest	7 silts, 44 soils, 3 rocks
18614	1988	Cominco	7 silts, 275 soils, 53 rocks
18987	1989	Corptech	Airborne VLF/magnetics, 198.7 line km
19262	1989	Corptech	Geological mapping, 447 soils, 147 rocks
27130	2002	Rimfire	69 soils, 118 rocks
29359	2007	Paget Resources	16 rocks

The first substantial exploration program on the property was carried out by Great Plains Development in the period 1974-1977 on the VV claims in the area south of King and north of Fewright Creeks. Despite generally favourable results, Great Plains allowed the claims to lapse in the early 1980's. Du Pont of Canada Exploration staked the Cole claim north of King Creek in 1980 and subsequently outlined an area of anomalous Cu-Au geochemistry in soils and stream sediments. Placer Development and Skyline Exploration optioned the Cole property and in 1983 carried out a small program of heavy mineral, silt, soil and rock sampling. In 1986-1987, the King-Consoat property was staked over an area including most of the prior Great Plains and Du Pont claims; these claims were owned by Crest Resources. Crest granted Cominco a "first right of refusal" on the property in 1988, and Cominco that year conducted a substantial program of soil and rock sampling. Crest and partner Corptech Industries in 1989 engaged Aerodat to conduct an airborne geophysical survey over the property. Additional geological mapping and soil

and rock sampling was carried out by OreQuest Consultants in 1989, and three drill holes were completed later that year (Awmack, 2003). Drill core and drill hole collars were relocated in 2007. In 2002 Rimfire Minerals completed a program of rock and soil geochemical sampling (Awmack, 2003).

6. Regional Geological Setting

The Mt. Dunn Property is located along the western margin of Stikine Terrane, which comprises mid-Paleozoic to middle Jurassic arc volcanics and intercalated sedimentary rocks intruded by a variety of cogenetic plutons. Regional geological mapping by the B.C. Geological Survey (e.g. Britton, 1989) is summarized in detail in Awmack (2003). According to Britton (1989), stratigraphy west of the Unuk River consists of a sedimentary dominated sequence of Upper Triassic age (Stuhini Group) overlain by a volcanic dominated sequence of Lower Jurassic age (Hazelton Group). The Mt. Dunn property straddles the contact between the two sequences. Bedded rocks in the Mt. Dunn vicinity include andesitic lapilli tuffs and tuff breccias with intercalated siltstone, calcareous sandstone and limestone. The sequence is bounded to the east by a major north striking east side down normal fault, the Harrymel Fault. Late Triassic diorite plutons intrude the Stuhini Group along the Unuk River. A north trending monzonite to quartz monzonite dyke of probable Jurassic age (Hawilson monzonite) intrudes Stuhini Group on the Mt. Dunn property. It is the host for the porphyry system drilled in 2009.



7. Property Geology

Severe topography in the King Creek drainage effectively divide the property into two areas; the Cole area north of King Creek (MINFILE 104B 209) and the Mt. Dunn (VV) area south of the creek (MINFILE 104B 079). Property geology is dominated by a 50-250 meter wide monzonite dike (Hawilson monzonite) which cuts folded Stuhini Group volcanic rocks and associated sediments. Alteration within the dike is widespread and dominantly phyllitic (quartz-pyrite-sericite). Previous work summarized by Awmack (2003) documented elevated values of copper and gold particularly within a north-south trending corridor of strong quartz vein stockwork and silicification which can migrate from the western contact zone to a more central location within the dike. No evidence of propylitic or potassic alteration was observed.

In addition to the porphyry target, values of 5-20 g/t Au have been obtained from arsenopyrite-rich massive sulfide lenses hosted by argillites in both hangingwall and footwall to the monzonite dike (Awmack, 2003). Persistent precious and base metal values are also recorded from one 20-200 meter wide zone within and to the east of a fault which occupies the precipitous trace of Gossan Creek at the northern end of the property. Neither of these targets has been worked in detail, nor drill tested.

8. Diamond Drill Program 2009

8.1 Drill Hole Locations and Sampling Procedures

The 2009 drill program consisted of five drill holes over a 1200 metre strike length of variably mineralized monzonite. Drilling was carried out by Ridgeline Diamond Drilling of Smithers, B.C. using a modified Hydracore 1000 drill (NQ core). Helicopter support was carried out by Lakelse Air Ltd. Of Terrace, B.C. and camp support by Rugged Edge Holdings of Smithers. Drill logs and assay data are in Appendix A.

Core logging of diamond drill core was performed by geologist Michael Hocking and recorded onto a logging form in Excel. Core logging focused on the identification of major lithological units and alteration assemblages as well as mineralized intervals and faults. Once identified, the lithological and alteration units were grouped into coded fields in the database.


Core intervals for sampling were tagged and logged and split. One half of each interval is sampled for assay, while the other half is kept for reference in the core box on site, presently stored at the Mt. Dunn camp. Assay samples were placed in plastic sample bags closed with zip ties. Several samples, depending on weight, were placed in rice bags and security sealed with security tags. Sample duplicates, blanks consisting of crushed landscaping limestone, and copper-gold reference samples (OREAS_52p and



OREAS_53p) were inserted at regular intervals into the sample stream. Assay samples were flown to the helicopter access site at Kilometer 54 on the Eskay Creek Road from where they were trucked to Acme Laboratories' sample prep lab in Smithers, B.C. At the prep laboratory, the samples were logged in, weighed and crushed before being shipped to Acme's analytical laboratory in Vancouver, B.C. where they were pulverized and split using standard rock preparation procedures. The samples were then analyzed for Au using a 30 gram fire assay with ICP-ES finish and for 30 elements by ICP-ES. A multi-acid digestion was utilized for the ICP analyses. Quality control at the laboratory is maintained by submitting blanks, standards and re-assaying duplicate samples from each analytical batch.

Details on hole locations and samples are included in Table 8.1; locations are plotted on Figures 4. A representative long section through four of the drill holes is in Figure 5.


Table 8.1 Mt Dunn Project 2009 Diamond Drill Hole Locations and Samples

DDH	Easting	Northing	Elev	Azim	Dip	Started	Finished	Depth m	# samples	Lab batch #
MD09-01	399250	6258368	1122	280	-60	August 21, 2009	August 23, 2009	334.67	195	SMI09000207, SMI09000220
MD09-02	399184	6258682	1195	105	-60	August 24, 2009	August 26, 2009	336.50	197	SMI09000208
MD09-03	399245	6259218	1253	100	-65	August 26, 2009	August 28, 2009	343.82	214	SMI09000209, SMI09000214
MD09-04	399632	6259510	1258	280	-60	August 29, 2009	September 1, 2008	233.72	132	SMI09000214
MD09-05	399260	6258990	1215	280	-65	September 4, 2008	September 2, 2008	337.94	198	SMI09000216
TOTAL								1586.7	936	





Paget Minerals Corp.
Figure 5 Long Section Mt. Dunn Project



8.2 Results

All drill holes except MD09-04 were extended beyond the target depth to the limit of available drill rods. MD09-04 was terminated at 234 metres in a strong fault zone. All drill holes intersected broad zones of low-grade gold and copper mineralization, as summarized in Table 8.2. Mineralization is associated with a dominant assemblage of silica-pyrite to silica-sericite(-chlorite)-pyrite alteration. Several phases of monzonite were intersected as well as monzonite clast breccias, especially in MD09-01 and MD09-02. Drill hole MD09-05 was the only drill hole to penetrate the monzonite contact and finished the hole in Stuhini Group mudstone-siltstone-sandstone west of the intrusion. Higher gold values with low copper were encountered at depth in this drill hole, associated with chlorite stringers and epidote.

The strongest mineralization was intersected in the southernmost drill hole (MD09-01) below an elevation of about 920 metres (see Figures 4, 5). This leaves open the possibility that the 2009 drill holes tested the system at a high structural level, with better grade obtainable at deeper levels in the system. Topography indicates that this level would be eventually come to surface south of MD09-01.

Table 8.2 Summary of intersections, 2009 drilling Mt. Dunn Project

DDH	From	To	m	Cu %	Au g/t	Mo %
MD09-01	3.04	334.67	331.63	0.128	0.178	
MD09-01	9.4	37.9	28.50	0.195	0.274	
MD09-01	16.03	37.9	21.87	0.216	0.301	
MD09-01	192.00	214	22.00	0.187	0.278	
MD09-01	129.65	334.67	205.02	0.159	0.208	
MD09-01	229.00	334.67	105.67	0.207	0.258	
MD09-01	242.00	334.67	92.67	0.217	0.277	
MD09-01	242.00	322.10	80.10	0.232	0.276	
MD09-01	242.00	288.00	46.00	0.254	0.311	
MD09-01	264.00	284.00	20.00	0.267	0.323	
MD09-02	12.19	301.00	288.81	0.118	0.140	
MD09-02	12.19	140.00	127.81	0.160	0.139	
MD09-02	34.00	44.00	10.00	0.237	0.162	
MD09-02	100.00	140.00	40.00	0.198	0.171	
MD09-02	100.00	118.00	18.00	0.221	0.200	
MD09-03	7.32	343.82	336.50	0.051	0.125	
MD09-03	18.00	115.00	97.00	0.065	0.191	
MD09-03	26.10	53.00	26.90	0.099	0.322	
MD09-03	42.00	53.00	11.00	0.169	0.557	
MD09-03	45.00	52.00	7.00	0.215	0.716	
MD09-03	150.00	229.15	79.15	0.074	0.188	
MD09-03	180.00	205.00	25.00	0.086	0.303	
MD09-03	192.00	203.00	11.00	0.135	0.381	
MD09-03	219.00	229.15	10.15	0.054	0.128	0.020
MD09-03	299.00	307.00	8.00	0.144	0.211	
MD09-04	19.52	94.00	74.48	0.102	0.110	
MD09-04	68.00	94.00	26.00	0.109	0.159	
MD09-04	68.00	82.00	14.00	0.138	0.196	
MD09-05	9.15	301.40	292.25	0.053	0.201	
MD09-05	9.15	54.00	44.85	0.099	0.161	
MD09-05	133.00	151.00	18.00	0.078	0.293	
MD09-05	217.00	301.40	84.40	0.024	0.331	
MD09-05	217.00	229.00	12.00	0.052	0.596	
MD09-05	247.00	301.40	54.40	0.017	0.357	
MD09-05	247.00	272.00	25.00	0.022	0.442	
MD09-05	261.00	272.00	11.00	0.016	0.616	

9. Conclusions and Recommendations

Drilling at Mt. Dunn in 2009 intersected broad zones of low-grade copper and gold over a strike length of about 1200 metres. Better grade mineralization was intersected in the southernmost drill hole below 920 metres elevation. A program of detailed geological

mapping and sampling is recommended, with a focus on the 1.6 km long zone between MD09-01 and Fewright Creek, in order to assess the possibility that better grade mineralization occurs at surface below 920 metres elevation. With positive results, further drilling of that target area can be contemplated.

References

- Adamson, R.S. (1987): Assessment Report on a Reconnaissance Geochemical Survey of the Consoat and King Claims. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 16316.
- Awmack, H. (2003): 2002 Geological and Geochemical Report on the Adam Property. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 27130.
- Britton, J.M., Webster, I.C.L., and Alldrick, D.J. (1989): Unuk Map Area. B.C. Ministry of Energy, Mines and Petroleum Resources, Geological Fieldwork 1988, pp. 241-249.
- Chapman, J. and Dewonck, B. (1989): Assessment Report on the King 1-4, Consoat and Nat Mineral Claims for CorpTech Industries Inc. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 19262.
- Gareau, M.B. (1983): Geochemical Assessment Report on the Cole Claim. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 11673.
- Korenic, J.A. (1982): Assessment Report of Geological, Geochemical and Geophysical Work Performed on the Cole Claim. B.C. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 10,474.
- Mallo, D.W. and Dvorak, Z. (1989): Assessment Report on the King-Consoat Property Airborne Geophysics Program King 1-4, and Nat Claims. B.C. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 18987.
- Marsden, H. (2007): Rock Geochemistry on the Mt. Dunn Property. B.C. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 29359.
- Mawer, M., Bojczyszyn, T., McInnis, M.D., and Marratt, G.L. (1977): Year End Report, Mt. Dunn Property, B.C. B.C. Department of Mines and Petroleum Resources Assessment Report 6234.
- Wescott, M.G. (1988): Assessment Report on Geological and Geochemical Work on the King (1-4) and Consoat Mineral Claims, B.C. B.C. Ministry of Energy, Mines and Petroleum Resources Assessment Report 18614.
- Winter, C.Q. and McInnis, M.D. (1975): Geological and Geochemical Report on the VV 1-6 Claims, Mt. Dunn Area, B.C. B.C. Department of Mines and Petroleum Resources Assessment Report 5616.

Appendix A Drill Logs and Assays

Project	Mt Dunn
Drill Hole	MD09-01
Zone	Evan
Start date	20-Aug-09
Finish date	23-Aug-09
Drilled by	Ridgeline Diamond Drilling
Logged by	M. W. A. Hocking
UTM E	399250
UTM N	6258368
Azimuth	280
Dip	-60
Elevation	1122
Length	334.67m
Surveys	EZ-Shot

From m	To m	Width m	Description		ALT CODE	Alteration							Mineralization							
			Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
0	3.04	3.04	CAS	No Recovery																
3.04	8.4	5.36		Oxidized rubble																
8.4	9.4	1	ALTINT	Intrusive. Patchy QSP, Bx txt, bleached yellow-pale grey colour. < 5% disseminated pyrite, rare white quartz veins at 60 degrees to CA. Irregular networks of dark grey silica veinlets. << 1% cpy	QSP_wm	w					m			tr	m					
9.4	13.3	3.9	ALTINT	Oxidized intrusive, rubble, orange feox	QSP_wm	w					m				m					
13.3	14.63	1.33	ALTINT	grey QSP altered intrusive, patchy yellowish alteration spots, 5% pyrite, disseminated and along fracture networks	QSP_wm	w					m			tr		5				
14.63	16.03	1.4	ALTINT	Pale grey-orange broken fracture zone. Rare feldspar texture. Malachite on fractures.	QSP_wm	w					w									3
16.03	19.59	3.56	ALTINT	Paler grey colour than previous. Visible feldspar porphyry texture. QSP alteration, moderately hard, non-magnetic, disseminated pyrite + quartz pyrite fractures, rare cpy, w-m malachite stain. Still in broken oxidized zone.	QSP_wm	m					m			tr		5				3
19.59	20.6	1.4	ALTINT	Broken rock, rubble, oxidized zone.																
20.6	21.7	1.1	ALTINT	Broken rubble with coherent blocks up to 20cm in length. Grey, moderately hard, oxidized, no visible intrusive texture, no obvious sericite, disseminated pyrite, rare disseminated chalcopyrite + malachite on fractures. Rare white quartz veins	Sil_py	w_m								tr		2			w	
21.7	22.3	0.6	AltINT BX	Grey silica altered intrusive with dark grey cm-scale fragments. hornblende is weakly altered to chlorite	Sil_ch	m			w					tr		2			w	
22.3	24.7	2.4	ALTINT	Silicified intrusive rock. Green chlorite altered hornblende, moderately hard, 2-3% disseminated pyrite, trace chalcopyrite, weak malachite. 5cm wide white quartz vein at 23.47m	Sil_ch_py	m			w					tr		2			w	
24.77	27.72	2.95	ALTINT	As above, rubble with cm-scale pieces of rock. W-M malachite stain	Sil_ch_py															
27.72	30.67	2.95	ALTINT	Green, patchy chlorite alteration, moderate-strong silicification, green feldspars, moderate stockwork of white-translucent quartz veinlets at 0-30 degrees to CA + steep veinlets at 90 degrees. Disseminated pyrite < 3% >> cpy.	Sil_ch_py	m-w			m					tr		3				
30.67	33.92	3.25	ALTINT	As above with fewer veinlets. Patchy zones of pervasive silica-chlorite-sericite creating dull grey to green-yellow appearance. Broken core. 31.27 - 31.37 moderate stockwork of white quartz veinlets,	QSP_ch	m			m		w			tr		2				
33.92	42.06	8.14	AltINT BX	Grey-green to black hornblende _ feldspar porphyry altered intrusive. Cm scale subangular dark-green to grey intrusive fragments, locally very pyritic, weak silica, ultra trace chalcopyrite. Interval comprised of 40% intervals, locally higher. Pyrite is disseminated to fracture controlled. Rare quartz veins.	QZCLP	w-m			w-m					u.tr		1				

From	To	Width	Description		ALT CODE	Alteration							Mineralization							
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
m	m	m	Rock Code																	
42.06	43.2	1.14	ALTINT	Feldspar (euhedral to subhedral)-hornblende (black to green) intrusive porphyry. Rare quartz veinlets 0 degrees to CA. ~ 6 quartz veinlets/m at 60 degrees to Ca.	QZCLP	w			w					tr		2				
43.2	44.6	1.4	ALTINT	as above but pale grey-yellow green QSP alteration with 8 pyrite fractures pyrite fractures at 60 degrees to Ca. Pyrite early, later silica	QSP_wm	w-m			w		w-m			tr		3				
44.6	47	2.4	ALTINT	Feldspar (euhedral to subhedral)-hornblende (black to green) intrusive porphyry. Rare quartz veinlets 0 degrees to CA. ~ 6 quartz veinlets/m at 60 degrees to Ca.	QZCLP	w			w					tr		2				
47	50.9	3.9	ALTINT	crowded hornblende-feldspar porphyry, pale yellow-grey, w-m quartz (dark silica veinlet stockwork at 0-35 degrees to CA. 15-20 veinlets over interval, hornblende slightly green colour. 10cm white quartz vein with dark grey silica-pyrite margins between 48.6 and 48.69m	QSP_wm	w			w		m			1		5				
50.9	52.66	1.76	ALTINT - QZSTK	As above porphy, patchy zones (totalling 0.7m) of dark grey silica-pyrite veinlet stockwork 30-50 degrees to Ca. Pale colour colour.	QZCLP	w-m								1		5				
52.66	53.21	0.55	QZPYVN	0.4m wide massive pyrite with white quartz vein on upper margin and lens of quartz (<10%) within zone	QZPYZN											70				
53.21	60.35	7.14	ALTINT	Crowded HF (hornblende-feldspar) porphyry texture. Black hornblende, m-s silica, hard. 5% diss pyrite and pyrite +/- silica fracture	QZCLP	m-s								tr		5 to 10				
60.35	64.37	4.02	ALTINT	Dark grey HFP, <5% diss pyrite + fracture controlled pyrite	QZCLP	m								tr		5				
64.37	71.8	7.43	ALTINT	HF crowded porphyry as above, lighter grey colour, stronger silica, very hard, diss pyrite. Up to 20/m pyrite to pyrite -silica veinlets generally 30 degrees to CA, also 0 to CA trace to ultra trace chalcopyrite. Good porphyry texture, black hornblende	SilPy	s								tr		<5				
71.8	95.2	23.4	ALTINT	Patchy yellow sericite QSP over 70% of interval. porphyry txt still visible. 6-10 white quartz veinlets/m often with pyritic margins. M-s pyrite (+-quartz) fracture network, 8-10/m. Slight chalcopyrite increase.	QSP WM	m					m			1		3				
95.2	96.6	1.4	ALTINT	Darker grey HFP, hornblende black to green in colour. < 5 white quartz veins/m at 20-40 degrees to CA, few steeper. < 2% disseminated and fracture controlled pyrite.	QZCLP	w-m			w					tr		2				
96.6	97.46	0.86	ALTINT	30-40% of interbal has patchy fine-grained breccia texture. Grey to slightly pink alteration silica (+/- k-spar)	QZCLP	w-m			w					tr		2				
97.46	99.5	2.04	ALTINT	As 95.2-96.6m, HFP, hornblende black to green in colour. < 5 white quartz veins/m at 20-40 degrees to CA, few steeper. < 2% disseminated and fracture controlled pyrite.	QZCLP	w-m			w-m					tr		2				
99.5	100.1	0.6	ALTINT	as above with increase silica alteration	QZCLP	m			w					tr		2				
100.1	105.5	5.4	ALTINT	as above slight silica decrease	QZCLP	w-m			w					tr		2				

From m	To m	Width m	Description		ALT CODE	Alteration							Mineralization							
			Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
105.5	125.6	20.1	ALTINT - INT BX	Increase in visible QSP, patchy pale grey-yellow sericite over 50% of interval. Weak porphyry texture. 5% disseminated pyrite, w-m pyrite fracture network. < 4 translucent quartz veins/m (yellow-white soft sulfate (?) margins). < 3cm wide at 0 - 70 degrees to CA. Breccia texture at 107.18-107.48m, 115.5-115.65m, 116.75-116.90m. Texture formed by dark-grey, subangular, intrusive textured to fine-grained fragments in paler intrusive matrix	QSP_wm	m					m			tr		4				
125.6	128.55	2.95	ALTINT- INT BX	Grey to yellow breccia interval, 1.6m of interval contains breccia textures. Dark-grey, fine-grained clasts (rarely porphyritic). Moderate pyrite fracture network + disseminated pyrite and rare chalcopyrite	QSP_wm	m			w	w-m				tr		5				
128.55	129.5	0.95	ALTINT	Porphyry texture. Disseminated pyrite, pyrite fractures, rare chalcopyrite.	QSP_wm	w-m				w-m				tr		5				
129.5	129.9	0.4	ALTINT	green colour, strong chlorite-pyrite, few carbonate fractures	CHPY	w_m			m					tr		5				
129.9	131.1	1.2	ALTINT	as 128.55-129.5m, stronger QSP.	QSP_wm	w_m			m					tr		5				
131.1	136	4.9	ALTINT - VN Bx	Crowded porphyry texture. Pale-grey to yellow colour. 1.7m of interval brecciated by white quartz veining. Pyrite is disseminated and fracture controlled and cut by white quartz. 0.5m of interval is darker grey silica pyrite with a network of pyrite fracture to silica-pyrite stockwork/breccia, blebs of chalcopyrite	QSP_wm	m					m			1		5				
136	145.5	9.5	ALTINT	Pale grey to yellow crowded HFP with 1% disseminated chalcopyrite. Pyrite-silica +/- chalcopyrite fractures/veinlets ~ 12/m. Intermittent visible yellow colouration over 50% of interval. Porphyry texture clear to slightly obscured. Quartz veins with yellow margins at 70 -90 degrees to CA ~ 15 veins/m with local stockwork. Green-black hornblende, chloritie on fractures.	QSP-wm	m		w		m				1		5				
145.5	150	4.5	ALTINT	As above with increase in dark grey-black, soft, pyrite-chlorite (+/- silica) fracture network	QSP_wm	m		m		m				1		5				
150	161.56	11.56	ALTINT	As 136-145.5. White quartz vein at 45 degrees to Ca between 138.7 to 138.75	QSP-wm	m		w		m				1		5				
161.56	164.8	3.24	ALTINT	Less yellow colouration. Pale grey with HFP texture, disseminated pyrite + pyrite fracture network. Possible chlorite on fractures	QZCLP	m-s		w						tr		5				
164.8	168.1	3.3	ALTINT - INT BX	Darker green moderately hard, finer grained Intrusive texture. BX texture cm-scale green-grey subangular fragments over 30% of interval. One intrusive intruding a 2nd? Green colour primary colour of intrusive darker than pale intrusive seen earlier? 2cm chlorite seem at 166.5m	QZCLP	w_m		m						tr		3				
168.1	179.69	11.59	ALTINT - INT BX	Porphyry texture visible. Green-grey. 1.95m of interval contains breccia/fragmental texture with fine-grained green intrusive textured fragments. 5-10/m white-yellow quartz veins at ~ 90 to CA. Silica - chlorite alteration. Fine-grained pyrite >> chalcopyrite.	QZCLP	m		m						tr		3				

From m	To m	Width m	Description		ALT CODE	Alteration							Mineralization							
			Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
179.69	195.2	15.51	ALTINT - INTBX	Less breccia texture visible. Grey-green intrusive with porphyry texture. Obscure circular patches of darker grey silica-pyrite creates mottled texture. Translucent < 2cm quartz veins (~3/m) with pyritic margins at 40-60 degrees to CA. At 189-190.5 irregular, translucent silica + pyrite breccia texture (vein).	QZCLP	m-s			w					<1		5				
195.2	203.61	8.41	ALTINT	Stronger silicification + pyrite. Texturally destructive alteration porphyry texture is difficult to observe. Increase chalcopyrite in fracture networks and disseminated. Few white quartz veinlets +/- pyrite at 40-60 degrees to CA. Intrusive breccia texture at 197.85-198.	SILPy	M-S								2		5				
203.61	204.2	0.59	ALTINT- INT BX	Intrusive breccia. Dark-grey, subangular, fine-grained intrusive textured fragments in lighter grey silica-altered matrix. Pyrite disseminated and	QZCLP	m								tr		4				
204.2	206.17	1.97	ALTINT	Dark grey m-s silica alteraton, hard but still scratches. Porphyry texture obscured. Increase in disseminated chalcopyrite. Very-weak brittle fracture network with white quartz veinlets. Pyrite is disseminated and fracture controlled	QZCLP	m-s								1		4				
206.17	206.73	0.56	ALTINT	Yellow-grey QSP, weak porphyry texture, m-s pyrite fracture network. Fractures expanded by white quartz locally.	QSP_ms	m-s					m-s			tr		5				
206.73	232.4	25.67	ALTINT	Moderately hard, grey, visible porphyry texture (partially obscured). Between 210.3 to 210.52: white brittle fracture network healed by white-quartz + pyrite and clots of chalcopyrite. Dark grey pyrite-silica +/- chlorite creates mottled texture locally. Brittle quartz veinlets at variable angles, 5-10/m. 227.30-230.42m: strong pyrite fracture network at 0-40 degrees to CA, up to 10% pyrite.	QZCLP	m								1		5				
232.4	234.5	2.1	ALTINT	Yellow-grey QSP obscures porphyry texture, moderate pyrite-chlorite fractures	QSP	m			w		m			tr		5				
234.5	244.35	9.85	ALTINT	Medium to dark grey, moderately hard, obscured porphyry texture, pyrite disseminated and in seams - up to 5% locally. Rare clots + disseminated chalcopyrite. Few white quartz veins/m, rare brittle stockwork zones healed by white quartz	QZCLP	m			w					1		5				
244.35	240.7	-3.65	ALTINT	As above, increase in quartz veinlets to weak stockwork	QZCLP	m			w					1		5				
240.7	250	9.3	ALTINT - INT BX	As above with intrusive breccia texture. Darker-grey intrusive fragments in lighter grey intrusive matrix. Disseminated pyrite + seams of pyrite-chlorite, brittle fractures.	QZCLP	m			w					1		5				
250	252	2	ALTINT	As 244.35-240.7	QZCLP	m			w					1		5				
252	259	7	ALTINT	As above with less late white quartz veinlets. Obscure porphyry texture, disseminated + fracture controlled pyrite. Local clots of chalcopyrite (at 257.5m)	QZCLP	m-s			w					1		5				
259	250.44	-8.56	ALTINT	Grey to slightly pink silicification cut by narrow pyrite -chlorite +/- chalcopyrite fractures. Rare white quartz veins cut pervasive alteration	QZPY	S			w					1		5				
250.44	261.52	11.08	ALTINT	As previous + sericite. Chlorite with pyrite on fractures, few white quartz veinlets	QSP_MS	m-s			w-m		m-s			<1		4				

From m	To m	Width m	Description		ALT CODE	Alteration								Mineralization							
			Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
261.52	280	18.48	ALTINT	Moderate to strong pervassive silica. Grey colour, locally pinkish (k?). Pyrite-chlorite fractures, few late white quartz veinlets. Disseminated pyrite, increased chalcopyrite. Porphyry texture is locally visible and never totally destroyed	QZPY K	ms	?		w-m		m-w			2		5					
280	282	2	ALTINT	As abovebut strong pink (K-spar) alteration?	QZPY K	ms	?		w-m		m-w			2		5					
282	296.31	14.31	AltINT	Moderate to strong pervassive silica. Grey colour, locally pinkish (k?). Pyrite-chlorite fractures, few late white quartz veinlets. Disseminated pyrite, increased chalcopyrite. Porphyry texture is locally visible and never totally destroyed. 280.55-289m white quartz veins 0-30 degrees to CA, local pyrite fracture network. 280.9 -281.15m : 30-40 degree to CA white quartz vein with 2-3cm band of pyrite with chalcopyrite	QZPY K	ms	?		w-m		m-w			2		5					
296.31	307.56	11.25	ALTINT	Box 53 and 54 mixed when core shack destroyed by storm. Top and bottom two rows of each box samples (2 samples/box). Intrusive texture visible. Pale grey to green QZCLPY to strong green chlorite (texturally destructive) with fine green green - to slight mauve colouration. Few white quartz-calcite veinlets, chlorite-pyrite fractures.	QZCLP - CHP	w-m			m-s		w		tr			5					
307.56	311	3.44	ALTINT	Grey to green texturally destructive, weak to moderatley hard quartz-pyrite +/-clay. hornblende visible, feldspar obscured. Disseminated + fracture controlled chlorite-pyrite	QZCLPY	m			m-s					tr-1			5				
311	318.8	7.8	ALTINT	Gradational contact over 10-15cm to green fg rock with irregular mottled grey (30%) silica (hard >5) with irregular black seams of magnetite locally with quartz margins. Green rock is soft-moderatley hard with less disseminated pyrite than previous, chalcopyrite + pyrite along fractures. Few late quartz-calcite veinlets with rare chalcopyrite. 313.33 315: Green fg-mg (visible relic hornblende) , intermediate to coarse grained volcanic, dark grey - green sub angular fragments, pyritic.	QZ-CHMT	m-s			s					3		5	7				
318.8	319.5	0.7	ALTINT	Green chlorite altered. More visible porphyry texture. Strong magnetite seams, disseminated - clots of pyrite + chalcopyrite	QZ CHMT	w-s			s					3		5	7				
319.5	324.62	5.12	ALTINT - mix	Boxes mixed when core shack destroyed by storm. As 311-318.8 interval. Sequence locally contain up to 10% magnetite seams and clots of pyrite + chalcopyrite in fractures	QZ CHMT	w-s			s					3		5	7				
324.62	327.7	3.08	ALTINT	Green-grey colour with 50% of interval very hard patchy grey silica. Disseminated pyrite and chalcopyrite, also in clots and seams of pyrite. Magnetite not observed	QZ CH	s			s					2		5 to 10					
327.7	328.4	0.7	ALTINT	Feldspar-hornblende porphyry texture. Medium grained, green-grey, green hornblende, disseminated pyrite +/- chalcopyrite, pyrite-chlorite fractures. 328.4-330: Patchy strong-verystrong, very hard texturally destructive quartz alteration.	QZ CH	m-s			w-m					<1		5					
328.4	330	1.6	ALTINT	As above with patchy strong chlorite and very hard, texturally destructive silica.	QZ CH	m-s			m-s					<1		5					

From	To	Width	Description		ALT CODE	Alteration							Mineralization							
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
m	m	m	Rock Code																	
330	332	2	ALTINT	As 327.7-328.4	QZ CH	m-s			w-m					<1		5				
332	334.67	2.67	ALTINT	As Above with strong array of sheeted - to stockwork- quartz-calcite veinlets. 10-30 veins/m at 45 to 90 degrees to CA with clots of pyrite	QZ CH	m-s			w-m					<1		5				
334.67		EOH																		

Project	Mt Dunn
Drill Hole	MD09-02
Zone	
Start date	24-Aug-09
Finish date	26-Aug-09
Drilled by	Ridgeline Diamond Drilling
Logged by	M.W.A Hocking
UTM E	399188.5327
UTM N	6258680.88
Azimuth	105
Dip	-60
Elevation	1195
Length	336.5m
Surveys	EZ-Shot

From	To	Width	Description				ALT CODE	Alteration						Mineralization									
			m	m	m	Rock Code		SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
0	12.19	12.19	collar	no recovery				N/A															
12.19	16.36	4.17	ALTINT	Fg-Mg feldspar-hornblende porphyry. Grey, silicified, porphyry texture still visible. Pyrite and chalcopyrite disseminated with increase total sulfide relative to MD09-01. Fe narrow quartz veinlets. Narrow black (locally green), soft, chlorite-pyrite fractures, locally cored by silica.				SILPY	w-m								2	5					
16.36	19.95	3.59	ALTINT	As above, porphyry texture obscured by stronger dark grey silica.				SILPY	m-s								2	5					
19.95	23	3.05	ALTINT	As 12.19 to 16.36m				SILPY	w-m								2	5					
23	25	2	ALTINT	As above. Fractured core with black Cu oxide (Cu pitch) on fractures locally (<10%) of interval. 23.6 - 24m: clots of chalcopyrite in thin veinlets				SILPY	w-m								2	5					
25	25.6	0.6	ALTINT	As 12.19 to 16.36m				SILPY	w-m								2	5					
25.6	30.4	4.8	ALTINT	moderate -strong silica, weak-moderate porphyry texture, black fracture network				SILPY	m-s								2	5					
30.4	34	3.6	ALTINT	As 12.19 to 16.36m				SILPY	w-m								2	5					
34	36.58	2.58	ALTINT	Grey, strongly altered, moderately hard porphyry with very strong black chlorite (soft waxy, white streak) fracture network/stockwork. Strong chalcopyrite on fractures. Disseminated pyrite				SILPY	m-s								3	5					
36.58	44.2	7.62	ALTINT	Visible porphyry texture. Very fine-grained chalcopyrite disseminated and fracture controlled + disseminated pyrite. Chalcopyrite upto 5% locally. 40-43.2: oxidized and fractured with malachite and Cu pitch on fractures. Weak chlorite fracture network to very localized stockwork textures.				SILPY	w-m								<5	5					
44.2	52.5	8.3	ALTINT	Lighter grey to yellow QSP. Very thin fractures with pyrite + disseminated pyrite, lexx chalcopyrite than revious. Strong black chlorite fracture network. 44.52-46.60 : strongly oxidized and broken core. 45-51m : intense black fracture network/stockwork.				QSP_wm	m-s		w_m	w-m					2	5					
52.5	54.1	1.6	ALTINT	Grey, m-s silica-pyrite. Fractures with oxidation				SILPY	m-s								1	5					
54.1	55.5	1.4	ALTINT	Green, Silica-pyrite + chlorite, oxidized core.				SILPY CH	m-s		m							5					
55.5	56	0.5	ALTINT -INTBX	Strong black fracture stockwork + pyrite. Intrusive BX texture, grey silica-pyrite alteration				SILPY	m-s									5					
56	97.5	41.5	ALTINT	Grey, moderately har, fg-mg, crowded FHP texture. Few quartz-calcite veinlets at 65 degrees to CA. Fracture + disseminated pyrite + chalcopyrite (fg). Locally coarse-grained porphyry texture at 56.8-57.6m, 70.70-71.60m, 77.3 77.95m. Calcite vein at 70-90 degrees to CA at 67.36 to 67.51m. Black fractures at 56-61m. 78.1-78.74m: very strong silicification cut by quartz-calcite veins and black fractures. 87.3-87.35m fractures with quartz vein core and quartz-pyrite margins. Margins cause silica alteration of porphyry and textural destruction 97.5-99.75m: Local BX texture dark-grey silica pyrite -with lighter grey silica-pyrite altered porphyry texture.97.8 -99.75m				SILPY	m-s								1	5					
97.5	99.75	2.25	ALTINT INTBX	as above with darkgrey silica-pyrite flooding of lighter grey silica-pyrite altered HFP creating breccia texture. More likely two intrusive units creating breccia texture. 97.8-99.75 calcite veing leached to created pitted texture.				SILPY	SIL								1	5					
99.75	115.9	16.15	ALTINT	as 97.5 - 99.75m. Strong black chlorite fracture network at 110.85 to 112m.				SILPY	m-s								1	5					
115.9	131.09	15.19	ALTINT	Green coarse-grained to megacrystic feldspar porphyry texture, feldspar up to 2cm in size, gradational contact with above fg-mg unit. Pyrite +/- chalcopyrite (locally strong) is disseminated and fracture controlled. White-pink quartz-calcite veining is weak-moderate, moderate chlorite fractures				SILPY	m-s		m-s						1	5					
131.09	133.9	2.81	ALTINT	Gradational contact with above unit over 0.5m. Unit is grey with less chlorite and greater silica than previous, fewer visible cg feldspars. Disseminated and fracture controlled pyrite + chalcopyrite. Moderate black fracture network.				SILPY	m-s								1	5					
133.9	147.44	13.54	ALTINT - BX	Fg-Mg porphyry matrix with few very coarse grained feldspars. Fragments of dark-grey, fg to mg, angular, cm-scaled, pyritic porphyry clasts. Few large, very hard grey-pink fg silicified fragments with stronger chalcopyrite. Possible hydrothermal breccia? Black chlorite fracture network over 1.5m of the interval.				SILPY	s								2	5					
147.44	152.9	5.46	ALTINT- INTBX	Pale grey-green porphyry matrix with dark green silica-pyrite +/- chlorite altered porphyry fragments. 50% of interval contains green (primary/chlorite) pyritic porphyry unit with sharp contact with paler porphyry on upper contact. Gradational lower contact. W-m calcite veining.				SILPY CH	w_m		m-s						<1	5					
152.9	158.75	5.85	ALTINT	Pale green mg-cg HFP, few chlorite-calcite seams and rare fragmental texture at 158.75.				SILPY CH	m		m						<1	3					
158.75	168.68	9.93	ALTINT - INT BX	Breccia textures. Cm-scale surrounded-subangular fragments in fg grey matrix, dark grey fragments are very hard with disseminated pyrite and chalcopyrite. Fine-grained sulfide, content likely underestimated.				SILPY	S								tr	2					
168.68	176.45	7.77	ALTINT - INT Bx	Breccia as above but matrix is paler grey in colour with visible porphyry textures locally. Silica pyrite alteration is stronger. Few late quartz-calcite veins				SILPY	m-s								2	3					
176.45	187.3	10.85	ALTINT - INT BX	Dark to light grey, patchy alteration, porphyry texture visible locally, 20-30% breccia texture as above				SILPY	m-s								tr	5					

From	To	Width	Description					ALT CODE	Alteration						Mineralization										
			m	m	m	Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH	
187.3	199.5	12.2	ALTINT - INTBX	(IntBX)	HFP w-m silica-pyrite, good porphyry texture. W-m chlorite fracture network. Rare grey silicified fragement		SILPY	w-m			w-m								2						
199.5	205.5	6	ALTINT		Dark grey, strong-moderate silica-pyrite, porphyry texture is obscured but visible, disseminated + fracture controlled pyrite.		SILPY	m-s									tr		6						
205.5	208.04	2.54	ALTINT - Vein		As above with 70% of interval as semi-massive pyrite + calcite veining		SILPY	m-s						s					20						
208.04	210.5	2.46	ALTINT		Dark grey-green colour, fg, crowded FHP. Fg disseminated chalcopyrite, likely underestimated.		SILPY	m-s						w			0.5		5						
210.5	215.9	5.4	ALTINT		Light grey, coarse-grained texture, porphyry texture moderately destroyed, gradtional alteration contact with above unit. Pyrite fracture network-stockwork over 70% of interval.		SILPY	m-s									tr		5 to 10						
215.9	248.9	33	ALTINT		Medium grey-green. Coarse-grained feldspar and hornblende porphyry texture. White euhedral feldspar up to 2cm long. Pyrite is disseminated and often rims/replaces mafics. Trace epidote around primary mafics. Weak chlorite fractures, rare calcite veinlets		SILPY CHEP	m		w	tr						tr		5						
248.9	249.5	0.6	ALTINT		Texturally destructive dark green-grey colour. Disseminated to clots of pyrite. Contacts gradational over 5cm, weak calcite fractures.		CHLPY	w		s			w				tr		5 to 10						
249.5	252	2.5	ALTINT		Silica-pyrite variabl, fg, texturally destructive over 0.9m to good porphyry texture with subhedral feldspars.		SILPY	m									tr		5						
252	254.2	2.2	ALTINT		as above, texturally destructive strong silica-pyrite		SILPY	S									tr		5						
254.2	258.99	4.79	ALTINT		As 249.5-252m		SILPY	m									tr		5						
258.99	283.25	24.26	ALTINT - INTBX		Medium to dark grey to locally pink colouration. Visible porphyry texture, sub-anhedral feldspars, visible hornblende. Epidote spots, few calcite veinlets. Rare quartz veins with pyritic margins at 260.75m. Fine-grained disseminated pyrite +/- chalcopyrite (likely underestimated). Rare fragmental textures: fragments are softer, darker grey, alteration or intrusive BX? Fracture controlled pyrite forms bacs with quartz at 267.2-267.3m		SILPY	m-s		w							tr		5						
283.25	301.75	18.5	ALTINT		Upper contact gradational over 0.1m. Very strong silicification, very hard. Grey to pink (kspar? Too hard). Mottled to banded texture. Fine-grained, grey silica margins on some fractures, few quartz-calcite veinlets. Irregular patches of dark-green chlorite-pyrite (1.2m of interval). Local breccia texture with silicified clasts in softer, grey, pyrite-silica-calcite matrix. Hydrothermal? Disseminated to fracture controlled pyrite, locally lots of chalcopyrite on fractures. Banded pink-grey silica -pyrite vein at 297.5-297.9, weak epidote spots in vein.		SILPY - CHPY	S-VS	?	m-s		w		<1				5							
301.75	304.5	2.75	ALTINT		Sharp upper contact. Hard, pale green, fg, disseminated pyrite. Few fg 30-60 degree to CA mod-hard veinlets with brown margins and pyrite		SILPY CH	m-s		m-s		w		tr				4							
304.5	307	2.5	ALTINT		Mixed pink-green unit. As unit 283.25-301.75m mixed with unit 301.75-304.5m. 306.5-307m; 8 fg quartz veinlets with pyrite.		SILPy - CHPY	m-s		m-s		w		tr				4							
307	311	4	ALTINT		Grey silica-pyrite altered porphyry. 307-307.1 gradual contact, less pink more grey. Feldspars (cg) become more visible. Very strong pyrite (8-10%) at 307.1 to 307.6m. Fg chalcopyrite.		SILPY	m-s									tr		7						
311	325.7	14.7	ALTINT		310.85-311 gradula loss of feldspar texture to fine grained pink-grey silica-pyrite altered unit as 283.25-301.75m. Sharp lower contact with pyritic, mg, HFP		SILPY	s	?								tr		5						
325.7	326.81	1.11	ALTINT - INTBx		Grey silica-pyrite matrix with intrusive breccia texture		SILPY	m									tr		5						
					Fg pink-grey altered unit as 311-325.7m. Moderately hard, banded texture (k-spar?). Bands of semi-massive pyrite-quartz-calcite at 330.25-330.45m		SILPY	s	?								tr		5 to 10						
326.81	331.65	4.84	ALTINT		Grey-pink silica-pyrite altered FHP, mg, partially destructive alteration, moderately hard.		SILPY	m									tr		3						
331.65	332.52	0.87	ALTINT		Sharp upper contact at 45 degrees to CA. Green fg-mg, non-magnetic dyke (?), black sub- to anhedral mafic minerals (hornblende) and feldspar.		N/A																		
332.52	336.5	3.98	MF-INT Dyke																						
336.5			EOH																						

Project	Mt Dunn
Drill Hole	MD09-03
Zone	
Start date	26-Aug-09
Finish date	30-Aug-09
Drilled by	Ridgeline Diamond Drilling
Logged by	M.W.A Hocking
UTM E	399246.1965
UTM N	6259218.113
Azimuth	100
Dip	-65
Elevation	1253
Length	343.82m
Surveys	EZ-Shot

From	To	Width	Rock Code	Description	ALT CODE	Alteration								Mineralization						
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
0	7.32	7.32	collar	Collar, no recovery	N/A															
7.32	15.75	8.43	ALTINT	Broken cire, poor recovery/RQD. Strong red oxidation, moderatley hard (scratches) HFP, weakly texturally destructive silica-pyrite	SILPY	m											3			
15.75	20.8	5.05	ALTINT - INTBX	Moderatley hard, texturally destructive dark grey silica-pyrite. Breccia texture with fg, grey, silica (grey to red) fragmetns in silica-pyrite dark grey moderatley hard matrix.	SILPY	m-s											3			
20.8	22.8	2	ALTINT	Strong pale grey, texturally destructive, silicification, pyrite fracture network forms clots.	SILPY	s											5			
22.8	24.35	1.55	ALTINT - INTBX	FG, disseminated pyrite, grey, very fg bx texture	SILPY	m-s											5			
24.35	26.1	1.75	Fault Zone	Wavy cleavage. Fg, grey, mod-hard fragments warpped in wavy cleavage wth bands of pyrite, few quartz veins.	SILPY	m-s											5			
26.1	54.26	28.16	ALTINT	pink-grey, silica-pyrite, mod text destructive. Disseminated pyrite (rims-replaces mafics). moderate to very hard. Pyrite fractures. Massive pyrite-calcite vein at 45.2 - 45.25m. Massive pyrite-silica breccia texture with grey silica fragments at 50.94-51.2m.	SILPY	m-w									tr		5			
54.26	59	4.74	ALTINT	As above, disseminated pyrite (replacing mafics), hard, grey, weak porphyry texture. Sulfide primarily disseminated with weak fracture controlled sulfide, trace chalcopyrite (underestimated?). 54.5-54.58m: 8cm pyrite-quartz-calcite vein at 50 degrees to CA.	SILPY	m-s														
59	60	1	ALTINT	Irregular massive black-green chlorite with semi massive pyrite bands and quartz-calcite veining.	CHPY	w-m		s				m-s		tr			10			
60	69.5	9.5	ALTINT	as 54.26-59m	SILPY	m-s											tr		5	
69.5	69.65	0.15	Fault	Fault. 60 degree to CA mm-cm scale dark to pale green, soft, fault-shear. Sharp contacts, very pyritic (fg) with silicic fragments	SILPY - CHPY	m-s		m-s										10		
69.65	75.11	5.46	ALTINT	As 60-69.5m unit but slightly darker grey + pink colouration, hard 5% + disseminated pyrite. Few soft, black pyrite-chlorite fractures.	SILPY	m-s		w										5		
75.11	77.92	2.81	Dyke	Green, fine-grained feldspar-hornblende porphyry dyke, non-magnetic, few calcite veins, rare pyritic fractures.	N/A															
77.92	83.5	5.58	ALTINT	As 69.65-75.11m interval. Alteration is weakly to moderatley texturally destructive. Breccia textures (alteration?) between 82 and 83.5m. Few late calcite veins.	SILPY	m-s									tr		5 to 10			
83.5	86	2.5	ALTINT	As above with patchy QSP over 50% of interval.	QSP	m-s					m				tr		5 to 10			
86	93.45	7.45	ALTINT	As 77.92 -83.5m	SILPY	m-s										tr		5 to 10		
93.45	94.5	1.05	Fault	Shear zones. Strong cleavage at 60-80 degree to CA. Grey with pyritic bands	SILPY	m-s												5		
94.5	99	4.5	ALTINT	As 77.92-83.5m, grey to pink, moderatley hard to hard	SILPY	m-s										tr		5		
99	106.17	7.17	Dyke	Dyke. Grey-brown, similar to previous dyke. Moderatley soft, feldspar-hornblende porphyritic cut by numerous calcite veinlets. Quartz-calcite vein at 101.2-101.6m	N/A															

From	To	Width	Rock Code	Description	ALT CODE	Alteration							Mineralization								
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
106.17	106.45	0.28	AltInt	Short interval between dykes, ALTINT as above	SILPY	m-s								tr		5					
106.45	110.26	3.81	Dyke	Dyke as above, upper contact obscured by vein, lower contact is sharp and irregular. < 5% quartz-calcite in brittle veins	N/A																
110.26	115.88	5.62	ALTINT	Dark grey, weak porphyry texture, fg disseminated sulfide, w-m thin quartz veinlets overprinted by quartz-calcite veinlets. Pyrite-calcite vein at 106.6 to 106.88m.	SILPY	m-s								tr		3					
115.88	116.02	0.14	Dyke	sharp contacts, as dykes above																	
116.02	117.91	1.89	Vein	Carbonate vein at 30 degrees to CA. Wallrock fragments and vein breccia textures.																	
117.91	121.56	3.65	ALTINT	As 110.26 - 115.88m, Cut by white quartz veins (5-10%) of interval, weak porphyry texture.	SILP	m-s								tr		3					
121.56	122.24	0.68	Dyke	Green, fg, soft unit with 10-15% white quartz veins. Dyke?																	
122.24	138.65	16.41	INT	Weakly altered feldspar-biotite =/- hornblende equigranular intrusive, green to grey colour, few irregular quartz veins and chlorite fractures.																	
138.65	140.75	2.1	Dyke	green dyke, fg-mg, lower contact at 40 degrees to CA with quartz-calcite margins.																	
140.75	150	9.25	INT	As intrusive above, fg-mg intrusive,																	
150	162.7	12.7	ALTINT	Fg, dark grey-pink, strongly silicified intrusive, quartz-calcite veins-weak stockwork. Rare chalcopyrite in veinlets. Pyrite content is variable 1-5% disseminated and fracture controlled	SILPY	s								tr		1 to 5					
162.7	168.3	5.6	ALTINT - VNBX	Pink (ksp? - too hard) to grey strongly silicified zone, porphyry texture not visible. Breccia textures: subangular fragments healed by pyrite-silica (?) matrix soft (from high pyrite content).	SILPY	s-vs								tr		10 to 20					
168.3	172	3.7	ALTINT	As above less breccia textures, pyrite + quartz-calcite fractures/veinlets. Green chlorite-pyrite fractures	SILPY	s		w-m			w		tr		5 to 10	tr					
172	174.15	2.15	ALTINT	Mottled to banded (40 degrees to CA) texture. Massive green-black chlorite + pyrite and calcite zones with relic grey silica. Few magnetite spots. Silicification appears to have occurred prior to chlorite-pyrite-calcite alteration	SILPY CCP	m-w		s		m						5 to 10	tr				
174.15	177.34	3.19	ALTINT	Pink-grey fine-grained, strongly silicified, very hard	SILPY	S															
177.34	178	0.66	ALTINT	Green black irregular chlorite-pyrite-calcite wth relic silicified interval	CCP	m-w		s		m						5 to 10	tr				
178	180.6	2.6	ALTINT	As 174.15-177.34m. Massive pyrite seam from 179.65-179.75m.	SILPY	S											5				
180.6	185.75	5.15	ALTINT	Porphyry. Moderately hard, grey cg, subhedral feldspar, moderate network of dark grey pyritic (=/- silica) stringers, disseminated pyrite, subangular mafics	SILPY	m-s								tr		5 to 10					
185.75	188.37	2.62	ALTINT - VNBX	Silica-sulfide breccia. Hard, strongly silicified interval, very weak porphyry texture at upper contact and in patchy zones of weaker alteration. Pyrite =/- silica fracture network to breccia texture. 186.9-187.3m: massive coarse-grained pyrite -calcite +/- silica vein	SILPY	s											5				

From	To	Width	Rock Code	Description	ALT CODE	Alteration								Mineralization							
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
188.37	191	2.63	ALTINT	Pink-grey strongly sstrong silica, fg, wavy textured alteration, very hard to moderately hard	SILPY	s-vs															
191	206	15	ALTINT	Gradational uppercontact. Zone varies fom pink-grey, very hard silica-pyrite to softer, green, chlorit with weak epidote spots.	SILPY CHEP	m-s			m-s	w							5				
206	217.22	11.22	ALTINT	Gradational upper contact. Grey-pink, weak porphyry texture becomes visible. Mod-hard (still scratches) Pyrite is disseminated and fracture controlled. Few fractures with chalcopyrite + pyrite.	SILPY	m-s			w	w					1		5				
217.22	229.15	11.93	ALTINT	Fg, grey-green, mottled texture to banded. Silica-pyrite-chlorite, disseminated and fracture controlled pyrite into breccia texture locally. Few calcite vens, weak epidote spots. Sharp 45 degree to CA upper contact but visible porphyry to fg alteration within interval. Gradational lower contact into porphyry texture.	SILPY	s			w-m	w							5				
229.15	238	8.85	ALTINT	Grey porphyry texture as before. Few black chlorite-pyrite fractures	SILPY	m-s											5				
238	239.7	1.7	ALTNT	Fg, grey-pink, strongly altered interval as above, disseminated pyrite 5%, locally up to 10%, weak epidote spots.	SILPY	s				w							7				
239.7	240	0.3	Fault	wavy cleavage at 50 degrees to CA. Fine-grained pyrite	SILPY																
240	242	2	ALTINT	As 238-239.17	SILPY	s				w							5				
242	243.23	1.23	ALTINT - DYKE	As above with few small dykes as below.	SILPY	s				w							5				
243.23	247.25	4.02	DYKE	Green-grey dyke, subhedral green-black mafics, unaltered	SILPY																
247.25	247.64	0.39	ALTINT	as 240-242m, small interval bounded by dyke	SILPY	s				w							5				
247.64	248	0.36	DYKE	as 243.33-247.25m	SILPY																
248	243.3	-4.7	ALTINT	as 240-242m, small interval bounded by dyke	SILPY	s				w							5				
243.3	248.85	5.55	Dyke	as 243.33-247.25m	SILPY																
248.85	254.85	6	ALTINT	Fine-grained, pink-grey alteration with weak epidote spots. Thin black chlorite-pyrite-calcite veinlets. Weak-very weak porphyry texture locally.	SILPY	s				w							3				
254.85	265.75	10.9	ALTINT	Weaker silica, visible porphyry texture, gradational upper contact. Sharp lower contact, broken. Pyrite rims/replaces mafics.	SILPY	m												3			
				Pink, fine-grained, altered intrusive. Strong pyrite fracture network to breccia between 266.3 and 266.5m. Strong pyrite fracture network at 266.75m.	SILPY	m-s			w								5				
265.75	266.5	0.75	ALTINT	as 254.85 to 265.75m	SILPY	m											3				
266.5	269.85	3.35	ALTINT	Pink-grey, fine-grained, broken upper contact. Disseminated and fracture controlled pyrite	SILPY	s				w							3				
269.85	271.25	1.4	ALTINT		SILPY												3				

From	To	Width	Rock Code	Description	ALT CODE	Alteration							Mineralization								
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
271.25	273.42	2.17	DYKE	Green dyke subhedral feldspar-hornblende porphyritic. Non-magnetic, 45 degree to CA sharp upper contact. Lower contact horizontal from 273.42-273.71m																	
273.42	277.14	3.72	ALTINT	Strong pink-grey silica-pyrite alteration. Few brown felted spots of biotite? Chlorite?	SILPY	s	?	?	w-m								4				
277.14	278.75	1.61	Dyke	Dyke as above. 70 degrees to CA, sharp contact. Lower contact at 45 degrees to CA.																	
278.75	285.25	6.5	ALTINT	As 273.42-277.14m late calcite veinlets at 45 degrees to CA. Mottled to banded texture	SILPY	s	?	?	w-m								4				
285.25	288.35	3.1	Dyke	As above dyke. 45 to CA sharp upper contact, lower contact obscured by calcite vein breccia.																	
288.35	292.7	4.35	ALTINT	Pink-grey moderate-very strong silica-pyrite. Fine-grained strongly silicified to visible porphyry texture. Chlorite spots. 289.55-290m : verystrong silica + pyrite fractures to breccia texture. 291.39-292.6m : Pyrite-chlorite fractures, silica healed by calcite (vein breccia)	296	m-vs		w									5				
292.7	296.95	4.25	DYKE	Dyke as above, green																	
296.95	302	5.05	ALTINT	Pink-grey very hard silica-pyrite alteration with porphyry texture visible locally. Pyrite fractures with pale-pik silica halos/margins. Few fractures with chalcopyrite.	SILPY	s-vs		w-m									3				
302	305	3	ALTINT	As above but with pervasive green colour few quartz veinlets at 60 degrees to CA.	SILPY CH	s-vs		w-m									3				
305	306.8	1.8	ALTINT VNBX	Strong Silica alteration as above moderate to strong pyrite fracture network to breccia.	SILPY	s-vs		w-m									5 to 10				
306.8	308.07	1.27	ALTINT	Grey, porphyry texture, broken core	SILPY	m											5				
308.07	313.15	5.08	ALTINT	As 296.95 - 305m. Grey to slight pink and green colourations. Local breccia texture at 309.4 - 310m healed by fine-grained pyrite (+/-silica) locally the green colour is softer. Weak to no porphyry texture.	SILPY	s-vs		w									5				
313.15	314.85	1.7	ALTINT	Broken contact grades into less altered zone with visible porphyry texture, diss py, trace disseminated chalcopyrite, fine-grain fg chlorite-epidote sports.	SILPY	m-s		w								tr		5			
314.85	319	4.15	ALTINT	Above unit grades into more silicified phase with weak porphyry texture.	SILPY	s		w								0.5		5			
319	320	1	ALTINT	As above but patchy green-black chlorite alteration	SILPY	s		m								0.5		5			
320	330.1	10.1	ALTINT - INT BX	Grey silica-pyrite altered porphyry as above. Fine-grained grey-green moderately hard pyritic (+/- chalcopyrite) subangular fragments, softer than matrix, up to 5cm in size. Pyritic fracture networks.	SILPY	m		w-m								tr		5			
330.1	332.1	2	ALTINT - INTBX	As above, green colouration, fragments. Increased chlorite fractures and pyrite fractures, weak calcite. Fine-grained disseminated sulfide.	SILPY CH	m		m-s										5			

From	To	Width	Rock Code	Description	ALT CODE	Alteration								Mineralization						
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL
332.1	332.51	0.41	DYKE	Green, fine-grained, andesite dyke, feldspar-hornblende porphyritic, contact at 80 degrees to CA.																
332.51	335	2.49	ALTINT	Visible porphyry texture, chlorite-calcite veinlets to stockwork	SILPY CHCL	m				m-s		m		tr		3				
335	340.1	5.1	ALTINT	Grey, visible porphyry texture with spots of epidote and disseminated pyrite, pyrite fractures present locally,	SILPY	m				w				tr		3				
				As above. 1.16m of interval has very strong pink-grey silicification. Late calcite veinlets and rare epidote spots. A pyrite fracture network-stockwork is present at 342.2-342.3m. From 341.09 to 341.29 a translucent grey suart vein with reasonably sharp margins.	SILPY	s				w				tr		5				
340.1	343.82	3.72	ALTINT																	
343.82		EOH																		

Project	Mt Dunn
Drill Hole	MD09-04
Zone	
Start date	30-Aug-09
Finish date	01-Sep-09
Drilled by	Ridgeline Diamond Drilling
Logged by	M.W.A Hocking
UTM E	399262.8409
UTM N	6258988.909
Azimuth	280
Dip	-60
Elevation	1215
Length	232.72m
Surveys	EZ-Shot

From	To	Width		Description	ALT CODE	Alteration								Mineralization								
m	m	m	Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH	
0	19.52	19.52	Collar	Collar, no recovery																		
19.52	22.55	3.03	ALTINT	hornblende-feldspar porphyritic intrusive. Medium grey colour, broken, rubble, oxidized, moderately hard. 5% disseminated and fracture controlled pyrite. Tr, fine-grained, chalcopyrite (likely underestimated)	SILPY	m									tr	5						
22.55	26.84	4.29	ALTINT	As above. Competent rock. Pyrite disseminated + fracture controlled, fine-grained chalcopyrite	SILPY	m									tr	5						
26.84	33	6.16	ALTINT	As above, dark colour, high concentration of chalcopyrite	SILPY	m									0.5	5						
33	34.18	1.18	ALTINT	As above, numerous fractures with orange-yellow feox margins. Interval is paler grey than previous. Oxidation of pyrite creates local clay alteration and iron-oxide of coarse-grained porphyry texture. hornblende altering to chorite	SILPY	m		w		w-m					tr	5						
34.18	34.65	0.47	ALTINT	Visible weak porphyry texture, stronger Silica-pyrite, very hard to mod hard. Disseminated and fracture controlled pyrite. Increased chalcopyrite (fine-grained)	SILPY	s									0.5	5						
34.65	38	3.35	ALTINT	Well defined porphyry texture. Moderately hard (still scratches), dry molybdenite fractures at 35.35m, black-brown square to tabular mafic minerals. Increased fine-grained, disseminated chalcopyrite,	SLPY	m									1	tr	5					
38	48	10	ALTINT	Decrease in size of mafic minerals, increased alteration, dark grey, numerous pyrite fractures. molybdenite on fractures at 39.85m, 40.32m, and 40.64m	SILPY	m-s									0.5	tr	5					
48	50	2	ALTINT	Grey, medium-grained porphyry texture, broken core, oxidized	SILPY	w-m									tr		5			tr		
50	58.35	8.35	ALTINT	As above, stronger alteration, decreased porphyry texture	SILPY	m-s									tr		5					
58.35	60.64	2.29	ALTINT	As above, fine-grained, pale, hard (scratches locally), Silica - pyrite fractures locally +/- sericite. Few quartz-calcite veins at 90 degrees to CA. Tr to 1% chalcopyrite.	SILPY	s				w					0.5	3						
60.64	62.75	2.11	ALTINT	As above, increase porphyry texture, green colouration, decrease in silica alteration, increased chlorite, increase in very fine-grained chalcopyrite. Pyrite fractures	SILPY CH	m		w							0.5	4						
62.75	64.5	1.75	ALTINT	As above, paler grey to yellow colouration, decreased porphyry texture, weak sericite, 4-6 translucent to milky quartz veinlets per meter, locally offset by pyrite fractures. fine-grained, chalcopyrite clots within veinlets.	QSP	m									1	4						
64.5	67.5	3	ALTINT	Increase porphyry texture, brown-grey colouration, pyritic fracture.	SILPY	w-m											4					
67.5	84.79	17.29	ALTINT	Dark grey, visible porphyry texture, moderately hard (scratches, disseminated and fracture controlled pyrite, pyrite is fine-grained to locally coarse-grained and present in calcite veins. Few 5cm sized brown-black, soft spots, possible secondary biotite? Vein breccia of grey, altered wall rock in pyrite-silica matrix (78.69-78.95m)	SILPY	m	?	w							1.5	5						

From	To	Width		Description	ALT CODE	Alteration								Mineralization							
m	m	m	Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
84.79	85.2	0.41	ALTINT	As above, increased chlorite, black-green colouration.	SILPY	m	?	m						1.5	5						
85.2	91.5	6.3	ALTINT	As 67.5 - 84.79m	SILPY	m	?	w						1.5	5						
91.5	92.25	0.75	ALTINT	Transition zone from fine-grained, grey unit above to porphyry-equigranular texture. 10-12 calcite veinlets per meter to weak stockwork.	SILPY	m-s						m									
92.25	106	13.75	ALTINT	Pervasive w-m silicification, pyrite fractures with very hard silica margins observed locally, clearly visible porphyry texture, 5% + disseminated pyrite often replacing hornblende, very fine-grained chalcopyrite. Few late quartz-calcite veins (2cm wide) at 70-80 degrees to CA with soft yellow margins. Quartz vein at 102.1-102.3m. Quartz-calcite veins at 80 degrees to CA + narrow fault at 104.9-105.05m.	SILPY	m								0.5	5						
106	113.4	7.4	ALTINT	As above with increase green colouration (increased chlorite, possibly decreased silica)	SILPY	m		w-m						0.5	5						
113.4	117	3.6	ALTINT - BX	Contact is comprised of subangular fragments of fine-grained, grey, pyritic unit with weak pervasive carbonate and green chloritic spots. Interval is 70 fragmental unit and 3% silica-pyrite altered porphyry. Fragmental is xenolith of footwall rocks? Or strongly altered intrusive (less likely)?	SILPY CCP	w-m		w			w		tr		5						
117	124.5	7.5	ALTINT	Sharp contact (80 degrees to CA) with above xenolith unit, Medium-grained feldspar hornblende porphyry as above, visible texture, green colouration, chlorite replacing mafics, chlorite fractures, few chlorite-calcite-pyrite-silica veins at 20-40 degrees to CA. Disseminated pyrite with trace chalcopyrite.	SILPY CCP	w-m		w-m			w		tr		5						
124.5	141.65	17.15	ALTINT	124-125m transition from porphyry texture to less visible porphyry texture and increased silica and chlorite alteration. Few translucent quartz veins per meter. 134-135m ~ 20 quartz veinslets at 60-80 degrees to CA, sheeted, very rare sulfide in veins.	SILPY CH	m		w-m						tr		3					
141.65	146.2	4.55	ALTINT	As above, green-grey colour with irregular magnetic fracture network. Grey-pink very hard silica margins. Few non-magnetic quartz veins with pink margins, K-spar (too hard)	SILPY MT	m-s	?	w						1	2	5					
146.2	149	2.8	ALTINT	As above with fewer magnetite veinlets, chlorite fractures, few quartz veinlets to very weak stockwork	SILPY MT	m-s		w						tr		3	1				
149	153.9	4.9	ALTINT	Contact over 10cm. Very pale grey silica-pyrite +/- sericite alteration. Loss of dark grey colour seen above. Few quartz veinlets.	SILPY to QSP	m-s					w					3					
153.9	154.1	0.2	Vein	50 degrees to CA. Calcite-quartz-chlorite-pyrite vein																	
154.1	154.63	0.53	ALTINT	Grey, silica-pyrite alteration	SILPY	s										3	1				
154.63	154.47	-0.16	ALTINT	Dark grey-green, weak porphyry texture, weak magnetite seams	SILPY	m-s		w								3	1				

From	To	Width		Description	ALT CODE	Alteration								Mineralization									
m	m	m	Rock Code			SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH		
154.47	158	3.53	ALTINT	Broken zore, orange oxide on fracture surfaces, pale grey, silica-sericite-pyrite alteration. Visible porphyry texture.	SILPY	m-s			w-m							3							
158	160	2	ALTINT	Green, visible porphyry texture, chlorite fractures, weak magnetite seams	SILPY CHMT	w-m		w								2	1						
				Pale grey weakly magnetic, feldspar-hornblende porphyry with xenoliths up to 5cm in size of grey-green intrusive/porphyry as above 160m. Fragments are pyritic with trace amounts of chalcopyrite. Very weak chlorite alteration of mafic minerals. Few chloritic fractures. Pale grey unit intrudes green-grey porphyry unit.																			
160	166.27	6.27	ALTINT INTBX		SILPY CH	w-m		w							tr	3							
166.27	170.23	3.96	DYKE	Sharp contacts. Coarse-grained, sub hedral feldspar-hornblende porphyry dyke, strongly magnetic.																			
170.23	175.2	4.97	ALTINT INTBX	As 160-166.27m interval. Fragments are silica-pyrite altered, decrease in chlorite.	SILPY	w-m											2						
175.2	191.52	16.32	ALTINT	Dark grey-green medium-grained to coarse-grained crowded feldspar-hornblende porphyry (source of fragments in above ALTINT - INT BX intervals. Moderate-strong magneite-chlorite seams. Broken core from 182 -194m	SILPY	wm		wm		w							2						
191.52	192.8	1.28	ALTINT	Lighter grey porphyry - dyke	SILPY	w-m		wm									2						
192.8	195.15	2.35	ALTINT	Darker green porphyry as 175.2-191.52m	SILPY	m		m									2						
195.15	199	3.85	ALTINT - INTBX	Lighter grey porphyry (as 191.52-192.8m) with fragments of darker green porphyry unit (as 192.8 - 195.15m)	SILPY	w-m		w-m									2						
199	213	14	ALTINT	Dark grey to slight green colour, weak porphyry texture, increase in silica-pyrite alteration, few translucent quartz veins at 30-40 degrees to CA. Broken core from 203-205.75m.	SILPY	m-s		w-m		w				tr	5								
213	215	2	ALTINT	Grey, increased wilica pyrite, weak-moderate translucent-mily coloured quartz vein stockwork.	SILPY	m-s		w								4							
215	225.7	10.7	ALTINT	as 199-213m	SILPY	m-s		w-m		w					tr	5							
225.7	227.6	1.9	ALTINT - INTBX	Fragments of lighter-grey altered porphyry in above unit.	SILPY	m-s		w-m		w					tr	5							
227.6	230.15	2.55	ALTINT	Rubble zone, moderate-strong silica alteration, visible porphyry-intrusive texture. Voids/rubble cemented by calcite viens. Banded fine-grained quartz vein from 228.75-229m. Chlorite fractures.	SILPY	m-s		w								3							
230.15	232.72	2.57	ALTINT	Green-grey colour, visible porphyry-intrusive texture, medium-grained, drill encountered void at 232.72m and could not continue.	SILPY	w		w									2						
232.72	EOH																						

Project	Mt Dunn
Drill Hole	MD09-05
Zone	
Start date	01-Sep-09
Finish date	04-Sep-09
Drilled by	Ridgeline Diamond Drilling
Logged by	M.W.A Hocking
UTM E	399262.8409
UTM N	6258988.909
Azimuth	280
Dip	-65
Elevation	1215
Length	337.94m
Surveys	EZ-Shot

From	To	Width	Rock Code	Description	ALT CODE	Alteration								Mineralization							
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
m	m	m																			
0	9.15	9.15	Collar	Collar, no recovery																	
9.15	20.17	11.02	ALTINT	Rubble, feox stained, poor recovery/rqd. Feldspar-hornblende porphyry	SILPY	w			w						tr		5			tr	
20.17	26.54	6.37	ALTINT	Broken, oxidized, more competent than above, grey-green, patchy chlorite chlorite fractures	SILPy CH	w-m			w-m						tr		5				
26.54	30	3.46	ALTINT	Grey to dark-grey, moderate to strong, silica-pyrite, silica veinlets with medial pyrite bands and mm-scale silica alteration halos. Pervasive silica and disseminated pyrite replacing hornblende. Feldspars crowded and clearly visible.	SILPY	m									tr		5				
30	50	20	ALTINT	Grey with slight mauve colouration. Increase silica and pyrite fractures relative to above. Weak epidote along fractures + epidote-pyrite spots after mafic minerals. Rare, late, quartz veins. Alteration fades between visible porphyry texture and fine-grained strongly altered rock. Chalcopyrite is fine-grained and disseminated - likely underestimated. Rare chalcopyrite-bearing fractures are also observed. The strongest silica occurs in the following intervals: 30-32.6m, 34-36m, 36.25-37.25m, 40.25-40.75m, 45.5-46.5m, 48-50m.	SILPY	m-s				w					tr		5				
50	54	4	ALTINT	As above, chlorite-pyrite fracture network, green colouration, weak porphyry texture	SILPY CH	m-s			w-m	w					tr		5				
54	60.35	6.35	ALTINT	As above, less chlorite, less silica, grey to dark-grey. Mafics more visible, crowded porphyry texture visible, weak epidote spots.	SILPY	m-s			w						tr		5				
60.35	72.36	12.01	ALTINT	As above, decreased alteration, clear mg porphyry texture, pink colouration from 68 to 69.5m. Silica-pyrite cemented vein breccia at 70-70.5m . Disseminated and fracture controlled pyrite, few chlorite seams, few late calcite veinlets.	SILPY	w-m			w			w			tr		5				
72.36	73.6	1.24	DYKE	Green fine-grained, hornblende-feldspar porphyry dyke, magnetite, upper contact at 70 degrees to CA. Lower contact at 50 degrees to CA.																	
73.6	75.64	2.04	ALTINT	As ALTINT interval 60.35 to 72.36m, slight increase in chlorite	SILPY	w-m			w-m	w					tr		5				
75.64	77	1.36	ALTINT	As above with increase in silica-pyrite alteration intensity, decrease in porphyry texture. Increase in chlorite fractures. Horizontal-irregular milky white quartz vein from 76.23 to 76.75m.	SILPY	m			m	w					tr		5				
77	93	16	ALTINT - IVNBX	As interval above with increased alteration intensity. Dark green-grey, silica-pyrite altered intrusive with black-green chlorite-pyrite +/- silica fracture network creating local vein breccia textures. Notable chalcopyrite increase between 77 and 79m.	SILPY CHPY	m-s			m-s						tr-0.5		5				
93	106.14	13.14	ALTINT	Paler colour than above, gradual increase in porphyry texture (decrease in alteration intensity). Medium-grained to coarse-grained porphyry texture. Few late chlorite-calcite veinlets, silica alteration is locally strong (texturally destructive) over 20cm intervals. Fine-grained pyrite and ultra fin-grained chalcopyrite	SILPY CH	m-s			w-m			w			tr		3				

From	To	Width	Rock Code	Description	ALT CODE	Alteration								Mineralization							
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH
m	m	m																			
106.14	107.75	1.61	ALTINT - Dyke?	Feldspar-hornblende (green) porphyritic. Green to grey, weak silica-pyrite, clear porphyry texture. Less altered than above interval. Sharp lower contact at 45 degrees to CA.	SILPY	w											3				
107.75	127.2	19.45	ALTINT	Strongly silica altered, fine-grained. Very weak to absent porphyry texture, very hard, palegreen-grey. Silica-chlorite-pyrite fractures. Slight banded textures, weak brittle calcite veinlets.	SILPY CH	s			m-s			w		tr		3					
127.2	128.55	1.35	ALTINT	Gradational contact. Very strong pink-grey silica with pyrite fractures - with traces of very fine-grained chalcopyrite	SILPY	vs								tr		3					
128.55	131	2.45	ALTINT	As previous (107.75 - 127.2m) with increased visible porphyry texture, decreased alteration. 40% of interval is strongly silica altered with no visible porphyry texture, 60% visible porphyry texture. Alteration alternated throughout interval.	SILPY	m-s			w					tr		2					
131	133.9	2.9	ALTINT	10cm gradational contact to green chloritic zone. Non-existent to moderately visible porphyry texture. Disseminated and fracture controlled pyrite.	SILPY CH	m-s			m-s					tr		2					
133.9	144.5	10.6	ALTINT	Above unit grades into pale grey, fine-grained, very strong silica alteration with irregular patches of softer chlorite. 1 cumulative meter of interval displays visible porphyry textures. Pyrite fractures network form breccia texture very locally.	SILPY	vs			w					tr		2					
144.5	146.5	2	ALTINT	Fairly sharp transition into grey, medium grained to coarse-grained crowded feldspar-hornblende porphyry texture. Pyrite is disseminated and in fracture networks and very fine-grained disseminated and fracture controlled chalcopyrite. Few late calcite veins and weak chlorite fractures.	SILPY	m-s			w					0.5		2					
146.5	151	4.5	ALTINT	As above with increased silica, decreased porphyry texture, increased chalcopyrite. Increases pyrite (5-10%) between 150.5 and 151m .	SILPY	s			w					0.5		5					
151	168.62	17.62	ALTINT	As 144.5-146.5m , chlorite intensity begins to rise slightly near 161m.	SILPY	m-s			w					0.5		2					
168.62	180	11.38	ALTINT	Sharp contact to weak porphyry texture, increased silica alteration. Dark-grey colour, few chlorite fractures	SILPY	s			w					tr		4					
180	208	28	ALTINT	Porphyry (coarse-grained) texture becomes more visible. Brown grey colour with patchy zones of increase silica alteration (decreased porphyry texture). 4.2 cumulative meters of pale-grey to pink, very hard, strongly silicified rock. Pyrite is disseminated and fracture controlled. Increased number of silica/pyrite fractures between 200.75m and 201.75m .	SILPY	m-s			w					tr		5					
208	215.6	7.6	ALTINT CG	Increase in chlorite intensity, coarse-grained porphyry texture as above with black, soft chlorite-pyrite spots and fractures	SILPY CHPY	w-m			m					tr		5					
215.6	224.75	9.15	ALTINT MG	Sharp uppercontact at 30 degrees to CA. Calcite vein along contact. Fine-grained grey to slight mauve coloured unit with a weak porphyry texture. Alteration contact or contact between two porphyry units (more likely), both altered. Small epidote spots and few pyrite fractures.	SILPY	m-s			w					tr		5					

From	To	Width	Rock Code	Description	ALT CODE	Alteration								Mineralization								
						SIL	OR	BI	CH	EP	SER	CAL	OTH	CP	MO	PY	MT	HT	LIM	MAL	OTH	
m	m	m																				
224.75	225.15	0.4	ALTINT CG BX	Sharp upper contact Breccia texture, Fine-grained to Coarse-grained porphyry in fine-grained pyritic, soft, chlorite? Matrix. Intrusive xenoliths	SILPY	ms			w								7					
225.15	236	10.85	ALTINT CG	Coarse-grained feldspar porphyry texture moderately obscured/destroyed by alteration. Grey colour, numerous pyritic fractures which are dark coloured and fine-grained with chlorite +/- silica.	SILPY	m			w							tr	6					
236	237.5	1.5	ALTINT CG	As above with increase silica, decreased porphyry texture, and increased pyrite-silica fractures	SILPY	m-s			w							tr	7					
237.5	245	7.5	ALTINT CG	As 225.15-236m	SILPY	m			w							tr	6					
245	246	1	ALTINT CG	As above with increased green colouration, more visible mafics, decreased silica, increased chlorite	SILPY CH	w			m							tr	5					
246	254.5	8.5	ALTINT CG	As above with patchy zones of increased silica-pyrite and a decrease in porphyry texture. Alteration creates a slight mottled texture with grey-pink-green colouration and chlorite spots.	SILPY CH	w-m			w							tr	5					
254.5	256.73	2.23	ALTINT VNBX	As above with strong pyrite fracture network to breccia. Soft pyritic +/- chlorite and silica matrix.	SILPY	m										tr	8					
256.73	269.85	13.12	ALTINT CG	as 246 - 254.5m. With increased silica-pyrite, decreased porphyry texture and an increase in chlorite fractures. Moderately hard. Pyrite fracture networks-breccia at 259-260.2m and 262-262.5m.	SILPY	m-s			w								tr	5				
269.85	286	16.15	ALTINT CG-FG	Irregular contact from 269.6-269.85m. Increased silica pyrite alteration, darker grey colour, slight mauve colouration. Weak coarse-grained feldspar texture. Chlorite spots with epidote. Moderately hard, disseminated and fracture controlled pyrite. 277.55 - 278.07m : oblique cut of contact between this interval and a paler grey salt and pepper textures pyritic hornblende-feldspar porphyry unit.	SILPY CHEP	m-s			m	w								4				
286	292.55	6.55	ALTINT CG	Coarse-grained porphyry texture becomes more visible, grey to slight pink (k-spar?) colouration, disseminated and fracture controlled pyrite. Moderately hard. Few pyritic-chlorite fractures, mafics not visible, broken upper contact. Lower contact occurs over 5cm, grey-green weak porphyry texture to sharp black matrix, strong colour change.	SILPY CH	m	?		w									5				
292.55	301.4	8.85	ALTINT - SSH	Black fine-grained matrix with visible coarse-grained feldspar porphyry texture as above. Porphyry assimilating blackshale unit below, transition zone. Few late white quartz-calcite veinlets and pyrite veinlets.	SILPY	m			w									2				
301.4	337.94	36.54	SSH	Branded/shear contact at 45 degrees to CA with above transition zone. Black fine-grained mudstone-shale with some interbedded siltstone, numerous brittle calcite veins. Local clastic textures. Few pyritic veinlets. Fragmental textures at 318.75m and between 325.74 and 326.5m.														1				
337.94		EOH																				

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-01	3.04	5.49	2.45	927301	SMI09000207	1.86	719	89	5	6	19	0.8
MD09-01	5.49	7.50	2.01	927302	SMI09000207	2.15	1466	188	7	12	20	1.0
MD09-01	7.50	8.40	0.90	927303	SMI09000207	1.9	1839	92	4	6	28	1.2
MD09-01	8.40	9.40	1.00	927304	SMI09000207	4.6	1209	157	8	7	19	1.1
MD09-01	9.40	11.28	1.88	927305	SMI09000207	1.68	1541	292	7	21	23	2.9
MD09-01	11.28	13.30	2.02	927306	SMI09000207	2.68	758	136	5	7	17	1.9
MD09-01	13.30	14.63	1.33	927307	SMI09000207	1.92	2249	153	6	7	25	2.2
MD09-01	14.63	16.03	1.40	927308	SMI09000207	2.14	607	127	4	6	15	1.2
MD09-01	16.03	17.48	1.45	927309	SMI09000207	3.53	2560	264	-2	-5	18	1.5
MD09-01	17.48	19.59	2.11	927310	SMI09000207	2.79	1861	243	9	7	20	1.8
MD09-01	19.59	20.78	1.19	927311	SMI09000207	2.15	1158	148	3	6	22	0.9
MD09-01	20.78	22.63	1.85	927312	SMI09000207	4.11	2082	91	5	7	22	1.5
MD09-01	22.63	24.77	2.14	927313	SMI09000207	3.56	3143	297	3	-5	25	1.4
MD09-01	24.77	27.72	2.95	927314	SMI09000207	1.93	2693	243	11	-5	28	1.1
MD09-01	27.72	29.92	2.20	927315	SMI09000207	4.73	1178	220	6	-5	24	0.7
MD09-01	29.92	31.97	2.05	927316	SMI09000207	4.65	2895	675	5	5	38	2.0
MD09-01	31.97	33.92	1.95	927317	SMI09000207	4.2	1514	247	4	-5	33	0.9
MD09-01	33.92	35.90	1.98	927318	SMI09000207	4.64	655	135	-2	-5	26	-0.5
MD09-01	35.90	37.90	2.00	927319	SMI09000207	4.83	3493	692	17	-5	24	1.6
MD09-01	37.90	39.90	2.00	927321	SMI09000207	4.81	188	23	2	-5	26	-0.5
MD09-01	39.90	41.90	2.00	927322	SMI09000207	4.81	185	29	-2	-5	26	-0.5
MD09-01	41.90	43.90	2.00	927323	SMI09000207	5.25	137	22	3	-5	17	-0.5
MD09-01	43.90	46.44	2.54	927324	SMI09000207	4.29	487	105	6	7	21	-0.5
MD09-01	46.44	48.79	2.35	927325	SMI09000207	5.35	518	129	12	7	12	-0.5
MD09-01	48.79	50.90	2.11	927326	SMI09000207	4.8	154	35	4	6	19	-0.5
MD09-01	50.40	52.66	2.26	927327	SMI09000207	3.71	624	181	28	16	25	1.0
MD09-01	52.66	53.20	0.54	927328	SMI09000207	1.68	313	1052	28	156	319	8.2
MD09-01	53.20	54.05	0.85	927329	SMI09000207	2.69	720	323	48	35	119	2.0
MD09-01	54.05	56.00	1.95	927332	SMI09000207	4.79	319	79	11	8	18	-0.5
MD09-01	56.00	58.00	2.00	927333	SMI09000207	4.3	273	45	13	7	14	-0.5
MD09-01	58.00	60.00	2.00	927334	SMI09000207	5.53	619	161	37	11	8	-0.5
MD09-01	60.00	62.00	2.00	927335	SMI09000207	5.05	268	31	15	5	13	-0.5
MD09-01	62.00	64.00	2.00	927336	SMI09000207	4.86	303	34	20	7	14	-0.5
MD09-01	64.00	66.00	2.00	927337	SMI09000207	5.04	449	42	23	7	9	-0.5
MD09-01	66.00	68.00	2.00	927338	SMI09000207	5.1	377	50	13	10	10	-0.5
MD09-01	68.00	70.00	2.00	927339	SMI09000207	4.43	207	29	5	5	15	-0.5
MD09-01	70.00	72.00	2.00	927341	SMI09000207	5.27	202	48	9	10	12	-0.5
MD09-01	72.00	74.00	2.00	927342	SMI09000207	4.95	130	26	5	-5	11	-0.5
MD09-01	74.00	76.00	2.00	927343	SMI09000207	4.95	346	80	12	8	10	-0.5
MD09-01	76.00	78.00	2.00	927344	SMI09000207	4.56	252	33	11	7	12	-0.5
MD09-01	78.00	80.00	2.00	927345	SMI09000207	5.65	127	12	6	-5	12	-0.5
MD09-01	80.00	82.00	2.00	927346	SMI09000207	4.75	149	31	4	9	15	-0.5
MD09-01	82.00	84.00	2.00	927347	SMI09000207	5.02	240	34	8	9	112	-0.5
MD09-01	84.00	86.00	2.00	927348	SMI09000207	5	141	14	6	7	17	-0.5
MD09-01	86.00	88.00	2.00	927349	SMI09000207	4.9	189	32	6	6	16	-0.5
MD09-01	88.00	90.00	2.00	927351	SMI09000207	0.9	374	41	15	8	19	-0.5
MD09-01	90.00	92.00	2.00	927352	SMI09000207	4.66	169	16	6	5	17	-0.5
MD09-01	92.00	94.00	2.00	927353	SMI09000207	4.86	299	40	6	8	18	-0.5
MD09-01	94.00	96.00	2.00	927354	SMI09000207	4.95	405	47	5	-5	26	-0.5
MD09-01	96.00	98.00	2.00	927355	SMI09000207	4.97	491	64	4	6	15	-0.5
MD09-01	98.00	100.00	2.00	927356	SMI09000207	4.55	444	67	4	9	20	-0.5
MD09-01	100.00	102.00	2.00	927357	SMI09000207	5.01	495	98	7	8	19	-0.5
MD09-01	102.00	104.00	2.00	927358	SMI09000207	4.82	493	335	5	9	25	-0.5
MD09-01	104.00	106.00	2.00	927359	SMI09000207	5.19	465	99	14	-5	23	-0.5
MD09-01	106.00	108.00	2.00	927362	SMI09000207	4.67	570	142	6	-5	18	-0.5
MD09-01	108.00	110.00	2.00	927363	SMI09000207	5.14	438	70	4	6	20	-0.5
MD09-01	110.00	112.00	2.00	927364	SMI09000207	4.68	962	162	12	-5	22	0.6
MD09-01	112.00	114.00	2.00	927365	SMI09000207	4.58	588	59	12	-5	13	-0.5
MD09-01	114.00	116.00	2.00	927366	SMI09000207	4.98	566	139	6	-5	16	-0.5
MD09-01	116.00	118.00	2.00	927367	SMI09000207	4.78	442	94	4	-5	17	-0.5
MD09-01	118.00	120.00	2.00	927368	SMI09000207	5	357	88	10	-5	15	-0.5
MD09-01	120.00	122.00	2.00	927369	SMI09000207	5.43	350	102	15	97	25	3.6
MD09-01	122.00	124.00	2.00	927371	SMI09000220	4.89	386	102	9	8	17	-0.5
MD09-01	124.00	125.60	1.60	927372	SMI09000220	3.77	403	44	14	7	16	-0.5
MD09-01	125.60	127.65	2.05	927373	SMI09000220	5.32	728	83	19	9	18	-0.5
MD09-01	127.65	128.65	1.00	927374	SMI09000220	2.54	1343	199	4	-5	24	-0.5
MD09-01	128.65	129.65	1.00	927375	SMI09000220	2.62	1042	104	6	-5	16	-0.5
MD09-01	129.65	131.10	1.45	927376	SMI09000207	3.95	1973	502	12	9	24	1.9
MD09-01	131.10	133.10	2.00	927377	SMI09000207	5.41	1579	243	28	10	23	1.6
MD09-01	133.10	135.10	2.00	927378	SMI09000207	5	616	83	12	11	32	0.9

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-01	135.10	136.05	0.95	927379	SMI09000207	2.31	446	77	20	20	84	0.7
MD09-01	136.05	138.00	1.95	927381	SMI09000207	4.84	594	79	5	-5	23	0.8
MD09-01	138.00	140.00	2.00	927382	SMI09000207	4.98	411	50	13	7	18	0.8
MD09-01	140.00	142.00	2.00	927383	SMI09000207	4.56	248	38	3	13	34	0.6
MD09-01	142.00	144.00	2.00	927384	SMI09000207	5.14	485	57	7	-5	13	0.7
MD09-01	144.00	146.00	2.00	927385	SMI09000207	4.57	646	79	11	8	13	0.8
MD09-01	146.00	148.00	2.00	927386	SMI09000207	5.35	580	52	19	-5	31	0.7
MD09-01	148.00	150.00	2.00	927387	SMI09000207	5.07	613	97	12	9	17	0.8
MD09-01	150.00	152.00	2.00	927388	SMI09000207	5.46	484	86	9	-5	16	0.6
MD09-01	152.00	154.00	2.00	927389	SMI09000207	5.6	569	80	6	14	44	0.6
MD09-01	154.00	156.00	2.00	927392	SMI09000207	4.98	863	93	26	20	17	0.7
MD09-01	156.00	158.00	2.00	927393	SMI09000207	5.36	747	69	24	-5	27	0.6
MD09-01	158.00	160.00	2.00	927394	SMI09000207	4.21	916	93	22	12	18	1.0
MD09-01	160.00	161.56	1.56	927395	SMI09000207	4.23	892	97	18	5	19	0.8
MD09-01	161.56	163.18	1.62	927369	SMI09000207	3.91	1397	165	22	17	14	1.2
MD09-01	163.80	164.80	1.00	927397	SMI09000207	3.49	617	70	9	9	19	1.0
MD09-01	164.80	166.80	2.00	927398	SMI09000207	5.72	740	101	10	-5	23	1.0
MD09-01	166.80	168.80	2.00	927399	SMI09000207	2.32	1031	137	23	-5	24	1.0
MD09-01	168.80	170.80	2.00	927401	SMI09000207	9.38	856	109	10	6	22	0.9
MD09-01	170.80	172.80	2.00	927402	SMI09000207	2.67	989	142	21	9	21	0.8
MD09-01	172.80	174.80	2.00	927403	SMI09000207	6.86	900	109	21	-5	23	0.7
MD09-01	174.80	176.17	1.37	927404	SMI09000207	3.43	788	71	19	6	26	0.9
MD09-01	176.17	178.00	1.83	927405	SMI09000207	4.83	591	64	15	7	29	0.6
MD09-01	178.00	180.00	2.00	927406	SMI09000207	5.21	1082	136	9	-5	25	1.2
MD09-01	180.00	182.00	2.00	927407	SMI09000207	4.46	887	114	23	7	18	1.1
MD09-01	182.00	184.00	2.00	927408	SMI09000207	4.6	1210	168	30	8	24	1.3
MD09-01	184.00	186.00	2.00	927409	SMI09000207	4.62	948	187	11	8	20	1.4
MD09-01	186.00	188.00	2.00	927411	SMI09000207	4.69	1337	117	24	7	19	1.4
MD09-01	188.00	190.00	2.00	927412	SMI09000207	4.66	1345	94	19	6	17	1.5
MD09-01	190.00	192.00	2.00	927413	SMI09000207	4.74	1401	234	18	13	14	1.4
MD09-01	192.00	194.00	2.00	927414	SMI09000207	5.06	1983	227	68	8	13	1.7
MD09-01	194.00	195.20	1.20	927415	SMI09000207	2.92	2913	336	16	-5	19	2.3
MD09-01	195.20	197.20	2.00	927416	SMI09000207	5.31	1643	226	67	-5	15	0.7
MD09-01	197.20	199.20	2.00	927417	SMI09000207	4.31	2162	163	50	7	23	1.6
MD09-01	199.20	201.10	1.90	927418	SMI09000207	4.81	1774	190	7	6	24	1.5
MD09-01	201.20	203.61	2.41	927419	SMI09000207	3.91	2077	214	17	7	25	1.7
MD09-01	203.61	205.00	1.39	927422	SMI09000207	5.17	1526	198	11	14	51	1.6
MD09-01	205.00	206.17	1.17	927423	SMI09000207	3.41	1688	230	3	5	24	1.2
MD09-01	206.17	206.75	0.58	927424	SMI09000207	1.35	1234	156	6	8	42	1.3
MD09-01	206.75	208.00	1.25	927425	SMI09000207	2.87	1937	227	-2	10	36	1.6
MD09-01	208.00	210.00	2.00	927426	SMI09000207	4.67	1629	261	3	8	25	0.9
MD09-01	210.00	212.00	2.00	927427	SMI09000207	4.37	2199	336	21	6	19	1.1
MD09-01	212.00	214.00	2.00	927428	SMI09000207	5	1384	746	5	12	19	0.7
MD09-01	214.00	216.00	2.00	927429	SMI09000207	4.84	995	163	5	9	28	0.8
MD09-01	216.00	218.00	2.00	927431	SMI09000207	4.69	932	164	-2	6	28	0.5
MD09-01	218.00	220.00	2.00	927432	SMI09000207	4.99	1182	173	12	8	21	1.0
MD09-01	220.00	222.00	2.00	927433	SMI09000207	4.34	789	105	3	10	19	0.5
MD09-01	222.00	224.00	2.00	927434	SMI09000207	4.08	912	111	6	6	21	0.8
MD09-01	224.00	225.35	1.35	927435	SMI09000207	3.35	821	135	3	10	22	1.2
MD09-01	225.35	227.30	1.95	927436	SMI09000207	4.39	732	173	4	11	14	0.7
MD09-01	227.30	229.00	1.70	927437	SMI09000207	4.2	583	131	3	25	32	1.5
MD09-01	229.00	231.00	2.00	927438	SMI09000207	4.58	1460	148	5	16	25	1.5
MD09-01	231.00	232.40	1.40	927439	SMI09000207	3.24	1807	145	11	13	31	1.3
MD09-01	232.40	234.50	2.10	927441	SMI09000207	8.3	1445	125	8	17	33	0.9
MD09-01	234.50	236.00	1.50	927442	SMI09000207	4.06	2052	198	8	9	34	1.6
MD09-01	238.00	240.00	2.00	927443	SMI09000207	4.42	1768	162	9	7	56	1.1
MD09-01	240.00	242.00	2.00	927444	SMI09000207	4.98	988	97	10	7	26	0.6
MD09-01	242.00	244.00	2.00	927445	SMI09000207	5.25	3246	413	48	13	41	1.3
MD09-01	244.00	246.00	2.00	927446	SMI09000207	4.75	2840	351	29	15	26	1.0
MD09-01	246.00	248.00	2.00	927447	SMI09000207	5.74	3313	371	9	10	23	1.5
MD09-01	248.00	249.33	1.33	927448	SMI09000207	3.11	1964	242	15	8	17	1.0
MD09-01	249.33	250.00	0.67	927449	SMI09000207	1.72	2007	209	32	12	17	-0.5
MD09-01	250.00	252.00	2.00	927452	SMI09000207	4.73	3029	222	23	14	23	1.4
MD09-01	252.00	254.00	2.00	927453	SMI09000207	4.59	2190	423	7	13	27	0.6
MD09-01	254.00	256.00	2.00	927454	SMI09000207	6.31	1708	511	11	11	27	-0.5
MD09-01	256.00	258.47	2.47	927455	SMI09000207	6.57	1550	273	9	14	31	0.6
MD09-01	258.47	260.00	1.53	927456	SMI09000207	3.84	2920	351	7	12	27	1.1
MD09-01	260.00	261.32	1.32	927457	SMI09000207	2.99	2217	292	49	16	29	1.1
MD09-01	261.32	263.00	1.68	927458	SMI09000207	4.02	1927	201	44	15	23	1.2
MD09-01	263.00	264.00	1.00	927459	SMI09000207	2.65	2575	189	10	8	26	1.3

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-01	264.00	266.00	2.00	927461	SMI09000207	4.86	2545	246	8	11	32	1.1
MD09-01	266.00	268.00	2.00	927462	SMI09000207	4.86	2974	372	47	15	28	1.1
MD09-01	268.00	270.00	2.00	927463	SMI09000207	4.64	2133	261	35	13	23	0.8
MD09-01	270.00	272.00	2.00	927464	SMI09000207	9.33	3431	506	37	11	20	1.1
MD09-01	272.00	274.00	2.00	927465	SMI09000207	4.67	2529	390	25	11	21	0.7
MD09-01	274.00	276.00	2.00	n.s.								
MD09-01	276.00	278.00	2.00	927466	SMI09000207	4.89	1661	219	25	14	18	1.1
MD09-01	278.00	280.00	2.00	927467	SMI09000207	4.54	2572	218	43	13	22	1.4
MD09-01	280.00	282.00	2.00	927468	SMI09000207	4.97	3191	381	40	14	19	0.9
MD09-01	282.00	284.00	2.00	927469	SMI09000207	4.72	2945	312	113	9	29	1.2
MD09-01	284.00	286.00	2.00	927471	SMI09000207	4.94	2493	175	37	12	26	1.1
MD09-01	286.00	288.00	2.00	927472	SMI09000207	4.94	2533	171	52	12	26	1.4
MD09-01	288.00	290.00	2.00	927473	SMI09000207	5.05	1724	93	88	11	21	1.6
MD09-01	290.00	292.00	2.00	927474	SMI09000207	4.44	1823	169	90	16	25	1.0
MD09-01	292.00	294.00	2.00	927475	SMI09000207	5.02	3113	401	30	14	29	1.7
MD09-01	294.00	296.31	2.31	927476	SMI09000207	5.79	1997	253	46	13	28	1.9
MD09-01	296.31	299.20	2.89	927477	SMI09000207	5.75	2044	231	10	13	25	0.7
MD09-01	299.80	302.70	2.90	927478	SMI09000207	5.54	1729	218	8	13	23	0.5
MD09-01	302.07	304.60	2.53	927479	SMI09000207	6.22	2018	220	15	12	24	0.9
MD09-01	304.60	307.56	2.96	927482	SMI09000207	6.53	1912	221	12	11	28	-0.5
MD09-01	307.56	309.56	2.00	927483	SMI09000207	4.51	1222	134	11	10	23	-0.5
MD09-01	309.56	311.00	1.44	927484	SMI09000207	3.59	1100	110	16	14	32	-0.5
MD09-01	311.00	313.00	2.00	927485	SMI09000207	3.93	2437	310	13	12	27	0.8
MD09-01	313.00	315.00	2.00	927486	SMI09000207	4.33	2058	279	4	7	29	-0.5
MD09-01	315.00	317.00	2.00	927487	SMI09000207	4.89	3095	369	6	9	29	0.7
MD09-01	317.00	319.15	2.15	927488	SMI09000207	4.33	2036	194	8	12	31	0.5
MD09-01	319.15	322.10	2.95	927489	SMI09000207	7.13	2195	232	8	12	36	0.6
MD09-01	322.10	324.62	2.52	927491	SMI09000207	6.62	1417	157	11	12	32	-0.5
MD09-01	324.62	325.70	1.08	927492	SMI09000207	2.16	1079	278	15	16	24	-0.5
MD09-01	325.70	327.00	1.30	927493	SMI09000207	2.44	1291	217	6	17	29	-0.5
MD09-01	327.00	329.00	2.00	927494	SMI09000207	4.37	1504	255	5	13	34	-0.5
MD09-01	329.00	331.00	2.00	927495	SMI09000207	4.74	1338	332	5	11	31	-0.5
MD09-01	331.00	333.00	2.00	927496	SMI09000207	4.61	1197	442	6	12	31	-0.5
MD09-01	333.00	334.67	1.67	927497	SMI09000207	3.53	685	346	4	10	28	-0.5
MD09-02	12.19	14.00	1.81	927551	SMI09000208	4.32	1867	187	16	10	18	1.1
MD09-02	14.00	16.00	2.00	927552	SMI09000208	4.69	1598	141	8	10	17	0.6
MD09-02	16.00	18.00	2.00	927553	SMI09000208	4.58	1233	83	17	7	45	-0.5
MD09-02	18.00	20.00	2.00	927554	SMI09000208	5.65	1143	77	24	13	23	-0.5
MD09-02	20.00	22.00	2.00	927555	SMI09000208	3.8	1773	223	15	12	24	-0.5
MD09-02	22.00	24.00	2.00	927556	SMI09000208	4.6	986	61	26	8	23	-0.5
MD09-02	24.00	26.00	2.00	927557	SMI09000208	4.25	1217	156	38	12	24	-0.5
MD09-02	26.00	28.00	2.00	927558	SMI09000208	3.95	1487	207	111	9	19	-0.5
MD09-02	28.00	30.00	2.00	927559	SMI09000208	4.95	1188	146	53	10	18	-0.5
MD09-02	30.00	32.00	2.00	927561	SMI09000208	4.32	787	68	17	11	17	-0.5
MD09-02	32.00	34.00	2.00	927562	SMI09000208	4.72	1237	104	36	11	20	-0.5
MD09-02	34.00	36.00	2.00	927563	SMI09000208	4.89	1800	183	46	9	16	-0.5
MD09-02	36.00	38.00	2.00	927564	SMI09000208	4.67	1828	117	96	13	19	-0.5
MD09-02	38.00	40.00	2.00	927565	SMI09000208	4.45	3042	204	31	8	24	0.9
MD09-02	40.00	42.00	2.00	927566	SMI09000208	3.55	3108	179	18	7	26	1.1
MD09-02	42.00	44.00	2.00	927567	SMI09000208	5.76	2050	125	23	5	24	0.8
MD09-02	44.00	46.00	2.00	927568	SMI09000208	2.26	830	50	42	8	12	-0.5
MD09-02	46.00	48.00	2.00	927569	SMI09000208	4.13	720	112	39	11	17	-0.5
MD09-02	48.00	50.00	2.00	927571	SMI09000208	5.3	723	49	76	9	15	-0.5
MD09-02	50.00	52.00	2.00	927572	SMI09000208	4.73	854	93	108	9	14	0.7
MD09-02	52.00	54.00	2.00	927573	SMI09000208	4.56	1172	115	66	9	12	1.0
MD09-02	54.00	56.00	2.00	927574	SMI09000208	4.85	1346	82	56	-5	19	1.3
MD09-02	56.00	58.00	2.00	927575	SMI09000208	6.99	1670	128	21	11	25	1.7
MD09-02	58.00	60.00	2.00	927576	SMI09000208	4.87	1217	83	7	5	30	0.6
MD09-02	60.00	62.00	2.00	927577	SMI09000208	5.16	2305	225	153	12	18	1.5
MD09-02	62.00	64.00	2.00	927578	SMI09000208	4.22	1959	172	175	6	17	1.3
MD09-02	64.00	66.00	2.00	927579	SMI09000208	4.89	1092	87	20	11	30	0.6
MD09-02	66.00	68.00	2.00	927582	SMI09000208	4.57	969	54	26	10	19	0.8
MD09-02	68.00	70.00	2.00	927583	SMI09000208	5.13	1143	66	15	9	21	0.5
MD09-02	70.00	72.00	2.00	927584	SMI09000208	3.89	1657	124	33	8	28	1.4
MD09-02	72.00	74.00	2.00	927585	SMI09000208	4.69	1601	154	23	11	20	1.0
MD09-02	74.00	76.00	2.00	927586	SMI09000208	4.82	1780	164	14	8	17	1.6
MD09-02	76.00	78.00	2.00	927587	SMI09000208	4.61	1517	123	21	7	17	0.9
MD09-02	78.00	80.00	2.00	927588	SMI09000208	4.62	1672	211	20	8	12	0.6
MD09-02	80.00	82.00	2.00	927589	SMI09000208	4.41	1012	88	46	8	21	0.7
MD09-02	82.00	84.00	2.00	927591	SMI09000208	4.25	1799	125	26	6	22	0.6

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-02	84.00	86.00	2.00	927592	SMI09000208	5.36	666	71	19	13	24	-0.5
MD09-02	86.00	88.00	2.00	927593	SMI09000208	4.46	1409	102	28	9	17	1.0
MD09-02	88.00	90.00	2.00	927594	SMI09000208	4.75	1327	96	28	12	16	-0.5
MD09-02	90.00	92.00	2.00	927595	SMI09000208	5.19	1034	84	34	10	19	0.5
MD09-02	92.00	94.00	2.00	927596	SMI09000208	4.97	1135	115	27	7	40	-0.5
MD09-02	94.00	96.00	2.00	927597	SMI09000208	5.09	1163	163	23	10	170	0.6
MD09-02	96.00	98.00	2.00	927598	SMI09000208	4.98	1094	110	12	12	19	1.0
MD09-02	98.00	100.00	2.00	927599	SMI09000208	4.52	1696	178	26	10	17	1.5
MD09-02	100.00	102.00	2.00	927601	SMI09000208	4.86	2259	252	15	9	84	1.1
MD09-02	102.00	104.00	2.00	927602	SMI09000208	4.37	2586	265	20	6	34	1.0
MD09-02	104.00	106.00	2.00	927603	SMI09000208	5.34	2420	229	7	7	31	1.1
MD09-02	106.00	108.00	2.00	927604	SMI09000208	5.39	2274	210	9	-5	32	1.0
MD09-02	108.00	110.00	2.00	927605	SMI09000208	5.2	1547	149	18	6	17	1.2
MD09-02	110.00	112.00	2.00	927606	SMI09000208	4.71	1705	144	15	5	14	0.9
MD09-02	112.00	114.00	2.00	927607	SMI09000208	5.09	1668	187	17	8	13	0.8
MD09-02	114.00	116.00	2.00	927608	SMI09000208	4.35	2853	197	7	5	23	1.6
MD09-02	116.00	118.00	2.00	927609	SMI09000208	4.37	2541	163	12	5	21	1.4
MD09-02	118.00	120.00	2.00	927612	SMI09000208	4.59	1688	134	6	-5	18	1.0
MD09-02	120.00	122.00	2.00	927613	SMI09000208	5.08	1960	208	17	7	23	0.9
MD09-02	122.00	124.00	2.00	927614	SMI09000208	4.73	1703	153	4	5	30	0.7
MD09-02	124.00	126.00	2.00	927615	SMI09000208	4.64	1645	146	7	9	27	0.7
MD09-02	126.00	128.00	2.00	927616	SMI09000208	4.28	1422	139	14	13	27	0.5
MD09-02	128.00	130.00	2.00	927617	SMI09000208	4.34	1650	177	10	10	20	0.7
MD09-02	130.00	131.04	1.04	927618	SMI09000208	2.57	1346	124	18	8	21	1.0
MD09-02	131.04	133.00	1.96	927619	SMI09000208	5.45	2106	150	10	9	24	1.0
MD09-02	133.00	135.00	2.00	927621	SMI09000208	4.44	1985	102	8	-5	31	1.1
MD09-02	135.00	136.40	1.40	927622	SMI09000208	3.32	1297	105	6	6	25	0.5
MD09-02	136.40	138.00	1.60	927623	SMI09000208	3.62	2435	167	5	-5	34	1.1
MD09-02	138.00	140.00	2.00	927624	SMI09000208	4.85	2041	144	8	9	29	1.0
MD09-02	140.00	142.00	2.00	927625	SMI09000208	4.25	1710	146	11	7	26	1.0
MD09-02	142.00	144.00	2.00	927626	SMI09000208	4.9	1680	151	5	8	26	0.8
MD09-02	144.00	146.00	2.00	927627	SMI09000208	4.27	1247	95	6	-5	22	0.8
MD09-02	146.00	147.44	1.44	927628	SMI09000208	3.35	1409	87	5	6	32	0.6
MD09-02	147.44	149.00	1.56	927629	SMI09000208	3.96	320	29	5	9	24	-0.5
MD09-02	149.00	151.00	2.00	927631	SMI09000208	4.39	907	43	6	10	30	-0.5
MD09-02	151.00	153.00	2.00	927632	SMI09000208	5.28	1657	74	14	8	32	1.2
MD09-02	153.00	155.00	2.00	927633	SMI09000208	4.66	225	20	28	7	25	-0.5
MD09-02	155.00	157.00	2.00	927634	SMI09000208	4.57	256	18	14	7	26	-0.5
MD09-02	157.00	158.75	1.75	927635	SMI09000208	4.14	181	13	8	15	26	-0.5
MD09-02	158.75	160.00	1.25	927636	SMI09000208	2.77	1016	79	48	13	32	0.9
MD09-02	160.00	161.00	1.00	927637	SMI09000208	2.19	1340	86	51	12	25	0.8
MD09-02	161.00	162.68	1.68	927638	SMI09000208	4.1	1375	136	56	14	26	0.7
MD09-02	162.68	164.00	1.32	927639	SMI09000208	3.24	1123	121	20	16	23	0.8
MD09-02	164.00	166.00	2.00	927642	SMI09000208	5.13	817	90	11	11	23	-0.5
MD09-02	166.00	168.30	2.30	927643	SMI09000208	6.15	543	87	18	14	20	-0.5
MD09-02	168.30	170.00	1.70	927644	SMI09000208	3.84	829	112	15	14	21	0.6
MD09-02	170.00	171.45	1.45	927645	SMI09000208	3.54	1098	121	20	14	22	0.7
MD09-02	171.45	173.00	1.55	927646	SMI09000208	3.94	654	113	15	16	18	0.5
MD09-02	173.00	175.00	2.00	927647	SMI09000208	4.89	443	108	21	15	14	-0.5
MD09-02	175.00	177.00	2.00	927648	SMI09000208	4.94	537	70	22	12	14	-0.5
MD09-02	177.00	179.00	2.00	927649	SMI09000208	4.81	884	102	7	12	17	0.5
MD09-02	179.00	181.00	2.00	927651	SMI09000208	5.3	792	148	17	12	18	0.7
MD09-02	181.00	183.00	2.00	927652	SMI09000208	4.78	490	124	25	16	13	-0.5
MD09-02	183.00	185.00	2.00	927653	SMI09000208	5.27	668	225	13	27	17	0.9
MD09-02	185.00	187.30	2.30	927654	SMI09000208	5.53	996	97	41	16	16	0.7
MD09-02	187.30	189.00	1.70	927655	SMI09000208	4.15	121	40	3	18	30	-0.5
MD09-02	189.00	191.00	2.00	927654	SMI09000208	4.79	200	41	7	12	23	-0.5
MD09-02	191.00	193.00	2.00	927657	SMI09000208	4.63	202	53	4	13	28	-0.5
MD09-02	193.00	195.00	2.00	927658	SMI09000208	4.42	192	48	5	14	21	-0.5
MD09-02	195.00	197.00	2.00	927659	SMI09000208	5.07	788	117	6	18	24	-0.5
MD09-02	197.00	198.00	1.00	927661	SMI09000208	2.54	899	145	12	15	29	-0.5
MD09-02	198.00	199.50	1.50	927662	SMI09000208	3.56	918	79	6	14	28	0.6
MD09-02	199.50	201.00	1.50	927663	SMI09000208	3.66	960	568	7	14	26	0.9
MD09-02	201.00	203.00	2.00	927664	SMI09000208	5.28	1064	81	15	12	23	0.8
MD09-02	203.00	204.00	1.00	927665	SMI09000208	2.37	1257	189	17	13	18	1.1
MD09-02	204.00	205.90	1.90	927666	SMI09000208	4.31	1336	176	15	12	19	1.2
MD09-02	205.90	207.80	1.90	927667	SMI09000208	5.07	688	257	34	31	28	2.2
MD09-02	207.80	209.00	1.20	927668	SMI09000208	4.8	952	140	17	14	23	0.9
MD09-02	209.00	210.80	1.80	927669	SMI09000208	4	1271	152	32	11	20	1.0
MD09-02	210.80	212.00	1.20	927672	SMI09000208	2.86	229	43	9	8	21	-0.5

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-02	212.00	214.00	2.00	927673	SMI09000208	4.78	129	46	12	9	27	-0.5
MD09-02	214.00	215.90	1.90	927674	SMI09000208	4.57	142	37	4	10	19	-0.5
MD09-02	215.90	218.00	2.10	927675	SMI09000208	4.95	828	165	14	11	24	0.7
MD09-02	218.00	220.00	2.00	927676	SMI09000208	4.91	911	131	19	9	27	-0.5
MD09-02	220.00	222.00	2.00	927677	SMI09000208	4.55	910	112	15	11	24	-0.5
MD09-02	222.00	224.00	2.00	927678	SMI09000208	5.19	1428	124	9	10	23	-0.5
MD09-02	224.00	226.00	2.00	927679	SMI09000208	4.74	1010	84	22	13	23	-0.5
MD09-02	226.00	228.00	2.00	927681	SMI09000208	5.01	769	109	14	9	19	-0.5
MD09-02	228.00	230.00	2.00	927682	SMI09000208	5.5	1183	223	73	11	17	-0.5
MD09-02	230.00	232.00	2.00	927683	SMI09000208	4.78	1199	200	92	11	20	-0.5
MD09-02	232.00	234.00	2.00	927684	SMI09000208	4.66	708	96	15	12	23	-0.5
MD09-02	234.00	236.00	2.00	927685	SMI09000208	4.79	1244	110	19	11	22	-0.5
MD09-02	236.00	238.00	2.00	927686	SMI09000208	5.05	868	92	19	11	28	0.6
MD09-02	238.00	240.00	2.00	927687	SMI09000208	4.54	826	121	18	14	37	-0.5
MD09-02	240.00	242.00	2.00	927688	SMI09000208	4.43	715	70	17	14	31	-0.5
MD09-02	242.00	244.00	2.00	927689	SMI09000208	4.6	870	108	17	12	29	0.6
MD09-02	244.00	245.25	1.25	927691	SMI09000208	3.17	743	66	28	11	31	-0.5
MD09-02	245.25	247.00	1.75	927692	SMI09000208	4.48	636	84	43	14	28	-0.5
MD09-02	247.00	248.90	1.90	927693	SMI09000208	4.42	612	55	26	9	23	-0.5
MD09-02	248.90	249.50	0.60	927694	SMI09000208	1.67	2318	226	24	11	45	1.0
MD09-02	249.50	251.00	1.50	927695	SMI09000208	4.11	767	94	21	10	24	0.5
MD09-02	251.00	253.00	2.00	927696	SMI09000208	4.79	731	111	21	9	20	-0.5
MD09-02	253.00	255.00	2.00	927697	SMI09000208	4.83	860	660	28	8	16	-0.5
MD09-02	255.00	257.00	2.00	927698	SMI09000208	5.06	913	234	28	11	15	-0.5
MD09-02	257.00	259.00	2.00	927699	SMI09000208	4.74	708	112	11	9	17	-0.5
MD09-02	258.99	261.00	2.01	927702	SMI09000208	4.56	573	127	10	8	17	-0.5
MD09-02	261.00	263.00	2.00	927703	SMI09000208	4.94	735	121	10	11	21	-0.5
MD09-02	263.00	265.00	2.00	927704	SMI09000208	5.23	628	81	12	10	21	-0.5
MD09-02	265.00	267.00	2.00	927705	SMI09000208	4.78	914	126	9	7	24	-0.5
MD09-02	267.00	269.00	2.00	927706	SMI09000208	4.85	888	88	60	5	22	-0.5
MD09-02	269.00	271.00	2.00	927707	SMI09000208	4.95	633	86	11	-5	24	-0.5
MD09-02	271.00	273.00	2.00	927708	SMI09000208	5	818	66	22	6	23	-0.5
MD09-02	273.00	275.00	2.00	927709	SMI09000208	4.97	882	141	99	-5	21	-0.5
MD09-02	275.00	277.00	2.00	927711	SMI09000208	4.8	596	84	37	10	27	-0.5
MD09-02	277.00	279.00	2.00	927712	SMI09000208	4.76	592	73	18	18	26	-0.5
MD09-02	279.00	281.00	2.00	927713	SMI09000208	5.54	747	110	22	8	22	-0.5
MD09-02	281.00	283.00	2.00	927714	SMI09000208	4.18	512	78	11	10	21	-0.5
MD09-02	283.00	285.00	2.00	927715	SMI09000208	4.32	869	151	26	7	24	-0.5
MD09-02	285.00	287.00	2.00	927716	SMI09000208	5.56	2721	425	78	6	28	1.7
MD09-02	287.00	289.00	2.00	927717	SMI09000208	5.39	1100	136	49	10	17	-0.5
MD09-02	289.00	291.00	2.00	927718	SMI09000208	5.17	1566	182	53	10	23	0.9
MD09-02	291.00	293.00	2.00	927719	SMI09000208	5.07	368	47	14	-5	18	-0.5
MD09-02	293.00	295.00	2.00	927721	SMI09000208	4.92	554	60	34	-5	21	-0.5
MD09-02	295.00	297.00	2.00	927722	SMI09000208	4.98	367	50	22	-5	19	-0.5
MD09-02	297.00	299.00	2.00	927723	SMI09000208	5.05	1353	395	24	-5	21	0.6
MD09-02	299.00	301.00	2.00	927724	SMI09000208	4.99	1097	1429	37	-5	21	0.5
MD09-02	301.00	301.75	0.75	927725	SMI09000208	2.08	574	109	25	-5	21	-0.5
MD09-02	301.75	303.00	1.25	927726	SMI09000208	3.1	606	118	255	-5	25	-0.5
MD09-02	303.00	304.50	1.50	927727	SMI09000208	3.96	362	78	39	-5	23	-0.5
MD09-02	304.50	306.00	1.50	927728	SMI09000208	3.68	348	104	108	-5	18	-0.5
MD09-02	306.00	307.00	1.00	927729	SMI09000208	2.47	224	81	12	-5	19	-0.5
MD09-02	307.00	309.00	2.00	927732	SMI09000208	4.78	520	114	49	9	18	-0.5
MD09-02	309.00	311.00	2.00	927733	SMI09000208	5.24	191	52	31	10	17	-0.5
MD09-02	311.00	313.00	2.00	927734	SMI09000208	4.86	205	63	27	5	18	-0.5
MD09-02	313.00	315.00	2.00	927735	SMI09000208	4.87	191	91	43	-5	15	-0.5
MD09-02	315.00	317.00	2.00	927736	SMI09000208	5.29	223	85	8	5	13	-0.5
MD09-02	317.00	319.00	2.00	927737	SMI09000208	4.7	186	67	18	6	12	-0.5
MD09-02	319.00	321.00	2.00	927738	SMI09000208	5.46	107	61	19	-5	14	-0.5
MD09-02	321.00	323.00	2.00	927739	SMI09000208	5.19	123	72	6	-5	15	-0.5
MD09-02	323.00	325.00	2.00	927741	SMI09000208	5.37	251	34	32	8	11	0.6
MD09-02	325.00	325.70	0.70	927742	SMI09000208	1.82	338	66	48	6	10	-0.5
MD09-02	325.70	326.81	1.11	927743	SMI09000208	2.84	127	53	17	7	9	-0.5
MD09-02	326.81	328.00	1.19	927744	SMI09000208	2.24	161	24	4	-5	5	-0.5
MD09-02	328.00	330.00	2.00	927745	SMI09000208	5.18	373	75	36	8	9	0.6
MD09-02	330.00	331.65	1.65	927746	SMI09000208	4.39	595	107	52	8	7	0.8
MD09-02	331.65	332.52	0.87	927747	SMI09000208	2.22	378	34	13	12	10	0.6
MD09-02	332.62	334.50	1.88	927748	SMI09000208	4.71	44	4	-2	8	60	-0.5
MD09-02	334.50	336.50	2.00	927749	SMI09000208	5.08	36	3	-2	-5	57	-0.5
MD09-03	7.32	9.53	2.21	927751	SMI09000209	3.47	246	35	38	11	61	-0.5
MD09-03	9.53	12.26	2.73	927752	SMI09000209	5.06	338	43	80	14	64	-0.5

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-03	12.26	14.75	2.49	927753	SMI09000209	5.18	222	39	81	13	73	-0.5
MD09-03	14.75	16.00	1.25	927754	SMI09000209	2.7	179	59	82	13	63	-0.5
MD09-03	16.00	18.00	2.00	927755	SMI09000209	4.1	221	51	357	10	59	-0.5
MD09-03	18.00	20.00	2.00	927756	SMI09000209	4.88	1138	292	209	9	89	0.6
MD09-03	20.00	21.00	1.00	927757	SMI09000209	2.63	205	50	73	11	51	-0.5
MD09-03	21.00	23.00	2.00	927758	SMI09000209	4.75	93	22	64	9	54	-0.5
MD09-03	23.00	24.35	1.35	927759	SMI09000209	3.18	364	30	90	11	44	-0.5
MD09-03	24.35	26.10	1.75	927762	SMI09000209	4.31	545	160	14	12	22	0.7
MD09-03	26.10	28.00	1.90	927763	SMI09000209	4.3	907	214	7	15	36	1.0
MD09-03	28.00	30.00	2.00	927764	SMI09000209	3.87	659	206	14	16	29	0.8
MD09-03	30.00	32.00	2.00	927765	SMI09000209	4.86	305	249	9	16	29	-0.5
MD09-03	32.00	34.00	2.00	927766	SMI09000209	4.71	638	321	7	8	19	0.8
MD09-03	34.00	36.00	2.00	927767	SMI09000209	4.66	456	87	3	10	19	0.6
MD09-03	36.00	38.00	2.00	927768	SMI09000209	4.92	624	112	3	7	19	0.8
MD09-03	38.00	40.00	2.00	927769	SMI09000209	4.48	304	52	3	-5	19	-0.5
MD09-03	40.00	42.00	2.00	927771	SMI09000209	4.54	170	44	2	7	14	-0.5
MD09-03	42.00	44.00	2.00	927772	SMI09000209	4.92	952	195	2	-5	17	0.7
MD09-03	44.00	45.00	1.00	927773	SMI09000209	1.85	1193	421	37	-5	17	1.4
MD09-03	45.00	46.00	1.00	927774	SMI09000209	2.85	3312	742	47	46	27	5.3
MD09-03	46.00	48.00	2.00	927775	SMI09000209	4.68	2624	1107	7	15	18	2.5
MD09-03	48.00	50.00	2.00	927776	SMI09000209	4.71	1830	444	4	8	16	1.6
MD09-03	50.00	52.00	2.00	927777	SMI09000209	4.55	1414	584	21	11	19	1.0
MD09-03	52.00	53.00	1.00	927778	SMI09000209	2.51	480	302	30	18	31	-0.5
MD09-03	53.00	55.00	2.00	927779	SMI09000209	4.6	475	125	17	9	14	0.6
MD09-03	55.00	57.00	2.00	927781	SMI09000209	4.47	463	54	25	6	17	-0.5
MD09-03	57.00	59.00	2.00	927782	SMI09000209	5.2	769	147	13	-5	13	0.6
MD09-03	59.00	60.00	1.00	927783	SMI09000209	1.89	348	88	34	7	24	-0.5
MD09-03	60.00	62.00	2.00	927784	SMI09000209	4.88	871	259	52	-5	24	1.0
MD09-03	62.00	64.00	2.00	927785	SMI09000209	4.24	423	77	19	-5	19	-0.5
MD09-03	64.00	66.00	2.00	927786	SMI09000209	5.08	349	181	12	5	13	0.7
MD09-03	66.00	68.00	2.00	927787	SMI09000209	4.72	278	125	14	7	16	0.6
MD09-03	68.00	70.00	2.00	927788	SMI09000209	4.41	544	461	18	5	19	0.9
MD09-03	70.00	72.00	2.00	927789	SMI09000209	4.48	322	211	6	6	22	0.8
MD09-03	72.00	74.00	2.00	927791	SMI09000209	4.44	363	130	5	-5	24	-0.5
MD09-03	74.00	75.11	1.11	927792	SMI09000209	2.7	508	265	9	7	25	0.6
MD09-03	75.11	76.92	1.81	927793	SMI09000209	4.54	45	5	-2	-5	70	-0.5
MD09-03	76.92	79.00	2.08	927794	SMI09000209	4.45	767	170	16	-5	23	0.9
MD09-03	79.00	81.00	2.00	927795	SMI09000209	5.43	1346	299	14	-5	26	1.6
MD09-03	81.00	83.00	2.00	927796	SMI09000209	4.39	602	148	14	24	20	0.8
MD09-03	83.00	85.00	2.00	927797	SMI09000209	4.66	729	134	4	-5	28	1.2
MD09-03	85.00	87.00	2.00	927798	SMI09000209	5.63	689	126	4	6	31	1.0
MD09-03	87.00	89.00	2.00	927799	SMI09000209	4.02	873	281	8	-5	60	1.2
MD09-03	89.00	91.00	2.00	927802	SMI09000209	4.95	1227	158	7	-5	24	1.5
MD09-03	91.00	93.00	2.00	927803	SMI09000209	4.79	888	148	6	-5	25	1.3
MD09-03	93.00	95.00	2.00	927804	SMI09000209	5.05	631	159	8	9	38	1.7
MD09-03	95.00	97.00	2.00	927805	SMI09000209	4.82	410	87	4	5	99	1.6
MD09-03	97.00	99.00	2.00	927806	SMI09000209	4.87	517	81	16	-5	21	0.8
MD09-03	99.00	101.00	2.00	927807	SMI09000209	5.24	133	241	-2	-5	45	-0.5
MD09-03	101.00	103.00	2.00	927808	SMI09000209	4.31	85	7	3	-5	52	-0.5
MD09-03	103.00	105.00	2.00	927809	SMI09000209	5.17	33	4	-2	-5	61	-0.5
MD09-03	105.00	106.17	1.17	927811	SMI09000209	2.51	39	5	-2	-5	57	-0.5
MD09-03	106.17	106.45	0.28	927812	SMI09000209	0.82	284	13	11	30	29	0.8
MD09-03	106.45	108.00	1.55	927813	SMI09000209	3.89	44	4	-2	-5	62	0.6
MD09-03	108.00	110.26	2.26	927814	SMI09000209	5	49	5	-2	8	71	-0.5
MD09-03	110.26	111.00	0.74	927815	SMI09000209	1.83	294	204	10	30	37	3.3
MD09-03	111.00	113.00	2.00	927816	SMI09000209	4.55	554	103	16	6	22	1.2
MD09-03	113.00	115.00	2.00	927817	SMI09000209	4.72	834	211	9	-5	21	1.2
MD09-03	115.00	116.00	1.00	927818	SMI09000209	2.76	407	73	7	-5	23	1.1
MD09-03	116.00	118.00	2.00	927819	SMI09000209	4.89	194	17	-2	-5	14	-0.5
MD09-03	118.00	120.00	2.00	927822	SMI09000209	4.38	390	55	7	6	17	-0.5
MD09-03	120.00	122.24	2.24	927823	SMI09000209	5.01	134	57	4	10	26	-0.5
MD09-03	122.24	124.00	1.76	927824	SMI09000209	4.39	46	40	3	6	24	-0.5
MD09-03	124.00	126.00	2.00	927825	SMI09000209	4.56	29	36	2	7	23	-0.5
MD09-03	126.00	128.00	2.00	927826	SMI09000209	4.98	30	51	2	9	24	-0.5
MD09-03	128.00	130.00	2.00	927827	SMI09000209	5.06	83	32	2	13	30	-0.5
MD09-03	130.00	132.00	2.00	927828	SMI09000209	4.54	34	16	-2	11	34	-0.5
MD09-03	132.00	134.00	2.00	927829	SMI09000209	5.02	37	22	2	8	28	-0.5
MD09-03	134.00	136.00	2.00	927831	SMI09000209	4.87	61	91	-2	-5	28	-0.5
MD09-03	136.00	138.65	2.65	927832	SMI09000209	6.61	52	31	2	7	25	-0.5
MD09-03	138.65	140.75	2.10	927833	SMI09000209	5.31	43	9	-2	6	68	-0.5

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-03	140.75	142.00	1.25	927834	SMI09000209	2.98	20	13	-2	-5	25	-0.5
MD09-03	142.00	144.00	2.00	927835	SMI09000209	5.17	22	69	-2	10	41	-0.5
MD09-03	144.00	146.00	2.00	927836	SMI09000209	4.57	34	37	-2	7	33	-0.5
MD09-03	146.00	148.00	2.00	927837	SMI09000209	5.11	73	65	-2	9	32	-0.5
MD09-03	148.00	150.00	2.00	927838	SMI09000209	4.9	155	33	2	-5	29	-0.5
MD09-03	150.00	152.00	2.00	927839	SMI09000209	3.98	1679	278	6	5	33	1.7
MD09-03	152.00	154.00	2.00	927841	SMI09000209	4.5	437	59	6	6	23	-0.5
MD09-03	154.00	156.00	2.00	927842	SMI09000209	4.91	916	122	7	7	22	1.4
MD09-03	156.00	158.00	2.00	927843	SMI09000209	4.98	778	96	6	9	28	1.0
MD09-03	158.00	160.00	2.00	927844	SMI09000209	4.9	569	185	7	8	20	0.9
MD09-03	160.00	161.00	1.00	927845	SMI09000209	2.46	428	151	5	7	13	0.6
MD09-03	161.00	162.70	1.70	927846	SMI09000209	3.99	993	367	5	-5	24	0.9
MD09-03	162.70	164.00	1.30	927847	SMI09000209	3.67	458	133	20	8	18	-0.5
MD09-03	164.00	166.00	2.00	927848	SMI09000209	5.37	400	100	37	11	12	-0.5
MD09-03	166.00	168.00	2.00	927849	SMI09000209	5.55	837	58	29	-5	12	-0.5
MD09-03	168.00	170.00	2.00	927852	SMI09000209	4.94	869	61	27	7	10	-0.5
MD09-03	170.00	172.00	2.00	927853	SMI09000209	4.94	1097	68	21	10	16	-0.5
MD09-03	172.00	174.00	2.00	927854	SMI09000209	5.25	1295	92	46	-5	21	0.9
MD09-03	174.00	175.00	1.00	927855	SMI09000209	2.68	836	140	23	14	18	0.7
MD09-03	175.00	177.00	2.00	927856	SMI09000209	5.19	859	74	65	19	12	0.8
MD09-03	177.00	179.00	2.00	927857	SMI09000209	4.53	1091	167	51	16	14	1.3
MD09-03	179.00	180.00	1.00	927858	SMI09000209	2.58	520	99	28	28	12	1.4
MD09-03	180.00	182.00	2.00	927859	SMI09000209	5.46	502	116	119	15	8	-0.5
MD09-03	182.00	184.00	2.00	927861	SMI09000209	5.62	657	218	18	12	14	0.6
MD09-03	184.00	185.75	1.75	927862	SMI09000209	4.42	537	211	2	22	13	0.7
MD09-03	185.75	188.00	2.25	927863	SMI09000209	6.01	110	173	10	14	11	-0.5
MD09-03	188.00	189.00	1.00	927864	SMI09000209	2.79	207	567	11	135	161	4.9
MD09-03	189.00	191.00	2.00	927865	SMI09000209	5.17	631	212	20	23	20	-0.5
MD09-03	191.00	192.00	1.00	927866	SMI09000209	2.67	701	484	20	13	16	3.7
MD09-03	192.00	193.00	1.00	927867	SMI09000209	3.16	1336	68	10	13	28	1.5
MD09-03	193.00	195.00	2.00	927868	SMI09000209	4.88	1227	295	37	10	20	1.4
MD09-03	195.00	196.00	1.00	927869	SMI09000209	2.39	556	154	35	8	18	-0.5
MD09-03	196.00	198.00	2.00	927871	SMI09000209	5.14	1273	468	62	6	22	0.7
MD09-03	198.00	200.00	2.00	927872	SMI09000209	4.74	1987	574	53	11	13	1.2
MD09-03	200.00	201.00	1.00	927873	SMI09000209	2.61	1347	442	102	7	13	0.7
MD09-03	201.00	203.00	2.00	927874	SMI09000209	5.18	1327	428	59	17	10	0.6
MD09-03	203.00	205.00	2.00	927875	SMI09000209	4.63	499	245	25	5	14	-0.5
MD09-03	205.00	206.00	1.00	927876	SMI09000209	2.49	428	139	19	10	93	-0.5
MD09-03	206.00	208.00	2.00	927877	SMI09000209	5.73	1392	160	9	26	213	3.7
MD09-03	208.00	210.00	2.00	927878	SMI09000209	4.42	376	119	16	9	73	1.0
MD09-03	210.00	212.00	2.00	927879	SMI09000209	5.4	166	255	7	9	82	-0.5
MD09-03	212.00	214.00	2.00	927882	SMI09000209	5.26	140	108	10	8	106	-0.5
MD09-03	214.00	216.00	2.00	927883	SMI09000209	5	243	152	21	13	54	-0.5
MD09-03	216.00	217.22	1.22	927884	SMI09000209	2.81	329	164	22	12	18	0.5
MD09-03	217.22	219.00	1.78	927885	SMI09000209	4.65	20	77	30	14	24	-0.5
MD09-03	219.00	221.00	2.00	927886	SMI09000209	4.92	189	65	186	9	42	-0.5
MD09-03	221.00	223.00	2.00	927887	SMI09000209	5.1	446	254	145	-5	44	1.2
MD09-03	223.00	225.00	2.00	927888	SMI09000209	5	1027	151	291	21	92	3.0
MD09-03	225.00	227.00	2.00	927889	SMI09000209	5.55	422	66	267	7	104	1.4
MD09-03	227.00	229.15	2.15	927891	SMI09000209	4.63	586	105	103	10	225	1.5
MD09-03	229.15	230.00	0.85	927892	SMI09000209	2.19	221	59	8	15	101	0.5
MD09-03	230.00	232.00	2.00	927893	SMI09000209	5.29	275	50	7	28	175	0.6
MD09-03	232.00	234.00	2.00	927894	SMI09000209	5.01	305	150	43	11	87	0.9
MD09-03	234.00	236.00	2.00	927895	SMI09000209	4.93	246	60	27	10	171	-0.5
MD09-03	236.00	238.00	2.00	927896	SMI09000209	4.63	244	47	10	8	70	-0.5
MD09-03	238.00	240.00	2.00	927897	SMI09000209	5.1	53	74	87	10	177	-0.5
MD09-03	240.00	242.00	2.00	927898	SMI09000209	4.8	225	79	43	12	77	0.7
MD09-03	242.00	243.30	1.30	927899	SMI09000209	3.62	212	58	11	7	42	-0.5
MD09-03	243.30	245.00	1.70	927901	SMI09000209	3.8	42	3	-2	9	82	-0.5
MD09-03	245.00	247.00	2.00	927902	SMI09000209	4.15	50	2	-2	8	74	-0.5
MD09-03	247.00	248.85	1.85	927903	SMI09000209	4.97	168	8	4	5	62	-0.5
MD09-03	248.85	250.00	1.15	927904	SMI09000209	2.73	517	36	103	12	44	0.9
MD09-03	250.00	252.00	2.00	927905	SMI09000209	5.19	342	31	38	8	32	-0.5
MD09-03	252.00	254.00	2.00	927906	SMI09000209	4.94	168	49	23	11	30	-0.5
MD09-03	254.00	254.85	0.85	927907	SMI09000209	2.33	1060	56	193	13	65	1.2
MD09-03	254.85	256.00	1.15	927908	SMI09000209	3.14	424	27	29	5	41	-0.5
MD09-03	256.00	258.00	2.00	927909	SMI09000209	4.62	99	46	60	6	58	-0.5
MD09-03	258.00	260.00	2.00	927912	SMI09000209	5.07	256	18	44	-5	96	-0.5
MD09-03	260.00	262.00	2.00	927913	SMI09000209	4.51	186	18	14	7	23	-0.5
MD09-03	262.00	264.00	2.00	927914	SMI09000209	5.09	197	49	12	-5	31	-0.5

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-03	264.00	265.75	1.75	927915	SMI09000209	4.31	118	16	6	-5	24	-0.5
MD09-03	265.75	266.75	1.00	927916	SMI09000209	2.69	143	53	46	14	30	-0.5
MD09-03	266.75	268.00	1.25	927917	SMI09000209	2.82	382	67	24	87	164	1.3
MD09-03	268.00	269.85	1.85	927918	SMI09000209	4.45	320	28	10	9	25	-0.5
MD09-03	269.85	271.25	1.40	927919	SMI09000209	3.14	57	10	52	-5	23	-0.5
MD09-03	271.25	273.42	2.17	927921	SMI09000209	4.13	43	-2	-2	6	66	-0.5
MD09-03	273.42	275.00	1.58	927922	SMI09000209	3.82	422	30	2	-5	45	0.5
MD09-03	275.00	277.14	2.14	927923	SMI09000209	5.25	101	39	2	8	27	-0.5
MD09-03	277.14	278.75	1.61	927924	SMI09000209	4.53	53	-2	-2	-5	81	-0.5
MD09-03	278.75	280.00	1.25	927925	SMI09000209	3.03	117	26	-2	-5	43	-0.5
MD09-03	280.00	282.00	2.00	927926	SMI09000209	4.88	113	32	4	-5	42	-0.5
MD09-03	282.00	284.00	2.00	927927	SMI09000209	5.16	127	14	-2	-5	39	-0.5
MD09-03	284.00	285.25	1.25	927928	SMI09000209	3.03	406	54	-2	9	45	0.9
MD09-03	285.25	287.00	1.75	927929	SMI09000209	4.11	33	6	-2	-5	67	-0.5
MD09-03	287.00	288.35	1.35	927931	SMI09000209	3.84	31	-2	-2	-5	68	-0.5
MD09-03	288.35	290.00	1.65	927932	SMI09000209	4.38	533	32	8	-5	26	-0.5
MD09-03	290.00	292.00	2.00	927933	SMI09000209	5.21	561	66	8	-5	20	-0.5
MD09-03	292.00	292.70	0.70	927934	SMI09000209	2.02	857	51	25	-5	18	-0.5
MD09-03	292.70	294.70	2.00	927935	SMI09000209	5.15	50	8	-2	-5	66	-0.5
MD09-03	294.70	296.95	2.25	927936	SMI09000209	5.37	53	7	-2	-5	82	-0.5
MD09-03	296.95	299.00	2.05	927937	SMI09000209	5.21	674	120	4	-5	25	-0.5
MD09-03	299.00	301.00	2.00	927938	SMI09000209	5.02	882	155	7	-5	19	-0.5
MD09-03	301.00	303.00	2.00	927939	SMI09000209	5.07	1925	300	9	-5	19	-0.5
MD09-03	303.00	305.00	2.00	927942	SMI09000209	5.23	1831	262	10	-5	27	-0.5
MD09-03	305.00	307.00	2.00	927943	SMI09000209	5.06	1118	126	13	-5	28	0.7
MD09-03	307.00	309.00	2.00	927944	SMI09000209	3.78	691	68	13	-5	16	-0.5
MD09-03	309.00	311.00	2.00	927945	SMI09000209	5.2	612	93	11	-5	18	-0.5
MD09-03	311.00	313.19	2.19	927946	SMI09000209	3.22	556	74	15	-5	31	-0.5
MD09-03	313.19	314.85	1.66	927947	SMI09000209	3.88	529	112	9	-5	15	-0.5
MD09-03	314.85	316.00	1.15	927948	SMI09000209	2.9	1035	83	6	-5	36	-0.5
MD09-03	316.00	318.00	2.00	927949	SMI09000209	5.11	878	75	6	-5	32	1.0
MD09-03	318.00	320.00	2.00	927951	SMI09000214	4.97	612	88	10	7	19	-0.5
MD09-03	320.00	321.46	1.46	927952	SMI09000214	3.91	464	63	4	8	14	-0.5
MD09-03	321.46	322.48	1.02	927953	SMI09000214	2.31	88	16	-2	6	13	-0.5
MD09-03	322.48	324.00	1.52	927954	SMI09000214	3.21	101	17	2	10	16	-0.5
MD09-03	324.00	326.00	2.00	927955	SMI09000214	4.57	178	33	-2	7	17	-0.5
MD09-03	326.00	328.00	2.00	927956	SMI09000214	4.79	162	37	-2	9	14	-0.5
MD09-03	328.00	330.00	2.00	927957	SMI09000214	4.94	141	47	-2	9	16	-0.5
MD09-03	330.00	332.08	2.08	927958	SMI09000214	5.22	564	105	3	9	21	-0.5
MD09-03	332.08	332.51	0.43	927959	SMI09000214	1.19	43	-2	-2	-5	69	-0.5
MD09-03	332.51	334.00	1.49	927961	SMI09000214	3.43	229	26	10	6	18	-0.5
MD09-03	334.00	336.00	2.00	927962	SMI09000214	5.37	704	48	14	7	11	-0.5
MD09-03	336.00	338.00	2.00	927963	SMI09000214	5.65	593	73	39	7	12	-0.5
MD09-03	338.00	340.00	2.00	927964	SMI09000214	5.57	671	128	61	7	8	-0.5
MD09-03	340.00	342.00	2.00	927965	SMI09000214	4.81	302	47	63	6	10	-0.5
MD09-03	342.00	343.82	1.82	927966	SMI09000214	4.43	493	37	19	-5	10	-0.5
MD09-04	19.52	22.55	3.03	927967	SMI09000214	3.74	1256	126	13	6	17	0.8
MD09-04	22.55	24.00	1.45	927968	SMI09000214	6.08	1639	136	12	8	17	1.3
MD09-04	24.00	26.00	2.00	927969	SMI09000214	5.4	1511	141	11	20	24	1.4
MD09-04	26.00	28.00	2.00	927972	SMI09000214	4.72	796	53	5	6	20	-0.5
MD09-04	28.00	30.00	2.00	927973	SMI09000214	5.23	825	55	23	-5	20	-0.5
MD09-04	30.00	32.00	2.00	927974	SMI09000214	4.18	599	63	11	6	26	-0.5
MD09-04	32.00	33.00	1.00	927975	SMI09000214	2.59	686	60	11	6	26	-0.5
MD09-04	33.00	35.00	2.00	927976	SMI09000214	5.59	837	86	11	15	37	4.2
MD09-04	35.00	37.00	2.00	927977	SMI09000214	4.67	775	76	72	14	19	-0.5
MD09-04	37.00	39.00	2.00	927978	SMI09000214	4.7	772	67	62	8	18	-0.5
MD09-04	39.00	41.00	2.00	927979	SMI09000214	4.75	894	103	62	10	18	-0.5
MD09-04	41.00	43.00	2.00	927981	SMI09000214	4.29	1657	167	29	10	22	-0.5
MD09-04	43.00	45.00	2.00	927982	SMI09000214	4.6	824	75	29	9	30	-0.5
MD09-04	45.00	47.00	2.00	927983	SMI09000214	4.15	1041	104	22	8	17	-0.5
MD09-04	47.00	49.00	2.00	927984	SMI09000214	4.27	1428	93	15	12	222	-0.5
MD09-04	49.00	50.00	1.00	927985	SMI09000214	2	1509	143	7	13	26	-0.5
MD09-04	50.00	52.00	2.00	927986	SMI09000214	4.32	955	88	33	10	25	-0.5
MD09-04	52.00	54.00	2.00	927987	SMI09000214	4.56	1204	105	18	-5	20	-0.5
MD09-04	54.00	56.00	2.00	927988	SMI09000214	4.63	903	70	23	12	26	-0.5
MD09-04	56.00	58.35	2.35	927989	SMI09000214	5.64	873	64	8	7	27	-0.5
MD09-04	58.35	60.35	2.00	927991	SMI09000214	4.55	424	35	9	-5	109	1.0
MD09-04	60.35	62.00	1.65	927992	SMI09000214	4.15	805	58	11	10	22	0.6
MD09-04	62.00	64.00	2.00	927993	SMI09000214	4.68	955	68	18	7	24	0.7
MD09-04	64.00	65.00	1.00	927994	SMI09000214	2.38	734	36	16	8	27	0.6

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppm	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-04	65.00	66.00	1.00	927995	SMI09000214	2.33	902	41	52	7	22	0.8
MD09-04	66.00	68.00	2.00	927996	SMI09000214	4.45	857	73	9	10	29	-0.5
MD09-04	68.00	70.00	2.00	927997	SMI09000214	4.96	1210	99	5	9	23	0.7
MD09-04	70.00	72.00	2.00	927998	SMI09000214	5.08	893	108	34	11	24	0.7
MD09-04	72.00	74.00	2.00	927999	SMI09000214	4.79	1644	147	4	9	26	0.7
MD09-04	74.00	76.00	2.00	928002	SMI09000214	5.07	1512	164	17	10	30	0.6
MD09-04	76.00	78.00	2.00	928003	SMI09000214	4.22	1138	144	3	16	34	1.2
MD09-04	78.00	80.00	2.00	928004	SMI09000214	3.97	1819	531	5	28	38	2.8
MD09-04	80.00	82.00	2.00	928005	SMI09000214	4.69	1421	182	3	9	26	2.0
MD09-04	82.00	84.00	2.00	928006	SMI09000214	5.22	600	105	2	13	35	0.7
MD09-04	84.00	86.00	2.00	928007	SMI09000214	4.7	796	96	3	8	28	0.7
MD09-04	86.00	88.00	2.00	928008	SMI09000214	4.87	590	73	2	9	29	-0.5
MD09-04	88.00	90.00	2.00	928009	SMI09000214	4.87	818	115	-2	15	38	0.7
MD09-04	90.00	92.00	2.00	928011	SMI09000214	4.29	708	128	-2	10	41	-0.5
MD09-04	92.00	94.00	2.00	928012	SMI09000214	5.13	1014	169	2	16	37	1.1
MD09-04	94.00	96.00	2.00	928013	SMI09000214	5.14	350	55	-2	13	85	-0.5
MD09-04	96.00	98.00	2.00	928014	SMI09000214	5.08	491	62	-2	13	45	-0.5
MD09-04	98.00	100.00	2.00	928015	SMI09000214	4.95	492	57	-2	13	41	0.6
MD09-04	100.00	102.00	2.00	928016	SMI09000214	5.35	338	48	-2	11	38	-0.5
MD09-04	102.00	104.00	2.00	928017	SMI09000214	4.58	710	225	2	10	89	0.6
MD09-04	104.00	106.00	2.00	928018	SMI09000214	4.95	488	76	2	8	50	0.7
MD09-04	106.00	108.00	2.00	928019	SMI09000214	4.72	405	64	-2	16	33	-0.5
MD09-04	108.00	110.00	2.00	928021	SMI09000214	4.74	445	72	-2	9	30	-0.5
MD09-04	110.00	112.00	2.00	928022	SMI09000214	3.95	253	90	-2	19	31	-0.5
MD09-04	112.00	113.40	1.40	928023	SMI09000214	4.03	363	48	4	14	42	-0.5
MD09-04	113.40	115.29	1.89	928024	SMI09000214	4.7	170	40	3	10	34	-0.5
MD09-04	115.29	117.00	1.71	928025	SMI09000214	4.23	322	53	-2	12	31	-0.5
MD09-04	117.00	119.00	2.00	928026	SMI09000214	4.82	130	57	2	13	32	-0.5
MD09-04	119.00	121.00	2.00	928027	SMI09000214	4.66	120	37	-2	13	44	-0.5
MD09-04	121.00	123.00	2.00	928028	SMI09000214	4.83	114	24	-2	14	39	-0.5
MD09-04	123.00	125.00	2.00	927029	SMI09000214	4.83	276	67	4	9	31	-0.5
MD09-04	125.00	127.00	2.00	928032	SMI09000214	4.69	290	55	-2	14	33	-0.5
MD09-04	127.00	129.00	2.00	928033	SMI09000214	5.21	115	24	-2	7	29	-0.5
MD09-04	129.00	131.00	2.00	928034	SMI09000214	3.87	110	37	-2	12	33	-0.5
MD09-04	131.00	133.00	2.00	928035	SMI09000214	4.66	130	66	3	9	34	-0.5
MD09-04	133.00	135.00	2.00	928036	SMI09000214	4.94	203	20	-2	12	32	-0.5
MD09-04	135.00	137.00	2.00	928037	SMI09000214	4.94	184	13	3	13	26	-0.5
MD09-04	137.00	139.00	2.00	928038	SMI09000214	5.11	274	42	2	13	31	-0.5
MD09-04	139.00	141.00	2.00	928039	SMI09000214	5.23	515	90	2	14	46	-0.5
MD09-04	141.00	143.00	2.00	928041	SMI09000214	3.86	470	142	3	13	48	-0.5
MD09-04	143.00	145.00	2.00	928042	SMI09000214	5.35	314	64	2	13	34	-0.5
MD09-04	145.00	147.00	2.00	928043	SMI09000214	5.03	273	64	3	15	38	-0.5
MD09-04	147.00	149.00	2.00	928044	SMI09000214	4.29	268	45	3	15	38	-0.5
MD09-04	149.00	151.00	2.00	928045	SMI09000214	5.01	41	15	-2	10	15	-0.5
MD09-04	151.00	153.00	2.00	928046	SMI09000214	4.76	46	16	2	8	17	-0.5
MD09-04	153.00	153.80	0.80	928047	SMI09000214	1.76	60	9	-2	9	30	-0.5
MD09-04	153.80	155.08	1.28	928048	SMI09000214	5	162	32	3	16	37	-0.5
MD09-04	155.80	158.00	2.20	928049	SMI09000214	5.17	70	21	2	13	26	-0.5
MD09-04	158.00	160.00	2.00	928051	SMI09000214	4.72	312	54	3	15	41	-0.5
MD09-04	160.00	162.00	2.00	928052	SMI09000214	4.86	237	21	3	11	33	-0.5
MD09-04	162.00	164.00	2.00	928053	SMI09000214	5.23	118	26	3	15	28	-0.5
MD09-04	164.00	166.25	2.25	928054	SMI09000214	5.26	165	26	3	-5	28	-0.5
MD09-04	166.25	168.25	2.00	928055	SMI09000214	4.75	99	22	-2	5	56	-0.5
MD09-04	168.25	170.23	1.98	928056	SMI09000214	3.71	115	24	-2	-5	47	-0.5
MD09-04	170.23	172.00	1.77	928057	SMI09000214	5.81	221	36	-2	5	27	-0.5
MD09-04	172.00	174.00	2.00	928058	SMI09000214	4.88	132	41	-2	15	28	-0.5
MD09-04	174.00	174.20	0.20	928059	SMI09000214	3.38	149	13	-2	10	29	-0.5
MD09-04	175.20	177.00	1.80	928062	SMI09000214	5.1	85	12	-2	-5	72	-0.5
MD09-04	177.00	179.00	2.00	928063	SMI09000214	5.21	86	84	-2	7	72	-0.5
MD09-04	179.00	181.00	2.00	928064	SMI09000214	5.25	124	21	-2	7	57	-0.5
MD09-04	181.00	183.00	2.00	928065	SMI09000214	4.05	156	36	-2	10	57	1.0
MD09-04	183.00	184.00	1.00	928066	SMI09000214	1.77	139	63	-2	59	172	2.0
MD09-04	184.00	186.00	2.00	928067	SMI09000214	6.03	397	100	3	-5	36	-0.5
MD09-04	186.00	188.00	2.00	928068	SMI09000214	4.5	507	129	2	-5	31	-0.5
MD09-04	188.00	190.00	2.00	928069	SMI09000214	4.59	1247	307	3	-5	46	1.0
MD09-04	190.00	192.00	2.00	928071	SMI09000214	5.6	142	53	3	-5	37	-0.5
MD09-04	192.00	194.00	2.00	928072	SMI09000214	4.5	70	27	-2	-5	52	-0.5
MD09-04	194.00	195.15	1.15	928073	SMI09000214	3	59	18	-2	5	61	-0.5
MD09-04	195.15	197.00	1.85	928074	SMI09000214	4.24	73	10	-2	-5	20	-0.5
MD09-04	197.00	199.00	2.00	928075	SMI09000214	4.76	164	32	4	-5	17	-0.5

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-04	199.00	201.00	2.00	928076	SMI09000214	4.48	38	20	3	-5	23	-0.5
MD09-04	201.00	203.00	2.00	928077	SMI09000214	5.31	48	9	2	-5	32	-0.5
MD09-04	203.00	205.00	2.00	928078	SMI09000214	3.67	103	34	4	7	34	-0.5
MD09-04	205.00	205.75	0.75	928079	SMI09000214	1.41	37	16	3	10	54	-0.5
MD09-04	205.75	207.00	1.25	928081	SMI09000214	3.04	31	39	4	66	185	-0.5
MD09-04	207.00	209.00	2.00	928082	SMI09000214	4.17	30	19	3	-5	38	-0.5
MD09-04	209.00	210.00	1.00	928083	SMI09000214	3.26	45	17	3	-5	36	-0.5
MD09-04	210.00	212.00	2.00	928084	SMI09000214	4.87	132	14	2	-5	38	-0.5
MD09-04	212.00	213.00	1.00	928085	SMI09000214	2.27	52	10	2	6	29	-0.5
MD09-04	213.00	215.00	2.00	928086	SMI09000214	4.88	20	6	2	-5	21	-0.5
MD09-04	215.00	217.00	2.00	928087	SMI09000214	5.52	61	8	2	-5	42	-0.5
MD09-04	217.00	219.00	2.00	928088	SMI09000214	4.89	34	18	2	5	36	-0.5
MD09-04	219.00	221.00	2.00	928089	SMI09000214	4.79	64	9	3	13	31	-0.5
MD09-04	221.00	223.00	2.00	928092	SMI09000214	4.19	76	7	3	12	33	-0.5
MD09-04	223.00	225.00	2.00	928093	SMI09000214	4.77	36	19	-2	9	37	-0.5
MD09-04	225.00	227.00	2.00	928094	SMI09000214	4.43	171	14	3	13	39	-0.5
MD09-04	227.00	227.60	0.60	928095	SMI09000214	1.3	91	9	-2	10	33	-0.5
MD09-04	227.60	229.00	1.40	928096	SMI09000214	3.02	23	6	-2	28	42	0.5
MD09-04	229.00	230.15	1.15	928097	SMI09000214	3.36	30	6	-2	-5	17	-0.5
MD09-04	230.15	231.00	0.85	928098	SMI09000214	1.26	65	8	-2	7	26	-0.5
MD09-04	231.00	232.72	1.72	928099	SMI09000214	2.82	44	10	3	9	24	-0.5
MD09-05	9.15	11.59	2.44	928301	SMI09000216	2.53	2352	237	5	7	56	1.1
MD09-05	11.59	14.04	2.45	928302	SMI09000216	1.3	621	204	5	8	32	1.0
MD09-05	14.04	16.00	1.96	928303	SMI09000216	2.8	706	136	3	9	34	0.6
MD09-05	16.00	17.69	1.69	928304	SMI09000216	2.87	1073	218	7	10	40	0.9
MD09-05	17.69	20.74	3.05	928305	SMI09000216	2.2	454	64	3	9	31	0.5
MD09-05	20.74	22.00	1.26	928306	SMI09000216	2.57	464	77	7	5	39	-0.5
MD09-05	22.00	24.00	2.00	928307	SMI09000216	4.63	682	104	4	5	46	-0.5
MD09-05	24.00	25.00	1.00	928308	SMI09000216	2.41	1221	162	10	14	58	0.7
MD09-05	25.00	26.54	1.54	928309	SMI09000216	3.43	1021	121	3	6	76	-0.5
MD09-05	26.54	28.00	1.46	928311	SMI09000216	3.43	899	129	16	8	26	0.5
MD09-05	28.00	30.00	2.00	928312	SMI09000216	4.33	1003	225	19	8	30	0.5
MD09-05	30.00	32.00	2.00	928313	SMI09000216	4.77	648	167	7	9	23	-0.5
MD09-05	32.00	34.00	2.00	928314	SMI09000216	4.61	894	117	15	11	22	-0.5
MD09-05	34.00	36.00	2.00	928315	SMI09000216	5.02	1018	191	54	11	24	0.7
MD09-05	36.00	38.00	2.00	928316	SMI09000216	4.65	1030	129	22	8	18	0.7
MD09-05	38.00	40.00	2.00	928317	SMI09000216	4.45	813	130	12	11	35	-0.5
MD09-05	40.00	42.00	2.00	928318	SMI09000216	4.42	883	145	6	9	22	0.7
MD09-05	42.00	44.00	2.00	928319	SMI09000216	5.01	967	149	5	11	29	-0.5
MD09-05	44.00	46.00	2.00	928321	SMI09000216	4.95	974	134	6	8	72	0.8
MD09-05	46.00	48.00	2.00	928322	SMI09000216	4.85	1200	176	4	-5	41	1.1
MD09-05	48.00	50.00	2.00	928323	SMI09000216	4.77	1099	219	13	6	25	1.0
MD09-05	50.00	52.00	2.00	928324	SMI09000216	4.99	1469	226	10	6	27	1.5
MD09-05	52.00	54.00	2.00	928325	SMI09000216	4.63	1294	228	15	-5	20	0.9
MD09-05	54.00	56.00	2.00	928326	SMI09000216	5.14	883	143	5	-5	25	1.1
MD09-05	56.00	58.00	2.00	928327	SMI09000216	5.54	650	120	6	7	25	0.8
MD09-05	58.00	60.00	2.00	928328	SMI09000216	5.41	521	93	5	12	24	0.8
MD09-05	60.00	62.00	2.00	928329	SMI09000216	4.87	269	76	3	7	27	-0.5
MD09-05	62.00	64.00	2.00	928332	SMI09000216	4.76	462	100	4	8	30	0.8
MD09-05	64.00	66.00	2.00	928333	SMI09000216	5.2	442	91	6	7	56	1.0
MD09-05	66.00	68.00	2.00	928334	SMI09000216	5.4	595	68	12	10	24	0.9
MD09-05	68.00	70.00	2.00	928335	SMI09000216	5.19	725	114	16	10	24	1.3
MD09-05	70.00	72.30	2.30	928336	SMI09000216	5.95	637	109	8	8	27	1.3
MD09-05	72.30	73.60	1.30	928337	SMI09000216	3.08	42	4	2	-5	129	-0.5
MD09-05	73.60	75.00	1.40	928338	SMI09000216	3.55	381	86	5	6	26	0.9
MD09-05	75.00	77.00	2.00	928339	SMI09000216	5.44	756	139	7	-5	19	1.1
MD09-05	77.00	79.00	2.00	928341	SMI09000216	4.04	1107	180	11	15	33	1.4
MD09-05	79.00	81.00	2.00	928342	SMI09000216	5.3	930	205	10	6	23	1.4
MD09-05	81.00	83.00	2.00	928343	SMI09000216	4.77	928	107	8	-5	24	1.0
MD09-05	83.00	85.00	2.00	928344	SMI09000216	5.26	851	163	11	-5	27	0.7
MD09-05	85.00	87.00	2.00	928345	SMI09000216	4.86	734	73	5	-5	22	0.9
MD09-05	87.00	89.00	2.00	928346	SMI09000216	5.36	914	188	11	10	24	1.5
MD09-05	89.00	91.00	2.00	928347	SMI09000216	5.07	1217	182	6	8	27	1.5
MD09-05	91.00	93.00	2.00	928348	SMI09000216	5.17	799	125	7	7	29	0.8
MD09-05	93.00	95.00	2.00	928349	SMI09000216	4.93	699	103	7	6	22	0.8
MD09-05	95.00	97.00	2.00	928351	SMI09000216	4.42	585	71	18	6	19	0.8
MD09-05	97.00	99.00	2.00	928352	SMI09000216	4.93	1030	194	14	5	22	1.3
MD09-05	99.00	101.00	2.00	928353	SMI09000216	4.98	1287	319	9	5	18	1.2
MD09-05	101.00	103.00	2.00	928354	SMI09000216	4.69	790	332	6	-5	21	0.8
MD09-05	103.00	105.00	2.00	928355	SMI09000216	4.38	785	170	28	-5	25	0.8

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-05	105.00	106.00	1.00	928356	SMI09000216	2.39	320	105	62	-5	19	0.5
MD09-05	106.00	107.50	1.50	928357	SMI09000216	3.63	422	102	17	7	26	0.7
MD09-05	107.50	109.00	1.50	928358	SMI09000216	4.35	671	126	42	6	13	-0.5
MD09-05	109.00	111.00	2.00	928359	SMI09000216	5.07	503	74	99	7	11	-0.5
MD09-05	111.00	113.00	2.00	928362	SMI09000216	4.85	594	142	22	5	9	-0.5
MD09-05	113.00	115.00	2.00	928363	SMI09000216	4.71	555	156	32	6	11	-0.5
MD09-05	115.00	117.00	2.00	928364	SMI09000216	5.11	318	134	47	8	13	-0.5
MD09-05	117.00	119.00	2.00	928365	SMI09000216	5.22	321	95	92	6	13	-0.5
MD09-05	119.00	121.00	2.00	928366	SMI09000216	4.93	412	82	12	7	12	-0.5
MD09-05	121.00	123.00	2.00	928367	SMI09000216	4.92	292	62	23	-5	15	-0.5
MD09-05	123.00	125.00	2.00	928368	SMI09000216	5.22	849	203	40	9	16	-0.5
MD09-05	125.00	127.00	2.00	928369	SMI09000216	5	412	168	51	6	11	-0.5
MD09-05	127.00	129.00	2.00	928371	SMI09000216	5.11	467	112	53	6	9	-0.5
MD09-05	129.00	131.00	2.00	928372	SMI09000216	5.04	194	60	19	7	12	-0.5
MD09-05	131.00	133.00	2.00	928373	SMI09000216	5.15	389	177	25	5	12	-0.5
MD09-05	133.00	134.15	1.15	928374	SMI09000216	2.73	688	262	20	-5	10	-0.5
MD09-05	134.15	136.00	1.85	928375	SMI09000216	4.34	944	599	13	8	16	-0.5
MD09-05	136.00	138.00	2.00	928376	SMI09000216	5.09	959	252	17	8	13	-0.5
MD09-05	138.00	139.00	1.00	928377	SMI09000216	2.08	666	182	20	6	16	-0.5
MD09-05	139.00	140.00	1.00	928378	SMI09000216	2.53	731	225	34	5	13	-0.5
MD09-05	140.00	141.00	1.00	928379	SMI09000216	2.48	543	100	22	9	13	-0.5
MD09-05	141.00	143.00	2.00	928381	SMI09000216	4.57	719	169	34	-5	12	-0.5
MD09-05	143.00	144.00	1.00	928382	SMI09000216	2.49	605	467	57	-5	11	-0.5
MD09-05	144.00	145.00	1.00	928383	SMI09000216	2.53	829	390	22	7	18	-0.5
MD09-05	145.00	147.00	2.00	928384	SMI09000216	4.88	1009	374	36	-5	15	-0.5
MD09-05	147.00	149.00	2.00	928385	SMI09000216	5.12	636	162	48	5	9	-0.5
MD09-05	149.00	151.00	2.00	928386	SMI09000216	5.07	746	296	43	16	10	0.7
MD09-05	151.00	153.00	2.00	928387	SMI09000216	4.87	396	129	14	6	13	-0.5
MD09-05	153.00	155.00	2.00	928388	SMI09000216	5.03	353	192	20	7	11	-0.5
MD09-05	155.00	157.00	2.00	928389	SMI09000216	5.35	459	137	42	9	11	-0.5
MD09-05	157.00	159.00	2.00	928392	SMI09000216	5.1	675	247	47	13	10	-0.5
MD09-05	159.00	161.00	2.00	928393	SMI09000216	4.95	497	103	34	-5	17	0.6
MD09-05	161.00	163.00	2.00	928394	SMI09000216	5.12	507	92	12	-5	18	0.6
MD09-05	163.00	165.00	2.00	928395	SMI09000216	4.61	851	187	29	-5	19	0.8
MD09-05	165.00	167.00	2.00	928396	SMI09000216	4.69	575	110	20	7	22	0.8
MD09-05	167.00	168.60	1.60	928397	SMI09000216	3.62	515	94	24	6	20	0.6
MD09-05	168.60	170.00	1.40	928398	SMI09000216	3.24	921	222	32	-5	24	0.9
MD09-05	170.00	172.00	2.00	928399	SMI09000216	4.79	482	72	30	7	20	0.7
MD09-05	172.00	174.00	2.00	928401	SMI09000216	5.04	401	108	7	6	19	0.6
MD09-05	174.00	176.00	2.00	928402	SMI09000216	4.57	427	92	19	11	19	0.8
MD09-05	176.00	178.00	2.00	928403	SMI09000216	4.67	432	168	12	6	16	0.8
MD09-05	178.00	180.00	2.00	928404	SMI09000216	5.11	487	141	22	10	17	0.7
MD09-05	180.00	182.00	2.00	928405	SMI09000216	5.26	329	163	19	7	17	0.6
MD09-05	182.00	184.00	2.00	928406	SMI09000216	5.42	207	164	13	6	17	0.7
MD09-05	184.00	186.00	2.00	928407	SMI09000216	4.73	319	143	7	6	16	0.9
MD09-05	186.00	188.00	2.00	928408	SMI09000216	4.45	312	136	9	7	17	0.6
MD09-05	188.00	190.00	2.00	928409	SMI09000216	4.68	337	167	14	-5	17	-0.5
MD09-05	190.00	192.00	2.00	928411	SMI09000216	4.95	282	138	10	8	14	-0.5
MD09-05	192.00	194.00	2.00	928412	SMI09000216	4.98	276	88	7	6	18	0.5
MD09-05	194.00	196.00	2.00	928413	SMI09000216	4.62	231	100	12	-5	13	-0.5
MD09-05	196.00	198.00	2.00	928414	SMI09000216	5.02	152	50	8	6	16	-0.5
MD09-05	198.00	200.00	2.00	928415	SMI09000216	4.85	161	37	21	-5	21	-0.5
MD09-05	200.00	202.00	2.00	928416	SMI09000216	5.04	242	60	12	8	15	0.7
MD09-05	202.00	204.00	2.00	928417	SMI09000216	5.12	249	86	30	6	15	0.5
MD09-05	204.00	206.00	2.00	928418	SMI09000216	4.73	380	198	77	5	19	-0.5
MD09-05	206.00	208.00	2.00	928419	SMI09000216	5.04	287	106	13	7	16	0.5
MD09-05	208.00	210.00	2.00	928422	SMI09000216	4.99	262	93	13	7	18	-0.5
MD09-05	210.00	212.00	2.00	928423	SMI09000216	4.4	330	54	26	-5	17	0.6
MD09-05	212.00	214.00	2.00	928424	SMI09000216	5.09	272	58	18	6	17	0.7
MD09-05	214.00	215.60	1.60	928425	SMI09000216	3.58	264	58	27	6	17	-0.5
MD09-05	215.60	217.00	1.40	928426	SMI09000216	3.58	367	90	33	6	22	0.8
MD09-05	217.00	219.00	2.00	928427	SMI09000216	5.17	956	901	114	-5	23	1.3
MD09-05	219.00	221.10	2.10	928428	SMI09000216	5.12	587	335	41	12	18	-0.5
MD09-05	221.10	223.00	1.90	928429	SMI09000216	4.54	898	951	65	-5	19	0.7
MD09-05	223.00	225.15	2.15	928431	SMI09000216	5.84	283	448	2	11	18	-0.5
MD09-05	225.15	227.00	1.85	928432	SMI09000216	3.8	186	646	3	19	13	-0.5
MD09-05	227.00	229.00	2.00	928433	SMI09000216	5.5	227	339	3	-5	13	-0.5
MD09-05	229.00	231.00	2.00	928434	SMI09000216	4.21	185	166	10	-5	17	-0.5
MD09-05	231.00	233.00	2.00	928435	SMI09000216	5.21	287	71	17	14	12	-0.5
MD09-05	233.00	235.00	2.00	928436	SMI09000216	5.12	258	54	19	19	14	-0.5

Drill Hole	From	To	m	Sample	File	Wgt	Cu ppm	Au ppb	Mo ppm	Pb ppm	Zn ppm	Ag ppm
MD09-05	235.00	237.00	2.00	928437	SMI09000216	5.62	282	72	16	9	11	-0.5
MD09-05	237.00	239.00	2.00	928438	SMI09000216	4.72	317	76	15	15	14	-0.5
MD09-05	239.00	241.00	2.00	928439	SMI09000216	5.15	244	42	11	22	17	-0.5
MD09-05	241.00	243.00	2.00	928441	SMI09000216	5.47	191	66	5	-5	15	-0.5
MD09-05	243.00	245.00	2.00	928442	SMI09000216	4.33	201	70	-2	-5	12	-0.5
MD09-05	245.00	247.00	2.00	928443	SMI09000216	5.42	263	77	-2	-5	14	-0.5
MD09-05	247.00	249.00	2.00	928444	SMI09000216	5.08	393	350	17	-5	21	-0.5
MD09-05	249.00	251.00	2.00	928445	SMI09000216	5	227	497	4	16	15	-0.5
MD09-05	251.00	253.00	2.00	928446	SMI09000216	4.81	275	310	-2	-5	14	-0.5
MD09-05	253.00	255.00	2.00	928447	SMI09000216	4.98	250	107	7	16	16	-0.5
MD09-05	255.00	256.75	1.75	928448	SMI09000216	4.53	250	225	11	20	32	-0.5
MD09-05	256.73	258.00	1.27	928449	SMI09000216	3.82	250	341	7	20	16	-0.5
MD09-05	258.00	259.00	1.00	928452	SMI09000216	2.52	228	279	9	-5	16	-0.5
MD09-05	259.00	261.00	2.00	928453	SMI09000216	4.81	247	320	14	-5	31	-0.5
MD09-05	261.00	263.00	2.00	928454	SMI09000216	4.97	177	799	4	14	41	-0.5
MD09-05	263.00	265.00	2.00	928455	SMI09000216	4.32	145	374	4	-5	16	-0.5
MD09-05	265.00	267.00	2.00	928456	SMI09000216	5.31	169	1000	2	-5	18	-0.5
MD09-05	267.00	269.00	2.00	928457	SMI09000216	4.86	141	389	4	7	16	-0.5
MD09-05	269.00	269.85	0.85	928458	SMI09000216	2.29	73	402	9	14	16	-0.5
MD09-05	269.85	272.00	2.15	928459	SMI09000216	5.29	187	611	-2	17	27	-0.5
MD09-05	272.00	274.00	2.00	928461	SMI09000216	4.71	122	160	-2	7	27	-0.5
MD09-05	274.00	276.00	2.00	928462	SMI09000216	4.83	40	87	-2	8	23	-0.5
MD09-05	276.00	278.10	2.10	928463	SMI09000216	5.55	66	170	-2	6	30	0.6
MD09-05	278.10	280.00	1.90	928464	SMI09000216	4.9	96	159	-2	7	32	-0.5
MD09-05	280.00	282.00	2.00	928465	SMI09000216	4.95	211	362	-2	8	42	0.9
MD09-05	282.00	284.00	2.00	928466	SMI09000216	5.15	179	375	-2	12	36	0.6
MD09-05	284.00	286.00	2.00	928467	SMI09000216	4.21	275	680	-2	13	36	1.5
MD09-05	286.00	288.00	2.00	928468	SMI09000216	4.9	135	234	25	10	27	-0.5
MD09-05	288.00	290.00	2.00	928469	SMI09000216	4.66	103	138	8	-5	23	-0.5
MD09-05	290.00	291.00	1.00	928471	SMI09000216	2.77	103	11	-2	8	31	0.6
MD09-05	291.00	292.55	1.55	928472	SMI09000216	3.39	115	24	-2	8	31	-0.5
MD09-05	292.55	294.00	1.45	928473	SMI09000216	3.72	96	198	-2	11	48	1.0
MD09-05	294.00	296.00	2.00	928474	SMI09000216	5.44	79	11	5	5	52	-0.5
MD09-05	296.00	298.00	2.00	928475	SMI09000216	4.61	76	21	2	-5	163	-0.5
MD09-05	298.00	300.00	2.00	928476	SMI09000216	4.88	103	163	3	11	49	0.7
MD09-05	300.00	301.40	1.40	928477	SMI09000216	3.46	237	2086	3	28	345	2.0
MD09-05	301.40	303.50	2.10	928478	SMI09000216	3.73	65	46	-2	23	126	-0.5
MD09-05	303.00	305.00	2.00	928479	SMI09000216	4.25	73	30	9	24	194	0.8
MD09-05	305.00	307.00	2.00	928482	SMI09000216	5.27	109	15	2	15	137	1.1
MD09-05	307.00	309.00	2.00	928483	SMI09000216	4.66	106	34	-2	19	117	1.1
MD09-05	309.00	311.00	2.00	928484	SMI09000216	5.02	65	18	-2	14	156	0.7
MD09-05	311.00	313.00	2.00	928485	SMI09000216	4.4	38	29	-2	24	210	0.9
MD09-05	313.00	315.00	2.00	928486	SMI09000216	4.53	18	21	-2	35	258	0.7
MD09-05	315.00	317.00	2.00	928487	SMI09000216	5.11	18	17	6	16	127	-0.5
MD09-05	317.00	319.00	2.00	928488	SMI09000216	4.41	16	10	-2	19	129	-0.5
MD09-05	319.00	321.00	2.00	928489	SMI09000216	4.47	9	2	-2	-5	99	-0.5
MD09-05	321.00	323.00	2.00	928491	SMI09000216	4	12	3	-2	8	101	-0.5
MD09-05	323.00	325.00	2.00	928492	SMI09000216	4.72	32	2	-2	10	111	-0.5
MD09-05	325.00	327.00	2.00	928493	SMI09000216	5.04	31	7	-2	6	115	-0.5
MD09-05	327.00	329.00	2.00	928494	SMI09000216	3.31	59	3	-2	6	94	-0.5
MD09-05	329.00	331.00	2.00	928495	SMI09000216	3.27	77	6	-2	-5	105	-0.5
MD09-05	331.00	333.00	2.00	928496	SMI09000216	5.12	68	2	-2	-5	93	-0.5
MD09-05	333.00	335.00	2.00	928497	SMI09000216	4.37	48	-2	-2	-5	105	-0.5
MD09-05	335.00	337.00	2.00	928498	SMI09000216	4.76	56	-2	-2	-5	88	-0.5
MD09-05	337.00	337.94	0.94	928499	SMI09000216	2.35	75	-2	-2	-5	85	-0.5

Drill Hole	From	To	m	Sample	Other	File	Wgt	Au	Mo	Cu	Pb	Zn	Ag
MD09-01				927320	BLANK	SMI09000207	1.39	-2	-2	6	-5	15	-0.5
MD09-01				927330	BLANK	SMI09000207	1.18	-2	-2	-2	-5	15	-0.5
MD09-01				927340	BLANK	SMI09000207	1.24	-2	-2	2	-5	14	-0.5
MD09-01				927350	BLANK	SMI09000207	5.54	-2	-2	2	-5	13	-0.5
MD09-01				927360	BLANK	SMI09000207	0.93	-2	-2	3	-5	13	-0.5
MD09-01				927370	BLANK	SMI09000220	0.97	-2	-2	11	-5	13	-0.5
MD09-01				927380	BLANK	SMI09000207	1.1	-2	-2	4	-5	18	-0.5
MD09-01				927390	BLANK	SMI09000207	1.01	-2	-2	5	-5	13	-0.5
MD09-01				927400	BLANK	SMI09000207	1.22	-2	-2	4	-5	15	-0.5
MD09-01				927410	BLANK	SMI09000207	1.1	2	-2	6	5	15	-0.5
MD09-01				927420	BLANK	SMI09000207	1.04	-2	-2	10	-5	13	-0.5
MD09-01				927430	BLANK	SMI09000207	1.19	-2	-2	4	-5	14	-0.5
MD09-01				927440	BLANK	SMI09000207	1.17	-2	-2	5	6	14	-0.5
MD09-01				927450	BLANK	SMI09000207	0.9	-2	-2	5	-5	13	-0.5
MD09-01				927460	BLANK	SMI09000207	1.18	-2	-2	5	-5	12	-0.5
MD09-01				927470	BLANK	SMI09000207	1.16	3	-2	5	-5	11	-0.5
MD09-01				927480	BLANK	SMI09000207	1.03	-2	-2	3	-5	14	-0.5
MD09-01				927490	BLANK	SMI09000207	1.19	-2	-2	6	-5	14	-0.5
MD09-02				927560	BLANK	SMI09000208	1.17	-2	-2	6	-5	14	-0.5
MD09-02				927570	BLANK	SMI09000208	1.08	-2	-2	4	-5	14	-0.5
MD09-02				927580	BLANK	SMI09000208	1.18	-2	-2	4	-5	14	-0.5
MD09-02				927590	BLANK	SMI09000208	1.26	-2	-2	6	-5	14	-0.5
MD09-02				927600	BLANK	SMI09000208	1.2	-2	-2	6	-5	13	-0.5
MD09-02				927610	BLANK	SMI09000208	0.99	-2	-2	9	-5	13	-0.5
MD09-02				927620	BLANK	SMI09000208	1.17	-2	-2	6	-5	17	-0.5
MD09-02				927630	BLANK	SMI09000208	1.42	-2	-2	4	-5	13	-0.5
MD09-02				927640	BLANK	SMI09000208	1.25	-2	-2	4	7	15	-0.5
MD09-02				927650	BLANK	SMI09000208	1.24	-2	-2	2	-5	13	-0.5
MD09-02				927660	BLANK	SMI09000208	1.48	-2	-2	5	-5	13	-0.5
MD09-02				927670	BLANK	SMI09000208	1.24	-2	-2	4	-5	14	-0.5
MD09-02				927680	BLANK	SMI09000208	1.06	-2	-2	6	-5	14	-0.5
MD09-02				927690	BLANK	SMI09000208	1.22	3	-2	3	-5	14	-0.5
MD09-02				927700	BLANK	SMI09000208	1.17	-2	-2	7	-5	12	-0.5
MD09-02				927710	BLANK	SMI09000208	1.74	-2	-2	2	-5	15	-0.5
MD09-02				927720	BLANK	SMI09000208	1.23	3	-2	9	-5	12	-0.5
MD09-02				927730	BLANK	SMI09000208	1.3	-2	-2	-2	-5	14	-0.5
MD09-02				927740	BLANK	SMI09000208	1.24	-2	-2	-2	-5	13	-0.5
MD09-02				927750	BLANK	SMI09000208	1.31	-2	-2	-2	-5	13	-0.5
MD09-03				927760	BLANK	SMI09000209	1.03	-2	-2	-2	5	9	-0.5
MD09-03				927770	BLANK	SMI09000209	0.85	-2	-2	3	5	10	-0.5
MD09-03				927780	BLANK	SMI09000209	0.75	-2	-2	3	-5	6	-0.5
MD09-03				927790	BLANK	SMI09000209	0.73	-2	-2	3	-5	16	-0.5
MD09-03				927800	BLANK	SMI09000209	0.74	-2	-2	9	-5	14	-0.5
MD09-03				927810	BLANK	SMI09000209	0.8	-2	-2	-2	20	14	0.6
MD09-03				927820	BLANK	SMI09000209	0.96	-2	-2	2	-5	5	-0.5
MD09-03				927830	BLANK	SMI09000209	0.89	-2	-2	-2	-5	4	-0.5
MD09-03				927840	BLANK	SMI09000209	1.23	-2	-2	2	-5	3	-0.5
MD09-03				927850	BLANK	SMI09000209	1.05	-2	-2	-2	-5	4	-0.5
MD09-03				927860	BLANK	SMI09000209	1.07	-2	-2	-2	9	-2	-0.5
MD09-03				927870	BLANK	SMI09000209	1.26	-2	-2	4	-5	-2	-0.5
MD09-03				927880	BLANK	SMI09000209	1.22	-2	-2	-2	9	-2	-0.5

Drill Hole	From	To	m	Sample	Other	File	Wgt	Au	Mo	Cu	Pb	Zn	Ag
MD09-03				927890	BLANK	SMI09000209	1.32	-2	-2	-2	6	-2	-0.5
MD09-03				927900	BLANK	SMI09000209	1.36	-2	-2	-2	-5	-2	-0.5
MD09-03				927910	BLANK	SMI09000209	0.83	3	-2	-2	-5	7	-0.5
MD09-03				927920	BLANK	SMI09000209	0.71	-2	-2	2	-5	8	-0.5
MD09-03				927930	BLANK	SMI09000209	0.85	-2	-2	3	-5	13	-0.5
MD09-03				927940	BLANK	SMI09000209	0.84	-2	-2	6	-5	16	-0.5
MD09-03				927950	BLANK	SMI09000209	1.19	-2	-2	4	-5	-2	-0.5
MD09-03				927960	BLANK	SMI09000214	1.3	-2	-2	2	-5	-2	-0.5
MD09-04				927970	BLANK	SMI09000214	0.72	-2	-2	10	-5	10	-0.5
MD09-04				927980	BLANK	SMI09000214	0.58	-2	-2	3	-5	11	-0.5
MD09-04				927990	BLANK	SMI09000214	0.85	-2	-2	3	-5	7	-0.5
MD09-04				928000	BLANK	SMI09000214	0.71	-2	-2	-2	-5	4	-0.5
MD09-04				928010	BLANK	SMI09000214	0.77	-2	-2	3	-5	4	-0.5
MD09-04				928020	BLANK	SMI09000214	0.62	-2	-2	-2	-5	6	-0.5
MD09-04				928030	BLANK	SMI09000214	0.75	-2	-2	-2	6	5	-0.5
MD09-04				928040	BLANK	SMI09000214	0.76	-2	-2	3	-5	4	-0.5
MD09-04				928050	BLANK	SMI09000214	0.83	-2	-2	-2	-5	4	-0.5
MD09-04				928060	BLANK	SMI09000214	1.29	-2	-2	-2	-5	3	-0.5
MD09-04				928070	BLANK	SMI09000214	1.47	-2	-2	-2	-5	3	-0.5
MD09-04				928080	BLANK	SMI09000214	0.55	-2	-2	-2	-5	3	-0.5
MD09-04				928090	BLANK	SMI09000214	0.55	-2	-2	4	-5	3	-0.5
MD09-04				928100	BLANK	SMI09000214	0.54	-2	-2	3	-5	4	-0.5
MD09-05				928310	BLANK	SMI09000216	0.57	-2	-2	8	-5	4	-0.5
MD09-05				928320	BLANK	SMI09000216	0.63	-2	-2	4	-5	5	-0.5
MD09-05				928330	BLANK	SMI09000216	0.48	6	-2	4	-5	-2	-0.5
MD09-05				928340	BLANK	SMI09000216	0.57	-2	-2	2	-5	-2	-0.5
MD09-05				928350	BLANK	SMI09000216	0.52	4	-2	5	-5	-2	-0.5
MD09-05				928360	BLANK	SMI09000216	0.58	-2	-2	4	-5	3	-0.5
MD09-05				928370	BLANK	SMI09000216	0.36	10	-2	3	-5	3	-0.5
MD09-05				928380	BLANK	SMI09000216	0.59	-2	-2	3	-5	4	-0.5
MD09-05				928390	BLANK	SMI09000216	0.83	-2	-2	3	-5	4	-0.5
MD09-05				928400	BLANK	SMI09000216	0.51	-2	-2	3	-5	-2	-0.5
MD09-05				928410	BLANK	SMI09000216	0.51	-2	-2	-2	-5	-2	-0.5
MD09-05				928420	BLANK	SMI09000216	0.54	-2	-2	-2	-5	-2	-0.5
MD09-05				928430	BLANK	SMI09000216	0.66	3	-2	3	-5	-2	-0.5
MD09-05				928440	BLANK	SMI09000216	0.85	-2	-2	4	-5	-2	-0.5
MD09-05				928450	BLANK	SMI09000216	0.74	2	-2	-2	-5	-2	-0.5
MD09-05				928460	BLANK	SMI09000216	0.81	-2	-2	-2	-5	-2	-0.5
MD09-05				928470	BLANK	SMI09000216	0.63	-2	-2	-2	-5	-2	-0.5
MD09-05				928480	BLANK	SMI09000216	1.06	-2	-2	6	-5	-2	-0.5
MD09-05				928490	BLANK	SMI09000216	0.77	-2	-2	-2	-5	-2	-0.5
MD09-05				928500	BLANK	SMI09000216	0.84	-2	-2	-2	-5	3	-0.5

Drill Hole	From	To	m	Sample	Other	File	Wgt	Au	Cu			
MD09-01				927391	52Pb	SMI09000207	0.14	307	3377			
MD09-01				927451	52Pb	SMI09000207	0.08	301	3212			
MD09-01				927481	52Pb	SMI09000207	0.08	300	3212			
MD09-02				927581	52Pb	SMI09000208	0.13	321	3209			
MD09-02				927611	52Pb	SMI09000208	0.11	304	3282			
MD09-02				927671	52Pb	SMI09000208	0.11	323	3203			
MD09-02				927731	52Pb	SMI09000208	0.12	317	3201			
MD09-03				927761	52Pb	SMI09000209	0.15	310	3393			
MD09-03				927801	52Pb	SMI09000209	0.15	322	3301			
MD09-03				927851	52Pb	SMI09000209	0.14	328	3219			
MD09-03				927911	52Pb	SMI09000209	0.15	297	3266			
MD09-03				927941	52Pb	SMI09000209	0.11	305	3260			
MD09-04				927971	52Pb	SMI09000214	0.15	325	3177			
MD09-04				928031	52Pb	SMI09000214	0.14	318	3214			
MD09-04				928061	52Pb	SMI09000214	0.14	317	3116			
MD09-05				928331	52Pb	SMI09000216	0.14	329	3455			
MD09-05				928451	52Pb	SMI09000216	0.11	309	3411			
Avg								314	3265			
Std Dev								10	93			
MD09-01				927331	53Pb	SMI09000207	0.1	633	5410			
MD09-01				927361	53Pb	SMI09000207	0.13	658	5219			
MD09-01				927421	53Pb	SMI09000207	0.17	617	5305			
MD09-02				927641	53Pb	SMI09000208	0.09	623	5023			
MD09-02				927701	53Pb	SMI09000208	0.1	626	5200			
MD09-03				927821	53Pb	SMI09000209	0.15	647	5191			
MD09-03				927881	53Pb	SMI09000209	0.14	634	5145			
MD09-04				928001	53Pb	SMI09000214	0.1	646	5330			
MD09-04				928091	53Pb	SMI09000214	0.14	639	5390			
MD09-05				928361	53Pb	SMI09000216	0.14	641	5048			
MD09-05				928391	53Pb	SMI09000216	0.14	651	5224			
MD09-05				928421	53Pb	SMI09000216	0.1	630	5443			
MD09-05				928481	53Pb	SMI09000216	0.1	625	5480			
Avg								636	5262			
Std Dev								12	145			
				Std	Cu rec	Cu low	Cu high	Au low	Au rec	Au high	% diff	
				52P	0.3338	0.3301	0.3375	0.299	0.307	0.315		
				All n=1	0.3265			0.297	0.314	0.329	2.2%	
				53P	0.546	0.54	0.553	0.612	0.623	0.634		
				All n=1	0.5262				0.636		3.6%	

Appendix B Author's Certificate

STATEMENT OF QUALIFICATIONS

I, John Bradford, P.Geo., certify that:

1. I am presently Chief Geoscientist for Paget Minerals Corporation with a business address located at:
1160-1040 W. Georgia St.
Vancouver, BC, Canada
V6E 4H1
2. I am a member in good standing of the Association of Professional Engineers and Geoscientists of B.C.
3. I graduated from the University of British Columbia in 1985 with a Bachelor of Science in Geology and from the University of British Columbia in 1988 with a Master of Science in Geology.
4. Since 1988 I have been continuously employed in exploration for base and precious metals in North America, South America and China.
5. I supervised and participated in the 2009 exploration program at Mt. Dunn and am therefore personally familiar with the geology of the Mt. Dunn Property and the work conducted in 2009. I have prepared all sections of this report.

Dated this 16th Day of December, 2009


Signature

John Bradford, M.Sc, PGeo

Appendix C Statement of Costs

Item	Name	Date	#	Cost	Item sub-total	Sub-totals
MT DUNN WORK COSTS						
Geological - salaries and wages						
	Mike Hocking		days	daily rate		
			30	500	15000.00	
	Jim Young		30	300	9000.00	
	Dave Nash		24	300	7200.00	
	Chris Leslie		2	400	800.00	
	Curtis Brett		2	300	600.00	
	John Bradford		2	635	1270.00	
	John Fleishman		2	500	1000.00	
						34870.00
Food & Accommodation: on-site						
	Rugged Edge Holdings - Camp set up / tear down				5,400.00	
	Rugged Edge Holdings - Camp - general				31,152.56	
	Rugged Edge Holdings - Camp Expediting				5,400.00	
	Rugged Edge Holdings - Camp - food				6,925.99	
	Rugged Edge Holdings - Camp - equipment and supplies				8,507.91	
	Rugged Edge Holdings - Camp - Equipment rentals				9,166.75	
	Fuel				2,437.12	
						68990.33
Communications						
	Sat phones: rental & time and charges				2300.88	
	Radio rentals				288.37	
						2589.25
Report						
	Preparation		days	daily rate		
			4	635	2540.00	
	Materials, maps, binding, copying		1	100	100.00	
						2640.00
Geochemical						
	Rock sample assays		947	35	33145.00	
						33145.00
Vehicle						
	Truck rental		30	80	2400.00	
	Mileage		1200	0.25	300.00	
						2700.00
Drilling						
	Ridgeline Drilling				140699.44	
						140699.44
MOB/DEMOB COSTS						
Food & Accommodation: travel to/from site						
	Hotel		man-days	rate		
			16	75	1200.00	
	Food		16	75	1200.00	
						2400.00
Wages: travel to/from site						
	Mike Hocking		days	daily rate		
			4	500	2000.00	
	Jim Young		4	300	1200.00	
	Dave Nash		1	300	300.00	
	Chris Leslie		2	400	800.00	
	Curtis Brett		2	300	600.00	
	John Bradford		2	635	1270.00	
	John Fleishman		2	500	1000.00	
						7170.00
Vehicle						
	Truck rental		4	80	320.00	
	Mileage		3200	0.25	800.00	
						1120.00
						SUBTOTAL work/mob-demob <u>296324.02</u>
Transportation on-site - Helicopter						
	Lakelse Air				152636.00	
						SUBTOTAL helicopter costs: <u>152636.00</u>
						Allowable helicopter costs (maximum of 50% work) <u>148162.01</u>
						Assessment work to claim: <u>444486.03</u>

Appendix D Analytical Certificates



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 09, 2009
Report Date: October 02, 2009
Page: 1 of 8

CERTIFICATE OF ANALYSIS

SMI09000207.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 197

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
Code					
R200	185	Crush split and pulverize drill core to 200 mesh			VAN
3B	191	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	191	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL


STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC: Nigel Luckman
B. Booth



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 2 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000207.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi		
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	V		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
927301	Drill Core		1.86	89	5	719	6	19	0.8	<2	6	236	2.12	19	<20	<4	10	361	<0.4	<5	<5	173
927302	Drill Core		2.15	188	7	1466	12	20	1.0	2	10	463	2.94	33	<20	<4	10	394	<0.4	<5	<5	187
927303	Drill Core		1.90	92	4	1839	6	28	1.2	3	12	541	2.97	110	<20	<4	12	401	<0.4	<5	<5	191
927304	Drill Core		4.60	157	8	1209	7	19	1.1	3	9	549	2.68	22	<20	<4	9	348	<0.4	<5	<5	173
927305	Drill Core		1.68	292	7	1541	21	23	2.9	3	12	557	4.68	150	<20	<4	9	338	<0.4	<5	<5	178
927306	Drill Core		2.68	136	5	758	7	17	1.9	<2	9	350	3.08	29	<20	<4	11	402	<0.4	<5	<5	193
927307	Drill Core		1.92	153	6	2249	7	25	2.2	5	13	464	4.52	32	<20	<4	9	347	<0.4	<5	<5	192
927308	Drill Core		2.14	127	4	607	6	15	1.2	<2	6	252	2.59	17	<20	<4	10	453	<0.4	<5	<5	183
927309	Drill Core		3.53	264	<2	2560	<5	18	1.5	4	12	435	2.05	<5	<20	<4	10	381	<0.4	<5	<5	166
927310	Drill Core		2.79	243	9	1861	7	20	1.8	4	15	451	2.45	10	<20	<4	11	371	<0.4	<5	<5	178
927311	Drill Core		2.15	148	3	1158	6	22	0.9	4	19	648	2.39	<5	<20	<4	9	376	<0.4	<5	<5	174
927312	Drill Core		4.11	91	5	2082	7	22	1.5	10	13	553	2.72	12	<20	<4	6	263	<0.4	<5	<5	188
927313	Drill Core		3.56	297	3	3143	<5	25	1.4	6	14	347	2.48	<5	<20	<4	8	259	<0.4	<5	<5	184
927314	Drill Core		1.93	243	11	2693	<5	28	1.1	5	10	368	2.36	<5	<20	<4	9	264	<0.4	<5	<5	177
927315	Drill Core		4.73	220	6	1178	<5	24	0.7	5	8	372	2.35	<5	<20	<4	7	294	<0.4	<5	<5	149
927316	Drill Core		4.65	675	5	2895	5	38	2.0	8	9	426	2.95	<5	<20	<4	5	240	<0.4	<5	<5	173
927317	Drill Core		4.20	247	4	1514	<5	33	0.9	10	10	455	3.15	<5	<20	<4	4	251	<0.4	<5	<5	161
927318	Drill Core		4.64	135	<2	655	<5	26	<0.5	3	6	430	2.38	<5	<20	<4	10	244	<0.4	<5	<5	128
927319	Drill Core		4.83	692	17	3493	<5	24	1.6	19	11	306	2.73	<5	<20	<4	3	224	<0.4	<5	<5	176
927320	Drill Core		1.39	<2	<2	6	<5	15	<0.5	<2	<2	190	0.39	<5	<20	<4	<2	51	<0.4	<5	<5	3
927321	Drill Core		4.81	23	2	188	<5	26	<0.5	2	6	346	2.98	<5	<20	<4	11	275	<0.4	<5	<5	138
927322	Drill Core		4.81	29	<2	185	<5	26	<0.5	<2	7	463	3.21	9	<20	<4	11	321	<0.4	<5	<5	135
927323	Drill Core		5.25	22	3	137	<5	17	<0.5	2	7	402	2.65	18	<20	<4	10	268	<0.4	<5	<5	132
927324	Drill Core		4.29	105	6	487	7	21	<0.5	2	7	400	2.90	52	<20	<4	10	266	<0.4	<5	<5	135
927325	Drill Core		5.35	129	12	518	7	12	<0.5	3	7	314	2.75	79	<20	<4	9	156	<0.4	<5	<5	121
927326	Drill Core		4.80	35	4	154	6	19	<0.5	2	7	478	2.97	33	<20	<4	12	297	<0.4	<5	<5	129
927327	Drill Core		3.71	181	28	624	16	25	1.0	2	8	296	3.39	179	<20	<4	10	217	<0.4	8	<5	124
927328	Drill Core		1.68	1052	28	313	156	319	8.2	<2	<2	686	30.37	765	<20	<4	<2	157	<0.4	52	<5	50
927329	Drill Core		2.69	323	48	720	35	119	2.0	<2	9	254	5.14	253	<20	<4	10	218	0.5	7	<5	109
927330	Drill Core		1.18	<2	<2	<2	<5	15	<0.5	<2	<2	191	0.41	<5	<20	<4	<2	48	<0.4	<5	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 2 of 8 Part 2

SMI09000207.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927301	Drill Core	0.46	0.166	13	5	0.60	479	0.38	10.10	6.22	1.58	6	49	<2	11	9	2	11	<0.1
927302	Drill Core	0.44	0.149	16	4	0.58	914	0.37	9.62	5.44	1.92	17	49	<2	13	8	2	10	0.1
927303	Drill Core	0.55	0.161	25	2	0.47	844	0.39	9.82	6.04	1.64	<4	57	<2	17	9	2	10	0.3
927304	Drill Core	2.55	0.153	19	4	0.65	201	0.35	8.95	5.21	1.71	<4	49	2	14	8	2	9	1.3
927305	Drill Core	0.44	0.145	22	4	0.88	698	0.32	8.90	5.18	1.87	7	46	<2	18	7	2	10	0.5
927306	Drill Core	0.44	0.156	19	4	0.74	658	0.36	9.40	5.76	1.90	<4	58	<2	13	8	2	10	0.3
927307	Drill Core	1.53	0.151	25	3	1.04	54	0.37	9.82	4.30	2.98	<4	59	<2	12	8	2	11	2.7
927308	Drill Core	0.44	0.153	17	3	0.74	890	0.37	9.50	5.69	1.96	<4	55	<2	9	8	2	10	0.1
927309	Drill Core	0.75	0.145	23	5	0.79	969	0.35	9.31	5.23	2.17	<4	51	<2	19	8	2	10	0.5
927310	Drill Core	0.50	0.152	22	5	0.73	947	0.36	9.19	5.42	2.11	6	58	<2	16	8	2	10	0.7
927311	Drill Core	1.13	0.148	22	3	0.76	1397	0.36	9.75	5.35	2.29	<4	60	<2	15	8	2	9	0.4
927312	Drill Core	1.94	0.133	17	15	0.75	378	0.35	8.27	4.09	2.74	6	49	<2	16	7	1	10	0.7
927313	Drill Core	0.53	0.137	19	6	0.70	1118	0.32	8.77	4.30	3.46	5	56	3	16	7	2	8	0.6
927314	Drill Core	0.64	0.139	20	4	0.72	1372	0.33	8.97	4.91	2.83	5	61	<2	15	7	1	8	0.4
927315	Drill Core	3.09	0.133	15	5	0.68	978	0.29	8.04	4.29	2.97	5	51	<2	11	7	1	7	0.6
927316	Drill Core	2.26	0.133	16	13	0.76	963	0.28	8.75	3.77	3.71	<4	51	2	11	6	1	9	0.5
927317	Drill Core	2.37	0.135	13	23	0.94	762	0.28	8.26	4.03	2.94	<4	39	<2	10	5	1	9	0.5
927318	Drill Core	2.55	0.092	15	5	0.69	2020	0.25	7.88	3.59	3.96	<4	48	<2	9	6	1	5	0.4
927319	Drill Core	1.83	0.112	13	31	0.70	1203	0.30	7.65	3.58	3.12	6	37	<2	8	5	1	8	0.6
927320	Drill Core	22.65	0.030	3	<2	12.46	20	<0.01	0.27	0.02	0.04	<4	2	<2	<2	<2	<1	<1	<0.1
927321	Drill Core	1.79	0.111	28	3	0.81	742	0.30	9.44	3.47	4.20	<4	56	<2	11	8	2	7	0.5
927322	Drill Core	2.44	0.107	25	3	0.71	459	0.29	8.97	3.75	3.80	<4	51	<2	10	8	1	6	0.7
927323	Drill Core	1.92	0.102	27	3	0.63	443	0.30	9.19	4.09	3.12	<4	52	<2	11	8	1	7	0.9
927324	Drill Core	1.64	0.099	24	3	0.73	184	0.28	9.22	3.62	3.63	8	47	<2	11	7	1	7	1.1
927325	Drill Core	1.60	0.093	24	3	0.38	74	0.26	8.41	3.20	3.33	5	44	<2	11	7	1	6	2.4
927326	Drill Core	2.12	0.104	24	2	0.65	155	0.30	9.33	3.76	3.77	<4	45	<2	11	8	1	6	1.5
927327	Drill Core	1.49	0.096	22	4	0.53	57	0.27	9.06	3.15	3.84	34	48	2	11	7	2	7	3.0
927328	Drill Core	3.68	0.026	16	<2	0.33	32	0.05	2.42	0.66	0.80	<4	19	4	9	<2	<1	3	28.9
927329	Drill Core	1.46	0.081	19	4	0.45	32	0.20	8.64	2.92	4.20	15	53	<2	10	6	2	6	5.1
927330	Drill Core	22.42	0.022	2	<2	12.44	12	<0.01	0.05	0.02	0.03	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 3 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000207.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
927331	Rock Pulp		0.10	633	3	5410	10	66	1.7	18	14	455	5.56	<5	<20	<4	4	469	<0.4	<5	<5	131
927332	Drill Core		4.79	79	11	319	8	18	<0.5	<2	7	365	3.34	79	<20	<4	9	331	<0.4	<5	<5	104
927333	Drill Core		4.30	45	13	273	7	14	<0.5	<2	7	326	2.77	52	<20	<4	12	390	<0.4	<5	<5	106
927334	Drill Core		5.53	161	37	619	11	8	<0.5	<2	8	277	2.62	203	<20	<4	10	346	<0.4	<5	5	98
927335	Drill Core		5.05	31	15	268	5	13	<0.5	<2	6	300	2.52	15	<20	<4	10	382	<0.4	<5	7	104
927336	Drill Core		4.86	34	20	303	7	14	<0.5	<2	6	192	2.45	10	<20	<4	11	347	<0.4	<5	10	107
927337	Drill Core		5.04	42	23	449	7	9	<0.5	<2	7	247	2.46	19	<20	<4	10	281	<0.4	<5	11	105
927338	Drill Core		5.10	50	13	377	10	10	<0.5	<2	7	267	2.37	18	<20	<4	9	359	<0.4	<5	7	103
927339	Drill Core		4.43	29	5	207	5	15	<0.5	<2	6	223	2.38	9	<20	<4	9	396	<0.4	<5	6	103
927340	Drill Core		1.24	<2	<2	2	<5	14	<0.5	<2	<2	165	0.37	<5	<20	<4	<2	43	<0.4	<5	<5	2
927341	Drill Core		5.27	48	9	202	10	12	<0.5	<2	6	235	2.53	22	<20	<4	9	368	<0.4	<5	6	104
927342	Drill Core		4.95	26	5	130	<5	11	<0.5	<2	6	333	2.38	16	<20	<4	8	389	<0.4	<5	8	101
927343	Drill Core		4.95	80	12	346	8	10	<0.5	<2	6	271	2.38	28	<20	<4	10	341	<0.4	<5	6	98
927344	Drill Core		4.56	33	11	252	7	12	<0.5	<2	5	222	2.59	9	<20	<4	11	387	1.3	<5	<5	103
927345	Drill Core		5.65	12	6	127	<5	12	<0.5	<2	6	254	2.35	39	<20	<4	11	424	1.5	<5	8	107
927346	Drill Core		4.75	31	4	149	9	15	<0.5	<2	6	285	2.45	111	<20	<4	10	398	<0.4	<5	5	103
927347	Drill Core		5.02	34	8	240	9	112	<0.5	<2	5	294	2.61	68	<20	<4	10	280	1.4	<5	13	96
927348	Drill Core		5.00	14	6	141	7	17	<0.5	<2	5	292	2.53	20	<20	<4	11	411	<0.4	<5	<5	103
927349	Drill Core		4.90	32	6	189	6	16	<0.5	<2	5	336	2.64	108	<20	<4	10	404	<0.4	<5	7	103
927350	Drill Core		5.54	<2	<2	2	<5	13	<0.5	<2	<2	167	0.39	<5	<20	<4	<2	43	<0.4	<5	<5	3
927351	Drill Core		0.90	41	15	374	8	19	<0.5	<2	7	263	2.52	12	<20	<4	10	456	<0.4	<5	7	101
927352	Drill Core		4.66	16	6	169	5	17	<0.5	<2	7	364	2.86	10	<20	<4	8	539	<0.4	<5	<5	119
927353	Drill Core		4.86	40	6	299	8	18	<0.5	<2	9	277	3.04	51	<20	<4	9	405	<0.4	<5	7	135
927354	Drill Core		4.95	47	5	405	<5	26	<0.5	3	8	304	2.90	47	<20	<4	9	461	<0.4	<5	8	135
927355	Drill Core		4.97	64	4	491	6	15	<0.5	3	8	299	2.77	5	<20	<4	9	426	<0.4	<5	6	142
927356	Drill Core		4.55	67	4	444	9	20	<0.5	2	6	294	2.92	8	<20	<4	8	361	<0.4	<5	6	138
927357	Drill Core		5.01	98	7	495	8	19	<0.5	<2	8	373	3.37	<5	<20	<4	7	440	<0.4	<5	9	152
927358	Drill Core		4.82	335	5	493	9	25	<0.5	<2	7	326	3.57	7	<20	<4	8	429	<0.4	<5	<5	155
927359	Drill Core		5.19	99	14	465	<5	23	<0.5	<2	7	301	3.05	<5	<20	<4	7	393	<0.4	<5	6	141
927360	Drill Core		0.93	<2	<2	3	<5	13	<0.5	<2	<2	153	0.37	<5	<20	<4	<2	49	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 3 of 8 Part 2

SMI09000207.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927331	Rock Pulp	1.84	0.103	14	25	1.40	719	0.28	7.91	3.00	3.45	4	75	6	13	8	2	13	0.6
927332	Drill Core	2.06	0.081	21	3	0.67	104	0.24	8.33	3.48	3.77	10	56	<2	10	7	2	6	2.3
927333	Drill Core	1.99	0.086	23	3	0.63	120	0.25	8.77	3.90	3.89	13	56	<2	11	8	2	5	1.7
927334	Drill Core	2.15	0.077	16	<2	0.48	77	0.20	7.64	3.32	3.44	17	53	<2	10	6	1	5	2.2
927335	Drill Core	1.87	0.081	18	4	0.61	169	0.24	7.72	3.91	2.89	4	59	<2	9	7	1	5	1.2
927336	Drill Core	1.39	0.082	21	3	0.66	137	0.24	8.00	4.02	2.96	<4	59	<2	10	7	1	5	1.2
927337	Drill Core	1.72	0.081	17	5	0.55	83	0.21	7.81	3.46	3.07	<4	58	<2	10	5	1	5	1.8
927338	Drill Core	1.97	0.080	17	3	0.60	117	0.23	7.55	3.49	2.99	<4	56	<2	9	7	1	5	1.3
927339	Drill Core	1.82	0.077	17	3	0.59	151	0.24	7.45	3.81	2.85	<4	56	<2	8	7	1	4	1.0
927340	Drill Core	22.37	0.044	2	<2	12.24	20	<0.01	0.12	0.02	0.07	<4	<2	<2	<2	<2	<1	<1	<0.1
927341	Drill Core	1.75	0.076	15	6	0.58	133	0.23	7.58	3.41	3.23	<4	54	<2	9	7	1	5	1.3
927342	Drill Core	2.51	0.076	15	2	0.53	196	0.23	7.40	3.59	3.28	<4	54	<2	9	6	1	4	1.0
927343	Drill Core	1.88	0.077	17	4	0.58	119	0.22	7.80	3.43	3.46	<4	54	<2	9	6	1	5	1.4
927344	Drill Core	1.88	0.082	18	2	0.59	142	0.24	8.03	3.77	2.96	<4	56	<2	9	7	1	5	1.2
927345	Drill Core	2.06	0.082	20	3	0.57	953	0.26	8.52	3.85	3.14	<4	60	<2	8	7	1	5	0.6
927346	Drill Core	2.15	0.081	18	2	0.64	418	0.24	7.88	3.60	2.60	<4	57	<2	8	7	1	5	0.9
927347	Drill Core	2.26	0.076	19	5	0.71	196	0.22	7.59	3.26	2.45	<4	53	<2	9	6	1	4	1.3
927348	Drill Core	1.99	0.082	19	2	0.58	200	0.25	8.20	3.91	2.71	<4	59	<2	8	8	1	5	1.0
927349	Drill Core	2.47	0.079	17	4	0.63	464	0.25	7.91	3.74	3.08	<4	58	<2	8	7	1	5	0.7
927350	Drill Core	22.02	0.024	2	<2	12.51	18	<0.01	0.13	0.01	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927351	Drill Core	2.00	0.083	18	3	0.59	166	0.25	8.17	3.91	2.95	<4	54	<2	9	7	2	5	1.1
927352	Drill Core	2.94	0.097	16	<2	0.66	161	0.29	8.17	3.78	2.98	<4	40	<2	10	7	1	5	1.3
927353	Drill Core	2.23	0.110	20	3	0.71	151	0.31	8.61	4.15	2.91	<4	46	<2	9	8	1	6	1.5
927354	Drill Core	2.44	0.104	17	3	0.65	204	0.30	8.19	3.73	2.95	<4	42	<2	9	7	1	6	1.0
927355	Drill Core	2.47	0.110	18	3	0.77	247	0.30	8.07	3.80	2.83	<4	43	<2	10	7	1	7	1.0
927356	Drill Core	2.19	0.105	16	4	0.73	316	0.30	7.93	3.53	2.82	<4	41	<2	9	7	1	6	0.8
927357	Drill Core	2.70	0.134	15	3	0.81	335	0.36	7.84	3.62	3.06	<4	35	<2	11	8	1	6	0.8
927358	Drill Core	2.20	0.142	17	<2	1.05	450	0.36	8.31	3.71	2.74	<4	35	<2	11	7	1	7	0.7
927359	Drill Core	2.30	0.129	17	3	0.96	1310	0.33	7.58	3.38	2.72	<4	32	<2	12	6	1	6	0.5
927360	Drill Core	22.34	0.024	<2	<2	12.33	20	<0.01	0.10	0.02	0.05	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 4 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000207.1

Analyte	Method	Unit	WGHT	3B	1E																	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	%	ppm	V														
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927361	Rock Pulp		0.13	658	3	5219	14	60	1.6	16	14	418	5.15	10	<20	<4	4	439	<0.4	<5	9	126
927362	Drill Core		4.67	142	6	570	<5	18	<0.5	<2	6	314	2.76	<5	<20	<4	8	318	<0.4	<5	<5	128
927363	Drill Core		5.14	70	4	438	6	20	<0.5	<2	8	427	3.53	15	<20	<4	5	389	<0.4	<5	8	145
927364	Drill Core		4.68	162	12	962	<5	22	0.6	<2	10	277	3.62	9	<20	<4	8	317	<0.4	<5	<5	145
927365	Drill Core		4.58	59	12	588	<5	13	<0.5	<2	11	251	2.97	8	<20	<4	9	411	<0.4	<5	8	122
927366	Drill Core		4.98	139	6	566	<5	16	<0.5	<2	7	338	2.97	109	<20	<4	9	438	<0.4	<5	7	121
927367	Drill Core		4.78	94	4	442	<5	17	<0.5	<2	7	266	3.11	7	<20	<4	10	401	<0.4	<5	7	123
927368	Drill Core		5.00	88	10	357	<5	15	<0.5	<2	6	221	2.70	31	<20	<4	9	460	<0.4	<5	5	121
927369	Drill Core		5.43	102	15	350	97	25	3.6	<2	10	450	3.34	108	<20	<4	11	409	<0.4	7	<5	142
927370	Drill Core		L.N.R.																			
927371	Drill Core		L.N.R.																			
927372	Drill Core		L.N.R.																			
927373	Drill Core		L.N.R.																			
927374	Drill Core		L.N.R.																			
927375	Drill Core		L.N.R.																			
927376	Drill Core		3.95	502	12	1973	9	24	1.9	6	10	603	5.21	353	<20	<4	11	290	<0.4	<5	<5	139
927377	Drill Core		5.41	243	28	1579	10	23	1.6	3	8	1022	2.62	151	<20	<4	9	316	<0.4	<5	<5	110
927378	Drill Core		5.00	83	12	616	11	32	0.9	<2	6	368	2.55	129	<20	<4	13	250	<0.4	<5	<5	108
927379	Drill Core		2.31	77	20	446	20	84	0.7	<2	7	288	2.64	59	<20	<4	19	251	0.6	<5	<5	109
927380	Drill Core		1.10	<2	<2	4	<5	18	<0.5	<2	<2	181	0.37	<5	<20	<4	<2	48	<0.4	<5	<5	3
927381	Drill Core		4.84	79	5	594	<5	23	0.8	<2	5	248	1.88	125	<20	<4	17	322	<0.4	<5	<5	101
927382	Drill Core		4.98	50	13	411	7	18	0.8	<2	5	262	2.22	110	<20	<4	16	253	<0.4	<5	<5	99
927383	Drill Core		4.56	38	3	248	13	34	0.6	<2	5	281	2.25	6	<20	<4	17	356	<0.4	<5	<5	97
927384	Drill Core		5.14	57	7	485	<5	13	0.7	<2	5	278	2.15	61	<20	<4	16	347	<0.4	<5	<5	99
927385	Drill Core		4.57	79	11	646	8	13	0.8	<2	6	196	2.30	134	<20	<4	17	296	<0.4	<5	<5	105
927386	Drill Core		5.35	52	19	580	<5	31	0.7	<2	7	290	2.58	68	<20	<4	18	235	<0.4	<5	<5	100
927387	Drill Core		5.07	97	12	613	9	17	0.8	<2	6	170	1.98	82	<20	<4	18	279	<0.4	<5	<5	100
927388	Drill Core		5.46	86	9	484	<5	16	0.6	<2	6	193	2.19	<5	<20	<4	17	305	<0.4	<5	<5	104
927389	Drill Core		5.60	80	6	569	14	44	0.6	<2	6	224	2.15	7	<20	<4	17	344	<0.4	<5	<5	103
927390	Drill Core		1.01	<2	<2	5	<5	13	<0.5	<2	<2	184	0.39	<5	<20	<4	<2	47	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 4 of 8 Part 2

SMI09000207.1

CERTIFICATE OF ANALYSIS

	Method	1E																	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927361	Rock Pulp	1.64	0.099	12	23	1.31	687	0.27	7.41	3.00	2.97	<4	72	4	12	8	1	12	0.6
927362	Drill Core	2.51	0.106	13	6	0.77	455	0.28	7.07	2.90	2.99	<4	29	<2	10	6	<1	5	0.7
927363	Drill Core	3.19	0.128	9	2	0.80	143	0.31	6.47	3.61	3.47	<4	33	<2	8	7	1	5	1.5
927364	Drill Core	2.01	0.128	14	3	1.00	100	0.32	7.80	3.19	2.90	<4	37	<2	12	7	1	6	1.8
927365	Drill Core	1.89	0.113	19	3	0.94	170	0.27	8.38	3.86	3.13	<4	33	<2	13	6	1	5	1.2
927366	Drill Core	2.44	0.106	15	6	0.96	298	0.28	7.98	4.01	2.88	<4	33	<2	11	7	1	5	0.9
927367	Drill Core	1.51	0.104	16	<2	0.94	247	0.28	8.55	3.99	3.03	<4	36	<2	11	7	1	5	1.0
927368	Drill Core	1.68	0.106	20	3	0.92	567	0.28	8.14	4.06	3.00	<4	37	<2	12	7	1	5	0.7
927369	Drill Core	2.51	0.107	21	4	0.75	370	0.29	8.51	3.50	3.66	4	40	<2	12	8	2	7	1.4
927370	Drill Core	L.N.R.																	
927371	Drill Core	L.N.R.																	
927372	Drill Core	L.N.R.																	
927373	Drill Core	L.N.R.																	
927374	Drill Core	L.N.R.																	
927375	Drill Core	L.N.R.																	
927376	Drill Core	2.80	0.101	17	11	1.02	87	0.23	7.18	2.83	2.19	<4	22	<2	12	5	1	7	2.8
927377	Drill Core	6.42	0.086	27	4	0.60	712	0.22	7.24	2.71	2.84	<4	25	<2	18	6	1	5	1.6
927378	Drill Core	2.74	0.088	23	3	0.90	759	0.22	7.79	2.27	2.76	<4	46	<2	9	7	1	4	0.9
927379	Drill Core	2.33	0.075	30	2	0.71	701	0.24	8.87	3.01	2.90	<4	71	<2	9	9	1	4	1.3
927380	Drill Core	22.06	0.027	3	<2	12.03	15	<0.01	0.11	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	
927381	Drill Core	1.93	0.078	23	4	0.49	2061	0.23	8.41	3.78	3.90	<4	59	<2	8	8	1	4	0.6
927382	Drill Core	2.10	0.076	26	4	0.57	1060	0.22	8.48	3.51	2.83	4	61	<2	8	7	1	4	0.8
927383	Drill Core	2.33	0.072	23	4	0.41	2337	0.23	8.17	3.68	4.36	<4	61	<2	9	8	1	4	0.5
927384	Drill Core	2.22	0.076	25	4	0.55	1748	0.22	8.24	3.77	3.45	<4	60	<2	9	7	1	4	0.6
927385	Drill Core	1.68	0.074	23	4	0.50	378	0.20	8.07	3.38	3.83	4	57	<2	9	7	1	4	1.0
927386	Drill Core	2.29	0.077	27	4	0.69	688	0.20	8.42	3.80	2.34	5	58	<2	9	6	1	4	1.2
927387	Drill Core	1.43	0.074	22	5	0.45	721	0.21	8.24	3.52	4.23	5	56	<2	8	7	1	4	0.8
927388	Drill Core	1.76	0.070	18	5	0.51	990	0.21	8.42	3.33	4.73	5	54	<2	8	6	1	4	0.6
927389	Drill Core	2.13	0.077	24	3	0.44	1147	0.21	8.08	3.35	4.39	<4	57	<2	9	7	2	4	0.7
927390	Drill Core	22.83	0.029	3	<2	12.16	27	<0.01	0.26	0.02	0.05	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 5 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000207.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927391	Rock Pulp	0.14	307	2	3377	26	69	1.4	17	7	354	3.75	<5	<20	<4	14	171	<0.4	<5	<5	45
927392	Drill Core	4.98	93	26	863	20	17	0.7	<2	7	213	2.09	50	<20	<4	15	276	<0.4	<5	<5	97
927393	Drill Core	5.36	69	24	747	<5	27	0.6	<2	8	266	2.27	71	<20	<4	18	303	<0.4	<5	<5	100
927394	Drill Core	4.21	93	22	916	12	18	1.0	<2	8	220	2.56	84	<20	<4	16	287	<0.4	<5	<5	104
927395	Drill Core	4.23	97	18	892	5	19	0.8	<2	8	273	2.59	263	<20	<4	18	325	<0.4	<5	<5	100
927396	Drill Core	3.91	165	22	1397	17	14	1.2	<2	7	242	2.46	114	<20	<4	16	316	<0.4	<5	<5	87
927397	Drill Core	3.49	70	9	617	9	19	1.0	2	7	277	3.03	<5	<20	<4	15	405	<0.4	<5	<5	97
927398	Drill Core	5.72	101	10	740	<5	23	1.0	9	10	405	4.31	<5	<20	<4	11	587	<0.4	<5	<5	161
927399	Drill Core	2.32	137	23	1031	<5	24	1.0	10	13	393	4.27	<5	<20	<4	10	499	<0.4	<5	<5	166
927400	Drill Core	1.22	<2	<2	4	<5	15	<0.5	<2	<2	188	0.38	<5	<20	<4	<2	49	<0.4	<5	<5	2
927401	Drill Core	9.38	109	10	856	6	22	0.9	5	9	351	3.44	<5	<20	<4	11	527	<0.4	<5	<5	130
927402	Drill Core	2.67	142	21	989	9	21	0.8	4	12	259	3.65	5	<20	<4	12	440	<0.4	<5	<5	144
927403	Drill Core	6.86	109	21	900	<5	23	0.7	3	9	346	3.23	<5	<20	<4	10	580	<0.4	<5	<5	136
927404	Drill Core	3.43	71	19	788	6	26	0.9	4	11	374	3.28	6	<20	<4	13	481	<0.4	<5	<5	139
927405	Drill Core	4.83	64	15	591	7	29	0.6	3	9	471	3.35	12	<20	<4	12	513	<0.4	<5	<5	142
927406	Drill Core	5.21	136	9	1082	<5	25	1.2	5	10	454	3.57	<5	<20	<4	12	477	<0.4	<5	<5	149
927407	Drill Core	4.46	114	23	887	7	18	1.1	5	10	280	2.49	<5	<20	<4	12	376	<0.4	<5	<5	141
927408	Drill Core	4.60	168	30	1210	8	24	1.3	3	9	356	3.06	<5	<20	<4	14	408	<0.4	<5	<5	139
927409	Drill Core	4.62	187	11	948	8	20	1.4	2	7	419	2.98	48	<20	<4	12	399	<0.4	<5	<5	118
927410	Drill Core	1.10	2	<2	6	5	15	<0.5	<2	<2	200	0.40	<5	<20	<4	<2	49	<0.4	<5	<5	3
927411	Drill Core	4.69	117	24	1337	7	19	1.4	3	7	351	3.15	6	<20	<4	6	336	<0.4	<5	<5	145
927412	Drill Core	4.66	94	19	1345	6	17	1.5	3	7	376	2.82	<5	<20	<4	7	306	<0.4	<5	<5	116
927413	Drill Core	4.74	234	18	1401	13	14	1.4	4	6	398	3.44	12	<20	<4	5	261	<0.4	6	<5	102
927414	Drill Core	5.06	227	68	1983	8	13	1.7	4	8	386	2.27	10	<20	<4	4	244	<0.4	<5	5	94
927415	Drill Core	2.92	336	16	2913	<5	19	2.3	4	6	336	2.48	6	<20	<4	6	203	<0.4	<5	<5	131
927416	Drill Core	5.31	226	67	1643	<5	15	0.7	9	8	316	2.04	<5	<20	<4	6	232	<0.4	<5	5	129
927417	Drill Core	4.31	163	50	2162	7	23	1.6	16	10	379	3.16	9	<20	<4	3	239	<0.4	<5	7	160
927418	Drill Core	4.81	190	7	1774	6	24	1.5	18	9	458	3.69	19	<20	<4	4	260	<0.4	<5	<5	181
927419	Drill Core	3.91	214	17	2077	7	25	1.7	16	9	466	3.61	27	<20	<4	3	233	<0.4	<5	<5	171
927420	Drill Core	1.04	<2	<2	10	<5	13	<0.5	<2	<2	192	0.40	<5	<20	<4	<2	49	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 5 of 8 Part 2

SMI09000207.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927391	Rock Pulp	1.36	0.044	27	17	0.53	820	0.16	7.13	2.43	3.62	6	60	9	14	10	3	7	0.4
927392	Drill Core	2.04	0.077	24	5	0.51	359	0.19	7.93	3.29	3.91	6	53	17	9	6	1	4	0.9
927393	Drill Core	2.46	0.073	25	8	0.60	791	0.21	8.48	3.47	3.93	<4	57	<2	9	7	1	4	0.8
927394	Drill Core	2.13	0.071	22	5	0.56	175	0.19	8.42	3.22	4.35	6	51	2	9	5	1	4	1.4
927395	Drill Core	2.92	0.073	24	4	0.72	213	0.18	7.87	3.04	3.24	4	49	<2	10	6	1	4	1.2
927396	Drill Core	2.96	0.067	21	5	0.41	162	0.18	7.77	2.88	4.35	5	48	<2	9	5	1	4	2.0
927397	Drill Core	2.73	0.079	21	4	0.60	160	0.23	8.20	3.61	4.18	<4	50	<2	11	7	2	4	1.6
927398	Drill Core	3.67	0.124	26	15	0.99	235	0.32	8.60	4.03	3.09	<4	34	<2	17	7	2	9	1.2
927399	Drill Core	4.10	0.124	23	19	0.85	155	0.33	8.20	4.33	2.63	<4	41	<2	17	7	1	9	1.5
927400	Drill Core	22.66	0.023	3	<2	12.20	16	<0.01	0.08	0.02	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927401	Drill Core	3.70	0.115	21	6	0.62	164	0.30	8.34	4.24	3.25	4	46	<2	13	8	2	6	1.8
927402	Drill Core	2.82	0.122	25	8	0.79	113	0.29	8.80	4.42	3.44	5	44	<2	14	7	1	6	2.1
927403	Drill Core	3.40	0.111	27	4	0.65	418	0.31	8.89	4.41	3.34	4	49	<2	12	9	2	6	1.0
927404	Drill Core	3.10	0.112	21	5	0.71	291	0.30	8.70	4.40	3.32	6	41	<2	12	8	2	6	1.3
927405	Drill Core	3.10	0.115	25	4	0.75	547	0.31	9.06	4.48	3.24	<4	46	<2	12	9	1	6	1.0
927406	Drill Core	3.09	0.122	23	7	0.82	456	0.31	8.73	4.24	3.30	5	42	<2	12	8	1	7	1.0
927407	Drill Core	2.36	0.106	23	8	0.80	169	0.29	8.40	4.00	3.60	<4	33	<2	12	7	1	6	1.3
927408	Drill Core	2.92	0.105	29	5	0.91	150	0.29	8.54	4.05	3.48	5	36	<2	14	8	2	6	1.6
927409	Drill Core	3.08	0.101	20	3	0.81	160	0.27	8.05	3.37	3.59	4	39	<2	11	7	1	5	1.4
927410	Drill Core	21.35	0.020	2	<2	11.84	26	<0.01	0.18	0.03	0.04	<4	<2	<2	<2	<1	<1	<0.1	
927411	Drill Core	1.79	0.107	18	5	1.03	186	0.28	8.13	3.86	3.41	4	43	<2	11	8	1	6	1.1
927412	Drill Core	2.54	0.093	15	5	0.85	181	0.25	7.27	3.67	3.28	<4	38	<2	11	7	1	5	1.2
927413	Drill Core	3.24	0.078	14	8	0.61	83	0.23	6.18	3.33	3.34	<4	30	<2	10	6	<1	4	2.8
927414	Drill Core	3.10	0.080	14	5	0.56	157	0.24	6.13	2.84	3.45	5	30	<2	10	7	<1	4	1.5
927415	Drill Core	1.82	0.103	12	5	0.85	235	0.28	7.14	2.85	3.80	4	35	<2	10	7	<1	5	0.9
927416	Drill Core	2.20	0.112	18	20	0.75	549	0.25	6.34	3.19	3.40	<4	40	<2	13	6	<1	6	0.7
927417	Drill Core	2.27	0.121	21	30	0.84	197	0.27	6.46	3.01	3.41	5	47	<2	12	7	<1	8	1.1
927418	Drill Core	2.39	0.102	14	29	0.85	184	0.29	6.62	3.15	3.20	<4	47	<2	9	7	<1	8	1.4
927419	Drill Core	2.68	0.098	11	28	0.81	136	0.27	6.21	2.82	3.46	<4	40	<2	10	6	<1	8	1.8
927420	Drill Core	22.17	0.027	2	<2	12.08	17	<0.01	0.16	0.02	0.05	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 6 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000207.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
927421	Rock Pulp		0.17	617	3	5305	10	62	1.9	17	14	445	5.35	<5	<20	<4	3	449	<0.4	<5	5	128
927422	Drill Core		5.17	198	11	1526	14	51	1.6	13	7	492	3.45	35	<20	<4	4	266	<0.4	<5	<5	156
927423	Drill Core		3.41	230	3	1688	5	24	1.2	10	6	484	3.64	12	<20	<4	4	315	<0.4	<5	<5	155
927424	Drill Core		1.35	156	6	1234	8	42	1.3	8	6	582	3.35	134	<20	<4	3	414	<0.4	<5	10	153
927425	Drill Core		2.87	227	<2	1937	10	36	1.6	10	7	551	3.57	17	<20	<4	3	354	<0.4	<5	<5	136
927426	Drill Core		4.67	261	3	1629	8	25	0.9	9	6	410	3.71	8	<20	<4	6	360	<0.4	<5	<5	150
927427	Drill Core		4.37	336	21	2199	6	19	1.1	5	9	480	3.66	<5	<20	<4	6	361	<0.4	<5	<5	155
927428	Drill Core		5.00	746	5	1384	12	19	0.7	6	7	520	6.45	11	<20	<4	4	323	<0.4	8	<5	162
927429	Drill Core		4.84	163	5	995	9	28	0.8	3	7	576	4.41	<5	<20	<4	6	360	<0.4	<5	<5	183
927430	Drill Core		1.19	<2	<2	4	<5	14	<0.5	<2	<2	175	0.35	<5	<20	<4	<2	47	<0.4	<5	<5	3
927431	Drill Core		4.69	164	<2	932	6	28	0.5	2	7	663	4.39	14	<20	<4	7	427	<0.4	<5	<5	186
927432	Drill Core		4.99	173	12	1182	8	21	1.0	3	8	578	3.91	9	<20	<4	6	372	<0.4	<5	<5	173
927433	Drill Core		4.34	105	3	789	10	19	0.5	3	7	475	3.40	10	<20	<4	6	335	<0.4	<5	<5	184
927434	Drill Core		4.08	111	6	912	6	21	0.8	3	7	553	3.78	12	<20	<4	3	352	<0.4	<5	<5	194
927435	Drill Core		3.35	135	3	821	10	22	1.2	2	8	558	4.51	19	<20	<4	4	358	<0.4	<5	<5	169
927436	Drill Core		4.39	173	4	732	11	14	0.7	3	7	786	3.76	16	<20	<4	6	364	<0.4	<5	<5	155
927437	Drill Core		4.20	131	3	583	25	32	1.5	3	6	580	6.97	21	<20	<4	5	436	<0.4	<5	<5	163
927438	Drill Core		4.58	148	5	1460	16	25	1.5	5	10	508	5.06	17	<20	<4	3	379	<0.4	<5	<5	161
927439	Drill Core		3.24	145	11	1807	13	31	1.3	3	11	457	4.11	10	<20	<4	4	392	<0.4	<5	<5	176
927440	Drill Core		1.17	<2	<2	5	6	14	<0.5	<2	<2	191	0.37	<5	<20	<4	<2	50	<0.4	<5	<5	3
927441	Drill Core		8.30	125	8	1445	17	33	0.9	4	9	605	3.55	148	<20	<4	4	432	<0.4	<5	<5	145
927442	Drill Core		4.06	198	8	2052	9	34	1.6	4	12	505	4.35	7	<20	<4	5	368	<0.4	<5	<5	159
927443	Drill Core		4.42	162	9	1768	7	56	1.1	4	10	457	3.79	6	<20	<4	4	391	<0.4	<5	<5	180
927444	Drill Core		4.98	97	10	988	7	26	0.6	3	10	504	4.46	7	<20	<4	2	381	<0.4	<5	<5	180
927445	Drill Core		5.25	413	48	3246	13	41	1.3	7	20	566	5.32	<5	<20	<4	8	382	1.2	<5	<5	180
927446	Drill Core		4.75	351	29	2840	15	26	1.0	4	13	441	4.49	6	<20	<4	6	370	0.8	<5	<5	202
927447	Drill Core		5.74	371	9	3313	10	23	1.5	5	25	347	3.81	<5	<20	<4	6	308	0.8	<5	<5	172
927448	Drill Core		3.11	242	15	1964	8	17	1.0	3	7	327	2.40	<5	<20	<4	9	280	<0.4	<5	5	123
927449	Drill Core		1.72	209	32	2007	12	17	<0.5	2	8	269	2.11	<5	<20	<4	6	325	<0.4	<5	<5	118
927450	Drill Core		0.90	<2	<2	5	<5	13	<0.5	<2	<2	181	0.41	<5	<20	<4	<2	45	<0.4	<5	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 6 of 8 Part 2

SMI09000207.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927421	Rock Pulp	1.72	0.098	12	23	1.34	706	0.28	7.28	2.95	3.49	5	76	5	12	9	2	12	0.6
927422	Drill Core	2.88	0.096	13	23	0.75	130	0.27	6.26	3.09	3.28	<4	41	<2	9	7	<1	7	1.8
927423	Drill Core	3.25	0.096	12	15	0.90	115	0.28	6.65	3.33	3.42	<4	34	<2	11	7	1	7	2.1
927424	Drill Core	3.72	0.090	10	15	0.84	166	0.26	6.12	3.41	3.06	<4	34	<2	10	7	1	6	1.7
927425	Drill Core	3.86	0.095	11	15	0.71	114	0.29	6.49	3.48	3.65	<4	37	<2	9	7	1	7	2.3
927426	Drill Core	2.87	0.110	14	13	1.02	155	0.31	7.41	3.68	3.35	<4	40	<2	11	8	1	8	1.6
927427	Drill Core	4.49	0.135	17	5	1.06	121	0.31	7.13	3.48	3.35	<4	24	<2	17	7	1	9	2.6
927428	Drill Core	4.29	0.114	16	4	0.98	77	0.31	6.68	3.39	2.82	<4	22	<2	15	8	1	9	5.7
927429	Drill Core	3.77	0.134	16	4	0.89	155	0.35	7.25	3.45	3.56	<4	27	<2	14	9	1	10	1.7
927430	Drill Core	21.47	0.029	2	<2	11.90	16	<0.01	0.13	0.02	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927431	Drill Core	3.41	0.141	18	5	1.09	228	0.37	7.66	3.49	3.43	<4	27	<2	16	9	1	12	1.3
927432	Drill Core	3.88	0.138	17	4	0.97	111	0.35	7.14	3.62	3.04	<4	25	<2	13	8	1	11	2.3
927433	Drill Core	3.26	0.141	16	4	0.77	139	0.36	7.42	3.91	3.56	<4	30	<2	11	9	1	10	1.9
927434	Drill Core	3.62	0.140	19	4	0.92	149	0.37	7.42	3.86	3.43	<4	29	<2	12	9	1	11	1.8
927435	Drill Core	4.21	0.133	19	3	0.76	84	0.33	7.29	3.40	3.69	<4	34	<2	12	9	1	10	3.3
927436	Drill Core	5.57	0.122	25	4	0.70	132	0.30	7.20	3.65	2.70	<4	31	<2	15	7	1	10	3.0
927437	Drill Core	5.43	0.127	24	4	0.69	88	0.30	7.06	3.76	2.11	<4	29	<2	15	8	1	11	6.7
927438	Drill Core	5.12	0.125	19	7	0.54	86	0.32	6.64	3.21	3.52	<4	33	<2	12	8	1	11	4.6
927439	Drill Core	3.73	0.140	17	3	0.83	107	0.35	7.15	3.45	3.99	<4	34	<2	11	9	1	11	2.6
927440	Drill Core	21.52	0.023	2	<2	12.06	15	<0.01	0.16	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	
927441	Drill Core	4.60	0.135	17	4	0.77	124	0.33	6.82	3.46	2.99	<4	37	<2	11	8	1	10	2.0
927442	Drill Core	4.06	0.142	22	4	0.85	105	0.33	7.33	3.51	3.67	<4	43	<2	12	9	1	11	3.0
927443	Drill Core	3.63	0.130	20	5	0.71	125	0.32	6.90	3.17	3.72	<4	43	<2	12	8	1	10	2.3
927444	Drill Core	3.70	0.123	18	5	0.83	90	0.31	6.84	3.20	3.38	<4	44	<2	13	8	1	9	2.7
927445	Drill Core	3.23	0.143	22	4	1.31	94	0.29	8.25	3.54	3.13	<4	43	<2	20	6	1	10	2.2
927446	Drill Core	2.96	0.126	21	5	1.07	80	0.31	7.41	2.66	2.78	<4	38	<2	16	5	1	9	2.1
927447	Drill Core	2.69	0.105	23	8	1.04	74	0.26	6.81	2.73	2.63	<4	32	<2	14	4	<1	8	2.1
927448	Drill Core	2.68	0.086	18	5	0.74	166	0.24	6.80	2.26	3.44	<4	43	<2	11	4	<1	7	1.1
927449	Drill Core	2.25	0.092	17	4	0.82	162	0.26	6.98	2.45	3.53	<4	36	<2	14	5	1	8	1.2
927450	Drill Core	22.55	0.030	<2	<2	12.20	19	<0.01	0.07	<0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 7 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000207.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	ppm
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927451	Rock Pulp	0.08	301	<2	3212	32	67	0.9	17	6	336	3.49	<5	<20	<4	12	167	0.6	<5	12	43
927452	Drill Core	4.73	222	23	3029	14	23	1.4	4	13	345	2.47	<5	<20	<4	7	348	<0.4	<5	8	155
927453	Drill Core	4.59	423	7	2190	13	27	0.6	7	10	275	2.80	<5	<20	<4	6	310	<0.4	<5	7	147
927454	Drill Core	6.31	511	11	1708	11	27	<0.5	8	9	311	3.22	<5	<20	<4	6	304	0.5	<5	<5	177
927455	Drill Core	6.57	273	9	1550	14	31	0.6	6	13	270	4.24	<5	<20	<4	7	338	0.4	<5	<5	161
927456	Drill Core	3.84	351	7	2920	12	27	1.1	15	12	214	2.47	<5	<20	<4	3	371	<0.4	<5	9	195
927457	Drill Core	2.99	292	49	2217	16	29	1.1	13	12	267	2.81	7	<20	<4	4	401	<0.4	<5	<5	198
927458	Drill Core	4.02	201	44	1927	15	23	1.2	9	11	198	2.30	6	<20	<4	5	359	<0.4	<5	<5	150
927459	Drill Core	2.65	189	10	2575	8	26	1.3	12	11	196	2.16	<5	<20	<4	6	489	<0.4	<5	<5	191
927460	Drill Core	1.18	<2	<2	5	<5	12	<0.5	<2	<2	177	0.40	<5	<20	<4	<2	44	<0.4	<5	<5	2
927461	Drill Core	4.86	246	8	2545	11	32	1.1	7	14	218	2.03	<5	<20	<4	11	681	0.4	<5	<5	227
927462	Drill Core	4.86	372	47	2974	15	28	1.1	5	14	155	2.08	<5	<20	<4	13	641	<0.4	<5	<5	200
927463	Drill Core	4.64	261	35	2133	13	23	0.8	4	10	146	1.89	<5	<20	<4	13	584	<0.4	<5	<5	186
927464	Drill Core	9.33	506	37	3431	11	20	1.1	4	18	212	3.14	<5	<20	<4	11	561	0.5	<5	<5	164
927465	Drill Core	4.67	390	25	2529	11	21	0.7	3	14	160	2.15	<5	<20	<4	11	412	<0.4	<5	<5	139
927466	Drill Core	4.89	219	25	1661	14	18	1.1	3	9	199	1.92	<5	<20	<4	13	492	<0.4	<5	<5	130
927467	Drill Core	4.54	218	43	2572	13	22	1.4	5	15	185	2.62	<5	<20	<4	13	472	<0.4	<5	<5	187
927468	Drill Core	4.97	381	40	3191	14	19	0.9	4	11	192	2.40	<5	<20	<4	8	420	<0.4	<5	<5	154
927469	Drill Core	4.72	312	113	2945	9	29	1.2	5	25	321	3.97	<5	<20	<4	10	578	0.5	<5	<5	225
927470	Drill Core	1.16	3	<2	5	<5	11	<0.5	<2	<2	180	0.39	<5	<20	<4	<2	44	<0.4	<5	<5	3
927471	Drill Core	4.94	175	37	2493	12	26	1.1	4	25	400	3.81	<5	<20	<4	11	565	0.5	<5	<5	213
927472	Drill Core	4.94	171	52	2533	12	26	1.4	5	25	474	4.37	<5	<20	<4	9	573	0.6	<5	<5	262
927473	Drill Core	5.05	93	88	1724	11	21	1.6	3	20	436	3.37	<5	<20	<4	10	485	0.5	<5	<5	211
927474	Drill Core	4.44	169	90	1823	16	25	1.0	6	23	456	4.17	5	<20	<4	11	565	0.6	<5	<5	251
927475	Drill Core	5.02	401	30	3113	14	29	1.7	5	19	402	3.19	<5	<20	<4	8	375	0.5	<5	<5	183
927476	Drill Core	5.79	253	46	1997	13	28	1.9	8	17	653	3.71	8	<20	<4	8	347	0.5	<5	<5	209
927477	Drill Core	5.75	231	10	2044	13	25	0.7	16	25	384	5.08	<5	<20	<4	4	563	0.9	<5	<5	176
927478	Drill Core	5.54	218	8	1729	13	23	0.5	12	23	359	4.23	<5	<20	<4	5	524	0.8	<5	<5	178
927479	Drill Core	6.22	220	15	2018	12	24	0.9	9	18	326	3.51	<5	<20	<4	6	528	<0.4	<5	<5	176
927480	Drill Core	1.03	<2	<2	3	<5	14	<0.5	<2	<2	167	0.39	<5	<20	<4	<2	43	<0.4	<5	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 02, 2009

Page: 7 of 8 Part 2

SMI09000207.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927451	Rock Pulp	1.26	0.043	28	15	0.51	782	0.16	6.95	2.37	2.24	<4	54	9	14	9	2	7	0.3
927452	Drill Core	2.55	0.120	19	6	0.89	194	0.30	7.94	2.86	3.85	<4	44	3	12	5	1	9	1.1
927453	Drill Core	2.00	0.108	18	12	0.94	137	0.25	7.85	3.15	4.15	<4	34	<2	12	5	1	8	1.3
927454	Drill Core	2.00	0.114	20	11	1.11	133	0.29	7.69	2.75	3.21	<4	41	<2	12	5	1	8	1.3
927455	Drill Core	1.38	0.116	22	9	1.07	63	0.28	8.32	3.34	3.10	<4	47	<2	11	6	1	8	2.1
927456	Drill Core	1.63	0.147	19	32	0.66	102	0.35	8.29	3.77	3.14	4	38	<2	10	4	<1	10	1.6
927457	Drill Core	2.07	0.155	20	24	1.14	112	0.35	8.05	2.92	3.18	4	42	<2	13	5	1	11	1.5
927458	Drill Core	1.26	0.133	25	21	0.72	90	0.28	8.56	4.18	3.00	5	47	<2	9	4	1	8	1.4
927459	Drill Core	1.25	0.170	27	20	0.89	120	0.34	9.17	4.97	2.57	<4	44	<2	10	5	1	11	1.0
927460	Drill Core	22.20	0.032	2	<2	12.21	23	<0.01	0.07	0.02	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927461	Drill Core	1.82	0.187	25	6	0.63	135	0.38	9.62	5.25	2.41	7	62	<2	10	6	2	14	1.1
927462	Drill Core	1.33	0.123	35	8	0.60	111	0.32	9.17	5.35	2.23	5	48	<2	10	7	2	9	1.2
927463	Drill Core	1.22	0.129	35	6	0.67	186	0.32	9.24	5.69	1.96	<4	48	<2	11	8	1	9	0.9
927464	Drill Core	2.65	0.105	37	8	0.88	90	0.27	7.85	4.73	1.47	4	43	<2	18	6	2	7	1.9
927465	Drill Core	1.31	0.099	26	4	0.84	113	0.24	8.70	4.16	2.57	<4	48	<2	15	5	1	6	1.0
927466	Drill Core	1.39	0.113	25	5	0.84	179	0.27	9.14	4.98	2.52	<4	51	<2	16	6	1	7	0.8
927467	Drill Core	1.09	0.159	28	5	1.04	85	0.33	9.06	4.95	2.21	<4	54	<2	17	6	2	10	1.4
927468	Drill Core	2.09	0.140	19	12	0.95	117	0.28	7.07	3.47	2.23	<4	41	<2	15	5	1	10	1.4
927469	Drill Core	2.58	0.174	29	4	1.34	83	0.37	8.99	4.79	1.54	<4	52	<2	20	6	2	13	1.7
927470	Drill Core	22.24	0.021	<2	<2	12.26	19	<0.01	0.08	0.02	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927471	Drill Core	2.87	0.175	30	4	1.32	120	0.35	8.81	4.70	1.54	<4	49	<2	20	6	2	13	1.7
927472	Drill Core	3.65	0.184	27	10	1.32	78	0.41	8.49	4.77	1.32	<4	53	<2	21	7	1	15	2.3
927473	Drill Core	3.22	0.169	29	7	0.97	94	0.33	7.40	4.13	1.30	<4	57	<2	19	6	1	12	1.8
927474	Drill Core	3.06	0.200	29	4	1.26	66	0.39	8.80	4.84	1.57	<4	67	<2	20	7	2	12	2.5
927475	Drill Core	2.43	0.140	21	3	1.27	122	0.31	8.97	3.58	2.92	5	54	<2	14	6	1	8	1.5
927476	Drill Core	3.65	0.124	34	7	1.03	72	0.30	7.55	3.96	2.48	5	46	<2	19	6	1	11	2.7
927477	Drill Core	3.44	0.131	20	24	1.41	89	0.34	8.53	4.51	1.52	<4	35	<2	18	4	1	11	1.9
927478	Drill Core	3.19	0.127	17	18	1.25	79	0.32	8.35	4.64	1.57	<4	38	<2	16	4	1	10	1.7
927479	Drill Core	3.11	0.119	18	12	1.02	125	0.31	8.40	3.93	2.59	<4	49	<2	19	5	1	8	1.3
927480	Drill Core	21.99	0.021	2	<2	12.29	23	<0.01	0.10	0.01	0.06	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 8 of 8 Part 1

SMI09000207.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927481	Rock Pulp	0.08	300	<2	3212	29	69	1.0	16	7	343	3.52	<5	<20	<4	11	167	<0.4	<5	<5	43
927482	Drill Core	6.53	221	12	1912	11	28	<0.5	6	19	377	4.65	<5	<20	<4	6	492	0.7	<5	<5	180
927483	Drill Core	4.51	134	11	1222	10	23	<0.5	4	15	306	3.92	<5	<20	<4	6	805	<0.4	<5	<5	178
927484	Drill Core	3.59	110	16	1100	14	32	<0.5	4	18	293	4.18	<5	<20	<4	6	641	<0.4	<5	<5	162
927485	Drill Core	3.93	310	13	2437	12	27	0.8	47	21	451	5.99	<5	<20	<4	<2	279	0.9	<5	<5	287
927486	Drill Core	4.33	279	4	2058	7	29	<0.5	29	16	371	4.44	<5	<20	<4	4	294	0.7	<5	<5	196
927487	Drill Core	4.89	369	6	3095	9	29	0.7	46	31	449	5.89	<5	<20	<4	<2	319	1.0	<5	<5	241
927488	Drill Core	4.33	194	8	2036	12	31	0.5	46	34	550	7.85	<5	<20	<4	4	340	1.3	<5	<5	237
927489	Drill Core	7.13	232	8	2195	12	36	0.6	52	40	576	9.52	<5	<20	<4	2	295	1.7	<5	6	250
927490	Drill Core	1.19	<2	<2	6	<5	14	<0.5	<2	<2	174	0.41	<5	<20	<4	<2	46	<0.4	<5	<5	3
927491	Drill Core	6.62	157	11	1417	12	32	<0.5	29	21	596	5.53	<5	<20	<4	2	262	0.8	<5	<5	255
927492	Drill Core	2.16	278	15	1079	16	24	<0.5	18	12	515	5.29	<5	<20	<4	3	281	0.7	<5	<5	272
927493	Drill Core	2.44	217	6	1291	17	29	<0.5	9	9	461	3.85	<5	<20	<4	5	495	0.6	<5	<5	254
927494	Drill Core	4.37	255	5	1504	13	34	<0.5	5	12	462	3.75	5	<20	<4	7	609	0.5	<5	<5	247
927495	Drill Core	4.74	332	5	1338	11	31	<0.5	9	12	498	3.86	<5	<20	<4	4	538	0.6	<5	<5	226
927496	Drill Core	4.61	442	6	1197	12	31	<0.5	6	9	455	3.57	<5	<20	<4	6	572	0.5	<5	<5	247
927497	Drill Core	3.53	346	4	685	10	28	<0.5	7	6	405	3.10	<5	<20	<4	4	356	<0.4	<5	<5	228



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 8 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000207.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927481	Rock Pulp	1.25	0.044	25	19	0.50	798	0.15	6.76	2.39	3.65	5	51	6	13	10	2	7	0.3
927482	Drill Core	2.76	0.132	14	4	1.18	191	0.31	7.80	3.36	3.31	7	52	<2	16	6	1	7	1.4
927483	Drill Core	3.48	0.143	15	3	0.90	141	0.37	8.17	3.50	3.84	5	64	<2	18	7	2	8	2.0
927484	Drill Core	3.77	0.148	16	5	0.97	122	0.34	7.79	3.24	4.12	<4	61	<2	19	7	1	7	2.4
927485	Drill Core	3.85	0.156	18	76	0.96	168	0.34	6.37	3.69	1.64	<4	36	<2	21	4	<1	12	1.8
927486	Drill Core	3.56	0.129	16	51	1.19	150	0.35	6.69	3.26	3.23	<4	37	<2	19	5	<1	12	1.8
927487	Drill Core	3.82	0.132	20	92	1.55	147	0.37	6.62	4.03	1.50	5	38	<2	21	4	1	15	2.6
927488	Drill Core	4.49	0.131	18	48	1.16	150	0.35	6.57	3.72	1.43	5	40	<2	20	5	<1	13	1.9
927489	Drill Core	3.87	0.114	16	50	1.31	243	0.33	5.77	2.81	1.71	4	35	<2	18	4	<1	12	1.5
927490	Drill Core	21.99	0.028	2	<2	12.21	20	<0.01	0.10	0.02	0.06	<4	<2	<2	<2	<2	<1	<1	<0.1
927491	Drill Core	3.97	0.122	15	59	1.41	293	0.35	5.83	2.40	2.56	5	37	<2	20	5	<1	13	1.1
927492	Drill Core	4.02	0.115	10	49	0.74	80	0.33	5.77	2.73	2.48	<4	35	<2	16	5	<1	10	3.0
927493	Drill Core	3.37	0.135	10	8	0.84	496	0.35	7.22	4.34	2.36	6	46	<2	15	6	1	10	0.9
927494	Drill Core	3.45	0.153	19	4	0.99	421	0.36	8.04	4.58	2.25	6	48	<2	18	6	1	12	1.1
927495	Drill Core	3.50	0.138	11	11	1.04	540	0.36	7.11	3.67	2.91	<4	41	2	15	6	1	10	0.8
927496	Drill Core	3.05	0.145	14	6	1.13	1651	0.37	7.57	3.37	3.35	<4	38	<2	16	5	1	11	0.4
927497	Drill Core	2.34	0.097	9	6	0.76	1713	0.27	6.48	2.38	3.44	<4	37	<2	9	4	<1	6	0.4



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 02, 2009

Page:

1 of 4 Part 1

QUALITY CONTROL REPORT

SMI09000207.1

	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
	MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
Pulp Duplicates																					
REP 927315	QC		207																		
927319	Drill Core	4.83	692	17	3493	<5	24	1.6	19	11	306	2.73	<5	<20	<4	3	224	<0.4	<5	<5	176
REP 927319	QC			15	3467	<5	23	1.5	18	10	296	2.64	<5	<20	<4	5	221	<0.4	<5	<5	172
927339	Drill Core	4.43	29	5	207	5	15	<0.5	<2	6	223	2.38	9	<20	<4	9	396	<0.4	<5	6	103
REP 927339	QC			5	213	8	15	<0.5	<2	6	228	2.42	12	<20	<4	10	403	<0.4	<5	6	105
927351	Drill Core	0.90	41	15	374	8	19	<0.5	<2	7	263	2.52	12	<20	<4	10	456	<0.4	<5	7	101
REP 927351	QC		40																		
927361	Rock Pulp	0.13	658	3	5219	14	60	1.6	16	14	418	5.15	10	<20	<4	4	439	<0.4	<5	9	126
REP 927361	QC		635																		
927402	Drill Core	2.67	142	21	989	9	21	0.8	4	12	259	3.65	5	<20	<4	12	440	<0.4	<5	<5	144
REP 927402	QC		141																		
927406	Drill Core	5.21	136	9	1082	<5	25	1.2	5	10	454	3.57	<5	<20	<4	12	477	<0.4	<5	<5	149
REP 927406	QC			8	997	6	23	1.1	4	9	418	3.29	6	<20	<4	12	432	<0.4	<5	<5	138
927437	Drill Core	4.20	131	3	583	25	32	1.5	3	6	580	6.97	21	<20	<4	5	436	<0.4	<5	<5	163
REP 927437	QC			3	570	25	40	1.3	3	7	588	7.11	21	<20	<4	4	426	<0.4	7	6	163
927441	Drill Core	8.30	125	8	1445	17	33	0.9	4	9	605	3.55	148	<20	<4	4	432	<0.4	<5	<5	145
REP 927441	QC		127																		
927445	Drill Core	5.25	413	48	3246	13	41	1.3	7	20	566	5.32	<5	<20	<4	8	382	1.2	<5	<5	180
REP 927445	QC			45	3164	11	37	1.5	7	19	557	5.24	<5	<20	<4	8	370	1.1	<5	<5	178
927495	Drill Core	4.74	332	5	1338	11	31	<0.5	9	12	498	3.86	<5	<20	<4	4	538	0.6	<5	<5	226
REP 927495	QC		351																		
Core Reject Duplicates																					
927315	Drill Core	4.73	220	6	1178	<5	24	0.7	5	8	372	2.35	<5	<20	<4	7	294	<0.4	<5	<5	149
DUP 927315	QC		225	5	1220	<5	23	0.7	4	8	367	2.34	<5	<20	<4	7	292	<0.4	<5	<5	149
927350	Drill Core	5.54	<2	<2	2	<5	13	<0.5	<2	<2	167	0.39	<5	<20	<4	<2	43	<0.4	<5	<5	3
DUP 927350	QC		<2	<2	<2	<5	13	<0.5	<2	<2	163	0.39	<5	<20	<4	<2	43	<0.4	<5	<5	3
927385	Drill Core	4.57	79	11	646	8	13	0.8	<2	6	196	2.30	134	<20	<4	17	296	<0.4	<5	<5	105
DUP 927385	QC		73	11	660	9	13	0.9	<2	6	193	2.27	137	<20	<4	17	298	<0.4	<5	<5	104

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 02, 2009

www.acmelab.com

Page:

1 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000207.1

Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc
Unit	%	%	ppm	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1
Pulp Duplicates																	
REP 927315	QC																
927319	Drill Core	1.83	0.112	13	31	0.70	1203	0.30	7.65	3.58	3.12	6	37	<2	8	5	1
REP 927319	QC	1.81	0.107	12	31	0.68	984	0.29	7.69	3.58	3.05	8	35	<2	8	5	1
927339	Drill Core	1.82	0.077	17	3	0.59	151	0.24	7.45	3.81	2.85	<4	56	<2	8	7	1
REP 927339	QC	1.86	0.078	17	4	0.61	138	0.25	7.64	3.84	2.83	<4	56	<2	9	6	1
927351	Drill Core	2.00	0.083	18	3	0.59	166	0.25	8.17	3.91	2.95	<4	54	<2	9	7	2
REP 927351	QC																
927361	Rock Pulp	1.64	0.099	12	23	1.31	687	0.27	7.41	3.00	2.97	<4	72	4	12	8	1
REP 927361	QC																
927402	Drill Core	2.82	0.122	25	8	0.79	113	0.29	8.80	4.42	3.44	5	44	<2	14	7	1
REP 927402	QC																
927406	Drill Core	3.09	0.122	23	7	0.82	456	0.31	8.73	4.24	3.30	5	42	<2	12	8	1
REP 927406	QC	2.85	0.110	20	7	0.76	445	0.29	7.89	3.87	3.24	4	39	<2	11	8	1
927437	Drill Core	5.43	0.127	24	4	0.69	88	0.30	7.06	3.76	2.11	<4	29	<2	15	8	1
REP 927437	QC	5.57	0.127	23	4	0.69	84	0.30	6.96	3.81	2.14	<4	29	<2	15	7	1
927441	Drill Core	4.60	0.135	17	4	0.77	124	0.33	6.82	3.46	2.99	<4	37	<2	11	8	1
REP 927441	QC																
927445	Drill Core	3.23	0.143	22	4	1.31	94	0.29	8.25	3.54	3.13	<4	43	<2	20	6	1
REP 927445	QC	3.19	0.137	25	3	1.31	77	0.30	8.24	3.47	2.46	<4	46	<2	20	6	1
927495	Drill Core	3.50	0.138	11	11	1.04	540	0.36	7.11	3.67	2.91	<4	41	2	15	6	1
REP 927495	QC																
Core Reject Duplicates																	
927315	Drill Core	3.09	0.133	15	5	0.68	978	0.29	8.04	4.29	2.97	5	51	<2	11	7	1
DUP 927315	QC	2.99	0.126	15	4	0.67	844	0.28	8.03	4.33	2.97	4	50	<2	11	6	1
927350	Drill Core	22.02	0.024	2	<2	12.51	18	<0.01	0.13	0.01	0.05	<4	<2	<2	<2	<1	<1
DUP 927350	QC	21.99	0.023	2	<2	12.54	20	<0.01	0.11	0.03	0.06	<4	<2	<2	<2	<1	<1
927385	Drill Core	1.68	0.074	23	4	0.50	378	0.20	8.07	3.38	3.83	4	57	<2	9	7	1
DUP 927385	QC	1.71	0.073	24	4	0.51	362	0.20	8.25	3.48	3.95	<4	57	<2	9	6	1



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunc

Report Date:

October 02, 2009

www.acmelab.com

Page:

2 of 4 Part

QUALITY CONTROL REPORT

SMI09000207.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

Page: 2 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000207.1

		1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S
		% 0.01	% 0.002	ppm 2	ppm 2	% 0.01	ppm 1	% 0.01	% 0.01	% 0.01	% 0.01	ppm 4	ppm 2	ppm 2	ppm 2	ppm 2	ppm 1	ppm 1	% 0.1
927420	Drill Core	22.17	0.027	2	<2	12.08	17	<0.01	0.16	0.02	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
DUP 927420	QC	20.73	0.025	2	<2	11.58	15	<0.01	0.12	0.02	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927455	Drill Core	1.38	0.116	22	9	1.07	63	0.28	8.32	3.34	3.10	<4	47	<2	11	6	1	8	2.1
DUP 927455	QC	1.52	0.128	26	10	1.16	68	0.30	9.31	3.62	3.85	<4	49	2	13	6	1	9	2.3
927490	Drill Core	21.99	0.028	2	<2	12.21	20	<0.01	0.10	0.02	0.06	<4	<2	<2	<2	<2	<1	<1	<0.1
DUP 927490	QC	22.08	0.030	2	<2	12.22	19	<0.01	0.13	0.02	0.06	<4	<2	<2	<2	<1	<1	<0.1	
Reference Materials																			
STD OREAS24P	Standard	5.99	0.137	20	204	4.12	286	1.09	8.02	2.43	0.71	<4	153	<2	23	25	1	21	<0.1
STD OREAS24P	Standard	6.15	0.136	19	189	4.10	289	1.11	8.03	2.42	0.71	<4	153	<2	23	26	1	21	<0.1
STD OREAS24P	Standard	6.03	0.136	20	198	4.13	286	1.10	8.01	2.52	0.71	<4	152	<2	22	26	1	21	<0.1
STD OREAS24P	Standard	5.49	0.131	18	195	3.87	273	1.00	7.68	2.30	0.69	<4	142	<2	22	21	1	20	<0.1
STD OREAS24P	Standard	5.64	0.132	18	194	3.99	279	1.02	8.07	2.37	0.70	<4	146	<2	22	21	1	21	<0.1
STD OREAS24P	Standard	5.59	0.133	18	195	3.94	277	1.03	7.82	2.43	0.70	<4	143	<2	22	21	1	20	<0.1
STD OREAS45P	Standard	0.30	0.047	29	1137	0.19	304	1.08	7.33	0.09	0.37	<4	173	<2	14	25	1	73	<0.1
STD OREAS45P	Standard	0.30	0.046	29	1142	0.20	306	1.08	7.21	0.08	0.36	<4	180	<2	15	25	1	72	<0.1
STD OREAS45P	Standard	0.29	0.044	26	1072	0.18	294	1.03	6.93	0.08	0.35	<4	169	<2	13	25	1	68	<0.1
STD OREAS45P	Standard	0.28	0.046	24	1048	0.19	294	1.00	6.90	0.07	0.35	<4	160	<2	14	21	<1	67	<0.1
STD OREAS45P	Standard	0.30	0.045	24	1084	0.20	302	1.04	7.16	0.07	0.36	<4	171	3	14	22	<1	72	<0.1
STD OREAS45P	Standard	0.30	0.046	25	1067	0.20	295	1.02	7.09	0.07	0.36	<4	161	<2	14	21	<1	69	<0.1
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 02, 2009

www.acmelab.com

Page:

3 of 4 Part

QUALITY CONTROL REPORT

SMI09000207.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 02, 2009

www.acmelab.com

Page:

3 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000207.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 02, 2009

www.acmelab.com

Page:

4 of 4 Part

QUALITY CONTROL REPORT

SMI09000207.1

	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi		
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2	
G1	Prep Blank		<2	<2	3	18	56	<0.5	4	5	780	2.50	<5	<20	<4	6	747	<0.4	<5	<5	55
G1	Prep Blank		<2	<2	2	20	57	<0.5	4	5	796	2.48	<5	<20	<4	6	741	<0.4	<5	<5	56



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 02, 2009

www.acmelab.com

Page: 4 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000207.1

	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E
	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1
G1	Prep Blank	2.53	0.087	23	12	0.70	1006	0.25	7.78	2.57	2.95	<4	9	<2	15	24	3	6 <0.1
G1	Prep Blank	2.59	0.088	21	10	0.71	1068	0.26	7.72	2.61	3.07	<4	9	<2	15	25	3	6 <0.1



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 09, 2009
Report Date: October 05, 2009
Page: 1 of 8

CERTIFICATE OF ANALYSIS

SMI09000208.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 200

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
Code					
R200	194	Crush split and pulverize drill core to 200 mesh			VAN
3B	200	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	200	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL


STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC: Nigel Luckman
B. Booth



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page: 2 of 8 Part 1

SMI09000208.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927551	Drill Core	4.32	187	16	1867	10	18	1.1	4	9	182	2.62	<5	<20	<4	8	359	<0.4	<5	<5	194
927552	Drill Core	4.69	141	8	1598	10	17	0.6	3	8	249	2.29	<5	<20	<4	9	431	<0.4	<5	<5	169
927553	Drill Core	4.58	83	17	1233	7	45	<0.5	5	15	342	3.31	<5	<20	<4	8	433	<0.4	<5	<5	224
927554	Drill Core	5.65	77	24	1143	13	23	<0.5	5	17	341	4.13	<5	<20	<4	7	542	0.5	<5	<5	218
927555	Drill Core	3.80	223	15	1773	12	24	<0.5	3	10	202	2.51	<5	<20	<4	8	449	<0.4	<5	<5	272
927556	Drill Core	4.60	61	26	986	8	23	<0.5	3	7	263	1.83	<5	<20	<4	9	509	<0.4	<5	<5	193
927557	Drill Core	4.25	156	38	1217	12	24	<0.5	3	9	364	2.41	<5	<20	<4	8	435	<0.4	<5	<5	227
927558	Drill Core	3.95	207	111	1487	9	19	<0.5	<2	8	353	1.74	<5	<20	<4	7	442	<0.4	<5	<5	198
927559	Drill Core	4.95	146	53	1188	10	18	<0.5	3	10	332	1.96	<5	<20	<4	6	470	<0.4	<5	<5	208
927560	Drill Core	1.17	<2	<2	6	<5	14	<0.5	<2	<2	173	0.38	<5	<20	<4	<2	44	<0.4	<5	<5	2
927561	Drill Core	4.32	68	17	787	11	17	<0.5	<2	7	267	2.19	<5	<20	<4	8	467	<0.4	<5	<5	177
927562	Drill Core	4.72	104	36	1237	11	20	<0.5	2	9	252	2.12	<5	<20	<4	8	421	<0.4	<5	<5	205
927563	Drill Core	4.89	183	46	1800	9	16	<0.5	2	7	150	1.68	<5	<20	<4	10	384	<0.4	<5	<5	181
927564	Drill Core	4.67	117	96	1828	13	19	<0.5	3	6	152	1.69	<5	<20	<4	7	352	<0.4	<5	<5	201
927565	Drill Core	4.45	204	31	3042	8	24	0.9	3	9	150	2.53	<5	<20	<4	6	351	<0.4	<5	<5	295
927566	Drill Core	3.55	179	18	3108	7	26	1.1	2	8	172	2.26	<5	<20	<4	7	407	0.5	<5	9	288
927567	Drill Core	5.76	125	23	2050	5	24	0.8	2	7	163	1.98	<5	<20	<4	7	399	0.5	<5	<5	217
927568	Drill Core	2.26	50	42	830	8	12	<0.5	<2	3	203	1.53	<5	<20	<4	8	154	<0.4	<5	<5	109
927569	Drill Core	4.13	112	39	720	11	17	<0.5	<2	5	215	1.81	<5	<20	<4	8	236	<0.4	<5	<5	111
927570	Drill Core	1.08	<2	<2	4	<5	14	<0.5	<2	<2	173	0.37	<5	<20	<4	<2	44	<0.4	<5	<5	2
927571	Drill Core	5.30	49	76	723	9	15	<0.5	<2	7	387	1.81	6	<20	<4	6	317	<0.4	<5	<5	113
927572	Drill Core	4.73	93	108	854	9	14	0.7	<2	8	347	2.16	<5	<20	<4	6	320	0.5	<5	<5	121
927573	Drill Core	4.56	115	66	1172	9	12	1.0	<2	10	212	2.45	<5	<20	<4	9	273	<0.4	<5	6	142
927574	Drill Core	4.85	82	56	1346	<5	19	1.3	2	14	275	2.85	<5	<20	<4	8	377	<0.4	<5	<5	194
927575	Drill Core	6.99	128	21	1670	11	25	1.7	<2	12	225	2.77	<5	<20	<4	10	566	0.5	<5	<5	172
927576	Drill Core	4.87	83	7	1217	5	30	0.6	2	9	387	2.46	<5	<20	<4	7	556	0.4	<5	<5	192
927577	Drill Core	5.16	225	153	2305	12	18	1.5	2	7	260	1.85	<5	<20	<4	8	339	<0.4	<5	<5	187
927578	Drill Core	4.22	172	175	1959	6	17	1.3	4	8	329	1.96	<5	<20	<4	6	424	0.4	<5	<5	174
927579	Drill Core	4.89	87	20	1092	11	30	0.6	<2	9	466	2.89	<5	<20	<4	8	688	0.7	<5	<5	189
927580	Drill Core	1.18	<2	<2	4	<5	14	<0.5	2	<2	176	0.40	<5	<20	<4	<2	47	<0.4	<5	<5	4

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 2 of 8 Part 2

SMI09000208.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927551	Drill Core	0.87	0.160	16	5	0.77	129	0.32	8.82	3.64	3.76	7	51	<2	10	6	1	8	1.8
927552	Drill Core	1.29	0.115	16	4	0.81	232	0.27	8.86	3.54	3.51	6	54	<2	10	7	1	6	1.3
927553	Drill Core	1.87	0.158	18	9	1.47	200	0.33	8.39	3.76	3.65	<4	55	<2	13	6	1	12	1.5
927554	Drill Core	3.33	0.139	15	11	1.34	103	0.31	7.04	3.05	3.60	<4	60	<2	14	6	2	12	2.6
927555	Drill Core	1.05	0.173	21	3	1.09	394	0.41	8.90	3.93	3.83	7	43	<2	10	7	1	10	0.7
927556	Drill Core	1.83	0.240	21	3	0.83	1254	0.39	8.86	4.21	3.59	4	40	<2	15	9	1	10	0.6
927557	Drill Core	2.06	0.256	24	3	1.21	720	0.35	8.55	3.92	3.51	5	36	<2	14	7	1	10	0.9
927558	Drill Core	2.92	0.189	18	3	0.83	957	0.33	7.68	3.13	3.90	<4	31	<2	15	7	2	9	0.6
927559	Drill Core	2.67	0.129	14	2	0.81	654	0.30	7.16	3.32	3.13	<4	33	<2	13	6	2	7	0.8
927560	Drill Core	21.57	0.024	<2	<2	12.11	19	<0.01	0.09	0.01	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927561	Drill Core	1.80	0.117	20	3	0.88	511	0.27	8.76	3.64	3.97	<4	51	<2	12	7	2	6	0.8
927562	Drill Core	1.81	0.120	22	2	1.07	506	0.27	8.66	3.31	4.03	<4	43	<2	14	6	2	10	0.7
927563	Drill Core	1.15	0.165	24	3	0.84	333	0.27	8.91	3.30	3.74	6	41	<2	14	6	1	8	0.8
927564	Drill Core	0.56	0.162	14	3	1.11	657	0.35	8.47	3.22	3.61	6	36	<2	11	6	2	8	0.5
927565	Drill Core	0.48	0.155	16	5	1.16	232	0.38	8.55	3.56	3.49	6	59	<2	8	6	2	9	1.2
927566	Drill Core	0.65	0.164	17	5	1.24	361	0.39	9.21	3.25	3.32	10	56	<2	9	6	2	11	0.8
927567	Drill Core	1.01	0.128	20	3	0.94	312	0.30	8.67	3.03	3.23	5	49	<2	10	5	1	8	0.8
927568	Drill Core	1.20	0.074	19	2	0.30	1948	0.20	8.23	1.74	3.37	<4	47	<2	8	5	1	4	0.3
927569	Drill Core	1.50	0.084	22	2	0.49	321	0.23	8.74	2.58	3.17	<4	62	<2	8	5	1	5	0.7
927570	Drill Core	21.42	0.025	<2	<2	11.94	20	<0.01	0.10	0.01	0.05	<4	<2	<2	<2	<1	<1	<0.1	
927571	Drill Core	2.72	0.077	16	<2	0.56	352	0.18	8.00	2.57	3.48	5	49	<2	10	4	1	4	0.8
927572	Drill Core	2.99	0.080	16	<2	0.57	194	0.17	7.25	2.79	2.99	<4	48	<2	10	4	1	4	1.2
927573	Drill Core	1.77	0.106	24	3	0.59	123	0.21	8.74	3.62	3.25	4	51	<2	12	4	1	6	1.8
927574	Drill Core	1.63	0.134	24	3	0.83	131	0.28	9.27	3.55	3.46	<4	57	2	13	5	1	8	1.6
927575	Drill Core	1.62	0.120	22	<2	0.78	104	0.27	9.40	3.85	3.16	<4	57	<2	13	5	2	6	1.9
927576	Drill Core	3.12	0.133	18	3	0.57	337	0.33	8.65	3.34	3.09	<4	60	<2	12	6	1	7	1.0
927577	Drill Core	2.12	0.129	18	2	0.69	287	0.30	8.15	2.87	2.93	5	38	<2	16	5	1	8	0.9
927578	Drill Core	3.02	0.127	16	4	0.63	333	0.31	7.94	3.35	3.88	<4	37	<2	14	5	1	8	1.1
927579	Drill Core	3.61	0.136	20	<2	0.76	242	0.32	8.78	3.75	3.18	<4	61	<2	16	6	1	8	1.1
927580	Drill Core	20.95	0.026	3	4	12.09	37	<0.01	0.27	0.02	0.14	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page: 3 of 8 Part 1

SMI09000208.1

CERTIFICATE OF ANALYSIS

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	V	
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2
927581	Rock Pulp		0.13	321	<2	3209	30	67	0.9	16	6	334	3.45	<5	<20	<4	13	166	0.7	<5	43
927582	Drill Core		4.57	54	26	969	10	19	0.8	<2	10	611	3.00	<5	<20	<4	8	556	0.5	<5	122
927583	Drill Core		5.13	66	15	1143	9	21	0.5	<2	8	281	2.68	<5	<20	<4	9	613	0.5	<5	120
927584	Drill Core		3.89	124	33	1657	8	28	1.4	3	11	382	2.32	<5	<20	<4	6	469	0.6	<5	193
927585	Drill Core		4.69	154	23	1601	11	20	1.0	3	10	358	2.34	<5	<20	<4	6	442	<0.4	<5	250
927586	Drill Core		4.82	164	14	1780	8	17	1.6	2	7	360	2.02	<5	<20	<4	7	423	<0.4	<5	171
927587	Drill Core		4.61	123	21	1517	7	17	0.9	2	6	379	2.05	<5	<20	<4	6	398	0.5	<5	186
927588	Drill Core		4.62	211	20	1672	8	12	0.6	<2	4	374	1.54	<5	<20	<4	5	313	<0.4	<5	157
927589	Drill Core		4.41	88	46	1012	8	21	0.7	<2	8	442	3.27	<5	<20	<4	7	320	0.4	<5	161
927590	Drill Core		1.26	<2	<2	6	<5	14	<0.5	<2	<2	166	0.38	<5	<20	<4	<2	43	<0.4	<5	2
927591	Drill Core		4.25	125	26	1799	6	22	0.6	<2	11	381	3.13	<5	<20	<4	6	331	0.7	<5	168
927592	Drill Core		5.36	71	19	666	13	24	<0.5	<2	8	607	2.57	<5	<20	<4	6	383	0.6	<5	144
927593	Drill Core		4.46	102	28	1409	9	17	1.0	<2	10	372	2.92	<5	<20	<4	6	355	0.5	<5	185
927594	Drill Core		4.75	96	28	1327	12	16	<0.5	<2	9	325	3.44	<5	<20	<4	7	381	0.5	<5	160
927595	Drill Core		5.19	84	34	1034	10	19	0.5	<2	13	320	3.30	<5	<20	<4	7	430	0.5	<5	144
927596	Drill Core		4.97	115	27	1135	7	40	<0.5	<2	11	345	3.16	<5	<20	<4	7	417	0.8	<5	135
927597	Drill Core		5.09	163	23	1163	10	170	0.6	<2	12	374	2.88	<5	<20	<4	6	385	4.9	<5	128
927598	Drill Core		4.98	110	12	1094	12	19	1.0	<2	9	265	3.32	<5	<20	<4	9	360	<0.4	<5	145
927599	Drill Core		4.52	178	26	1696	10	17	1.5	<2	9	512	3.69	7	<20	<4	6	288	0.4	<5	152
927600	Drill Core		1.20	<2	<2	6	<5	13	<0.5	<2	<2	172	0.39	<5	<20	<4	<2	45	<0.4	<5	4
927601	Drill Core		4.86	252	15	2259	9	84	1.1	3	12	519	3.90	<5	<20	<4	8	542	1.7	<5	205
927602	Drill Core		4.37	265	20	2586	6	34	1.0	<2	13	470	3.73	<5	<20	<4	8	561	0.6	<5	222
927603	Drill Core		5.34	229	7	2420	7	31	1.1	3	15	504	4.00	<5	<20	<4	7	542	0.5	<5	217
927604	Drill Core		5.39	210	9	2274	<5	32	1.0	2	13	436	4.02	<5	<20	<4	9	472	0.4	<5	220
927605	Drill Core		5.20	149	18	1547	6	17	1.2	<2	10	399	2.36	<5	<20	<4	10	417	<0.4	<5	151
927606	Drill Core		4.71	144	15	1705	5	14	0.9	<2	7	219	1.73	<5	<20	<4	11	374	<0.4	<5	118
927607	Drill Core		5.09	187	17	1668	8	13	0.8	2	6	261	1.98	<5	<20	<4	10	419	<0.4	<5	148
927608	Drill Core		4.35	197	7	2853	5	23	1.6	2	13	372	3.27	<5	<20	<4	10	450	0.4	<5	214
927609	Drill Core		4.37	163	12	2541	5	21	1.4	<2	11	410	3.29	<5	<20	<4	11	415	0.4	<5	211
927610	Drill Core		0.99	<2	<2	9	<5	13	<0.5	<2	<2	176	0.37	<5	<20	<4	<2	44	<0.4	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 3 of 8 Part 2

SMI09000208.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927581	Rock Pulp	1.21	0.043	27	17	0.50	772	0.15	6.73	2.39	2.08	<4	52	9	14	9	2	6	0.3
927582	Drill Core	4.22	0.091	23	<2	0.66	130	0.25	8.46	3.26	3.02	<4	75	<2	18	7	1	5	2.1
927583	Drill Core	2.63	0.086	26	<2	0.60	144	0.26	9.12	3.62	3.45	<4	83	<2	19	8	1	4	2.0
927584	Drill Core	3.05	0.131	17	2	0.72	230	0.32	8.31	3.21	3.36	<4	52	<2	18	6	1	7	1.2
927585	Drill Core	3.32	0.133	14	2	0.54	229	0.31	7.96	3.29	3.38	<4	45	<2	16	6	1	7	1.3
927586	Drill Core	3.30	0.132	16	<2	0.51	179	0.30	8.32	3.28	2.77	<4	44	<2	16	6	1	7	1.4
927587	Drill Core	3.29	0.121	15	3	0.57	204	0.30	7.51	2.85	3.51	<4	39	<2	15	5	1	7	1.3
927588	Drill Core	3.23	0.109	16	3	0.57	258	0.25	6.62	2.44	3.40	<4	34	<2	14	5	1	7	0.9
927589	Drill Core	3.00	0.131	18	2	1.00	170	0.31	8.06	3.02	3.38	<4	49	<2	17	7	1	7	1.6
927590	Drill Core	21.23	0.027	<2	<2	11.85	20	<0.01	0.09	0.01	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927591	Drill Core	3.11	0.131	19	<2	1.08	195	0.31	7.74	2.58	3.67	4	45	<2	18	6	1	7	1.6
927592	Drill Core	4.87	0.116	24	<2	0.80	140	0.26	7.82	3.09	2.98	6	50	<2	23	5	1	7	1.7
927593	Drill Core	2.60	0.121	21	3	0.98	187	0.30	8.39	3.15	3.42	<4	50	<2	18	6	1	8	1.5
927594	Drill Core	2.54	0.133	19	4	0.99	123	0.31	8.35	3.43	3.34	<4	46	<2	18	7	2	7	2.2
927595	Drill Core	2.77	0.119	22	<2	0.84	101	0.30	8.60	3.52	3.19	<4	61	<2	19	7	2	6	2.2
927596	Drill Core	2.62	0.096	23	<2	0.82	194	0.26	8.67	3.41	3.66	<4	69	<2	18	7	2	4	1.6
927597	Drill Core	3.17	0.093	19	<2	0.65	136	0.25	8.40	3.47	3.59	<4	67	<2	18	7	1	4	2.2
927598	Drill Core	1.56	0.103	22	<2	0.72	62	0.27	9.23	3.80	2.79	<4	67	<2	15	7	1	6	2.5
927599	Drill Core	3.80	0.098	17	3	0.83	77	0.22	8.06	2.34	2.96	<4	47	<2	18	5	1	6	3.1
927600	Drill Core	22.54	0.021	2	<2	12.39	23	<0.01	0.07	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	
927601	Drill Core	4.43	0.129	21	5	0.81	111	0.35	8.18	3.02	4.16	5	61	<2	21	6	1	9	2.9
927602	Drill Core	3.70	0.135	23	3	0.97	112	0.37	8.75	3.21	4.49	<4	67	<2	22	6	1	9	2.1
927603	Drill Core	3.81	0.147	17	3	0.91	126	0.37	7.82	3.05	4.45	<4	63	<2	19	7	1	9	2.3
927604	Drill Core	2.91	0.143	25	2	1.09	117	0.35	9.14	3.23	4.73	<4	57	<2	18	6	1	10	1.9
927605	Drill Core	3.10	0.094	19	<2	0.87	199	0.25	9.05	3.22	4.98	4	55	<2	17	6	1	5	1.2
927606	Drill Core	1.86	0.073	17	<2	0.60	528	0.22	9.22	3.49	5.02	5	54	<2	13	5	1	4	0.8
927607	Drill Core	2.43	0.092	20	<2	0.62	334	0.26	8.51	2.86	5.22	5	54	<2	15	7	1	5	1.0
927608	Drill Core	2.59	0.127	20	<2	0.89	167	0.33	8.83	3.19	4.83	5	59	<2	17	7	1	8	1.4
927609	Drill Core	2.91	0.105	21	<2	0.85	212	0.30	9.10	3.04	5.19	<4	70	<2	18	8	1	6	1.2
927610	Drill Core	22.76	0.027	2	<2	12.15	26	<0.01	0.06	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page: 4 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000208.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927611	Rock Pulp	0.11	304	<2	3282	28	68	1.0	17	7	342	3.55	<5	<20	<4	13	172	<0.4	<5	<5	43
927612	Drill Core	4.59	134	6	1688	<5	18	1.0	<2	7	433	2.75	<5	<20	<4	10	528	<0.4	<5	<5	182
927613	Drill Core	5.08	208	17	1960	7	23	0.9	2	9	527	3.91	<5	<20	<4	10	479	0.6	<5	<5	204
927614	Drill Core	4.73	153	4	1703	5	30	0.7	3	11	460	3.71	<5	<20	<4	9	622	0.7	<5	<5	218
927615	Drill Core	4.64	146	7	1645	9	27	0.7	<2	11	418	3.04	<5	<20	<4	10	639	<0.4	<5	<5	184
927616	Drill Core	4.28	139	14	1422	13	27	0.5	<2	10	377	3.10	<5	<20	<4	11	638	<0.4	<5	<5	190
927617	Drill Core	4.34	177	10	1650	10	20	0.7	2	10	392	2.81	<5	<20	<4	10	494	<0.4	<5	<5	185
927618	Drill Core	2.57	124	18	1346	8	21	1.0	3	11	346	3.44	<5	<20	<4	11	385	<0.4	<5	<5	187
927619	Drill Core	5.45	150	10	2106	9	24	1.0	3	12	484	3.35	<5	<20	<4	9	390	0.5	<5	<5	193
927620	Drill Core	1.17	<2	<2	6	<5	17	<0.5	<2	<2	176	0.39	<5	<20	<4	<2	45	<0.4	<5	<5	2
927621	Drill Core	4.44	102	8	1985	<5	31	1.1	4	17	415	4.11	<5	<20	<4	10	408	<0.4	<5	<5	203
927622	Drill Core	3.32	105	6	1297	6	25	0.5	4	12	392	3.44	<5	<20	<4	10	403	0.4	<5	<5	177
927623	Drill Core	3.62	167	5	2435	<5	34	1.1	22	19	627	5.53	<5	<20	<4	5	337	<0.4	<5	<5	252
927624	Drill Core	4.85	144	8	2041	9	29	1.0	26	18	594	4.63	<5	<20	<4	4	263	0.8	<5	<5	227
927625	Drill Core	4.25	146	11	1710	7	26	1.0	19	14	548	4.22	<5	<20	<4	5	274	0.6	<5	<5	222
927626	Drill Core	4.90	151	5	1680	8	26	0.8	15	14	550	4.02	<5	<20	<4	7	292	0.5	<5	<5	203
927627	Drill Core	4.27	95	6	1247	<5	22	0.8	10	11	448	3.53	<5	<20	<4	9	321	0.5	<5	<5	170
927628	Drill Core	3.35	87	5	1409	6	32	0.6	30	17	782	4.62	<5	<20	<4	3	283	0.8	<5	<5	243
927629	Drill Core	3.96	29	5	320	9	24	<0.5	5	8	557	3.24	<5	<20	<4	12	333	<0.4	<5	<5	154
927630	Drill Core	1.42	<2	<2	4	<5	13	<0.5	<2	<2	175	0.40	<5	<20	<4	<2	47	<0.4	<5	<5	2
927631	Drill Core	4.39	43	6	907	10	30	<0.5	23	15	723	4.17	<5	<20	<4	7	330	0.8	<5	<5	184
927632	Drill Core	5.28	74	14	1657	8	32	1.2	24	21	593	4.46	6	<20	<4	5	282	0.7	<5	<5	225
927633	Drill Core	4.66	20	28	225	7	25	<0.5	2	7	391	3.12	<5	<20	<4	11	452	0.5	<5	<5	125
927634	Drill Core	4.57	18	14	256	7	26	<0.5	3	9	464	2.96	<5	<20	<4	9	462	<0.4	<5	<5	126
927635	Drill Core	4.14	13	8	181	15	26	<0.5	3	7	495	2.64	<5	<20	<4	8	429	<0.4	<5	<5	131
927636	Drill Core	2.77	79	48	1016	13	32	0.9	35	15	873	3.78	<5	<20	<4	4	341	0.6	<5	<5	209
927637	Drill Core	2.19	86	51	1340	12	25	0.8	29	15	655	3.52	<5	<20	<4	3	607	<0.4	<5	<5	229
927638	Drill Core	4.10	136	56	1375	14	26	0.7	28	13	734	3.73	<5	<20	<4	3	306	0.7	<5	<5	207
927639	Drill Core	3.24	121	20	1123	16	23	0.8	19	14	666	3.75	<5	<20	<4	4	234	0.5	<5	<5	203
927640	Drill Core	1.25	<2	<2	4	7	15	<0.5	<2	<2	179	0.38	<5	<20	<4	<2	49	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 4 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000208.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927611	Rock Pulp	1.30	0.044	28	18	0.51	799	0.16	7.17	2.43	3.48	<4	55	8	15	9	2	7	0.3
927612	Drill Core	3.43	0.110	18	<2	0.79	206	0.30	8.60	3.24	4.98	5	68	<2	17	7	1	6	1.1
927613	Drill Core	3.38	0.138	22	2	0.93	161	0.31	8.24	2.87	4.45	<4	62	<2	17	6	1	9	1.2
927614	Drill Core	3.86	0.145	21	3	0.72	224	0.34	8.54	3.21	4.54	<4	71	<2	18	7	1	9	1.2
927615	Drill Core	3.29	0.116	21	<2	0.67	222	0.32	8.94	3.58	4.56	<4	80	<2	19	8	1	7	1.2
927616	Drill Core	2.69	0.118	23	3	0.86	221	0.32	9.35	3.36	4.75	<4	71	<2	18	7	2	7	1.1
927617	Drill Core	3.23	0.122	22	2	0.81	152	0.31	8.72	3.22	4.57	<4	66	<2	17	7	1	8	1.3
927618	Drill Core	2.39	0.111	25	3	0.67	111	0.30	9.21	3.48	4.45	<4	75	<2	19	7	1	7	1.8
927619	Drill Core	3.92	0.114	20	3	0.62	218	0.31	8.14	2.95	4.87	<4	63	<2	17	6	<1	7	1.2
927620	Drill Core	22.18	0.020	2	<2	12.32	17	<0.01	0.06	0.01	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927621	Drill Core	2.56	0.122	20	3	0.89	123	0.33	9.29	3.34	4.66	<4	72	<2	17	7	1	8	1.6
927622	Drill Core	2.83	0.112	25	4	0.77	471	0.30	8.83	3.34	4.62	4	59	<2	17	7	1	7	0.7
927623	Drill Core	4.81	0.123	20	31	0.84	395	0.34	8.53	3.42	3.89	4	52	<2	19	5	<1	11	1.0
927624	Drill Core	4.72	0.138	19	46	0.63	243	0.34	7.94	3.28	3.25	5	45	<2	20	4	<1	12	0.9
927625	Drill Core	3.51	0.123	24	32	0.74	192	0.33	7.94	3.07	3.67	<4	48	<2	21	4	<1	11	0.9
927626	Drill Core	3.84	0.117	19	24	0.61	362	0.31	8.07	3.18	4.02	4	51	<2	18	5	<1	9	0.9
927627	Drill Core	2.73	0.094	19	10	0.65	1194	0.27	8.49	3.23	4.45	<4	49	<2	14	6	<1	6	0.6
927628	Drill Core	5.08	0.129	19	43	0.84	222	0.35	7.92	3.37	2.85	<4	40	<2	19	4	<1	14	1.0
927629	Drill Core	3.18	0.110	27	3	0.72	562	0.30	9.07	3.67	4.43	<4	47	<2	19	7	1	7	0.8
927630	Drill Core	22.71	0.026	2	<2	12.45	16	<0.01	0.10	0.02	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927631	Drill Core	4.44	0.116	18	24	0.90	116	0.31	8.11	3.82	3.07	<4	47	<2	18	5	<1	11	1.7
927632	Drill Core	3.06	0.126	19	38	0.92	100	0.35	7.88	3.86	2.52	<4	47	2	18	4	<1	13	1.8
927633	Drill Core	2.05	0.108	25	<2	0.64	205	0.29	9.06	4.19	3.48	<4	43	<2	16	7	1	6	1.1
927634	Drill Core	2.96	0.103	22	2	0.62	276	0.29	8.88	3.58	3.92	4	43	<2	15	7	1	6	1.0
927635	Drill Core	2.94	0.104	17	<2	0.52	1526	0.29	7.93	3.77	3.66	<4	41	<2	14	7	1	6	0.5
927636	Drill Core	5.43	0.122	15	36	0.73	223	0.33	7.20	3.64	2.42	<4	37	3	20	4	<1	12	1.2
927637	Drill Core	5.91	0.131	12	48	0.67	145	0.34	7.14	3.41	2.97	<4	32	3	18	3	<1	14	2.1
927638	Drill Core	5.16	0.123	14	38	0.60	262	0.32	7.18	3.19	3.37	<4	35	<2	18	4	<1	11	1.2
927639	Drill Core	4.07	0.130	15	30	0.73	249	0.29	7.06	2.89	3.45	<4	39	2	17	5	<1	9	1.2
927640	Drill Core	22.10	0.021	<2	<2	12.06	18	<0.01	0.07	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page: 5 of 8 Part 1

SMI09000208.1

CERTIFICATE OF ANALYSIS

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	
927641	Rock Pulp		0.09	623	4	5023	24	64	1.4	17	13	419	5.01	5	<20	<4	4	425	0.7	<5	<5	126
927642	Drill Core		5.13	90	11	817	11	23	<0.5	13	11	549	3.01	<5	<20	<4	6	250	<0.4	<5	<5	185
927643	Drill Core		6.15	87	18	543	14	20	<0.5	5	10	561	3.36	9	<20	<4	6	343	0.4	<5	<5	181
927644	Drill Core		3.84	112	15	829	14	21	0.6	10	15	683	3.45	<5	<20	<4	7	292	<0.4	<5	<5	185
927645	Drill Core		3.54	121	20	1098	14	22	0.7	15	11	681	3.72	<5	<20	<4	6	267	0.6	<5	<5	201
927646	Drill Core		3.94	113	15	654	16	18	0.5	4	9	679	3.33	<5	<20	<4	8	470	0.5	<5	<5	177
927647	Drill Core		4.89	108	21	443	15	14	<0.5	4	8	506	3.28	<5	<20	<4	7	512	<0.4	<5	<5	169
927648	Drill Core		4.94	70	22	537	12	14	<0.5	3	8	666	3.26	<5	<20	<4	8	552	0.4	<5	<5	161
927649	Drill Core		4.81	102	7	884	12	17	0.5	3	10	539	3.28	<5	<20	<4	6	586	<0.4	<5	<5	193
927650	Drill Core		1.24	<2	<2	2	<5	13	<0.5	<2	<2	176	0.39	<5	<20	<4	<2	44	<0.4	<5	<5	2
927651	Drill Core		5.30	148	17	792	12	18	0.7	4	8	513	3.82	8	<20	<4	4	296	0.7	<5	<5	146
927652	Drill Core		4.78	124	25	490	16	13	<0.5	3	7	546	2.42	13	<20	<4	8	259	<0.4	<5	<5	106
927653	Drill Core		5.27	225	13	668	27	17	0.9	15	11	735	4.32	53	<20	<4	5	216	0.6	10	<5	160
927654	Drill Core		5.53	97	41	996	16	16	0.7	2	9	613	2.69	<5	<20	<4	8	274	0.5	<5	<5	147
927655	Drill Core		4.15	40	3	121	18	30	<0.5	<2	5	383	2.42	<5	<20	<4	10	304	<0.4	<5	<5	108
927656	Drill Core		4.79	41	7	200	12	23	<0.5	<2	7	259	2.15	<5	<20	<4	12	581	<0.4	<5	<5	121
927657	Drill Core		4.63	53	4	202	13	28	<0.5	<2	6	403	2.50	<5	<20	<4	9	316	<0.4	<5	<5	109
927658	Drill Core		4.42	48	5	192	14	21	<0.5	<2	7	253	1.95	<5	<20	<4	12	309	<0.4	<5	<5	107
927659	Drill Core		5.07	117	6	788	18	24	<0.5	<2	9	306	2.40	<5	<20	<4	9	346	<0.4	<5	<5	146
927660	Drill Core		1.48	<2	<2	5	<5	13	<0.5	<2	<2	165	0.37	<5	<20	<4	<2	47	<0.4	<5	<5	3
927661	Drill Core		2.54	145	12	899	15	29	<0.5	<2	8	436	3.34	<5	<20	<4	9	373	<0.4	<5	<5	169
927662	Drill Core		3.56	79	6	918	14	28	0.6	<2	9	457	3.14	<5	<20	<4	7	406	<0.4	<5	<5	207
927663	Drill Core		3.66	568	7	960	14	26	0.9	3	11	406	4.10	<5	<20	<4	6	407	0.6	<5	<5	209
927664	Drill Core		5.28	81	15	1064	12	23	0.8	2	11	494	3.16	<5	<20	<4	6	410	0.4	<5	<5	211
927665	Drill Core		2.37	189	17	1257	13	18	1.1	2	15	349	4.66	13	<20	<4	6	282	0.6	<5	<5	214
927666	Drill Core		4.31	176	15	1336	12	19	1.2	2	16	398	5.31	30	<20	<4	7	232	0.5	<5	<5	212
927667	Drill Core		5.07	257	34	688	31	28	2.2	3	9	1044	7.84	108	<20	<4	7	281	1.9	8	<5	119
927668	Drill Core		4.80	140	17	952	14	23	0.9	2	11	553	3.55	47	<20	<4	7	274	<0.4	<5	<5	189
927669	Drill Core		4.00	152	32	1271	11	20	1.0	<2	14	504	4.02	22	<20	<4	7	406	0.4	<5	<5	200
927670	Drill Core		1.24	<2	<2	4	<5	14	<0.5	<2	<2	162	0.37	<5	<20	<4	<2	46	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 5 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000208.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927641	Rock Pulp	1.61	0.097	11	23	1.26	670	0.26	6.91	2.97	3.08	5	69	8	12	6	1	11	0.6
927642	Drill Core	3.50	0.113	15	20	0.55	491	0.29	7.35	3.40	3.43	<4	44	2	14	5	<1	8	0.6
927643	Drill Core	2.97	0.119	18	4	0.87	374	0.29	7.70	3.23	4.03	4	43	<2	15	6	1	8	1.2
927644	Drill Core	4.47	0.116	20	14	0.94	371	0.29	7.55	2.93	3.87	<4	36	2	19	5	<1	9	1.1
927645	Drill Core	3.83	0.121	18	23	0.91	246	0.29	7.59	3.08	3.65	<4	37	2	17	5	<1	10	1.1
927646	Drill Core	4.07	0.123	16	4	0.98	284	0.30	8.14	3.54	3.84	4	42	<2	17	6	1	8	1.2
927647	Drill Core	3.55	0.115	15	3	0.79	163	0.29	7.71	3.58	3.70	<4	47	3	14	6	1	8	1.7
927648	Drill Core	4.70	0.115	19	2	0.83	250	0.28	7.87	3.47	3.71	<4	43	<2	19	5	1	8	1.3
927649	Drill Core	3.93	0.133	18	2	0.82	181	0.33	7.94	3.99	2.95	<4	47	<2	13	6	1	9	1.4
927650	Drill Core	21.68	0.028	<2	<2	12.02	18	<0.01	0.06	0.01	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927651	Drill Core	3.96	0.092	7	3	0.68	76	0.24	5.66	3.18	2.89	6	36	3	9	5	1	5	2.9
927652	Drill Core	3.62	0.073	12	2	0.52	205	0.20	6.95	3.06	3.82	5	39	<2	11	5	1	4	1.6
927653	Drill Core	4.08	0.110	13	22	0.87	102	0.27	6.81	2.58	3.37	<4	34	<2	13	5	<1	9	3.0
927654	Drill Core	3.97	0.098	15	2	0.72	205	0.25	7.26	2.54	3.76	5	56	3	15	6	1	5	1.7
927655	Drill Core	2.58	0.083	18	3	0.51	310	0.23	7.62	3.52	3.53	<4	47	<2	13	6	1	4	0.9
927656	Drill Core	1.44	0.095	23	4	0.56	259	0.27	8.86	3.47	3.28	5	56	<2	11	7	1	5	0.8
927657	Drill Core	2.59	0.086	18	5	0.52	305	0.23	8.00	3.68	3.71	<4	50	<2	13	7	1	4	1.0
927658	Drill Core	1.51	0.092	24	3	0.48	438	0.25	8.08	3.69	3.82	<4	54	<2	12	7	1	4	0.7
927659	Drill Core	1.88	0.113	20	4	0.63	331	0.29	7.90	3.39	3.55	5	55	3	12	7	1	6	0.8
927660	Drill Core	22.05	0.028	<2	<2	12.33	21	<0.01	0.09	0.02	0.06	<4	<2	<2	<2	<1	<1	<0.1	
927661	Drill Core	2.04	0.101	26	3	0.95	400	0.28	8.02	3.30	3.81	5	64	<2	15	7	1	6	0.7
927662	Drill Core	3.07	0.128	16	3	0.88	302	0.36	8.16	3.40	3.29	4	71	<2	17	6	1	8	1.3
927663	Drill Core	2.53	0.141	27	5	1.00	109	0.37	8.41	3.65	3.80	4	78	3	19	6	1	10	2.7
927664	Drill Core	3.05	0.143	19	4	0.94	187	0.39	7.95	4.01	3.42	5	75	<2	16	6	1	9	1.7
927665	Drill Core	2.36	0.155	27	4	0.89	69	0.35	8.47	2.99	3.99	6	71	<2	14	6	1	10	3.9
927666	Drill Core	2.20	0.158	34	3	0.91	59	0.31	8.11	3.16	3.67	6	63	3	16	5	1	10	4.8
927667	Drill Core	9.26	0.078	21	<2	0.52	58	0.19	5.99	1.72	2.39	10	40	3	18	4	<1	6	8.6
927668	Drill Core	3.46	0.130	20	3	0.86	93	0.35	7.88	3.43	2.97	<4	76	<2	16	7	1	8	2.4
927669	Drill Core	2.86	0.138	22	3	0.89	102	0.35	7.80	3.01	3.42	4	71	2	17	6	1	9	2.4
927670	Drill Core	21.77	0.029	2	<2	12.27	16	<0.01	0.11	<0.01	0.05	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page:

6 of 8

Part 1

SMI09000208.1

CERTIFICATE OF ANALYSIS

Method	Analyte	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi	V
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5
927671	Rock Pulp		0.11	323	<2	3203	27	67	1.0	16	6	339	3.48	6	<20	<4	10	167	<0.4	<5	<5
927672	Drill Core		2.86	43	9	229	8	21	<0.5	2	6	480	2.37	7	<20	<4	10	327	<0.4	<5	<5
927673	Drill Core		4.78	46	12	129	9	27	<0.5	<2	5	443	2.22	10	<20	<4	7	314	<0.4	<5	<5
927674	Drill Core		4.57	37	4	142	10	19	<0.5	<2	5	403	2.20	6	<20	<4	9	304	<0.4	<5	<5
927675	Drill Core		4.95	165	14	828	11	24	0.7	<2	9	394	3.38	13	<20	<4	8	517	<0.4	<5	<5
927676	Drill Core		4.91	131	19	911	9	27	<0.5	<2	10	428	3.12	8	<20	<4	9	585	<0.4	<5	<5
927677	Drill Core		4.55	112	15	910	11	24	<0.5	<2	9	430	3.25	8	<20	<4	8	694	<0.4	<5	<5
927678	Drill Core		5.19	124	9	1428	10	23	<0.5	<2	11	431	3.10	<5	<20	<4	9	857	<0.4	<5	<5
927679	Drill Core		4.74	84	22	1010	13	23	<0.5	<2	11	384	3.79	<5	<20	<4	8	866	<0.4	<5	<5
927680	Drill Core		1.06	<2	<2	6	<5	14	<0.5	<2	<2	168	0.40	<5	<20	<4	<2	46	<0.4	<5	3
927681	Drill Core		5.01	109	14	769	9	19	<0.5	<2	10	274	3.10	5	<20	<4	7	669	<0.4	<5	<5
927682	Drill Core		5.50	223	73	1183	11	17	<0.5	<2	10	308	2.94	<5	<20	<4	8	614	<0.4	<5	<5
927683	Drill Core		4.78	200	92	1199	11	20	<0.5	2	12	319	2.98	<5	<20	<4	8	478	<0.4	<5	<5
927684	Drill Core		4.66	96	15	708	12	23	<0.5	<2	10	375	3.14	6	<20	<4	9	610	<0.4	<5	<5
927685	Drill Core		4.79	110	19	1244	11	22	<0.5	<2	14	368	3.44	11	<20	<4	7	561	<0.4	<5	<5
927686	Drill Core		5.05	92	19	868	11	28	0.6	<2	12	362	3.40	12	<20	<4	7	593	<0.4	<5	<5
927687	Drill Core		4.54	121	18	826	14	37	<0.5	3	13	383	4.14	<5	<20	<4	7	637	<0.4	<5	<5
927688	Drill Core		4.43	70	17	715	14	31	<0.5	<2	10	471	3.33	6	<20	<4	8	637	<0.4	<5	<5
927689	Drill Core		4.60	108	17	870	12	29	0.6	<2	11	530	3.63	8	<20	<4	9	665	<0.4	<5	<5
927690	Drill Core		1.22	3	<2	3	<5	14	<0.5	<2	<2	190	0.41	<5	<20	<4	<2	45	<0.4	<5	4
927691	Drill Core		3.17	66	28	743	11	31	<0.5	<2	8	585	3.90	<5	<20	<4	8	662	<0.4	<5	<5
927692	Drill Core		4.48	84	43	636	14	28	<0.5	3	8	516	3.43	<5	<20	<4	9	691	<0.4	<5	<5
927693	Drill Core		4.42	55	26	612	9	23	<0.5	<2	7	425	3.66	<5	<20	<4	8	655	<0.4	<5	<5
927694	Drill Core		1.67	226	24	2318	11	45	1.0	10	41	762	10.59	13	<20	<4	4	354	<0.4	<5	<5
927695	Drill Core		4.11	94	21	767	10	24	0.5	<2	12	345	4.32	<5	<20	<4	7	524	<0.4	<5	<5
927696	Drill Core		4.79	111	21	731	9	20	<0.5	<2	12	355	4.09	<5	<20	<4	5	628	<0.4	<5	<5
927697	Drill Core		4.83	660	28	860	8	16	<0.5	<2	18	320	4.71	<5	<20	<4	6	679	<0.4	<5	<5
927698	Drill Core		5.06	234	28	913	11	15	<0.5	2	14	321	4.89	<5	<20	<4	6	662	<0.4	<5	<5
927699	Drill Core		4.74	112	11	708	9	17	<0.5	<2	14	392	5.00	<5	<20	<4	6	737	<0.4	<5	<5
927700	Drill Core		1.17	<2	<2	7	<5	12	<0.5	<2	<2	175	0.39	<5	<20	<4	<2	46	<0.4	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 6 of 8 Part 2

SMI09000208.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927671	Rock Pulp	1.21	0.043	22	19	0.49	780	0.15	6.66	2.40	3.94	5	51	9	13	9	2	6	0.3
927672	Drill Core	2.69	0.083	21	3	0.48	399	0.25	8.00	3.84	3.92	<4	52	2	13	6	1	4	0.8
927673	Drill Core	3.19	0.073	12	3	0.27	200	0.23	6.78	3.70	3.54	4	50	<2	9	7	1	3	1.5
927674	Drill Core	2.98	0.077	16	4	0.34	229	0.23	7.13	3.74	3.86	<4	54	<2	12	6	<1	4	1.2
927675	Drill Core	2.84	0.095	23	<2	0.59	191	0.28	8.05	3.37	4.05	7	80	<2	16	7	1	5	1.8
927676	Drill Core	2.92	0.108	24	2	0.71	380	0.30	8.28	3.55	4.00	4	83	<2	18	7	2	6	1.0
927677	Drill Core	3.69	0.109	24	3	0.66	273	0.31	8.01	3.76	3.97	5	85	<2	18	7	2	6	1.2
927678	Drill Core	4.06	0.107	22	3	0.64	268	0.31	8.25	3.76	3.68	<4	92	<2	19	7	2	7	1.2
927679	Drill Core	3.08	0.101	19	<2	0.78	178	0.32	8.13	3.54	3.61	<4	86	<2	18	7	2	6	1.6
927680	Drill Core	20.56	0.045	2	<2	11.81	39	<0.01	0.13	0.02	0.06	<4	<2	<2	<2	<2	<1	<1	<0.1
927681	Drill Core	2.76	0.107	20	2	0.66	159	0.31	8.21	3.50	4.07	4	94	<2	18	8	2	6	1.8
927682	Drill Core	2.78	0.099	21	3	0.77	221	0.28	8.25	3.58	3.96	<4	86	<2	17	7	2	5	1.3
927683	Drill Core	2.44	0.108	19	4	0.84	281	0.29	8.19	3.30	4.03	4	80	<2	16	6	1	6	1.1
927684	Drill Core	3.40	0.116	20	2	0.73	212	0.31	8.26	3.43	4.33	4	89	<2	18	7	2	6	1.4
927685	Drill Core	2.62	0.104	17	2	0.71	128	0.30	7.80	3.22	4.25	4	89	<2	16	6	1	6	2.0
927686	Drill Core	3.12	0.109	18	3	0.63	141	0.31	7.97	3.04	3.99	<4	88	<2	18	7	1	6	2.0
927687	Drill Core	3.22	0.106	18	5	0.79	106	0.32	8.01	3.40	3.93	<4	87	<2	18	7	2	6	2.4
927688	Drill Core	3.01	0.106	20	3	0.85	121	0.31	8.02	3.35	3.85	<4	101	<2	19	6	2	6	2.0
927689	Drill Core	3.36	0.111	25	2	1.03	148	0.32	8.32	3.05	4.01	<4	99	<2	20	7	2	6	1.9
927690	Drill Core	21.59	0.025	2	<2	12.42	24	<0.01	0.14	0.01	0.07	<4	<2	<2	<2	<2	<1	<1	<0.1
927691	Drill Core	3.45	0.107	20	2	1.02	124	0.32	8.31	3.05	3.97	<4	100	<2	20	7	2	6	2.3
927692	Drill Core	3.75	0.116	24	4	0.89	140	0.34	8.72	3.43	4.21	5	106	<2	23	7	2	7	2.1
927693	Drill Core	3.21	0.112	22	<2	0.84	133	0.34	8.62	3.09	4.60	<4	105	2	21	7	2	7	2.3
927694	Drill Core	5.14	0.404	35	13	3.09	116	0.88	7.58	1.82	1.53	6	56	<2	32	5	2	33	5.5
927695	Drill Core	2.88	0.114	15	3	0.87	117	0.30	8.35	2.96	4.07	<4	94	<2	18	6	2	6	2.6
927696	Drill Core	3.37	0.126	16	3	0.99	103	0.35	7.92	3.49	3.60	5	87	<2	17	6	2	8	2.5
927697	Drill Core	2.86	0.139	15	3	1.15	67	0.34	8.31	3.82	2.92	7	77	<2	18	5	2	10	3.2
927698	Drill Core	3.19	0.122	15	3	1.10	66	0.31	7.99	3.76	3.09	6	74	<2	17	5	2	8	3.6
927699	Drill Core	3.55	0.127	19	3	1.08	73	0.34	8.29	3.92	2.93	9	76	<2	18	5	1	9	3.4
927700	Drill Core	22.06	0.024	<2	<2	12.20	15	<0.01	0.08	0.01	0.03	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page: 7 of 8 Part 1

SMI09000208.1

CERTIFICATE OF ANALYSIS

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	V	
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927701	Rock Pulp		0.10	626	3	5200	12	63	1.4	16	13	427	5.11	6	<20	<4	3	445	<0.4	<5	<5	126
927702	Drill Core		4.56	127	10	573	8	17	<0.5	<2	16	289	4.81	<5	<20	<4	7	920	<0.4	<5	<5	174
927703	Drill Core		4.94	121	10	735	11	21	<0.5	<2	14	331	4.26	6	<20	<4	7	758	<0.4	<5	<5	198
927704	Drill Core		5.23	81	12	628	10	21	<0.5	<2	14	406	4.20	<5	<20	<4	6	638	<0.4	<5	<5	208
927705	Drill Core		4.78	126	9	914	7	24	<0.5	2	18	474	4.37	<5	<20	<4	6	554	<0.4	<5	<5	203
927706	Drill Core		4.85	88	60	888	5	22	<0.5	2	15	397	4.01	<5	<20	<4	6	596	<0.4	<5	<5	206
927707	Drill Core		4.95	86	11	633	<5	24	<0.5	2	14	379	4.17	<5	<20	<4	6	645	<0.4	<5	<5	206
927708	Drill Core		5.00	66	22	818	6	23	<0.5	2	17	310	3.82	<5	<20	<4	6	608	<0.4	<5	<5	214
927709	Drill Core		4.97	141	99	882	<5	21	<0.5	3	16	263	4.20	<5	<20	<4	6	670	<0.4	<5	<5	214
927710	Drill Core		1.74	<2	<2	2	<5	15	<0.5	<2	<2	166	0.37	<5	<20	<4	<2	45	<0.4	<5	<5	2
927711	Drill Core		4.80	84	37	596	10	27	<0.5	3	12	299	3.08	6	<20	<4	7	569	<0.4	<5	<5	185
927712	Drill Core		4.76	73	18	592	18	26	<0.5	2	12	356	3.18	<5	<20	<4	6	494	<0.4	<5	<5	187
927713	Drill Core		5.54	110	22	747	8	22	<0.5	2	12	331	3.87	<5	<20	<4	6	563	<0.4	<5	<5	198
927714	Drill Core		4.18	78	11	512	10	21	<0.5	11	12	579	4.08	12	<20	<4	6	402	<0.4	<5	<5	204
927715	Drill Core		4.32	151	26	869	7	24	<0.5	29	13	570	4.04	9	<20	<4	2	223	<0.4	<5	<5	198
927716	Drill Core		5.56	425	78	2721	6	28	1.7	63	20	742	5.59	35	<20	<4	<2	156	<0.4	<5	<5	259
927717	Drill Core		5.39	136	49	1100	10	17	<0.5	42	14	505	4.33	22	<20	<4	<2	194	<0.4	<5	<5	182
927718	Drill Core		5.17	182	53	1566	10	23	0.9	40	16	546	5.50	36	<20	<4	<2	238	<0.4	<5	<5	249
927719	Drill Core		5.07	47	14	368	<5	18	<0.5	28	8	588	3.60	7	<20	<4	<2	341	<0.4	<5	<5	218
927720	Drill Core		1.23	3	<2	9	<5	12	<0.5	<2	<2	177	0.42	<5	<20	<4	<2	48	<0.4	<5	<5	3
927721	Drill Core		4.92	60	34	554	<5	21	<0.5	44	11	724	5.12	15	<20	<4	<2	426	<0.4	<5	<5	202
927722	Drill Core		4.98	50	22	367	<5	19	<0.5	21	11	595	3.68	6	<20	<4	3	431	<0.4	<5	<5	202
927723	Drill Core		5.05	395	24	1353	<5	21	0.6	51	38	534	7.34	6	<20	<4	<2	401	<0.4	<5	<5	193
927724	Drill Core		4.99	1429	37	1097	<5	21	0.5	32	26	419	3.94	<5	<20	<4	2	375	<0.4	<5	<5	198
927725	Drill Core		2.08	109	25	574	<5	21	<0.5	29	28	376	4.24	<5	<20	<4	<2	380	<0.4	<5	<5	200
927726	Drill Core		3.10	118	255	606	<5	25	<0.5	39	31	376	4.69	<5	<20	<4	<2	412	<0.4	<5	<5	191
927727	Drill Core		3.96	78	39	362	<5	23	<0.5	31	22	438	4.17	<5	<20	<4	<2	414	<0.4	<5	<5	196
927728	Drill Core		3.68	104	108	348	<5	18	<0.5	41	17	523	4.52	6	<20	<4	<2	263	<0.4	<5	<5	186
927729	Drill Core		2.47	81	12	224	<5	19	<0.5	40	12	364	4.11	<5	<20	<4	<2	285	<0.4	<5	<5	206
927730	Drill Core		1.30	<2	<2	<2	<5	14	<0.5	<2	<2	157	0.34	<5	<20	<4	<2	43	<0.4	<5	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 7 of 8 Part 2

SMI09000208.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927701	Rock Pulp	1.65	0.097	10	24	1.29	686	0.27	6.94	2.94	3.27	7	72	5	12	6	1	10	0.5
927702	Drill Core	3.44	0.120	21	3	1.17	79	0.32	8.23	3.60	2.64	<4	72	<2	19	6	2	9	3.1
927703	Drill Core	3.22	0.140	24	3	1.24	97	0.35	8.49	3.88	2.99	5	76	3	19	6	1	10	2.6
927704	Drill Core	3.19	0.151	20	4	1.15	111	0.38	8.43	3.73	3.26	4	67	<2	19	5	1	11	2.4
927705	Drill Core	4.20	0.142	11	2	1.02	92	0.36	7.24	3.59	3.03	7	61	<2	16	6	1	10	2.6
927706	Drill Core	3.72	0.145	24	4	0.99	102	0.37	7.44	3.64	3.19	9	65	<2	15	6	1	10	2.6
927707	Drill Core	3.68	0.148	18	4	1.02	112	0.38	7.32	3.81	3.08	5	64	<2	17	6	1	10	2.7
927708	Drill Core	3.14	0.152	14	3	1.05	107	0.37	7.70	4.01	3.24	9	62	2	16	6	1	11	2.3
927709	Drill Core	3.30	0.149	15	4	1.09	88	0.37	7.32	3.80	2.68	8	69	<2	16	5	1	10	2.7
927710	Drill Core	21.00	0.019	<2	<2	11.98	17	<0.01	0.06	<0.01	0.03	<4	<2	<2	<2	<2	<1	<1	<0.1
927711	Drill Core	3.17	0.122	21	5	0.76	137	0.35	7.50	3.45	3.14	7	96	<2	16	6	1	8	2.1
927712	Drill Core	3.64	0.117	15	6	0.76	140	0.33	7.11	3.39	3.14	<4	91	<2	15	6	1	8	2.2
927713	Drill Core	3.55	0.135	17	4	0.94	105	0.35	7.37	3.60	3.11	8	78	2	16	6	1	9	2.7
927714	Drill Core	3.84	0.139	16	12	1.14	106	0.36	7.55	3.37	2.99	6	68	<2	17	5	<1	11	2.6
927715	Drill Core	3.41	0.109	7	41	1.32	127	0.35	6.64	2.68	3.36	8	48	<2	21	4	<1	12	2.2
927716	Drill Core	3.55	0.113	8	56	1.57	125	0.34	6.60	2.18	3.26	8	49	3	21	3	<1	13	2.5
927717	Drill Core	4.15	0.116	6	53	0.92	83	0.33	6.18	2.29	3.41	8	44	<2	15	4	<1	11	3.2
927718	Drill Core	3.59	0.123	6	44	1.22	65	0.38	6.83	3.50	2.66	10	36	2	14	4	<1	12	3.5
927719	Drill Core	3.91	0.135	7	48	1.47	127	0.40	7.08	3.91	2.10	<4	42	<2	19	4	<1	13	2.2
927720	Drill Core	21.44	0.021	<2	<2	12.41	21	<0.01	0.10	0.02	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927721	Drill Core	4.37	0.108	9	31	1.58	60	0.43	8.11	4.34	1.55	9	37	<2	17	5	<1	15	3.7
927722	Drill Core	4.53	0.124	10	32	1.24	130	0.36	7.46	4.79	1.13	6	53	<2	18	5	<1	12	2.6
927723	Drill Core	3.96	0.117	10	32	1.98	53	0.39	6.99	3.86	0.94	7	39	5	18	4	<1	14	5.8
927724	Drill Core	3.20	0.113	8	35	2.11	95	0.40	7.09	3.95	1.61	5	40	<2	16	5	<1	13	2.3
927725	Drill Core	3.13	0.117	8	39	2.12	72	0.40	7.22	4.02	1.60	6	37	<2	17	4	<1	13	2.7
927726	Drill Core	2.56	0.133	7	37	2.37	66	0.35	7.40	3.78	2.28	7	44	<2	16	6	<1	11	3.1
927727	Drill Core	3.00	0.118	8	43	2.22	104	0.39	7.53	4.22	1.65	4	40	<2	17	5	<1	13	2.2
927728	Drill Core	3.98	0.129	10	45	1.69	129	0.35	6.77	3.04	2.76	4	42	<2	19	4	<1	13	3.0
927729	Drill Core	3.00	0.137	9	52	1.96	139	0.37	6.92	2.78	3.14	5	45	3	20	4	<1	13	2.4
927730	Drill Core	21.32	0.027	<2	<2	12.19	18	<0.01	0.07	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 05, 2009

Page: 8 of 8 Part 1

SMI09000208.1

CERTIFICATE OF ANALYSIS

Method	Analyte	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927731	Rock Pulp	0.12	317	<2	3201	30	67	0.7	16	7	325	3.34	6	<20	<4	13	164	<0.4	<5	<5	41
927732	Drill Core	4.78	114	49	520	9	18	<0.5	10	23	251	5.54	10	<20	<4	7	312	<0.4	<5	<5	171
927733	Drill Core	5.24	52	31	191	10	17	<0.5	3	13	217	3.42	<5	<20	<4	7	403	<0.4	<5	<5	140
927734	Drill Core	4.86	63	27	205	5	18	<0.5	12	6	298	2.93	<5	<20	<4	4	569	<0.4	<5	<5	135
927735	Drill Core	4.87	91	43	191	<5	15	<0.5	27	7	237	3.42	7	<20	<4	<2	430	<0.4	<5	<5	128
927736	Drill Core	5.29	85	8	223	5	13	<0.5	49	11	281	3.86	7	<20	<4	3	207	<0.4	<5	<5	204
927737	Drill Core	4.70	67	18	186	6	12	<0.5	40	12	428	4.52	9	<20	<4	<2	314	<0.4	<5	<5	191
927738	Drill Core	5.46	61	19	107	<5	14	<0.5	42	10	365	3.66	8	<20	<4	2	271	<0.4	<5	<5	197
927739	Drill Core	5.19	72	6	123	<5	15	<0.5	40	13	370	4.11	7	<20	<4	<2	252	<0.4	<5	<5	196
927740	Drill Core	1.24	<2	<2	<2	<5	13	<0.5	3	<2	179	0.42	<5	<20	<4	<2	45	<0.4	<5	<5	3
927741	Drill Core	5.37	34	32	251	8	11	0.6	42	17	631	5.73	7	<20	<4	<2	327	1.4	<5	<5	228
927742	Drill Core	1.82	66	48	338	6	10	<0.5	35	20	598	7.12	20	<20	<4	<2	266	1.9	<5	7	225
927743	Drill Core	2.84	53	17	127	7	9	<0.5	6	14	442	4.58	6	<20	<4	8	430	0.8	<5	<5	172
927744	Drill Core	2.24	24	4	161	<5	5	<0.5	31	13	588	4.04	<5	<20	<4	<2	390	1.0	<5	<5	194
927745	Drill Core	5.18	75	36	373	8	9	0.6	43	18	547	5.80	6	<20	<4	<2	290	1.7	<5	<5	210
927746	Drill Core	4.39	107	52	595	8	7	0.8	38	27	608	8.10	6	<20	<4	<2	387	2.2	<5	5	173
927747	Drill Core	2.22	34	13	378	12	10	0.6	5	15	420	3.74	<5	<20	<4	8	596	0.8	<5	6	191
927748	Drill Core	4.71	4	<2	44	8	60	<0.5	51	27	1191	5.43	<5	<20	<4	<2	627	1.9	<5	<5	213
927749	Drill Core	5.08	3	<2	36	<5	57	<0.5	72	29	1097	5.16	<5	<20	<4	<2	444	1.5	<5	8	191
927750	Drill Core	1.31	<2	<2	<2	<5	13	<0.5	<2	<2	162	0.35	<5	<20	<4	<2	49	<0.4	<5	<5	2



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 05, 2009

Page: 8 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000208.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927731	Rock Pulp	1.10	0.042	23	16	0.47	742	0.15	6.17	2.28	3.39	8	50	7	13	9	2	6	0.3
927732	Drill Core	2.67	0.109	26	14	0.78	65	0.29	6.99	4.25	2.81	7	85	<2	15	6	1	7	5.1
927733	Drill Core	3.41	0.102	19	3	0.57	64	0.26	6.54	5.09	2.19	8	89	2	13	6	1	5	3.2
927734	Drill Core	4.03	0.116	9	13	0.95	106	0.32	7.66	4.75	2.11	9	61	<2	15	4	2	7	2.3
927735	Drill Core	3.15	0.116	5	27	1.36	70	0.29	7.10	5.02	1.13	8	37	3	13	2	1	8	2.7
927736	Drill Core	3.51	0.138	7	53	1.16	83	0.34	6.33	3.30	2.75	6	44	<2	18	3	<1	12	3.2
927737	Drill Core	4.85	0.118	10	45	0.93	51	0.36	6.87	3.73	2.05	9	41	<2	19	4	<1	13	3.9
927738	Drill Core	4.31	0.122	11	58	1.19	65	0.35	7.00	4.12	1.55	7	47	<2	20	4	<1	12	2.8
927739	Drill Core	3.34	0.127	9	53	1.38	91	0.37	6.75	3.33	2.49	4	40	3	19	4	<1	13	2.8
927740	Drill Core	23.58	0.024	2	10	13.16	18	<0.01	0.08	0.01	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927741	Drill Core	4.73	0.132	13	48	1.51	63	0.40	8.11	4.01	1.32	<4	41	<2	20	4	<1	18	4.0
927742	Drill Core	4.26	0.138	17	41	1.46	143	0.37	7.16	4.38	0.29	<4	42	<2	20	3	<1	17	5.7
927743	Drill Core	3.40	0.138	43	6	1.32	67	0.36	9.52	4.37	2.08	<4	86	3	23	7	1	11	3.4
927744	Drill Core	5.13	0.126	17	33	1.13	160	0.50	8.66	5.46	0.75	<4	66	<2	21	5	<1	16	3.0
927745	Drill Core	4.39	0.123	11	45	1.53	88	0.38	7.65	4.59	0.58	<4	50	3	20	4	<1	15	4.3
927746	Drill Core	5.21	0.089	10	32	1.14	54	0.37	7.91	4.66	0.86	5	35	<2	18	4	<1	15	7.9
927747	Drill Core	3.37	0.150	35	11	1.17	85	0.41	10.00	3.91	4.09	<4	94	3	26	7	1	12	2.2
927748	Drill Core	4.91	0.133	14	80	3.43	1664	0.56	9.78	2.51	2.30	<4	62	<2	20	5	1	28	0.4
927749	Drill Core	5.93	0.112	11	93	4.06	1925	0.48	10.20	1.30	2.41	<4	54	<2	16	4	<1	25	0.2
927750	Drill Core	22.78	0.029	2	<2	12.61	27	<0.01	0.15	0.01	0.08	<4	<2	<2	<2	<1	<1	<0.1	



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 05, 2009

Page:

1 of 4 Part 1

QUALITY CONTROL REPORT

SMI09000208.1

Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2	
Pulp Duplicates																					
REP 927562	QC		106	34	1222	9	19	<0.5	2	9	250	2.07	<5	<20	<4	8	417	<0.4	<5	<5	202
927576	Drill Core	4.87	83	7	1217	5	30	0.6	2	9	387	2.46	<5	<20	<4	7	556	0.4	<5	<5	192
REP 927576	QC			6	1227	11	30	0.8	<2	9	391	2.51	<5	<20	<4	7	558	0.6	<5	<5	196
927616	Drill Core	4.28	139	14	1422	13	27	0.5	<2	10	377	3.10	<5	<20	<4	11	638	<0.4	<5	<5	190
REP 927616	QC		136																		
927627	Drill Core	4.27	95	6	1247	<5	22	0.8	10	11	448	3.53	<5	<20	<4	9	321	0.5	<5	<5	170
REP 927627	QC			5	1253	6	23	0.7	10	11	447	3.55	<5	<20	<4	10	319	<0.4	<5	<5	171
927630	Drill Core	1.42	<2	<2	4	<5	13	<0.5	<2	<2	175	0.40	<5	<20	<4	<2	47	<0.4	<5	<5	2
REP 927630	QC		<2																		
927655	Drill Core	4.15	40	3	121	18	30	<0.5	<2	5	383	2.42	<5	<20	<4	10	304	<0.4	<5	<5	108
REP 927655	QC		35																		
927663	Drill Core	3.66	568	7	960	14	26	0.9	3	11	406	4.10	<5	<20	<4	6	407	0.6	<5	<5	209
REP 927663	QC			6	960	14	25	0.8	2	11	406	4.14	6	<20	<4	7	408	0.5	<5	<5	207
927686	Drill Core	5.05	92	19	868	11	28	0.6	<2	12	362	3.40	12	<20	<4	7	593	<0.4	<5	<5	166
REP 927686	QC			19	899	12	29	0.8	<2	12	373	3.46	17	<20	<4	7	618	<0.4	<5	<5	166
927709	Drill Core	4.97	141	99	882	<5	21	<0.5	3	16	263	4.20	<5	<20	<4	6	670	<0.4	<5	<5	214
REP 927709	QC		157																		
927722	Drill Core	4.98	50	22	367	<5	19	<0.5	21	11	595	3.68	6	<20	<4	3	431	<0.4	<5	<5	202
REP 927722	QC			18	358	8	18	<0.5	20	10	579	3.56	6	<20	<4	2	413	<0.4	<5	<5	197
927734	Drill Core	4.86	63	27	205	5	18	<0.5	12	6	298	2.93	<5	<20	<4	4	569	<0.4	<5	<5	135
REP 927734	QC		57																		
927741	Drill Core	5.37	34	32	251	8	11	0.6	42	17	631	5.73	7	<20	<4	<2	327	1.4	<5	<5	228
REP 927741	QC			32	245	6	10	<0.5	42	17	631	5.72	8	<20	<4	<2	327	1.5	<5	5	228
Core Reject Duplicates																					
927562	Drill Core	4.72	104	36	1237	11	20	<0.5	2	9	252	2.12	<5	<20	<4	8	421	<0.4	<5	<5	205
DUP 927562	QC		111	39	1176	10	19	<0.5	2	9	249	2.05	<5	<20	<4	8	397	<0.4	<5	<5	197
927597	Drill Core	5.09	163	23	1163	10	170	0.6	<2	12	374	2.88	<5	<20	<4	6	385	4.9	<5	<5	128
DUP 927597	QC		154	24	1118	12	257	<0.5	<2	12	370	2.80	<5	<20	<4	7	375	5.7	<5	<5	126

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 05, 2009

Page:

1 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000208.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1
Pulp Duplicates																		
REP 927562	QC	1.79	0.116	20	2	1.06	530	0.27	8.48	3.24	3.87	<4	42	<2	13	6	2	0.7
927576	Drill Core	3.12	0.133	18	3	0.57	337	0.33	8.65	3.34	3.09	<4	60	<2	12	6	1	7
REP 927576	QC	3.14	0.134	18	2	0.57	328	0.33	8.62	3.43	3.47	4	62	<2	12	7	1	7
927616	Drill Core	2.69	0.118	23	3	0.86	221	0.32	9.35	3.36	4.75	<4	71	<2	18	7	2	7
REP 927616	QC																	
927627	Drill Core	2.73	0.094	19	10	0.65	1194	0.27	8.49	3.23	4.45	<4	49	<2	14	6	<1	6
REP 927627	QC	2.74	0.096	19	9	0.66	954	0.27	8.48	3.25	4.45	<4	51	<2	14	6	<1	6
927630	Drill Core	22.71	0.026	2	<2	12.45	16	<0.01	0.10	0.02	0.04	<4	<2	<2	<2	<1	<1	<0.1
REP 927630	QC																	
927655	Drill Core	2.58	0.083	18	3	0.51	310	0.23	7.62	3.52	3.53	<4	47	<2	13	6	1	4
REP 927655	QC																	
927663	Drill Core	2.53	0.141	27	5	1.00	109	0.37	8.41	3.65	3.80	4	78	3	19	6	1	10
REP 927663	QC	2.53	0.137	26	5	0.99	101	0.37	8.19	3.63	3.61	7	79	3	18	6	1	10
927686	Drill Core	3.12	0.109	18	3	0.63	141	0.31	7.97	3.04	3.99	<4	88	<2	18	7	1	6
REP 927686	QC	3.18	0.107	15	2	0.62	135	0.32	7.80	3.01	4.25	4	89	<2	17	6	2	6
927709	Drill Core	3.30	0.149	15	4	1.09	88	0.37	7.32	3.80	2.68	8	69	<2	16	5	1	10
REP 927709	QC																	
927722	Drill Core	4.53	0.124	10	32	1.24	130	0.36	7.46	4.79	1.13	6	53	<2	18	5	<1	12
REP 927722	QC	4.42	0.120	9	30	1.21	130	0.36	7.22	4.78	1.10	6	51	<2	17	5	<1	12
927734	Drill Core	4.03	0.116	9	13	0.95	106	0.32	7.66	4.75	2.11	9	61	<2	15	4	2	7
REP 927734	QC																	
927741	Drill Core	4.73	0.132	13	48	1.51	63	0.40	8.11	4.01	1.32	<4	41	<2	20	4	<1	18
REP 927741	QC	4.70	0.131	13	45	1.54	63	0.40	8.03	3.98	1.31	<4	42	<2	20	4	<1	17
Core Reject Duplicates																		
927562	Drill Core	1.81	0.120	22	2	1.07	506	0.27	8.66	3.31	4.03	<4	43	<2	14	6	2	10
DUP 927562	QC	1.81	0.116	18	<2	1.02	461	0.27	8.18	3.22	3.77	<4	41	<2	13	6	1	9
927597	Drill Core	3.17	0.093	19	<2	0.65	136	0.25	8.40	3.47	3.59	<4	67	<2	18	7	1	4
DUP 927597	QC	3.10	0.091	17	5	0.62	124	0.24	7.75	3.37	3.38	4	64	<2	17	6	1	4



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dun

Report Date

October 05, 2009

www.acmelab.com

Page:

2 of 4 Part

QUALITY CONTROL REPORT

SMI09000208.1



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 05, 2009

Page:

2 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000208.1

		1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S
		% 0.01	% 0.002	ppm 2	ppm 2	% 0.01	ppm 1	% 0.01	% 0.01	% 0.01	% 0.01	ppm 4	ppm 2	ppm 2	ppm 2	ppm 2	ppm 1	ppm 1	% 0.1
927632	Drill Core	3.06	0.126	19	38	0.92	100	0.35	7.88	3.86	2.52	<4	47	2	18	4	<1	13	1.8
DUP 927632	QC	3.05	0.128	20	38	0.93	95	0.36	7.93	3.83	2.56	4	48	<2	18	5	<1	13	1.9
927667	Drill Core	9.26	0.078	21	<2	0.52	58	0.19	5.99	1.72	2.39	10	40	3	18	4	<1	6	8.6
DUP 927667	QC	9.34	0.078	20	<2	0.51	54	0.19	5.85	1.71	2.31	10	39	2	17	4	<1	5	8.6
927702	Drill Core	3.44	0.120	21	3	1.17	79	0.32	8.23	3.60	2.64	<4	72	<2	19	6	2	9	3.1
DUP 927702	QC	3.30	0.122	19	3	1.13	90	0.32	8.20	3.55	2.64	5	70	<2	18	5	2	9	3.0
927737	Drill Core	4.85	0.118	10	45	0.93	51	0.36	6.87	3.73	2.05	9	41	<2	19	4	<1	13	3.9
DUP 927737	QC	4.07	0.122	9	47	0.90	55	0.36	6.68	3.93	2.08	8	40	<2	18	3	<1	12	3.3
Reference Materials																			
STD OREAS24P	Standard	5.44	0.128	17	189	3.84	269	0.99	7.76	2.33	0.68	<4	145	<2	22	19	1	19	<0.1
STD OREAS24P	Standard	5.52	0.130	17	186	3.89	272	1.00	7.82	2.35	0.69	4	146	<2	22	20	1	18	<0.1
STD OREAS24P	Standard	5.49	0.131	18	195	3.87	273	1.00	7.68	2.30	0.69	<4	142	<2	22	21	1	20	<0.1
STD OREAS24P	Standard	5.41	0.132	17	196	3.93	267	0.97	7.72	2.30	0.53	<4	142	<2	22	19	1	20	<0.1
STD OREAS24P	Standard	5.65	0.133	18	188	3.97	277	1.01	7.97	2.46	0.71	<4	146	<2	22	21	1	20	<0.1
STD OREAS24P	Standard	5.91	0.139	19	210	4.14	289	1.06	8.19	2.43	0.73	<4	152	<2	24	22	1	21	<0.1
STD OREAS24P	Standard	5.73	0.135	18	195	4.05	281	1.03	8.04	2.47	0.72	<4	149	<2	23	21	1	20	<0.1
STD OREAS45P	Standard	0.28	0.044	23	1019	0.18	283	0.98	6.73	0.07	0.34	<4	163	<2	13	20	<1	63	<0.1
STD OREAS45P	Standard	0.28	0.045	23	1042	0.19	294	1.02	6.74	0.07	0.35	7	167	3	13	21	<1	62	<0.1
STD OREAS45P	Standard	0.28	0.046	24	1048	0.19	294	1.00	6.90	0.07	0.35	<4	160	<2	14	21	<1	67	<0.1
STD OREAS45P	Standard	0.29	0.045	25	1063	0.19	293	0.94	6.98	0.07	0.35	<4	159	<2	14	19	<1	68	<0.1
STD OREAS45P	Standard	0.30	0.046	25	1088	0.19	298	0.97	7.10	0.07	0.36	<4	163	4	14	21	<1	68	<0.1
STD OREAS45P	Standard	0.31	0.047	26	1130	0.21	307	1.02	7.43	0.07	0.37	<4	169	<2	15	22	<1	72	<0.1
STD OREAS45P	Standard	0.29	0.046	25	1084	0.20	299	1.07	7.04	0.07	0.36	<4	168	3	14	21	<1	68	<0.1
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 05, 2009

www.acmelab.com

Page:

3 of 4 Part

QUALITY CONTROL REPORT

SMI09000208.1



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Durn

Report Date:

October 05, 2009

www.acmelab.com

Page:

3 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000208.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 05, 2009

www.acmelab.com

Page:

4 of 4 Part

QUALITY CONTROL REPORT

SMI09000208.1

	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
Prep Wash																				
G1	Prep Blank	<2	<2	4	21	55	<0.5	4	5	731	2.40	<5	<20	<4	6	684	<0.4	<5	<5	53
G1	Prep Blank	<2	<2	9	24	70	<0.5	4	5	751	2.36	<5	<20	<4	5	692	<0.4	<5	<5	53



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date: October 05, 2009

www.acmelab.com

Page: 4 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000208.1

	1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S	
	% %	% %	ppm ppm	ppm ppm	% %	ppm ppm	% %	% %	% %	ppm ppm	ppm %								
	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1	
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
G1	Prep Blank	2.43	0.085	21	13	0.64	965	0.24	7.14	2.60	2.66	<4	10	<2	14	23	3	5	<0.1
G1	Prep Blank	2.37	0.085	21	11	0.66	971	0.25	7.03	2.61	2.47	<4	10	<2	14	24	3	5	<0.1



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 09, 2009
Report Date: October 12, 2009
Page: 1 of 8

CERTIFICATE OF ANALYSIS

SMI09000209.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 200

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
Code					
R200	193	Crush split and pulverize drill core to 200 mesh			VAN
3B	200	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	200	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC: Nigel Luckman
B. Booth



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page: 2 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000209.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
927751	Drill Core		3.47	35	38	246	11	61	<0.5	3	16	789	8.77	52	<20	<4	6	222	<0.4	<5	6	269
927752	Drill Core		5.06	43	80	338	14	64	<0.5	<2	15	944	8.54	44	<20	<4	5	239	<0.4	<5	8	195
927753	Drill Core		5.18	39	81	222	13	73	<0.5	<2	18	850	8.39	41	<20	<4	5	195	<0.4	<5	8	252
927754	Drill Core		2.70	59	82	179	13	63	<0.5	2	17	877	6.56	103	<20	<4	4	219	<0.4	<5	<5	175
927755	Drill Core		4.10	51	357	221	10	59	<0.5	<2	22	1021	6.75	94	<20	<4	5	300	<0.4	<5	12	217
927756	Drill Core		4.88	292	209	1138	9	89	0.6	<2	24	1521	6.18	186	<20	<4	5	317	<0.4	12	7	193
927757	Drill Core		2.63	50	73	205	11	51	<0.5	<2	9	967	6.05	63	<20	<4	4	271	<0.4	<5	5	135
927758	Drill Core		4.75	22	64	93	9	54	<0.5	<2	11	829	5.21	12	<20	<4	5	272	<0.4	<5	6	105
927759	Drill Core		3.18	30	90	364	11	44	<0.5	3	18	743	7.04	18	<20	<4	4	264	<0.4	<5	6	149
927760	Drill Core		1.03	<2	<2	<2	5	9	<0.5	<2	<2	197	0.44	<5	<20	<4	<2	46	<0.4	<5	<5	4
927761	Rock Pulp		0.15	310	2	3393	31	70	1.2	18	7	355	3.70	<5	<20	<4	12	169	<0.4	<5	9	43
927762	Drill Core		4.31	160	14	545	12	22	0.7	3	15	594	3.85	21	<20	<4	9	287	0.5	<5	8	221
927763	Drill Core		4.30	214	7	907	15	36	1.0	2	31	455	5.03	10	<20	<4	9	378	0.4	<5	<5	212
927764	Drill Core		3.87	206	14	659	16	29	0.8	2	17	543	4.01	15	<20	<4	8	359	0.4	<5	<5	196
927765	Drill Core		4.86	249	9	305	16	29	<0.5	<2	10	674	3.73	35	<20	<4	8	324	0.4	<5	11	146
927766	Drill Core		4.71	321	7	638	8	19	0.8	3	17	727	4.30	56	<20	<4	8	611	0.6	<5	<5	221
927767	Drill Core		4.66	87	3	456	10	19	0.6	2	23	715	3.96	<5	<20	<4	10	650	<0.4	<5	6	227
927768	Drill Core		4.92	112	3	624	7	19	0.8	2	24	602	4.76	<5	<20	<4	9	582	0.5	<5	<5	225
927769	Drill Core		4.48	52	3	304	<5	19	<0.5	3	18	776	4.55	<5	<20	<4	8	525	<0.4	<5	7	206
927770	Drill Core		0.85	<2	<2	3	5	10	<0.5	<2	<2	197	0.43	<5	<20	<4	<2	45	<0.4	<5	<5	3
927771	Drill Core		4.54	44	2	170	7	14	<0.5	<2	8	397	3.43	<5	<20	<4	7	271	<0.4	<5	<5	116
927772	Drill Core		4.92	195	2	952	<5	17	0.7	3	19	678	3.98	<5	<20	<4	8	639	<0.4	<5	8	218
927773	Drill Core		1.85	421	37	1193	<5	17	1.4	3	23	633	3.26	<5	<20	<4	9	407	<0.4	<5	<5	205
927774	Drill Core		2.85	742	47	3312	46	27	5.3	5	26	915	8.15	106	<20	<4	9	342	<0.4	<5	10	268
927775	Drill Core		4.68	1107	7	2624	15	18	2.5	5	32	412	3.88	12	<20	<4	10	414	<0.4	<5	5	232
927776	Drill Core		4.71	444	4	1830	8	16	1.6	3	23	505	3.21	<5	<20	<4	10	417	<0.4	<5	<5	239
927777	Drill Core		4.55	584	21	1414	11	19	1.0	4	34	678	5.09	38	<20	<4	9	347	<0.4	<5	<5	242
927778	Drill Core		2.51	302	30	480	18	31	<0.5	<2	15	667	6.14	24	<20	<4	9	272	0.5	<5	7	193
927779	Drill Core		4.60	125	17	475	9	14	0.6	5	7	750	3.76	7	<20	<4	9	390	0.5	<5	6	219
927780	Drill Core		0.75	<2	<2	3	<5	6	<0.5	<2	<2	194	0.42	<5	<20	<4	<2	45	0.8	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 2 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927751	Drill Core	0.55	0.188	36	2	1.66	22	0.48	8.74	4.38	1.63	13	29	<2	25	6	1	17	4.3
927752	Drill Core	1.30	0.170	34	2	1.52	27	0.40	9.03	4.51	1.61	22	28	<2	29	4	1	15	4.8
927753	Drill Core	1.35	0.197	28	3	1.70	29	0.45	8.62	4.13	2.00	32	25	<2	28	5	1	17	4.1
927754	Drill Core	2.61	0.188	32	4	1.33	35	0.42	8.35	3.31	3.34	19	32	<2	33	5	1	14	4.9
927755	Drill Core	4.07	0.160	46	<2	1.59	33	0.50	8.23	4.38	1.28	27	21	<2	31	5	1	16	5.4
927756	Drill Core	7.58	0.185	63	<2	1.99	54	0.40	7.32	3.67	1.18	31	27	<2	39	5	1	15	5.1
927757	Drill Core	4.65	0.139	30	<2	1.31	38	0.41	7.94	4.03	1.84	22	22	<2	28	6	1	10	5.0
927758	Drill Core	2.11	0.153	34	6	1.12	33	0.32	8.52	5.00	1.62	17	42	<2	28	5	1	7	3.7
927759	Drill Core	1.77	0.165	33	2	1.19	24	0.35	8.92	5.48	0.88	11	32	<2	27	5	1	12	5.5
927760	Drill Core	21.49	0.029	2	<2	11.93	18	<0.01	0.13	0.03	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927761	Rock Pulp	1.31	0.045	25	19	0.52	587	0.16	7.14	2.44	3.94	<4	48	7	15	10	3	7	0.3
927762	Drill Core	3.78	0.160	21	8	1.01	74	0.46	8.71	3.25	3.22	7	55	<2	20	6	2	12	2.5
927763	Drill Core	3.72	0.161	23	3	0.64	46	0.41	8.76	4.22	2.53	<4	64	<2	19	7	2	11	4.5
927764	Drill Core	4.37	0.142	18	3	0.58	52	0.37	8.59	3.80	3.19	4	77	<2	19	7	2	10	3.6
927765	Drill Core	3.48	0.103	16	2	0.74	63	0.28	8.47	3.06	4.28	<4	79	<2	18	6	2	6	2.6
927766	Drill Core	4.79	0.153	23	4	0.83	65	0.39	7.88	5.11	1.06	<4	34	<2	20	6	2	12	3.1
927767	Drill Core	5.01	0.160	29	4	0.83	72	0.39	8.83	5.35	0.89	<4	34	<2	24	6	2	13	2.9
927768	Drill Core	4.53	0.153	21	3	0.87	58	0.39	8.49	4.92	1.16	<4	31	<2	21	6	1	12	3.6
927769	Drill Core	4.24	0.152	26	5	0.80	51	0.37	9.07	4.54	2.10	<4	39	<2	23	6	2	12	3.3
927770	Drill Core	21.02	0.020	<2	<2	11.71	16	<0.01	0.07	<0.01	0.03	<4	<2	<2	<2	<1	<1	<0.1	
927771	Drill Core	2.93	0.078	11	2	0.53	61	0.21	8.90	2.91	4.42	<4	83	<2	17	6	1	5	2.7
927772	Drill Core	5.42	0.161	21	4	0.69	83	0.40	8.56	5.24	1.10	<4	39	<2	21	7	2	12	2.7
927773	Drill Core	3.47	0.169	25	4	1.27	188	0.36	9.44	5.86	0.57	5	34	<2	23	6	1	14	0.7
927774	Drill Core	4.78	0.152	27	3	1.34	32	0.29	8.08	4.69	0.84	12	25	<2	28	4	1	14	6.8
927775	Drill Core	2.79	0.168	32	5	0.74	60	0.38	9.13	5.60	0.94	11	36	<2	18	6	1	12	2.7
927776	Drill Core	3.00	0.189	25	4	0.80	111	0.41	9.59	5.92	1.04	9	41	2	18	6	2	13	1.8
927777	Drill Core	3.47	0.158	28	2	1.23	43	0.31	8.22	4.24	1.12	10	33	<2	23	4	2	13	3.7
927778	Drill Core	3.82	0.131	18	<2	1.00	35	0.28	8.81	3.02	3.25	7	61	<2	22	5	3	10	5.7
927779	Drill Core	5.14	0.117	16	13	0.73	51	0.35	8.61	4.63	2.02	4	40	<2	20	5	1	11	3.2
927780	Drill Core	21.40	0.022	2	<2	11.83	18	<0.01	0.13	0.01	0.05	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page: 3 of 8 Part 1

SMI09000209.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	2	0.01	5	20	4	2	2	0.4	5	5	2
927781	Drill Core	4.47	54	25	463	6	17	<0.5	<2	8	491	3.76	<5	<20	<4	12	425	<0.4	<5	6	195
927782	Drill Core	5.20	147	13	769	<5	13	0.6	3	8	486	2.76	<5	<20	<4	7	317	<0.4	<5	<5	171
927783	Drill Core	1.89	88	34	348	7	24	<0.5	6	4	1085	6.88	8	<20	<4	8	183	<0.4	<5	7	291
927784	Drill Core	4.88	259	52	871	<5	24	1.0	4	11	615	4.28	<5	<20	<4	8	323	<0.4	<5	<5	251
927785	Drill Core	4.24	77	19	423	<5	19	<0.5	3	7	662	2.98	<5	<20	<4	6	457	<0.4	<5	<5	178
927786	Drill Core	5.08	181	12	349	5	13	0.7	<2	9	373	3.71	<5	<20	<4	7	413	<0.4	<5	<5	169
927787	Drill Core	4.72	125	14	278	7	16	0.6	4	5	654	3.37	<5	<20	<4	7	588	<0.4	<5	<5	251
927788	Drill Core	4.41	461	18	544	5	19	0.9	2	10	401	4.68	<5	<20	<4	7	490	<0.4	<5	<5	174
927789	Drill Core	4.48	211	6	322	6	22	0.8	2	8	505	4.93	<5	<20	<4	8	579	<0.4	<5	<5	187
927790	Drill Core	0.73	<2	<2	3	<5	16	<0.5	2	<2	188	0.37	<5	<20	<4	<2	53	<0.4	<5	<5	4
927791	Drill Core	4.44	130	5	363	<5	24	<0.5	3	6	712	3.09	<5	<20	<4	7	589	<0.4	<5	<5	187
927792	Drill Core	2.70	265	9	508	7	25	0.6	4	6	862	2.91	<5	<20	<4	5	501	<0.4	<5	<5	185
927793	Drill Core	4.54	5	<2	45	<5	70	<0.5	22	21	1203	5.16	<5	<20	<4	<2	511	<0.4	<5	<5	195
927794	Drill Core	4.45	170	16	767	<5	23	0.9	4	11	504	3.75	<5	<20	<4	8	466	<0.4	<5	<5	204
927795	Drill Core	5.43	299	14	1346	<5	26	1.6	4	19	715	6.13	<5	<20	<4	8	354	<0.4	<5	<5	263
927796	Drill Core	4.39	148	14	602	24	20	0.8	2	7	604	3.05	<5	<20	<4	7	336	<0.4	<5	<5	188
927797	Drill Core	4.66	134	4	729	<5	28	1.2	3	8	756	5.86	<5	<20	<4	5	593	<0.4	<5	<5	254
927798	Drill Core	5.63	126	4	689	6	31	1.0	3	8	620	5.17	<5	<20	<4	11	745	<0.4	<5	<5	212
927799	Drill Core	4.02	281	8	873	<5	60	1.2	3	14	663	5.56	5	<20	<4	5	615	<0.4	<5	<5	230
927800	Drill Core	0.74	<2	<2	9	<5	14	<0.5	<2	<2	182	0.38	<5	<20	<4	<2	51	<0.4	<5	<5	4
927801	Rock Pulp	0.15	322	<2	3301	25	67	1.4	17	7	349	3.67	<5	<20	<4	12	171	<0.4	<5	<5	43
927802	Drill Core	4.95	158	7	1227	<5	24	1.5	4	16	567	4.95	7	<20	<4	6	431	<0.4	<5	<5	242
927803	Drill Core	4.79	148	6	888	<5	25	1.3	2	7	615	3.30	<5	<20	<4	7	372	<0.4	<5	<5	177
927804	Drill Core	5.05	159	8	631	9	38	1.7	19	18	1038	4.34	16	<20	<4	3	375	<0.4	<5	<5	213
927805	Drill Core	4.82	87	4	410	5	99	1.6	3	16	1013	3.63	8	<20	<4	5	347	0.6	<5	<5	236
927806	Drill Core	4.87	81	16	517	<5	21	0.8	4	10	919	2.42	<5	<20	<4	6	350	<0.4	<5	<5	274
927807	Drill Core	5.24	241	<2	133	<5	45	<0.5	13	16	877	3.88	<5	<20	<4	<2	285	<0.4	<5	<5	195
927808	Drill Core	4.31	7	3	85	<5	52	<0.5	20	18	996	4.14	<5	<20	<4	<2	277	<0.4	<5	<5	182
927809	Drill Core	5.17	4	<2	33	<5	61	<0.5	25	20	1193	4.81	<5	<20	<4	<2	315	<0.4	<5	<5	180
927810	Drill Core	0.80	<2	<2	<2	20	14	0.6	<2	<2	184	0.39	<5	<20	<4	<2	44	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 3 of 8 Part 2

SMI09000209.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927781	Drill Core	2.95	0.132	26	6	1.13	87	0.31	9.38	5.56	1.16	<4	63	<2	22	6	1	10	1.7
927782	Drill Core	3.73	0.122	16	6	0.52	100	0.32	8.75	3.76	4.26	<4	60	<2	16	6	1	8	1.7
927783	Drill Core	4.38	0.070	17	7	1.68	98	0.26	7.37	3.28	0.71	6	29	<2	17	4	<1	7	1.7
927784	Drill Core	3.14	0.116	17	7	1.11	393	0.33	8.58	4.30	2.74	4	52	<2	14	8	1	8	0.9
927785	Drill Core	3.81	0.112	19	4	0.92	284	0.33	8.78	4.79	2.12	<4	77	<2	19	8	2	8	1.3
927786	Drill Core	3.01	0.115	23	3	0.59	176	0.33	9.32	3.98	3.76	4	97	<2	19	9	2	8	3.0
927787	Drill Core	4.99	0.152	20	4	0.49	153	0.39	8.53	4.37	2.63	<4	75	<2	19	9	2	10	2.0
927788	Drill Core	2.39	0.120	26	5	1.03	182	0.33	9.31	3.84	3.76	6	91	<2	23	8	2	9	3.0
927789	Drill Core	3.38	0.121	24	3	1.01	146	0.33	8.62	4.21	2.66	<4	82	<2	19	8	2	8	2.2
927790	Drill Core	22.67	0.030	3	<2	12.12	22	<0.01	0.23	0.02	0.11	<4	<2	<2	<2	<2	<1	<1	<0.1
927791	Drill Core	4.87	0.129	22	8	0.73	325	0.37	8.60	3.53	4.11	<4	66	<2	19	9	1	10	0.9
927792	Drill Core	6.56	0.115	15	7	0.53	311	0.35	6.94	3.87	3.76	<4	56	<2	16	9	1	8	1.0
927793	Drill Core	5.03	0.156	18	39	2.45	1046	0.58	9.06	3.27	1.92	<4	72	<2	17	12	1	19	0.3
927794	Drill Core	2.63	0.117	23	4	0.83	333	0.36	9.33	4.82	2.87	<4	64	<2	12	9	1	8	1.4
927795	Drill Core	3.50	0.124	21	4	0.75	157	0.37	8.55	3.98	3.15	<4	63	<2	14	8	1	12	3.2
927796	Drill Core	3.93	0.104	16	3	0.39	216	0.30	7.83	2.41	5.38	<4	74	<2	11	7	1	9	1.4
927797	Drill Core	4.48	0.125	23	3	0.82	138	0.39	8.09	3.69	3.05	<4	64	<2	12	7	2	13	2.5
927798	Drill Core	4.66	0.135	40	<2	0.98	2326	0.35	9.24	3.24	3.47	<4	83	<2	19	7	2	12	2.8
927799	Drill Core	4.74	0.147	17	3	0.76	82	0.37	7.63	3.99	2.74	<4	62	<2	11	7	2	9	3.6
927800	Drill Core	22.23	0.026	3	<2	12.02	29	<0.01	0.13	0.03	0.05	<4	<2	<2	<2	<1	<1	<0.1	
927801	Rock Pulp	1.34	0.042	27	17	0.52	810	0.16	7.11	2.38	3.91	<4	58	8	14	10	3	7	0.3
927802	Drill Core	3.43	0.144	21	5	0.60	166	0.35	8.57	3.68	3.51	5	66	<2	10	7	1	11	3.9
927803	Drill Core	3.76	0.106	14	4	0.56	190	0.32	7.52	2.43	4.97	<4	67	<2	9	9	1	7	1.7
927804	Drill Core	5.93	0.120	13	18	1.00	139	0.38	7.04	3.17	2.81	<4	56	<2	12	8	1	10	2.5
927805	Drill Core	5.23	0.149	14	<2	1.11	178	0.34	7.43	4.26	1.60	<4	67	<2	13	6	1	10	2.0
927806	Drill Core	5.10	0.159	20	6	1.23	450	0.34	8.05	4.28	1.51	<4	48	<2	16	7	1	13	0.8
927807	Drill Core	4.03	0.150	14	26	1.95	784	0.47	8.05	2.43	2.38	<4	58	<2	15	10	1	15	0.4
927808	Drill Core	3.90	0.141	13	35	2.12	1032	0.50	8.68	2.61	2.56	<4	62	<2	15	10	1	15	0.3
927809	Drill Core	4.10	0.149	11	42	2.54	958	0.55	8.43	2.88	2.17	<4	64	<2	12	11	1	15	0.3
927810	Drill Core	21.41	0.023	2	<2	11.76	16	<0.01	0.11	0.01	0.04	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page: 4 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000209.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	V	
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927811	Drill Core		2.51	5	<2	39	<5	57	<0.5	19	21	1201	5.01	<5	<20	<4	<2	339	<0.4	<5	<5	195
927812	Drill Core		0.82	13	11	284	30	29	0.8	27	12	1199	2.79	<5	<20	<4	5	364	<0.4	<5	<5	158
927813	Drill Core		3.89	4	<2	44	<5	62	0.6	98	31	1729	5.79	9	<20	<4	<2	219	<0.4	<5	<5	215
927814	Drill Core		5.00	5	<2	49	8	71	<0.5	102	31	1455	5.64	<5	<20	<4	3	304	0.4	<5	6	199
927815	Drill Core		1.83	204	10	294	30	37	3.3	9	10	983	16.60	157	<20	<4	2	234	<0.4	19	<5	128
927816	Drill Core		4.55	103	16	554	6	22	1.2	6	10	480	2.00	52	<20	<4	7	361	<0.4	<5	<5	209
927817	Drill Core		4.72	211	9	834	<5	21	1.2	4	11	437	3.07	6	<20	<4	6	364	<0.4	<5	<5	199
927818	Drill Core		2.76	73	7	407	<5	23	1.1	15	12	655	2.79	12	<20	<4	5	275	<0.4	<5	<5	269
927819	Drill Core		4.89	17	<2	194	<5	14	<0.5	7	4	3243	1.43	<5	<20	<4	3	471	<0.4	<5	<5	82
927820	Drill Core		0.96	<2	<2	2	<5	5	<0.5	<2	<2	32	0.04	<5	<20	<4	<2	4079	<0.4	<5	<5	<2
927821	Rock Pulp		0.15	647	2	5191	12	66	1.1	17	13	432	5.24	5	<20	<4	4	439	<0.4	<5	<5	124
927822	Drill Core		4.38	55	7	390	6	17	<0.5	5	8	638	1.85	<5	<20	<4	6	313	<0.4	<5	<5	202
927823	Drill Core		5.01	57	4	134	10	26	<0.5	9	9	775	3.00	5	<20	<4	4	184	<0.4	<5	<5	208
927824	Drill Core		4.39	40	3	46	6	24	<0.5	3	7	1062	3.13	14	<20	<4	8	244	<0.4	<5	<5	190
927825	Drill Core		4.56	36	2	29	7	23	<0.5	3	7	812	3.15	14	<20	<4	7	217	<0.4	<5	<5	231
927826	Drill Core		4.98	51	2	30	9	24	<0.5	3	7	818	3.29	17	<20	<4	8	227	<0.4	<5	<5	223
927827	Drill Core		5.06	32	2	83	13	30	<0.5	2	8	781	4.08	17	<20	<4	9	290	<0.4	<5	<5	215
927828	Drill Core		4.54	16	<2	34	11	34	<0.5	2	8	720	3.85	12	<20	<4	8	313	<0.4	<5	<5	225
927829	Drill Core		5.02	22	2	37	8	28	<0.5	3	7	832	3.62	12	<20	<4	7	258	<0.4	<5	<5	259
927830	Drill Core		0.89	<2	<2	<2	<5	4	<0.5	<2	<2	32	0.06	<5	21	<4	<2	4449	<0.4	<5	<5	<2
927831	Drill Core		4.87	91	<2	61	<5	28	<0.5	2	7	716	3.74	10	<20	<4	7	202	<0.4	<5	<5	219
927832	Drill Core		6.61	31	2	52	7	25	<0.5	4	6	713	3.10	10	<20	<4	6	155	<0.4	<5	<5	226
927833	Drill Core		5.31	9	<2	43	6	68	<0.5	43	22	1000	5.43	10	<20	<4	<2	194	<0.4	<5	<5	218
927834	Drill Core		2.98	13	<2	20	<5	25	<0.5	6	5	943	2.98	8	<20	<4	5	189	<0.4	<5	<5	248
927835	Drill Core		5.17	69	<2	22	10	41	<0.5	5	7	703	3.25	14	<20	<4	6	222	<0.4	<5	<5	289
927836	Drill Core		4.57	37	<2	34	7	33	<0.5	5	7	714	3.73	13	<20	<4	7	256	<0.4	<5	<5	305
927837	Drill Core		5.11	65	<2	73	9	32	<0.5	4	7	611	3.40	11	<20	<4	7	224	<0.4	<5	<5	219
927838	Drill Core		4.90	33	2	155	<5	29	<0.5	8	7	697	3.51	12	<20	<4	6	255	<0.4	<5	<5	305
927839	Drill Core		3.98	278	6	1679	5	33	1.7	23	12	795	3.91	7	<20	<4	3	321	<0.4	<5	<5	295
927840	Drill Core		1.23	<2	<2	2	<5	3	<0.5	<2	<2	25	0.04	<5	<20	<4	<2	4041	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 4 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927811	Drill Core	4.64	0.163	19	36	2.56	734	0.59	8.88	3.06	1.75	<4	87	<2	18	12	1	20	0.3
927812	Drill Core	7.12	0.119	22	25	1.70	336	0.39	7.76	3.50	1.07	<4	68	<2	16	8	1	12	0.2
927813	Drill Core	8.55	0.186	22	100	3.74	456	0.58	7.81	1.03	1.57	<4	93	<2	21	11	1	23	0.2
927814	Drill Core	7.87	0.180	17	104	3.67	526	0.57	7.62	0.76	1.75	<4	43	<2	18	7	1	21	0.3
927815	Drill Core	6.00	0.074	15	7	0.64	53	0.20	4.96	1.98	1.31	6	29	<2	16	4	1	11	17.1
927816	Drill Core	3.51	0.124	14	6	0.79	339	0.34	8.47	4.59	1.91	13	58	2	13	8	2	10	0.9
927817	Drill Core	3.17	0.110	13	4	0.78	157	0.31	8.61	4.17	2.54	7	57	<2	16	7	2	8	1.9
927818	Drill Core	3.80	0.146	13	16	1.05	323	0.41	8.53	3.66	2.69	10	47	<2	15	9	2	13	0.9
927819	Drill Core	24.07	0.045	20	6	0.70	182	0.13	3.19	1.14	0.56	<4	23	<2	25	2	<1	5	0.2
927820	Drill Core	38.45	0.004	<2	<2	2.22	6	<0.01	0.02	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
927821	Rock Pulp	1.70	0.100	13	24	1.32	699	0.27	7.83	2.91	3.17	<4	72	5	13	7	1	12	0.6
927822	Drill Core	4.05	0.117	14	4	0.91	865	0.30	7.85	3.55	2.33	6	37	<2	12	5	1	9	0.5
927823	Drill Core	3.41	0.122	12	20	1.15	261	0.33	7.48	1.31	3.59	4	37	<2	13	5	<1	11	1.0
927824	Drill Core	3.17	0.115	18	<2	0.95	456	0.28	8.24	2.01	4.54	<4	67	<2	17	7	1	6	0.7
927825	Drill Core	2.14	0.119	16	3	0.98	484	0.29	8.35	1.86	4.00	<4	64	<2	14	6	1	7	0.6
927826	Drill Core	2.60	0.118	16	3	0.95	329	0.30	8.50	2.16	4.04	4	69	2	14	6	1	6	0.8
927827	Drill Core	2.44	0.135	21	2	1.21	418	0.34	9.56	2.94	4.37	<4	77	<2	16	8	1	7	0.9
927828	Drill Core	2.71	0.129	19	<2	1.10	571	0.32	9.18	2.96	4.07	<4	67	<2	17	7	<1	7	0.8
927829	Drill Core	2.96	0.124	19	3	1.08	544	0.32	8.71	2.41	4.19	<4	64	3	16	7	<1	7	0.7
927830	Drill Core	38.79	0.003	<2	<2	1.82	12	<0.01	0.05	<0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	
927831	Drill Core	2.23	0.135	19	3	1.23	519	0.33	9.13	2.16	4.71	<4	64	<2	15	6	<1	7	0.8
927832	Drill Core	2.38	0.135	15	3	1.14	707	0.28	7.01	1.54	3.26	<4	47	<2	13	6	<1	8	0.5
927833	Drill Core	3.15	0.193	14	59	2.72	1019	0.64	8.70	1.10	2.85	5	54	<2	18	9	2	22	0.5
927834	Drill Core	4.07	0.109	16	5	1.12	558	0.25	6.61	1.46	3.33	<4	41	<2	15	5	<1	8	0.5
927835	Drill Core	2.63	0.163	14	3	1.14	466	0.31	7.57	2.07	4.21	<4	54	<2	14	6	<1	7	0.6
927836	Drill Core	2.67	0.154	17	4	1.20	604	0.35	8.83	2.36	4.41	<4	65	<2	15	7	1	8	0.6
927837	Drill Core	2.09	0.128	19	3	1.19	744	0.33	8.60	2.50	4.19	<4	67	<2	14	7	<1	8	0.5
927838	Drill Core	2.60	0.140	16	9	1.13	707	0.34	8.34	2.42	4.20	<4	61	<2	12	6	<1	9	0.6
927839	Drill Core	3.66	0.123	15	38	1.43	569	0.37	7.65	3.42	1.83	<4	37	<2	12	5	<1	13	0.9
927840	Drill Core	38.00	0.003	<2	<2	2.01	10	<0.01	0.05	<0.01	0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page:

5 of 8

Part 1

CERTIFICATE OF ANALYSIS

SMI09000209.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V		
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi		
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm			
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2		
927841	Drill Core		4.50	59	6	437	6	23	<0.5	19	7	660	3.04	7	<20	<4	<2	370	<0.4	<5	<5	298	
927842	Drill Core		4.91	122	7	916	7	22	1.4	19	9	610	3.35	8	<20	<4	<2	328	<0.4	<5	<5	251	
927843	Drill Core		4.98	96	6	778	9	28	1.0	22	10	702	3.52	<5	<20	<4	<2	375	<0.4	<5	<5	308	
927844	Drill Core		4.90	185	7	569	8	20	0.9	19	6	639	2.55	7	<20	<4	<2	205	<0.4	<5	<5	263	
927845	Drill Core		2.46	151	5	428	7	13	0.6	13	4	340	1.60	10	<20	<4	<2	100	<0.4	<5	<5	157	
927846	Drill Core		3.99	367	5	993	<5	24	0.9	22	6	403	3.19	8	<20	<4	<2	110	<0.4	<5	<5	299	
927847	Drill Core		3.67	133	20	458	8	18	<0.5	9	15	487	4.07	6	<20	<4	5	508	<0.4	<5	<5	172	
927848	Drill Core		5.37	100	37	400	11	12	<0.5	18	13	452	4.87	9	<20	<4	4	444	<0.4	<5	<5	185	
927849	Drill Core		5.55	58	29	837	<5	12	<0.5	54	13	491	4.05	6	<20	<4	<2	321	<0.4	<5	<5	215	
927850	Drill Core		1.05	<2	<2	<2	<5	4	<0.5	<2	<2	22	0.04	<5	<20	<4	<2	4066	<0.4	<5	<5	<2	
927851	Rock Pulp		0.14	328	<2	3219	30	66	1.0	16	6	335	3.49	<5	<20	<4	12	164	<0.4	<5	<5	43	
927852	Drill Core		4.94	61	27	869	7	10	<0.5	57	16	472	5.23	7	<20	<4	<2	243	<0.4	<5	<5	216	
927853	Drill Core		4.94	68	21	1097	10	16	<0.5	54	27	519	7.16	6	<20	<4	<2	300	<0.4	<5	<5	205	
927854	Drill Core		5.25	92	46	1295	<5	21	0.9	49	56	694	14.66	<5	23	<4	4	109	0.8	5	14	211	
927855	Drill Core		2.68	140	23	836	14	18	0.7	45	24	600	7.38	<5	<20	<4	2	268	0.6	<5	<5	197	
927856	Drill Core		5.19	74	65	859	19	12	0.8	55	19	505	5.79	15	<20	<4	<2	257	<0.4	7	6	196	
927857	Drill Core		4.53	167	51	1091	16	14	1.3	61	20	794	7.65	23	<20	<4	<2	180	0.7	6	14	186	
927858	Drill Core		2.58	99	28	520	28	12	1.4	34	13	428	10.38	18	<20	<4	4	213	0.5	15	17	185	
927859	Drill Core		5.46	116	119	502	15	8	<0.5	2	11	393	3.43	<5	<20	<4	9	405	<0.4	6	7	182	
927860	Drill Core		1.07	<2	<2	<2	9	<2	<0.5	<2	<2	22	0.03	<5	<20	<4	<2	4010	<0.4	<5	<5	<2	
927861	Drill Core		5.62	218	18	657	12	14	0.6	3	11	441	3.70	<5	24	<4	9	469	<0.4	<5	9	191	
927862	Drill Core		4.42	211	2	537	22	13	0.7	<2	9	498	3.19	<5	<20	<4	9	535	<0.4	<5	11	167	
927863	Drill Core		6.01	173	10	110	14	11	<0.5	5	23	318	11.79	98	<20	<4	6	293	0.5	6	18	175	
927864	Drill Core		2.79	567	11	207	135	161	4.9	29	19	621	7.17	25	<20	<4	3	198	1.4	5	16	235	
927865	Drill Core		5.17	212	20	631	23	20	<0.5	41	18	866	5.40	<5	<20	<4	2	217	0.4	<5	9	260	
927866	Drill Core		2.67	484	20	701	13	16	3.7	52	29	918	5.79	<5	<20	<4	9	2	285	<0.4	7	5	210
927867	Drill Core		3.16	68	10	1336	13	28	1.5	49	55	1089	10.31	18	<20	<4	<2	377	0.9	<5	11	165	
927868	Drill Core		4.88	295	37	1227	10	20	1.4	48	34	1093	6.79	<5	<20	<4	<2	461	0.4	<5	9	207	
927869	Drill Core		2.39	154	35	556	8	18	<0.5	35	27	791	5.48	<5	<20	<4	3	676	<0.4	<5	8	190	
927870	Drill Core		1.26	<2	<2	4	<5	<2	<0.5	<2	<2	23	0.05	<5	<20	<4	<2	3809	<0.4	<5	<5	<2	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 5 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927841	Drill Core	2.86	0.131	11	59	1.33	709	0.40	7.74	3.38	2.14	<4	33	<2	14	4	<1	16	0.6
927842	Drill Core	2.87	0.122	11	36	1.15	401	0.29	7.30	3.61	1.90	4	30	<2	14	4	<1	12	0.9
927843	Drill Core	3.53	0.108	13	34	1.60	666	0.48	8.12	3.34	2.15	<4	33	<2	17	4	<1	18	0.7
927844	Drill Core	3.39	0.088	14	41	1.09	535	0.37	5.75	1.88	1.97	<4	31	<2	14	4	<1	14	0.5
927845	Drill Core	2.30	0.047	7	36	0.47	531	0.19	3.42	0.95	1.82	<4	22	<2	11	2	<1	7	0.7
927846	Drill Core	1.25	0.085	10	45	1.02	310	0.28	5.25	1.43	2.58	<4	30	<2	11	4	<1	10	0.7
927847	Drill Core	3.27	0.114	17	16	1.24	133	0.35	8.97	3.74	3.04	6	74	<2	15	6	2	9	2.6
927848	Drill Core	4.49	0.115	13	16	0.84	86	0.34	7.10	3.76	2.93	<4	80	<2	14	6	1	8	4.6
927849	Drill Core	5.60	0.127	11	49	0.62	119	0.36	6.69	2.74	3.39	4	42	<2	18	3	<1	14	3.5
927850	Drill Core	39.56	0.003	<2	<2	1.73	9	<0.01	0.05	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
927851	Rock Pulp	1.23	0.043	27	17	0.51	786	0.15	6.98	2.35	3.50	<4	53	7	14	10	2	7	0.3
927852	Drill Core	5.51	0.132	12	43	0.57	167	0.34	6.64	2.12	4.13	5	47	<2	21	3	<1	13	5.0
927853	Drill Core	5.02	0.120	12	42	0.96	141	0.36	7.13	2.94	3.05	<4	44	<2	19	3	<1	14	5.5
927854	Drill Core	4.53	0.088	18	26	1.40	174	0.19	3.68	0.16	1.16	4	54	4	19	5	<1	9	7.2
927855	Drill Core	4.69	0.111	11	37	0.91	661	0.31	6.66	2.16	3.46	7	56	<2	25	4	<1	14	5.5
927856	Drill Core	5.65	0.123	10	38	0.56	1259	0.34	6.59	1.99	4.48	7	58	<2	23	4	<1	14	5.5
927857	Drill Core	5.38	0.124	10	31	0.79	526	0.31	5.92	1.41	4.14	5	46	2	25	4	<1	12	7.0
927858	Drill Core	4.53	0.116	7	21	0.63	92	0.29	6.66	1.99	3.89	10	51	2	16	4	1	12	11.5
927859	Drill Core	3.82	0.104	15	11	0.63	64	0.32	8.14	4.21	3.29	13	94	2	15	8	2	7	3.0
927860	Drill Core	35.97	0.005	<2	<2	1.85	10	<0.01	0.08	<0.01	<0.01	5	<2	2	<2	<1	<1	<0.1	
927861	Drill Core	3.16	0.126	22	8	0.96	82	0.34	8.80	4.03	3.62	7	99	<2	19	8	2	8	2.4
927862	Drill Core	3.79	0.117	24	3	0.90	105	0.32	8.61	3.99	3.17	6	106	3	20	7	2	7	1.8
927863	Drill Core	3.80	0.118	12	4	0.47	51	0.32	7.48	2.22	2.96	9	86	6	19	7	2	12	13.6
927864	Drill Core	4.44	0.154	10	32	1.53	164	0.34	6.80	1.04	4.55	5	66	5	20	5	1	14	7.0
927865	Drill Core	5.83	0.178	13	52	1.50	278	0.35	6.22	1.27	4.43	5	51	3	25	4	<1	15	3.5
927866	Drill Core	6.73	0.128	15	47	1.77	229	0.39	7.01	2.61	2.65	<4	44	2	23	4	<1	16	3.1
927867	Drill Core	4.36	0.093	20	39	2.63	430	0.33	7.90	3.24	0.88	4	27	<2	17	3	<1	14	7.4
927868	Drill Core	6.06	0.126	19	46	2.43	273	0.43	8.24	3.87	0.79	<4	38	<2	20	4	<1	16	3.4
927869	Drill Core	6.13	0.114	15	46	2.21	328	0.43	9.02	3.42	1.41	<4	29	2	18	3	1	16	1.0
927870	Drill Core	38.06	0.004	<2	<2	1.60	16	<0.01	0.16	0.01	<0.01	4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page: 6 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000209.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	
927871	Drill Core		5.14	468	62	1273	6	22	0.7	38	32	711	5.91	<5	<20	<4	<2	663	<0.4	<5	7	171
927872	Drill Core		4.74	574	53	1987	11	13	1.2	62	32	682	5.00	<5	<20	<4	2	431	<0.4	<5	6	226
927873	Drill Core		2.61	442	102	1347	7	13	0.7	50	21	695	4.30	<5	<20	<4	<2	377	<0.4	<5	6	219
927874	Drill Core		5.18	428	59	1327	17	10	0.6	56	18	808	4.15	<5	<20	<4	3	293	<0.4	<5	10	252
927875	Drill Core		4.63	245	25	499	5	14	<0.5	45	9	1093	3.68	<5	<20	<4	2	270	<0.4	<5	7	237
927876	Drill Core		2.49	139	19	428	10	93	<0.5	33	13	1158	3.81	<5	<20	<4	3	310	0.7	<5	9	216
927877	Drill Core		5.73	160	9	1392	26	213	3.7	7	17	505	5.21	9	<20	<4	7	504	1.5	<5	12	194
927878	Drill Core		4.42	119	16	376	9	73	1.0	4	17	595	4.27	5	<20	<4	8	815	0.6	<5	9	210
927879	Drill Core		5.40	255	7	166	9	82	<0.5	4	11	562	3.91	5	<20	<4	9	786	0.7	<5	<5	205
927880	Drill Core		1.22	<2	<2	<2	9	<2	<0.5	<2	<2	26	0.04	<5	<20	<4	<2	3936	<0.4	<5	<5	<2
927881	Rock Pulp		0.14	634	4	5145	17	62	1.4	16	14	434	5.19	<5	<20	<4	<2	453	<0.4	<5	9	122
927882	Drill Core		5.26	108	10	140	8	106	<0.5	3	12	706	3.74	<5	<20	<4	8	729	0.8	<5	<5	208
927883	Drill Core		5.00	152	21	243	13	54	<0.5	4	14	708	3.78	<5	<20	<4	7	652	0.5	<5	<5	206
927884	Drill Core		2.81	164	22	329	12	18	0.5	3	23	573	4.22	<5	<20	<4	9	697	<0.4	<5	8	202
927885	Drill Core		4.65	77	30	20	14	24	<0.5	31	11	784	4.00	<5	<20	<4	6	396	<0.4	<5	10	231
927886	Drill Core		4.92	65	186	189	9	42	<0.5	28	13	640	3.79	<5	<20	<4	5	421	<0.4	<5	<5	212
927887	Drill Core		5.10	254	145	446	<5	44	1.2	41	25	859	4.84	<5	<20	<4	<2	393	<0.4	6	<5	231
927888	Drill Core		5.00	151	291	1027	21	92	3.0	57	34	872	4.86	6	<20	<4	<2	301	0.8	6	7	236
927889	Drill Core		5.55	66	267	422	7	104	1.4	41	28	893	4.87	33	<20	<4	<2	447	1.3	<5	12	229
927890	Drill Core		1.32	<2	<2	<2	6	<2	<0.5	<2	<2	25	0.04	<5	<20	<4	9	4207	<0.4	<5	<5	<2
927891	Drill Core		4.63	105	103	586	10	225	1.5	39	25	1084	5.11	37	<20	<4	<2	558	2.2	<5	6	202
927892	Drill Core		2.19	59	8	221	15	101	0.5	10	9	948	4.48	15	<20	<4	7	532	0.9	<5	5	223
927893	Drill Core		5.29	50	7	275	28	175	0.6	5	14	676	4.14	14	<20	<4	8	581	1.5	<5	<5	196
927894	Drill Core		5.01	150	43	305	11	87	0.9	4	15	524	4.57	34	<20	<4	8	546	0.8	<5	<5	169
927895	Drill Core		4.93	60	27	246	10	171	<0.5	4	16	639	4.77	25	<20	<4	10	675	1.4	<5	5	186
927896	Drill Core		4.63	47	10	244	8	70	<0.5	5	17	573	3.80	13	<20	<4	7	572	0.5	<5	<5	206
927897	Drill Core		5.10	74	87	53	10	177	<0.5	30	40	741	6.24	11	<20	<4	2	613	1.9	<5	9	233
927898	Drill Core		4.80	79	43	225	12	77	0.7	28	22	810	4.68	16	<20	<4	<2	445	0.9	<5	6	191
927899	Drill Core		3.62	58	11	212	7	42	<0.5	67	22	1312	5.29	9	<20	<4	<2	424	0.6	<5	5	195
927900	Drill Core		1.36	<2	<2	<2	<5	<2	<0.5	<2	<2	23	0.07	<5	<20	<4	7	4097	<0.4	<5	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page: 6 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927871	Drill Core	5.37	0.109	16	60	2.39	339	0.36	8.90	3.35	1.37	<4	27	<2	16	4	1	15	1.4
927872	Drill Core	4.63	0.137	16	60	2.01	295	0.42	8.30	4.11	1.57	<4	47	2	23	4	1	18	1.0
927873	Drill Core	4.55	0.141	18	61	1.80	403	0.44	8.59	3.58	2.93	5	50	3	23	4	<1	17	1.2
927874	Drill Core	6.02	0.137	15	50	1.53	277	0.39	7.24	2.60	3.67	4	51	<2	24	4	<1	17	2.2
927875	Drill Core	6.90	0.115	19	50	1.56	215	0.38	6.88	2.86	2.72	<4	52	2	23	4	<1	17	1.7
927876	Drill Core	7.43	0.112	19	46	1.67	171	0.37	6.82	2.12	3.90	<4	52	<2	22	4	<1	16	2.3
927877	Drill Core	3.99	0.125	22	5	1.02	66	0.36	8.20	3.39	3.32	7	119	5	22	8	2	10	5.0
927878	Drill Core	4.12	0.144	29	7	1.32	88	0.41	8.98	3.62	2.99	<4	127	<2	25	8	2	12	2.8
927879	Drill Core	3.95	0.142	29	4	1.39	102	0.42	8.89	3.85	3.06	<4	127	<2	24	8	2	12	1.9
927880	Drill Core	37.40	0.005	<2	<2	1.58	17	<0.01	0.09	0.01	<0.01	5	<2	2	<2	<2	<1	<1	<0.1
927881	Rock Pulp	1.74	0.099	13	25	1.33	696	0.28	7.72	2.97	3.36	<4	75	6	13	7	2	12	0.6
927882	Drill Core	4.92	0.137	25	4	1.20	93	0.41	8.64	3.56	3.52	<4	125	<2	23	8	2	11	2.3
927883	Drill Core	4.95	0.133	24	5	1.16	108	0.40	8.46	3.31	3.68	<4	127	<2	24	9	2	11	2.3
927884	Drill Core	3.23	0.135	20	4	1.39	109	0.40	8.84	3.58	3.64	4	121	<2	23	8	2	11	1.6
927885	Drill Core	5.11	0.129	17	40	1.51	208	0.40	7.65	2.81	3.77	<4	74	<2	23	5	1	15	2.2
927886	Drill Core	4.61	0.121	28	30	1.50	506	0.38	7.75	2.99	3.62	6	79	2	23	6	1	13	2.0
927887	Drill Core	5.20	0.130	15	44	2.03	159	0.39	7.44	3.33	2.22	4	50	<2	22	5	1	16	2.4
927888	Drill Core	4.68	0.129	13	55	2.12	148	0.36	6.75	3.24	1.94	<4	51	3	21	5	1	15	2.2
927889	Drill Core	5.32	0.126	15	52	2.09	263	0.40	7.71	2.87	2.66	<4	42	<2	23	4	2	17	2.5
927890	Drill Core	>40	0.003	<2	<2	1.69	7	<0.01	0.03	0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
927891	Drill Core	5.73	0.138	20	44	2.47	296	0.42	7.94	3.61	0.66	4	40	<2	20	3	2	16	3.3
927892	Drill Core	3.16	0.153	52	14	2.76	132	0.42	8.97	4.00	1.74	6	88	2	21	7	3	14	2.7
927893	Drill Core	4.15	0.140	22	10	1.45	138	0.38	8.94	3.92	2.72	<4	78	<2	21	6	2	14	2.6
927894	Drill Core	2.84	0.132	22	3	1.16	92	0.35	9.18	4.21	1.99	<4	83	<2	21	6	3	11	4.2
927895	Drill Core	3.94	0.130	37	6	1.54	84	0.36	9.61	4.33	1.99	<4	90	<2	24	6	3	13	3.8
927896	Drill Core	3.70	0.141	25	10	1.35	145	0.39	9.02	3.78	3.16	<4	87	<2	20	7	2	14	2.6
927897	Drill Core	5.26	0.114	20	38	1.67	82	0.42	8.59	3.89	1.20	<4	41	<2	21	3	3	20	5.4
927898	Drill Core	5.40	0.106	14	38	1.40	372	0.35	7.81	3.51	1.50	<4	40	2	18	3	2	15	3.7
927899	Drill Core	5.99	0.123	17	65	2.61	798	0.42	8.50	2.81	1.41	<4	43	<2	20	3	2	17	1.9
927900	Drill Core	37.79	0.004	<2	<2	1.71	7	<0.01	0.12	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 12, 2009

Page:

7 of 8

Part 1

CERTIFICATE OF ANALYSIS

SMI09000209.1

Method	Analyte	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927901	Drill Core		3.80	3	<2	42	9	82	<0.5	111	33	1496	6.33	<5	<20	<4	<2	391	0.7	<5	<5	225
927902	Drill Core		4.15	2	<2	50	8	74	<0.5	85	30	1827	5.97	<5	<20	<4	<2	353	0.7	<5	<5	228
927903	Drill Core		4.97	8	4	168	5	62	<0.5	79	27	1059	5.57	<5	<20	<4	2	484	0.6	<5	<5	211
927904	Drill Core		2.73	36	103	517	12	44	0.9	40	18	621	4.17	15	<20	<4	3	585	0.7	<5	<5	194
927905	Drill Core		5.19	31	38	342	8	32	<0.5	58	8	874	4.19	15	<20	<4	<2	493	0.5	<5	8	236
927906	Drill Core		4.94	49	23	168	11	30	<0.5	51	11	792	5.75	30	<20	<4	<2	474	0.5	<5	9	236
927907	Drill Core		2.33	56	193	1060	13	65	1.2	22	12	1051	4.42	17	<20	<4	<2	576	0.7	<5	7	183
927908	Drill Core		3.14	27	29	424	5	41	<0.5	9	6	701	2.96	8	<20	<4	9	778	0.5	<5	<5	187
927909	Drill Core		4.62	46	60	99	6	58	<0.5	7	4	755	2.48	21	<20	<4	10	744	0.5	<5	<5	189
927910	Drill Core		0.83	3	<2	<2	<5	7	<0.5	<2	<2	195	0.37	<5	<20	<4	4	51	<0.4	<5	<5	3
927911	Rock Chip		0.15	297	<2	3266	27	65	1.0	16	6	341	3.47	<5	<20	<4	12	165	<0.4	<5	<5	41
927912	Drill Core		5.07	18	44	256	<5	96	<0.5	4	5	635	2.29	8	<20	<4	11	799	0.7	<5	<5	189
927913	Drill Core		4.51	18	14	186	7	23	<0.5	3	10	602	2.90	11	<20	<4	10	709	<0.4	<5	<5	193
927914	Drill Core		5.09	49	12	197	<5	31	<0.5	7	4	637	2.51	10	<20	<4	11	800	<0.4	<5	<5	200
927915	Drill Core		4.31	16	6	118	<5	24	<0.5	8	3	719	2.69	6	<20	<4	11	794	<0.4	<5	<5	197
927916	Drill Core		2.69	53	46	143	14	30	<0.5	39	13	681	4.04	15	<20	<4	4	376	<0.4	<5	<5	175
927917	Drill Core		2.82	67	24	382	87	164	1.3	8	19	381	5.55	23	<20	<4	9	635	1.4	<5	5	141
927918	Drill Core		4.45	28	10	320	9	25	<0.5	3	21	435	3.48	11	<20	<4	9	718	<0.4	<5	<5	145
927919	Drill Core		3.14	10	52	57	<5	23	<0.5	48	10	654	3.04	<5	<20	<4	<2	352	<0.4	<5	<5	244
927920	Drill Core		0.71	<2	<2	2	<5	8	<0.5	3	<2	201	0.44	<5	<20	<4	2	47	<0.4	<5	<5	3
927921	Drill Core		4.13	<2	<2	43	6	66	<0.5	17	20	1113	4.93	<5	<20	<4	<2	791	0.6	<5	<5	187
927922	Drill Core		3.82	30	2	422	<5	45	0.5	40	18	791	4.64	11	<20	<4	<2	444	0.6	<5	6	215
927923	Drill Core		5.25	39	2	101	8	27	<0.5	50	15	758	3.54	5	<20	<4	<2	393	<0.4	<5	6	237
927924	Drill Core		4.53	<2	<2	53	<5	81	<0.5	86	29	1216	5.90	<5	<20	<4	<2	744	<0.4	<5	<5	222
927925	Drill Core		3.03	26	<2	117	<5	43	<0.5	40	14	774	3.90	13	<20	<4	<2	419	<0.4	<5	<5	202
927926	Drill Core		4.88	32	4	113	<5	42	<0.5	43	15	1090	3.96	9	<20	<4	<2	334	<0.4	<5	<5	183
927927	Drill Core		5.16	14	<2	127	<5	39	<0.5	36	18	885	4.72	16	<20	<4	<2	516	<0.4	<5	<5	184
927928	Drill Core		3.03	54	<2	406	9	45	0.9	47	23	892	5.46	11	<20	<4	<2	434	<0.4	<5	<5	165
927929	Drill Core		4.11	6	<2	33	<5	67	<0.5	23	19	1180	4.78	<5	<20	<4	<2	435	<0.4	<5	<5	174
927930	Drill Core		0.85	<2	<2	3	<5	13	<0.5	<2	<2	179	0.41	<5	<20	<4	<2	46	<0.4	<5	<5	4

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 7 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927901	Drill Core	5.38	0.198	16	125	3.92	1303	0.66	8.17	1.50	1.44	<4	78	<2	20	9	2	24	0.4
927902	Drill Core	6.75	0.202	18	86	3.60	886	0.65	8.19	1.61	1.53	<4	76	<2	21	9	2	25	0.3
927903	Drill Core	5.76	0.184	20	93	3.19	1001	0.55	8.13	2.48	1.23	4	83	<2	20	8	2	20	0.7
927904	Drill Core	3.90	0.113	14	61	1.74	140	0.39	8.38	4.59	0.66	<4	55	2	19	4	3	14	2.9
927905	Drill Core	5.24	0.126	15	67	2.25	291	0.42	7.74	4.19	0.32	<4	50	6	21	4	2	16	2.3
927906	Drill Core	4.44	0.119	16	39	2.11	89	0.42	8.35	3.72	0.89	5	35	<2	19	3	3	16	4.7
927907	Drill Core	5.96	0.113	18	24	2.08	560	0.44	9.50	3.01	1.65	<4	33	<2	20	3	3	15	2.3
927908	Drill Core	4.50	0.131	32	<2	1.23	486	0.39	9.37	4.84	0.98	<4	104	2	21	9	3	8	1.7
927909	Drill Core	5.53	0.130	40	2	1.26	479	0.39	9.29	4.74	1.00	<4	107	<2	21	8	3	9	1.2
927910	Drill Core	23.28	0.027	2	<2	13.00	17	<0.01	0.13	0.02	0.05	<4	<2	<2	<2	<2	<1	<1	<0.1
927911	Rock Chip	1.24	0.042	25	16	0.51	774	0.16	6.95	2.35	3.08	6	48	9	14	10	3	6	0.4
927912	Drill Core	4.85	0.140	58	<2	1.34	573	0.42	9.67	4.92	1.00	<4	107	<2	21	10	3	9	0.8
927913	Drill Core	4.91	0.139	43	<2	1.30	882	0.42	9.43	5.08	1.10	<4	110	<2	20	9	3	8	1.5
927914	Drill Core	4.49	0.137	37	2	1.20	549	0.42	9.47	5.43	0.81	<4	113	<2	19	9	3	9	1.3
927915	Drill Core	5.10	0.141	46	4	1.27	492	0.42	9.53	5.49	0.82	<4	108	<2	21	9	3	9	1.3
927916	Drill Core	4.36	0.120	18	37	1.45	103	0.42	8.49	4.05	1.25	4	67	<2	22	6	2	13	2.7
927917	Drill Core	2.41	0.099	29	<2	0.99	49	0.30	9.10	4.66	1.39	5	103	<2	22	7	3	6	5.9
927918	Drill Core	3.34	0.106	46	<2	0.97	84	0.31	9.18	5.03	1.39	<4	102	<2	24	8	3	5	2.6
927919	Drill Core	4.63	0.131	16	54	1.96	492	0.41	7.58	4.55	0.31	<4	62	<2	26	4	2	16	0.8
927920	Drill Core	22.56	0.032	2	<2	13.05	16	<0.01	0.12	0.02	0.04	<4	<2	<2	<2	<2	<1	<1	<0.1
927921	Drill Core	4.52	0.159	17	40	2.59	983	0.60	9.30	3.96	0.76	<4	78	<2	19	9	2	21	0.2
927922	Drill Core	4.00	0.131	20	48	1.87	283	0.43	7.83	4.67	0.15	<4	68	<2	21	5	2	17	2.6
927923	Drill Core	4.36	0.133	20	56	1.96	383	0.42	7.69	4.58	0.42	<4	58	<2	25	5	2	17	1.5
927924	Drill Core	6.01	0.239	18	113	4.02	1885	0.67	8.09	2.29	1.12	<4	95	<2	19	10	1	25	0.2
927925	Drill Core	4.12	0.120	14	50	1.70	342	0.36	7.22	4.33	0.30	<4	61	<2	19	3	<1	16	2.5
927926	Drill Core	5.77	0.118	16	49	1.82	678	0.35	6.91	3.72	0.81	<4	53	<2	21	3	<1	16	1.9
927927	Drill Core	4.36	0.110	10	64	2.22	113	0.38	8.41	3.87	1.27	<4	29	<2	16	2	<1	16	2.1
927928	Drill Core	4.27	0.112	12	48	2.23	229	0.33	7.73	4.35	0.26	<4	47	<2	17	2	<1	14	3.4
927929	Drill Core	4.06	0.147	12	41	2.53	1643	0.54	8.89	3.62	1.82	<4	70	<2	15	8	1	17	0.1
927930	Drill Core	21.15	0.025	2	<2	11.93	23	<0.01	0.21	0.02	0.04	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 8 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000209.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927931	Drill Core	3.84	<2	<2	31	<5	68	<0.5	23	19	1145	4.69	<5	<20	<4	<2	479	<0.4	<5	<5	166
927932	Drill Core	4.38	32	8	533	<5	26	<0.5	39	16	921	3.94	9	<20	<4	2	310	<0.4	<5	<5	185
927933	Drill Core	5.21	66	8	561	<5	20	<0.5	29	19	527	4.81	18	<20	<4	7	421	<0.4	6	<5	192
927934	Drill Core	2.02	51	25	857	<5	18	<0.5	38	17	547	4.35	<5	<20	<4	<2	349	<0.4	<5	<5	187
927935	Drill Core	5.15	8	<2	50	<5	66	<0.5	23	19	1034	4.49	<5	<20	<4	<2	689	<0.4	<5	<5	164
927936	Drill Core	5.37	7	<2	53	<5	82	<0.5	79	29	1164	5.91	<5	<20	<4	<2	444	<0.4	<5	<5	222
927937	Drill Core	5.21	120	4	674	<5	25	<0.5	44	18	555	4.61	<5	<20	<4	<2	312	<0.4	<5	<5	219
927938	Drill Core	5.02	155	7	882	<5	19	<0.5	33	11	448	3.35	6	<20	<4	4	426	<0.4	<5	<5	218
927939	Drill Core	5.07	300	9	1925	<5	19	<0.5	31	15	482	4.33	<5	<20	<4	<2	357	<0.4	<5	<5	208
927940	Drill Core	0.84	<2	<2	6	<5	16	<0.5	3	<2	169	0.38	<5	<20	<4	<2	44	<0.4	<5	<5	3
927941	Rock Pulp	0.11	305	<2	3260	19	65	0.8	16	7	318	3.35	<5	<20	<4	10	146	<0.4	<5	<5	42
927942	Drill Core	5.23	262	10	1831	<5	27	<0.5	36	15	456	4.55	<5	<20	<4	<2	343	<0.4	<5	<5	227
927943	Drill Core	5.06	126	13	1118	<5	28	0.7	24	16	503	4.34	<5	<20	<4	5	341	<0.4	<5	<5	217
927944	Drill Core	3.78	68	13	691	<5	16	<0.5	20	18	377	2.84	<5	<20	<4	3	372	<0.4	<5	<5	174
927945	Drill Core	5.20	93	11	612	<5	18	<0.5	18	14	586	2.85	<5	<20	<4	<2	424	<0.4	<5	<5	175
927946	Drill Core	3.22	74	15	556	<5	31	<0.5	18	12	612	2.95	<5	<20	<4	<2	587	<0.4	<5	<5	183
927947	Drill Core	3.88	112	9	529	<5	15	<0.5	2	9	344	2.27	<5	<20	<4	10	745	<0.4	<5	<5	141
927948	Drill Core	2.90	83	6	1035	<5	36	<0.5	12	22	567	3.84	<5	<20	<4	8	558	<0.4	<5	<5	299
927949	Drill Core	5.11	75	6	878	<5	32	1.0	8	18	783	4.03	10	<20	<4	9	593	<0.4	<5	<5	323
927950	Drill Core	1.19	<2	<2	4	<5	<2	<0.5	<2	<2	24	0.05	<5	<20	<4	<2	3966	<0.4	<5	<5	<2



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 8 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927931	Drill Core	3.48	0.143	11	43	2.43	1835	0.52	8.29	3.37	2.05	<4	68	2	14	8	1	16 <0.1	
927932	Drill Core	5.41	0.128	14	37	1.26	916	0.39	7.38	3.48	1.75	7	68	<2	20	5	<1	15 2.0	
927933	Drill Core	4.33	0.143	20	18	1.08	67	0.37	8.05	4.38	1.66	4	68	2	21	6	1	14 3.5	
927934	Drill Core	4.73	0.119	8	37	1.21	313	0.39	7.53	4.98	0.48	7	31	3	17	4	<1	14 2.5	
927935	Drill Core	4.01	0.141	12	42	2.29	1628	0.52	8.38	3.74	1.77	<4	72	<2	14	8	<1	16 0.2	
927936	Drill Core	6.10	0.227	20	101	3.69	1551	0.68	8.18	2.09	1.55	<4	102	<2	19	10	1	25 0.4	
927937	Drill Core	4.53	0.138	10	54	1.39	187	0.41	7.46	3.49	2.07	14	37	3	20	4	<1	17 2.6	
927938	Drill Core	3.87	0.146	14	40	0.99	152	0.38	7.67	3.80	2.79	31	54	2	20	5	1	14 1.9	
927939	Drill Core	3.93	0.116	9	36	1.48	146	0.36	7.42	3.22	2.70	13	31	5	17	4	<1	14 1.9	
927940	Drill Core	20.21	0.021	2	2	11.70	31	<0.01	0.33	0.02	0.08	<4	<2	<2	<2	<1	<1	<0.1	
927941	Rock Pulp	1.08	0.041	21	17	0.48	720	0.15	5.83	2.27	2.83	<4	55	10	12	9	2	6 0.3	
927942	Drill Core	3.85	0.120	9	48	1.52	188	0.35	7.14	2.81	2.99	5	29	4	18	4	<1	15 1.8	
927943	Drill Core	3.14	0.145	13	26	1.20	115	0.38	7.94	3.56	3.01	5	56	4	19	5	1	13 2.4	
927944	Drill Core	2.50	0.129	10	24	0.78	175	0.37	7.81	3.69	3.05	7	42	3	16	4	<1	12 1.7	
927945	Drill Core	4.48	0.111	9	27	1.12	490	0.39	7.89	4.45	1.54	20	32	2	17	5	1	15 1.3	
927946	Drill Core	4.48	0.124	10	31	1.42	1089	0.42	8.16	4.50	1.75	<4	38	3	20	5	1	14 0.8	
927947	Drill Core	2.84	0.093	21	<2	0.61	326	0.28	8.31	3.48	3.15	<4	73	4	18	7	2	5 1.3	
927948	Drill Core	4.24	0.212	26	11	0.82	160	0.47	7.60	4.67	1.43	5	93	3	22	8	1	14 1.9	
927949	Drill Core	5.11	0.236	30	4	1.14	181	0.50	8.00	3.91	1.87	<4	95	4	26	9	2	16 1.7	
927950	Drill Core	38.38	0.004	<2	<2	1.77	5	<0.01	0.07	0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunc

Report Date

October 12, 2009

www.acmelab.com

Page:

1 of 4 Part

QUALITY CONTROL REPORT

SMI09000209.1

	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	V		
	MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
Pulp Duplicates																					
927766	Drill Core	4.71	321	7	638	8	19	0.8	3	17	727	4.30	56	<20	<4	8	611	0.6	<5	<5	221
REP 927766	QC		310																		
927783	Drill Core	1.89	88	34	348	7	24	<0.5	6	4	1085	6.88	8	<20	<4	8	183	<0.4	<5	7	291
REP 927783	QC		35	330	10	23	<0.5	5	4	1029	6.48	<5	<20	<4	7	173	<0.4	<5	7	272	
927828	Drill Core	4.54	16	<2	34	11	34	<0.5	2	8	720	3.85	12	<20	<4	8	313	<0.4	<5	<5	225
REP 927828	QC		28																		
927833	Drill Core	5.31	9	<2	43	6	68	<0.5	43	22	1000	5.43	10	<20	<4	<2	194	<0.4	<5	<5	218
REP 927833	QC		10																		
927844	Drill Core	4.90	185	7	569	8	20	0.9	19	6	639	2.55	7	<20	<4	<2	205	<0.4	<5	<5	263
REP 927844	QC		6	572	6	19	1.2	18	6	636	2.50	<5	<20	<4	<2	204	<0.4	<5	<5	262	
927871	Drill Core	5.14	468	62	1273	6	22	0.7	38	32	711	5.91	<5	<20	<4	<2	663	<0.4	<5	7	171
REP 927871	QC		62	1282	14	22	0.8	40	33	740	6.02	<5	<20	<4	<2	678	0.5	<5	13	176	
927877	Drill Core	5.73	160	9	1392	26	213	3.7	7	17	505	5.21	9	<20	<4	7	504	1.5	<5	12	194
REP 927877	QC		159																		
927913	Drill Core	4.51	18	14	186	7	23	<0.5	3	10	602	2.90	11	<20	<4	10	709	<0.4	<5	<5	193
REP 927913	QC		15	185	<5	25	<0.5	4	10	581	2.81	10	<20	<4	10	710	<0.4	<5	<5	186	
927926	Drill Core	4.88	32	4	113	<5	42	<0.5	43	15	1090	3.96	9	<20	<4	<2	334	<0.4	<5	<5	183
REP 927926	QC		32																		
927940	Drill Core	0.84	<2	<2	6	<5	16	<0.5	3	<2	169	0.38	<5	<20	<4	<2	44	<0.4	<5	<5	3
REP 927940	QC		<2	5	<5	13	<0.5	3	<2	161	0.37	<5	<20	<4	<2	42	<0.4	<5	<5	4	
Core Reject Duplicates																					
927767	Drill Core	4.66	87	3	456	10	19	0.6	2	23	715	3.96	<5	<20	<4	10	650	<0.4	<5	6	227
DUP 927767	QC		87	4	479	<5	18	<0.5	3	23	744	4.00	10	<20	<4	3	644	<0.4	<5	<5	242
927802	Drill Core	4.95	158	7	1227	<5	24	1.5	4	16	567	4.95	7	<20	<4	6	431	<0.4	<5	<5	242
DUP 927802	QC		155	6	1197	5	23	1.8	3	16	570	4.85	6	<20	<4	6	428	<0.4	<5	<5	242
927837	Drill Core	5.11	65	<2	73	9	32	<0.5	4	7	611	3.40	11	<20	<4	7	224	<0.4	<5	<5	219
DUP 927837	QC		48	<2	67	13	35	<0.5	4	8	639	3.58	13	<20	<4	7	244	<0.4	<5	<5	232
927872	Drill Core	4.74	574	53	1987	11	13	1.2	62	32	682	5.00	<5	<20	<4	2	431	<0.4	<5	6	226

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 12, 2009

Page:

1 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000209.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	1	1	0.1
Pulp Duplicates																		
927766	Drill Core	4.79	0.153	23	4	0.83	65	0.39	7.88	5.11	1.06	<4	34	<2	20	6	2	3.1
REP 927766	QC																	
927783	Drill Core	4.38	0.070	17	7	1.68	98	0.26	7.37	3.28	0.71	6	29	<2	17	4	<1	1.7
REP 927783	QC																	
927828	Drill Core	4.11	0.066	15	9	1.54	98	0.24	6.85	3.11	0.67	<4	27	<2	16	3	<1	1.6
REP 927828	QC																	
927828	Drill Core	2.71	0.129	19	<2	1.10	571	0.32	9.18	2.96	4.07	<4	67	<2	17	7	<1	0.8
REP 927828	QC																	
927833	Drill Core	3.15	0.193	14	59	2.72	1019	0.64	8.70	1.10	2.85	5	54	<2	18	9	2	0.5
REP 927833	QC																	
927844	Drill Core	3.39	0.088	14	41	1.09	535	0.37	5.75	1.88	1.97	<4	31	<2	14	4	<1	14
REP 927844	QC																	0.5
927871	Drill Core	3.39	0.088	14	40	1.09	534	0.37	5.76	1.91	1.94	6	30	<2	14	4	<1	14
REP 927871	QC																	0.4
927871	Drill Core	5.37	0.109	16	60	2.39	339	0.36	8.90	3.35	1.37	<4	27	<2	16	4	1	15
REP 927871	QC																	1.4
927877	Drill Core	5.52	0.110	17	60	2.43	358	0.37	9.13	3.52	1.42	4	28	<2	17	3	1	15
REP 927877	QC																	1.4
927913	Drill Core	3.99	0.125	22	5	1.02	66	0.36	8.20	3.39	3.32	7	119	5	22	8	2	10
REP 927913	QC																	5.0
927926	Drill Core	3.91	0.139	43	<2	1.30	882	0.42	9.43	5.08	1.10	<4	110	<2	20	9	3	8
REP 927913	QC																	1.5
927926	Drill Core	4.75	0.132	45	<2	1.27	688	0.41	9.19	4.98	1.06	5	107	<2	20	9	3	8
REP 927926	QC																	1.5
927940	Drill Core	5.77	0.118	16	49	1.82	678	0.35	6.91	3.72	0.81	<4	53	<2	21	3	<1	16
REP 927940	QC																	1.9
927940	Drill Core	5.52	0.110	17	60	2.43	358	0.37	9.13	3.52	1.42	4	28	<2	17	3	1	15
REP 927940	QC																	1.4
Core Reject Duplicates																		
927767	Drill Core	20.21	0.021	2	2	11.70	31	<0.01	0.33	0.02	0.08	<4	<2	<2	<2	<1	<1	<0.1
DUP 927767	QC																	<0.1
927802	Drill Core	20.74	0.021	2	2	11.35	26	<0.01	0.16	0.01	0.08	<4	<2	<2	<2	<1	<1	<0.1
DUP 927802	QC																	<0.1
927837	Drill Core	5.01	0.160	29	4	0.83	72	0.39	8.83	5.35	0.89	<4	34	<2	24	6	2	13
DUP 927837	QC																	2.9
927872	Drill Core	3.43	0.144	21	5	0.60	166	0.35	8.57	3.68	3.51	5	66	<2	10	7	1	11
DUP 927872	QC																	3.9
927837	Drill Core	3.49	0.146	21	4	0.62	141	0.37	8.65	3.59	3.61	5	68	<2	11	7	2	11
DUP 927837	QC																	3.8
927872	Drill Core	2.09	0.128	19	3	1.19	744	0.33	8.60	2.50	4.19	<4	67	<2	14	7	<1	8
DUP 927872	QC																	0.5
927872	Drill Core	2.07	0.139	18	3	1.23	1252	0.35	8.79	2.69	3.70	<4	73	<2	14	7	<1	8
DUP 927872	QC																	0.6
927872	Drill Core	4.63	0.137	16	60	2.01	295	0.42	8.30	4.11	1.57	<4	47	2	23	4	1	18
DUP 927872	QC																	1.0

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunc

Report Date

October 12, 2009

www.acmelab.com

Page 1

Part

QUALITY CONTROL REPORT

SMI09000209.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 12, 2009

www.acmelab.com

Page:

2 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000209.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 12, 2009

www.acmelab.com

Page:

3 of 4 Part

QUALITY CONTROL REPORT

SMI09000209.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 12, 2009

www.acmelab.com

Page:

3 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000209.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date: October 12, 2009

www.acmelab.com

Page: 4 of 4 Part 1

QUALITY CONTROL REPORT

SMI09000209.1

	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	
BLK	Blank		<2	<2	<5	<2	<0.5	<2	<2	<5	<0.01	<5	<20	<4	<2	<2	<0.4	<5	<5	
BLK	Blank		<2																	
BLK	Blank		<2																	
BLK	Blank		<2	<2	<5	<2	<0.5	<2	<2	<5	<0.01	<5	<20	<4	<2	<2	<0.4	<5	<5	
BLK	Blank		<2	<2	<5	<2	<0.5	<2	<2	<5	<0.01	<5	<20	<4	<2	<2	<0.4	<5	<5	
BLK	Blank		<2																	
BLK	Blank		<2																	
BLK	Blank		<2																	
BLK	Blank		<2																	
BLK	Blank		<2																	
BLK	Blank		<2																	
BLK	Blank		<2																	
Prep Wash																				
G1	Prep Blank		<2	<2	4	24	61	<0.5	4	5	802	2.52	<5	<20	<4	8	725	<0.4	<5	9
G1	Prep Blank		<2	<2	3	22	58	<0.5	4	5	777	2.45	<5	<20	<4	7	717	<0.4	<5	8



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 12, 2009

Page: 4 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000209.1

		1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S
		% 0.01	% 0.002	ppm 2	ppm 2	% 0.01	ppm 1	% 0.01	ppm 0.01	% 0.01	ppm 0.01	ppm 4	ppm 2	ppm 2	ppm 2	ppm 2	ppm 1	ppm 1	% 0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	6	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
Prep Wash																			
G1	Prep Blank	2.61	0.088	22	8	0.74	1010	0.27	7.78	2.67	2.05	<4	8	<2	17	25	3	6	<0.1
G1	Prep Blank	2.57	0.087	22	9	0.70	997	0.25	7.64	2.64	2.31	<4	7	<2	16	24	3	6	<0.1



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 10, 2009
Report Date: October 09, 2009
Page: 1 of 6

CERTIFICATE OF ANALYSIS

SMI09000214.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 150

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200	145	Crush split and pulverize drill core to 200 mesh			VAN
3B	150	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	150	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL


STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC:



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 2 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000214.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	V	
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927951	Drill Core		4.97	88	10	612	7	19	<0.5	18	15	554	4.28	8	<20	<4	4	410	0.5	<5	<5	265
927952	Drill Core		3.91	63	4	464	8	14	<0.5	17	11	467	3.04	<5	<20	<4	6	222	0.4	<5	6	170
927953	Drill Core		2.31	16	<2	88	6	13	<0.5	10	4	273	1.88	<5	<20	<4	6	168	<0.4	<5	<5	138
927954	Drill Core		3.21	17	2	101	10	16	<0.5	10	5	324	2.29	<5	<20	<4	9	176	<0.4	<5	<5	138
927955	Drill Core		4.57	33	<2	178	7	17	<0.5	10	5	354	2.50	<5	<20	<4	7	188	<0.4	<5	<5	165
927956	Drill Core		4.79	37	<2	162	9	14	<0.5	11	6	326	2.57	<5	<20	<4	8	206	<0.4	<5	7	166
927957	Drill Core		4.94	47	<2	141	9	16	<0.5	9	5	320	2.55	<5	<20	<4	7	221	<0.4	<5	<5	136
927958	Drill Core		5.22	105	3	564	9	21	<0.5	12	7	352	2.79	<5	<20	<4	7	268	<0.4	<5	<5	159
927959	Drill Core		1.19	<2	<2	43	<5	69	<0.5	52	25	1010	5.43	<5	<20	<4	<2	432	0.7	<5	6	214
927960	Drill Core		1.30	<2	<2	2	<5	<2	<0.5	<2	<2	26	0.04	<5	<20	<4	<2	3803	<0.4	<5	<5	<2
927961	Drill Core		3.43	26	10	229	6	18	<0.5	9	9	396	2.74	<5	<20	<4	8	364	0.4	<5	<5	148
927962	Drill Core		5.37	48	14	704	7	11	<0.5	3	18	428	4.22	<5	<20	<4	7	755	0.5	<5	<5	186
927963	Drill Core		5.65	73	39	593	7	12	<0.5	2	15	346	4.60	<5	<20	<4	6	746	<0.4	<5	<5	185
927964	Drill Core		5.57	128	61	671	7	8	<0.5	3	16	335	3.76	<5	<20	<4	9	888	<0.4	<5	<5	180
927965	Drill Core		4.81	47	63	302	6	10	<0.5	23	13	510	3.92	6	<20	<4	4	440	<0.4	<5	<5	188
927966	Drill Core		4.43	37	19	493	<5	10	<0.5	18	6	555	3.70	<5	<20	<4	5	594	<0.4	<5	<5	169
927967	Drill Core		3.74	126	13	1256	6	17	0.8	<2	12	224	2.86	<5	<20	<4	10	331	<0.4	<5	<5	182
927968	Drill Core		6.08	136	12	1639	8	17	1.3	3	13	288	2.90	<5	<20	<4	9	298	<0.4	<5	5	186
927969	Drill Core		5.40	141	11	1511	20	24	1.4	3	13	318	3.14	<5	<20	<4	9	347	<0.4	<5	<5	228
927970	Drill Core		0.72	<2	<2	10	<5	10	<0.5	<2	<2	162	0.39	<5	<20	<4	<2	47	<0.4	<5	<5	3
927971	Rock Pulp		0.15	325	<2	3177	26	61	0.8	16	6	319	3.35	<5	<20	<4	10	156	<0.4	<5	<5	41
927972	Drill Core		4.72	53	5	796	6	20	<0.5	<2	10	323	2.92	<5	<20	<4	11	402	<0.4	<5	<5	183
927973	Drill Core		5.23	55	23	825	<5	20	<0.5	2	14	248	3.40	6	<20	<4	7	349	<0.4	<5	<5	228
927974	Drill Core		4.18	63	11	599	6	26	<0.5	<2	12	264	3.55	<5	<20	<4	8	323	<0.4	<5	<5	256
927975	Drill Core		2.59	60	11	686	6	26	<0.5	<2	10	269	3.48	<5	<20	<4	9	344	<0.4	<5	<5	295
927976	Drill Core		5.59	86	11	837	15	37	4.2	<2	9	523	2.98	29	<20	<4	8	336	<0.4	13	<5	169
927977	Drill Core		4.67	76	72	775	14	19	<0.5	<2	11	340	2.98	<5	<20	<4	9	507	0.5	<5	6	148
927978	Drill Core		4.70	67	62	772	8	18	<0.5	<2	10	212	3.00	<5	<20	<4	8	387	<0.4	<5	<5	159
927979	Drill Core		4.75	103	62	894	10	18	<0.5	<2	11	194	2.91	7	<20	<4	9	346	<0.4	<5	<5	171
927980	Drill Core		0.58	<2	<2	3	<5	11	<0.5	<2	<2	153	0.34	<5	<20	<4	<2	42	<0.4	<5	<5	3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 2 of 6 Part 2

SMI09000214.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927951	Drill Core	3.17	0.152	12	26	1.21	133	0.43	7.32	3.79	2.58	<4	46	<2	19	6	1	14	1.8
927952	Drill Core	3.65	0.090	10	19	0.78	452	0.29	7.02	2.48	4.75	<4	42	<2	16	6	<1	9	0.7
927953	Drill Core	1.62	0.059	7	11	0.56	1647	0.23	5.93	1.80	5.10	<4	42	<2	8	4	<1	5	0.2
927954	Drill Core	2.06	0.072	9	12	0.55	670	0.25	6.70	2.40	5.11	<4	52	<2	13	5	<1	6	0.5
927955	Drill Core	2.08	0.078	9	13	0.67	926	0.27	6.31	2.29	5.37	<4	49	<2	11	5	<1	7	0.4
927956	Drill Core	2.64	0.072	8	13	0.52	710	0.24	6.37	2.07	5.55	<4	45	<2	12	5	<1	6	0.5
927957	Drill Core	2.57	0.072	8	11	0.54	656	0.24	6.72	2.29	5.26	<4	44	<2	13	6	<1	6	0.5
927958	Drill Core	1.84	0.084	8	16	0.88	1371	0.28	7.07	2.48	4.60	<4	41	<2	13	6	<1	7	0.3
927959	Drill Core	4.88	0.193	18	66	3.15	993	0.62	8.81	1.97	2.11	<4	56	<2	19	10	2	25	0.3
927960	Drill Core	37.15	0.003	<2	<2	1.91	8	<0.01	0.03	<0.01	0.01	<4	<2	<2	<2	<1	<1	<0.1	
927961	Drill Core	3.54	0.093	19	12	0.93	298	0.30	7.32	2.78	4.20	<4	58	<2	14	6	1	8	0.9
927962	Drill Core	4.53	0.138	27	5	1.30	140	0.40	8.73	3.63	2.33	<4	93	<2	23	7	2	11	3.0
927963	Drill Core	3.51	0.140	17	4	1.12	81	0.41	7.90	4.25	2.31	<4	97	<2	20	7	2	10	3.8
927964	Drill Core	3.85	0.149	30	4	1.22	157	0.40	8.91	4.89	1.48	5	98	<2	22	7	1	11	2.6
927965	Drill Core	5.09	0.134	17	26	0.93	187	0.36	7.66	2.72	3.92	<4	76	<2	22	5	<1	13	3.2
927966	Drill Core	4.66	0.138	17	16	1.06	128	0.34	7.88	3.83	2.35	5	88	2	22	6	1	10	3.1
927967	Drill Core	1.02	0.126	22	2	1.06	239	0.27	8.12	3.18	5.25	7	48	<2	15	5	1	7	1.1
927968	Drill Core	1.42	0.136	21	5	1.06	203	0.27	7.76	2.84	5.35	<4	41	<2	15	6	1	8	1.3
927969	Drill Core	1.94	0.135	17	5	0.99	143	0.33	8.20	2.96	4.73	4	46	<2	12	6	1	11	1.5
927970	Drill Core	21.22	0.025	<2	<2	12.19	29	<0.01	0.13	0.02	0.06	<4	<2	<2	<2	<1	<1	<0.1	
927971	Rock Pulp	1.14	0.042	22	15	0.49	757	0.15	6.16	2.30	3.85	5	56	7	13	9	2	6	0.3
927972	Drill Core	1.92	0.132	23	2	0.96	250	0.33	8.42	3.37	4.60	6	51	<2	12	7	1	8	1.1
927973	Drill Core	1.30	0.156	20	3	1.03	156	0.42	8.31	3.51	4.28	5	55	2	10	6	1	13	1.4
927974	Drill Core	1.25	0.163	21	<2	1.07	315	0.44	7.93	3.66	3.88	<4	63	<2	10	7	1	14	0.8
927975	Drill Core	1.28	0.164	23	<2	0.96	665	0.48	8.90	4.42	2.98	8	66	<2	10	7	1	16	0.7
927976	Drill Core	1.85	0.116	20	<2	0.82	456	0.29	9.03	3.41	3.38	5	57	<2	11	6	2	6	0.9
927977	Drill Core	2.65	0.101	16	<2	0.74	164	0.27	7.82	3.43	3.73	5	57	<2	11	7	1	6	1.2
927978	Drill Core	1.55	0.106	20	<2	0.77	152	0.28	8.71	3.71	4.19	5	58	<2	11	7	1	6	1.4
927979	Drill Core	1.24	0.123	21	<2	0.90	165	0.30	8.24	3.71	4.10	5	57	<2	11	7	1	6	1.3
927980	Drill Core	20.36	0.029	2	<2	11.90	23	<0.01	0.12	0.02	0.06	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 3 of 6 Part 1

SMI09000214.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
927981	Drill Core	4.29	167	29	1657	10	22	<0.5	<2	14	182	2.99	<5	<20	<4	11	306	<0.4	<5	<5	168
927982	Drill Core	4.60	75	29	824	9	30	<0.5	<2	10	256	2.67	<5	<20	<4	11	384	<0.4	<5	<5	166
927983	Drill Core	4.15	104	22	1041	8	17	<0.5	<2	9	176	2.15	<5	<20	<4	10	393	<0.4	<5	<5	151
927984	Drill Core	4.27	93	15	1428	12	222	<0.5	<2	13	211	3.22	<5	<20	<4	12	451	2.1	<5	<5	212
927985	Drill Core	2.00	143	7	1509	13	26	<0.5	2	15	198	3.49	6	<20	<4	12	399	<0.4	<5	<5	195
927986	Drill Core	4.32	88	33	955	10	25	<0.5	2	11	250	2.77	<5	<20	<4	13	452	0.5	<5	<5	183
927987	Drill Core	4.56	105	18	1204	<5	20	<0.5	<2	14	238	2.85	<5	<20	<4	10	493	<0.4	<5	<5	168
927988	Drill Core	4.63	70	23	903	12	26	<0.5	<2	12	299	3.07	<5	<20	<4	13	475	0.5	<5	<5	176
927989	Drill Core	5.64	64	8	873	7	27	<0.5	3	12	472	3.50	12	<20	<4	10	434	0.6	<5	6	195
927990	Drill Core	0.85	<2	<2	3	<5	7	<0.5	<2	<2	69	0.14	<5	<20	<4	<2	2927	<0.4	<5	<5	2
927991	Drill Core	4.55	35	9	424	<5	109	1.0	8	5	612	2.17	18	<20	<4	4	240	0.8	<5	<5	175
927992	Drill Core	4.15	58	11	805	10	22	0.6	4	8	422	2.84	11	<20	<4	8	344	<0.4	<5	<5	201
927993	Drill Core	4.68	68	18	955	7	24	0.7	3	9	632	2.51	<5	<20	<4	8	246	0.5	<5	<5	184
927994	Drill Core	2.38	36	16	734	8	27	0.6	<2	7	474	3.08	<5	<20	<4	9	420	0.5	<5	<5	179
927995	Drill Core	2.33	41	52	902	7	22	0.8	<2	11	355	3.00	<5	<20	<4	11	434	<0.4	<5	<5	217
927996	Drill Core	4.45	73	9	857	10	29	<0.5	<2	10	364	3.43	<5	<20	<4	11	474	0.5	<5	7	229
927997	Drill Core	4.96	99	5	1210	9	23	0.7	<2	11	451	3.60	<5	<20	<4	12	531	0.5	<5	<5	175
927998	Drill Core	5.08	108	34	893	11	24	0.7	2	10	442	2.97	8	<20	<4	8	358	0.6	<5	<5	158
927999	Drill Core	4.79	147	4	1644	9	26	0.7	3	8	451	2.51	<5	<20	<4	9	456	0.5	<5	<5	162
928000	Drill Core	0.71	<2	<2	<2	<5	4	<0.5	<2	<2	20	0.03	<5	<20	<4	<2	3860	<0.4	<5	<5	<2
928001	Rock Pulp	0.10	646	3	5330	16	65	1.6	18	13	437	5.25	9	<20	<4	4	448	0.5	<5	<5	127
928002	Drill Core	5.07	164	17	1512	10	30	0.6	<2	9	371	2.56	<5	<20	<4	9	420	0.5	<5	<5	141
928003	Drill Core	4.22	144	3	1138	16	34	1.2	2	9	617	3.99	17	<20	<4	8	389	0.7	<5	<5	196
928004	Drill Core	3.97	531	5	1819	28	38	2.8	4	14	518	4.12	19	<20	<4	8	287	1.1	<5	<5	228
928005	Drill Core	4.69	182	3	1421	9	26	2.0	2	12	528	2.94	12	<20	<4	10	425	0.6	<5	<5	206
928006	Drill Core	5.22	105	2	600	13	35	0.7	<2	7	686	3.24	8	<20	<4	10	384	0.6	<5	<5	161
928007	Drill Core	4.70	96	3	796	8	28	0.7	<2	10	548	3.90	10	<20	<4	9	233	0.6	<5	<5	163
928008	Drill Core	4.87	73	2	590	9	29	<0.5	<2	7	728	3.16	13	<20	<4	8	340	0.6	<5	<5	146
928009	Drill Core	4.87	115	<2	818	15	38	0.7	<2	7	853	3.49	12	<20	<4	8	412	0.5	<5	<5	147
928010	Drill Core	0.77	<2	<2	3	<5	4	<0.5	<2	<2	22	0.04	<5	<20	<4	<2	4251	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 3 of 6 Part 2

SMI09000214.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927981	Drill Core	1.05	0.121	22	2	0.88	125	0.27	8.36	3.34	4.35	<4	43	<2	13	7	1	7	1.6
927982	Drill Core	1.77	0.117	21	2	0.92	296	0.28	8.24	3.48	4.33	<4	62	<2	13	7	1	6	0.8
927983	Drill Core	1.27	0.106	22	4	0.76	288	0.27	8.21	3.70	4.46	<4	65	<2	14	7	2	5	0.8
927984	Drill Core	1.14	0.141	29	2	1.11	240	0.31	8.83	3.57	4.13	<4	56	<2	15	6	2	8	1.3
927985	Drill Core	0.85	0.141	27	2	1.10	252	0.28	9.00	3.25	4.74	<4	44	<2	14	6	2	7	1.5
927986	Drill Core	1.76	0.117	28	<2	1.14	495	0.27	9.16	3.55	4.18	<4	41	<2	16	6	2	8	0.9
927987	Drill Core	1.70	0.105	22	2	1.10	282	0.25	8.94	3.91	3.42	<4	44	<2	16	5	2	7	1.4
927988	Drill Core	1.78	0.119	32	2	1.05	676	0.28	9.66	4.35	3.31	<4	54	<2	17	6	2	7	1.3
927989	Drill Core	2.83	0.142	22	7	1.08	376	0.32	8.74	3.44	4.11	<4	50	<2	14	6	1	9	1.4
927990	Drill Core	32.92	0.010	<2	<2	4.52	17	<0.01	0.10	0.02	0.03	<4	<2	<2	<2	<1	<1	<0.1	
927991	Drill Core	2.82	0.124	18	35	0.70	1182	0.30	7.63	3.25	2.63	<4	37	<2	12	5	<1	8	0.8
927992	Drill Core	2.69	0.154	20	10	0.86	316	0.37	8.51	4.42	2.75	<4	35	<2	13	7	1	11	1.2
927993	Drill Core	2.34	0.143	19	5	0.89	907	0.35	8.20	3.01	3.25	<4	34	<2	12	7	1	10	0.9
927994	Drill Core	1.57	0.148	23	4	1.22	2896	0.35	9.25	4.35	3.32	<4	35	<2	13	6	1	9	0.5
927995	Drill Core	1.54	0.143	27	<2	1.21	1438	0.33	9.18	4.61	3.04	<4	52	<2	14	6	1	9	0.8
927996	Drill Core	1.64	0.154	31	<2	1.42	1245	0.35	9.51	5.12	2.37	<4	53	<2	17	8	2	9	0.8
927997	Drill Core	3.50	0.135	24	3	1.06	179	0.32	8.94	4.15	3.26	<4	46	<2	18	7	2	9	2.0
927998	Drill Core	3.97	0.122	19	2	0.89	384	0.29	7.95	3.13	3.85	<4	38	<2	18	7	1	8	1.4
927999	Drill Core	4.22	0.129	25	2	0.91	232	0.28	8.27	3.02	4.55	<4	38	<2	20	6	1	7	1.3
928000	Drill Core	38.59	0.003	<2	<2	1.78	11	<0.01	0.04	<0.01	0.01	<4	<2	<2	<2	<1	<1	<0.1	
928001	Rock Pulp	1.67	0.100	13	24	1.34	706	0.27	7.60	2.97	3.56	4	75	6	13	8	1	12	0.6
928002	Drill Core	3.73	0.113	21	<2	0.80	436	0.27	8.68	4.08	3.57	<4	40	<2	16	6	1	6	1.2
928003	Drill Core	4.23	0.137	20	<2	0.99	209	0.31	8.44	3.79	3.08	<4	42	<2	16	6	1	9	2.2
928004	Drill Core	4.24	0.164	26	4	0.91	103	0.38	8.41	3.97	2.54	<4	39	2	18	5	1	12	2.6
928005	Drill Core	4.14	0.150	33	3	1.01	819	0.37	9.27	4.60	2.56	<4	36	<2	19	7	1	11	1.3
928006	Drill Core	3.91	0.126	29	3	0.80	984	0.30	8.63	3.76	3.36	<4	55	<2	18	7	1	7	1.0
928007	Drill Core	3.53	0.120	26	3	0.81	213	0.27	7.93	2.98	3.58	<4	50	<2	17	6	1	7	1.5
928008	Drill Core	3.31	0.113	24	3	1.01	1064	0.28	8.33	3.38	3.71	<4	53	<2	19	7	1	7	0.8
928009	Drill Core	3.34	0.112	25	2	1.06	1597	0.28	8.18	3.22	3.84	<4	51	2	19	7	1	7	0.7
928010	Drill Core	37.28	0.003	<2	<2	1.68	17	<0.01	0.06	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 4 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000214.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	ppm
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
928011	Drill Core	4.29	128	<2	708	10	41	<0.5	<2	7	737	3.40	7	<20	<4	9	366	0.7	<5	<5	150
928012	Drill Core	5.13	169	2	1014	16	37	1.1	<2	9	595	4.90	27	<20	<4	10	262	0.6	<5	<5	170
928013	Drill Core	5.14	55	<2	350	13	85	<0.5	<2	8	868	3.91	17	<20	<4	8	434	0.8	<5	<5	148
928014	Drill Core	5.08	62	<2	491	13	45	<0.5	<2	7	1026	3.70	20	<20	<4	9	372	0.8	<5	<5	135
928015	Drill Core	4.95	57	<2	492	13	41	0.6	<2	9	870	3.96	19	<20	<4	8	437	0.7	<5	<5	149
928016	Drill Core	5.35	48	<2	338	11	38	<0.5	<2	6	981	3.44	19	<20	<4	8	475	0.5	<5	<5	138
928017	Drill Core	4.58	225	2	710	10	89	0.6	<2	8	889	3.60	21	<20	<4	8	353	0.7	<5	<5	146
928018	Drill Core	4.95	76	2	488	8	50	0.7	<2	7	1050	3.68	24	<20	<4	7	333	0.7	<5	<5	157
928019	Drill Core	4.72	64	<2	405	16	33	<0.5	<2	11	841	4.33	32	<20	<4	5	355	1.4	<5	<5	189
928020	Drill Core	0.62	<2	<2	<2	<5	6	<0.5	<2	<2	29	0.05	<5	<20	<4	<2	3771	<0.4	<5	<5	<2
928021	Drill Core	4.74	72	<2	445	9	30	<0.5	<2	8	887	3.54	18	<20	<4	7	413	1.0	<5	<5	151
928022	Drill Core	3.95	90	<2	253	19	31	<0.5	<2	7	904	3.69	31	<20	<4	6	384	1.2	<5	<5	168
928023	Drill Core	4.03	48	4	363	14	42	<0.5	2	9	762	3.10	19	<20	<4	7	386	1.1	<5	<5	160
928024	Drill Core	4.70	40	3	170	10	34	<0.5	20	8	816	3.71	10	<20	<4	4	232	0.9	<5	<5	187
928025	Drill Core	4.23	53	<2	322	12	31	<0.5	27	11	777	3.49	10	<20	<4	4	298	1.1	<5	<5	184
928026	Drill Core	4.82	57	2	130	13	32	<0.5	2	6	849	4.18	10	<20	<4	7	374	1.3	<5	<5	178
928027	Drill Core	4.66	37	<2	120	13	44	<0.5	<2	7	759	3.54	<5	<20	<4	8	581	0.9	<5	<5	176
928028	Drill Core	4.83	24	<2	114	14	39	<0.5	<2	7	770	3.64	6	<20	<4	6	471	0.9	<5	<5	210
928029	Drill Core	4.83	67	4	276	9	31	<0.5	<2	8	787	3.27	12	<20	<4	6	376	0.8	<5	<5	177
928030	Drill Core	0.75	<2	<2	<2	6	5	<0.5	<2	<2	24	0.04	<5	<20	<4	<2	3953	<0.4	<5	<5	<2
928031	Rock Pulp	0.14	318	<2	3214	33	66	0.9	16	7	331	3.45	<5	<20	<4	12	158	0.8	<5	<5	42
928032	Drill Core	4.69	55	<2	290	14	33	<0.5	<2	8	693	3.29	7	<20	<4	8	602	0.7	<5	<5	160
928033	Drill Core	5.21	24	<2	115	7	29	<0.5	<2	5	701	3.43	7	<20	<4	7	409	0.7	<5	<5	167
928034	Drill Core	3.87	37	<2	110	12	33	<0.5	<2	7	790	3.45	<5	<20	<4	5	439	0.9	<5	<5	162
928035	Drill Core	4.66	66	3	130	9	34	<0.5	<2	6	604	3.26	7	<20	<4	5	325	0.7	<5	<5	176
928036	Drill Core	4.94	20	<2	203	12	32	<0.5	<2	6	644	3.11	<5	<20	<4	6	393	0.8	<5	<5	178
928037	Drill Core	4.94	13	3	184	13	26	<0.5	<2	5	604	2.67	<5	<20	<4	6	364	0.6	<5	<5	161
928038	Drill Core	5.11	42	2	274	13	31	<0.5	<2	6	602	3.07	<5	<20	<4	6	385	0.5	<5	<5	180
928039	Drill Core	5.23	90	2	515	14	46	<0.5	2	10	800	4.68	6	<20	<4	6	477	0.9	<5	<5	270
928040	Drill Core	0.76	<2	<2	3	<5	4	<0.5	<2	<2	25	0.05	<5	<20	<4	<2	4288	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 4 of 6 Part 2

SMI09000214.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928011	Drill Core	3.92	0.120	21	3	0.90	925	0.29	8.42	3.47	3.78	<4	41	<2	15	7	1	8	0.8
928012	Drill Core	2.36	0.118	15	2	1.05	106	0.28	8.99	3.00	4.19	<4	43	<2	15	7	1	6	2.5
928013	Drill Core	3.01	0.117	16	<2	1.16	340	0.28	9.05	3.49	3.87	<4	46	<2	18	8	1	6	1.1
928014	Drill Core	4.54	0.113	23	<2	1.18	304	0.29	8.55	3.47	3.64	<4	47	<2	22	8	<1	6	1.2
928015	Drill Core	3.57	0.118	17	<2	1.05	159	0.28	8.57	3.72	3.48	<4	42	<2	18	6	1	6	1.8
928016	Drill Core	3.06	0.116	18	<2	1.16	604	0.29	8.54	3.31	3.76	<4	48	2	19	7	1	6	0.9
928017	Drill Core	2.89	0.112	15	<2	1.16	427	0.28	8.60	3.24	3.93	<4	41	4	16	7	1	6	1.1
928018	Drill Core	3.67	0.117	15	<2	1.24	760	0.26	8.20	2.83	3.78	<4	32	<2	14	5	1	6	1.0
928019	Drill Core	2.74	0.126	14	3	1.36	159	0.30	8.44	3.32	3.84	<4	36	<2	15	7	1	8	1.3
928020	Drill Core	38.70	0.002	<2	<2	1.79	43	<0.01	0.06	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928021	Drill Core	3.83	0.118	16	<2	1.09	247	0.31	8.14	3.46	3.72	<4	41	<2	18	6	1	7	0.8
928022	Drill Core	4.19	0.126	18	3	1.17	180	0.30	7.99	3.51	3.17	<4	37	<2	18	5	<1	7	1.0
928023	Drill Core	3.17	0.117	20	3	1.05	252	0.29	8.18	3.51	3.80	<4	38	<2	19	6	<1	6	0.7
928024	Drill Core	3.66	0.105	17	33	1.37	213	0.29	7.00	2.65	3.47	<4	35	<2	18	5	<1	10	0.7
928025	Drill Core	3.69	0.115	20	34	1.51	264	0.35	7.16	3.18	2.92	<4	32	<2	21	7	1	10	0.6
928026	Drill Core	4.18	0.116	15	2	0.91	133	0.30	7.90	3.22	3.43	<4	40	<2	16	6	1	7	1.4
928027	Drill Core	3.44	0.122	17	<2	1.00	925	0.30	8.63	3.35	3.69	<4	45	<2	17	6	1	7	0.3
928028	Drill Core	3.56	0.118	15	<2	1.04	392	0.30	8.41	3.36	3.63	<4	44	<2	15	5	1	7	0.5
928029	Drill Core	4.10	0.114	17	<2	0.95	283	0.30	8.10	3.16	4.08	<4	42	2	17	6	1	7	0.6
928030	Drill Core	38.67	0.003	<2	<2	1.96	25	<0.01	0.06	0.02	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928031	Rock Pulp	1.20	0.043	25	19	0.50	769	0.15	6.47	2.32	3.53	4	54	7	14	10	2	6	0.3
928032	Drill Core	3.33	0.119	18	3	0.97	908	0.33	8.42	3.44	3.63	<4	46	<2	17	7	1	7	0.3
928033	Drill Core	3.79	0.113	12	<2	0.74	196	0.31	8.09	3.30	3.95	<4	43	<2	15	6	1	7	0.9
928034	Drill Core	4.35	0.117	11	<2	0.76	253	0.29	8.16	3.15	3.96	<4	42	<2	13	5	1	6	0.8
928035	Drill Core	3.10	0.108	10	<2	0.95	236	0.28	7.88	2.67	4.08	5	39	<2	13	4	1	6	0.7
928036	Drill Core	3.07	0.113	11	<2	0.95	436	0.30	7.95	3.24	3.43	<4	37	<2	14	6	1	7	0.4
928037	Drill Core	3.34	0.110	9	3	0.78	714	0.30	7.92	3.44	3.64	<4	35	<2	13	7	1	7	0.4
928038	Drill Core	2.49	0.116	11	<2	0.96	754	0.30	8.07	3.24	3.58	<4	33	<2	13	6	1	7	0.4
928039	Drill Core	3.50	0.131	13	3	1.10	246	0.36	8.02	2.66	4.14	4	44	<2	15	5	1	9	0.8
928040	Drill Core	38.89	0.004	<2	<2	1.81	23	<0.01	0.07	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page:

5 of 6

Part 1

SMI09000214.1

CERTIFICATE OF ANALYSIS

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V		
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi		
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
928041	Drill Core		3.86	142	3	470	13	48	<0.5	<2	8	639	4.47	<5	<20	<4	7	466	1.0	<5	255	
928042	Drill Core		5.35	64	2	314	13	34	<0.5	3	8	584	6.14	<5	<20	<4	7	456	1.2	<5	409	
928043	Drill Core		5.03	64	3	273	15	38	<0.5	<2	6	566	4.03	<5	<20	<4	8	399	0.8	<5	249	
928044	Drill Core		4.29	45	3	268	15	38	<0.5	2	8	573	4.06	<5	<20	<4	7	408	0.8	<5	240	
928045	Drill Core		5.01	15	<2	41	10	15	<0.5	2	3	289	1.38	<5	<20	<4	11	165	<0.4	<5	136	
928046	Drill Core		4.76	16	2	46	8	17	<0.5	3	3	349	1.72	<5	<20	<4	11	156	<0.4	<5	165	
928047	Drill Core		1.76	9	<2	60	9	30	<0.5	4	4	362	1.95	<5	<20	<4	9	164	<0.4	<5	176	
928048	Drill Core		5.00	32	3	162	16	37	<0.5	4	8	666	4.87	13	<20	<4	6	233	0.9	9	<5	184
928049	Drill Core		5.17	21	2	70	13	26	<0.5	3	8	716	3.47	6	<20	<4	8	367	0.8	<5	<5	203
928050	Drill Core		0.83	<2	<2	<2	<5	4	<0.5	<2	<2	23	0.05	<5	<20	<4	<2	4055	<0.4	<5	<5	<2
928051	Drill Core		4.72	54	3	312	15	41	<0.5	2	7	789	3.71	<5	<20	<4	9	626	0.8	<5	<5	174
928052	Drill Core		4.86	21	3	237	11	33	<0.5	3	7	558	2.77	6	<20	<4	8	272	<0.4	<5	<5	154
928053	Drill Core		5.23	26	3	118	15	28	<0.5	4	5	379	2.15	<5	<20	<4	10	274	0.4	<5	<5	134
928054	Drill Core		5.26	26	3	165	<5	28	<0.5	4	5	364	2.02	<5	<20	<4	12	309	0.4	<5	7	145
928055	Drill Core		4.75	22	<2	99	5	56	<0.5	3	12	1103	4.11	<5	<20	<4	7	888	0.9	<5	12	184
928056	Drill Core		3.71	24	<2	115	<5	47	<0.5	3	12	1072	4.04	<5	21	<4	8	709	0.7	<5	9	177
928057	Drill Core		5.81	36	<2	221	5	27	<0.5	4	6	366	2.26	<5	<20	<4	11	206	0.4	<5	8	135
928058	Drill Core		4.88	41	<2	132	15	28	<0.5	5	4	456	2.23	<5	<20	<4	10	155	0.5	<5	6	112
928059	Drill Core		3.38	13	<2	149	10	29	<0.5	6	6	563	2.10	<5	<20	<4	11	144	0.5	<5	8	141
928060	Drill Core		1.29	<2	<2	<2	<5	3	<0.5	<2	<2	23	0.04	<5	<20	<4	<2	3681	<0.4	<5	<5	<2
928061	Rock Pulp		0.14	317	<2	3116	24	62	0.8	16	7	326	3.36	<5	<20	<4	13	160	0.5	<5	8	41
928062	Drill Core		5.10	12	<2	85	<5	72	<0.5	3	12	1141	4.10	<5	<20	<4	7	617	0.8	<5	12	175
928063	Drill Core		5.21	84	<2	86	7	72	<0.5	4	13	1166	4.46	<5	21	<4	8	662	0.6	<5	8	180
928064	Drill Core		5.25	21	<2	124	7	57	<0.5	2	10	966	3.97	<5	<20	<4	10	563	0.6	<5	7	163
928065	Drill Core		4.05	36	<2	156	10	57	1.0	<2	9	928	4.47	9	<20	<4	9	382	1.1	5	11	174
928066	Drill Core		1.77	63	<2	139	59	172	2.0	3	7	723	3.12	15	<20	<4	9	163	3.6	9	<5	151
928067	Drill Core		6.03	100	3	397	<5	36	<0.5	2	7	696	4.42	6	<20	<4	8	387	1.0	<5	5	172
928068	Drill Core		4.50	129	2	507	<5	31	<0.5	2	7	709	3.28	<5	<20	<4	8	467	0.8	<5	8	150
928069	Drill Core		4.59	307	3	1247	<5	46	1.0	5	11	1044	5.79	18	<20	<4	9	360	1.1	<5	<5	308
928070	Drill Core		1.47	<2	<2	<2	<5	3	<0.5	<2	<2	25	0.04	<5	<20	<4	<2	3926	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 5 of 6 Part 2

SMI09000214.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928041	Drill Core	2.88	0.132	13	3	0.98	1728	0.33	8.11	2.80	4.74	<4	42	<2	15	6	1	8	0.3
928042	Drill Core	2.81	0.128	13	5	0.80	3122	0.32	7.99	2.72	5.02	<4	30	<2	16	6	1	8	<0.1
928043	Drill Core	2.78	0.112	12	4	0.83	2202	0.29	7.97	3.04	4.34	<4	31	<2	15	6	1	8	0.3
928044	Drill Core	3.02	0.126	11	4	0.75	578	0.29	8.11	3.12	4.31	<4	34	<2	14	5	1	8	0.4
928045	Drill Core	1.55	0.049	11	6	0.32	1729	0.18	6.90	2.06	4.38	<4	58	<2	8	6	<1	4	0.2
928046	Drill Core	1.84	0.064	9	8	0.44	1701	0.20	7.25	1.87	5.12	<4	54	<2	9	5	<1	5	0.4
928047	Drill Core	1.97	0.063	9	7	0.38	1823	0.21	7.19	2.11	4.59	<4	58	<2	8	6	<1	5	0.2
928048	Drill Core	3.42	0.115	12	10	0.93	80	0.26	7.35	2.08	4.17	<4	39	<2	11	5	1	8	2.5
928049	Drill Core	3.30	0.109	11	16	0.99	1690	0.27	6.92	2.60	3.68	<4	38	<2	12	5	1	10	0.3
928050	Drill Core	38.08	0.004	<2	<2	1.63	22	<0.01	0.07	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928051	Drill Core	3.54	0.117	16	4	0.99	915	0.31	8.10	3.70	3.46	<4	40	<2	16	7	2	10	0.3
928052	Drill Core	2.91	0.091	13	5	0.81	416	0.24	7.59	3.25	3.99	<4	44	<2	13	6	1	7	0.5
928053	Drill Core	2.38	0.066	10	7	0.49	1737	0.21	7.46	2.79	5.60	<4	53	<2	14	7	1	5	0.3
928054	Drill Core	2.12	0.075	13	5	0.54	1772	0.24	7.35	3.01	3.33	<4	53	<2	14	6	2	6	0.2
928055	Drill Core	4.00	0.148	19	7	1.12	2831	0.35	8.27	3.16	3.76	<4	46	<2	17	7	2	9	<0.1
928056	Drill Core	4.04	0.146	20	6	1.06	2956	0.35	8.71	3.10	3.92	<4	47	<2	18	6	2	9	0.1
928057	Drill Core	1.75	0.078	11	6	0.64	1526	0.25	7.47	2.89	5.26	<4	44	<2	15	6	1	6	0.2
928058	Drill Core	2.63	0.065	12	6	0.49	783	0.21	6.85	2.65	4.37	<4	50	<2	14	5	<1	5	0.9
928059	Drill Core	2.74	0.077	14	7	0.61	1817	0.24	7.32	2.71	4.63	<4	53	<2	15	6	<1	6	0.2
928060	Drill Core	37.87	0.003	<2	<2	1.62	17	<0.01	0.06	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928061	Rock Pulp	1.19	0.042	26	15	0.49	754	0.15	6.69	2.30	3.84	<4	50	8	13	9	2	6	0.3
928062	Drill Core	4.09	0.146	21	5	1.25	2696	0.35	8.39	2.76	3.85	<4	59	<2	18	6	2	9	0.2
928063	Drill Core	4.75	0.153	24	6	1.06	2751	0.36	8.87	2.88	3.89	<4	65	<2	21	6	2	10	0.7
928064	Drill Core	4.54	0.131	21	4	0.83	661	0.32	8.76	3.16	3.80	<4	61	<2	19	6	1	9	0.9
928065	Drill Core	3.72	0.124	15	<2	0.82	444	0.29	8.60	3.20	3.56	<4	38	<2	14	5	1	8	1.1
928066	Drill Core	2.78	0.096	14	6	0.77	1037	0.25	7.56	2.04	3.11	<4	45	<2	11	5	1	7	0.9
928067	Drill Core	4.03	0.115	14	<2	0.83	162	0.28	8.07	3.30	3.59	<4	38	<2	13	5	1	7	1.9
928068	Drill Core	3.47	0.108	15	<2	0.89	2266	0.28	8.46	3.64	3.54	<4	40	<2	15	5	1	7	0.6
928069	Drill Core	4.73	0.173	22	3	1.46	336	0.42	8.31	3.21	2.61	<4	49	<2	22	6	1	15	1.5
928070	Drill Core	38.35	0.003	<2	<2	1.70	14	<0.01	0.05	0.01	0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 6 of 6 Part 1

SMI09000214.1

CERTIFICATE OF ANALYSIS

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi		
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	
928071	Drill Core		5.60	53	3	142	<5	37	<0.5	4	9	866	5.54	14	<20	<4	9	314	1.2	<5	5	228
928072	Drill Core		4.50	27	<2	70	<5	52	<0.5	5	11	985	3.88	5	<20	<4	8	305	0.6	<5	<5	193
928073	Drill Core		3.00	18	<2	59	5	61	<0.5	4	13	1113	4.07	10	<20	<4	10	406	1.0	<5	<5	186
928074	Drill Core		4.24	10	<2	73	<5	20	<0.5	4	4	387	1.84	<5	<20	<4	11	129	<0.4	<5	6	154
928075	Drill Core		4.76	32	4	164	<5	17	<0.5	4	4	511	2.24	15	<20	<4	11	194	<0.4	<5	5	163
928076	Drill Core		4.48	20	3	38	<5	23	<0.5	2	6	690	2.39	7	<20	<4	9	263	<0.4	<5	<5	150
928077	Drill Core		5.31	9	2	48	<5	32	<0.5	4	9	529	3.66	<5	<20	<4	7	355	0.4	<5	7	214
928078	Drill Core		3.67	34	4	103	7	34	<0.5	4	9	598	3.06	<5	<20	<4	8	341	0.7	<5	8	200
928079	Drill Core		1.41	16	3	37	10	54	<0.5	3	8	836	3.83	10	<20	<4	7	347	1.0	<5	7	191
928080	Drill Core		0.55	<2	<2	<2	<5	3	<0.5	<2	<2	24	0.04	<5	<20	<4	<2	4011	<0.4	<5	<5	<2
928081	Drill Core		3.04	39	4	31	66	185	<0.5	6	9	660	5.03	15	<20	<4	9	259	3.4	13	<5	195
928082	Drill Core		4.17	19	3	30	<5	38	<0.5	3	8	821	4.10	9	<20	<4	9	418	1.0	<5	<5	214
928083	Drill Core		3.26	17	3	45	<5	36	<0.5	3	8	645	3.45	<5	<20	<4	7	556	0.8	<5	8	234
928084	Drill Core		4.87	14	2	132	<5	38	<0.5	2	8	822	3.80	<5	<20	<4	9	465	0.8	<5	8	192
928085	Drill Core		2.27	10	2	52	6	29	<0.5	4	8	739	3.32	7	<20	<4	9	333	0.8	<5	<5	232
928086	Drill Core		4.88	6	2	20	<5	21	<0.5	4	6	466	1.91	<5	<20	<4	7	275	<0.4	<5	<5	128
928087	Drill Core		5.52	8	2	61	<5	42	<0.5	4	10	756	4.91	<5	<20	<4	8	496	0.6	<5	9	265
928088	Drill Core		4.89	18	2	34	5	36	<0.5	4	10	750	4.81	16	<20	<4	8	363	0.8	<5	8	259
928089	Drill Core		4.79	9	3	64	13	31	<0.5	4	8	637	3.78	<5	<20	<4	7	396	0.6	<5	9	217
928090	Drill Core		0.55	<2	<2	4	<5	3	<0.5	<2	<2	34	0.06	<5	<20	<4	<2	4221	<0.4	<5	<5	2
928091	Rock Pulp		0.14	639	3	5390	19	65	1.5	17	14	437	5.25	5	<20	<4	4	449	0.9	<5	8	130
928092	Drill Core		4.19	7	3	76	12	33	<0.5	3	7	570	3.62	<5	<20	<4	7	416	0.4	<5	8	241
928093	Drill Core		4.77	19	<2	36	9	37	<0.5	4	9	840	4.44	7	<20	<4	8	522	0.7	<5	6	261
928094	Drill Core		4.43	14	3	171	13	39	<0.5	4	10	745	4.38	14	<20	<4	7	331	0.9	<5	9	226
928095	Drill Core		1.30	9	<2	91	10	33	<0.5	5	9	586	3.37	<5	<20	<4	7	420	0.5	<5	11	285
928096	Drill Core		3.02	6	<2	23	28	42	0.5	2	2	676	1.02	<5	<20	<4	4	157	0.9	<5	<5	66
928097	Drill Core		3.36	6	<2	30	<5	17	<0.5	<2	5	600	1.55	<5	<20	<4	7	267	<0.4	<5	<5	115
928098	Drill Core		1.26	8	<2	65	7	26	<0.5	3	14	795	3.37	10	<20	<4	7	294	0.7	<5	8	241
928099	Drill Core		2.82	10	3	44	9	24	<0.5	2	7	747	3.13	8	<20	<4	8	278	0.5	<5	8	297
928100	Drill Core		0.54	<2	<2	3	<5	4	<0.5	<2	<2	22	0.04	<5	<20	<4	<2	4095	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 6 of 6 Part 2

SMI09000214.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928071	Drill Core	5.09	0.157	20	4	0.96	113	0.34	7.72	3.04	3.27	<4	48	<2	20	6	1	12	3.2
928072	Drill Core	4.27	0.150	22	10	1.09	2319	0.33	8.51	2.87	4.07	<4	58	<2	16	6	1	10	0.6
928073	Drill Core	4.25	0.154	25	6	1.28	1546	0.36	8.74	2.91	4.13	<4	65	<2	19	6	1	10	0.7
928074	Drill Core	2.26	0.062	12	6	0.48	1834	0.19	7.21	2.06	4.62	<4	46	<2	10	5	<1	5	0.3
928075	Drill Core	4.06	0.078	11	8	0.35	280	0.23	7.23	2.33	5.09	<4	44	<2	11	5	<1	7	1.5
928076	Drill Core	5.06	0.127	14	4	0.62	442	0.31	7.47	2.70	4.53	<4	42	<2	16	7	<1	9	1.2
928077	Drill Core	2.38	0.124	10	7	1.16	1594	0.36	8.40	3.25	4.28	<4	40	<2	10	5	<1	11	0.8
928078	Drill Core	3.58	0.130	14	4	1.13	2583	0.35	9.01	3.16	4.68	<4	40	<2	13	7	<1	11	0.6
928079	Drill Core	4.31	0.111	15	6	1.37	1471	0.30	7.71	2.47	2.96	<4	36	<2	16	5	1	11	0.7
928080	Drill Core	38.04	0.003	<2	<2	1.70	20	<0.01	0.06	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928081	Drill Core	4.66	0.123	12	12	1.01	117	0.36	8.13	3.27	3.19	<4	40	<2	14	8	<1	12	2.6
928082	Drill Core	4.38	0.149	16	3	1.16	707	0.36	8.99	3.19	3.76	4	48	<2	17	6	1	11	1.0
928083	Drill Core	3.60	0.130	15	3	0.98	3121	0.36	8.83	2.67	4.72	<4	46	<2	16	6	1	10	0.4
928084	Drill Core	3.69	0.147	17	3	1.18	2786	0.36	8.65	3.00	4.01	<4	51	<2	19	6	1	10	0.5
928085	Drill Core	4.02	0.141	16	5	1.19	1683	0.38	8.56	3.51	3.45	<4	42	<2	15	7	<1	12	0.7
928086	Drill Core	3.11	0.122	12	6	0.79	1654	0.32	7.06	2.92	3.70	<4	33	2	13	6	<1	9	0.4
928087	Drill Core	3.14	0.145	16	7	1.56	2564	0.40	8.82	3.16	3.82	<4	42	<2	18	6	1	13	0.5
928088	Drill Core	2.59	0.147	13	9	1.50	930	0.39	8.57	3.07	3.99	<4	35	<2	15	5	<1	14	0.8
928089	Drill Core	3.11	0.120	14	8	1.22	2153	0.39	7.81	3.10	1.89	5	43	<2	18	7	1	11	0.4
928090	Drill Core	39.53	0.004	<2	<2	1.76	22	<0.01	0.07	0.01	0.03	<4	<2	<2	<2	<1	<1	<0.1	
928091	Rock Pulp	1.65	0.099	13	26	1.36	703	0.28	7.45	3.05	1.97	5	75	4	13	7	1	12	0.6
928092	Drill Core	2.17	0.143	14	7	1.01	3076	0.42	8.92	3.83	1.95	<4	49	<2	16	8	1	9	0.3
928093	Drill Core	4.24	0.119	15	7	1.37	1903	0.37	7.88	3.66	2.27	5	41	<2	17	7	1	13	1.1
928094	Drill Core	3.01	0.128	16	7	1.32	2640	0.39	8.56	3.52	3.03	5	49	<2	18	8	<1	12	0.8
928095	Drill Core	2.53	0.125	13	12	1.20	1789	0.43	8.54	3.62	3.30	5	44	<2	15	8	1	14	0.9
928096	Drill Core	5.80	0.036	9	7	0.24	695	0.11	3.96	1.16	1.50	<4	25	<2	10	3	<1	3	0.4
928097	Drill Core	3.53	0.103	11	9	0.64	1448	0.22	5.46	2.02	1.54	<4	28	<2	13	4	<1	6	0.2
928098	Drill Core	3.83	0.159	14	3	1.11	1740	0.33	8.21	3.34	2.38	5	39	<2	14	6	<1	8	0.7
928099	Drill Core	4.54	0.150	15	3	1.01	1140	0.31	8.14	2.92	2.31	<4	36	<2	15	5	<1	7	0.9
928100	Drill Core	39.86	0.004	<2	<2	2.11	9	<0.01	0.11	<0.01	0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 09, 2009

Page:

1 of 3 Part 1

SMI09000214.1

QUALITY CONTROL REPORT

	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi		
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
	MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	0.4	5	5	2	228	
Pulp Duplicates																						
927973	Drill Core	5.23	55	23	825	<5	20	<0.5	2	14	248	3.40	6	<20	<4	7	349	<0.4	<5	<5	228	
REP 927973	QC			23	806	10	20	<0.5	2	14	240	3.31	6	<20	<4	7	334	<0.4	<5	<5	219	
927993	Drill Core	4.68	68	18	955	7	24	0.7	3	9	632	2.51	<5	<20	<4	8	246	0.5	<5	<5	184	
REP 927993	QC			19	987	12	24	0.9	3	10	645	2.61	<5	<20	<4	10	250	<0.4	<5	<5	191	
927999	Drill Core	4.79	147	4	1644	9	26	0.7	3	8	451	2.51	<5	<20	<4	9	456	0.5	<5	<5	162	
REP 927999	QC			146																		
928014	Drill Core	5.08	62	<2	491	13	45	<0.5	<2	7	1026	3.70	20	<20	<4	9	372	0.8	<5	<5	135	
REP 928014	QC			58																		
REP 928039	QC			2	517	13	46	<0.5	<2	10	784	4.73	6	<20	<4	6	455	1.0	<5	<5	273	
928061	Rock Pulp	0.14	317	<2	3116	24	62	0.8	16	7	326	3.36	<5	<20	<4	13	160	0.5	<5	8	41	
REP 928061	QC			314																		
928066	Drill Core	1.77	63	<2	139	59	172	2.0	3	7	723	3.12	15	<20	<4	9	163	3.6	9	<5	151	
REP 928066	QC			<2	139	57	175	1.8	3	7	737	3.17	15	<20	<4	10	165	3.8	10	6	153	
928092	Drill Core	4.19	7	3	76	12	33	<0.5	3	7	570	3.62	<5	<20	<4	7	416	0.4	<5	8	241	
REP 928092	QC			11																		
Core Reject Duplicates																						
927969	Drill Core	5.40	141	11	1511	20	24	1.4	3	13	318	3.14	<5	<20	<4	9	347	<0.4	<5	<5	228	
DUP 927969	QC			130	9	1400	14	21	1.2	2	11	290	2.92	<5	<20	<4	9	337	<0.4	<5	<5	207
928004	Drill Core	3.97	531	5	1819	28	38	2.8	4	14	518	4.12	19	<20	<4	8	287	1.1	<5	<5	228	
DUP 928004	QC			587	4	1847	22	37	2.8	3	14	522	4.10	18	<20	<4	7	292	0.7	<5	<5	225
928039	Drill Core	5.23	90	2	515	14	46	<0.5	2	10	800	4.68	6	<20	<4	6	477	0.9	<5	<5	270	
DUP 928039	QC			91	2	529	8	47	<0.5	2	10	808	4.76	7	<20	<4	6	453	1.2	<5	<5	275
928074	Drill Core	4.24	10	<2	73	<5	20	<0.5	4	4	387	1.84	<5	<20	<4	11	129	<0.4	<5	6	154	
DUP 928074	QC			11	<2	75	<5	20	<0.5	4	4	406	1.86	<5	<20	<4	11	132	<0.4	<5	<5	156
Reference Materials																						
STD OREAS24P	Standard			<2	44	6	111	<0.5	136	41	1059	7.31	<5	<20	<4	2	382	1.3	<5	10	155	
STD OREAS24P	Standard			<2	46	6	119	<0.5	142	43	1091	7.63	<5	<20	<4	2	391	1.7	<5	12	161	
STD OREAS24P	Standard			<2	45	<5	115	<0.5	134	41	1041	7.21	<5	<20	<4	3	385	2.0	<5	<5	153	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 09, 2009

Page:

1 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000214.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1
Pulp Duplicates																		
927973	Drill Core	1.30	0.156	20	3	1.03	156	0.42	8.31	3.51	4.28	5	55	2	10	6	1	13
REP 927973	QC	1.26	0.152	19	3	0.99	175	0.40	8.07	3.45	4.18	<4	54	<2	10	6	1	13
927993	Drill Core	2.34	0.143	19	5	0.89	907	0.35	8.20	3.01	3.25	<4	34	<2	12	7	1	10
REP 927993	QC	2.44	0.149	20	5	0.93	406	0.35	8.77	3.03	3.42	<4	33	<2	12	6	1	11
927999	Drill Core	4.22	0.129	25	2	0.91	232	0.28	8.27	3.02	4.55	<4	38	<2	20	6	1	7
REP 927999	QC																	
928014	Drill Core	4.54	0.113	23	<2	1.18	304	0.29	8.55	3.47	3.64	<4	47	<2	22	8	<1	6
REP 928014	QC																	
REP 928039	QC	3.52	0.129	12	3	1.11	196	0.35	8.06	2.63	4.15	<4	44	2	15	5	1	10
928061	Rock Pulp	1.19	0.042	26	15	0.49	754	0.15	6.69	2.30	3.84	<4	50	8	13	9	2	6
REP 928061	QC																	
928066	Drill Core	2.78	0.096	14	6	0.77	1037	0.25	7.56	2.04	3.11	<4	45	<2	11	5	1	7
REP 928066	QC	2.85	0.098	16	6	0.79	978	0.25	7.95	2.07	3.19	<4	44	<2	11	5	1	7
928092	Drill Core	2.17	0.143	14	7	1.01	3076	0.42	8.92	3.83	1.95	<4	49	<2	16	8	1	9
REP 928092	QC																	
Core Reject Duplicates																		
927969	Drill Core	1.94	0.135	17	5	0.99	143	0.33	8.20	2.96	4.73	4	46	<2	12	6	1	11
DUP 927969	QC	1.76	0.128	18	5	0.93	181	0.31	8.24	2.95	4.92	5	43	<2	12	6	1	10
928004	Drill Core	4.24	0.164	26	4	0.91	103	0.38	8.41	3.97	2.54	<4	39	2	18	5	1	12
DUP 928004	QC	4.27	0.165	28	4	0.91	157	0.38	8.31	4.15	2.54	<4	41	4	19	5	1	12
928039	Drill Core	3.50	0.131	13	3	1.10	246	0.36	8.02	2.66	4.14	4	44	<2	15	5	1	9
DUP 928039	QC	3.61	0.133	12	4	1.10	219	0.36	8.12	2.62	4.37	<4	44	<2	15	6	1	9
928074	Drill Core	2.26	0.062	12	6	0.48	1834	0.19	7.21	2.06	4.62	<4	46	<2	10	5	<1	5
DUP 928074	QC	2.37	0.063	12	6	0.51	1885	0.21	7.60	2.08	4.55	<4	48	<2	11	6	<1	5
Reference Materials																		
STD OREAS24P	Standard	5.48	0.132	17	191	3.95	274	1.02	8.07	2.37	0.70	<4	145	<2	22	19	1	20
STD OREAS24P	Standard	5.77	0.133	18	209	4.05	277	1.04	8.10	2.39	0.72	<4	151	<2	23	22	1	20
STD OREAS24P	Standard	5.42	0.127	17	182	3.89	272	0.99	7.74	2.31	0.68	<4	142	<2	22	20	1	19



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Durn

Report Date:

October 09, 2009

www.acmelab.com

Page:

2 of 3 Part

QUALITY CONTROL REPORT

SMI09000214.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 2 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000214.1

		1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S
		% 0.01	% 0.002	ppm 2	ppm 2	% 0.01	ppm 1	% 0.01	% 0.01	% 0.01	ppm 4	ppm 2	ppm 2	ppm 2	ppm 2	ppm 1	ppm 1	% 0.1	
STD OREAS24P	Standard	5.56	0.129	17	204	3.89	273	1.01	7.91	2.34	0.70	<4	143	<2	22	20	1	20 <0.1	
STD OREAS24P	Standard	5.67	0.133	19	192	4.08	276	1.04	8.18	2.43	0.71	<4	151	<2	23	21	1	20 <0.1	
STD OREAS45P	Standard	0.28	0.043	23	984	0.19	282	0.98	6.75	0.07	0.34	<4	163	<2	14	21	<1	66 <0.1	
STD OREAS45P	Standard	0.29	0.045	25	1116	0.20	293	1.03	7.08	0.07	0.36	5	172	7	14	23	<1	69 <0.1	
STD OREAS45P	Standard	0.29	0.045	24	1054	0.20	286	1.04	6.86	0.07	0.35	<4	163	<2	14	21	<1	67 <0.1	
STD OREAS45P	Standard	0.28	0.044	24	1075	0.19	289	1.03	6.94	0.07	0.35	5	161	<2	14	21	<1	68 <0.1	
STD OREAS45P	Standard	0.29	0.044	24	1072	0.20	295	1.00	6.89	0.07	0.35	<4	167	3	14	21	<1	67 <0.1	
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OREAS24P Expected		5.83	0.136	17.4	196	4.13	285	1.1	7.66	2.34	0.7	0.5	141	1.6	21.3	21	20		
STD OREAS45P Expected		0.3	0.047	24.8	1089	0.1962	296	1.037	6.82	0.081	0.35	1.1	154	2.5	13	21.6	67	0.03	
STD OXH55 Expected																			
STD OXE56 Expected																			
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 09, 2009

www.acmelab.com

Page:

3 of 3 Part

QUALITY CONTROL REPORT

SMI09000214.1

	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi		
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2	
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
Prep Wash																					
G1	Prep Blank		3	<2	<2	17	53	<0.5	4	5	732	2.35	<5	<20	<4	5	678	<0.4	<5	<5	54
G1	Prep Blank		<2	<2	<2	18	49	<0.5	3	5	707	2.20	<5	<20	<4	6	651	<0.4	<5	<5	51



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

www.acmelab.com

Page: 3 of 3 **Part** 2

QUALITY CONTROL REPORT

SMI09000214.1

		1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
		%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
		0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
G1	Prep Blank	2.33	0.082	25	8	0.67	972	0.25	6.91	2.60	2.91	<4	8	<2	13	21	3	5	<0.1
G1	Prep Blank	2.30	0.083	23	8	0.64	969	0.24	6.70	2.61	2.90	<4	9	<2	14	21	3	5	<0.1



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 11, 2009
Report Date: October 09, 2009
Page: 1 of 8

CERTIFICATE OF ANALYSIS

SMI09000216.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 200

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
Code					
R200	194	Crush split and pulverize drill core to 200 mesh			VAN
3B	200	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	200	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL


STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC: Nigel Luckman
B. Booth



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 2 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000216.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
928301	Drill Core	2.53	237	5	2352	7	56	1.1	6	35	658	4.94	<5	<20	<4	7	464	0.7	<5	<5	263
928302	Drill Core	1.30	204	5	621	8	32	1.0	4	23	679	4.87	<5	<20	<4	6	558	0.4	<5	7	574
928303	Drill Core	2.80	136	3	706	9	34	0.6	3	16	612	4.01	<5	<20	<4	9	549	0.4	<5	7	267
928304	Drill Core	2.87	218	7	1073	10	40	0.9	3	18	466	4.11	8	<20	<4	7	483	0.6	<5	<5	247
928305	Drill Core	2.20	64	3	454	9	31	0.5	2	13	623	3.40	<5	<20	<4	9	451	0.5	<5	9	204
928306	Drill Core	2.57	77	7	464	5	39	<0.5	2	18	646	2.92	<5	<20	<4	8	415	0.4	<5	<5	239
928307	Drill Core	4.63	104	4	682	5	46	<0.5	2	17	506	3.34	5	<20	<4	7	396	0.5	<5	11	259
928308	Drill Core	2.41	162	10	1221	14	58	0.7	4	30	524	4.66	8	<20	<4	9	519	1.0	<5	<5	222
928309	Drill Core	3.43	121	3	1021	6	76	<0.5	3	23	519	3.42	<5	<20	<4	10	430	0.8	<5	7	208
928310	Drill Core	0.57	<2	<2	8	<5	4	<0.5	<2	<2	21	0.05	<5	<20	<4	<2	4346	<0.4	<5	<5	<2
928311	Drill Core	3.43	129	16	899	8	26	0.5	3	29	400	3.95	<5	<20	<4	10	527	0.5	<5	<5	246
928312	Drill Core	4.33	225	19	1003	8	30	0.5	3	33	390	4.47	<5	<20	<4	10	674	0.7	<5	<5	230
928313	Drill Core	4.77	167	7	648	9	23	<0.5	<2	18	530	3.28	<5	<20	<4	11	826	0.5	<5	<5	206
928314	Drill Core	4.61	117	15	894	11	22	<0.5	3	26	421	3.61	<5	<20	<4	9	684	0.5	<5	<5	180
928315	Drill Core	5.02	191	54	1018	11	24	0.7	<2	29	389	3.23	7	<20	<4	10	678	0.5	<5	6	194
928316	Drill Core	4.65	129	22	1030	8	18	0.7	3	30	495	4.11	7	<20	<4	11	726	0.8	<5	<5	241
928317	Drill Core	4.45	130	12	813	11	35	<0.5	2	19	497	4.28	9	<20	<4	9	492	0.6	<5	<5	238
928318	Drill Core	4.42	145	6	883	9	22	0.7	3	12	602	4.80	<5	<20	<4	7	543	0.7	<5	7	208
928319	Drill Core	5.01	149	5	967	11	29	<0.5	3	14	473	4.91	<5	<20	<4	7	578	0.8	<5	10	214
928320	Drill Core	0.63	<2	<2	4	<5	5	<0.5	<2	<2	30	0.09	<5	<20	<4	<2	4086	<0.4	<5	<5	<2
928321	Drill Core	4.95	134	6	974	8	72	0.8	3	14	467	4.42	<5	<20	<4	8	577	0.9	<5	8	210
928322	Drill Core	4.85	176	4	1200	<5	41	1.1	3	13	674	3.19	<5	<20	<4	6	466	0.5	<5	<5	243
928323	Drill Core	4.77	219	13	1099	6	25	1.0	3	18	745	3.44	<5	<20	<4	9	601	<0.4	<5	6	261
928324	Drill Core	4.99	226	10	1469	6	27	1.5	3	25	787	4.12	<5	<20	<4	9	623	<0.4	<5	<5	254
928325	Drill Core	4.63	228	15	1294	<5	20	0.9	<2	15	458	3.02	<5	<20	<4	11	532	<0.4	<5	<5	197
928326	Drill Core	5.14	143	5	883	<5	25	1.1	<2	15	562	4.27	<5	<20	<4	12	681	<0.4	<5	<5	211
928327	Drill Core	5.54	120	6	650	7	25	0.8	<2	13	537	4.70	8	<20	<4	12	742	<0.4	<5	<5	196
928328	Drill Core	5.41	93	5	521	12	24	0.8	<2	14	567	4.43	12	<20	<4	12	634	<0.4	<5	<5	191
928329	Drill Core	4.87	76	3	269	7	27	<0.5	<2	16	608	4.67	<5	<20	<4	13	595	<0.4	<5	<5	204
928330	Drill Core	0.48	6	<2	4	<5	<2	<0.5	<2	<2	29	0.06	<5	<20	<4	<2	4035	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 2 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928301	Drill Core	0.94	0.225	29	4	1.62	704	0.36	8.45	5.14	1.27	6	33	<2	24	5	2	13	0.8
928302	Drill Core	0.78	0.242	24	5	1.41	742	0.54	8.38	5.44	1.42	6	40	3	21	6	2	17	0.1
928303	Drill Core	0.79	0.250	27	11	1.52	582	0.42	8.49	5.28	1.25	7	34	<2	20	7	2	15	0.2
928304	Drill Core	0.80	0.267	23	11	1.50	897	0.44	8.04	5.04	1.59	6	34	<2	23	7	2	13	0.8
928305	Drill Core	0.77	0.298	28	7	0.99	421	0.45	8.86	6.39	1.07	6	35	<2	26	8	2	13	0.1
928306	Drill Core	0.74	0.288	17	4	0.98	334	0.45	7.74	5.91	1.15	4	34	<2	17	10	1	14	0.4
928307	Drill Core	1.10	0.244	20	7	1.23	529	0.43	8.37	5.99	1.26	7	34	<2	24	8	1	11	0.8
928308	Drill Core	0.71	0.170	22	3	1.22	839	0.36	8.44	5.25	1.99	5	57	<2	23	7	2	10	1.7
928309	Drill Core	1.91	0.139	22	3	0.96	1409	0.33	8.59	5.14	2.15	5	60	<2	21	6	1	9	0.8
928310	Drill Core	>40	0.004	<2	<2	1.78	8	<0.01	0.05	0.02	0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
928311	Drill Core	2.76	0.153	33	4	1.06	1041	0.38	8.72	5.37	1.67	7	60	<2	20	7	2	11	1.7
928312	Drill Core	3.26	0.151	35	4	0.99	192	0.36	8.37	4.94	1.79	<4	71	2	21	6	2	10	2.5
928313	Drill Core	4.74	0.141	37	3	0.85	749	0.36	8.93	5.06	1.82	<4	73	<2	24	7	2	10	1.9
928314	Drill Core	3.72	0.126	30	3	0.95	675	0.30	8.92	5.88	1.16	4	68	<2	16	6	2	8	2.0
928315	Drill Core	3.19	0.145	32	3	0.79	557	0.35	8.48	6.04	1.06	5	69	2	21	7	1	9	1.9
928316	Drill Core	3.90	0.152	42	3	0.94	626	0.36	8.45	5.33	1.17	<4	66	<2	21	6	2	10	2.7
928317	Drill Core	2.63	0.145	28	3	1.11	305	0.34	8.57	4.80	1.88	5	67	<2	16	6	1	10	2.2
928318	Drill Core	3.71	0.120	18	2	1.10	114	0.31	8.53	3.28	3.56	5	71	<2	20	6	1	9	3.0
928319	Drill Core	2.84	0.127	18	3	1.25	182	0.33	8.87	3.37	3.76	<4	78	<2	18	7	1	9	2.7
928320	Drill Core	39.84	0.005	<2	<2	1.78	15	<0.01	0.15	0.01	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928321	Drill Core	2.85	0.132	20	2	1.15	250	0.32	8.99	3.26	4.11	5	75	<2	15	6	1	10	2.5
928322	Drill Core	4.02	0.131	19	4	0.86	872	0.34	7.84	3.15	3.25	5	40	3	15	6	1	11	1.5
928323	Drill Core	4.77	0.159	23	5	0.75	156	0.41	8.74	4.72	2.71	<4	48	<2	23	9	2	13	1.8
928324	Drill Core	4.60	0.175	24	4	1.00	179	0.42	8.95	3.79	3.65	5	55	2	22	9	2	14	1.8
928325	Drill Core	3.04	0.126	24	3	0.80	140	0.33	8.08	3.81	4.07	5	71	2	18	8	1	9	1.5
928326	Drill Core	3.59	0.132	29	4	0.89	90	0.34	8.53	3.93	3.77	<4	90	<2	21	9	2	9	2.5
928327	Drill Core	3.42	0.128	28	3	0.85	88	0.34	8.65	3.50	4.31	<4	99	<2	22	9	2	8	3.0
928328	Drill Core	3.79	0.123	28	3	0.70	85	0.32	8.58	3.67	3.98	<4	97	2	19	8	2	8	3.0
928329	Drill Core	4.75	0.132	31	3	0.70	94	0.34	8.70	3.06	4.05	<4	91	<2	20	9	2	9	3.1
928330	Drill Core	38.98	0.003	<2	<2	1.52	22	<0.01	0.13	0.02	0.02	<4	<2	<2	<2	2	<1	<1	<0.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 3 of 8 Part 1

SMI09000216.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
928331	Rock Pulp	0.14	329	<2	3455	27	72	1.5	17	8	357	3.72	<5	<20	<4	13	161	<0.4	<5	6	45
928332	Drill Core	4.76	100	4	462	8	30	0.8	<2	15	580	4.82	7	<20	<4	11	441	<0.4	<5	<5	203
928333	Drill Core	5.20	91	6	442	7	56	1.0	<2	12	551	4.64	9	<20	<4	12	487	0.6	<5	<5	177
928334	Drill Core	5.40	68	12	595	10	24	0.9	<2	15	535	4.12	8	<20	<4	12	498	<0.4	<5	<5	159
928335	Drill Core	5.19	114	16	725	10	24	1.3	<2	16	608	4.36	15	<20	<4	11	479	<0.4	<5	<5	173
928336	Drill Core	5.95	109	8	637	8	27	1.3	<2	16	652	4.73	13	<20	<4	10	424	<0.4	<5	<5	182
928337	Drill Core	3.08	4	2	42	<5	129	<0.5	18	24	1094	6.52	<5	<20	<4	4	752	0.8	<5	5	186
928338	Drill Core	3.55	86	5	381	6	26	0.9	<2	12	590	4.59	6	<20	<4	12	504	<0.4	<5	<5	185
928339	Drill Core	5.44	139	7	756	<5	19	1.1	<2	16	744	4.31	9	<20	<4	12	484	<0.4	<5	<5	199
928340	Drill Core	0.57	<2	<2	2	<5	<2	<0.5	<2	<2	24	0.05	<5	<20	<4	<2	3891	<0.4	<5	<5	<2
928341	Drill Core	4.04	180	11	1107	15	33	1.4	2	22	872	4.76	22	<20	<4	9	458	<0.4	<5	<5	227
928342	Drill Core	5.30	205	10	930	6	23	1.4	4	18	848	4.00	41	<20	<4	8	496	<0.4	<5	8	237
928343	Drill Core	4.77	107	8	928	<5	24	1.0	3	18	732	4.29	18	<20	<4	9	459	<0.4	<5	<5	205
928344	Drill Core	5.26	163	11	851	<5	27	0.7	3	16	882	3.94	<5	<20	<4	8	650	<0.4	<5	<5	221
928345	Drill Core	4.86	73	5	734	<5	22	0.9	6	18	774	3.78	9	<20	<4	8	553	<0.4	<5	<5	206
928346	Drill Core	5.36	188	11	914	10	24	1.5	3	19	789	4.10	62	<20	<4	9	396	0.5	<5	6	216
928347	Drill Core	5.07	182	6	1217	8	27	1.5	3	23	873	4.88	23	<20	<4	8	450	<0.4	<5	<5	188
928348	Drill Core	5.17	125	7	799	7	29	0.8	3	15	828	4.08	25	<20	<4	7	474	<0.4	<5	<5	193
928349	Drill Core	4.93	103	7	699	6	22	0.8	3	11	621	2.79	<5	<20	<4	9	645	<0.4	<5	<5	184
928350	Drill Core	0.52	4	<2	5	<5	<2	<0.5	<2	<2	26	0.06	<5	<20	<4	<2	4554	<0.4	<5	<5	2
928351	Drill Core	4.42	71	18	585	6	19	0.8	4	12	313	2.75	8	<20	<4	11	622	<0.4	<5	<5	181
928352	Drill Core	4.93	194	14	1030	5	22	1.3	4	13	525	3.25	<5	<20	<4	9	565	<0.4	<5	<5	177
928353	Drill Core	4.98	319	9	1287	5	18	1.2	6	13	367	3.16	9	<20	<4	6	439	<0.4	<5	<5	192
928354	Drill Core	4.69	332	6	790	<5	21	0.8	4	10	566	2.74	<5	<20	<4	8	645	<0.4	<5	<5	177
928355	Drill Core	4.38	170	28	785	<5	25	0.8	5	13	455	3.08	<5	<20	<4	9	465	<0.4	<5	<5	181
928356	Drill Core	2.39	105	62	320	<5	19	0.5	6	12	315	3.53	6	<20	<4	9	369	<0.4	<5	8	165
928357	Drill Core	3.63	102	17	422	7	26	0.7	3	16	484	5.40	9	<20	<4	10	278	0.5	<5	6	170
928358	Drill Core	4.35	126	42	671	6	13	<0.5	24	15	583	4.08	6	<20	<4	2	208	0.6	<5	<5	210
928359	Drill Core	5.07	74	99	503	7	11	<0.5	39	13	533	3.98	6	<20	<4	<2	299	0.7	<5	5	182
928360	Drill Core	0.58	<2	<2	4	<5	3	<0.5	<2	<2	24	0.03	<5	<20	<4	<2	3872	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 3 of 8 Part 2

SMI09000216.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928331	Rock Pulp	1.26	0.043	22	17	0.53	806	0.16	6.64	2.47	4.08	<4	60	9	13	10	3	7	0.4
928332	Drill Core	3.86	0.148	25	2	0.76	71	0.35	8.20	3.07	3.89	<4	98	<2	16	9	2	9	3.5
928333	Drill Core	3.69	0.115	21	3	0.61	67	0.30	8.40	2.97	4.10	<4	97	<2	14	8	2	7	3.4
928334	Drill Core	3.08	0.103	19	2	0.59	83	0.28	8.41	3.33	4.44	4	112	<2	15	9	1	5	3.3
928335	Drill Core	3.22	0.117	20	3	0.59	60	0.30	8.59	3.88	3.63	<4	108	<2	17	9	2	6	3.2
928336	Drill Core	3.69	0.122	22	4	0.88	65	0.31	7.70	4.05	2.97	<4	87	2	20	8	2	7	3.3
928337	Drill Core	4.43	0.326	53	40	2.30	2022	1.08	8.28	3.08	2.40	<4	91	2	15	29	2	16	0.2
928338	Drill Core	3.37	0.127	25	3	0.94	79	0.35	8.32	3.47	4.19	<4	99	2	19	9	2	7	3.1
928339	Drill Core	4.41	0.136	32	5	0.96	94	0.33	7.76	3.22	3.13	<4	69	3	22	8	2	10	2.7
928340	Drill Core	39.48	0.004	<2	<2	1.83	20	<0.01	0.09	0.02	0.02	<4	<2	<2	<2	<2	<1	<1	<0.1
928341	Drill Core	4.48	0.139	26	6	1.14	73	0.37	8.14	3.71	2.81	<4	73	<2	21	8	2	11	2.8
928342	Drill Core	4.27	0.143	19	5	0.97	249	0.38	8.32	5.40	1.39	6	60	2	20	8	2	12	1.6
928343	Drill Core	3.67	0.146	22	4	0.86	150	0.36	8.35	5.22	1.80	6	67	<2	21	9	1	10	1.8
928344	Drill Core	4.31	0.158	29	5	1.12	781	0.40	8.85	5.41	1.12	4	81	3	23	9	2	13	0.9
928345	Drill Core	3.82	0.141	23	14	0.93	672	0.38	8.58	5.54	1.11	<4	66	<2	21	8	2	11	1.1
928346	Drill Core	3.53	0.130	19	4	0.91	253	0.34	7.65	4.65	1.78	9	56	<2	20	8	2	10	1.8
928347	Drill Core	4.11	0.141	23	4	0.81	176	0.36	8.52	4.88	1.93	6	63	<2	22	8	2	9	2.0
928348	Drill Core	3.73	0.142	21	3	0.97	389	0.36	8.41	4.79	2.11	4	62	3	21	9	2	9	1.2
928349	Drill Core	3.64	0.155	18	3	0.42	426	0.38	8.50	5.68	1.50	8	66	<2	21	9	2	10	1.4
928350	Drill Core	>40	0.004	<2	<2	1.59	13	<0.01	0.11	0.03	0.02	<4	<2	<2	<2	<1	<1	<0.1	
928351	Drill Core	2.08	0.166	21	4	0.39	364	0.40	9.21	6.15	1.71	10	75	<2	16	10	2	10	2.0
928352	Drill Core	3.56	0.146	21	4	0.58	172	0.38	8.65	5.99	1.68	5	71	<2	20	9	2	9	1.6
928353	Drill Core	1.75	0.144	15	3	0.62	257	0.36	7.55	5.77	1.62	6	71	<2	13	8	1	8	1.5
928354	Drill Core	3.74	0.148	28	4	0.65	757	0.37	8.45	5.79	1.52	<4	74	2	22	9	2	9	1.1
928355	Drill Core	2.73	0.159	22	4	0.84	834	0.36	8.44	6.06	1.15	6	68	<2	19	9	2	8	0.8
928356	Drill Core	2.31	0.124	32	8	0.87	220	0.33	7.41	5.85	0.73	<4	59	2	19	8	1	8	2.1
928357	Drill Core	2.17	0.181	17	5	1.18	267	0.32	7.86	5.45	0.56	6	51	<2	22	8	1	7	1.8
928358	Drill Core	3.81	0.132	32	49	1.31	131	0.34	6.87	4.78	0.24	<4	43	3	25	4	<1	13	2.0
928359	Drill Core	4.21	0.124	29	55	1.19	241	0.36	7.15	5.09	0.24	<4	42	3	25	4	<1	13	2.5
928360	Drill Core	36.46	0.003	<2	<2	1.72	9	<0.01	0.07	0.02	<0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 4 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000216.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	
928361	Rock Pulp		0.14	641	3	5048	12	59	1.3	15	14	414	4.99	<5	<20	<4	4	433	1.0	<5	124	
928362	Drill Core		4.85	142	22	594	5	9	<0.5	40	11	444	3.54	<5	<20	<4	2	275	0.5	<5	157	
928363	Drill Core		4.71	156	32	555	6	11	<0.5	32	11	412	2.98	<5	<20	<4	<2	310	<0.4	<5	158	
928364	Drill Core		5.11	134	47	318	8	13	<0.5	35	7	441	2.73	<5	<20	<4	2	315	0.4	<5	170	
928365	Drill Core		5.22	95	92	321	6	13	<0.5	37	11	556	2.77	<5	<20	<4	3	316	<0.4	<5	184	
928366	Drill Core		4.93	82	12	412	7	12	<0.5	35	13	433	3.09	7	<20	<4	<2	332	<0.4	<5	157	
928367	Drill Core		4.92	62	23	292	<5	15	<0.5	30	11	459	3.69	<5	<20	<4	2	257	<0.4	<5	192	
928368	Drill Core		5.22	203	40	849	9	16	<0.5	42	23	455	4.25	<5	<20	<4	<2	270	0.6	<5	198	
928369	Drill Core		5.00	168	51	412	6	11	<0.5	33	12	284	2.74	<5	<20	<4	3	254	<0.4	<5	170	
928370	Drill Core		0.36	10	<2	3	<5	3	<0.5	<2	<2	24	0.05	<5	<20	<4	<2	4271	<0.4	<5	<2	
928371	Drill Core		5.11	112	53	467	6	9	<0.5	21	17	477	4.28	11	<20	<4	4	273	0.8	<5	163	
928372	Drill Core		5.04	60	19	194	7	12	<0.5	8	9	227	2.23	<5	<20	<4	8	522	<0.4	<5	168	
928373	Drill Core		5.15	177	25	389	5	12	<0.5	18	9	259	2.71	<5	<20	<4	5	282	<0.4	<5	204	
928374	Drill Core		2.73	262	20	688	<5	10	<0.5	18	9	154	1.86	<5	<20	<4	2	197	<0.4	<5	138	
928375	Drill Core		4.34	599	13	944	8	16	<0.5	25	13	319	4.02	<5	<20	<4	7	340	0.4	<5	229	
928376	Drill Core		5.09	252	17	959	8	13	<0.5	4	12	324	3.45	<5	<20	<4	11	553	0.6	<5	207	
928377	Drill Core		2.08	182	20	666	6	16	<0.5	15	14	549	5.88	<5	<20	<4	6	322	1.1	<5	237	
928378	Drill Core		2.53	225	34	731	5	13	<0.5	38	10	361	3.83	<5	<20	<4	4	274	0.6	<5	230	
928379	Drill Core		2.48	100	22	543	9	13	<0.5	31	11	275	3.15	<5	<20	<4	9	367	<0.4	<5	265	
928380	Drill Core		0.59	<2	<2	3	<5	4	<0.5	<2	<2	26	0.05	<5	<20	<4	<2	3869	<0.4	<5	<2	
928381	Drill Core		4.57	169	34	719	<5	12	<0.5	66	14	483	2.81	<5	<20	<4	3	133	<0.4	<5	311	
928382	Drill Core		2.49	467	57	605	<5	11	<0.5	36	17	266	2.81	<5	<20	<4	4	148	<0.4	<5	213	
928383	Drill Core		2.53	390	22	829	7	18	<0.5	35	12	354	3.57	9	<20	<4	6	276	<0.4	<5	238	
928384	Drill Core		4.88	374	36	1009	<5	15	<0.5	12	11	259	2.63	<5	<20	<4	9	398	<0.4	<5	168	
928385	Drill Core		5.12	162	48	636	5	9	<0.5	4	12	285	3.28	6	<20	<4	7	318	0.6	<5	5	143
928386	Drill Core		5.07	296	43	746	16	10	0.7	3	11	647	5.36	18	<20	<4	9	364	1.2	7	<5	139
928387	Drill Core		4.87	129	14	396	6	13	<0.5	2	12	298	2.67	<5	<20	<4	7	365	<0.4	<5	143	
928388	Drill Core		5.03	192	20	353	7	11	<0.5	3	9	262	2.52	<5	<20	<4	8	418	<0.4	<5	145	
928389	Drill Core		5.35	137	42	459	9	11	<0.5	2	8	268	1.93	<5	<20	<4	8	491	<0.4	<5	165	
928390	Drill Core		0.83	<2	<2	3	<5	4	<0.5	<2	<2	21	0.03	<5	<20	<4	<2	3475	<0.4	<5	<2	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 4 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928361	Rock Pulp	1.63	0.096	11	24	1.28	672	0.27	7.18	2.85	3.00	4	69	5	12	7	1	11	0.5
928362	Drill Core	3.44	0.123	30	51	0.97	108	0.33	7.00	5.31	0.15	<4	37	<2	21	5	<1	11	2.0
928363	Drill Core	3.11	0.119	14	44	0.93	143	0.31	7.04	5.11	0.32	<4	34	<2	20	4	<1	10	1.4
928364	Drill Core	3.19	0.113	14	41	1.02	139	0.34	7.43	5.46	0.30	<4	38	<2	22	5	<1	10	1.3
928365	Drill Core	4.06	0.120	15	36	1.16	194	0.36	7.49	5.41	0.29	<4	39	<2	25	5	<1	12	1.3
928366	Drill Core	3.12	0.117	14	32	1.12	303	0.35	7.73	5.33	0.58	<4	37	<2	21	4	<1	11	1.6
928367	Drill Core	1.97	0.107	10	40	1.50	155	0.36	7.54	5.03	0.30	5	36	<2	20	5	1	14	0.9
928368	Drill Core	2.56	0.117	15	37	1.52	207	0.39	7.90	4.97	0.45	<4	38	<2	23	5	1	13	1.4
928369	Drill Core	1.84	0.111	12	51	0.88	150	0.33	6.70	4.73	0.45	5	35	<2	20	4	1	13	1.3
928370	Drill Core	37.53	0.004	<2	<2	1.78	14	<0.01	0.13	0.02	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
928371	Drill Core	3.67	0.083	10	33	0.69	78	0.26	6.41	3.92	1.30	9	32	<2	17	3	<1	11	3.6
928372	Drill Core	2.69	0.134	13	9	1.02	333	0.34	8.52	5.86	0.87	<4	51	<2	21	7	1	9	0.9
928373	Drill Core	2.05	0.115	13	20	1.22	112	0.32	7.64	5.50	0.33	4	43	<2	19	5	1	10	1.3
928374	Drill Core	1.21	0.072	9	31	0.84	69	0.26	5.39	4.13	0.19	<4	32	<2	12	5	<1	9	0.9
928375	Drill Core	2.04	0.119	36	25	1.51	357	0.35	7.77	4.66	0.74	<4	57	<2	21	5	1	13	0.9
928376	Drill Core	3.58	0.160	51	4	1.00	362	0.39	8.26	5.10	1.60	5	96	<2	22	7	2	11	1.3
928377	Drill Core	4.19	0.118	22	27	1.66	251	0.32	7.54	4.42	0.22	<4	53	<2	24	4	1	14	1.3
928378	Drill Core	3.08	0.110	16	40	1.03	84	0.35	6.87	4.34	0.24	5	40	<2	22	4	1	14	0.9
928379	Drill Core	2.49	0.146	22	14	0.90	282	0.37	7.70	5.35	0.67	<4	64	<2	19	6	1	13	1.2
928380	Drill Core	36.60	0.004	<2	<2	1.72	13	<0.01	0.08	0.01	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
928381	Drill Core	3.51	0.086	58	95	0.73	363	0.20	3.67	2.33	0.06	<4	37	<2	24	4	<1	9	1.2
928382	Drill Core	2.80	0.131	44	115	0.65	30	0.20	3.86	2.64	0.06	<4	37	3	18	4	<1	9	1.6
928383	Drill Core	2.49	0.135	18	48	1.31	168	0.30	7.33	4.58	0.43	5	50	<2	21	5	1	12	1.1
928384	Drill Core	2.16	0.126	15	3	1.02	329	0.32	8.75	5.80	0.83	6	73	<2	18	6	2	8	1.0
928385	Drill Core	2.93	0.116	9	4	0.58	203	0.29	7.65	5.79	0.69	13	79	<2	15	5	1	8	2.5
928386	Drill Core	6.85	0.098	17	<2	0.61	104	0.25	7.67	4.94	0.71	12	67	<2	21	5	<1	8	4.9
928387	Drill Core	2.84	0.120	13	2	0.96	269	0.30	7.84	5.56	0.65	5	85	<2	18	7	1	7	1.3
928388	Drill Core	2.69	0.126	14	5	1.01	306	0.31	8.19	5.75	0.63	7	91	<2	19	6	2	8	1.2
928389	Drill Core	3.46	0.126	13	2	0.67	405	0.32	8.23	5.93	0.80	<4	94	<2	19	7	2	8	1.3
928390	Drill Core	36.21	0.004	<2	<2	1.87	8	<0.01	0.11	0.02	<0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 5 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000216.1

Analyte	Method	Unit	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
			Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi		
			kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	V		
		MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	2	
928391	Rock Pulp		0.14	651	3	5224	17	59	1.3	17	13	421	5.07	<5	<20	<4	5	423	0.4	<5	125	
928392	Drill Core		5.10	247	47	675	13	10	<0.5	4	16	351	3.84	52	<20	<4	7	424	0.5	<5	166	
928393	Drill Core		4.95	103	34	497	<5	17	0.6	3	11	457	2.90	7	<20	<4	7	622	<0.4	<5	185	
928394	Drill Core		5.12	92	12	507	<5	18	0.6	3	16	382	2.95	<5	<20	<4	7	571	<0.4	<5	186	
928395	Drill Core		4.61	187	29	851	<5	19	0.8	3	22	391	3.67	<5	<20	<4	8	574	<0.4	<5	182	
928396	Drill Core		4.69	110	20	575	7	22	0.8	4	17	447	3.80	<5	<20	<4	8	623	0.4	<5	187	
928397	Drill Core		3.62	94	24	515	6	20	0.6	3	13	407	3.34	<5	<20	<4	9	609	<0.4	<5	191	
928398	Drill Core		3.24	222	32	921	<5	24	0.9	3	18	537	4.40	<5	<20	<4	9	654	0.5	<5	227	
928399	Drill Core		4.79	72	30	482	7	20	0.7	2	14	457	3.83	6	<20	<4	8	726	<0.4	<5	233	
928400	Drill Core		0.51	<2	<2	3	<5	<2	<0.5	<2	<2	22	0.04	<5	<20	<4	<2	3842	<0.4	<5	<2	
928401	Drill Core		5.04	108	7	401	6	19	0.6	3	15	356	4.17	<5	<20	<4	9	677	<0.4	<5	242	
928402	Drill Core		4.57	92	19	427	11	19	0.8	3	18	247	4.51	12	<20	<4	8	617	0.4	<5	237	
928403	Drill Core		4.67	168	12	432	6	16	0.8	2	13	234	3.64	8	<20	<4	9	586	<0.4	<5	239	
928404	Drill Core		5.11	141	22	487	10	17	0.7	2	22	378	4.79	23	<20	<4	8	554	0.4	<5	221	
928405	Drill Core		5.26	163	19	329	7	17	0.6	3	13	422	3.17	<5	<20	<4	8	645	<0.4	<5	174	
928406	Drill Core		5.42	164	13	207	6	17	0.7	3	10	391	3.09	<5	<20	<4	8	602	<0.4	<5	182	
928407	Drill Core		4.73	143	7	319	6	16	0.9	3	12	388	3.00	<5	<20	<4	7	695	<0.4	<5	182	
928408	Drill Core		4.45	136	9	312	7	17	0.6	3	16	383	3.90	<5	<20	<4	6	652	<0.4	<5	178	
928409	Drill Core		4.68	167	14	337	<5	17	<0.5	3	11	277	2.82	<5	<20	<4	8	628	<0.4	<5	194	
928410	Drill Core		0.51	<2	<2	<2	<5	<2	<0.5	<2	<2	26	0.04	<5	<20	<4	<2	4129	<0.4	<5	<2	
928411	Drill Core		4.95	138	10	282	8	14	<0.5	3	11	232	2.92	<5	<20	<4	8	679	<0.4	<5	184	
928412	Drill Core		4.98	88	7	276	6	18	0.5	3	9	276	2.52	<5	<20	<4	8	751	<0.4	<5	180	
928413	Drill Core		4.62	100	12	231	<5	13	<0.5	4	11	167	2.49	<5	<20	<4	10	613	<0.4	<5	186	
928414	Drill Core		5.02	50	8	152	6	16	<0.5	2	7	300	2.16	<5	<20	<4	9	715	<0.4	<5	195	
928415	Drill Core		4.85	37	21	161	<5	21	<0.5	<2	10	547	4.15	6	<20	<4	10	723	<0.4	<5	239	
928416	Drill Core		5.04	60	12	242	8	15	0.7	3	12	276	2.72	<5	<20	<4	9	666	<0.4	<5	197	
928417	Drill Core		5.12	86	30	249	6	15	0.5	3	11	587	2.74	<5	<20	<4	8	614	<0.4	<5	167	
928418	Drill Core		4.73	198	77	380	5	19	<0.5	2	12	442	2.96	<5	<20	<4	9	566	<0.4	<5	154	
928419	Drill Core		5.04	106	13	287	7	16	0.5	2	9	269	2.83	<5	<20	<4	10	628	<0.4	<5	166	
928420	Drill Core		0.54	<2	<2	<2	<2	<5	<2	<0.5	<2	<2	23	0.03	<5	<20	<4	<2	3897	<0.4	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 5 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928391	Rock Pulp	1.66	0.096	12	27	1.29	677	0.27	7.27	2.90	3.33	5	69	4	12	7	1	11	0.5
928392	Drill Core	3.96	0.119	9	2	0.66	223	0.32	7.58	5.75	0.66	6	89	<2	15	6	1	8	3.2
928393	Drill Core	4.35	0.142	18	<2	0.63	289	0.39	8.98	6.39	0.80	4	113	<2	21	9	2	10	1.5
928394	Drill Core	3.88	0.141	17	4	0.64	252	0.39	8.55	6.48	0.71	4	115	3	21	9	2	9	0.9
928395	Drill Core	4.08	0.142	26	2	0.67	286	0.37	9.20	6.52	0.65	4	113	<2	22	9	2	10	1.3
928396	Drill Core	3.76	0.140	23	2	0.85	278	0.37	9.06	6.52	0.53	<4	116	<2	22	9	2	10	1.0
928397	Drill Core	2.81	0.153	19	3	0.80	252	0.38	9.20	6.61	0.66	5	119	<2	19	9	2	10	0.8
928398	Drill Core	2.87	0.181	37	3	1.32	286	0.43	9.46	6.09	0.67	7	111	<2	27	9	2	12	0.9
928399	Drill Core	3.08	0.178	40	3	0.96	401	0.44	9.28	6.10	1.08	5	103	<2	23	10	2	13	1.4
928400	Drill Core	38.75	0.004	<2	<2	1.86	5	<0.01	0.09	0.03	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
928401	Drill Core	3.06	0.182	45	3	0.87	402	0.42	9.21	5.71	1.29	6	97	<2	20	8	2	12	2.6
928402	Drill Core	2.13	0.183	40	3	0.88	133	0.45	9.22	5.92	1.29	6	110	<2	19	9	2	11	3.6
928403	Drill Core	2.14	0.175	41	3	0.74	98	0.47	9.32	5.81	1.58	11	113	<2	17	10	2	12	2.9
928404	Drill Core	2.83	0.168	31	4	0.85	59	0.44	8.63	4.73	2.46	10	110	<2	19	9	2	11	3.8
928405	Drill Core	3.16	0.144	19	<2	0.89	677	0.39	9.14	5.94	1.24	4	113	<2	24	9	2	10	1.5
928406	Drill Core	3.03	0.142	19	2	0.88	460	0.37	9.13	6.07	1.19	6	113	2	24	8	2	10	1.6
928407	Drill Core	3.69	0.140	16	2	0.53	130	0.39	9.07	5.59	2.13	<4	118	<2	22	9	2	10	1.9
928408	Drill Core	3.45	0.137	14	3	0.56	381	0.37	8.39	6.37	0.84	4	111	3	18	9	2	9	2.5
928409	Drill Core	2.11	0.146	14	2	0.64	400	0.39	8.67	6.60	0.83	4	111	<2	17	9	2	10	1.3
928410	Drill Core	38.71	0.003	<2	<2	1.83	7	<0.01	0.07	0.02	<0.01	<4	<2	<2	<2	2	<1	<1	<0.1
928411	Drill Core	2.54	0.142	15	3	0.36	211	0.40	9.00	6.34	1.50	5	114	<2	17	9	2	9	2.3
928412	Drill Core	3.10	0.141	16	2	0.50	758	0.38	8.96	6.39	1.19	<4	109	<2	20	9	2	9	1.3
928413	Drill Core	1.84	0.149	17	3	0.32	401	0.40	9.45	6.73	1.26	7	110	2	17	9	2	9	1.9
928414	Drill Core	3.04	0.150	15	2	0.44	439	0.41	9.37	6.40	1.31	<4	110	<2	19	9	2	10	1.3
928415	Drill Core	3.12	0.170	48	2	1.11	584	0.45	9.37	5.92	0.86	<4	114	2	25	9	2	13	1.7
928416	Drill Core	2.42	0.157	25	3	0.44	462	0.42	9.40	6.50	1.13	5	113	<2	16	10	2	11	1.7
928417	Drill Core	3.91	0.167	19	2	0.59	162	0.37	9.08	5.97	1.73	5	102	<2	22	8	2	9	1.7
928418	Drill Core	2.62	0.140	14	2	1.17	929	0.36	9.10	6.28	1.07	6	104	<2	22	8	2	9	1.1
928419	Drill Core	2.46	0.136	94	<2	0.97	251	0.36	8.87	4.80	3.28	<4	93	<2	21	8	2	9	1.4
928420	Drill Core	38.41	0.003	<2	<2	1.61	14	<0.01	0.09	0.02	<0.01	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 6 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000216.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	ppm
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
928421	Rock Pulp	0.10	630	4	5443	11	68	1.7	17	14	465	5.50	<5	<20	<4	4	473	<0.4	<5	<5	129
928422	Drill Core	4.99	93	13	262	7	18	<0.5	3	9	372	3.60	<5	<20	<4	8	591	<0.4	<5	<5	159
928423	Drill Core	4.40	54	26	330	<5	17	0.6	3	14	304	3.86	<5	<20	<4	8	569	<0.4	<5	<5	163
928424	Drill Core	5.09	58	18	272	6	17	0.7	3	10	243	3.48	<5	<20	<4	8	533	<0.4	<5	<5	148
928425	Drill Core	3.58	58	27	264	6	17	<0.5	2	12	313	3.44	<5	<20	<4	8	635	<0.4	<5	5	156
928426	Drill Core	3.58	90	33	367	6	22	0.8	6	16	458	4.28	<5	<20	<4	8	436	<0.4	<5	<5	219
928427	Drill Core	5.17	901	114	956	<5	23	1.3	5	22	390	4.17	<5	<20	<4	9	449	<0.4	<5	<5	175
928428	Drill Core	5.12	335	41	587	12	18	<0.5	<2	14	350	4.33	<5	<20	<4	9	422	<0.4	<5	19	185
928429	Drill Core	4.54	951	65	898	<5	19	0.7	<2	14	404	4.57	<5	26	<4	9	443	<0.4	<5	13	190
928430	Drill Core	0.66	3	<2	3	<5	<2	<0.5	<2	<2	25	0.04	<5	<20	<4	<2	4369	<0.4	<5	5	<2
928431	Drill Core	5.84	448	2	283	11	18	<0.5	<2	8	433	3.76	<5	<20	<4	5	360	<0.4	<5	12	198
928432	Drill Core	3.80	646	3	186	19	13	<0.5	<2	10	431	3.79	8	<20	<4	7	439	<0.4	<5	22	158
928433	Drill Core	5.50	339	3	227	<5	13	<0.5	<2	10	469	3.49	<5	<20	<4	6	407	<0.4	<5	12	153
928434	Drill Core	4.21	166	10	185	<5	17	<0.5	<2	11	501	3.78	8	<20	<4	7	422	<0.4	<5	12	155
928435	Drill Core	5.21	71	17	287	14	12	<0.5	<2	13	556	4.26	22	<20	<4	6	450	<0.4	6	19	158
928436	Drill Core	5.12	54	19	258	19	14	<0.5	<2	12	535	4.17	11	<20	<4	8	436	<0.4	<5	17	155
928437	Drill Core	5.62	72	16	282	9	11	<0.5	<2	15	467	4.81	15	<20	<4	7	405	<0.4	<5	12	151
928438	Drill Core	4.72	76	15	317	15	14	<0.5	<2	15	462	5.01	6	<20	<4	6	414	<0.4	<5	15	152
928439	Drill Core	5.15	42	11	244	22	17	<0.5	<2	13	396	3.95	<5	<20	<4	6	447	<0.4	6	12	156
928440	Drill Core	0.85	<2	<2	4	<5	<2	<0.5	<2	<2	25	0.04	6	<20	<4	<2	4771	<0.4	<5	6	<2
928441	Drill Core	5.47	66	5	191	<5	15	<0.5	<2	12	444	3.75	<5	<20	<4	6	441	<0.4	<5	9	146
928442	Drill Core	4.33	70	<2	201	<5	12	<0.5	<2	12	379	3.74	<5	<20	<4	7	523	<0.4	<5	10	149
928443	Drill Core	5.42	77	<2	263	<5	14	<0.5	<2	15	326	4.38	<5	<20	<4	7	511	<0.4	10	7	144
928444	Drill Core	5.08	350	17	393	<5	21	<0.5	<2	17	398	4.64	16	<20	<4	7	386	<0.4	5	13	145
928445	Drill Core	5.00	497	4	227	16	15	<0.5	<2	13	362	4.34	14	<20	<4	6	463	<0.4	6	14	149
928446	Drill Core	4.81	310	<2	275	<5	14	<0.5	<2	14	380	4.17	<5	<20	<4	7	454	<0.4	7	16	147
928447	Drill Core	4.98	107	7	250	16	16	<0.5	<2	14	385	4.26	5	<20	<4	7	420	<0.4	7	11	145
928448	Drill Core	4.53	225	11	250	20	32	<0.5	<2	12	582	6.63	88	<20	<4	6	446	<0.4	<5	19	149
928449	Drill Core	3.82	341	7	250	20	16	<0.5	<2	15	499	4.65	19	<20	<4	5	443	<0.4	7	<5	146
928450	Drill Core	0.74	2	<2	<2	<5	<2	<0.5	<2	<2	26	0.04	11	<20	<4	4	4421	<0.4	<5	<5	<2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 6 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928421	Rock Pulp	1.80	0.102	15	24	1.40	728	0.29	7.76	3.08	2.37	4	77	7	14	8	2	13	0.6
928422	Drill Core	2.76	0.135	24	3	1.12	191	0.36	9.14	5.18	2.29	5	97	<2	22	8	2	10	1.2
928423	Drill Core	2.82	0.131	14	3	0.89	407	0.32	8.72	6.52	0.67	5	98	<2	20	8	2	9	1.9
928424	Drill Core	2.14	0.135	13	2	0.92	405	0.33	8.81	6.66	0.69	6	98	<2	21	8	2	8	1.9
928425	Drill Core	2.45	0.133	14	3	1.02	506	0.33	9.03	6.12	0.87	<4	101	<2	21	8	2	9	1.7
928426	Drill Core	2.58	0.147	46	13	1.54	103	0.38	8.84	3.93	3.49	6	108	2	20	8	2	15	2.1
928427	Drill Core	2.30	0.141	44	9	1.54	89	0.36	8.60	4.83	1.77	7	101	<2	21	7	2	13	2.0
928428	Drill Core	1.92	0.151	27	3	1.40	54	0.37	9.12	4.35	2.38	16	116	<2	18	6	2	9	2.3
928429	Drill Core	2.63	0.146	33	6	1.43	52	0.34	9.22	4.75	2.19	15	111	<2	20	5	2	11	3.0
928430	Drill Core	>40	0.004	<2	<2	1.53	16	<0.01	0.08	0.02	0.01	5	<2	<2	<2	<2	<1	<1	<0.1
928431	Drill Core	2.89	0.145	42	9	1.38	83	0.38	8.84	2.94	4.62	10	112	4	17	6	1	14	2.2
928432	Drill Core	2.35	0.141	11	2	0.89	64	0.35	9.77	5.85	1.25	12	94	3	16	6	2	9	2.5
928433	Drill Core	2.89	0.133	10	<2	0.73	80	0.34	8.82	5.80	1.05	7	88	3	17	6	2	8	2.3
928434	Drill Core	3.00	0.130	12	<2	0.88	88	0.34	9.10	5.72	1.12	9	89	<2	17	6	2	8	2.3
928435	Drill Core	3.29	0.129	10	<2	0.80	70	0.34	8.75	5.31	1.28	13	90	<2	17	6	2	8	2.9
928436	Drill Core	2.79	0.137	11	4	0.89	80	0.35	9.65	6.09	0.75	16	93	<2	18	6	2	10	2.5
928437	Drill Core	2.58	0.127	11	<2	0.77	48	0.33	8.62	5.82	0.82	12	89	<2	16	5	2	8	3.4
928438	Drill Core	2.54	0.130	10	<2	0.76	54	0.34	8.96	6.04	0.73	11	91	<2	16	6	1	8	3.8
928439	Drill Core	2.30	0.131	9	2	0.76	79	0.35	8.90	6.23	0.78	8	94	<2	16	6	1	8	2.6
928440	Drill Core	39.75	0.004	<2	<2	1.86	15	<0.01	0.14	0.01	0.01	4	<2	2	<2	<2	<1	<1	<0.1
928441	Drill Core	3.16	0.129	7	2	0.63	90	0.35	8.30	6.26	0.76	9	90	<2	14	6	1	7	2.6
928442	Drill Core	2.90	0.132	11	<2	0.58	80	0.34	8.81	6.23	0.77	7	92	<2	15	6	2	8	2.6
928443	Drill Core	2.09	0.132	12	2	0.66	42	0.32	9.32	5.79	1.35	9	93	2	16	6	2	8	2.8
928444	Drill Core	2.26	0.131	12	4	0.83	51	0.33	9.36	5.17	2.35	11	97	<2	19	5	1	9	3.2
928445	Drill Core	2.31	0.127	13	3	0.76	53	0.33	8.44	5.50	1.53	9	90	<2	17	5	2	9	3.1
928446	Drill Core	2.23	0.130	14	3	0.91	67	0.33	9.06	4.60	3.21	8	98	<2	15	6	1	8	2.7
928447	Drill Core	2.23	0.127	12	<2	0.92	60	0.32	9.10	4.70	3.05	10	96	13	15	6	1	8	2.8
928448	Drill Core	2.98	0.122	11	<2	0.91	35	0.32	8.07	4.75	2.05	17	91	<2	17	6	2	10	5.6
928449	Drill Core	3.10	0.129	14	<2	0.90	59	0.32	8.69	4.66	2.60	13	89	<2	15	6	2	9	3.4
928450	Drill Core	>40	0.003	<2	<2	1.93	10	<0.01	0.10	0.01	<0.01	8	<2	<2	<2	<2	<1	<1	<0.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn

Report Date: October 09, 2009

Page: 7 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000216.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	5	2
928451	Rock Pulp	0.11	309	3	3411	24	68	1.1	14	7	349	3.69	<5	<20	<4	13	169	0.5	<5	8	43
928452	Drill Core	2.52	279	9	228	<5	16	<0.5	<2	13	353	4.41	<5	<20	<4	7	412	<0.4	<5	14	155
928453	Drill Core	4.81	320	14	247	<5	31	<0.5	<2	15	428	4.81	31	<20	<4	8	401	<0.4	5	12	145
928454	Drill Core	4.97	799	4	177	14	41	<0.5	<2	9	496	4.91	58	<20	<4	4	400	0.5	12	<5	145
928455	Drill Core	4.32	374	4	145	<5	16	<0.5	<2	11	380	4.22	<5	<20	<4	8	464	<0.4	<5	6	143
928456	Drill Core	5.31	1000	2	169	<5	18	<0.5	<2	11	360	4.93	<5	<20	<4	8	503	0.5	<5	13	162
928457	Drill Core	4.86	389	4	141	7	16	<0.5	<2	12	503	5.06	9	<20	<4	10	546	<0.4	<5	10	151
928458	Drill Core	2.29	402	9	73	14	16	<0.5	<2	12	468	4.83	5	<20	<4	9	591	<0.4	<5	10	169
928459	Drill Core	5.29	611	<2	187	17	27	<0.5	<2	17	508	6.84	10	<20	<4	8	407	0.4	<5	13	213
928460	Drill Core	0.81	<2	<2	<2	<5	<2	<0.5	<2	<2	27	0.05	6	<20	<4	<2	4212	<0.4	<5	<5	<2
928461	Drill Core	4.71	160	<2	122	7	27	<0.5	<2	21	536	6.06	13	24	<4	7	470	<0.4	5	10	221
928462	Drill Core	4.83	87	<2	40	8	23	<0.5	<2	18	669	5.86	6	<20	<4	6	623	<0.4	<5	16	223
928463	Drill Core	5.55	170	<2	66	6	30	0.6	<2	18	597	5.79	12	<20	<4	7	658	<0.4	<5	<5	232
928464	Drill Core	4.90	159	<2	96	7	32	<0.5	2	20	601	5.85	10	<20	<4	8	688	<0.4	<5	<5	240
928465	Drill Core	4.95	362	<2	211	8	42	0.9	6	23	708	7.90	10	<20	<4	8	482	<0.4	<5	7	264
928466	Drill Core	5.15	375	<2	179	12	36	0.6	<2	23	544	7.89	16	<20	<4	7	524	<0.4	<5	6	221
928467	Drill Core	4.21	680	<2	275	13	36	1.5	<2	21	574	8.53	16	<20	<4	8	503	0.6	<5	6	214
928468	Drill Core	4.90	234	25	135	10	27	<0.5	2	22	468	6.82	8	<20	<4	7	546	<0.4	<5	<5	153
928469	Drill Core	4.66	138	8	103	<5	23	<0.5	2	8	402	3.96	9	<20	<4	8	532	<0.4	<5	<5	162
928470	Drill Core	0.63	<2	<2	<2	<5	<2	<0.5	<2	<2	22	0.05	<5	<20	<4	<2	3939	<0.4	<5	<5	<2
928471	Drill Core	2.77	11	<2	103	8	31	0.6	3	14	349	3.33	11	<20	<4	10	499	<0.4	<5	<5	166
928472	Drill Core	3.39	24	<2	115	8	31	<0.5	3	10	408	3.20	11	<20	<4	9	478	<0.4	<5	<5	163
928473	Drill Core	3.72	198	<2	96	11	48	1.0	4	14	743	5.21	11	<20	<4	9	432	<0.4	<5	<5	187
928474	Drill Core	5.44	11	5	79	5	52	<0.5	2	12	890	4.52	12	<20	<4	11	493	<0.4	<5	<5	191
928475	Drill Core	4.61	21	2	76	<5	163	<0.5	<2	11	1028	4.48	50	<20	<4	12	490	1.1	<5	8	184
928476	Drill Core	4.88	163	3	103	11	49	0.7	2	12	958	4.91	11	<20	<4	9	466	0.4	<5	<5	177
928477	Drill Core	3.46	2086	3	237	28	345	2.0	<2	15	1407	7.10	72	<20	<4	8	434	2.9	5	8	165
928478	Drill Core	3.73	46	<2	65	23	126	<0.5	16	12	1435	4.32	7	<20	<4	6	432	0.9	<5	<5	187
928479	Drill Core	4.25	30	9	73	24	194	0.8	57	13	1353	4.10	25	<20	<4	<2	578	1.7	20	<5	261
928480	Drill Core	1.06	<2	<2	6	<5	<2	<0.5	<2	<2	41	0.10	<5	<20	<4	<2	3887	<0.4	<5	<5	2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 7 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928451	Rock Pulp	1.21	0.044	26	16	0.53	817	0.16	7.00	2.48	3.71	<4	56	7	13	9	2	6	0.3
928452	Drill Core	1.69	0.137	16	<2	1.04	36	0.34	9.50	4.81	2.82	12	92	<2	15	6	2	9	2.9
928453	Drill Core	2.66	0.126	12	<2	0.91	46	0.31	8.74	4.43	2.79	19	93	<2	19	6	1	10	3.7
928454	Drill Core	3.05	0.125	13	<2	0.79	52	0.31	8.64	3.91	3.40	10	102	3	17	6	2	8	3.8
928455	Drill Core	2.68	0.129	18	<2	0.71	58	0.31	9.28	4.46	3.09	7	94	<2	16	5	2	7	2.8
928456	Drill Core	2.32	0.133	13	<2	0.93	50	0.35	9.24	5.19	2.23	6	96	<2	18	6	2	9	3.3
928457	Drill Core	2.97	0.129	16	2	0.96	57	0.32	9.18	5.61	1.27	14	94	<2	21	6	2	9	3.5
928458	Drill Core	2.93	0.131	14	<2	0.92	63	0.32	9.31	5.92	0.96	9	97	5	18	6	2	10	3.2
928459	Drill Core	2.72	0.164	15	<2	1.57	51	0.39	9.04	2.87	4.00	9	79	<2	18	5	2	11	3.6
928460	Drill Core	>40	0.005	<2	<2	1.79	15	<0.01	0.10	0.01	0.01	6	<2	<2	<2	<2	<1	<1	<0.1
928461	Drill Core	3.48	0.163	16	<2	1.41	55	0.40	9.59	2.87	4.46	6	86	<2	20	5	2	14	3.3
928462	Drill Core	3.97	0.169	17	<2	1.41	61	0.42	9.55	2.80	4.07	8	81	<2	21	5	1	13	3.0
928463	Drill Core	3.82	0.152	20	<2	1.37	75	0.41	8.83	3.01	3.71	<4	79	<2	21	7	2	13	3.2
928464	Drill Core	4.00	0.163	23	2	1.47	77	0.40	9.22	3.25	3.86	5	85	<2	24	7	2	15	3.2
928465	Drill Core	3.86	0.177	19	2	1.96	63	0.44	8.53	2.51	3.92	5	74	<2	20	6	1	19	4.5
928466	Drill Core	3.30	0.148	17	4	1.44	54	0.38	8.57	2.54	4.39	6	73	<2	18	6	1	13	5.5
928467	Drill Core	3.48	0.160	19	<2	1.36	124	0.38	8.60	2.39	4.77	5	74	<2	21	6	1	13	6.2
928468	Drill Core	3.07	0.127	15	3	0.98	39	0.34	8.41	5.50	1.06	<4	95	<2	16	7	2	9	5.3
928469	Drill Core	3.00	0.133	18	3	0.92	91	0.35	8.89	6.21	1.04	<4	104	<2	17	9	2	10	2.4
928470	Drill Core	38.84	0.004	<2	<2	1.72	9	<0.01	0.05	0.02	<0.01	<4	<2	<2	<2	<1	<1	<0.1	
928471	Drill Core	2.54	0.135	59	2	0.95	112	0.34	8.79	5.07	2.62	5	107	<2	15	8	2	9	2.2
928472	Drill Core	2.87	0.131	40	2	0.85	124	0.34	8.98	4.80	2.94	7	111	<2	15	8	2	9	1.9
928473	Drill Core	3.32	0.144	25	4	1.20	87	0.36	8.74	3.12	3.61	5	114	<2	17	7	2	10	2.4
928474	Drill Core	2.86	0.152	29	3	1.39	538	0.36	9.02	3.49	3.54	<4	122	<2	16	8	2	10	0.7
928475	Drill Core	3.75	0.143	30	<2	1.36	855	0.35	8.97	3.30	3.52	<4	121	<2	18	8	2	9	0.7
928476	Drill Core	3.45	0.144	26	3	1.26	120	0.34	8.77	3.33	3.17	<4	114	<2	19	7	2	9	1.8
928477	Drill Core	5.73	0.122	28	<2	0.95	85	0.28	7.92	2.59	3.09	6	93	<2	19	6	2	9	4.6
928478	Drill Core	7.47	0.126	22	26	1.52	441	0.35	7.85	1.35	2.95	<4	70	<2	16	6	2	12	1.0
928479	Drill Core	8.62	0.214	11	105	1.48	396	0.29	5.39	0.40	1.86	<4	42	<2	16	4	1	13	1.3
928480	Drill Core	39.09	0.004	<2	<2	1.74	22	<0.01	0.18	0.02	0.02	<4	<2	<2	<2	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 8 of 8 Part 1

CERTIFICATE OF ANALYSIS

SMI09000216.1

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Bi	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	5	0.01	5	20	4	2	2	0.4	5	
928481	Rock Pulp	0.10	625	3	5480	11	68	1.9	17	14	460	5.47	8	<20	<4	5	458	<0.4	<5	<5 136
928482	Drill Core	5.27	15	2	109	15	137	1.1	38	20	1110	5.54	13	<20	<4	<2	269	0.9	<5	<5 239
928483	Drill Core	4.66	34	<2	106	19	117	1.1	34	21	1392	5.51	48	<20	<4	<2	342	0.8	7	<5 237
928484	Drill Core	5.02	18	<2	65	14	156	0.7	25	14	1148	4.98	24	<20	<4	<2	327	0.5	5	<5 198
928485	Drill Core	4.40	29	<2	38	24	210	0.9	14	19	1519	4.56	22	<20	<4	2	280	1.4	<5	<5 190
928486	Drill Core	4.53	21	<2	18	35	258	0.7	3	14	1763	4.24	10	<20	<4	2	359	1.6	6	<5 127
928487	Drill Core	5.11	17	6	18	16	127	<0.5	5	7	3229	3.23	8	<20	<4	2	400	1.0	<5	<5 85
928488	Drill Core	4.41	10	<2	16	19	129	<0.5	<2	7	2383	3.64	<5	<20	<4	3	464	0.8	<5	6 99
928489	Drill Core	4.47	2	<2	9	<5	99	<0.5	<2	10	1903	4.67	<5	<20	<4	4	552	<0.4	<5	<5 157
928490	Drill Core	0.77	<2	<2	<2	<5	<2	<0.5	<2	<2	29	0.03	<5	<20	<4	<2	3737	<0.4	<5	<5 <2
928491	Drill Core	4.00	3	<2	12	8	101	<0.5	<2	11	1477	4.51	<5	<20	<4	4	477	0.5	<5	<5 159
928492	Drill Core	4.72	2	<2	32	10	111	<0.5	<2	15	1144	5.02	<5	<20	<4	3	492	0.5	<5	<5 191
928493	Drill Core	5.04	7	<2	31	6	115	<0.5	<2	15	1402	5.17	<5	<20	<4	4	562	<0.4	<5	5 207
928494	Drill Core	3.31	3	<2	59	6	94	<0.5	4	20	1329	5.55	<5	<20	<4	3	591	<0.4	<5	<5 194
928495	Drill Core	3.27	6	<2	77	<5	105	<0.5	5	22	1234	6.02	7	<20	<4	3	595	0.5	<5	6 221
928496	Drill Core	5.12	2	<2	68	<5	93	<0.5	4	19	1357	5.72	<5	<20	<4	<2	544	<0.4	<5	<5 205
928497	Drill Core	4.37	<2	<2	48	<5	105	<0.5	4	18	1411	5.62	<5	<20	<4	3	530	0.6	<5	7 193
928498	Drill Core	4.76	<2	<2	56	<5	88	<0.5	5	20	1898	5.41	<5	<20	<4	<2	587	<0.4	<5	<5 187
928499	Drill Core	2.35	<2	<2	75	<5	85	<0.5	6	20	1844	5.42	<5	<20	<4	<2	696	<0.4	<5	<5 208
928500	Drill Core	0.84	<2	<2	<2	<5	3	<0.5	<2	<2	75	0.16	<5	<20	<4	<2	3808	<0.4	<5	<5 4



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 8 of 8 Part 2

CERTIFICATE OF ANALYSIS

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
928481	Rock Pulp	1.79	0.101	16	24	1.40	731	0.28	7.75	3.09	3.13	5	77	5	14	8	2	13	0.6
928482	Drill Core	3.64	0.104	10	52	2.39	521	0.52	8.04	1.29	2.02	<4	32	<2	12	7	1	19	1.1
928483	Drill Core	4.99	0.110	10	48	2.59	640	0.54	8.04	1.63	1.76	<4	43	<2	14	7	1	19	0.9
928484	Drill Core	3.36	0.110	13	38	1.69	994	0.45	8.49	1.32	2.36	<4	38	<2	13	7	2	16	0.8
928485	Drill Core	4.09	0.147	16	22	1.30	734	0.53	8.48	1.68	2.16	<4	54	<2	19	10	2	15	0.8
928486	Drill Core	4.67	0.150	15	3	1.12	725	0.49	8.49	1.48	2.08	<4	62	<2	16	11	2	11	0.9
928487	Drill Core	11.43	0.131	20	4	0.87	571	0.32	7.27	1.21	1.73	<4	67	<2	23	8	1	7	0.5
928488	Drill Core	6.84	0.150	18	<2	0.92	1131	0.38	8.33	2.21	2.29	<4	88	<2	21	9	1	8	0.7
928489	Drill Core	5.65	0.193	20	<2	1.48	1314	0.59	8.77	2.73	2.55	<4	67	<2	23	12	1	13	0.1
928490	Drill Core	38.08	0.003	<2	<2	1.78	9	<0.01	0.06	<0.01	<0.01	<4	<2	<2	<2	2	<1	<1	<0.1
928491	Drill Core	4.45	0.184	18	<2	1.38	1727	0.57	8.93	2.85	2.10	<4	72	<2	21	11	1	13	0.3
928492	Drill Core	3.13	0.200	16	<2	1.49	2361	0.65	8.63	2.71	2.34	<4	67	<2	20	12	2	15	<0.1
928493	Drill Core	4.44	0.181	18	<2	1.47	1931	0.68	8.94	3.43	1.79	<4	76	<2	23	11	1	17	<0.1
928494	Drill Core	2.97	0.157	14	<2	2.64	2560	0.52	9.05	2.77	3.27	<4	65	<2	18	9	1	12	0.6
928495	Drill Core	1.92	0.175	14	<2	3.69	4231	0.57	9.12	1.50	3.11	<4	42	<2	17	9	1	15	0.2
928496	Drill Core	2.84	0.166	13	<2	3.14	2940	0.56	8.75	1.41	4.72	<4	38	<2	18	8	1	13	0.5
928497	Drill Core	2.81	0.159	14	<2	2.97	4259	0.50	9.03	2.05	2.79	<4	59	<2	19	9	1	12	0.2
928498	Drill Core	5.88	0.148	14	2	2.69	3250	0.49	8.21	1.72	3.52	<4	34	<2	19	8	1	13	<0.1
928499	Drill Core	5.16	0.145	15	3	2.36	2566	0.51	8.35	2.33	2.95	<4	42	<2	19	8	1	16	<0.1
928500	Drill Core	37.32	0.005	<2	<2	1.51	50	<0.01	0.27	0.02	0.04	<4	<2	<2	<2	<1	<1	<0.1	



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 09, 2009

Page:

1 of 4 Part 1

QUALITY CONTROL REPORT

SMI09000216.1

	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi			
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
	MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	5	2	
Pulp Duplicates																							
928308	Drill Core	2.41	162	10	1221	14	58	0.7	4	30	524	4.66	8	<20	<4	9	519	1.0	<5	<5	<5	222	
REP 928308	QC		180																				
928311	Drill Core	3.43	129	16	899	8	26	0.5	3	29	400	3.95	<5	<20	<4	10	527	0.5	<5	<5	<5	246	
REP 928311	QC			17	887	7	26	0.5	3	31	402	4.00	<5	<20	<4	12	545	0.5	<5	<5	<5	245	
928353	Drill Core	4.98	319	9	1287	5	18	1.2	6	13	367	3.16	9	<20	<4	6	439	<0.4	<5	<5	<5	192	
REP 928353	QC			8	1313	5	18	1.6	6	13	373	3.24	8	<20	<4	5	439	<0.4	<5	<5	<5	194	
928366	Drill Core	4.93	82	12	412	7	12	<0.5	35	13	433	3.09	7	<20	<4	<2	332	<0.4	<5	<5	<5	157	
REP 928366	QC		81																				
928375	Drill Core	4.34	599	13	944	8	16	<0.5	25	13	319	4.02	<5	<20	<4	7	340	0.4	<5	<5	<5	229	
REP 928375	QC		582																				
928388	Drill Core	5.03	192	20	353	7	11	<0.5	3	9	262	2.52	<5	<20	<4	8	418	<0.4	<5	<5	<5	145	
REP 928388	QC			18	345	6	10	<0.5	3	9	259	2.47	6	<20	<4	9	413	<0.4	<5	<5	<5	143	
928394	Drill Core	5.12	92	12	507	<5	18	0.6	3	16	382	2.95	<5	<20	<4	7	571	<0.4	<5	7	<5	186	
REP 928394	QC				12	508	5	18	0.6	3	16	390	3.04	<5	<20	<4	9	609	<0.4	<5	<5	<5	188
928402	Drill Core	4.57	92	19	427	11	19	0.8	3	18	247	4.51	12	<20	<4	8	617	0.4	<5	<5	<5	237	
REP 928402	QC		94																				
928441	Drill Core	5.47	66	5	191	<5	15	<0.5	<2	12	444	3.75	<5	<20	<4	6	441	<0.4	<5	9	146		
REP 928441	QC			5	191	<5	14	<0.5	<2	12	445	3.75	<5	<20	<4	4	406	<0.4	<5	12	146		
928458	Drill Core	2.29	402	9	73	14	16	<0.5	<2	12	468	4.83	5	<20	<4	9	591	<0.4	<5	10	169		
REP 928458	QC		368																				
928466	Drill Core	5.15	375	<2	179	12	36	0.6	<2	23	544	7.89	16	<20	<4	7	524	<0.4	<5	6	221		
REP 928466	QC			<2	187	9	36	0.9	2	23	559	8.03	14	<20	<4	7	541	0.4	<5	<5	<5	227	
REP 928497	QC		<2																				
928500	Drill Core	0.84	<2	<2	<2	<5	3	<0.5	<2	<2	75	0.16	<5	<20	<4	<2	3808	<0.4	<5	<5	4		
REP 928500	QC			<2	<2	<5	4	<0.5	<2	<2	63	0.15	<5	<20	<4	<2	3837	<0.4	<5	<5	4		
Core Reject Duplicates																							
928322	Drill Core	4.85	176	4	1200	<5	41	1.1	3	13	674	3.19	<5	<20	<4	6	466	0.5	<5	<5	<5	243	
DUP 928322	QC		147	4	1220	7	48	1.6	2	14	697	3.40	<5	<20	<4	8	506	0.5	<5	6	258		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 09, 2009

www.acmelab.com

Page:

1 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000216.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
Pulp Duplicates																			
928308	Drill Core	0.71	0.170	22	3	1.22	839	0.36	8.44	5.25	1.99	5	57	<2	23	7	2	10	1.7
REP 928308	QC																		
928311	Drill Core	2.76	0.153	33	4	1.06	1041	0.38	8.72	5.37	1.67	7	60	<2	20	7	2	11	1.7
REP 928311	QC	2.83	0.157	37	4	1.08	961	0.37	8.99	5.35	1.72	<4	60	2	21	7	2	11	1.7
928353	Drill Core	1.75	0.144	15	3	0.62	257	0.36	7.55	5.77	1.62	6	71	<2	13	8	1	8	1.5
REP 928353	QC	1.77	0.145	15	5	0.64	342	0.36	7.59	5.83	1.64	6	72	<2	14	8	1	8	1.6
928366	Drill Core	3.12	0.117	14	32	1.12	303	0.35	7.73	5.33	0.58	<4	37	<2	21	4	<1	11	1.6
REP 928366	QC																		
928375	Drill Core	2.04	0.119	36	25	1.51	357	0.35	7.77	4.66	0.74	<4	57	<2	21	5	1	13	0.9
REP 928375	QC																		
928388	Drill Core	2.69	0.126	14	5	1.01	306	0.31	8.19	5.75	0.63	7	91	<2	19	6	2	8	1.2
REP 928388	QC	2.68	0.126	14	2	1.00	302	0.31	8.13	5.79	0.62	<4	90	<2	19	7	2	8	1.2
928394	Drill Core	3.88	0.141	17	4	0.64	252	0.39	8.55	6.48	0.71	4	115	3	21	9	2	9	0.9
REP 928394	QC	4.02	0.140	20	2	0.66	260	0.39	9.29	6.47	0.74	<4	119	2	23	9	2	10	0.9
928402	Drill Core	2.13	0.183	40	3	0.88	133	0.45	9.22	5.92	1.29	6	110	<2	19	9	2	11	3.6
REP 928402	QC																		
928441	Drill Core	3.16	0.129	7	2	0.63	90	0.35	8.30	6.26	0.76	9	90	<2	14	6	1	7	2.6
REP 928441	QC	3.23	0.127	7	<2	0.63	94	0.34	7.64	6.08	0.76	9	92	<2	14	7	1	7	2.6
928458	Drill Core	2.93	0.131	14	<2	0.92	63	0.32	9.31	5.92	0.96	9	97	5	18	6	2	10	3.2
REP 928458	QC																		
928466	Drill Core	3.30	0.148	17	4	1.44	54	0.38	8.57	2.54	4.39	6	73	<2	18	6	1	13	5.5
REP 928466	QC	3.41	0.151	18	2	1.50	61	0.40	8.85	2.63	4.51	7	76	<2	19	7	1	14	5.6
REP 928497	QC																		
928500	Drill Core	37.32	0.005	<2	<2	1.51	50	<0.01	0.27	0.02	0.04	<4	<2	<2	<2	<1	<1	<0.1	
REP 928500	QC	37.39	0.006	<2	<2	1.54	48	<0.01	0.19	0.02	0.05	<4	<2	<2	<2	<1	<1	<0.1	
Core Reject Duplicates																			
928322	Drill Core	4.02	0.131	19	4	0.86	872	0.34	7.84	3.15	3.25	5	40	3	15	6	1	11	1.5
DUP 928322	QC	4.03	0.146	21	4	0.92	165	0.38	8.62	3.33	4.11	5	47	3	15	9	1	13	1.5



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunc

Report Date

October 09, 2009

www.acmelab.com

Page:

2 of 4 Part

QUALITY CONTROL REPORT

SMI09000216.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 09, 2009

Page:

2 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000216.1

		1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S
		% 0.01	% 0.002	ppm 2	ppm 2	% 0.01	ppm 1	% 0.01	ppm 0.01	% 0.01	ppm 4	ppm 2	ppm 2	ppm 2	ppm 2	ppm 1	ppm 1	% 0.1	
928357	Drill Core	2.17	0.181	17	5	1.18	267	0.32	7.86	5.45	0.56	6	51	<2	22	8	1	7	1.8
DUP 928357	QC	1.88	0.160	14	3	1.13	284	0.30	7.75	5.30	0.53	6	44	<2	20	6	1	6	1.6
928392	Drill Core	3.96	0.119	9	2	0.66	223	0.32	7.58	5.75	0.66	6	89	<2	15	6	1	8	3.2
DUP 928392	QC	4.07	0.127	10	3	0.69	216	0.35	7.40	6.17	0.66	6	103	<2	15	9	2	8	3.1
928427	Drill Core	2.30	0.141	44	9	1.54	89	0.36	8.60	4.83	1.77	7	101	<2	21	7	2	13	2.0
DUP 928427	QC	2.03	0.144	40	7	1.53	54	0.36	8.72	4.90	1.75	9	103	<2	20	5	2	13	1.8
928462	Drill Core	3.97	0.169	17	<2	1.41	61	0.42	9.55	2.80	4.07	8	81	<2	21	5	1	13	3.0
DUP 928462	QC	4.02	0.170	25	<2	1.44	76	0.42	9.26	2.86	4.11	<4	85	<2	25	7	2	14	3.0
928497	Drill Core	2.81	0.159	14	<2	2.97	4259	0.50	9.03	2.05	2.79	<4	59	<2	19	9	1	12	0.2
DUP 928497	QC	2.62	0.151	13	<2	2.86	4042	0.48	8.87	1.95	3.64	<4	52	<2	18	9	1	12	0.2
Reference Materials																			
STD OREAS24P	Standard	5.77	0.133	18	209	4.05	277	1.04	8.10	2.39	0.72	<4	151	<2	23	22	1	20	<0.1
STD OREAS24P	Standard	6.00	0.137	20	226	4.09	291	1.10	8.01	2.45	0.73	<4	154	<2	23	26	1	21	<0.1
STD OREAS24P	Standard	6.04	0.138	20	225	4.18	292	1.05	8.01	2.49	0.72	<4	152	<2	23	25	1	21	<0.1
STD OREAS24P	Standard	5.48	0.128	17	199	3.88	269	1.00	7.66	2.29	0.68	<4	142	<2	22	20	1	19	<0.1
STD OREAS24P	Standard	6.13	0.137	20	195	4.13	296	1.11	8.12	2.43	0.74	<4	154	<2	22	26	1	21	<0.1
STD OREAS24P	Standard	5.87	0.135	18	214	4.00	280	1.05	7.97	2.33	0.69	5	146	<2	22	20	1	20	<0.1
STD OREAS24P	Standard	5.85	0.130	19	200	3.97	283	1.05	7.67	2.28	0.69	<4	143	<2	22	23	1	20	<0.1
STD OREAS45P	Standard	0.29	0.045	25	1116	0.20	293	1.03	7.08	0.07	0.36	5	172	7	14	23	<1	69	<0.1
STD OREAS45P	Standard	0.31	0.046	28	1136	0.19	305	1.11	7.15	0.08	0.36	<4	173	<2	14	25	1	69	<0.1
STD OREAS45P	Standard	0.30	0.046	28	1129	0.19	303	1.08	6.96	0.09	0.36	<4	172	3	14	24	1	69	<0.1
STD OREAS45P	Standard	0.28	0.044	24	1083	0.19	286	1.03	7.07	0.07	0.35	<4	160	<2	14	21	<1	67	<0.1
STD OREAS45P	Standard	0.29	0.045	28	1108	0.19	295	1.05	7.04	0.09	0.36	<4	172	2	14	25	1	69	<0.1
STD OREAS45P	Standard	0.29	0.047	25	1109	0.19	310	1.04	7.16	0.07	0.36	8	164	7	13	21	1	69	<0.1
STD OREAS45P	Standard	0.28	0.045	28	1053	0.18	300	0.99	6.97	0.08	0.36	<4	159	4	13	22	1	69	<0.1
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Durn

Report Date:

October 09, 2009

www.acmelab.com

Page:

3 of 4 Part

QUALITY CONTROL REPORT

SMI09000216.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 3 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000216.1

		1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
		%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
		0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
STD OXH55	Standard																		
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	<0.1
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<										



AcmeLabs

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project

Mt. Dunn

Report Date:

October 09, 2009

www.acmelab.com

Page:

4 of 4 Part

QUALITY CONTROL REPORT

SMI09000216.1

	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		
Prep Wash																				
G1	Prep Blank	<2	<2	<2	23	56	<0.5	4	4	761	2.37	<5	<20	<4	6	695	0.4	<5	8	55
G1	Prep Blank	<2	<2	<2	20	58	<0.5	5	5	763	2.32	<5	<20	<4	5	705	<0.4	<5	5	54



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 4 of 4 Part 2

QUALITY CONTROL REPORT

SMI09000216.1

		1E Ca	1E P	1E La	1E Cr	1E Mg	1E Ba	1E Ti	1E Al	1E Na	1E K	1E W	1E Zr	1E Sn	1E Y	1E Nb	1E Be	1E Sc	1E S
		% 0.01	% 0.002	ppm 2	ppm 2	% 0.01	ppm 1	% 0.01	% 0.01	% 0.01	% 0.01	ppm 4	ppm 2	ppm 2	ppm 2	ppm 2	ppm 1	ppm 1	% 0.1
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
G1	Prep Blank	2.43	0.089	20	10	0.68	1030	0.26	7.46	2.68	1.83	<4	9	<2	15	25	3	6	<0.1
G1	Prep Blank	2.42	0.087	17	9	0.69	1084	0.28	7.52	2.67	2.31	<4	9	<2	15	25	3	5	<0.1



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 11, 2009
Report Date: October 07, 2009
Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI09000217.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 21

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200	21	Crush split and pulverize drill core to 200 mesh			VAN
3B	21	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	21	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL


STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC: Nigel Luckman
B. Booth



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.
** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 07, 2009

www.acmelab.com

Page: 2 of 2 Part 1

SMI09000217.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	2	0.01	5	20	4	2	2	0.4	5	5	2
926953	Drill Core	3.31	17	4	64	51	290	<0.5	5	9	1104	3.71	10	<20	<4	9	209	1.5	<5	<5	127
926954	Drill Core	3.44	132	6	375	11	32	<0.5	3	13	549	4.45	28	<20	<4	9	367	<0.4	<5	<5	209
926955	Drill Core	2.47	131	4	332	5	18	<0.5	2	10	675	3.58	9	<20	<4	10	440	<0.4	<5	<5	151
926956	Drill Core	3.29	230	3	599	11	21	<0.5	3	28	417	4.27	10	<20	<4	10	485	<0.4	<5	<5	200
926957	Drill Core	3.34	328	<2	714	13	40	<0.5	3	19	503	3.37	<5	<20	<4	11	802	<0.4	<5	<5	226
926958	Drill Core	3.69	311	4	786	12	25	0.7	3	24	823	3.87	7	<20	<4	9	749	<0.4	<5	<5	231
926959	Drill Core	3.83	624	2	1449	8	24	1.0	3	26	489	4.13	6	<20	<4	10	890	<0.4	<5	<5	219
926960	Drill Core	3.65	279	6	671	14	15	<0.5	2	29	442	3.67	8	<20	<4	11	815	<0.4	<5	<5	185
926961	Drill Core	3.85	53	<2	56	6	40	<0.5	8	14	763	4.44	<5	<20	<4	9	739	<0.4	<5	<5	161
926962	Drill Core	2.46	6	<2	38	<5	67	<0.5	25	21	1251	4.90	<5	<20	<4	3	576	0.5	<5	<5	175
926963	Drill Core	2.51	82	<2	104	<5	26	<0.5	3	9	627	3.62	<5	<20	<4	12	530	<0.4	<5	<5	131
926964	Drill Core	2.26	614	3	1177	<5	22	1.1	3	24	495	4.74	11	<20	<4	10	560	<0.4	<5	<5	216
926965	Drill Core	4.91	651	6	1052	7	15	0.8	4	18	494	4.01	12	<20	<4	11	617	<0.4	<5	<5	251
926966	Drill Core	3.11	311	3	906	10	15	0.7	4	20	638	3.76	<5	<20	<4	10	589	<0.4	<5	<5	235
926967	Drill Core	2.60	150	<2	522	9	40	<0.5	72	32	969	5.87	22	<20	<4	7	384	0.5	<5	<5	246
926968	Drill Core	2.12	206	<2	615	13	28	<0.5	40	29	927	5.22	14	<20	<4	6	360	<0.4	6	<5	275
926969	Drill Core	6.26	4	<2	73	<5	34	<0.5	96	24	3710	4.24	10	<20	<4	<2	530	0.8	<5	<5	138
926970	Drill Core	2.42	11	<2	190	<5	44	<0.5	129	30	2377	6.18	12	<20	<4	<2	283	0.6	<5	<5	199
926971	Drill Core	3.32	63	8	653	6	24	<0.5	48	15	1150	4.23	9	<20	<4	11	311	0.5	<5	<5	180
926972	Drill Core	3.42	78	14	680	<5	13	<0.5	5	10	1416	3.46	7	<20	<4	10	383	<0.4	<5	<5	139
926973	Drill Core	3.43	45	22	670	<5	22	<0.5	28	15	1397	4.09	<5	<20	<4	9	323	<0.4	<5	<5	166



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 07, 2009

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

SMI09000217.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1	
926953	Drill Core	3.19	0.131	20	11	1.49	639	0.35	8.35	1.34	3.20	4	102	2	16	10	2	9	0.8
926954	Drill Core	2.76	0.166	26	4	1.00	52	0.39	9.52	4.21	2.35	13	56	5	17	6	1	13	3.4
926955	Drill Core	4.59	0.115	26	2	0.62	74	0.29	9.07	4.26	3.10	6	67	<2	17	6	1	8	2.7
926956	Drill Core	2.94	0.156	25	<2	0.66	52	0.37	9.84	4.44	2.89	<4	94	4	14	7	2	11	3.7
926957	Drill Core	3.59	0.175	55	3	0.74	189	0.43	9.84	5.16	1.71	6	97	4	17	7	2	12	2.6
926958	Drill Core	5.61	0.166	34	3	0.80	271	0.37	9.21	4.71	1.39	6	61	3	19	6	2	13	3.0
926959	Drill Core	3.86	0.168	35	4	0.72	159	0.39	9.72	5.22	1.43	8	58	<2	19	6	2	13	3.6
926960	Drill Core	3.39	0.149	26	<2	0.50	56	0.34	9.90	5.15	2.12	6	81	4	17	6	2	10	3.4
926961	Drill Core	3.31	0.130	23	16	1.40	105	0.40	9.77	3.66	3.27	4	88	<2	20	8	1	11	1.8
926962	Drill Core	3.48	0.154	17	46	2.65	1662	0.55	9.77	3.67	2.09	7	63	<2	18	9	<1	19	0.3
926963	Drill Core	3.24	0.100	26	4	0.92	92	0.29	9.59	3.05	4.67	<4	101	<2	20	7	1	6	1.8
926964	Drill Core	2.65	0.159	27	3	0.77	43	0.34	9.57	5.43	1.20	5	57	5	19	5	1	12	3.5
926965	Drill Core	3.67	0.188	32	4	0.56	178	0.39	9.58	5.59	1.24	6	43	4	18	6	1	13	3.5
926966	Drill Core	4.89	0.177	29	4	0.54	255	0.36	9.16	5.49	1.09	<4	40	2	19	5	1	12	3.1
926967	Drill Core	3.65	0.135	22	66	2.13	99	0.51	8.83	4.17	1.22	5	46	<2	18	5	1	20	2.5
926968	Drill Core	5.29	0.114	31	34	1.18	149	0.40	8.18	4.16	1.09	8	46	4	19	4	1	15	3.5
926969	Drill Core	23.96	0.024	11	86	1.86	115	0.40	4.45	0.71	0.61	5	17	2	19	<2	<1	16	0.1
926970	Drill Core	13.51	0.041	16	124	2.92	287	0.46	6.60	1.16	0.89	4	26	<2	20	2	<1	20	0.3
926971	Drill Core	5.73	0.103	27	44	1.52	588	0.36	8.52	3.39	2.15	4	55	<2	18	6	<1	12	1.1
926972	Drill Core	10.62	0.099	29	3	0.65	205	0.26	7.35	2.51	2.90	6	54	<2	19	6	<1	8	2.1
926973	Drill Core	8.61	0.095	21	27	1.25	166	0.34	7.69	2.62	2.52	<4	50	<2	16	6	<1	10	1.6



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 07, 2009

Page:

1 of 1 Part 1

QUALITY CONTROL REPORT

SMI09000217.1

	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	V	
	Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi		
	Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
	MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2	
Core Reject Duplicates																						
926962	Drill Core	2.46	6	<2	38	<5	67	<0.5	25	21	1251	4.90	<5	<20	<4	3	576	0.5	<5	<5	175	
DUP 926962	QC		3	<2	35	6	67	<0.5	25	20	1270	4.89	<5	<20	<4	3	568	<0.4	<5	<5	171	
Reference Materials																						
STD OREAS24P	Standard			<2	46	6	118	<0.5	140	42	1083	7.51	<5	<20	<4	3	384	0.8	<5	<5	158	
STD OREAS45P	Standard			<2	741	14	156	<0.5	392	121	1324	20.03	11	<20	<4	11	33	<0.4	<5	<5	274	
STD OXE56	Standard				638																	
STD OXE56	Standard				601																	
STD OXH55	Standard				1311																	
STD OXH55	Standard				1302																	
STD OREAS24P Expected				1.5	52	2.9	119	0.06	141	44	1100	7.53	1.2	0.75		2.85	403	0.15	0.09		158	
STD OREAS45P Expected				2.1	749	22	141	0.32	385	120	1338	19.22	12	2.4	0.055	9.8	32.6	0.2	0.82	0.21	267	
STD OXE56 Expected				611																		
STD OXH55 Expected				1282																		
BLK	Blank			<2	<2	<5	<2	<0.5	<2	<2	<5	<0.01	<5	<20	<4	<2	<2	<0.4	<5	<5	<2	
BLK	Blank			<2																		
BLK	Blank			<2																		
BLK	Blank			<2																		
Prep Wash																						
G1	Prep Blank			<2	<2	<2	17	54	<0.5	4	4	741	2.34	<5	<20	<4	8	750	<0.4	<5	<5	53
G1	Prep Blank			<2	<2	2	15	52	<0.5	4	4	717	2.27	<5	<20	<4	7	746	<0.4	<5	<5	51



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 07, 2009

Page: 1 of 1 **Part** 2

QUALITY CONTROL REPORT

SMI09000217.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	4	2	2	2	2	1	1	0.1	
Core Reject Duplicates																		
926962	Drill Core	3.48	0.154	17	46	2.65	1662	0.55	9.77	3.67	2.09	7	63	<2	18	9	<1	
DUP 926962	QC	3.55	0.152	17	46	2.63	1617	0.54	9.93	3.70	2.08	6	62	2	18	9	<1	
Reference Materials																		
STD OREAS24P	Standard	5.60	0.133	18	191	4.03	282	1.04	8.14	2.33	0.69	<4	144	<2	22	19	1	
STD OREAS45P	Standard	0.30	0.047	25	1079	0.20	297	1.00	7.22	0.07	0.36	5	161	5	14	19	<1	
STD OXE56	Standard																	
STD OXE56	Standard																	
STD OXH55	Standard																	
STD OXH55	Standard																	
STD OREAS24P Expected		5.83	0.136	17.4	196	4.13	285	1.1	7.66	2.34	0.7	0.5	141	1.6	21.3	21	20	
STD OREAS45P Expected		0.3	0.047	24.8	1089	0.1962	296	1.037	6.82	0.081	0.35	1.1	154	2.5	13	21.6	67	0.03
STD OXE56 Expected																		
STD OXH55 Expected																		
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<1	<0.1	
BLK	Blank																	
BLK	Blank																	
BLK	Blank																	
BLK	Blank																	
Prep Wash																		
G1	Prep Blank	2.59	0.082	23	6	0.68	1050	0.24	8.30	2.63	2.43	<4	8	2	14	21	3	
G1	Prep Blank	2.51	0.079	24	7	0.65	1027	0.23	8.19	2.63	2.68	<4	7	2	13	20	3	
																	<0.1	



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Submitted By: John Bradford
Receiving Lab: Canada-Smithers
Received: September 12, 2009
Report Date: October 09, 2009
Page: 1 of 2

CERTIFICATE OF ANALYSIS

SMI09000220.1

CLIENT JOB INFORMATION

Project: Mt. Dunn
Shipment ID:
P.O. Number
Number of Samples: 6

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200	6	Crush split and pulverize drill core to 200 mesh			VAN
3B	6	Fire assay fusion Au by ICP-ES	30	Completed	VAN
1E	6	4 Acid digestion ICP-ES analysis	0.25	Completed	VAN

SAMPLE DISPOSAL

STOR-PLP Store After 90 days Invoice for Storage
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Paget Resources Corp.
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1
Canada

CC: Nigel Luckman
B. Booth



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 2 of 2 Part 1

SMI09000220.1

CERTIFICATE OF ANALYSIS

Analyte	Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
		Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		MDL	0.01	2	2	2	5	2	0.5	2	2	0.01	5	20	4	2	2	0.4	5	5	2	
927370	Drill Core		0.97	<2	<2	11	<5	13	<0.5	<2	<2	180	0.42	<5	<20	<4	<2	42	<0.4	<5	<5	3
927371	Drill Core		4.89	102	9	386	8	17	<0.5	2	7	315	3.19	186	<20	<4	12	461	<0.4	<5	<5	126
927372	Drill Core		3.77	44	14	403	7	16	<0.5	2	7	260	2.82	15	<20	<4	11	444	<0.4	<5	<5	116
927373	Drill Core		5.32	83	19	728	9	18	<0.5	8	10	340	3.77	11	<20	<4	7	364	<0.4	<5	<5	157
927374	Drill Core		2.54	199	4	1343	<5	24	<0.5	14	12	390	4.41	<5	<20	<4	8	341	<0.4	<5	<5	162
927375	Drill Core		2.62	104	6	1042	<5	16	<0.5	4	9	324	2.75	6	<20	<4	12	297	<0.4	<5	<5	108



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 2 of 2 Part 2

SMI09000220.1

CERTIFICATE OF ANALYSIS

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
Analyte		Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
Unit		%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	%						
MDL		0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
927370	Drill Core	22.49	0.025	2	<2	12.29	19	<0.01	0.10	<0.01	0.05	<4	<2	<2	<2	<1	<1	<0.1	
927371	Drill Core	2.38	0.103	22	2	0.75	259	0.25	8.72	3.90	3.61	<4	35	2	11	6	1	5	1.2
927372	Drill Core	2.03	0.105	26	2	0.68	236	0.25	8.93	4.13	3.49	<4	38	<2	12	6	1	5	1.0
927373	Drill Core	2.20	0.123	22	15	1.17	79	0.27	8.40	3.75	2.78	<4	27	<2	14	5	1	8	1.5
927374	Drill Core	1.89	0.115	22	13	1.32	184	0.26	8.38	3.66	2.67	<4	24	<2	12	4	<1	8	1.0
927375	Drill Core	1.78	0.098	22	3	0.92	174	0.21	8.32	3.52	3.48	<4	26	<2	13	5	<1	5	0.9



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client:

Paget Resources Corp.

1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project:

Mt. Dunn

Report Date:

October 09, 2009

Page:

1 of 1 Part 1

QUALITY CONTROL REPORT

SMI09000220.1

Method	WGHT	3B	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E		
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm		
MDL	0.01	2	2	2	5	2	0.5	2	2	5	0.01	5	20	4	2	2	0.4	5	5	2	
Pulp Duplicates																					
927374	Drill Core	2.54	199	4	1343	<5	24	<0.5	14	12	390	4.41	<5	<20	<4	8	341	<0.4	<5	<5	162
REP 927374	QC			4	1345	<5	24	0.6	13	11	392	4.43	<5	<20	<4	7	341	<0.4	<5	<5	161
Reference Materials																					
STD OREAS24P	Standard		<2	46	6	118	<0.5	140	42	1083	7.51	<5	<20	<4	3	384	0.8	<5	<5	158	
STD OREAS45P	Standard		<2	741	14	156	<0.5	392	121	1324	20.03	11	<20	<4	11	33	<0.4	<5	<5	274	
STD OXE56	Standard		602																		
STD OXE56	Standard		642																		
STD OXH55	Standard		1296																		
STD OREAS24P Expected			1.5	52	2.9	119	0.06	141	44	1100	7.53	1.2	0.75	2.85	403	0.15	0.09			158	
STD OREAS45P Expected			2.1	749	22	141	0.32	385	120	1338	19.22	12	2.4	0.055	9.8	32.6	0.2	0.82	0.21	267	
STD OXH55 Expected			1282																		
STD OXE56 Expected			611																		
BLK	Blank		<2	<2	<5	<2	<0.5	<2	<2	<5	<0.01	<5	<20	<4	<2	<2	<0.4	<5	<5	<2	
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
Prep Wash																					
G1	Prep Blank		4	<2	33	18	51	<0.5	4	4	715	2.24	<5	<20	<4	6	764	<0.4	<5	<5	50
G1	Prep Blank		3	<2	24	21	57	<0.5	5	5	786	2.46	<5	<20	<4	8	715	<0.4	<5	<5	55



1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Paget Resources Corp.**
1160 - 1040 West Georgia Street
Vancouver BC V6E 4H1 Canada

Project: Mt. Dunn
Report Date: October 09, 2009

Page: 1 of 1 Part 2

QUALITY CONTROL REPORT

SMI09000220.1

	Method	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	1E	
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Sn	Y	Nb	Be	Sc	S
	Unit	%	%	ppm	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
	MDL	0.01	0.002	2	2	0.01	1	0.01	0.01	0.01	0.01	4	2	2	2	2	1	0.1	
Pulp Duplicates																			
927374	Drill Core	1.89	0.115	22	13	1.32	184	0.26	8.38	3.66	2.67	<4	24	<2	12	4	<1	8	1.0
REP 927374	QC	1.88	0.115	22	15	1.33	297	0.27	8.46	3.69	2.65	<4	24	2	12	4	<1	8	1.0
Reference Materials																			
STD OREAS24P	Standard	5.60	0.133	18	191	4.03	282	1.04	8.14	2.33	0.69	<4	144	<2	22	19	1	20	<0.1
STD OREAS45P	Standard	0.30	0.047	25	1079	0.20	297	1.00	7.22	0.07	0.36	5	161	5	14	19	<1	69	<0.1
STD OXE56	Standard																		
STD OXE56	Standard																		
STD OXH55	Standard																		
STD OREAS24P Expected		5.83	0.136	17.4	196	4.13	285	1.1	7.66	2.34	0.7	0.5	141	1.6	21.3	21		20	
STD OREAS45P Expected		0.3	0.047	24.8	1089	0.1962	296	1.037	6.82	0.081	0.35	1.1	154	2.5	13	21.6		67	0.03
STD OXH55 Expected																			
STD OXE56 Expected																			
BLK	Blank	<0.01	<0.002	<2	<2	<0.01	<1	<0.01	<0.01	<0.01	<0.01	<4	<2	<2	<2	<2	<1	<1	
BLK	Blank																		
BLK	Blank																		
BLK	Blank																		
Prep Wash																			
G1	Prep Blank	2.54	0.079	20	7	0.65	1063	0.23	8.20	2.62	2.72	<4	7	<2	14	22	3	5	<0.1
G1	Prep Blank	2.51	0.089	24	11	0.73	1017	0.27	7.95	2.58	2.94	<4	8	4	17	25	3	6	<0.1