


**Ministry of Energy & Mines**  
Energy & Minerals Division  
Geological Survey Branch

**ASSESSMENT REPORT  
TITLE PAGE AND SUMMARY**

TITLE OF REPORT [type of survey(s)]		TOTAL COST
Assessment Report on Diamond Drilling on the Bodine-Warren Property		\$ 406,197.12

AUTHOR(S) Gwendolen Ditson, Amy Kerckhoff, SIGNATURE(S)   
Mark Rebagliati

NOTICE OF WORK PERMIT NUMBER(S)/DATE(S) MX-GEN-116; 09-1300516-0820; August 20, 2009 YEAR OF WORK 2009

STATEMENT OF WORK - CASH PAYMENT EVENT NUMBER(S)/DATE(S) Event # 4445291/January 4, 2010

---

PROPERTY NAME BODINE-WARREN

CLAIM NAME(S) (on which work was done) BODINE 3 (533366) & MS (542892)

---

COMMODITIES SOUGHT Zn

MINERAL INVENTORY MINFILE NUMBER(S), IF KNOWN \_\_\_\_\_

MINING DIVISION Omineca NTS 93N/12

LATITUDE 55 ° 37 ' 21 " LONGITUDE 125 ° 49 ' 05 " (at centre of work)

OWNER(S)

1) Lorne B. Warren 2) Amarc Resources Ltd.

---

MAILING ADDRESS

<u>Box 622</u>	<u>1020 - 800 W. Pender St.</u>
<u>Smithers, B.C. V0J 2N0</u>	<u>Vancouver, B.C. V6C 2V6</u>

---

OPERATOR(S) [who paid for the work]

1) Amarc Resources Ltd. 2) \_\_\_\_\_

---

MAILING ADDRESS

<u>1020 - 800 W. Pender St.</u>	
<u>Vancouver, B.C. V6C 2V6</u>	

---

PROPERTY GEOLOGY KEYWORDS (lithology, age, stratigraphy, structure, alteration, mineralization, size and attitude):

Permian to Early Jurassic Sitlika assemblage

Thick sequence of bedded volcanic to lithic wackes, felsic to intermediate tuffs, and flows.

Low grade disseminated zinc mineralization associated with massive and fragmental felsic volcanics.

---

REFERENCES TO PREVIOUS ASSESSMENT WORK AND ASSESSMENT REPORT NUMBERS \_\_\_\_\_

06578, 07642, 08485, 09547, 12916, 14780, 16038, 19935, 26400, 31167

TYPE OF WORK IN THIS REPORT	EXTENT OF WORK (IN METRIC UNITS)	ON WHICH CLAIMS	PROJECT COSTS APPORTIONED (incl. support)
<b>GEOLOGICAL (scale, area)</b>			
Ground, mapping _____			
Photo interpretation _____			
<b>GEOPHYSICAL (line-kilometres)</b>			
Ground			
Magnetic _____			
Electromagnetic _____			
Induced Polarization _____			
Radiometric _____			
Seismic _____			
Other _____			
Airborne _____			
<b>GEOCHEMICAL</b> (number of samples analysed for ...)			
Soil _____			
Silt _____			
Rock _____			
Other _____			
<b>DRILLING</b> (total metres; number of holes, size)			
Core _____	4 NQ holes - 1419,7 m total	533366 & 542892	\$ 406.197.12
Non-core _____			
<b>RELATED TECHNICAL</b>			
Sampling/assaying _____			
Petrographic _____			
Mineralographic _____			
Metallurgic _____			
<b>PROSPECTING (scale, area)</b> _____			
<b>PREPARATORY/PHYSICAL</b>			
Line/grid (kilometres) _____			
Topographic/Photogrammetric (scale, area) _____			
Legal surveys (scale, area) _____			
Road, local access (kilometres)/trail _____			
Trench (metres) _____			
Underground dev. (metres) _____			
Other _____			
<b>TOTAL COST</b>			<b>\$ 406,197.12</b>

**Assessment Report on the 2009 Diamond Drilling Program  
on the Bodine-Warren Property**

**BC Geological Survey  
Assessment Report  
31438**

Work performed on 533366 (BODINE 3) and 542892 (MS)

Located in the Omineca Mining Division  
NTS map 93N/12, BCGS maps 093N.052,061

Owner: Lorne B. Warren  
Operators: Amarc Resources Ltd.

Work program centred at approximately  
55° 37' 21" N Latitude, 125° 49' 05" W Longitude  
6,167,678 m N, 322,568 m E; UTM NAD 83, Zone 10

Authors:  
Amy Kerckhoff, BSc. (Honours Geology)  
Gwendolen Ditson, M.Sc., P.Geo.  
Mark Rebagliati, P.Eng.

March 31, 2010

## TABLE OF CONTENTS

1.0 SUMMARY .....	1
2.0 INTRODUCTION .....	2
3.0 LOCATION AND ACCESS .....	2
4.0 PHYSIOGRAPHY AND CLIMATE .....	2
5.0 CLAIMS .....	2
6.0 EXPLORATION HISTORY .....	3
7.0 REGIONAL GEOLOGY .....	4
8.0 PROPERTY GEOLOGY .....	4
8.1 Mineralization.....	5
Eureka and Crystal Occurrences (MINFILE 093N 179): .....	5
Don Occurrence (MINFILE 093N 220): .....	5
New Bodine Occurrence: .....	5
9.0 DIAMOND DRILLING .....	6
10.0 RECOMMENDATIONS .....	7
11.0 REFERENCES .....	8
STATEMENT OF COSTS .....	9
STATEMENTS OF AUTHORS' QUALIFICATIONS .....	10

APPENDIX A	Diamond Drill Logs
APPENDIX B	Analytical Procedures
APPENDIX C	Analytical Certificates

## LIST OF FIGURES

Figure 3.1	Property Location .....	after page 2
Figure 5.1	Claims .....	after page 2
Figure 7.1	Regional Geology – BCGS (2005).....	after page 4
Figure 7.2	Geological Legend. ....	after page 4
Figure 9.1	Drill Hole Locations.....	In pocket
Figure 9.2	Cross Section 9009.....	In pocket
Figure 9.3	Cross Section 9010 & 9011.....	In pocket
Figure 9.4	Cross Section 9012.....	In pocket
Figure 9.5	Downhole Column – 9009 .....	after page 6
Figure 9.6	Downhole Column – 9010 .....	after page 6
Figure 9.7	Downhole Column – 9011 .....	after page 6
Figure 9.8	Downhole Column – 9012 .....	after page 6
Figure 9.9	Legend for Downhole Columns .....	after page 6
Figure 9.10	Drill Program Rock Codes .....	after page 6

## LIST OF TABLES

Table 5.1	Bodine-Warren claims .....	3
Table 6.1	Previous Work .....	3
Table 9.1	Drill Collar Data .....	6
Table 9.2	Significant Drill Results (2009 Drill Holes).....	6

## **1.0 SUMMARY**

The Bodine-Warren claims are located in central British Columbia in the Omineca Mining Division, approximately 170 km northwest of Fort St. James, B.C., on NTS map sheet 93N/12. The area of the current program is accessible only by helicopter; crews were housed at Silver Creek camp, 23 km east of the work area.

The property is underlain by Permo–Jurassic clastic and volcanic rocks of the Sitlika assemblage. These rocks have been correlated with the Kutcho assemblage located approximately 300 km to the north that hosts the Kutcho copper-zinc massive sulphide deposit.

In 2009, a total of 1,419.7 m of diamond drilling was completed in four holes. The work was carried out on tenure numbers 533366 and 542892.

Drill holes 9009, 9010 and 9011 intersected broad intervals of low grade zinc mineralization, expanding the mineralized alteration zone 400 m to the north, beyond its previous extent identified in earlier drilling. The drill program confirmed the prospectivity of the felsic volcanic assemblage, and excellent potential remains for the discovery of a major zinc-rich massive sulphide deposit. Additional drilling of broadly spaced holes along strike and to greater depths down dip are warranted.

## **2.0 INTRODUCTION**

The Bodine-Warren property is part of the Bodine Option Agreement with Lorne Warren of Smithers, B.C. The Bodine property originally consisted of a 71,000 hectare area of claims extending along a 110 km length of the Permo-Jurassic volcano-sedimentary Sitlika assemblage. These rocks have been correlated with the Kutcho assemblage to the north that hosts the Kutcho copper-zinc massive sulphide deposit. This report documents the results of diamond drilling on the Bodine-Warren property in 2009.

## **3.0 LOCATION AND ACCESS**

The Bodine-Warren claims are situated in central British Columbia in the Omineca Mining Division. The property is located on NTS map 93N/12 and BCGS maps 093N.051, 052, 061 and 062. The centre of the area of work is approximately 170 km northwest of Fort St. James, B.C. at 55° 37' 21" N Latitude, 125° 49' 05" W Longitude; or UTM NAD 83, Zone 10, at 6,167,678 m N and 322,568 m E (Figure 3.1).

The area of the current work program on the Bodine-Warren property is not accessible by road. Crews were mobilized by helicopter from Silver Creek Camp, 23 km east of the work area. The camp is owned and operated by CJL Enterprises Ltd. of Smithers, B.C. Drill core for the Bodine-Warren property is stored in Silver Creek camp. The camp is accessible from Fort St. James via the Tachie Highway northwest from Fort St. James to Leo Creek Forest Service Road (FSR), Driftwood FSR and Fall FSR. The Silver Creek road branches south from the Fall Road.



## **4.0 PHYSIOGRAPHY AND CLIMATE**

The Bodine-Warren claims are situated in the Fort St. James Forest District of the Northern Interior Forest Region. The general topography is mountainous. Elevations range from 1,250 to 2,040 m above sea level at the peak of Mt. Bodine. Lower elevations of the property are forested with spruce, balsam and pine. The upper elevations transition to sub-alpine and alpine environments with scrub balsam growing densely on some of the steep mountain sides. Locally there are wet areas of high alpine marsh.

Average temperatures in Fort St. James are 18.2°C in summer and -11.3°C in winter, with annual rainfall averaging 29.5 cm and annual snowfall averaging 192.3 cm, respectively (Environment Canada Climate Weather Office Public Website [http://www.climate.weatheroffice.ec.gc.ca/climate\\_normals/index\\_1961\\_1990\\_e.html](http://www.climate.weatheroffice.ec.gc.ca/climate_normals/index_1961_1990_e.html)).

## **5.0 CLAIMS**

The Bodine-Warren property consists of 11 claims comprising an area of approximately 2,175 hectares (Table 5.1 and Figure 5.1). All claims are part of the Bodine Option Agreement between Lorne Warren and Amarc Resources Ltd.





**Amarc Resources Ltd.**

**BODINE - WARREN**

**Property Location**

NTS: 93N	Figure 3.1
Date: March 24, 2010	Scale: 1 : 1 100 000
WARR_Fig3.1loco_Mar2410.WOR Projection: Lat/Long	Plotted by : GMD





**A**marc Resources Ltd.

**BODINE - WARREN  
Claims**

BCGS: 93N.051,052,061,062  
 NTS: 93N/12  
 Date: March 25, 2010  
 WARR\_Fig5.1claims\_Mar2510.WOR  
 UTM NAD83, Zones 9 & 10

**Figure 5.1**  
 Scale 1: 50 000  
 Plotted by : GMD

**Table 5.1 Bodine-Warren claims**

Tenure No.	Claim Name	Owner	Date Recorded	Expiry Date*	Area (ha)
528235	DIVER 11	Lorne Brian Warren	2006/Feb/14	2019/Dec/31	54.794
533365	BODINE 2	Lorne Brian Warren	2006/May/02	2019/Dec/31	109.6328
533366	BODINE 3	Lorne Brian Warren	2006/May/02	2019/Dec/31	201.027
541525	D7	Lorne Brian Warren	2006/Sep/18	2019/Dec/31	73.145
542892	MS	Lorne Brian Warren	2006/Oct/10	2019/Dec/31	127.8743
545832	2HUGE 68	Amarc Resources Ltd.	2006/Nov/24	2019/Dec/31	219.3813
628823	2HUGE 72	Amarc Resources Ltd.	2009/Sep/04	2020/Sep/01	292.4271
628824	2HUGE 73	Amarc Resources Ltd.	2009/Sep/04	2020/Sep/01	402.2521
628843	2HUGE 71	Amarc Resources Ltd.	2009/Sep/04	2020/Sep/01	274.1806
628846	2HUGE 70	Amarc Resources Ltd.	2009/Sep/04	2020/Sep/01	365.3464
629703	2HUGE 74	Amarc Resources Ltd.	2009/Sep/08	2020/Sep/05	54.79

\*upon acceptance of this report

## 6.0 EXPLORATION HISTORY

Work has been filed for assessment in the area of the Bodine-Warren claims since 1979, as summarized in Table 6.1, below. Additional work by Amarc Resources in 2007 includes geological mapping, prospecting, soil and silt sampling. In 2008, Amarc completed additional soil sampling and 2241 metres of diamond drilling in eight holes.

**Table 6.1 Previous Work**

Report	Year	Company	Work Done/Recommendations
7642	1979	Shell Canada	Geology and soils on 10 grids on SKYE property yielded several Cu +/- Zn anomalies, some of which are associated with felsic volcanics
8485	1980	Canadian Superior	Geological mapping and rock sampling on RUTH revealed anomalous Zn (and lesser Cu) in felsic volcanics near older sedimentary rocks
9547	1981	Shell Canada	Geology, soil and electromagnetic surveys on RUTH; an open Cu-Zn soil anomaly outlined; ground EM did not confirm airborne results
12,916	1984	C. Graf	Small soil survey on RUTH was inconclusive
14,780	1986	Noranda Exploration	Soils, electromagnetic and magnetometer surveys on RUTH found a strong Zn(Cu) soil anomaly, and a conductor coincident with a graphitic horizon; conductor and soil anomaly are not coincident
16,038	1987	Noranda Exploration	Magnetometer and induced polarization surveys on RUTH; a linear mag high is associated with pyritic cherty rhyolite/quartzite horizon; several zones of high IP
19,935	1990	Noranda Exploration	One drill hole on RUTH encountered 3.8 m of 0.44% Zn; further work recommended
24,658	1996	Angel Jade Mines Ltd	Prospecting identified several indications of potential volcanogenic massive sulphide environment on Bodine property (old RUTH property)
26,400	1999	L. B. Warren	Prospecting and soils encountered three coincident Cu-Zn-Pb anomalies on MS (RUTH) claim
29,729	2008	Amarc Resources	Soil sampling revealed multi-element coincident anomalies in silt and soil. Additional soil sampling + auger sampling and drilling recommended.
31,167	2008	Amarc Resources	Anomalous Cu and Zn in soil warrant follow-up.

## 7.0 REGIONAL GEOLOGY

(After Jakubowski, et al., 2008; Assessment Report 29729)

The Bodine-Warren claims are primarily underlain by metavolcanic and metasedimentary rocks of the Permian to Early Jurassic Sitlika assemblage, part of the Cache Creek Terrane (Figures 7.1 and 7.2). The Sitlika is bounded on the west by volcanic and sedimentary rocks of the upper Triassic Takla Group, and the lower to middle Jurassic Hazelton Group. The belt is bounded to the east by rocks of the Cache Creek Complex.

Paterson (1974) divided the Sitlika assemblage into three subdivisions: the volcanic unit, an eastern clastic unit and a western clastic unit. Schiarizza and Payie (1997) established that the eastern clastic unit rests stratigraphically above the volcanic unit, but did not establish the age or stratigraphic relationships of the western clastic unit. The volcanic unit comprises greenschist facies mafic to felsic flow and fragmental rocks, comagmatic mafic to felsic intrusions, and subordinate sedimentary rocks that include sandstone, slate and chert. The Triassic to Jurassic eastern clastic unit is composed of variably foliated siltstone, sandstone and conglomerate containing clasts of felsic volcanic rocks, plutonic rocks, and medium to dark grey slate and phyllite. It also locally includes foliated limestone, limestone conglomerate and green chloritic phyllite. The middle to upper Jurassic western clastic unit consists of dark grey slate, foliated chert pebble conglomerate and chert grain sandstone. It also contains lesser amounts of foliated limestone and grey phyllite containing flattened sedimentary and volcanic lithic granules. A near vertical, north-south trending schistosity penetrates the majority of the lithologies and represents an axial plane cleavage reflecting folding during a Late Jurassic - Early Cretaceous structural event.


Soil and glacial till cover is extensive and generally shallow. Overall bedrock exposure is poor to moderate, but is locally abundant in some stream gullies as well as on steep upper slopes and ridge tops.






## 8.0 PROPERTY GEOLOGY

Property geology has not been filed for assessment, and no mapping was conducted in 2009, but the following descriptions are extracted from Dr. Oliver's field report (Oliver, 2007):

“The Mount Bodine area is characterized by a diverse array of felsic volcanic types. Felsic sequences range from fine-grained distal tuffs, to poorly sorted felsic volcanoclastics, to massive coherent flows and sub-volcanic intrusions.” The stratigraphic package in this area includes the following:

- i. An abundance of felsic intrusions, both as sills and dykes.
- ii. An abundance of coherent and brecciated felsic flows.
- iii. An abundance of fine to medium grained felsic to intermediate felsic tuffaceous rocks.



-  Park
-  Terrane boundary
-  Gravel road
-  Railway
-  Claim boundary

Geological Legend on Figure 7.2



**A**marc Resources Ltd.

## BODINE - WARREN

Regional Geology  
BCGS (2005)

Figure 7.1

Date: March 31, 2010





Scale as shown

WARR\_Fig7.1reggeo\_Mar3110.WOR  
Latitude-Longitude






Plotted by : GMD





**POST-ACCRETIONARY  
INTRUSIVE ROCKS**

- Eocene**  
 quartz diorite, granodiorite, porphyritic and felsitic intrusions
- Early to Middle Cretaceous**  
 granodiorite, granite, lesser pegmatite, quartz monzonite, monzogranite, gabbro, diorite
- Late Jurassic**  
 diorite
- Middle to Late Jurassic**  
 syenite, granite, granodiorite, quartz diorite, quartz monzonite, monzogranite, diorite, gabbro







**OVERLAP STRATIGRAPHY**

- Nechako Plateau Group**
- Eocene**  
 volcanoclastic/pyroclastic volcanic rocks
- Upper Cretaceous to Eocene**  
 sedimentary rocks
- Sustut Group**
- Upper Cretaceous to Eocene**  
 sedimentary rocks
- Skeena Group**
- Early Cretaceous**  
 sedimentary and volcanic rocks
- Bowser Lake Group**
- Middle Jurassic to Late Cretaceous**  
 sedimentary and volcanic rocks







**STIKINE TERRANE**

- Hazelton Group**
- Early to Middle Jurassic**  
 volcanic and sedimentary rocks
- Takla Group**
- Late Triassic**  
 volcanic and sedimentary rocks

**QUESNEL TERRANE**

- Chuchi Lake/Twin Creek Successions**
- Early Jurassic**  
 volcanic rocks
- Hogem Plutonic Suite**
- Early Jurassic**  
 syenite, monzonite, quartz monzonite, monzogranite
- Late Triassic to Early Jurassic**  
 gabbro to diorite
- Various Complexes/Suites**
- Late Triassic to Early Jurassic**  
 ultramafic/serpentinitic rocks
- Takla Group**
- Triassic to Jurassic**  
 volcanic and sedimentary rocks
- Lay Range Assemblage**
- Early Mississippian to Late Permian**  
 volcanic and sedimentary rocks




**CACHE CREEK TERRANE**


- Sitlika Assemblage**
- Early Permian to Early Triassic**  
 tonalite, diorite
- Late Triassic to Early Jurassic**  
 sedimentary rocks
- Permian to Jurassic**  
 metavolcanic rocks
- Cache Creek Complex**
- Early Permian to Late Triassic**  
 Rubyrock Igneous Complex gabbro, diorite, diabase, basalt
- Late Pennsylvanian to Late Triassic**  
 Trembleur Ultramafite Unit ultramafic/serpentinitic rocks
- Pennsylvanian to Late Jurassic**  
 sedimentary and volcanic rocks

**SLIDE MOUNTAIN TERRANE**

- Nina Creek Group**
- Mississippian to Permian**  
 sedimentary and volcanic rocks

**CARIBOO-CASSIAR TERRANE**

- Big Creek Group**
- Late Devonian to Late Permian**  
 sedimentary and volcanic rocks
- Razorback/Echo Lake Groups**
- Cambrian to Devonian**  
 carbonate and clastic sediments
- Ingenika Group**
- Upper Proterozoic**  
 sedimentary rocks

	
<h1>BODINE - WARREN</h1>	
<h2>Geological Legend</h2>	
<b>Figure 7.2</b>	
Date: March 31, 2010	
WARR_Fig7.1reggeoL_Mar3110.WOR Latitude-Longitude	Plotted by : GMD

- iv. Rapid on strike changes in lithology.
- v. Well developed debris – mass flow volcanoclastic units.
- vi. Weak representation of mafic flow sequences.
- vii. A volcanic sequence capped by a thick sequence of well bedded lithic and volcanic wackes.

The stratigraphy and “the nature of the volcano-sedimentary sequence strongly suggest that at the time of volcanism, the Bodine Peak area was a primary topographic low. More importantly, the volume of sub-volcanic felsic intrusions and flows also suggests that this area was a primary synvolcanic centre.”

“Many of the units are laterally discontinuous and the area contains lithologic and alteration indicators of synvolcanic faults and growth faults. These structures are associated with regions of enhanced cross-strata permeability, hydrothermal alteration and potential sulphide deposition.”

### **8.1 Mineralization**

There are several known mineral occurrences within the Bodine-Warren claims which have been explored since the 1970's. Refer to the Drill Hole Locations map (Figure 9.1) for locations.

***Eureka and Crystal Occurrences (MINFILE 093N 179):*** The Eureka occurrence is a shear hosted vein system approximately 5 m wide that dips about 85° southwest in a highly strained felsic flow. Sericitization proximal to major veins has resulted in the development of paper schist. The zone was intersected in the 2008 drill program 80 m below the surface, where five quartz veins 1 cm to over 1 m in width are characterized as heavy bull quartz with coarse euhedral clots of 4-5% pyrite and only traces of chalcopyrite, galena and chalcopyrite.

The Crystal occurrence is 600 m southwest of Eureka. It is a zone of enhanced iron oxides and well laminated pyrite. It occurs at the contact between a massive felsic flow or sub-volcanic intrusion in the hanging wall, and mafic tuffaceous rocks in the footwall. It is essentially barren of economic base or precious metals.

***Don Occurrence (MINFILE 093N 220):*** This showing is located 800 m southwest of Mt. Bodine. A series of ladder and extension quartz veins flanked by well-defined iron-carbonate alteration zones are hosted by a dark black, vitric felsic intrusion. The intrusion cuts a sequence of well-bedded volcanoclastic sedimentary rocks and minor mafic flows, striking approximately 025° and averaging 25-50 m in width. Veins appear to be developing orthogonally to the contact of the intrusion and may be as long as the intrusion itself, ranging in width from a few centimetres to over a metre.

***New Bodine Occurrence:*** The New Bodine occurrence is located 75 m south of the Eureka occurrence, in the same creek that flows through Eureka. New Bodine is near the contact between a massive coherent felsic flow and penecontemporaneous heterolithic breccias. Cu-Zn mineralization in heterolithic fragmental rocks is present as a series of

stringers and disseminations of chalcopyrite and sphalerite in an area characterized by enhanced iron-carbonate alteration.

## 9.0 DIAMOND DRILLING

A total of 3,660.9 m in 12 holes has been drilled on the Bodine-Warren claims. Of that total, 2,241.2 m was drilled in 2008, and 1,419.7 m in 2009. All drilling was by Blackhawk Drilling Ltd. of Smithers, B.C. Drill hole location data is contained in Table 9.1, below and plotted on Figure 9.1.

**Table 9.1 Drill Collar Data**

Drill Hole Number	Location (UTM83 Z10)			Dip (deg.)	Azimuth (deg.)	Length (m)	Date Commenced	Date Completed
	Northing (m)	Easting (m)	Elev. (m)					
8001	6,136,362	323,411	1,618	-47	56	220.4	Sept. 17/08	Sept. 21/08
8002	6,165,814	323,617	1,748	-48	58	129	Sept. 22/08	Sept. 25/08
8003	6,166,883	322,960	1,705	-48	58	342.9	Sept. 26/08	Sept. 29/08
8004	6,167,527	322,685	1,530	-45	58	324.3	Sept. 29/08	Oct. 2/08
8005	6,167,591	322,812	1,529	-45	58	205.7	Oct. 2/08	Oct. 4/08
8006	6,168,086	323,165	1,460	-45	238	276.1	Oct. 4/08	Oct. 5/08
8007	6,165,975	323,903	1,577	-45	238	393.2	Oct. 6/08	Oct. 12/08
8008	6,167,040	323,764	1,501	-45	238	349.6	Oct. 12/08	Oct. 15/08
9009	6,167,448	322,597	1,524	-55	56	422.5	Sept. 12/09	Sept.16/09
9010	6,167,800	322,478	1,498	-45	56	326.7	Sept. 17/09	Sept.19/09
9011	6,168,001	322,614	1,474	-48	56	382.8	Sept. 20/09	Sept. 24/09
9012	6,164,466	324,018	1,668	-50	90	287.7	Sept. 24/09	Sept. 27/09

Drill logs for the 2009 program are located in Appendix A, analytical procedures are in Appendix B, and analytical certificates are in Appendix C. Significant drill intercepts with zinc concentrations generally greater than 1000 ppm are listed in Table 9.2, below. Cross sections illustrating Cu and Zn assays are shown in Figures 9.2 through 9.4. Downhole columns illustrating geology and assay results are illustrated in Figures 9.5 through 9.8. Figure 9.9 is a colour legend for downhole columns. Figure 9.10 is an explanation of rock codes used in downhole columns and on drill logs.

**Table 9.2 Significant Drill Results (2009 Drill Holes)**

Hole ID	From (m)	To (m)	Length (m)	Zn ppm	Cu ppm	Pb ppm	Au ppb	Ag ppm
9009	157.3	422.5	265.2	2742.6	129.0	18.7	41.7	0.3
9010	259.7	326.7	67	2533.0	535.6	26.9	43.2	0.8
9011	142	248.7	106.7	1779.7	105.7	218.0	8.0	0.6
9012	175	181.1	6.1	1743.8	70.2	7.7	1.0	0.3

# Amarc Resources - Bodine Project

HOLE-ID :9009

**Figure 9.5**


LOCATIONX :322597

LOCATIONY :6167448

LOCATIONZ :1524

Segment Start Depth :0.00

Segment End Depth :422.50



Scale As Shown in Meters

04 Dec 2009

By EDT / GY



# Amarc Resources - Bodine Project

HOLE-ID :9010

**Figure 9.6**


LOCATIONX :322478

LOCATIONY :6167800

LOCATIONZ :1498

Segment Start Depth :0.00

Segment End Depth :326.70



Scale As Shown in Meters

04 Dec 2009

By EDT / GY

# Amarc Resources - Bodine Project

HOLE-ID :9011

**Figure 9.7**


LOCATIONX :322614

LOCATIONY :6168001

LOCATIONZ :1474

Segment Start Depth :0.00

Segment End Depth :382.80



Scale As Shown in Meters

04 Dec 2009

By EDT / GY

# Amarc Resources - Bodine Project

HOLE-ID :9012

**Figure 9.8**


LOCATIONX :324018

LOCATIONY :6164466

LOCATIONZ :1668

Segment Start Depth :0.00

Segment End Depth :287.70



Scale As Shown in Meters

04 Dec 2009

By EDT / GY



***Composition /Primary Rock Codes  
(all capitals)***


F: Felsic  
I: Intermediate  
M: Mafic  
  
T: Siltite  
E: Epiclastic  
W: Wacke  
A: Argillite  
Q: Quartzite

***Alteration Modifiers (all small case)***

g: graphite  
s: sericite  
c: chlorite  
a: ankerite – iron carbonate  
k: clay  
h: hematite  
q: quartz  
ox: oxidized  
p: pyrite  
e: epidote  
t: potassium feldspar

***Lithofacie Modifiers (all small case)***

t: tuff  
l: lapilli  
f: flow  
a: ash  
b: banded  
v: vesicular  
x: breccias including autogenous flow  
breccias  
h: hyaloclastite  
p: plagioclase phyrlic  
q: quartz phyrlic  
vc: volcanoclastic  
d: dyke  
i: bioclastic

 Amarc Resources Ltd.	
<b>BODINE - WARREN</b>	
<b>Drill Program Rock Codes</b>	
<b>Figure 9.10</b>	
Date: March 31, 2010	
WARR_DownColumnLeg_Dec0409.WOR	Plotted by : AK

**Section 9009 (Figure 9.2)**

Drill hole 9009 targeted the continuation of strong zones of zinc mineralization intersected in previous drill holes 8004 and 8005. Hole 9009 intersected a significantly increased volume of felsic to intermediate flow rocks relative to the earlier drill holes (Figure 9.5), and bottomed in 265 m of 2742 ppm Zn.

**Section 9010 and 9011 (Figure 9.3)**

Drill holes 9010 and 9011 are located approximately 35 and 55 m, respectively, to the north of hole 9009. These holes were designed to test the extension of the altered felsic volcanic hosted zinc concentrations in previous drill holes. The altered, zinc-enhanced zone was successfully extended by 400 m. Hole 9010 bottomed in zinc mineralization and did not therefore test the full width of the prospective geological interval.

**Section 9012 (Figures 9.4)**

Drill hole 9012 is the southernmost drill hole on the property, located 1400 m south of 8002. This hole targeted a strong copper soil anomaly that straddles the contact between felsic tuff and overlying argillite. Stratigraphy targeted by 9012 is along strike with similar stratigraphy tested in 2008 by hole 8007. Unfortunately, rock alteration and sulphide development in hole 9012 is less intense than in hole 8007. The Eastern Sitlika contact is likely structural and appears to have moved up and into the central volcanic rock package, resulting in the loss of part of the felsic volcanic, pillowed mafic volcanic and volcanoclastic section, and the absence of a significant sulphide system.

Significant intervals of enhanced zinc concentrations were intersected in all four holes of the 2009 drilling program. This further confirms the observation made during the 2008 program that there are significant lithochemical indicators of a volcanogenic massive sulphide deposit within this stratigraphic package – along strike, to the north, south or down dip.

**10.0 RECOMMENDATIONS**

Although diamond drill testing of promising geological-geochemical-geophysical targets did not discover any massive sulphide deposits nor substantial good grade intervals of copper or zinc mineralization, low grade zinc mineralization was found associated with massive and fragmental felsic volcanic units in a number of holes. The distribution and tenor of the zinc mineralization is compatible with a peripheral VMS depositional environment. Drilling deeper and along strike to the north and south is warranted.

## 11.0 REFERENCES

- Environment Canada Climate Weather Office Public Website, accessed January 3, 2008:  
[http://www.climate.weatheroffice.ec.gc.ca/climate\\_normals/index\\_1961\\_1990\\_e.html](http://www.climate.weatheroffice.ec.gc.ca/climate_normals/index_1961_1990_e.html)
- Jakubowski, W. *et al.* 2008. Year: 2007 Assessment Report on Geochemical Work done on the Bodine Property, Ominica Mining Division; B.C.Ministry of Energy, Mines and Petroleum Resources Assessment Report No. 29729.
- Oliver, J. 2007: Geology of the Bodine Property, North Central British Columbia. Amarc Resources Ltd. Internal Report, December 6, 2007, 48 pages.
- Paterson, I.A. 1974: Geology of the Cache Creek Group and Mesozoic Rocks at the North End of Stuart Lake Belt, central British Columbia; *in* Report of Activities, November 1973 to March 1974, Geological Survey of Canada, Paper 74-1, part B, p. 31-42.
- Schiarizza, P., and Payie, G. 1997: Geology of the Sitlika assemblage in the Kenny Creek – Mount Olson area (93N/12, 13), central British Columbia; *in* Geological Fieldwork 1996, B.C. Geological Survey Branch Paper 1997-1, p. 79-100.

## STATEMENT OF COSTS

Exploration Work type	Comment	Days				Totals
<b>Personnel (Name)* / Position</b>						
	<b>Field Days (list actual days)</b>	<b>Days</b>	<b>Rate</b>	<b>Subtotal*</b>		
Amy Kerckhoff/Party Chief	Sept 10-11,13-14,16,18,21,22,Oct.1	17	\$600.00	\$10,200.00		
Jim Oliver/Geologist	Sept. 10-28	17.5	\$863.00	\$15,102.50		
Shaun Stroshin/Sampler	Sept 8-21,23-27, Oct.1	19	\$320.00	\$6,080.00		
Chris Roe/Sampler	Sept 8-11,13-22	12.85	\$320.00	\$4,112.00		
Pad builders	Sept 8-12,16,19-20,22-23	20.25	\$300.00	\$6,075.00		
		man-days:	86.6			
					<b>\$41,569.50</b>	
<b>Office Studies</b>						
<b>List Personnel (note - Office only, do not include field days)</b>						
Planning & supervision	Mark Rebagliati, P.Eng.	1.5	\$1,293.00	\$1,939.50		
Database compilation	Romeo Taras	1.5	\$650.00	\$975.00		
Maps/graphics	Gwendolen Ditson	1.0	\$750.00	\$750.00		
Report preparation	Amy Kerckhoff	2.0	\$600.00	\$1,200.00		
	Gwendolen Ditson	1.0	\$750.00	\$750.00		
					<b>\$5,614.50</b>	
<b>Geochemical Surveying</b>						
	<b>Number of Samples</b>	<b>No.</b>	<b>Rate</b>	<b>Subtotal</b>		
Drill (cuttings, core, etc.)	503 samples @ \$46.10 each	503.0	\$46.10	\$23,188.30		
		total samples:	503.0			
					<b>\$23,188.30</b>	
<b>Drilling</b>						
	<b>No. of Holes, Size of Core and Metres</b>	<b>No.</b>	<b>Rate</b>	<b>Subtotal</b>		
Diamond	4 NQ holes, 1419.7 m total	1419.7	\$118.19	\$167,799.00		
		man-days:	91.0			
					<b>\$167,799.00</b>	
<b>Reclamation</b>						
		<b>No.</b>	<b>Rate</b>	<b>Subtotal</b>		
After drilling	Drill site clean-up: bucking & scattering felled trees	6.0	\$300.00	\$1,800.00		
		man-days:	6.0			
					<b>\$1,800.00</b>	
<b>Transportation</b>						
		<b>No.</b>	<b>Rate</b>	<b>Subtotal</b>		
Airfare, taxi, motel, meals, etc.				\$1,500.00		
truck rental	Ron Ridley Rentals Ltd., Williams Lake Vanderhoof & Districts Co-Op, Vanderhoof			\$4,740.45		
fuel (gas & diesel)				\$6,480.85		
Helicopter (hours, including fuel)	Interior Helicopters Ltd., Fort St. James	85	\$1,390.00	\$118,428.00		
					<b>\$131,149.30</b>	
<b>Accommodation &amp; Food</b>						
	<b>Rates per day</b>					
Camp - CJL Enterprises	\$120/day/person	183.60	\$120.00	\$22,032.00		
					<b>\$22,032.00</b>	
<b>Miscellaneous</b>						
Telephone	\$1/day/man	183.60	\$1.00	\$183.60		
Field gear (tags, bags, etc.)	IRL Supplies, Prince George; Deakin Industries, Vancouver; Russell Transfer Ltd., Fort St. James; Ouellette Bros., Fort St. James			\$2,675.87		
					<b>\$2,859.47</b>	
<b>Freight, rock samples</b>						
Sample delivery to Smithers	Russell Transfer Ltd., Fort St. James			\$1,861.02		
Expediting services - hauling, fuel, propane, etc. to & from camp	Russell Transfer Ltd., Fort St. James			\$8,324.03		
					<b>\$10,185.05</b>	
<b>TOTAL Expenditures</b>					<b>\$406,197.12</b>	



## **STATEMENTS OF AUTHORS' QUALIFICATIONS**

## STATEMENT OF QUALIFICATIONS

I, *Amy Kerckhoff*, of Vancouver, British Columbia, hereby certify that:

1. I am an exploration geologist employed by Hunter Dickinson Inc. of 1020 - 800 West Pender Street, Vancouver, B.C., V6C 2V6.
2. I received a B.Sc (Honours) degree in Geological Sciences from Queen's University, Kingston, Ontario, in 2003.
3. I was the Project Geologist responsible for execution of the 2009 field program on the Bodine-Warren property.
4. I am an author of this report.

Signed on the 31<sup>st</sup> day of March, 2010

A handwritten signature in blue ink that reads "A. Kerckhoff". The signature is written in a cursive style with a large loop at the end of the last name.

Amy Kerckhoff, B.Sc. (Honours Geology)

## STATEMENT OF QUALIFICATIONS

I, *Gwendolen May Ditson*, do hereby state that:

1. I am a Compilation Geologist working for Amarc Resources Ltd., with offices located at 1020 – 800 West Pender Street, Vancouver, B.C.
2. I am a member of the Association of Professional Engineers and Geoscientists of the Province of British Columbia, holding License Number 20135.
3. I am a graduate of the University of Southern California (B.S., 1974), and the University of British Columbia (M.Sc., 1978).
4. I have been an exploration geologist since 1976, and have worked in Canada, the United States, Chile, Spain and Mexico.
5. I am an author of this report, and am also responsible for the technical figures.

Signed on the 31<sup>st</sup> day of March, 2010

A blue ink handwritten signature is written over a circular professional seal. The seal contains the text: "PROFESSIONAL ENGINEER AND GEOSCIENTIST", "PROVINCE OF BRITISH COLUMBIA", "G. M. DITSON", and "LICENSE NO. 20135".

Gwendolen May Ditson, M.Sc., P. Geo.

## STATEMENT OF QUALIFICATIONS

I, **Mark Rebagliati**, P. Eng., of Vancouver, British Columbia, Canada, do hereby state that:

1. I am a consulting geological engineer and President of Rebagliati Geological Consulting Ltd with offices at 317-2200 Highbury St, Vancouver, British Columbia, Canada.
2. I am a member of the Association of Professional Engineers and Geoscientists of the Province of British Columbia, holding License Number 8352.
3. I graduated with a B.Sc. in geological engineering from Michigan Technological University, Houghton, Michigan, USA in 1969.
4. I have worked as an exploration geologist for a total of 41 years since my graduation from university.
5. I am the Technical Manager directing activities on the Bodine-Warren Property for Amarc Resources Ltd.

Signed on the 31<sup>st</sup> day of March, 2010

A handwritten signature in black ink, appearing to read 'Mark Rebagliati', written in a cursive style.

Mark Rebagliati, P.Eng.

## **APPENDIX A**

### **DIAMOND DRILL LOGS**

































**Diamond Drill Core Logging Form**



HUNTER DICKINSON INC.  
AMARC RESOURCES LTD.

DDH No: B9010  
Dip -45 Az: 056

UTM N: 6167800  
UTM E: 0322478

Down Hole Surveys  
depth m: 15.8 Dip:-44.7 , Azi:56.4  
depth m: 76.7 Dip:-43.9 Azi: 58.4  
depth m: 137.8 Dip: -41.5, Azi: 61.3  
depth m: 198.7 Dip -38.4, Azi: 63.5  
depth m: 259.7 Dip: -35.4, Azi: 65.2  
depth m: 320.6 Dip: -32.7, Azi: 68.1  
Total Depth: 326.7

Elev m: 1498  
Date Collared: Sept 17, 09  
Date Completed: Sept. 19, 2009  
Date Logged: Sept. 17 - 19, 2009.  
Logged By: J. Oliver.

Date: Sept. 20, 2009.

FROM	TO	ALT MOD	COMP	LIT FACI	STR MOD	STR ORIN	DESCRIPTION	GANGUE		ALTERATION %										MINERALIZATION %								SAMPLING -ASSAY			
m	m							%	Ch	Se	Oz	Ab	Bi	Ca	Or	Ep	FeC	other %	Sp	Cp	Gl	Py	Mag	He	Ma/Az	other %	Sample #	From	To	Control	
0	2.9						Casing																				835802	2.90	6.70	3.8	
							2.9																				835803	6.70	9.75	3.1	
2.9	61.5		F	iqp			Quartz and Plagioclase Phyric Felsic Intrusion																1.0				835804	9.75	12.80	3.1	
																											835805	12.80	15.80	3.0	
	14.9					S1 45	The rock is a homogeneous, fine grained, quenched matrix felsic intrusion. The unit contains three recognizable phenocryst phases including:																				835806	15.80	18.90	3.1	
							i. Equant glassy quartz eyes 2-4 mm in dimension, 10% by volume.																				835807	18.90	21.90	3.0	
							ii. Elongate plagioclase phenocrysts, partially sericitized, 8-10% by volume.																				835808	21.90	25.00	3.1	
							iii. Minor partially chloritized hornblende lathes.																				835809	25.00	28.00	3.0	
	39.8					S1 55	The rock matrix is quenched, glassy, light grey and hard.																				835810	28.00	31.10	3.1	
							<i>Alteration and Mineralization:</i>																				835811	31.10	34.10	3.0	
							The intrusion contains no significant sulphides. Minor leucoxene grains are disseminated throughout the rock matrix. Very finely disseminated magnetite is noted throughout the rock matrix about 1.0%.																				835812	34.10	37.20	3.1	
							The unit contains no evidence of hydrothermal related mineral assemblages. Average SI in non-sheared rock: 5.5																				835813	37.20	40.20	3.0	
	9.75					V: 50	The broader interval is virtually devoid of veins, with only a single 5 cm banded qtz carbonate vein at 9.75 m.																				835814	40.20	43.30	3.1	
							Niton Zn values are low ranging from approx 20 to 165 ppm.																				835815	43.30	46.30	3.0	
							<i>Structural Characteristics:</i>																				835816	46.30	49.40	3.1	
							The intrusion does have a moderately well developed S1 fabric. Most significantly the rock is repeatedly cut by a series of late fault zones. These are characterized by buff to blond bleaching, by anastomosing clay microveinlets and by magnetite destruction, SI values 0.25.																				835817	49.40	52.40	3.0	
							These structural zones are identified at:																				835818	52.40	55.50	3.1	
																											835820	55.50	58.50	3.0	
																											835821	58.50	61.60	3.1	
																											835822	61.60	64.60	3.0	
																											835823	64.60	67.70	3.1	
																											835824	67.70	70.70	3.0	
																											835825	70.70	73.80	3.1	
																											835826	73.80	76.80	3.0	
																											835827	76.80	79.90	3.1	
																											835829	79.90	82.90	3.0	
																											835830	82.90	86.00	3.1	
																											835831	86.00	89.00	3.0	
																											835832	89.00	92.00	3.0	
																											835833	92.00	95.10	3.1	
																											835834	95.10	98.10	3.0	
																											835835	98.10	101.20	3.1	
																											835836	101.20	104.20	3.0	
																											835837	104.20	107.20	3.0	
	18.4					Sh: 45	17.4 - 19.2: Open space clay breccias, enhanced clays.																				835838	107.20	110.30	3.1	
	31					Sh: 65	29.3 - 32.1: Incipient breccias, late clay seams, bleached light grey core.																				835840	110.30	113.40	3.1	
																											835841	113.40	116.40	3.0	
	45.7					Sh: 30	42.0 - 46.5: Diffuse bleaching and structural zone's, intact core with incipient breccias. This partial failure zone is likely forming a damage envelope to the much stronger failure zone located at the structural lower contact.																				835842	116.40	119.50	3.1	
							80% Core recovery.																				835843	119.50	122.50	3.0	
																											835844	122.50	125.60	3.1	
																											835845	125.60	128.60	3.0	
																											835846	128.60	131.70	3.1	
																											835847	131.70	134.70	3.0	
							Sh: 45																				835848	134.70	137.80	3.1	
							51.7 - 61.5: Strong late fault and oxidation zone. Intrusion may be developing a chilled margin at the lower contact.																				835849	137.80	140.80	3.0	
							Good oxidation development throughout this interval.																				835850	140.80	143.90	3.1	
							45% Core recovery.																				835851	143.90	146.90	3.0	
							61.5																				835851	143.90	146.90	3.0	

DDH No: B9010						Diamond Drill Core Logging Form														Page 2 of 11											
FROM	TO	ALT MOD	COMP	LIT FACI	STR MOD	STR ORIN	DESCRIPTION	GANGUE	ALTERATION %										MINERALIZATION %						SAMPLING -ASSAY						
m	m							%	Ch	Se	Qz	Ab	Bi	Ca	Or	Ep	FeC	other %	Sp	Cp	Gl	Py	Mag	He	Ma/Az	other %	Sample #	From	To	Control	
61.5	65.4	s	M	t	e		<b>High Strain Zone: Mafic Ash Tufts</b>			15.0																	835852	146.90	150.00	3.1	
							The rock protolith in this interval is likely to have been a mafic ash tuff. The rock has been intensely deformed and displays well developed planar shear bands, strongly developed matrix talc-sericite and locally significant gouge zones development with extensive core loss. No residual or primary quartz eyes are identified within this unit.																				835853	150.00	153.10	3.1	
																											835854	153.10	156.10	3.0	
																											835855	156.10	159.10	3.0	
																											835856	159.10	162.10	3.0	
																											835857	162.10	165.20	3.1	
																											835858	165.20	168.20	3.0	
																											835860	168.20	171.30	3.1	
																											835861	171.30	174.30	3.0	
																											835862	174.30	177.40	3.1	
							<i>Alteration and Mineralization</i>																				835863	177.40	180.40	3.0	
							The rock contains no significant sulphides and no discordant vein sets. The matrix is khaki green, and contains abundant > 20% talc sericite. Locally early, blurred matrix, non sulphide quartz veins are identified. Net SI is low 0.1.																				835864	180.40	183.50	3.1	
																											835865	183.50	186.50	3.0	
																											835866	186.50	189.60	3.1	
																											835867	189.60	192.60	3.0	
																											835868	192.60	195.70	3.1	
	6.6					Sh: 44	<i>Structural Characteristics</i>																				835869	195.70	198.70	3.0	
							Intense planar flattening fabric and localized gouge development. Well define planar shear bands, noted.																				835870	198.70	201.80	3.1	
							Extensive clay gouge development. Core recoveries within this interval 70-75%.																				835871	201.80	204.80	3.0	
							Note: There is a moderate probability that the entire "Mafic" Ash unit is a complete high strain transformation of Fig. 65.4																				835872	204.80	207.90	3.1	
																											835873	207.90	210.90	3.0	
																											835874	210.90	214.00	3.1	
																											835875	214.00	217.00	3.0	
																											835876	217.00	220.10	3.1	
65.4	135.8	s	Fl	i			<b>Sheared Chloritized - Sericitized Non-Quartz Porphyritic Felsic to Intermediate Intrusion</b>	8.0	7.0												0.10					835877	220.10	223.25	3.2		
							The unit is again a fine grained, quenched matrix, light cream to olive green, felsic intrusion. Well formed quartz eyes are rarely preserved in this interval and when noted are usually corroded and partially replaced by a combination of zoisite, and other non-identifiable silicate phases.																				835878	223.25	226.20	3.0	
							Across this broad interval numerous textural variations are identified. Textural and compositional variations are:																				835880	226.20	229.20	3.0	
							A. Potentially strain related. The unit is cut by numerous brittle ductile zones.																				835881	229.20	232.30	3.1	
							B. Compositional changes may represent the influence of rafts or inclusions of mafic volcanic, ash tufts, or of fine grained more intermediate phases of the same intrusion.																				835882	232.30	235.30	3.0	
																											835883	235.30	238.40	3.1	
																											835884	238.40	241.40	3.0	
																											835885	241.40	244.45	3.1	
																											835886	244.45	247.50	3.1	
																											835887	247.50	250.50	3.0	
																											835888	250.50	253.60	3.1	
																											835889	253.60	256.60	3.0	
																											835890	256.60	259.70	3.1	
																											835891	259.70	262.70	3.0	
																											835892	262.70	265.80	3.1	
																											835893	265.80	268.80	3.0	
																											835894	268.80	271.90	3.1	
							<i>Alteration and Mineralization:</i>																				835895	271.90	274.90	3.0	
							Net sulphide content extremely low. Py < 0.1%. Magnetite has generally be altered to hematite, typically low SI numbers ranging from 0.0 to 0.5, averaging 0.05.																				835896	274.90	278.00	3.1	
							Core losses indicated in relevant intervals.																				835897	278.00	281.00	3.0	
							Alteration sub-intervals include:																				835898	281.00	284.10	3.1	
																											835900	284.10	287.10	3.0	
																											835901	287.10	290.20	3.1	
																											835902	290.20	293.60	3.4	
67.4						Sh:40	65.4 - 68.5: Bleached pale green to tan, felsic intrusion cut by numerous cream clay rich fractures. >95% recovery.																				835903	293.60	296.30	2.7	
																											835904	296.30	299.30	3.0	
	77.5					Sh: 40	68.5 - 73.8: Blue grey, fine grained, locally shattered felsic intrusion. Locally heavy development of green-clay gouge zones. 10-15% recovery between 70.7 and 73.8 m.																					835905	299.30	302.40	3.1
																											835906	302.40	305.40	3.0	
	82					Sh: 40	73.8 - 81.85: Blue-grey shattered felsic intrusion.																					835907	305.40	308.50	3.1
																											835908	308.50	311.50	3.0	
	92.4					Sh: 42	No significant sulphides. No discordant vein sets. Below 81.85, section becomes increasingly fine grained, less siliceous and with an increased percentage of pale green grey diffusely banded, thick 50 - 200 cm chlorite-sericite compositional layers. Niton Zn levels are typically																					835909	311.50	314.60	3.1
																											835910	314.60	317.60	3.0	
																											835911	317.60	320.60	3.0	
																											835912	320.60	323.70	3.1	
																											835914	323.70	326.70	3.0	


















































































## **APPENDIX B**

### **ANALYTICAL PROCEDURES**



## METHODS AND SPECIFICATIONS FOR ANALYTICAL PACKAGE GROUP 3B & 3B-MS - PRECIOUS METALS BY FIRE GEOCHEM



### Comments

#### Sample Preparation

All samples are dried at 60°C. Soil and sediment are sieved to -80 mesh (-177 µm). Moss-mats are disaggregated then sieved to yield -80 mesh sediment. Vegetation is pulverized or ashed (475°C). Rock and drill core is jaw crushed to 70% passing 10 mesh (2 mm), a 250 g riffle split is then pulverized to 95% passing 150 mesh (100 µm) in a mild-steel ring-and-puck mill. Pulp splits of 30 g are weighed into fire-assay crucibles.

#### Sample Digestion

The sample aliquot is custom blended with fire assay fluxes, PbO litharge and a Ag inquant. Firing the charge at 1050°C liberates Au ±PGEs that report to the molten Pb-metal phase. Once cooled the Pb button is recovered then fired in a MnO cupel at 950°C to render a Ag ±Au ±PGE dore bead. The bead is weighed and parted (i.e. leached in 1 mL of hot HNO<sub>3</sub>) to dissolve Ag then 10 mL of HCl is added to dissolve the Au ± PGEs. A Rh fire assay requires inquanting with Au for quantitative analysis.

#### Sample Analysis

**Group 3B:** Solutions analysed by a Jarrel Ash Atom-Comp 975 ICP-ES determine Au only. Analyses on a Perkin Elmer Elan 6000 ICP-MS determine Au, Pt and Pd.

**Group 3B-MS:** Lower Au, Pt and Pd detection limits are achieved by a longer determination time on the Elan 6000 ICP-MS.

**Rh** by Au inquant gives a quantitative analysis. Rh by Ag inquant is semi-quantitative owing to the limited solubility of Rh in Ag.


#### Quality Control and Data Verification

An Analytical Batch (1 page) comprises 34 samples. QA/QC protocol incorporates a sample-prep blank (SI or G-1) carried through all stages of preparation and analysis as the first sample, a pulp duplicate to monitor analytical precision, a -10 mesh rejects duplicate to monitor sub-sampling variation (drill core only), two reagent blanks to measure background and aliquots of in-house Standard Reference Materials like Au-S, Au-R, Au-1 or FA-10R and FA-100S monitor accuracy. Group 3B-MS incorporates new crucibles and additional reagent blanks to permit accurate analysis at very low concentration levels.

Raw and final data undergo a final verification by a British Columbia Certified Assayer who signs the Analytical Report before it is released to the client. Chief Assayer is Clarence Leong, other certified assayers are Leo Arciaga, Ken Kwok, Marcus Lau and Jacky Wang.



## METHODS AND SPECIFICATIONS FOR ANALYTICAL PACKAGE GROUP 7TX – MULTI-ELEMENT ASSAY BY ICP-ES/MS • 4-ACID DIGESTION



### Comments

#### Sample Preparation

All samples are dried at 60°C. Soil and sediment are sieved to -80 mesh (-177 µm). Moss-mats are disaggregated then sieved to yield -80 mesh sediment. Vegetation is pulverized or ashed (475°C). Rock and drill core is jaw crushed to 70% passing 10 mesh (2 mm), a 250 g riffle split is then pulverized to 95% passing 150 mesh (100 µm) in a mild-steel ring-and-puck mill. Pulp splits of 0.5 g are weighed into Teflon test tubes.

#### Sample Digestion

A 20 mL aliquot of the acid solution (2:2:1:1 H<sub>2</sub>O-HF-HClO<sub>4</sub>-HNO<sub>3</sub>) is added, heated until fuming on a hot plate and taken to dryness. A 16 mL aliquot of 50% HCl is added to the residue and heated in a hot-water bath (-95°C) for 30 minutes. After cooling the solutions are transferred to 100 mL volumetric flasks and made to volume with 5% HCl.

#### Sample Analysis

Solutions are aspirated into a Jarrel Ash Atomcomp model 800 or 975 or Spectro Ciros Vision ICP atomic-emission spectrometer followed by analysis by Perkin Elmer Elan 6000 or 9000 ICP Mass spectrometer analysed for a 40 element package comprising: Ag, Al, As, Ba, Be, Bi, Ca, Cd, Ce, Co, Cr, Cu, Fe, Hf, K, La, Li, Mg, Mn, Mo, Na, Nb, Ni, P, Pb, Rb, S, Sb, Sc, Sn, Sr, Ta, Th, Ti, U, V, W, Y, Zn and Zr. Very high grade samples may require a 0.4 g to 100 mL or 0.25 g to 250 mL sample to solution ratio for accurate determination.

#### Quality Control and Data Verification

An Analytical Batch (1 page) comprises 33 samples. QA/QC protocol incorporates a sample-prep blank (G-1) carried through all stages of preparation and analysis as the first sample, a pulp duplicate to monitor analytical precision, a -10 mesh rejects duplicate to monitor sub-sampling variation (drill core only), two reagent blanks to measure background and aliquots of in-house Standard Reference Materials like STD SF-2t to monitor accuracy.

Raw and final data undergo a final verification by a British Columbia Certified Assayer who signs the Analytical Report before it is released to the client. Certified assayers are Clarence Leong, Raymond Chan, Leo Arciaga, Ken Kwok, Marcus Lau, and Jacky Wang.

## **APPENDIX C**

### **ANALYTICAL CERTIFICATES**



1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Submitted By: Ted Oliver  
Receiving Lab: Canada-Smithers  
Received: September 21, 2009  
Report Date: October 13, 2009  
Page: 1 of 7

## CERTIFICATE OF ANALYSIS

SMI09000252.1

### CLIENT JOB INFORMATION

Project: Bodine  
Shipment ID:  
P.O. Number: WARR\_SSN\_B9009\_Sept1809  
Number of Samples: 152

### SAMPLE DISPOSAL

RTRN-PLP Return  
RTRN-RJT Return

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6  
Canada

CC:

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R150	143	Crush split and pulverize drill core to 200 mesh			VAN
3B	151	Fire assay fusion Au by ICP-ES	30	Completed	VAN
7TX	151	4 Acid Digestion Analysis by ICP-ES/ICP-MS	0.5	Completed	VAN

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.  
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.  
\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 2 of 7 Part 1

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835650	Drill Core	4.42	2	0.5	8.1	3.6	68	<0.5	3.0	3	567	1.73	7	<0.5	<0.5	219	<0.5	<0.5	<0.5	25	1.58
835651	Drill Core	5.24	2	<0.5	7.4	1.3	164	<0.5	1.5	1	1163	3.79	<5	<0.5	0.7	79	<0.5	<0.5	<0.5	18	1.34
835652	Drill Core	5.89	<2	<0.5	4.7	2.3	127	<0.5	<0.5	<1	719	2.38	<5	<0.5	0.5	136	<0.5	<0.5	<0.5	<10	1.01
835653	Drill Core	6.82	<2	<0.5	9.0	3.1	132	<0.5	2.3	1	865	2.36	<5	<0.5	0.6	79	0.6	<0.5	<0.5	10	1.46
835654	Drill Core	6.80	<2	<0.5	4.7	3.4	156	<0.5	1.1	1	828	2.67	<5	0.7	0.6	110	1.1	<0.5	<0.5	<10	0.61
835655	Drill Core	6.55	<2	<0.5	6.6	2.6	157	<0.5	<0.5	<1	749	2.02	<5	0.7	<0.5	180	1.5	<0.5	<0.5	<10	1.15
835656	Drill Core	6.50	<2	<0.5	2.3	2.7	143	<0.5	0.9	1	1016	2.81	<5	<0.5	0.8	52	<0.5	<0.5	<0.5	<10	1.10
835657	Rock Pulp	0.17	54	18.9	6078	7141	31760	22.5	64.6	64	1111	11.88	61	1.8	1.1	178	168.3	38.5	29.6	187	4.16
835658	Drill Core	6.78	<2	0.7	10.1	3.9	96	<0.5	0.9	1	835	1.75	<5	2.0	<0.5	114	2.1	<0.5	<0.5	<10	1.94
835659	Drill Core	6.05	<2	0.7	4.2	2.8	141	<0.5	<0.5	1	1067	3.25	<5	<0.5	0.6	112	<0.5	<0.5	<0.5	<10	1.94
835660	Drill Core	6.80	<2	<0.5	6.5	1.7	160	<0.5	<0.5	1	1090	3.24	<5	<0.5	0.7	113	<0.5	<0.5	<0.5	<10	1.65
835661	Drill Core	6.15	<2	<0.5	2.3	2.6	134	<0.5	<0.5	<1	956	2.97	<5	0.8	0.6	71	<0.5	<0.5	<0.5	<10	1.12
835662	Drill Core	4.37	<2	<0.5	7.6	2.3	104	<0.5	0.9	<1	545	1.59	<5	1.4	<0.5	47	<0.5	<0.5	<0.5	<10	0.72
835663	Drill Core	2.01	<2	2.2	5.4	4.0	154	<0.5	1.0	3	1359	2.91	<5	0.9	0.6	145	<0.5	0.5	<0.5	<10	2.56
835664	Drill Core	6.39	<2	0.6	5.7	2.3	90	<0.5	<0.5	1	682	2.01	<5	<0.5	<0.5	78	<0.5	0.5	<0.5	<10	0.88
835665	Drill Core	2.90	<2	1.0	1.8	3.1	124	<0.5	0.7	1	844	2.33	<5	<0.5	<0.5	94	<0.5	<0.5	<0.5	<10	1.03
835666	Drill Core	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
835667	Drill Core	4.66	<2	<0.5	2.4	3.1	119	<0.5	0.7	<1	867	2.67	<5	<0.5	<0.5	51	<0.5	<0.5	<0.5	<10	0.64
835668	Drill Core	7.45	<2	<0.5	2.1	2.0	143	<0.5	<0.5	1	1023	3.14	<5	<0.5	0.5	58	<0.5	<0.5	<0.5	<10	0.83
835669	Drill Core	7.01	<2	<0.5	7.6	2.7	125	<0.5	1.5	2	930	2.90	18	<0.5	<0.5	78	<0.5	<0.5	<0.5	<10	1.33
835670	Drill Core	7.53	<2	<0.5	20.0	5.7	75	<0.5	3.3	9	1092	3.29	5	<0.5	<0.5	102	<0.5	<0.5	<0.5	68	2.04
835671	Drill Core	7.35	<2	<0.5	23.2	3.6	77	<0.5	2.0	9	1231	3.53	7	<0.5	<0.5	113	<0.5	<0.5	<0.5	80	2.32
835672	Drill Core	6.12	<2	0.7	30.1	5.0	89	<0.5	3.3	10	1143	4.21	8	0.6	0.9	86	<0.5	<0.5	<0.5	92	1.81
835673	Drill Core	5.54	<2	0.8	27.0	7.1	101	<0.5	0.8	3	524	1.76	<5	1.6	2.1	66	0.9	<0.5	<0.5	15	1.35
835674	Drill Core	6.78	<2	1.9	22.2	11.0	104	<0.5	0.9	2	513	2.10	<5	1.8	1.8	53	1.2	<0.5	<0.5	14	0.94
835675	Drill Core	7.00	<2	0.5	8.9	8.5	120	<0.5	0.8	2	548	2.80	<5	0.8	1.1	48	0.5	<0.5	<0.5	<10	0.72
835676	Drill Core	6.04	5	0.7	38.1	10.0	134	<0.5	61.2	15	1206	3.68	<5	1.0	1.5	377	0.6	1.1	<0.5	81	3.80
835677	Rock Pulp	0.16	56	15.1	6129	7088	31748	22.1	60.3	64	1042	11.90	59	1.7	1.1	181	173.5	30.9	28.5	175	4.05
835678	Drill Core	6.25	<2	<0.5	5.3	6.3	130	<0.5	1.0	2	656	2.63	<5	0.5	0.6	103	<0.5	<0.5	<0.5	<10	1.40
835679	Drill Core	6.06	<2	<0.5	6.9	3.8	148	<0.5	<0.5	1	666	3.36	<5	<0.5	1.0	187	<0.5	<0.5	<0.5	<10	1.68

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 2 of 7 Part 2

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835650	Drill Core	0.03	5.7	13	0.52	30	0.190	4.05	2.95	0.38	0.7	8.2	18	2.4	30.2	2.4	<0.5	<5	7	1.6	<0.5
835651	Drill Core	0.05	6.7	9	1.34	162	0.280	7.24	1.72	3.31	<0.5	10.1	23	2.3	46.4	4.3	<0.5	<5	15	17.9	<0.5
835652	Drill Core	0.05	9.0	9	0.76	90	0.254	6.20	2.87	1.73	<0.5	17.0	29	2.1	47.7	4.0	<0.5	<5	11	6.9	<0.5
835653	Drill Core	0.03	7.7	7	0.87	80	0.221	5.58	2.61	1.41	<0.5	26.5	24	1.4	32.7	4.3	<0.5	<5	10	12.4	<0.5
835654	Drill Core	0.04	9.9	9	0.69	76	0.264	6.11	3.40	1.57	<0.5	26.8	31	2.2	46.9	4.6	<0.5	<5	12	6.8	<0.5
835655	Drill Core	0.03	8.3	10	0.36	61	0.209	5.49	2.99	1.04	0.5	23.0	26	2.3	44.1	4.1	<0.5	<5	8	2.6	<0.5
835656	Drill Core	0.04	10.2	8	0.95	96	0.256	6.40	2.81	2.02	<0.5	27.6	30	2.6	52.4	5.1	<0.5	<5	10	7.8	<0.5
835657	Rock Pulp	0.07	6.2	95	2.57	985	0.441	5.92	1.48	0.71	25.0	13.4	14	12.9	15.1	3.2	<0.5	<5	21	17.3	6.8
835658	Drill Core	0.03	5.5	13	0.42	30	0.154	4.15	3.12	0.49	<0.5	90.2	17	1.6	29.6	3.3	<0.5	<5	7	4.0	<0.5
835659	Drill Core	0.04	10.4	9	1.02	104	0.265	7.07	2.79	2.09	<0.5	28.8	32	1.9	57.2	4.4	<0.5	<5	12	8.8	<0.5
835660	Drill Core	0.04	10.5	5	0.99	93	0.294	7.59	3.75	1.77	<0.5	40.5	33	1.8	51.8	4.8	<0.5	<5	13	7.6	<0.5
835661	Drill Core	0.04	10.0	15	0.77	82	0.258	6.39	3.04	1.59	<0.5	53.6	31	2.1	42.5	4.5	<0.5	<5	12	4.1	<0.5
835662	Drill Core	0.04	5.5	10	0.36	28	0.174	4.58	3.10	0.51	<0.5	150.9	19	1.0	42.1	3.2	<0.5	<5	8	7.7	<0.5
835663	Drill Core	0.03	6.9	13	1.03	23	0.173	4.61	2.45	0.59	<0.5	64.4	20	1.2	55.7	2.3	<0.5	<5	10	10.7	<0.5
835664	Drill Core	0.03	7.7	13	0.56	59	0.182	5.02	2.82	0.70	<0.5	36.3	24	1.3	19.3	2.8	<0.5	<5	9	7.1	<0.5
835665	Drill Core	0.03	7.2	22	0.80	121	0.226	5.77	2.78	1.36	<0.5	17.1	23	1.9	19.1	4.3	<0.5	<5	10	14.2	<0.5
835666	Drill Core	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
835667	Drill Core	0.03	8.0	26	0.83	68	0.233	5.85	3.83	0.56	<0.5	45.5	26	1.5	29.7	4.0	<0.5	<5	9	6.1	<0.5
835668	Drill Core	0.04	10.3	11	1.10	186	0.250	6.34	3.08	1.20	<0.5	12.7	32	2.2	32.7	4.5	<0.5	<5	11	8.7	<0.5
835669	Drill Core	0.03	7.3	15	1.00	209	0.230	5.60	2.50	1.44	<0.5	15.5	23	2.2	26.9	3.7	<0.5	<5	10	10.1	<0.5
835670	Drill Core	0.05	4.3	24	1.24	131	0.275	5.71	2.73	1.08	<0.5	6.3	11	0.9	19.9	1.1	<0.5	<5	12	8.5	<0.5
835671	Drill Core	0.04	4.2	13	1.50	175	0.310	6.92	3.01	1.47	<0.5	7.1	11	0.5	23.9	1.0	<0.5	<5	15	6.1	<0.5
835672	Drill Core	0.05	5.5	17	1.84	285	0.334	7.71	2.59	2.07	<0.5	30.5	15	1.6	30.3	1.8	<0.5	<5	18	10.6	<0.5
835673	Drill Core	0.02	9.7	15	0.92	240	0.147	6.28	2.09	2.35	<0.5	53.0	26	2.1	42.0	3.5	<0.5	<5	9	5.6	<0.5
835674	Drill Core	0.02	10.9	17	0.94	255	0.170	6.22	2.48	2.20	<0.5	72.8	29	3.1	45.6	3.8	<0.5	<5	10	8.0	<0.5
835675	Drill Core	0.03	9.8	18	0.79	200	0.169	6.12	2.99	1.59	<0.5	40.7	28	1.8	23.5	2.5	<0.5	<5	11	5.2	<0.5
835676	Drill Core	0.21	22.9	109	1.87	395	0.399	5.65	2.93	0.63	<0.5	96.0	53	1.5	18.0	8.7	<0.5	<5	12	6.5	<0.5
835677	Rock Pulp	0.07	6.0	113	2.60	962	0.443	5.94	1.50	0.71	23.8	33.2	12	12.7	15.5	3.5	<0.5	<5	23	20.1	6.7
835678	Drill Core	0.02	8.3	7	0.74	79	0.168	5.78	3.08	0.85	<0.5	45.2	25	2.0	41.5	3.3	<0.5	<5	10	5.3	<0.5
835679	Drill Core	0.03	8.2	8	0.90	107	0.172	6.11	2.68	1.07	<0.5	26.4	25	1.2	40.1	3.8	<0.5	<5	11	7.0	<0.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 13, 2009

Page: 2 of 7 Part 3

CERTIFICATE OF ANALYSIS

SMI09000252.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb, 7TX Hf. Rows include sample IDs (835650-835679) and their corresponding analytical results for Rb and Hf.





Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 3 of 7 Part 1

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835680	Drill Core	7.48	<2	<0.5	9.1	3.5	144	<0.5	1.5	1	647	2.78	<5	<0.5	1.2	80	<0.5	<0.5	<0.5	<10	0.92
835681	Drill Core	6.11	<2	0.5	18.9	5.0	158	<0.5	0.9	2	1375	3.28	<5	<0.5	0.9	72	0.5	0.6	<0.5	11	1.43
835682	Drill Core	5.61	3	1.6	8.4	8.1	154	<0.5	0.8	1	1112	3.01	8	<0.5	0.8	70	<0.5	0.8	<0.5	<10	0.91
835683	Drill Core	6.81	4	1.2	7.6	7.0	111	<0.5	0.6	2	638	2.62	13	1.2	0.5	57	<0.5	0.9	<0.5	<10	0.87
835684	Drill Core	6.26	5	<0.5	<0.5	4.7	90	<0.5	<0.5	1	499	2.23	14	2.3	1.0	79	0.7	0.8	<0.5	<10	1.66
835685	Drill Core	6.27	3	0.7	1.2	2.8	113	<0.5	<0.5	<1	865	2.58	7	<0.5	0.6	80	<0.5	0.7	<0.5	<10	0.88
835686	Drill Core	6.81	2	1.3	<0.5	3.3	122	<0.5	<0.5	1	1063	2.74	11	<0.5	0.7	149	<0.5	0.8	<0.5	<10	0.91
835687	Drill Core	6.67	3	2.5	12.5	5.1	191	<0.5	<0.5	2	1212	2.70	7	<0.5	0.7	77	0.7	0.6	<0.5	14	1.07
835688	Drill Core	6.96	2	<0.5	8.7	2.2	74	<0.5	<0.5	<1	458	1.60	5	0.6	<0.5	71	<0.5	<0.5	<0.5	<10	0.83
835689	Drill Core	6.72	3	0.7	3.9	3.8	116	<0.5	1.2	1	779	2.38	10	1.2	<0.5	62	<0.5	<0.5	<0.5	<10	0.77
835690	Drill Core	6.56	13	0.9	4.2	73.6	118	<0.5	1.2	<1	904	2.39	<5	2.7	0.6	89	0.5	0.5	<0.5	<10	1.44
835691	Drill Core	6.59	3	0.6	7.4	4.0	100	<0.5	23.4	6	934	2.54	14	1.4	0.9	162	<0.5	1.0	<0.5	31	2.37
835692	Drill Core	6.82	16	1.0	17.1	3.7	130	<0.5	38.2	10	1472	3.66	9	0.7	1.4	297	<0.5	1.0	<0.5	53	2.59
835693	Drill Core	6.98	5	0.9	1.4	9.0	140	<0.5	7.8	2	1184	2.39	16	1.1	0.9	98	<0.5	0.9	<0.5	11	1.46
835694	Drill Core	6.52	3	<0.5	0.6	4.1	172	<0.5	<0.5	<1	1029	2.28	13	0.5	0.6	58	<0.5	0.7	<0.5	<10	0.87
835695	Drill Core	6.68	8	1.1	6.4	47.5	255	<0.5	<0.5	1	967	2.42	24	1.0	0.6	49	0.8	0.9	<0.5	<10	0.70
835696	Drill Core	7.31	8	0.5	8.1	11.2	185	<0.5	0.6	1	1360	2.73	14	0.6	0.6	41	<0.5	0.6	<0.5	<10	0.59
835697	Rock Pulp	0.15	59	16.7	6090	7078	32474	22.1	57.9	63	1019	11.77	63	1.7	1.0	177	168.1	38.0	30.3	193	4.09
835698	Drill Core	6.16	5	2.8	8.5	34.4	575	<0.5	<0.5	<1	1740	2.39	12	0.7	0.6	48	1.9	0.8	<0.5	<10	0.69
835699	Drill Core	6.57	8	1.8	17.7	306.5	1053	0.6	1.8	1	1952	2.70	17	<0.5	0.6	47	4.4	0.8	<0.5	<10	0.98
835700	Drill Core	6.76	6	<0.5	6.4	13.1	181	<0.5	<0.5	1	1616	2.79	22	<0.5	<0.5	41	<0.5	0.5	<0.5	<10	0.65
835701	Drill Core	6.69	3	2.0	4.1	76.9	291	<0.5	2.2	2	1718	2.39	11	0.9	0.5	58	1.9	<0.5	<0.5	<10	1.06
835702	Drill Core	6.59	3	1.1	7.0	19.8	210	<0.5	13.2	3	1708	2.75	12	<0.5	0.6	68	<0.5	<0.5	<0.5	20	0.81
835703	Drill Core	7.47	5	0.9	27.8	22.6	321	<0.5	3.4	2	1370	2.88	11	<0.5	<0.5	37	<0.5	0.6	<0.5	12	0.37
835704	Drill Core	7.64	4	2.0	14.6	26.3	149	<0.5	1.0	2	1049	2.30	13	<0.5	<0.5	31	<0.5	0.6	<0.5	<10	0.35
835705	Drill Core	6.91	2	1.3	4.5	54.9	141	<0.5	1.2	1	1286	2.91	9	<0.5	0.5	35	<0.5	<0.5	<0.5	<10	0.47
835706	Drill Core	6.97	9	2.7	16.6	27.7	269	<0.5	2.6	2	1623	3.63	9	0.9	<0.5	29	<0.5	<0.5	<0.5	20	0.17
835707	Drill Core	6.76	3246	2.5	1243	39.8	1778	1.6	1.8	2	1451	3.69	28	<0.5	<0.5	29	14.0	1.5	<0.5	12	0.18
835708	Drill Core	3.73	93	2.4	322.0	24.9	1201	0.6	0.9	5	2158	3.83	32	<0.5	<0.5	44	7.7	0.9	<0.5	55	0.59
835709	Drill Core	5.86	43	1.4	123.8	25.7	1814	<0.5	5.8	33	3501	9.76	50	<0.5	<0.5	36	6.4	2.0	<0.5	407	0.35

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 3 of 7 Part 2

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835680	Drill Core	0.03	9.1	30	0.94	119	0.204	7.12	3.74	1.13	<0.5	19.4	28	2.7	44.7	4.6	<0.5	<5	11	6.7	<0.5
835681	Drill Core	0.03	7.1	15	1.27	213	0.194	6.41	3.36	1.03	<0.5	26.4	22	1.8	37.9	3.8	<0.5	<5	11	4.6	<0.5
835682	Drill Core	0.04	10.2	17	1.17	146	0.276	7.10	3.84	1.23	<0.5	54.6	34	2.3	50.0	4.6	<0.5	<5	12	7.0	1.2
835683	Drill Core	0.04	9.1	36	0.68	97	0.249	6.36	4.13	0.97	<0.5	74.8	27	2.0	40.5	4.2	<0.5	<5	10	0.6	1.5
835684	Drill Core	0.04	9.1	9	0.42	78	0.235	6.29	4.37	0.77	<0.5	250.3	28	2.1	34.2	5.4	<0.5	<5	12	1.9	1.8
835685	Drill Core	0.03	10.0	10	0.76	134	0.259	6.18	3.35	1.34	<0.5	27.2	31	1.9	52.8	4.6	<0.5	<5	10	3.0	0.8
835686	Drill Core	0.03	9.5	7	0.87	160	0.270	6.52	3.07	1.61	<0.5	80.2	29	1.8	53.2	4.2	<0.5	<5	11	5.5	<0.5
835687	Drill Core	0.03	8.6	8	1.13	152	0.219	5.77	2.48	1.57	<0.5	134.1	25	2.2	52.0	4.0	<0.5	<5	11	10.4	1.1
835688	Drill Core	0.04	7.3	10	0.39	69	0.219	5.95	4.97	0.19	<0.5	78.8	25	2.0	26.0	4.0	<0.5	<5	7	<0.5	1.2
835689	Drill Core	0.04	12.5	7	0.89	31	0.234	6.42	4.98	0.15	<0.5	102.2	37	2.0	37.3	4.4	<0.5	<5	9	2.3	1.2
835690	Drill Core	0.04	9.0	15	0.75	97	0.225	6.15	4.46	0.46	<0.5	235.2	27	1.9	35.6	4.1	<0.5	<5	10	0.5	1.4
835691	Drill Core	0.10	14.7	37	1.50	104	0.301	6.12	4.26	0.25	0.6	236.6	40	1.6	26.4	5.8	<0.5	<5	11	7.6	0.9
835692	Drill Core	0.15	19.5	55	2.19	1115	0.406	6.58	2.77	1.45	0.7	190.7	52	2.2	32.2	8.1	<0.5	<5	14	18.1	<0.5
835693	Drill Core	0.05	11.2	15	1.20	168	0.262	6.48	3.95	0.81	<0.5	128.1	34	2.3	33.2	4.4	<0.5	<5	12	2.6	0.6
835694	Drill Core	0.04	10.7	7	1.42	119	0.257	6.81	4.23	0.67	<0.5	146.5	32	2.3	28.8	4.9	<0.5	<5	11	6.1	0.6
835695	Drill Core	0.04	11.1	125	1.47	311	0.308	6.84	3.91	1.47	<0.5	94.7	34	2.6	25.2	5.3	<0.5	<5	13	8.7	0.7
835696	Drill Core	0.04	9.8	8	1.46	275	0.276	6.98	3.83	1.06	<0.5	72.7	30	2.5	36.5	5.0	<0.5	<5	13	5.3	0.9
835697	Rock Pulp	0.06	5.9	82	2.55	359	0.463	5.97	1.47	0.69	29.4	14.1	13	14.2	16.8	3.1	<0.5	<5	22	21.4	6.9
835698	Drill Core	0.03	9.0	12	2.18	232	0.179	6.16	2.89	0.86	<0.5	82.0	27	1.7	33.1	3.7	<0.5	<5	12	11.8	0.8
835699	Drill Core	0.03	8.8	7	2.25	195	0.178	6.18	3.04	0.70	<0.5	66.5	26	1.7	34.6	3.5	<0.5	<5	12	18.2	1.3
835700	Drill Core	0.04	9.1	10	1.79	356	0.262	6.81	3.19	1.19	<0.5	23.6	29	2.0	47.1	5.0	<0.5	<5	12	13.4	1.2
835701	Drill Core	0.05	12.3	6	2.14	176	0.295	7.19	4.13	0.55	<0.5	96.4	36	2.3	43.7	4.8	<0.5	<5	12	10.8	0.9
835702	Drill Core	0.07	12.1	32	2.02	301	0.266	6.61	3.65	0.58	<0.5	32.3	34	2.1	25.3	5.3	<0.5	<5	12	10.3	0.7
835703	Drill Core	0.03	7.7	9	1.97	284	0.204	6.33	2.57	1.01	<0.5	38.9	25	1.8	19.0	3.1	<0.5	<5	12	13.3	1.3
835704	Drill Core	0.04	9.2	9	1.98	199	0.225	6.58	3.62	0.73	<0.5	44.2	27	1.6	21.6	3.9	<0.5	<5	10	7.1	1.3
835705	Drill Core	0.03	10.8	7	2.63	394	0.217	7.56	2.78	1.35	<0.5	93.8	33	2.0	21.5	3.9	<0.5	<5	13	13.9	1.5
835706	Drill Core	0.04	7.4	10	2.49	593	0.215	6.67	1.41	1.73	<0.5	74.5	23	2.0	19.2	2.5	<0.5	<5	16	16.6	1.4
835707	Drill Core	0.05	7.6	8	1.50	520	0.203	5.78	1.83	1.35	<0.5	25.5	23	2.7	14.6	2.5	<0.5	<5	12	10.7	2.0
835708	Drill Core	0.05	6.0	8	1.09	698	0.200	4.91	0.94	1.34	<0.5	25.5	18	0.9	15.4	1.1	<0.5	<5	11	4.9	2.5
835709	Drill Core	0.13	4.8	3	2.71	220	0.740	7.64	0.93	1.63	0.9	61.3	15	1.7	19.3	1.1	<0.5	<5	40	18.9	5.9

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 13, 2009

Page: 3 of 7 Part 3

CERTIFICATE OF ANALYSIS

SMI09000252.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (835680-835709) and sample types (Drill Core, Rock Pulp) with corresponding analytical values.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 4 of 7 Part 1

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835710	Drill Core	4.58	51	5.0	460.8	32.9	3249	1.4	1.3	4	543	5.29	101	<0.5	<0.5	38	17.0	8.8	<0.5	41	0.18
835711	Drill Core	7.37	19	8.4	107.2	48.1	1492	<0.5	<0.5	4	709	2.69	30	<0.5	<0.5	36	7.4	1.1	<0.5	22	0.04
835712	Drill Core	5.94	5	2.8	86.5	33.9	3619	<0.5	1.8	<1	647	1.62	29	<0.5	0.8	51	19.1	3.5	<0.5	<10	0.11
835713	Drill Core	5.80	5	1.2	38.4	5.7	2100	<0.5	0.6	2	1359	3.29	13	<0.5	<0.5	36	11.6	<0.5	<0.5	13	0.15
835714	Drill Core	6.90	10	1.9	636.2	320.7	5940	1.1	0.6	<1	1079	3.36	216	<0.5	<0.5	37	33.0	7.2	<0.5	<10	0.12
835715	Drill Core	4.56	<2	1.3	30.4	13.4	986	<0.5	0.5	<1	1446	3.76	22	<0.5	<0.5	39	4.8	<0.5	<0.5	<10	0.08
835716	Drill Core	4.81	4	2.4	93.2	26.9	1220	<0.5	0.5	<1	862	4.08	47	<0.5	<0.5	34	6.3	1.8	<0.5	<10	0.05
835717	Drill Core	0.98	<2	<0.5	2.7	20.0	69	<0.5	3.7	6	831	2.46	<5	3.3	6.0	737	<0.5	<0.5	<0.5	56	2.66
835718	Rock Pulp	0.17	73	17.2	6090	7193	32189	22.9	62.0	68	1070	11.77	65	1.6	0.9	173	178.1	40.5	29.3	189	4.17
835719	Drill Core	7.83	4	1.9	67.2	31.3	1469	<0.5	<0.5	<1	1386	3.55	23	<0.5	<0.5	47	8.3	0.7	<0.5	<10	0.35
835720	Drill Core	7.36	6	3.7	298.6	40.5	2836	0.5	1.8	1	1069	4.10	22	<0.5	<0.5	42	15.5	0.5	<0.5	<10	0.24
835721	Drill Core	7.52	3	0.9	198.3	12.1	3898	<0.5	1.0	<1	859	3.31	8	<0.5	<0.5	36	21.6	<0.5	<0.5	<10	0.08
835722	Drill Core	8.46	<2	0.9	51.6	16.6	1333	<0.5	1.1	<1	770	3.79	17	<0.5	<0.5	39	6.6	0.6	<0.5	10	0.08
835723	Drill Core	7.31	6	1.2	34.6	11.1	730	<0.5	0.7	<1	965	3.62	8	<0.5	<0.5	35	3.8	<0.5	<0.5	<10	0.09
835724	Drill Core	7.86	2	1.4	41.5	12.6	1629	<0.5	3.2	1	1118	3.53	9	<0.5	<0.5	31	8.1	<0.5	<0.5	<10	0.09
835725	Drill Core	7.48	<2	1.9	149.9	26.3	5672	<0.5	<0.5	<1	1068	3.64	22	<0.5	<0.5	31	30.5	0.7	<0.5	<10	0.09
835726	Drill Core	7.07	<2	1.0	127.9	58.2	2158	<0.5	1.0	<1	708	3.09	42	<0.5	<0.5	29	12.2	3.9	<0.5	<10	0.09
835727	Drill Core	7.46	<2	<0.5	79.1	9.8	1060	<0.5	0.5	<1	631	2.70	27	<0.5	<0.5	30	5.2	3.3	<0.5	<10	0.08
835728	Drill Core	7.94	5	0.8	25.2	9.7	548	<0.5	<0.5	1	2150	3.60	<5	<0.5	<0.5	30	1.3	<0.5	<0.5	<10	0.09
835729	Drill Core	7.41	2	0.6	50.6	20.2	1703	<0.5	<0.5	<1	1371	2.80	7	<0.5	<0.5	28	8.2	<0.5	<0.5	10	0.11
835730	Drill Core	7.04	3	0.9	98.0	8.7	1742	<0.5	1.8	2	1820	3.09	<5	<0.5	<0.5	32	8.9	<0.5	<0.5	10	0.19
835731	Drill Core	7.29	<2	0.7	45.4	27.1	2114	<0.5	<0.5	<1	1082	1.80	<5	<0.5	0.5	32	12.5	<0.5	<0.5	<10	0.16
835732	Drill Core	7.38	5	1.8	106.0	77.2	3368	<0.5	<0.5	<1	1080	1.99	11	<0.5	0.6	33	20.5	0.5	<0.5	<10	0.20
835733	Drill Core	7.26	23	2.9	549.2	48.7	8540	0.8	<0.5	2	1755	3.45	9	<0.5	<0.5	30	51.5	<0.5	<0.5	12	0.31
835734	Drill Core	7.53	8	1.2	85.6	19.6	2096	<0.5	2.7	3	2111	4.64	7	<0.5	<0.5	31	10.6	<0.5	<0.5	16	0.19
835735	Drill Core	7.48	5	0.5	64.0	10.2	1466	<0.5	1.5	3	1957	4.07	6	<0.5	<0.5	32	6.4	<0.5	<0.5	18	0.23
835736	Drill Core	7.41	9	1.1	154.2	16.7	3078	<0.5	1.9	4	1724	3.90	8	<0.5	<0.5	34	17.8	<0.5	<0.5	17	0.29
835737	Drill Core	7.80	5	0.9	57.6	10.5	2202	<0.5	0.7	5	2809	4.67	<5	<0.5	<0.5	31	12.3	<0.5	<0.5	25	0.46
835738	Rock Pulp	0.17	53	17.0	6110	7050	33313	24.6	58.9	65	1090	12.08	61	1.9	1.1	178	190.3	39.5	29.3	197	4.17
835739	Drill Core	8.21	7	3.7	85.8	31.1	1503	<0.5	2.7	5	1347	7.47	14	<0.5	<0.5	57	16.7	0.7	8.4	37	0.23

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 4 of 7 Part 2

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835710	Drill Core	0.02	4.8	8	0.51	405	0.125	4.26	1.43	0.97	<0.5	48.0	15	1.4	17.3	1.3	<0.5	<5	9	2.1	5.1
835711	Drill Core	0.02	4.1	9	1.07	571	0.121	4.45	0.67	1.18	<0.5	28.8	12	1.2	9.8	1.4	<0.5	<5	9	3.2	2.3
835712	Drill Core	<0.01	6.4	11	1.04	414	0.056	5.11	1.36	1.08	<0.5	53.7	18	1.0	11.2	2.2	<0.5	<5	9	3.7	1.5
835713	Drill Core	0.02	5.6	6	2.06	291	0.132	5.49	1.92	0.63	<0.5	26.0	17	1.4	15.6	2.1	<0.5	<5	10	9.4	2.8
835714	Drill Core	0.02	5.2	6	1.61	233	0.109	4.67	1.38	0.64	<0.5	12.7	16	1.9	15.3	2.0	<0.5	<5	9	11.0	3.3
835715	Drill Core	0.02	6.2	9	2.12	250	0.127	5.96	2.07	0.59	<0.5	27.7	19	1.7	19.0	1.9	<0.5	<5	11	7.1	3.3
835716	Drill Core	0.01	6.5	6	1.24	228	0.113	5.40	2.48	0.55	<0.5	18.0	19	1.6	16.5	1.7	<0.5	<5	10	7.3	4.0
835717	Drill Core	0.09	21.7	38	0.75	991	0.250	7.51	2.68	2.85	<0.5	9.8	43	1.4	14.0	24.4	1.6	<5	5	34.2	<0.5
835718	Rock Pulp	0.06	5.8	251	2.58	525	0.453	5.96	1.47	0.69	25.0	13.8	13	15.6	16.3	2.8	<0.5	<5	22	23.3	6.7
835719	Drill Core	0.01	6.2	5	1.47	554	0.108	5.29	2.48	0.47	<0.5	19.7	20	1.7	13.0	11.9	5.5	<5	9	7.5	3.4
835720	Drill Core	0.02	7.0	6	1.15	288	0.115	5.10	2.47	0.46	<0.5	16.5	22	2.0	19.7	11.4	8.0	<5	9	6.2	4.1
835721	Drill Core	0.02	7.7	5	1.16	168	0.132	5.39	2.35	0.59	<0.5	25.3	24	1.9	15.7	2.4	<0.5	<5	10	6.5	3.2
835722	Drill Core	0.02	5.7	5	1.13	156	0.130	5.64	2.30	0.68	<0.5	26.6	18	1.8	17.2	2.0	<0.5	<5	10	8.4	3.7
835723	Drill Core	0.01	6.5	6	1.35	87	0.113	5.68	2.59	0.44	<0.5	41.7	21	1.5	13.3	1.5	<0.5	<5	9	5.8	3.5
835724	Drill Core	0.01	6.5	7	1.50	75	0.120	5.59	2.69	0.35	<0.5	25.4	20	1.7	16.2	2.0	<0.5	<5	9	7.6	3.4
835725	Drill Core	0.01	6.6	6	1.46	119	0.119	5.35	2.29	0.50	<0.5	57.2	19	1.3	16.9	1.8	<0.5	<5	9	7.2	3.6
835726	Drill Core	0.02	5.7	10	0.98	83	0.125	5.44	3.05	0.39	<0.5	33.9	18	1.7	18.6	2.0	<0.5	<5	9	5.2	3.0
835727	Drill Core	0.02	5.9	14	0.92	47	0.114	5.26	3.13	0.23	<0.5	111.3	18	1.2	18.3	1.4	<0.5	<5	8	4.4	2.6
835728	Drill Core	0.02	5.9	6	2.98	39	0.129	5.94	2.23	0.19	<0.5	30.0	19	1.4	18.3	1.8	<0.5	<5	10	10.6	2.9
835729	Drill Core	0.03	5.2	10	1.65	90	0.136	5.40	2.26	0.53	<0.5	20.5	16	1.6	16.0	1.5	<0.5	<5	9	5.2	2.4
835730	Drill Core	0.05	11.2	9	1.98	118	0.201	6.20	2.46	0.75	<0.5	17.5	33	2.4	16.9	2.3	<0.5	<5	10	7.2	2.5
835731	Drill Core	0.03	9.0	6	1.17	90	0.144	6.50	3.70	0.61	<0.5	10.6	27	2.1	11.3	2.5	<0.5	<5	8	3.0	1.5
835732	Drill Core	0.03	11.3	7	1.04	116	0.155	6.49	3.55	0.75	<0.5	17.9	32	1.9	11.7	2.6	<0.5	<5	8	4.1	1.7
835733	Drill Core	0.05	4.8	7	1.44	129	0.158	5.52	2.27	0.76	<0.5	10.2	15	1.7	12.2	2.1	<0.5	<5	10	6.0	3.1
835734	Drill Core	0.06	5.7	6	2.17	158	0.185	6.23	1.55	1.09	<0.5	29.6	16	1.4	14.6	1.4	<0.5	<5	14	7.7	3.6
835735	Drill Core	0.09	5.4	9	2.05	152	0.251	6.24	1.79	1.03	<0.5	17.1	17	1.2	13.0	1.6	<0.5	<5	13	7.8	3.2
835736	Drill Core	0.07	9.3	16	1.57	146	0.224	6.20	2.27	0.94	<0.5	27.9	29	1.8	17.5	1.6	<0.5	<5	15	6.0	3.2
835737	Drill Core	0.13	4.2	5	2.39	118	0.291	6.16	1.74	0.85	<0.5	17.6	12	0.8	14.0	1.1	<0.5	<5	13	8.8	3.3
835738	Rock Pulp	0.07	6.3	82	2.60	508	0.462	6.00	1.47	0.71	27.3	14.2	14	16.9	15.3	3.1	<0.5	<5	23	21.2	6.9
835739	Drill Core	0.11	5.9	5	1.62	174	0.245	6.09	0.61	1.50	<0.5	59.0	18	4.5	23.4	1.0	<0.5	<5	17	5.4	7.0

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 13, 2009

Page: 4 of 7 Part 3

CERTIFICATE OF ANALYSIS

SMI09000252.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (835710-835739) and their corresponding analytical results for Drill Core and Rock Pulp samples.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 5 of 7 Part 1

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835740	Drill Core	7.71	3	<0.5	85.0	5.6	1889	<0.5	0.7	5	2642	5.10	<5	<0.5	<0.5	40	10.4	<0.5	1.3	25	0.28
835741	Drill Core	7.03	2	<0.5	77.5	5.7	2346	<0.5	1.0	4	2762	5.12	<5	<0.5	<0.5	37	14.6	<0.5	1.4	25	0.33
835742	Drill Core	7.89	3	<0.5	42.2	5.8	1125	<0.5	<0.5	5	3208	4.97	<5	<0.5	<0.5	36	3.9	<0.5	<0.5	24	0.55
835743	Drill Core	7.43	7	<0.5	107.9	16.4	2213	<0.5	0.8	5	3380	5.75	<5	<0.5	<0.5	33	10.9	<0.5	<0.5	26	0.84
835744	Drill Core	7.27	3	<0.5	224.2	14.6	2340	<0.5	0.6	4	3890	5.55	7	<0.5	<0.5	27	12.6	<0.5	<0.5	27	0.55
835745	Drill Core	6.88	3	<0.5	39.6	4.3	888	<0.5	0.5	4	1938	4.10	<5	<0.5	<0.5	33	6.7	<0.5	<0.5	23	0.34
835746	Drill Core	6.55	3	1.2	177.9	5.2	1235	<0.5	0.9	5	2413	5.25	8	<0.5	<0.5	32	6.6	<0.5	<0.5	32	0.35
835747	Drill Core	7.05	3	0.6	61.1	4.5	3146	<0.5	<0.5	4	2902	5.74	<5	<0.5	<0.5	30	30.0	<0.5	<0.5	30	0.34
835748	Drill Core	6.94	<2	<0.5	34.7	5.0	1476	<0.5	<0.5	4	2742	5.11	6	<0.5	<0.5	25	8.5	<0.5	<0.5	24	0.34
835749	Drill Core	6.89	<2	<0.5	34.9	3.4	985	<0.5	<0.5	4	2126	3.86	<5	<0.5	<0.5	25	5.1	<0.5	<0.5	21	0.32
835750	Drill Core	6.69	4	1.0	31.8	3.9	1611	<0.5	0.6	4	2268	4.31	<5	<0.5	<0.5	27	10.6	<0.5	<0.5	28	0.35
835751	Drill Core	6.72	4	0.8	173.7	4.2	6816	<0.5	1.5	4	2622	5.22	5	<0.5	<0.5	28	47.5	<0.5	<0.5	26	0.34
835752	Drill Core	6.31	4	1.0	229.0	5.3	9175	<0.5	0.9	4	2549	5.79	5	<0.5	<0.5	33	63.2	<0.5	<0.5	27	0.32
835753	Drill Core	6.90	2	<0.5	63.7	3.2	1635	<0.5	0.6	3	1741	2.92	<5	<0.5	<0.5	27	9.6	<0.5	<0.5	15	0.30
835754	Drill Core	6.76	7	4.7	194.1	13.6	6583	<0.5	<0.5	3	2378	5.11	11	<0.5	<0.5	28	39.2	<0.5	<0.5	15	0.34
835755	Drill Core	6.86	7	1.3	450.1	8.4	7763	<0.5	0.5	3	3496	5.15	11	<0.5	<0.5	27	48.9	<0.5	<0.5	<10	0.53
835756	Drill Core	6.88	<2	0.6	58.4	5.2	2558	<0.5	0.8	3	3516	4.81	10	<0.5	<0.5	28	11.3	<0.5	<0.5	<10	0.33
835757	Drill Core	5.53	<2	<0.5	42.5	5.0	2090	<0.5	<0.5	3	3330	4.22	8	<0.5	<0.5	24	9.2	<0.5	<0.5	<10	0.29
835758	Rock Pulp	0.17	49	18.2	6155	7128	31941	22.7	64.4	69	1094	12.05	58	1.7	0.8	181	168.5	27.8	28.7	179	4.12
835759	Drill Core	6.11	<2	0.8	77.9	7.4	3311	<0.5	2.2	3	3541	4.90	9	<0.5	<0.5	25	17.0	<0.5	<0.5	<10	0.36
835760	Drill Core	7.19	<2	0.8	96.8	5.1	2163	<0.5	0.9	2	2387	3.38	7	<0.5	<0.5	24	12.1	<0.5	<0.5	<10	0.33
835761	Drill Core	6.71	5	0.9	88.3	5.4	5421	<0.5	0.9	3	3056	4.36	13	<0.5	<0.5	26	30.7	<0.5	<0.5	<10	0.36
835762	Drill Core	6.79	4	1.1	165.0	5.5	5093	<0.5	2.4	2	2684	3.95	6	<0.5	<0.5	27	31.5	<0.5	<0.5	<10	0.47
835763	Drill Core	6.78	<2	7.3	31.5	6.2	1006	<0.5	<0.5	3	3045	4.13	8	<0.5	<0.5	35	4.5	<0.5	<0.5	<10	0.51
835764	Drill Core	6.91	2	1.2	22.7	3.9	1019	<0.5	<0.5	2	2752	4.03	6	<0.5	<0.5	29	6.3	<0.5	<0.5	<10	0.36
835765	Drill Core	7.85	<2	<0.5	27.7	4.4	1112	<0.5	<0.5	3	3601	4.82	8	<0.5	<0.5	26	5.8	<0.5	<0.5	<10	0.40
835766	Drill Core	6.45	<2	0.7	30.8	4.7	1017	<0.5	0.6	2	2691	4.43	8	<0.5	<0.5	26	4.6	<0.5	<0.5	<10	0.26
835767	Drill Core	7.00	<2	<0.5	28.5	6.7	1018	<0.5	1.8	3	3267	4.87	7	<0.5	<0.5	30	3.3	<0.5	<0.5	<10	0.33
835768	Drill Core	6.62	<2	0.6	27.8	4.7	668	<0.5	0.5	3	2985	4.91	7	<0.5	<0.5	25	1.2	<0.5	<0.5	<10	0.28
835769	Drill Core	6.57	<2	<0.5	29.9	3.8	1474	<0.5	0.6	3	3324	4.69	<5	<0.5	<0.5	25	6.1	<0.5	<0.5	<10	0.29

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 5 of 7 Part 2

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835740	Drill Core	0.13	5.5	4	2.62	139	0.260	6.60	1.40	0.95	<0.5	17.9	18	1.6	15.6	0.8	<0.5	<5	15	9.5	3.3
835741	Drill Core	0.13	5.9	5	2.70	122	0.279	6.66	1.71	0.80	<0.5	26.9	19	1.2	18.1	1.1	<0.5	<5	15	9.2	3.2
835742	Drill Core	0.14	6.0	40	2.84	125	0.324	6.73	1.89	0.72	<0.5	27.1	18	0.9	19.5	1.1	<0.5	<5	17	10.0	2.7
835743	Drill Core	0.15	7.0	11	2.90	136	0.342	6.79	2.09	0.71	<0.5	66.4	20	1.3	22.3	1.1	<0.5	<5	16	10.7	3.8
835744	Drill Core	0.12	5.4	21	3.98	129	0.220	6.91	1.59	0.61	<0.5	18.1	16	1.0	27.6	0.9	<0.5	<5	15	12.8	2.9
835745	Drill Core	0.14	4.5	11	2.01	134	0.296	6.32	2.32	0.71	<0.5	20.7	15	1.6	16.9	0.9	<0.5	<5	15	6.5	2.5
835746	Drill Core	0.13	5.8	6	2.85	141	0.326	6.92	2.12	0.84	<0.5	30.1	17	1.3	26.4	0.9	<0.5	<5	18	8.7	3.5
835747	Drill Core	0.14	7.1	6	3.33	139	0.314	7.31	2.45	0.64	<0.5	50.7	22	1.3	20.4	1.0	<0.5	<5	16	7.7	3.8
835748	Drill Core	0.12	4.9	6	3.19	77	0.308	6.84	2.55	0.45	<0.5	24.3	16	0.9	24.4	1.1	<0.5	<5	15	7.4	3.1
835749	Drill Core	0.11	5.8	17	2.35	93	0.259	6.41	2.70	0.56	<0.5	40.5	18	1.0	18.0	0.8	<0.5	<5	14	6.2	2.2
835750	Drill Core	0.11	5.2	17	2.54	97	0.232	6.41	2.65	0.54	<0.5	13.8	17	0.8	17.5	0.9	<0.5	<5	13	7.3	2.7
835751	Drill Core	0.11	4.9	13	3.12	111	0.294	6.47	1.88	0.71	<0.5	21.4	16	1.2	23.5	1.2	<0.5	<5	16	11.2	3.7
835752	Drill Core	0.12	5.5	13	3.04	166	0.326	6.61	1.59	0.98	<0.5	15.2	18	1.4	22.5	1.1	<0.5	<5	18	8.0	4.7
835753	Drill Core	0.10	3.4	20	1.83	91	0.262	5.55	2.66	0.48	<0.5	11.0	11	0.6	11.6	1.1	<0.5	<5	10	3.8	2.0
835754	Drill Core	0.11	5.1	4	2.41	133	0.229	5.70	2.08	0.80	<0.5	20.9	16	1.7	10.5	1.1	<0.5	<5	12	6.3	4.2
835755	Drill Core	0.10	4.5	7	3.11	92	0.189	5.89	2.12	0.50	<0.5	9.4	14	1.4	15.4	1.3	<0.5	<5	14	8.8	3.8
835756	Drill Core	0.10	5.1	2	3.17	84	0.198	6.30	2.40	0.49	<0.5	23.4	16	1.5	16.7	1.3	<0.5	<5	15	10.9	3.0
835757	Drill Core	0.09	4.0	7	2.79	57	0.207	5.88	2.77	0.33	<0.5	8.7	13	1.3	11.7	1.0	<0.5	<5	11	7.4	2.7
835758	Rock Pulp	0.06	6.0	96	2.61	250	0.448	5.98	1.48	0.71	25.1	14.6	13	13.8	16.4	2.5	<0.5	<5	20	19.9	6.7
835759	Drill Core	0.10	5.1	5	3.27	44	0.205	6.56	2.84	0.30	<0.5	17.4	16	0.7	14.2	0.9	<0.5	<5	15	9.0	2.9
835760	Drill Core	0.08	3.8	7	2.35	26	0.210	5.57	3.18	0.16	<0.5	8.1	12	1.0	14.2	1.0	<0.5	<5	13	6.4	2.1
835761	Drill Core	0.09	6.2	3	3.43	76	0.222	6.05	2.01	0.46	<0.5	109.6	20	0.7	19.1	1.0	<0.5	<5	14	10.5	3.1
835762	Drill Core	0.09	4.0	5	2.70	60	0.176	5.42	2.53	0.38	<0.5	9.7	13	1.3	12.1	1.2	<0.5	<5	12	8.7	3.0
835763	Drill Core	0.10	5.0	3	2.84	23	0.183	5.94	3.34	0.12	<0.5	18.9	15	1.9	12.1	1.3	<0.5	<5	14	11.0	2.8
835764	Drill Core	0.10	4.2	7	2.64	22	0.137	5.86	3.54	0.15	<0.5	13.5	14	1.2	11.5	0.8	<0.5	<5	13	6.8	2.7
835765	Drill Core	0.09	4.9	4	3.26	33	0.161	5.99	2.85	0.19	<0.5	13.8	15	1.0	13.4	1.0	<0.5	<5	14	10.0	3.3
835766	Drill Core	0.09	4.2	6	2.74	24	0.158	5.79	3.73	0.12	<0.5	17.6	14	0.8	14.3	1.0	<0.5	<5	11	5.3	3.5
835767	Drill Core	0.09	5.0	4	3.19	46	0.186	6.13	3.10	0.24	<0.5	8.5	15	1.0	16.3	1.2	<0.5	<5	15	9.3	3.6
835768	Drill Core	0.09	4.7	5	3.01	29	0.177	5.89	3.34	0.13	<0.5	9.4	15	1.0	15.6	1.0	<0.5	<5	14	9.4	3.8
835769	Drill Core	0.09	4.9	3	3.23	54	0.178	6.14	3.03	0.21	<0.5	17.3	17	0.6	17.6	1.3	<0.5	<5	14	11.8	3.6

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.





Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 13, 2009

Page: 5 of 7 Part 3

CERTIFICATE OF ANALYSIS

SMI09000252.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (835740-835769) and their corresponding analytical results for Rb and Hf.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 6 of 7 Part 1

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835770	Drill Core	6.39	<2	<0.5	35.9	5.4	2127	<0.5	1.3	2	2631	4.10	<5	<0.5	<0.5	23	13.3	<0.5	<0.5	<10	0.26
835771	Drill Core	6.74	<2	1.0	31.1	5.3	1246	<0.5	2.2	2	4557	3.49	<5	<0.5	0.6	34	6.1	<0.5	<0.5	<10	0.93
835772	Drill Core	6.49	3	1.0	64.6	5.1	1702	<0.5	1.0	3	2759	4.01	5	<0.5	<0.5	28	10.0	<0.5	<0.5	<10	0.32
835773	Drill Core	7.00	<2	<0.5	32.2	4.5	1385	<0.5	<0.5	2	4291	5.02	8	<0.5	<0.5	24	8.3	<0.5	<0.5	<10	0.32
835774	Drill Core	6.49	<2	0.6	19.0	3.1	196	<0.5	0.6	2	1782	3.23	<5	<0.5	<0.5	25	<0.5	<0.5	<0.5	<10	0.30
835775	Drill Core	6.76	<2	0.7	18.4	4.0	361	<0.5	0.8	3	2304	4.00	5	<0.5	<0.5	31	0.6	<0.5	<0.5	<10	0.30
835776	Drill Core	6.86	2	0.5	51.2	6.0	1978	<0.5	1.1	2	2776	4.77	5	<0.5	<0.5	33	12.1	<0.5	<0.5	<10	0.42
835777	Drill Core	7.18	4	0.9	246.5	8.1	3913	<0.5	0.8	3	3107	4.81	<5	<0.5	<0.5	38	24.7	<0.5	0.6	<10	0.48
835778	Rock Pulp	0.17	56	15.9	6142	7063	32155	23.9	63.3	64	1085	11.98	56	1.8	1.0	179	177.5	24.9	27.3	176	4.14
835779	Drill Core	6.96	<2	1.4	69.0	10.6	621	<0.5	1.2	4	2684	5.01	<5	<0.5	<0.5	43	2.1	<0.5	0.7	11	0.32
835780	Drill Core	6.85	<2	1.1	59.8	8.9	3585	<0.5	1.4	3	2448	4.35	<5	<0.5	<0.5	38	18.5	<0.5	<0.5	<10	0.36
835781	Drill Core	6.47	4	1.0	135.7	43.1	2381	<0.5	<0.5	3	3010	4.19	6	<0.5	<0.5	29	13.5	<0.5	<0.5	<10	0.43
835782	Drill Core	7.20	7	1.0	286.9	64.3	8271	<0.5	0.8	4	3614	5.46	12	<0.5	<0.5	29	50.5	<0.5	0.6	<10	0.30
835783	Drill Core	6.84	7	0.8	380.4	90.0	8924	0.5	1.1	3	1232	3.21	10	<0.5	<0.5	30	57.6	<0.5	<0.5	<10	0.24
835784	Drill Core	6.73	6	1.6	150.5	40.8	11488	0.5	1.2	4	2005	4.87	<5	<0.5	<0.5	34	80.1	<0.5	<0.5	14	0.24
835785	Drill Core	6.61	2	<0.5	21.7	5.4	846	<0.5	<0.5	3	3005	4.57	<5	<0.5	<0.5	39	1.3	<0.5	<0.5	12	0.50
835786	Drill Core	6.77	<2	<0.5	45.1	5.4	1019	<0.5	1.2	3	1943	4.45	6	<0.5	<0.5	25	4.2	<0.5	<0.5	13	0.20
835787	Drill Core	6.75	4	1.0	111.8	9.4	2959	<0.5	2.3	5	1760	5.08	13	<0.5	<0.5	39	18.6	0.6	<0.5	26	0.24
835788	Drill Core	6.80	5	1.5	74.3	12.4	4905	<0.5	1.9	4	1281	4.05	8	<0.5	<0.5	33	30.2	<0.5	<0.5	22	0.14
835789	Drill Core	6.58	6	2.2	143.1	11.6	2981	<0.5	2.8	2	1860	3.48	<5	<0.5	<0.5	25	19.9	<0.5	<0.5	12	0.24
835790	Drill Core	6.72	3	1.0	98.1	4.6	1731	<0.5	2.0	3	2291	4.02	<5	<0.5	<0.5	23	12.5	<0.5	<0.5	<10	0.20
835791	Drill Core	6.98	3	0.8	145.9	3.5	2721	<0.5	<0.5	3	1551	3.82	<5	<0.5	<0.5	21	17.0	<0.5	<0.5	<10	0.22
835792	Drill Core	6.74	5	<0.5	78.4	4.5	830	<0.5	<0.5	3	1320	3.54	<5	<0.5	<0.5	23	4.1	<0.5	<0.5	<10	0.40
835793	Drill Core	6.08	4	1.4	80.4	7.7	3037	<0.5	0.8	3	1461	3.80	8	<0.5	<0.5	29	17.6	<0.5	<0.5	14	0.46
835794	Drill Core	6.53	3	1.9	142.8	7.6	2234	<0.5	3.0	4	1224	3.22	<5	<0.5	<0.5	30	14.5	<0.5	<0.5	20	0.24
835795	Drill Core	6.41	<2	1.1	95.9	5.8	1447	<0.5	1.4	3	1438	4.00	<5	<0.5	<0.5	27	7.8	<0.5	<0.5	<10	0.25
835796	Drill Core	6.80	<2	0.6	59.4	7.2	872	<0.5	1.4	3	1252	3.64	<5	<0.5	<0.5	29	3.7	<0.5	<0.5	18	0.23
835797	Drill Core	6.93	<2	0.9	66.2	5.1	2411	<0.5	2.3	3	1348	3.76	<5	<0.5	<0.5	23	14.0	<0.5	<0.5	25	0.23
835798	Rock Pulp	0.17	1601	28.3	9207	5252	20328	84.6	1292	134	1183	33.95	1457	1.6	0.6	18	116.9	237.4	40.1	17	0.84
835799	Drill Core	7.28	4	1.6	203.1	21.4	2271	<0.5	8.7	12	1471	5.27	10	1.2	<0.5	29	11.2	0.6	<0.5	140	0.26

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 6 of 7 Part 2

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835770	Drill Core	0.09	4.8	7	2.57	62	0.169	5.42	3.22	0.25	<0.5	10.3	15	1.1	16.3	1.1	<0.5	<5	12	7.0	3.3
835771	Drill Core	0.08	5.5	11	2.42	65	0.178	5.80	3.31	0.15	<0.5	10.4	17	1.0	13.0	0.9	<0.5	<5	12	6.5	2.6
835772	Drill Core	0.08	4.7	6	2.15	39	0.139	5.32	3.69	0.14	<0.5	13.7	15	1.3	10.8	0.7	<0.5	<5	11	3.3	3.2
835773	Drill Core	0.10	4.7	5	3.78	69	0.195	6.79	2.53	0.32	<0.5	209.6	16	1.1	14.1	1.0	<0.5	<5	16	8.1	3.6
835774	Drill Core	0.08	4.6	10	1.47	31	0.180	4.78	4.04	0.15	<0.5	9.8	15	1.5	14.3	1.1	<0.5	<5	10	5.9	2.7
835775	Drill Core	0.09	4.2	8	2.09	37	0.177	5.22	3.22	0.21	<0.5	8.2	13	1.3	15.0	1.0	<0.5	<5	12	2.8	3.1
835776	Drill Core	0.08	4.8	8	2.59	52	0.180	5.27	2.39	0.35	<0.5	7.8	14	1.1	14.9	1.3	<0.5	<5	13	6.3	3.8
835777	Drill Core	0.09	5.0	10	2.48	78	0.169	5.41	2.14	0.58	<0.5	46.6	16	3.8	12.3	0.9	<0.5	<5	12	6.6	3.9
835778	Rock Pulp	0.06	6.3	102	2.59	430	0.448	5.99	1.49	0.71	30.2	28.4	13	22.3	16.0	3.7	<0.5	<5	22	20.5	6.8
835779	Drill Core	0.09	3.6	8	2.53	66	0.214	5.63	2.49	0.45	<0.5	6.5	12	3.0	12.5	1.4	<0.5	<5	13	8.3	3.9
835780	Drill Core	0.08	4.6	9	2.04	24	0.192	5.32	3.33	0.13	<0.5	9.3	14	1.6	18.4	1.3	<0.5	<5	12	4.9	3.5
835781	Drill Core	0.09	5.2	6	2.34	81	0.266	5.64	3.03	0.26	<0.5	14.3	17	1.3	23.9	1.5	<0.5	<5	13	5.7	3.1
835782	Drill Core	0.10	5.3	6	3.09	130	0.241	5.97	2.04	0.68	<0.5	22.8	17	3.6	25.1	1.3	<0.5	<5	17	5.8	4.2
835783	Drill Core	0.07	4.2	9	1.12	153	0.214	3.65	1.94	0.72	<0.5	7.0	13	1.9	15.7	1.7	<0.5	<5	10	2.1	3.0
835784	Drill Core	0.10	4.4	3	1.94	158	0.267	4.98	1.91	0.88	<0.5	7.7	13	2.1	14.0	1.2	<0.5	<5	11	4.7	4.4
835785	Drill Core	0.10	5.1	2	3.04	62	0.259	6.25	2.51	0.33	<0.5	23.8	16	1.9	14.0	1.4	<0.5	<5	13	6.6	3.0
835786	Drill Core	0.09	4.3	4	2.40	89	0.286	5.36	2.63	0.45	<0.5	9.0	14	1.6	13.6	1.4	<0.5	<5	11	4.4	3.2
835787	Drill Core	0.09	4.2	5	2.27	284	0.248	5.33	0.89	1.75	<0.5	26.9	13	3.5	11.6	1.1	<0.5	<5	15	8.9	4.2
835788	Drill Core	0.04	4.4	5	1.66	215	0.168	4.37	1.39	1.18	<0.5	30.0	16	2.0	14.2	1.4	<0.5	<5	10	5.3	3.6
835789	Drill Core	0.06	3.8	7	1.96	179	0.210	4.48	1.76	0.90	<0.5	10.4	13	1.4	13.3	1.5	<0.5	<5	11	5.3	2.7
835790	Drill Core	0.10	5.0	16	2.61	93	0.240	5.30	2.47	0.49	<0.5	9.7	17	1.7	10.0	1.4	<0.5	<5	12	6.5	2.8
835791	Drill Core	0.10	4.1	6	1.96	54	0.240	4.88	3.62	0.19	<0.5	8.2	15	1.1	15.1	1.5	<0.5	<5	10	3.7	3.2
835792	Drill Core	0.10	4.4	5	1.44	36	0.268	4.99	3.88	0.21	<0.5	8.6	14	0.9	12.6	1.3	<0.5	<5	9	3.6	3.1
835793	Drill Core	0.08	4.0	7	1.57	107	0.222	4.55	2.46	0.72	<0.5	37.8	15	1.7	12.6	1.4	<0.5	<5	11	3.8	3.5
835794	Drill Core	0.07	4.7	10	1.84	110	0.230	4.53	2.05	0.92	<0.5	26.2	16	1.1	13.6	1.6	<0.5	<5	11	2.9	2.7
835795	Drill Core	0.09	3.7	7	1.99	66	0.242	4.78	2.70	0.55	<0.5	11.4	13	1.6	13.6	1.7	<0.5	<5	10	9.0	3.3
835796	Drill Core	0.08	3.6	15	1.70	78	0.257	4.62	2.61	0.66	<0.5	14.2	12	1.3	14.2	1.3	<0.5	<5	12	4.7	3.1
835797	Drill Core	0.07	6.3	9	1.77	61	0.210	5.34	3.46	0.57	<0.5	14.0	20	1.2	14.3	1.4	<0.5	<5	10	6.6	3.1
835798	Rock Pulp	0.02	3.8	761	0.77	54	0.011	0.71	<0.01	0.11	6.6	12.7	7	16.2	4.1	3.2	<0.5	<5	1	4.0	31.5
835799	Drill Core	0.10	4.1	8	2.01	117	0.396	5.16	2.76	0.97	<0.5	39.9	14	1.5	15.4	1.2	<0.5	<5	17	6.1	4.8

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 13, 2009

**Page:** 6 of 7 **Part** 3

## CERTIFICATE OF ANALYSIS

SMI09000252.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
835770	Drill Core	2.9	<0.5
835771	Drill Core	1.9	1.2
835772	Drill Core	1.5	<0.5
835773	Drill Core	3.5	3.1
835774	Drill Core	1.3	<0.5
835775	Drill Core	2.2	<0.5
835776	Drill Core	3.6	0.6
835777	Drill Core	5.5	0.5
835778	Rock Pulp	21.9	1.4
835779	Drill Core	5.1	<0.5
835780	Drill Core	1.2	<0.5
835781	Drill Core	2.9	<0.5
835782	Drill Core	5.9	<0.5
835783	Drill Core	7.9	<0.5
835784	Drill Core	9.0	<0.5
835785	Drill Core	3.3	<0.5
835786	Drill Core	4.8	<0.5
835787	Drill Core	15.1	<0.5
835788	Drill Core	11.5	0.9
835789	Drill Core	9.5	0.5
835790	Drill Core	4.6	0.5
835791	Drill Core	1.9	<0.5
835792	Drill Core	1.9	<0.5
835793	Drill Core	7.0	<0.5
835794	Drill Core	10.3	0.6
835795	Drill Core	6.7	<0.5
835796	Drill Core	6.7	<0.5
835797	Drill Core	5.5	<0.5
835798	Rock Pulp	2.6	<0.5
835799	Drill Core	9.8	1.2



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 7 of 7 Part 1

**CERTIFICATE OF ANALYSIS**

**SMI09000252.1**

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835800	Drill Core	7.91	6	1.6	211.7	12.5	6500	<0.5	3.9	13	1507	5.92	6	0.8	<0.5	33	48.0	<0.5	<0.5	172	0.45
835801	Drill Core	6.60	15	2.1	279.5	29.7	5709	0.6	0.7	2	782	4.35	<5	<0.5	<0.5	32	39.0	<0.5	<0.5	12	0.25



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 7 of 7 Part 2

CERTIFICATE OF ANALYSIS

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835800	Drill Core	0.10	3.4	10	1.95	137	0.386	4.65	2.58	1.00	<0.5	41.9	12	1.2	11.6	1.1	<0.5	<5	20	9.2	5.8
835801	Drill Core	0.06	5.0	3	1.16	216	0.153	5.02	1.83	1.42	<0.5	19.6	16	1.6	10.7	1.0	<0.5	<5	11	6.2	4.4



Acme Analytical Laboratories (Vancouver) Ltd.  
1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 13, 2009

**Page:** 7 of 7 Part 3

## CERTIFICATE OF ANALYSIS

SMI09000252.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
835800	Drill Core	9.1	1.6
835801	Drill Core	14.8	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 1 of 3 Part 1

QUALITY CONTROL REPORT

SMI09000252.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
Pulp Duplicates																					
835652	Drill Core	5.89	<2	<0.5	4.7	2.3	127	<0.5	<0.5	<1	719	2.38	<5	<0.5	0.5	136	<0.5	<0.5	<0.5	<10	1.01
REP 835652	QC		<2																		
835675	Drill Core	7.00	<2	0.5	8.9	8.5	120	<0.5	0.8	2	548	2.80	<5	0.8	1.1	48	0.5	<0.5	<0.5	<10	0.72
REP 835675	QC			0.7	10.5	10.5	135	<0.5	0.5	3	542	2.80	6	0.6	0.8	52	<0.5	<0.5	<0.5	<10	0.75
835701	Drill Core	6.69	3	2.0	4.1	76.9	291	<0.5	2.2	2	1718	2.39	11	0.9	0.5	58	1.9	<0.5	<0.5	<10	1.06
REP 835701	QC			2.3	1.6	77.3	298	<0.5	1.5	2	1712	2.41	9	0.8	0.6	60	2.4	<0.5	<0.5	<10	1.05
835702	Drill Core	6.59	3	1.1	7.0	19.8	210	<0.5	13.2	3	1708	2.75	12	<0.5	0.6	68	<0.5	<0.5	<0.5	20	0.81
REP 835702	QC		5																		
835714	Drill Core	6.90	10	1.9	636.2	320.7	5940	1.1	0.6	<1	1079	3.36	216	<0.5	<0.5	37	33.0	7.2	<0.5	<10	0.12
REP 835714	QC		11																		
REP 835751	QC			<0.5	176.6	4.3	6946	<0.5	0.9	4	2576	5.24	6	<0.5	<0.5	28	46.4	<0.5	<0.5	27	0.36
835772	Drill Core	6.49	3	1.0	64.6	5.1	1702	<0.5	1.0	3	2759	4.01	5	<0.5	<0.5	28	10.0	<0.5	<0.5	<10	0.32
REP 835772	QC		2																		
835775	Drill Core	6.76	<2	0.7	18.4	4.0	361	<0.5	0.8	3	2304	4.00	5	<0.5	<0.5	31	0.6	<0.5	<0.5	<10	0.30
REP 835775	QC			0.7	18.9	4.0	347	<0.5	<0.5	3	2239	4.06	<5	<0.5	<0.5	31	0.5	<0.5	<0.5	<10	0.29
835795	Drill Core	6.41	<2	1.1	95.9	5.8	1447	<0.5	1.4	3	1438	4.00	<5	<0.5	<0.5	27	7.8	<0.5	<0.5	<10	0.25
REP 835795	QC		2																		
Core Reject Duplicates																					
835681	Drill Core	6.11	<2	0.5	18.9	5.0	158	<0.5	0.9	2	1375	3.28	<5	<0.5	0.9	72	0.5	0.6	<0.5	11	1.43
DUP 835681	QC		<2	0.8	15.7	4.8	165	<0.5	1.4	2	1327	3.37	6	<0.5	1.1	70	<0.5	<0.5	<0.5	<10	1.25
835716	Drill Core	4.81	4	2.4	93.2	26.9	1220	<0.5	0.5	<1	862	4.08	47	<0.5	<0.5	34	6.3	1.8	<0.5	<10	0.05
DUP 835716	QC		4	2.5	99.4	31.0	1377	<0.5	<0.5	<1	834	4.26	52	<0.5	<0.5	36	7.0	1.9	<0.5	<10	0.08
835751	Drill Core	6.72	4	0.8	173.7	4.2	6816	<0.5	1.5	4	2622	5.22	5	<0.5	<0.5	28	47.5	<0.5	<0.5	26	0.34
DUP 835751	QC		4	0.7	169.8	4.3	6695	<0.5	1.3	3	2621	5.17	6	<0.5	<0.5	26	45.8	<0.5	<0.5	28	0.36
835786	Drill Core	6.77	<2	<0.5	45.1	5.4	1019	<0.5	1.2	3	1943	4.45	6	<0.5	<0.5	25	4.2	<0.5	<0.5	13	0.20
DUP 835786	QC		3	<0.5	46.5	5.2	1116	<0.5	<0.5	3	2250	4.48	<5	<0.5	<0.5	27	4.6	<0.5	<0.5	12	0.25
Reference Materials																					
STD OXE56	Standard		631																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.





Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 1 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000252.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	5	1	0.5	0.5		
Pulp Duplicates																					
835652	Drill Core	0.05	9.0	9	0.76	90	0.254	6.20	2.87	1.73	<0.5	17.0	29	2.1	47.7	4.0	<0.5	<5	11	6.9	<0.5
REP 835652	QC																				
835675	Drill Core	0.03	9.8	18	0.79	200	0.169	6.12	2.99	1.59	<0.5	40.7	28	1.8	23.5	2.5	<0.5	<5	11	5.2	<0.5
REP 835675	QC	0.03	10.0	10	0.80	208	0.166	6.40	2.99	1.59	<0.5	40.3	28	1.5	20.9	3.2	<0.5	<5	11	6.8	<0.5
835701	Drill Core	0.05	12.3	6	2.14	176	0.295	7.19	4.13	0.55	<0.5	96.4	36	2.3	43.7	4.8	<0.5	<5	12	10.8	0.9
REP 835701	QC	0.05	11.8	9	2.13	178	0.292	7.18	4.12	0.56	<0.5	120.0	34	1.7	45.0	5.1	<0.5	<5	12	12.0	0.9
835702	Drill Core	0.07	12.1	32	2.02	301	0.266	6.61	3.65	0.58	<0.5	32.3	34	2.1	25.3	5.3	<0.5	<5	12	10.3	0.7
REP 835702	QC																				
835714	Drill Core	0.02	5.2	6	1.61	233	0.109	4.67	1.38	0.64	<0.5	12.7	16	1.9	15.3	2.0	<0.5	<5	9	11.0	3.3
REP 835714	QC																				
REP 835751	QC	0.11	4.9	15	3.14	108	0.321	6.51	1.90	0.71	<0.5	42.7	15	1.5	27.3	1.1	<0.5	<5	16	10.8	3.7
835772	Drill Core	0.08	4.7	6	2.15	39	0.139	5.32	3.69	0.14	<0.5	13.7	15	1.3	10.8	0.7	<0.5	<5	11	3.3	3.2
REP 835772	QC																				
835775	Drill Core	0.09	4.2	8	2.09	37	0.177	5.22	3.22	0.21	<0.5	8.2	13	1.3	15.0	1.0	<0.5	<5	12	2.8	3.1
REP 835775	QC	0.09	4.3	9	2.09	41	0.178	5.21	3.21	0.23	<0.5	8.3	13	1.6	13.7	0.6	<0.5	<5	12	7.3	3.2
835795	Drill Core	0.09	3.7	7	1.99	66	0.242	4.78	2.70	0.55	<0.5	11.4	13	1.6	13.6	1.7	<0.5	<5	10	9.0	3.3
REP 835795	QC																				
Core Reject Duplicates																					
835681	Drill Core	0.03	7.1	15	1.27	213	0.194	6.41	3.36	1.03	<0.5	26.4	22	1.8	37.9	3.8	<0.5	<5	11	4.6	<0.5
DUP 835681	QC	0.03	7.9	37	1.27	132	0.204	6.92	3.42	1.12	<0.5	33.8	25	1.8	43.7	3.9	<0.5	<5	11	8.0	<0.5
835716	Drill Core	0.01	6.5	6	1.24	228	0.113	5.40	2.48	0.55	<0.5	18.0	19	1.6	16.5	1.7	<0.5	<5	10	7.3	4.0
DUP 835716	QC	0.01	6.8	7	1.18	227	0.114	5.45	2.46	0.55	<0.5	21.8	21	2.0	17.7	1.9	<0.5	<5	11	4.9	4.2
835751	Drill Core	0.11	4.9	13	3.12	111	0.294	6.47	1.88	0.71	<0.5	21.4	16	1.2	23.5	1.2	<0.5	<5	16	11.2	3.7
DUP 835751	QC	0.12	4.9	10	3.13	111	0.286	6.47	1.92	0.70	<0.5	36.7	15	1.6	22.8	1.0	<0.5	<5	16	8.8	3.6
835786	Drill Core	0.09	4.3	4	2.40	89	0.286	5.36	2.63	0.45	<0.5	9.0	14	1.6	13.6	1.4	<0.5	<5	11	4.4	3.2
DUP 835786	QC	0.10	4.5	4	2.45	93	0.282	5.65	2.69	0.51	<0.5	10.7	14	2.3	13.9	1.6	<0.5	<5	13	7.2	3.2
Reference Materials																					
STD OXE56	Standard																				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 13, 2009

**Page:** 1 of 3 **Part** 3

## QUALITY CONTROL REPORT

SMI09000252.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
Pulp Duplicates			
835652	Drill Core	12.3	0.6
REP 835652	QC		
835675	Drill Core	19.6	1.3
REP 835675	QC	19.9	1.4
835701	Drill Core	6.0	2.5
REP 835701	QC	6.1	3.2
835702	Drill Core	6.5	1.9
REP 835702	QC		
835714	Drill Core	8.9	1.8
REP 835714	QC		
REP 835751	QC	7.4	0.7
835772	Drill Core	1.5	<0.5
REP 835772	QC		
835775	Drill Core	2.2	<0.5
REP 835775	QC	2.3	<0.5
835795	Drill Core	6.7	<0.5
REP 835795	QC		
Core Reject Duplicates			
835681	Drill Core	9.7	0.8
DUP 835681	QC	10.9	1.2
835716	Drill Core	6.1	1.5
DUP 835716	QC	7.6	0.6
835751	Drill Core	8.2	2.0
DUP 835751	QC	8.3	1.6
835786	Drill Core	4.8	<0.5
DUP 835786	QC	4.5	<0.5
Reference Materials			
STD OXE56	Standard		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 2 of 3 Part 1

QUALITY CONTROL REPORT

SMI09000252.1

	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01
STD OXE56	Standard	640																		
STD OXE56	Standard	626																		
STD OXE56	Standard	600																		
STD OXE56	Standard	622																		
STD OXH55	Standard	1318																		
STD OXH55	Standard	1332																		
STD OXH55	Standard	1318																		
STD OXH55	Standard	1188																		
STD OXH55	Standard	1271																		
STD SF-3T	Standard		315.3	7717	8653	10677	51.4	3505	183	4184	8.26	44	4.3	4.9	437	49.5	8.8	4.7	126	4.05
STD SF-3T	Standard		318.1	7728	8559	10669	52.3	3508	189	4173	8.23	42	4.2	4.8	437	48.2	8.7	4.8	125	4.05
STD SF-3T	Standard		356.7	7774	8883	11010	53.2	3527	190	4208	8.20	51	4.0	4.7	436	50.5	10.6	5.1	140	4.11
STD SF-3T	Standard		319.5	7709	8760	10950	52.7	3510	185	4173	8.17	46	3.9	4.8	436	48.8	9.8	4.8	140	4.08
STD SF-3T	Standard		317.9	7770	8535	11179	52.7	3536	179	4216	8.12	42	3.9	4.8	437	48.8	10.4	6.5	122	4.08
STD SF-3T	Standard		316.0	7771	8876	11207	53.3	3560	178	4233	8.11	39	4.0	4.7	434	47.9	9.7	4.8	123	4.11
STD SF-3T	Standard		326.3	7736	8692	10745	53.3	3530	186	4206	8.30	47	4.0	4.8	437	49.2	9.9	4.7	135	4.04
STD SF-3T	Standard		317.6	7714	8605	10719	53.1	3520	189	4177	8.28	46	4.1	4.6	439	46.6	10.6	4.6	122	4.02
STD SF-3T	Standard		322.4	7718	8547	10922	51.6	3478	187	4172	8.14	41	4.0	4.6	430	50.2	10.9	4.8	139	4.04
STD SF-3T	Standard		322.3	7685	8378	10982	51.3	3496	185	4130	7.99	44	4.1	4.7	431	50.2	10.7	4.9	137	4.05
STD SF-3T Expected			320	7723	9610	10672	52	3500	181	4320	8.33	40	4	4.7	440	47.5	11.1	4.8	143	4.1
STD OXE56 Expected		611																		
STD OXH55 Expected		1282																		
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank	<2																		
BLK	Blank	<2																		
BLK	Blank	<2																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 13, 2009

Page: 2 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000252.1

		7TX P	7TX La	7TX Cr	7TX Mg	7TX Ba	7TX Ti	7TX Al	7TX Na	7TX K	7TX W	7TX Zr	7TX Ce	7TX Sn	7TX Y	7TX Nb	7TX Ta	7TX Be	7TX Sc	7TX Li	7TX S	
		%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
STD OXE56	Standard																					
STD OXE56	Standard																					
STD OXE56	Standard																					
STD OXE56	Standard																					
STD OXH55	Standard																					
STD OXH55	Standard																					
STD OXH55	Standard																					
STD OXH55	Standard																					
STD SF-3T	Standard	0.06	17.6	197	4.61	565	0.189	5.44	2.11	2.49	4.1	13.9	40	5.9	9.1	14.7	0.8	<5	6	16.1	3.8	
STD SF-3T	Standard	0.06	17.3	199	4.61	545	0.189	5.45	2.09	2.48	4.1	13.1	39	5.6	10.5	14.3	0.8	<5	7	19.6	3.8	
STD SF-3T	Standard	0.06	18.2	194	4.62	771	0.195	5.48	2.12	2.48	4.3	17.0	44	5.7	10.7	16.1	0.7	<5	7	18.5	3.9	
STD SF-3T	Standard	0.06	18.0	197	4.59	758	0.193	5.45	2.10	2.46	4.1	13.6	40	5.5	10.3	15.0	0.7	<5	7	26.2	3.8	
STD SF-3T	Standard	0.06	18.1	179	4.64	534	0.192	5.51	2.11	1.98	4.4	20.5	41	5.4	10.7	15.4	0.8	<5	7	25.7	3.7	
STD SF-3T	Standard	0.06	17.5	197	4.62	612	0.194	5.49	2.13	2.35	4.2	14.5	41	5.4	10.5	15.0	0.8	<5	7	24.2	3.8	
STD SF-3T	Standard	0.06	17.5	208	4.63	553	0.190	5.46	2.11	2.49	3.7	13.9	39	6.2	10.1	14.5	0.8	<5	6	25.7	3.8	
STD SF-3T	Standard	0.06	17.9	201	4.63	569	0.190	5.44	2.09	2.48	4.3	13.5	40	6.2	10.4	14.4	0.8	<5	7	20.7	3.8	
STD SF-3T	Standard	0.06	18.5	187	4.57	694	0.193	5.40	2.08	2.42	4.1	14.9	40	5.7	10.6	15.2	1.0	<5	7	24.4	3.8	
STD SF-3T	Standard	0.06	18.0	186	4.57	748	0.192	5.40	2.06	2.38	4.2	14.8	40	5.7	10.9	15.5	0.9	<5	7	25.6	3.8	
STD SF-3T Expected		0.06	17	207.4	4.67	508	0.19	5.43	2.06	2.47	4.3	14	38	5.8	11.5	15.1	0.9	2.4	7	19.1	3.5	
STD OXE56 Expected																						
STD OXH55 Expected																						
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 13, 2009

**Page:** 2 of 3 **Part** 3

# QUALITY CONTROL REPORT

SMI09000252.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD SF-3T	Standard	88.1	0.7
STD SF-3T	Standard	86.2	<0.5
STD SF-3T	Standard	93.6	0.6
STD SF-3T	Standard	87.1	0.6
STD SF-3T	Standard	71.5	0.7
STD SF-3T	Standard	86.3	<0.5
STD SF-3T	Standard	88.0	0.6
STD SF-3T	Standard	90.0	0.7
STD SF-3T	Standard	89.2	0.6
STD SF-3T	Standard	89.5	0.8
STD SF-3T Expected		90.8	0.6
STD OXE56 Expected			
STD OXH55 Expected			
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** Amarc Resources  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 13, 2009

**Page:** 3 of 3 **Part** 1

QUALITY CONTROL REPORT

SMI09000252.1

		WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank			<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
Prep Wash																					
G1	Prep Blank		<2	<0.5	10.8	26.3	80	<0.5	3.8	5	821	2.45	<5	2.3	4.8	726	<0.5	<0.5	<0.5	57	2.52
G1	Prep Blank		3	<0.5	6.9	22.4	63	<0.5	6.1	5	824	2.54	<5	2.5	5.8	725	<0.5	<0.5	<0.5	56	2.51



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 13, 2009

**Page:** 3 of 3 **Part** 2

**QUALITY CONTROL REPORT**

**SMI09000252.1**

		7TX P	7TX La	7TX Cr	7TX Mg	7TX Ba	7TX Ti	7TX Al	7TX Na	7TX K	7TX W	7TX Zr	7TX Ce	7TX Sn	7TX Y	7TX Nb	7TX Ta	7TX Be	7TX Sc	7TX Li	7TX S	
		%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
Prep Wash																						
G1	Prep Blank	0.09	15.4	14	0.66	957	0.240	6.84	2.71	2.92	0.6	8.2	35	2.2	11.4	23.0	1.5	<5	4	35.3	<0.5	
G1	Prep Blank	0.09	18.7	15	0.68	985	0.245	6.81	2.67	3.05	<0.5	9.4	45	1.4	11.7	23.2	1.2	<5	4	31.2	<0.5	



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Project: Bodine

Report Date: October 13, 2009

Page: 3 of 3 Part 3

# QUALITY CONTROL REPORT

# SMI09000252.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank	<0.5	<0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
Prep Wash			
G1	Prep Blank	101.3	0.7
G1	Prep Blank	104.3	0.8





1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Submitted By: Ted Oliver  
Receiving Lab: Canada-Smithers  
Received: September 23, 2009  
Report Date: October 20, 2009  
Page: 1 of 5

## CERTIFICATE OF ANALYSIS

SMI09000263.1

### CLIENT JOB INFORMATION

Project: Bodine  
Shipment ID:  
P.O. Number /ARR\_SSNB9010\_sept2109  
Number of Samples: 113

### SAMPLE DISPOSAL

RTRN-PLP Return  
RTRN-RJT Return

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6  
Canada

CC:

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R150	107	Crush split and pulverize drill core to 200 mesh			VAN
3B	112	Fire assay fusion Au by ICP-ES	30	Completed	VAN
7TX	112	4 Acid Digestion Analysis by ICP-ES/ICP-MS	0.5	Completed	VAN

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.  
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.  
\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835802	Drill Core	6.97	<2	<0.5	6.5	4.0	71	<0.5	<0.5	1	585	1.88	<5	<0.5	0.5	42	<0.5	<0.5	<0.5	<10	0.26
835803	Drill Core	6.65	<2	0.6	4.4	12.8	78	<0.5	<0.5	1	713	2.04	<5	<0.5	0.5	49	<0.5	<0.5	<0.5	<10	0.26
835804	Drill Core	6.23	<2	0.7	2.8	2.9	69	<0.5	<0.5	1	889	1.94	<5	<0.5	<0.5	59	<0.5	<0.5	<0.5	<10	0.41
835805	Drill Core	6.22	<2	0.8	1.2	9.3	101	<0.5	<0.5	1	730	1.93	<5	<0.5	<0.5	44	<0.5	<0.5	<0.5	<10	0.34
835806	Drill Core	5.79	<2	<0.5	4.8	8.6	74	<0.5	0.9	1	946	2.02	<5	<0.5	<0.5	45	<0.5	<0.5	<0.5	<10	0.43
835807	Drill Core	6.18	3	<0.5	3.4	2.7	70	<0.5	<0.5	1	940	1.99	<5	<0.5	0.5	47	<0.5	<0.5	<0.5	<10	0.31
835808	Drill Core	5.91	<2	0.9	2.2	7.9	89	<0.5	<0.5	1	905	1.99	<5	<0.5	0.6	50	<0.5	<0.5	<0.5	<10	0.41
835809	Drill Core	6.38	4	<0.5	4.5	3.7	87	<0.5	<0.5	<1	797	1.98	<5	<0.5	0.6	57	<0.5	<0.5	<0.5	<10	0.32
835810	Drill Core	6.38	<2	<0.5	5.0	6.3	74	<0.5	0.6	1	876	1.93	<5	<0.5	0.5	53	<0.5	0.5	<0.5	<10	0.37
835811	Drill Core	5.60	3	0.5	5.0	3.8	73	<0.5	<0.5	1	920	1.78	<5	<0.5	0.6	51	<0.5	2.0	<0.5	<10	0.37
835812	Drill Core	5.27	5	0.6	4.2	7.9	77	<0.5	<0.5	1	852	1.79	<5	<0.5	0.6	49	<0.5	<0.5	<0.5	<10	0.38
835813	Drill Core	6.79	<2	<0.5	<0.5	3.5	71	<0.5	<0.5	1	599	1.65	<5	<0.5	0.5	51	<0.5	<0.5	<0.5	<10	0.24
835814	Drill Core	5.73	<2	0.9	5.3	6.5	79	<0.5	<0.5	1	629	1.66	<5	<0.5	0.5	48	<0.5	<0.5	<0.5	<10	0.29
835815	Drill Core	4.76	<2	<0.5	4.1	3.3	79	<0.5	<0.5	1	807	1.83	<5	<0.5	<0.5	49	<0.5	<0.5	<0.5	<10	0.42
835816	Drill Core	5.12	<2	<0.5	4.7	5.0	81	<0.5	<0.5	2	1045	2.06	<5	<0.5	0.6	57	<0.5	<0.5	<0.5	<10	0.55
835817	Drill Core	5.61	4	<0.5	2.8	2.0	83	<0.5	0.8	1	970	1.80	<5	<0.5	0.6	47	<0.5	0.5	<0.5	<10	0.54
835818	Drill Core	3.17	<2	<0.5	6.0	2.9	94	<0.5	1.5	1	803	2.20	<5	<0.5	0.6	41	<0.5	0.6	<0.5	<10	0.39
835819	Rock Pulp	0.17	34	17.6	6296	7221	32661	21.8	66.0	67	1090	12.17	58	2.0	1.1	180	174.8	39.1	30.9	190	4.18
835820	Drill Core	1.25	<2	<0.5	2.9	<0.5	88	<0.5	1.1	2	1081	2.32	<5	<0.5	<0.5	71	<0.5	0.7	<0.5	<10	1.00
835821	Drill Core	2.15	<2	3.2	10.0	9.5	117	<0.5	4.2	4	755	2.52	<5	<0.5	0.7	35	<0.5	<0.5	<0.5	13	0.50
835822	Drill Core	3.82	<2	8.8	4.8	6.4	136	<0.5	3.2	2	698	2.36	<5	<0.5	0.6	21	<0.5	<0.5	<0.5	<10	0.23
835823	Drill Core	3.27	<2	0.8	4.8	7.5	81	<0.5	2.1	<1	545	1.47	<5	<0.5	0.6	71	<0.5	<0.5	<0.5	<10	0.83
835824	Drill Core	4.56	<2	<0.5	5.5	3.0	80	<0.5	0.7	1	428	1.08	<5	<0.5	0.5	32	<0.5	0.5	<0.5	<10	0.46
835825	Drill Core	0.54	3	<0.5	0.9	4.6	119	<0.5	1.7	1	1024	1.84	<5	<0.5	0.5	77	<0.5	3.8	<0.5	<10	1.34
835826	Drill Core	2.14	<2	<0.5	5.8	3.0	56	<0.5	1.1	1	388	1.01	<5	<0.5	0.6	29	<0.5	4.8	<0.5	<10	0.27
835827	Drill Core	5.26	<2	<0.5	4.3	3.1	58	<0.5	1.0	1	286	1.00	<5	<0.5	<0.5	12	<0.5	0.6	<0.5	<10	0.15
835828	Drill Core	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
835829	Drill Core	5.84	<2	<0.5	2.2	2.5	74	<0.5	0.8	<1	431	1.50	<5	<0.5	<0.5	26	<0.5	<0.5	<0.5	<10	0.16
835830	Drill Core	6.15	<2	<0.5	5.0	7.8	113	<0.5	0.9	<1	640	1.68	<5	<0.5	<0.5	32	<0.5	<0.5	<0.5	<10	0.30
835831	Drill Core	6.22	<2	<0.5	2.4	1.9	86	<0.5	0.8	2	583	1.68	<5	<0.5	<0.5	26	<0.5	<0.5	<0.5	<10	0.23

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835802	Drill Core	0.02	7.3	3	0.26	64	0.145	5.43	5.32	0.44	<0.5	13.2	21	1.9	8.2	2.3	<0.5	<5	9	0.9	<0.5
835803	Drill Core	0.02	6.7	6	0.37	94	0.155	4.95	4.94	0.51	<0.5	17.5	20	2.0	10.7	2.6	<0.5	<5	9	1.6	<0.5
835804	Drill Core	0.02	6.6	4	0.39	72	0.127	5.25	4.59	0.66	<0.5	14.6	19	1.4	9.8	1.9	<0.5	<5	9	1.2	<0.5
835805	Drill Core	0.02	5.6	13	0.42	79	0.155	5.44	4.84	0.58	<0.5	18.6	18	1.5	16.0	2.5	<0.5	<5	8	2.6	<0.5
835806	Drill Core	0.02	6.1	4	0.44	62	0.155	5.08	4.63	0.66	<0.5	15.8	19	2.1	17.2	3.0	<0.5	<5	10	1.1	<0.5
835807	Drill Core	0.02	6.2	4	0.48	67	0.162	5.21	4.73	0.77	<0.5	15.8	20	1.4	15.2	2.8	<0.5	<5	9	<0.5	<0.5
835808	Drill Core	0.02	7.3	7	0.43	66	0.155	5.71	4.79	0.63	<0.5	16.4	21	1.5	19.0	3.2	<0.5	<5	10	0.5	<0.5
835809	Drill Core	0.02	6.6	4	0.42	109	0.153	5.29	4.87	0.60	<0.5	15.8	20	1.4	21.5	2.5	<0.5	<5	10	1.8	<0.5
835810	Drill Core	0.02	7.4	3	0.42	84	0.158	5.39	4.82	0.59	0.7	17.5	21	1.8	25.7	2.5	<0.5	<5	9	1.3	<0.5
835811	Drill Core	0.02	7.0	5	0.37	48	0.155	5.69	4.83	0.61	1.7	16.4	22	1.8	17.2	3.2	<0.5	<5	10	3.4	<0.5
835812	Drill Core	0.02	7.3	5	0.36	86	0.156	5.52	4.72	0.72	<0.5	16.7	21	2.3	18.2	3.0	<0.5	<5	10	<0.5	<0.5
835813	Drill Core	0.02	6.8	5	0.30	167	0.153	5.40	4.85	0.70	<0.5	17.3	20	2.6	23.0	2.8	<0.5	<5	10	0.9	<0.5
835814	Drill Core	0.02	7.1	5	0.28	73	0.154	5.42	4.95	0.58	0.7	22.8	22	2.0	18.9	2.7	<0.5	<5	9	<0.5	<0.5
835815	Drill Core	0.02	6.7	7	0.37	44	0.145	5.63	4.79	0.40	<0.5	16.9	20	1.2	14.7	2.4	<0.5	<5	9	3.0	<0.5
835816	Drill Core	0.02	7.3	6	0.45	63	0.151	5.81	4.67	0.57	1.1	15.5	21	1.4	17.7	2.5	<0.5	<5	10	1.8	<0.5
835817	Drill Core	0.02	9.0	4	0.41	57	0.158	6.03	4.72	0.63	0.8	14.1	21	1.6	18.5	2.7	<0.5	<5	10	7.6	<0.5
835818	Drill Core	0.02	6.7	7	0.26	30	0.145	5.69	4.92	0.36	0.6	17.0	18	1.5	13.3	2.5	<0.5	<5	11	9.0	<0.5
835819	Rock Pulp	0.06	7.1	78	2.64	382	0.450	6.10	1.49	0.75	26.7	18.3	15	13.5	16.1	3.6	<0.5	<5	20	27.4	7.5
835820	Drill Core	0.02	7.0	4	0.35	24	0.133	5.70	4.73	0.29	1.8	19.6	19	1.5	14.4	2.1	<0.5	<5	10	3.9	<0.5
835821	Drill Core	0.03	7.9	9	1.18	353	0.187	5.97	2.43	2.33	<0.5	22.5	23	2.4	17.9	2.8	<0.5	<5	11	5.0	<0.5
835822	Drill Core	0.01	7.5	3	1.52	393	0.145	5.36	0.91	3.34	<0.5	17.8	21	1.8	21.8	2.7	<0.5	<5	9	14.8	<0.5
835823	Drill Core	0.02	8.2	12	0.82	96	0.133	5.65	3.66	0.81	<0.5	37.5	25	1.5	19.3	2.6	<0.5	<5	7	13.3	<0.5
835824	Drill Core	0.01	6.5	<1	0.27	22	0.142	5.35	4.88	0.30	0.7	23.5	19	1.0	18.1	2.6	<0.5	<5	6	3.2	<0.5
835825	Drill Core	0.01	8.0	10	0.67	65	0.149	6.03	4.42	0.86	2.9	21.5	23	1.8	12.9	3.1	<0.5	<5	13	11.6	<0.5
835826	Drill Core	0.01	7.8	4	0.12	13	0.143	5.23	5.11	0.19	2.6	19.5	23	2.2	15.8	3.0	<0.5	<5	8	1.3	<0.5
835827	Drill Core	0.01	4.1	6	0.05	7	0.139	3.63	5.29	0.23	<0.5	34.3	12	3.5	16.2	3.2	<0.5	<5	5	<0.5	<0.5
835828	Drill Core	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.	L.N.R.
835829	Drill Core	0.01	5.8	4	0.51	102	0.148	4.07	3.60	1.63	<0.5	22.0	17	1.9	18.9	3.2	<0.5	<5	7	4.0	<0.5
835830	Drill Core	0.01	6.8	5	0.63	177	0.142	5.09	3.40	1.85	<0.5	23.9	21	1.1	24.5	2.8	<0.5	<5	8	10.0	<0.5
835831	Drill Core	0.01	6.0	15	0.51	165	0.147	4.30	4.06	1.27	<0.5	26.6	17	2.9	21.8	3.1	<0.5	<5	7	10.9	<0.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 20, 2009

**Page:** 2 of 5 **Part** 3

## CERTIFICATE OF ANALYSIS

SMI09000263.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
835802	Drill Core	3.6	<0.5
835803	Drill Core	3.7	<0.5
835804	Drill Core	4.4	<0.5
835805	Drill Core	3.1	0.6
835806	Drill Core	4.7	0.6
835807	Drill Core	5.2	0.5
835808	Drill Core	3.8	0.6
835809	Drill Core	4.1	0.6
835810	Drill Core	4.1	0.6
835811	Drill Core	5.1	0.5
835812	Drill Core	5.5	0.5
835813	Drill Core	5.5	0.7
835814	Drill Core	4.5	0.6
835815	Drill Core	3.9	0.5
835816	Drill Core	4.5	0.5
835817	Drill Core	24.1	0.6
835818	Drill Core	15.4	0.5
835819	Rock Pulp	35.1	0.7
835820	Drill Core	10.8	0.6
835821	Drill Core	48.3	0.6
835822	Drill Core	57.0	0.7
835823	Drill Core	18.0	1.0
835824	Drill Core	7.1	0.7
835825	Drill Core	21.9	0.7
835826	Drill Core	5.4	0.6
835827	Drill Core	6.8	0.6
835828	Drill Core	L.N.R.	L.N.R.
835829	Drill Core	23.3	0.5
835830	Drill Core	26.2	0.7
835831	Drill Core	14.4	0.8



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 3 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835832	Drill Core	6.79	<2	2.0	6.5	9.2	100	<0.5	5.7	2	981	2.11	<5	<0.5	0.7	37	0.7	<0.5	<0.5	12	0.55
835833	Drill Core	6.37	<2	<0.5	5.9	1.8	88	<0.5	1.2	1	746	1.61	<5	<0.5	0.7	25	<0.5	<0.5	<0.5	<10	0.22
835834	Drill Core	5.65	<2	<0.5	2.6	13.0	91	<0.5	3.7	<1	927	1.68	<5	<0.5	0.7	37	<0.5	<0.5	<0.5	<10	0.64
835835	Drill Core	5.86	<2	<0.5	1.3	2.5	86	<0.5	0.7	<1	875	1.42	<5	<0.5	0.7	32	<0.5	<0.5	<0.5	<10	0.46
835836	Drill Core	4.53	<2	<0.5	1.1	3.1	81	<0.5	0.9	<1	687	1.31	<5	0.6	1.6	39	<0.5	1.7	<0.5	<10	0.36
835837	Drill Core	6.71	<2	<0.5	2.8	5.8	94	<0.5	0.9	<1	722	1.53	<5	<0.5	0.7	28	<0.5	1.4	<0.5	<10	0.30
835838	Drill Core	6.55	<2	<0.5	3.7	4.5	91	<0.5	1.1	1	786	1.63	<5	<0.5	0.7	40	<0.5	<0.5	<0.5	<10	0.34
835839	Rock Pulp	0.17	68	17.6	6199	7246	32732	23.1	67.7	65	1041	12.04	58	1.9	1.1	178	170.0	38.6	30.6	188	4.16
835840	Drill Core	6.78	<2	<0.5	4.8	4.3	104	<0.5	1.9	2	679	1.83	<5	<0.5	0.8	51	<0.5	<0.5	<0.5	<10	0.51
835841	Drill Core	6.06	<2	<0.5	10.4	4.6	98	<0.5	1.8	2	754	1.66	<5	<0.5	0.7	55	<0.5	0.6	<0.5	<10	0.67
835842	Drill Core	6.49	<2	<0.5	<0.5	4.4	74	<0.5	<0.5	<1	502	1.23	<5	0.7	1.8	65	<0.5	1.3	<0.5	<10	0.61
835843	Drill Core	6.04	<2	<0.5	3.3	3.6	82	<0.5	0.9	<1	727	1.51	<5	<0.5	0.9	44	<0.5	<0.5	<0.5	<10	0.54
835844	Drill Core	6.39	<2	<0.5	3.5	2.0	87	<0.5	<0.5	<1	617	1.53	<5	<0.5	0.5	23	<0.5	<0.5	<0.5	<10	0.28
835845	Drill Core	6.99	3	28.5	4.3	6.8	90	<0.5	3.2	2	750	2.18	<5	0.5	0.9	116	<0.5	0.8	<0.5	17	1.10
835846	Drill Core	6.70	<2	<0.5	4.7	5.7	86	<0.5	0.6	1	503	1.59	<5	<0.5	0.8	48	<0.5	<0.5	<0.5	<10	0.88
835847	Drill Core	6.94	<2	<0.5	2.3	2.4	96	<0.5	0.8	1	492	1.62	<5	<0.5	1.0	40	<0.5	<0.5	<0.5	<10	0.62
835848	Drill Core	6.75	<2	<0.5	6.1	6.3	101	<0.5	1.1	2	444	1.82	<5	<0.5	0.8	59	<0.5	0.7	<0.5	<10	0.69
835849	Drill Core	6.74	<2	3.3	8.2	3.3	85	<0.5	2.9	2	482	1.93	<5	<0.5	<0.5	132	<0.5	0.7	<0.5	<10	0.96
835850	Drill Core	6.85	8	3.7	26.7	7.6	118	<0.5	7.3	5	625	2.60	<5	<0.5	0.7	227	0.6	3.3	<0.5	32	1.34
835851	Drill Core	6.68	11	1.4	11.8	7.0	76	<0.5	6.7	4	442	1.75	<5	0.6	<0.5	236	<0.5	2.0	<0.5	31	1.37
835852	Drill Core	6.26	<2	0.7	2.2	3.0	58	<0.5	1.0	2	473	1.33	<5	0.9	1.6	190	<0.5	3.7	<0.5	13	0.64
835853	Drill Core	6.85	<2	0.8	12.4	7.0	109	<0.5	3.7	6	1282	3.32	5	0.5	<0.5	147	<0.5	3.9	<0.5	62	1.11
835854	Drill Core	5.92	<2	<0.5	1.3	<0.5	114	<0.5	<0.5	<1	1217	2.74	<5	<0.5	<0.5	132	<0.5	0.8	<0.5	<10	0.89
835855	Drill Core	6.64	<2	0.8	2.5	2.5	106	<0.5	<0.5	3	941	2.44	<5	0.7	1.1	369	<0.5	1.6	<0.5	<10	1.97
835856	Drill Core	6.37	<2	<0.5	5.4	0.6	120	<0.5	1.1	2	1046	2.76	<5	<0.5	<0.5	196	1.2	1.0	<0.5	15	1.68
835857	Drill Core	6.34	<2	0.6	3.7	0.7	93	<0.5	1.3	2	845	2.42	<5	1.6	0.5	48	<0.5	<0.5	<0.5	12	0.89
835858	Drill Core	7.17	<2	<0.5	<0.5	1.1	117	<0.5	<0.5	1	885	2.41	<5	<0.5	<0.5	39	<0.5	<0.5	<0.5	<10	0.85
835859	Rock Pulp	0.18	52	18.9	6187	7169	32755	24.2	64.8	67	1081	12.00	57	1.8	1.1	180	174.0	37.0	31.0	190	4.13
835860	Drill Core	7.22	<2	<0.5	1.5	1.3	103	<0.5	<0.5	<1	913	2.72	<5	0.6	0.6	59	<0.5	<0.5	<0.5	<10	1.18
835861	Drill Core	6.76	<2	<0.5	<0.5	0.8	114	<0.5	<0.5	<1	914	2.75	<5	<0.5	0.7	49	<0.5	<0.5	<0.5	<10	1.14

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 3 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835832	Drill Core	0.02	7.3	3	1.11	187	0.159	5.41	1.77	2.56	<0.5	23.0	21	1.8	23.8	2.2	<0.5	<5	11	18.1	<0.5
835833	Drill Core	0.02	8.6	4	0.83	178	0.154	5.57	3.04	1.95	<0.5	27.7	24	2.1	25.5	3.2	<0.5	<5	8	18.0	<0.5
835834	Drill Core	0.01	7.9	3	1.00	291	0.151	6.07	1.65	3.14	<0.5	25.0	22	1.5	30.8	3.1	<0.5	<5	10	18.5	<0.5
835835	Drill Core	0.01	8.0	3	0.59	129	0.127	5.37	3.10	1.54	<0.5	20.7	21	1.6	20.4	2.9	<0.5	<5	9	12.6	<0.5
835836	Drill Core	<0.01	9.6	8	0.37	181	0.110	5.67	3.38	1.31	0.7	35.2	25	1.3	11.7	5.0	<0.5	<5	6	6.5	<0.5
835837	Drill Core	0.01	7.5	5	0.45	100	0.136	5.00	3.45	1.59	<0.5	38.7	21	4.6	12.4	4.5	<0.5	<5	7	4.5	<0.5
835838	Drill Core	0.01	8.3	4	0.51	131	0.141	5.76	3.36	1.66	<0.5	20.1	23	1.1	18.5	3.4	<0.5	<5	8	5.7	<0.5
835839	Rock Pulp	0.06	6.8	91	2.63	453	0.459	6.06	1.48	0.69	27.6	32.2	15	13.9	13.7	2.8	<0.5	<5	22	20.3	7.3
835840	Drill Core	0.01	9.7	6	0.37	163	0.141	6.03	4.04	1.46	0.7	11.7	27	1.3	24.2	3.5	<0.5	<5	10	3.9	<0.5
835841	Drill Core	0.01	10.0	7	0.38	214	0.128	5.96	4.20	0.94	3.5	35.2	27	2.6	16.7	2.7	<0.5	<5	9	3.4	<0.5
835842	Drill Core	0.01	11.2	5	0.40	481	0.120	5.85	3.29	1.39	2.4	29.5	26	1.7	17.9	5.1	<0.5	<5	7	8.1	<0.5
835843	Drill Core	<0.01	8.4	3	0.60	71	0.126	5.76	4.15	0.75	<0.5	24.8	24	2.1	22.8	2.5	<0.5	<5	7	8.3	<0.5
835844	Drill Core	0.01	7.6	3	0.55	97	0.129	5.28	3.75	1.03	<0.5	56.2	22	1.9	16.0	3.1	<0.5	<5	8	8.3	<0.5
835845	Drill Core	0.02	8.9	5	0.98	169	0.179	6.08	2.14	1.80	0.8	33.4	23	1.7	17.4	2.9	<0.5	<5	11	31.6	<0.5
835846	Drill Core	0.01	10.5	5	0.63	189	0.131	5.79	2.47	1.53	<0.5	12.6	27	2.4	36.5	3.0	<0.5	<5	10	11.0	<0.5
835847	Drill Core	<0.01	10.3	7	0.68	215	0.114	6.14	2.73	1.48	<0.5	15.8	28	2.5	36.1	4.4	<0.5	<5	9	9.9	<0.5
835848	Drill Core	0.01	8.2	7	0.94	243	0.132	5.76	2.29	1.40	<0.5	29.7	24	2.2	26.8	3.3	<0.5	<5	10	17.2	<0.5
835849	Drill Core	0.02	6.0	6	1.21	262	0.141	4.74	1.16	1.37	<0.5	12.3	17	1.6	15.8	2.2	<0.5	<5	9	13.6	<0.5
835850	Drill Core	0.04	6.6	7	1.46	302	0.175	5.08	0.83	1.40	2.3	18.2	16	1.4	13.0	2.2	<0.5	<5	12	33.2	<0.5
835851	Drill Core	0.04	5.6	12	0.84	308	0.145	3.82	1.24	1.06	4.7	78.4	13	1.4	8.5	1.6	<0.5	<5	10	11.4	<0.5
835852	Drill Core	0.01	9.0	10	0.51	112	0.109	5.13	2.19	0.95	7.3	33.4	20	1.2	7.9	5.1	<0.5	<5	6	21.0	<0.5
835853	Drill Core	0.02	6.5	3	1.12	88	0.238	5.81	3.06	0.64	5.7	31.5	14	6.7	7.7	2.7	<0.5	<5	14	59.1	<0.5
835854	Drill Core	<0.01	6.2	4	0.79	48	0.116	5.25	1.52	0.95	4.4	11.5	17	1.1	8.4	2.4	<0.5	<5	11	63.9	<0.5
835855	Drill Core	0.02	9.2	<1	1.00	308	0.162	5.80	0.51	1.45	6.9	76.0	23	3.0	24.2	3.8	<0.5	<5	11	24.8	<0.5
835856	Drill Core	0.03	6.8	1	0.96	285	0.234	5.70	1.88	1.90	5.3	17.7	21	1.5	11.2	3.7	<0.5	<5	11	27.3	<0.5
835857	Drill Core	0.06	7.0	6	0.59	135	0.212	5.57	3.12	1.12	0.6	82.9	21	1.5	21.5	3.4	<0.5	<5	11	22.8	<0.5
835858	Drill Core	0.03	8.8	3	0.64	156	0.230	6.05	2.80	1.63	0.8	17.5	27	1.8	19.0	4.3	<0.5	<5	11	13.1	<0.5
835859	Rock Pulp	0.06	6.3	100	2.63	687	0.442	6.01	1.49	0.67	26.1	13.9	13	12.0	14.8	3.2	<0.5	<5	21	23.1	7.4
835860	Drill Core	0.02	9.0	2	0.67	128	0.212	5.78	3.15	1.21	<0.5	50.4	29	2.0	38.0	4.1	<0.5	<5	9	6.8	0.6
835861	Drill Core	0.03	11.0	2	0.75	118	0.215	6.20	2.91	1.54	<0.5	26.5	33	1.6	46.0	3.8	<0.5	<5	10	6.6	<0.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 20, 2009

Page: 3 of 5 Part 3

CERTIFICATE OF ANALYSIS

SMI09000263.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (e.g., 835832) and sample types (e.g., Drill Core, Rock Pulp) with corresponding analytical results.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 4 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835862	Drill Core	6.49	<2	<0.5	<0.5	<0.5	143	<0.5	<0.5	<1	997	2.91	<5	<0.5	0.6	38	<0.5	<0.5	<0.5	<10	0.64
835863	Drill Core	6.50	<2	<0.5	<0.5	1.0	132	<0.5	<0.5	<1	1039	2.56	9	<0.5	0.9	99	<0.5	<0.5	<0.5	<10	1.41
835864	Drill Core	7.21	<2	0.6	<0.5	0.9	132	<0.5	<0.5	1	1328	2.63	<5	<0.5	1.0	105	0.6	<0.5	<0.5	<10	1.96
835865	Drill Core	6.69	2	0.5	<0.5	<0.5	143	<0.5	<0.5	<1	1509	3.09	<5	<0.5	0.6	54	0.5	<0.5	<0.5	<10	1.28
835866	Drill Core	6.68	15	<0.5	1.5	<0.5	127	<0.5	<0.5	<1	1065	2.80	<5	<0.5	0.7	64	0.6	<0.5	<0.5	<10	1.47
835867	Drill Core	6.71	<2	0.6	1.2	1.4	171	<0.5	1.6	1	982	3.59	<5	<0.5	0.8	58	<0.5	<0.5	<0.5	<10	0.76
835868	Drill Core	7.07	2	<0.5	2.7	<0.5	122	<0.5	0.5	<1	655	1.71	<5	<0.5	<0.5	58	<0.5	<0.5	<0.5	<10	0.77
835869	Drill Core	6.99	<2	<0.5	0.8	<0.5	158	<0.5	<0.5	<1	1083	3.48	<5	<0.5	0.8	70	<0.5	<0.5	<0.5	<10	1.10
835870	Drill Core	6.52	<2	0.5	<0.5	<0.5	130	<0.5	<0.5	<1	885	2.40	<5	<0.5	0.8	117	0.5	0.6	<0.5	<10	1.72
835871	Drill Core	5.29	2	<0.5	3.0	<0.5	129	<0.5	<0.5	1	1356	2.40	<5	<0.5	<0.5	81	0.9	<0.5	<0.5	<10	1.95
835872	Drill Core	6.47	<2	<0.5	<0.5	2.0	165	<0.5	0.5	<1	1347	3.67	11	<0.5	0.7	59	<0.5	<0.5	<0.5	<10	1.02
835873	Drill Core	6.55	<2	<0.5	<0.5	<0.5	119	<0.5	<0.5	<1	621	1.76	<5	<0.5	<0.5	48	0.7	<0.5	<0.5	<10	0.56
835874	Drill Core	8.20	14	1.4	1.6	4.2	145	<0.5	2.5	1	1088	3.06	9	<0.5	0.6	56	<0.5	<0.5	<0.5	<10	1.09
835875	Drill Core	7.85	<2	<0.5	<0.5	0.6	134	<0.5	<0.5	<1	1397	3.16	<5	<0.5	<0.5	71	<0.5	<0.5	<0.5	<10	1.35
835876	Drill Core	7.34	<2	<0.5	1.9	0.9	128	<0.5	<0.5	<1	1209	2.86	<5	<0.5	0.5	89	<0.5	<0.5	<0.5	<10	1.05
835877	Drill Core	8.18	<2	<0.5	<0.5	0.6	118	<0.5	<0.5	<1	1137	2.57	7	<0.5	<0.5	55	0.6	<0.5	<0.5	<10	0.92
835878	Drill Core	6.87	3	2.7	5.7	53.9	153	<0.5	0.7	<1	641	1.64	14	0.5	1.0	28	0.9	1.0	<0.5	<10	0.23
835879	Rock Pulp	0.17	52	16.5	6219	7260	32781	24.3	64.2	72	1035	12.11	60	2.2	1.0	178	178.7	34.5	30.9	184	4.22
835880	Drill Core	6.33	7	3.0	3.2	70.4	193	0.7	<0.5	<1	695	1.45	28	<0.5	0.8	18	<0.5	2.7	<0.5	<10	0.14
835881	Drill Core	6.30	5	3.0	5.3	6.0	84	<0.5	<0.5	<1	714	1.42	23	<0.5	<0.5	18	<0.5	0.9	<0.5	<10	0.19
835882	Drill Core	6.48	6	2.4	12.4	14.5	148	<0.5	1.7	1	1185	2.18	27	<0.5	0.7	20	0.7	0.7	<0.5	<10	0.16
835883	Drill Core	7.29	6	1.7	5.4	17.7	267	<0.5	<0.5	<1	1509	3.27	53	<0.5	0.6	32	1.7	1.0	<0.5	11	0.56
835884	Drill Core	6.78	4	1.6	4.0	8.5	150	<0.5	1.7	1	947	2.44	78	<0.5	<0.5	31	0.8	1.1	<0.5	<10	0.50
835885	Drill Core	6.53	5	1.7	2.7	9.8	175	<0.5	0.5	1	1103	3.21	31	<0.5	<0.5	37	0.7	1.2	<0.5	<10	0.60
835886	Drill Core	6.91	5	1.2	3.0	10.8	157	0.5	1.1	3	1380	3.20	18	<0.5	0.5	43	<0.5	0.8	<0.5	<10	0.86
835887	Drill Core	6.78	5	<0.5	5.1	12.1	144	<0.5	<0.5	2	1631	3.30	44	<0.5	<0.5	36	<0.5	1.0	<0.5	<10	0.62
835888	Drill Core	6.97	8	1.3	27.7	47.6	266	0.5	1.4	3	2102	3.01	370	<0.5	<0.5	58	1.0	1.1	<0.5	<10	1.63
835889	Drill Core	6.88	15	2.2	30.4	32.5	263	0.7	<0.5	3	1328	3.30	613	<0.5	<0.5	25	1.3	1.4	<0.5	16	0.37
835890	Drill Core	6.24	6	0.6	7.2	7.6	104	<0.5	<0.5	<1	399	1.34	<5	<0.5	<0.5	22	<0.5	<0.5	<0.5	<10	0.30
835891	Drill Core	6.82	109	9.7	340.1	41.9	1115	<0.5	0.7	6	1166	3.56	21	<0.5	<0.5	30	5.7	0.7	1.3	18	0.22

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.





Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 4 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835862	Drill Core	0.03	10.8	1	0.83	164	0.223	6.36	2.62	2.14	0.6	18.0	32	1.4	26.6	4.1	<0.5	<5	11	7.0	<0.5
835863	Drill Core	0.02	10.7	3	0.68	128	0.182	5.88	2.74	1.53	<0.5	20.1	29	1.9	25.8	5.0	<0.5	<5	10	13.5	<0.5
835864	Drill Core	0.02	9.9	3	0.86	115	0.188	6.05	2.31	1.72	<0.5	62.0	27	2.3	23.9	5.6	<0.5	<5	10	14.6	<0.5
835865	Drill Core	0.03	10.5	<1	0.93	125	0.210	6.46	2.44	1.87	<0.5	12.2	30	2.4	39.9	4.3	<0.5	<5	12	11.6	<0.5
835866	Drill Core	0.02	11.1	<1	0.65	100	0.236	6.76	2.52	2.10	<0.5	21.2	34	2.6	50.6	4.8	<0.5	<5	12	7.4	<0.5
835867	Drill Core	0.04	11.1	13	1.01	205	0.251	7.68	1.83	3.63	<0.5	10.1	37	3.0	24.2	4.8	<0.5	<5	15	6.3	<0.5
835868	Drill Core	0.02	8.3	4	0.18	53	0.189	5.28	3.51	0.83	<0.5	7.8	25	2.7	20.6	4.3	<0.5	<5	10	3.2	<0.5
835869	Drill Core	0.03	12.4	2	0.97	151	0.249	7.63	2.34	2.92	<0.5	17.5	37	2.6	44.6	4.1	<0.5	<5	14	6.8	<0.5
835870	Drill Core	0.02	10.0	6	0.54	112	0.164	5.65	2.40	1.58	0.6	15.2	29	1.9	18.0	4.6	<0.5	<5	10	6.5	<0.5
835871	Drill Core	0.02	7.1	5	0.65	72	0.124	4.92	3.35	0.72	<0.5	13.8	21	1.1	10.0	2.4	<0.5	<5	8	7.1	<0.5
835872	Drill Core	0.02	12.4	<1	1.06	197	0.160	8.29	1.88	3.35	<0.5	11.1	37	3.1	9.9	3.3	<0.5	<5	16	9.2	<0.5
835873	Drill Core	0.02	8.4	6	0.32	48	0.189	5.33	3.28	0.94	0.8	14.1	26	2.8	15.1	3.8	<0.5	<5	9	6.1	<0.5
835874	Drill Core	0.03	11.4	12	0.74	104	0.180	6.43	2.32	2.09	0.7	25.7	31	2.0	12.2	3.3	<0.5	<5	11	9.0	<0.5
835875	Drill Core	0.03	9.7	3	0.95	106	0.243	6.56	2.55	1.94	<0.5	9.2	30	2.0	64.0	3.9	<0.5	<5	12	8.8	<0.5
835876	Drill Core	0.04	9.8	2	0.83	99	0.260	6.61	2.76	1.71	2.6	19.3	30	2.3	29.8	5.4	<0.5	<5	11	8.0	<0.5
835877	Drill Core	0.03	10.0	1	0.78	135	0.246	6.23	3.03	1.28	2.1	12.1	29	2.4	30.8	4.4	<0.5	<5	10	9.0	<0.5
835878	Drill Core	<0.01	6.9	3	0.83	435	0.063	4.61	2.78	1.00	<0.5	64.2	19	2.7	20.3	2.5	<0.5	<5	11	7.1	1.1
835879	Rock Pulp	0.06	7.3	90	2.64	320	0.459	6.07	1.49	0.70	29.2	15.0	14	15.2	17.1	3.6	<0.5	<5	22	24.3	7.4
835880	Drill Core	<0.01	5.4	6	0.64	351	0.061	4.22	3.28	0.80	<0.5	70.2	15	1.7	16.2	2.6	<0.5	<5	10	6.3	0.9
835881	Drill Core	<0.01	3.4	6	0.57	243	0.088	3.84	3.58	0.54	<0.5	71.6	10	1.4	14.8	3.4	<0.5	<5	8	6.2	1.0
835882	Drill Core	0.01	7.3	17	1.30	336	0.112	4.88	3.00	0.95	<0.5	44.1	22	1.9	23.3	3.4	<0.5	<5	12	10.0	1.1
835883	Drill Core	0.02	8.5	3	2.08	864	0.193	5.58	0.82	3.08	<0.5	22.6	26	2.7	24.0	5.5	<0.5	<5	13	16.9	1.6
835884	Drill Core	0.02	9.0	16	0.86	155	0.136	4.79	3.64	0.41	<0.5	26.6	27	1.5	27.5	4.2	<0.5	<5	7	6.0	1.5
835885	Drill Core	0.04	9.3	5	1.36	478	0.231	6.16	2.89	1.58	<0.5	28.0	29	2.2	32.5	4.5	<0.5	<5	12	7.9	2.1
835886	Drill Core	0.05	9.4	3	1.50	420	0.257	6.31	3.03	1.26	<0.5	37.8	26	2.0	37.0	4.3	<0.5	<5	13	10.3	1.8
835887	Drill Core	0.04	8.2	8	1.78	307	0.281	6.04	3.27	0.98	0.7	39.1	25	1.7	36.8	4.3	<0.5	<5	12	13.3	1.4
835888	Drill Core	0.04	6.5	5	1.88	278	0.245	6.00	2.86	0.72	<0.5	43.5	20	2.0	27.8	3.8	<0.5	<5	10	11.0	1.0
835889	Drill Core	0.03	7.0	6	1.98	742	0.251	5.84	1.77	1.83	<0.5	52.4	21	2.6	25.2	3.7	<0.5	<5	13	11.9	1.7
835890	Drill Core	0.01	6.4	8	0.53	142	0.153	4.50	4.29	0.28	<0.5	59.4	20	2.1	16.8	3.8	<0.5	<5	7	1.6	1.3
835891	Drill Core	0.07	5.6	6	1.27	584	0.239	4.85	0.98	1.91	<0.5	25.3	18	1.7	15.8	2.3	<0.5	<5	11	11.3	2.4

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 20, 2009

Page: 4 of 5 Part 3

CERTIFICATE OF ANALYSIS

SMI09000263.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb, 7TX Hf. Rows include sample IDs (835862-835891) and their corresponding analytical results for Rb and Hf.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 5 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835892	Drill Core	7.14	246	22.0	1059	21.0	847	1.6	1.1	6	174	3.25	37	<0.5	0.6	34	7.7	0.6	4.3	<10	0.11
835893	Drill Core	6.60	42	5.6	293.3	23.6	375	0.7	<0.5	3	333	2.27	29	<0.5	0.5	34	4.3	0.6	0.9	<10	0.14
835894	Drill Core	7.01	51	4.0	457.0	12.6	385	0.9	4.7	4	310	2.27	26	<0.5	0.7	42	3.2	0.9	0.5	<10	0.15
835895	Drill Core	6.67	58	2.7	1923	22.6	155	2.4	<0.5	5	201	3.36	26	<0.5	0.7	42	1.4	0.7	1.0	<10	0.17
835896	Drill Core	6.84	33	1.8	246.2	7.3	96	<0.5	<0.5	3	220	1.85	12	<0.5	0.7	32	<0.5	<0.5	0.6	<10	0.11
835897	Drill Core	6.59	36	2.1	580.8	18.6	467	0.6	1.0	2	124	2.47	11	<0.5	0.9	31	2.5	<0.5	<0.5	<10	0.13
835898	Drill Core	7.15	72	2.0	773.6	11.7	4785	0.6	<0.5	5	165	2.38	39	<0.5	0.6	29	26.5	1.4	1.1	<10	0.16
835899	Rock Pulp	0.17	58	16.6	5913	7155	33194	23.2	56.3	60	1004	11.85	59	1.7	0.9	177	171.0	35.1	27.0	175	4.10
835900	Drill Core	6.74	31	4.9	1694	11.4	1063	0.8	<0.5	4	130	1.79	37	<0.5	0.7	25	5.8	1.1	0.7	<10	0.16
835901	Drill Core	6.61	109	5.9	1112	48.4	3304	2.2	<0.5	3	490	3.45	55	<0.5	0.5	27	20.5	2.2	0.8	<10	0.22
835902	Drill Core	7.45	11	2.0	364.6	142.0	4732	0.8	2.5	2	516	2.52	12	<0.5	<0.5	27	28.2	0.6	<0.5	12	0.17
835903	Drill Core	5.47	3	1.4	20.5	26.4	877	<0.5	2.5	1	872	4.13	11	<0.5	<0.5	35	3.8	<0.5	<0.5	<10	0.17
835904	Drill Core	6.38	6	0.5	56.6	22.7	1649	<0.5	1.4	2	727	3.84	11	<0.5	<0.5	29	10.4	<0.5	<0.5	<10	0.17
835905	Drill Core	7.12	6	1.1	44.5	7.4	2390	<0.5	<0.5	1	1478	4.13	8	<0.5	<0.5	32	15.5	<0.5	<0.5	<10	0.21
835906	Drill Core	7.09	26	0.9	104.9	13.6	2165	<0.5	<0.5	<1	902	4.09	<5	<0.5	<0.5	34	12.6	<0.5	0.9	<10	0.21
835907	Drill Core	7.48	12	4.3	1000	46.8	5851	1.6	<0.5	6	482	5.12	24	<0.5	<0.5	39	36.3	0.6	4.4	16	0.11
835908	Drill Core	7.76	12	1.6	214.7	13.0	2046	<0.5	<0.5	2	546	3.62	11	<0.5	<0.5	51	12.2	<0.5	0.5	11	0.16
835909	Drill Core	6.95	23	0.6	76.4	13.2	2881	<0.5	1.9	<1	555	4.79	7	<0.5	<0.5	30	17.2	<0.5	<0.5	<10	0.09
835910	Drill Core	6.84	23	1.4	415.2	17.5	4240	1.4	1.5	2	564	4.32	11	<0.5	<0.5	29	25.1	<0.5	1.4	<10	0.08
835911	Drill Core	6.85	17	1.5	302.2	37.8	4507	0.7	1.3	3	740	3.28	13	<0.5	<0.5	44	27.7	<0.5	0.6	<10	0.30
835912	Drill Core	6.65	13	2.0	577.5	12.2	8855	<0.5	1.2	2	1053	3.62	6	<0.5	<0.5	28	48.1	<0.5	0.6	<10	0.10
835913	Drill Core	0.81	<2	<0.5	6.4	22.1	112	<0.5	4.8	6	770	2.47	<5	3.7	7.4	732	0.7	<0.5	<0.5	54	2.63
835914	Drill Core	6.56	5	0.8	80.9	7.8	2263	<0.5	0.5	1	1658	3.54	6	<0.5	<0.5	20	12.7	<0.5	<0.5	<10	0.10



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 5 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000263.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835892	Drill Core	0.03	8.8	9	0.36	484	0.160	5.13	1.60	1.71	<0.5	27.6	28	1.6	20.6	2.4	<0.5	<5	7	3.6	2.9
835893	Drill Core	0.03	8.0	8	0.56	608	0.154	5.05	2.09	1.35	<0.5	21.1	24	2.4	14.7	2.8	<0.5	<5	6	4.7	1.6
835894	Drill Core	0.03	7.3	13	0.53	765	0.169	5.87	1.59	1.81	<0.5	28.7	22	1.2	14.1	3.4	<0.5	<5	9	8.8	1.6
835895	Drill Core	0.03	7.5	8	0.43	465	0.146	5.11	1.33	1.63	<0.5	16.4	24	4.7	18.4	2.2	<0.5	<5	7	2.7	3.0
835896	Drill Core	0.03	11.0	9	0.45	762	0.165	5.59	2.12	1.61	<0.5	22.5	32	2.8	20.1	2.8	<0.5	<5	8	3.4	1.6
835897	Drill Core	0.03	9.4	10	0.35	622	0.166	5.10	2.41	1.43	<0.5	17.7	29	2.0	23.2	3.5	<0.5	<5	7	2.2	2.3
835898	Drill Core	0.03	10.0	9	0.36	544	0.163	5.27	2.55	1.33	<0.5	22.2	30	1.8	22.3	3.5	<0.5	<5	7	4.0	2.4
835899	Rock Pulp	0.06	6.8	80	2.54	1271	0.449	5.89	1.45	0.69	29.7	25.4	14	12.0	16.2	3.7	<0.5	<5	22	22.6	7.4
835900	Drill Core	0.03	9.5	7	0.30	688	0.166	5.12	2.61	1.33	<0.5	18.3	31	2.3	24.2	2.9	<0.5	<5	7	2.6	1.9
835901	Drill Core	0.03	7.8	8	0.63	439	0.131	4.66	2.14	1.12	<0.5	18.1	24	2.2	20.6	1.9	<0.5	<5	7	5.4	3.4
835902	Drill Core	0.04	7.4	11	0.73	540	0.171	4.97	2.37	0.93	<0.5	13.6	22	2.0	16.8	2.8	<0.5	<5	7	4.8	2.4
835903	Drill Core	0.04	5.9	5	1.39	237	0.212	5.64	1.34	1.37	<0.5	14.5	18	1.4	23.4	2.1	<0.5	<5	12	9.1	4.1
835904	Drill Core	0.04	4.7	7	1.01	230	0.170	5.29	1.62	1.33	<0.5	39.4	15	1.6	16.0	1.8	<0.5	<5	10	6.5	3.8
835905	Drill Core	0.03	5.5	6	1.69	235	0.190	5.49	0.96	1.40	<0.5	50.6	19	1.5	21.5	2.1	<0.5	<5	12	11.8	3.5
835906	Drill Core	0.03	7.2	6	1.06	171	0.146	5.06	1.68	0.97	<0.5	13.4	21	2.6	18.0	1.8	<0.5	<5	10	4.1	3.9
835907	Drill Core	0.03	5.8	8	0.65	195	0.128	4.20	0.54	1.37	<0.5	11.4	18	6.1	17.6	1.2	<0.5	<5	10	3.4	5.6
835908	Drill Core	0.03	7.2	7	0.89	200	0.139	5.18	1.26	1.35	<0.5	12.7	22	2.5	13.2	1.8	<0.5	<5	9	7.6	3.7
835909	Drill Core	0.02	5.4	8	0.91	148	0.098	4.89	1.42	1.17	<0.5	15.0	18	1.8	24.3	1.5	<0.5	<5	9	3.7	5.1
835910	Drill Core	0.02	4.7	8	0.83	133	0.106	4.48	1.54	0.94	<0.5	9.6	16	1.7	15.1	1.4	<0.5	<5	9	0.9	4.7
835911	Drill Core	0.03	7.2	10	0.74	189	0.122	4.60	1.25	1.41	<0.5	13.1	22	1.8	13.7	2.2	<0.5	<5	9	3.2	3.5
835912	Drill Core	0.02	6.3	8	1.35	148	0.107	4.69	0.93	1.25	<0.5	15.2	19	2.1	14.0	1.7	<0.5	<5	9	7.9	3.8
835913	Drill Core	0.09	26.5	14	0.76	1056	0.256	7.29	2.69	2.94	<0.5	9.2	56	1.2	13.5	25.0	1.4	<5	6	35.4	<0.5
835914	Drill Core	0.02	4.0	7	2.10	125	0.100	4.48	1.06	1.12	<0.5	14.1	13	2.0	13.7	1.1	<0.5	<5	8	5.7	3.2



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Project: Bodine  
Report Date: October 20, 2009

Page: 5 of 5 Part 3

# CERTIFICATE OF ANALYSIS

# SMI09000263.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
835892	Drill Core	21.7	0.9
835893	Drill Core	15.9	0.5
835894	Drill Core	24.1	1.2
835895	Drill Core	19.6	0.6
835896	Drill Core	17.7	0.7
835897	Drill Core	17.0	<0.5
835898	Drill Core	14.8	0.8
835899	Rock Pulp	20.1	0.6
835900	Drill Core	15.4	<0.5
835901	Drill Core	13.4	0.6
835902	Drill Core	11.6	0.6
835903	Drill Core	13.5	0.6
835904	Drill Core	14.0	<0.5
835905	Drill Core	13.0	<0.5
835906	Drill Core	10.4	<0.5
835907	Drill Core	14.5	<0.5
835908	Drill Core	14.3	0.5
835909	Drill Core	12.3	0.9
835910	Drill Core	10.9	<0.5
835911	Drill Core	15.2	<0.5
835912	Drill Core	12.9	0.6
835913	Drill Core	107.8	0.6
835914	Drill Core	11.5	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 1 of 3 Part 1

QUALITY CONTROL REPORT

SMI09000263.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
Pulp Duplicates																					
835802	Drill Core	6.97	<2	<0.5	6.5	4.0	71	<0.5	<0.5	1	585	1.88	<5	<0.5	0.5	42	<0.5	<0.5	<0.5	<10	0.26
REP 835802	QC			<0.5	7.1	3.8	65	<0.5	<0.5	1	582	1.83	<5	<0.5	0.6	41	<0.5	<0.5	<0.5	<10	0.24
REP 835805	QC		<2																		
835835	Drill Core	5.86	<2	<0.5	1.3	2.5	86	<0.5	0.7	<1	875	1.42	<5	<0.5	0.7	32	<0.5	<0.5	<0.5	<10	0.46
REP 835835	QC		<2																		
835839	Rock Pulp	0.17	68	17.6	6199	7246	32732	23.1	67.7	65	1041	12.04	58	1.9	1.1	178	170.0	38.6	30.6	188	4.16
REP 835839	QC			17.8	6139	7188	32598	22.2	63.9	67	1079	11.90	63	1.7	1.1	177	174.3	39.2	29.9	183	4.16
835865	Drill Core	6.69	2	0.5	<0.5	<0.5	143	<0.5	<0.5	<1	1509	3.09	<5	<0.5	0.6	54	0.5	<0.5	<0.5	<10	1.28
REP 835865	QC		<2																		
835885	Drill Core	6.53	5	1.7	2.7	9.8	175	<0.5	0.5	1	1103	3.21	31	<0.5	<0.5	37	0.7	1.2	<0.5	<10	0.60
REP 835885	QC			1.5	3.2	9.7	174	<0.5	1.5	1	1097	3.19	31	<0.5	<0.5	33	0.5	1.0	<0.5	<10	0.58
835892	Drill Core	7.14	246	22.0	1059	21.0	847	1.6	1.1	6	174	3.25	37	<0.5	0.6	34	7.7	0.6	4.3	<10	0.11
REP 835892	QC			21.8	1058	22.8	874	1.5	1.6	8	175	3.21	35	<0.5	0.6	32	7.5	0.6	4.7	<10	0.12
Core Reject Duplicates																					
835805	Drill Core	6.22	<2	0.8	1.2	9.3	101	<0.5	<0.5	1	730	1.93	<5	<0.5	<0.5	44	<0.5	<0.5	<0.5	<10	0.34
DUP 835805	QC		4	0.5	3.2	3.7	65	<0.5	0.6	1	644	1.76	<5	<0.5	<0.5	40	<0.5	<0.5	<0.5	<10	0.36
835840	Drill Core	6.78	<2	<0.5	4.8	4.3	104	<0.5	1.9	2	679	1.83	<5	<0.5	0.8	51	<0.5	<0.5	<0.5	<10	0.51
DUP 835840	QC		3	<0.5	3.6	4.2	111	<0.5	1.3	2	673	1.81	<5	<0.5	0.9	52	<0.5	0.6	<0.5	<10	0.53
835875	Drill Core	7.85	<2	<0.5	<0.5	0.6	134	<0.5	<0.5	<1	1397	3.16	<5	<0.5	<0.5	71	<0.5	<0.5	<0.5	<10	1.35
DUP 835875	QC		<2	0.6	<0.5	2.0	128	<0.5	<0.5	<1	1419	3.32	<5	<0.5	<0.5	72	<0.5	<0.5	<0.5	<10	1.38
835910	Drill Core	6.84	23	1.4	415.2	17.5	4240	1.4	1.5	2	564	4.32	11	<0.5	<0.5	29	25.1	<0.5	1.4	<10	0.08
DUP 835910	QC		18	1.2	297.2	13.4	3591	1.1	1.1	1	526	3.81	11	<0.5	<0.5	26	21.1	<0.5	1.1	<10	0.08
Reference Materials																					
STD OXE56	Standard		608																		
STD OXE56	Standard		583																		
STD OXE56	Standard		575																		
STD OXE56	Standard		595																		
STD OXE56	Standard		613																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 1 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000263.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
Pulp Duplicates																					
835802	Drill Core	0.02	7.3	3	0.26	64	0.145	5.43	5.32	0.44	<0.5	13.2	21	1.9	8.2	2.3	<0.5	<5	9	0.9	<0.5
REP 835802	QC	0.02	7.2	4	0.26	70	0.152	4.87	5.37	0.44	<0.5	14.3	21	1.6	8.5	2.6	<0.5	<5	9	1.2	<0.5
REP 835805	QC																				
835835	Drill Core	0.01	8.0	3	0.59	129	0.127	5.37	3.10	1.54	<0.5	20.7	21	1.6	20.4	2.9	<0.5	<5	9	12.6	<0.5
REP 835835	QC																				
835839	Rock Pulp	0.06	6.8	91	2.63	453	0.459	6.06	1.48	0.69	27.6	32.2	15	13.9	13.7	2.8	<0.5	<5	22	20.3	7.3
REP 835839	QC	0.05	6.0	91	2.61	456	0.453	5.98	1.46	0.69	28.4	32.6	13	12.8	15.7	3.4	<0.5	<5	22	23.1	7.3
835865	Drill Core	0.03	10.5	<1	0.93	125	0.210	6.46	2.44	1.87	<0.5	12.2	30	2.4	39.9	4.3	<0.5	<5	12	11.6	<0.5
REP 835865	QC																				
835885	Drill Core	0.04	9.3	5	1.36	478	0.231	6.16	2.89	1.58	<0.5	28.0	29	2.2	32.5	4.5	<0.5	<5	12	7.9	2.1
REP 835885	QC	0.04	9.8	4	1.35	496	0.232	5.97	2.84	1.58	<0.5	28.7	29	2.5	30.0	3.8	<0.5	<5	13	8.8	2.1
835892	Drill Core	0.03	8.8	9	0.36	484	0.160	5.13	1.60	1.71	<0.5	27.6	28	1.6	20.6	2.4	<0.5	<5	7	3.6	2.9
REP 835892	QC	0.03	8.9	8	0.37	473	0.159	5.06	1.56	1.68	<0.5	24.6	26	2.9	20.4	2.3	<0.5	<5	7	2.9	2.9
Core Reject Duplicates																					
835805	Drill Core	0.02	5.6	13	0.42	79	0.155	5.44	4.84	0.58	<0.5	18.6	18	1.5	16.0	2.5	<0.5	<5	8	2.6	<0.5
DUP 835805	QC	0.03	5.0	4	0.40	74	0.136	6.21	4.82	0.53	<0.5	13.6	16	1.5	12.4	2.0	<0.5	<5	9	3.8	<0.5
835840	Drill Core	0.01	9.7	6	0.37	163	0.141	6.03	4.04	1.46	0.7	11.7	27	1.3	24.2	3.5	<0.5	<5	10	3.9	<0.5
DUP 835840	QC	0.01	9.1	4	0.39	160	0.147	6.23	4.08	1.47	0.6	11.3	28	1.7	24.8	3.0	<0.5	<5	10	3.7	<0.5
835875	Drill Core	0.03	9.7	3	0.95	106	0.243	6.56	2.55	1.94	<0.5	9.2	30	2.0	64.0	3.9	<0.5	<5	12	8.8	<0.5
DUP 835875	QC	0.03	10.4	21	0.97	105	0.255	6.83	2.66	1.96	<0.5	21.4	31	1.6	24.0	4.9	<0.5	<5	12	7.0	<0.5
835910	Drill Core	0.02	4.7	8	0.83	133	0.106	4.48	1.54	0.94	<0.5	9.6	16	1.7	15.1	1.4	<0.5	<5	9	0.9	4.7
DUP 835910	QC	0.02	4.5	14	0.79	127	0.097	4.32	1.65	0.85	<0.5	11.2	13	2.1	16.6	1.2	<0.5	<5	7	4.4	3.9
Reference Materials																					
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 20, 2009

**Page:** 1 of 3 **Part** 3

QUALITY CONTROL REPORT

SMI09000263.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
Pulp Duplicates			
835802	Drill Core	3.6	<0.5
REP 835802	QC	3.4	<0.5
REP 835805	QC		
835835	Drill Core	24.5	0.6
REP 835835	QC		
835839	Rock Pulp	17.7	<0.5
REP 835839	QC	22.2	<0.5
835865	Drill Core	17.0	0.7
REP 835865	QC		
835885	Drill Core	20.8	0.8
REP 835885	QC	17.1	0.9
835892	Drill Core	21.7	0.9
REP 835892	QC	20.8	0.8
Core Reject Duplicates			
835805	Drill Core	3.1	0.6
DUP 835805	QC	3.4	<0.5
835840	Drill Core	24.8	<0.5
DUP 835840	QC	19.1	0.6
835875	Drill Core	15.9	0.9
DUP 835875	QC	23.0	1.9
835910	Drill Core	10.9	<0.5
DUP 835910	QC	8.9	<0.5
Reference Materials			
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		





Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 3 Part 1

QUALITY CONTROL REPORT

SMI09000263.1

		WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01
STD OXH55	Standard		1246																		
STD OXH55	Standard		1232																		
STD OXH55	Standard		1275																		
STD OXH55	Standard		1202																		
STD OXH55	Standard		1322																		
STD SF-3T	Standard			315.3	7716	8750	11110	52.3	3545	179	4226	8.03	40	3.5	4.7	432	47.8	10.5	4.7	125	4.10
STD SF-3T	Standard			318.8	7769	8811	11192	53.5	3546	181	4217	8.08	39	3.6	4.7	436	48.0	10.5	4.5	126	4.11
STD SF-3T	Standard			320.0	7799	8799	10898	53.4	3552	191	4207	8.37	40	4.1	4.7	436	48.3	9.3	4.7	134	4.08
STD SF-3T	Standard			324.4	7809	8807	10898	53.4	3511	187	4202	8.34	38	4.0	4.7	434	48.7	10.7	4.8	134	4.06
STD SF-3T	Standard			322.5	7692	8575	11055	52.5	3497	186	4164	8.19	41	3.9	4.5	432	50.5	10.7	4.7	132	4.05
STD SF-3T	Standard			325.5	7692	8732	10829	51.6	3534	186	4190	8.21	41	4.1	4.5	433	51.5	10.5	4.8	135	4.07
STD SF-3T	Standard			316.8	7783	8675	10864	52.6	3527	182	4193	8.31	41	3.9	4.8	437	48.0	9.6	5.1	134	4.04
STD SF-3T	Standard			319.4	7805	8743	10915	53.3	3542	190	4225	8.36	42	4.1	4.8	437	49.7	9.6	4.9	134	4.07
STD SF-3T	Standard			322.9	7717	8661	10829	52.8	3495	191	4137	8.26	41	4.1	4.8	427	50.5	10.8	4.9	124	4.01
STD SF-3T	Standard			315.1	7677	8520	10839	51.1	3465	186	4133	8.27	36	4.0	4.8	426	54.8	10.6	4.9	123	4.02
STD SF-3T	Standard			318.3	7773	9234	10932	52.9	3544	185	4226	8.29	38	3.6	4.0	437	46.1	8.6	4.2	134	4.10
STD SF-3T	Standard			315.2	7733	9227	10957	57.6	3573	181	4234	8.28	40	3.9	4.8	439	47.6	9.4	4.7	135	4.10
STD OXE56 Expected			611																		
STD OXH55 Expected			1282																		
STD SF-3T Expected				320	7723	9610	10672	52	3500	181	4320	8.33	40	4	4.7	440	47.5	11.1	4.8	143	4.1
BLK	Blank			<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank			<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank			<0.5	<0.5	<0.5	76	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank			<0.5	<0.5	<0.5	<5	<0.5	2.8	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
BLK	Blank			<2																	
BLK	Blank			<2																	
BLK	Blank			<2																	
BLK	Blank			<2																	
BLK	Blank			<2																	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000263.1

		7TX P %	7TX La ppm	7TX Cr ppm	7TX Mg %	7TX Ba ppm	7TX Ti %	7TX Al %	7TX Na %	7TX K %	7TX W ppm	7TX Zr ppm	7TX Ce ppm	7TX Sn ppm	7TX Y ppm	7TX Nb ppm	7TX Ta ppm	7TX Be ppm	7TX Sc ppm	7TX Li ppm	7TX S %	
		0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
STD OXH55	Standard																					
STD OXH55	Standard																					
STD OXH55	Standard																					
STD OXH55	Standard																					
STD OXH55	Standard																					
STD SF-3T	Standard	0.06	17.9	157	4.59	478	0.193	5.44	2.09	2.03	4.3	14.7	41	5.8	11.2	15.9	0.8	<5	6	24.6	4.2	
STD SF-3T	Standard	0.06	17.6	174	4.62	430	0.191	5.49	2.10	1.98	4.2	14.6	41	4.8	11.3	14.7	0.9	<5	7	23.5	4.2	
STD SF-3T	Standard	0.06	17.3	173	4.63	419	0.190	5.51	2.11	2.48	4.2	14.3	39	6.2	10.5	14.8	0.6	<5	7	25.6	4.3	
STD SF-3T	Standard	0.06	18.3	172	4.62	429	0.192	5.50	2.09	2.48	4.3	14.4	40	5.9	10.7	15.1	0.6	<5	7	24.2	4.3	
STD SF-3T	Standard	0.06	17.7	186	4.55	479	0.190	5.41	2.08	2.31	4.1	14.7	39	5.9	10.5	15.4	0.7	<5	6	29.9	3.8	
STD SF-3T	Standard	0.06	17.9	196	4.59	479	0.192	5.44	2.09	2.07	4.2	14.8	40	4.9	10.8	15.8	0.9	<5	7	27.3	3.8	
STD SF-3T	Standard	0.05	18.3	196	4.63	476	0.191	5.52	2.10	2.56	3.8	13.8	40	5.6	11.5	15.9	0.6	<5	7	23.1	4.2	
STD SF-3T	Standard	0.06	17.8	201	4.63	486	0.191	5.51	2.11	2.50	4.2	14.2	40	6.1	10.6	15.4	<0.5	<5	7	26.4	4.2	
STD SF-3T	Standard	0.06	18.4	198	4.55	548	0.188	5.41	2.07	2.37	4.4	14.0	42	8.8	10.5	15.2	0.7	<5	7	24.1	3.7	
STD SF-3T	Standard	0.06	18.6	197	4.53	549	0.187	5.39	2.06	2.33	4.1	13.2	41	5.7	11.2	14.9	0.8	<5	7	29.2	3.7	
STD SF-3T	Standard	0.06	17.1	195	4.63	491	0.191	5.45	2.08	2.43	4.2	15.0	39	5.5	10.8	15.2	0.6	<5	7	23.8	3.8	
STD SF-3T	Standard	0.06	17.4	203	4.66	414	0.192	5.45	2.08	2.46	4.2	14.2	41	6.1	10.5	15.4	0.7	<5	7	29.2	3.8	
STD OXE56 Expected																						
STD OXH55 Expected																						
STD SF-3T Expected		0.06	17	207.4	4.67	508	0.19	5.43	2.06	2.47	4.3	14	38	5.8	11.5	15.1	0.9	2.4	7	19.1	3.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 20, 2009

**Page:** 2 of 3 **Part** 3

# QUALITY CONTROL REPORT

SMI09000263.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD SF-3T	Standard	76.7	<0.5
STD SF-3T	Standard	73.3	0.6
STD SF-3T	Standard	86.1	0.9
STD SF-3T	Standard	89.1	<0.5
STD SF-3T	Standard	76.3	0.5
STD SF-3T	Standard	68.7	<0.5
STD SF-3T	Standard	86.6	0.6
STD SF-3T	Standard	86.1	0.8
STD SF-3T	Standard	87.4	0.7
STD SF-3T	Standard	82.0	0.6
STD SF-3T	Standard	85.8	0.6
STD SF-3T	Standard	85.6	0.5
STD OXE56 Expected			
STD OXH55 Expected			
STD SF-3T Expected		90.8	0.6
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** Amarc Resources  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 20, 2009

**Page:** 3 of 3 **Part** 1

QUALITY CONTROL REPORT

SMI09000263.1

		WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX		
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
BLK	Blank		<2																			
BLK	Blank		<2																			
BLK	Blank		<2																			
BLK	Blank			<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01	
BLK	Blank		<2																			
BLK	Blank		<2																			
BLK	Blank			<0.5	<0.5	4.4	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01	
Prep Wash																						
G1	Prep Blank		<2	<0.5	14.8	24.1	65	<0.5	9.2	6	852	2.62	<5	2.4	6.0	722	<0.5	<0.5	<0.5	54	2.45	
G1	Prep Blank		<2	<0.5	15.2	44.7	59	<0.5	4.5	5	854	2.50	<5	3.9	7.1	729	<0.5	<0.5	<0.5	52	2.50	



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** Amarc Resources  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 20, 2009

**Page:** 3 of 3 **Part** 2

QUALITY CONTROL REPORT

SMI09000263.1

		7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX		
		P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
		%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
		0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
BLK	Blank																					
BLK	Blank																					
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5	
Prep Wash																						
G1	Prep Blank	0.09	18.0	12	0.66	958	0.237	6.79	2.64	1.68	<0.5	8.7	38	1.5	13.3	23.5	1.4	<5	5	38.8	<0.5	
G1	Prep Blank	0.10	20.2	13	0.69	984	0.241	7.42	2.63	2.52	<0.5	8.8	43	1.7	13.0	23.5	1.5	<5	5	40.4	<0.5	



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Project: Bodine

Report Date: October 20, 2009

Page: 3 of 3 Part 3

# QUALITY CONTROL REPORT

# SMI09000263.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank	<0.5	<0.5
BLK	Blank		
BLK	Blank		
BLK	Blank	<0.5	<0.5
Prep Wash			
G1	Prep Blank	55.5	0.6
G1	Prep Blank	89.6	0.6



1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Submitted By: Ted Oliver  
Receiving Lab: Canada-Smithers  
Received: September 29, 2009  
Report Date: October 16, 2009  
Page: 1 of 6

## CERTIFICATE OF ANALYSIS

SMI09000296.1

### CLIENT JOB INFORMATION

Project: Bodine  
Shipment ID:  
P.O. Number: WARR\_SSNB9011  
Number of Samples: 133

### SAMPLE DISPOSAL

RTRN-PLP Return  
RTRN-RJT Return

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6  
Canada

CC:

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R150	126	Crush split and pulverize drill core to 200 mesh			VAN
3B	133	Fire assay fusion Au by ICP-ES	30	Completed	VAN
7TX	133	4 Acid Digestion Analysis by ICP-ES/ICP-MS	0.5	Completed	VAN
DIS-RJT	133	Warehouse handling / Disposition of reject			SMI

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. \*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 2 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835915	Drill Core	2.77	<2	1.2	15.8	24.2	82	<0.5	<0.5	<1	513	1.51	<5	0.6	0.6	44	<0.5	<0.5	<0.5	<10	0.72
835916	Drill Core	2.51	<2	0.6	5.4	7.3	147	<0.5	0.8	<1	432	1.44	<5	<0.5	<0.5	29	<0.5	<0.5	<0.5	<10	0.21
835917	Drill Core	1.72	<2	<0.5	13.8	9.7	138	<0.5	<0.5	<1	493	1.50	<5	<0.5	0.6	32	<0.5	<0.5	<0.5	<10	0.45
835918	Drill Core	4.68	<2	2.9	5.2	21.8	107	<0.5	<0.5	1	575	1.87	<5	<0.5	0.5	26	<0.5	<0.5	<0.5	<10	0.26
835919	Drill Core	7.11	133	6.5	17.0	17.5	116	<0.5	<0.5	1	664	2.35	<5	<0.5	0.8	19	<0.5	<0.5	<0.5	<10	0.27
835920	Rock Pulp	0.11	58	16.2	6053	7074	33222	25.3	61.5	62	1078	11.92	57	1.7	1.1	174	181.2	24.3	30.2	178	4.18
835921	Drill Core	0.91	<2	0.9	4.3	14.3	72	<0.5	<0.5	1	551	1.74	<5	<0.5	0.6	15	<0.5	<0.5	<0.5	<10	0.30
835922	Drill Core	6.12	<2	1.6	13.5	17.5	397	<0.5	<0.5	<1	506	1.71	6	<0.5	0.7	26	4.6	<0.5	<0.5	<10	0.31
835923	Drill Core	6.33	<2	1.5	6.3	5.1	80	<0.5	<0.5	1	335	0.91	<5	<0.5	0.6	25	<0.5	<0.5	<0.5	<10	0.28
835924	Drill Core	2.47	<2	<0.5	3.3	7.1	114	<0.5	0.7	<1	1008	2.36	<5	<0.5	0.7	35	<0.5	<0.5	<0.5	<10	1.00
835925	Drill Core	2.71	<2	<0.5	4.9	4.8	127	<0.5	<0.5	<1	492	1.34	<5	<0.5	0.7	24	<0.5	<0.5	<0.5	<10	0.20
835926	Drill Core	2.45	2	1.7	4.7	14.0	125	<0.5	<0.5	2	795	2.01	<5	<0.5	0.7	29	<0.5	0.5	<0.5	<10	0.54
835927	Drill Core	6.04	3	2.0	23.8	22.7	67	<0.5	7.1	2	370	0.80	6	<0.5	0.5	18	1.6	<0.5	<0.5	<10	0.35
835928	Drill Core	5.25	<2	8.7	6.1	5.3	112	<0.5	2.3	2	1026	2.55	<5	<0.5	0.8	18	<0.5	0.6	<0.5	21	0.29
835929	Drill Core	0.63	<2	4.6	9.2	4.9	104	<0.5	1.6	1	992	2.32	<5	<0.5	0.6	19	<0.5	<0.5	<0.5	18	0.19
835930	Drill Core	4.94	<2	3.8	4.7	7.2	90	<0.5	1.5	<1	670	1.71	<5	<0.5	0.6	12	<0.5	<0.5	<0.5	<10	0.18
835931	Drill Core	5.24	<2	1.5	3.2	5.5	81	<0.5	0.5	<1	666	1.82	<5	<0.5	0.6	18	<0.5	<0.5	<0.5	<10	0.23
835932	Drill Core	1.86	<2	6.5	3.5	6.8	93	<0.5	0.8	<1	1284	2.27	<5	0.5	0.7	54	<0.5	<0.5	<0.5	<10	1.47
835933	Drill Core	1.73	<2	1.7	6.3	7.6	95	<0.5	<0.5	<1	906	2.09	<5	<0.5	0.7	23	<0.5	<0.5	<0.5	<10	0.27
835934	Drill Core	5.26	<2	3.1	41.1	10.6	91	<0.5	68.4	16	998	3.57	<5	0.8	2.5	368	<0.5	<0.5	<0.5	112	3.64
835935	Drill Core	6.42	<2	2.0	9.9	9.9	281	<0.5	2.2	2	767	1.90	<5	<0.5	0.5	22	1.3	<0.5	<0.5	<10	0.26
835936	Drill Core	5.70	<2	2.9	25.9	14.3	258	<0.5	5.6	3	844	2.13	<5	<0.5	0.6	30	1.0	<0.5	<0.5	18	0.28
835937	Drill Core	6.86	<2	2.2	19.6	13.7	198	<0.5	4.0	5	1187	3.45	<5	<0.5	0.6	33	<0.5	0.7	<0.5	33	0.38
835938	Drill Core	6.56	<2	1.7	14.3	8.9	214	<0.5	2.7	4	887	2.72	<5	<0.5	<0.5	31	0.5	<0.5	<0.5	28	0.20
835939	Drill Core	6.70	<2	1.7	6.1	7.9	93	<0.5	<0.5	2	760	2.11	<5	<0.5	<0.5	33	<0.5	<0.5	<0.5	<10	0.30
835940	Rock Pulp	0.17	61	17.8	6066	7097	33175	24.0	65.4	65	1103	11.84	59	1.7	1.0	174	166.5	26.2	31.1	176	4.11
835941	Drill Core	6.36	3	0.6	23.2	10.6	255	<0.5	<0.5	<1	438	1.50	<5	<0.5	<0.5	34	0.8	<0.5	<0.5	<10	0.33
835942	Drill Core	6.77	<2	1.8	14.0	11.6	98	<0.5	3.3	2	688	2.06	<5	<0.5	<0.5	34	<0.5	<0.5	<0.5	<10	0.30
835943	Drill Core	6.51	<2	1.9	15.0	5.5	95	<0.5	1.9	2	793	2.05	<5	<0.5	<0.5	35	<0.5	<0.5	<0.5	<10	0.27
835944	Drill Core	6.51	<2	1.7	8.7	3.8	101	<0.5	1.1	2	885	2.08	<5	<0.5	<0.5	37	<0.5	<0.5	<0.5	12	0.35

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.





Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 2 of 6 Part 2

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
835915	Drill Core	0.05	6.5	4	0.64	79	0.134	4.38	3.55	1.06	<0.5	26.0	18	2.1	15.3	2.2	<0.5	<5	8	4.1	<0.5
835916	Drill Core	0.02	6.2	5	0.35	67	0.147	4.64	4.39	0.80	<0.5	23.5	19	1.1	11.6	2.3	<0.5	<5	8	1.1	<0.5
835917	Drill Core	0.02	6.4	6	0.46	73	0.143	4.64	4.11	0.84	<0.5	22.8	20	1.4	9.8	2.5	<0.5	<5	8	<0.5	<0.5
835918	Drill Core	0.02	6.9	5	0.86	128	0.171	5.06	3.96	1.53	0.8	18.8	21	3.9	13.7	2.8	<0.5	<5	10	4.2	<0.5
835919	Drill Core	0.02	6.9	5	1.57	319	0.181	6.05	1.77	3.45	<0.5	34.0	20	3.0	18.6	3.2	<0.5	<5	10	9.9	<0.5
835920	Rock Pulp	0.06	5.7	93	2.54	365	0.450	5.87	1.47	0.68	27.4	12.9	13	15.3	16.2	3.2	<0.5	<5	21	19.5	7.6
835921	Drill Core	0.01	4.3	3	1.36	272	0.143	5.10	1.20	3.16	<0.5	75.3	14	1.6	10.4	3.2	<0.5	<5	8	9.4	<0.5
835922	Drill Core	0.02	7.6	6	0.74	161	0.141	4.40	3.03	1.83	<0.5	31.7	23	2.7	19.6	3.0	<0.5	<5	7	5.7	<0.5
835923	Drill Core	0.02	7.2	5	0.28	73	0.117	4.11	3.91	0.71	<0.5	28.1	21	1.3	23.0	3.0	<0.5	<5	6	<0.5	<0.5
835924	Drill Core	0.01	6.8	5	1.20	168	0.155	6.37	2.99	2.56	<0.5	21.5	21	1.8	10.0	3.4	<0.5	<5	10	<0.5	<0.5
835925	Drill Core	0.02	7.4	6	0.40	82	0.128	4.79	3.87	0.97	<0.5	28.2	21	2.2	19.4	2.6	<0.5	<5	8	0.7	<0.5
835926	Drill Core	0.01	6.8	6	1.11	197	0.146	5.75	2.51	2.52	<0.5	29.6	21	2.0	13.8	3.2	<0.5	<5	8	2.6	<0.5
835927	Drill Core	0.02	5.8	8	0.38	78	0.123	3.42	2.64	0.85	<0.5	27.7	15	1.6	12.4	2.0	<0.5	<5	5	0.7	<0.5
835928	Drill Core	0.03	8.1	6	1.54	388	0.209	6.16	0.96	3.83	<0.5	22.7	24	2.4	13.4	2.8	<0.5	<5	11	9.1	<0.5
835929	Drill Core	0.02	6.1	8	1.57	303	0.165	5.47	0.84	3.32	<0.5	45.4	19	2.1	12.0	3.2	<0.5	<5	9	7.7	<0.5
835930	Drill Core	0.01	7.0	6	1.40	396	0.129	5.19	0.50	3.75	<0.5	60.5	21	1.9	20.7	3.2	<0.5	<5	8	14.2	<0.5
835931	Drill Core	0.01	6.2	7	1.32	400	0.123	5.76	0.95	3.61	<0.5	28.4	20	2.9	19.6	3.5	<0.5	<5	9	9.7	<0.5
835932	Drill Core	<0.01	6.9	6	1.71	354	0.114	6.31	1.19	3.32	<0.5	169.1	20	3.8	22.8	3.1	<0.5	<5	10	6.5	<0.5
835933	Drill Core	0.01	7.7	8	1.30	295	0.118	5.85	1.80	3.11	<0.5	34.9	22	3.4	19.9	2.9	<0.5	<5	9	5.1	<0.5
835934	Drill Core	0.27	24.9	80	2.48	425	0.504	5.92	2.65	1.38	<0.5	88.3	60	1.6	16.1	13.5	0.6	<5	13	27.1	<0.5
835935	Drill Core	0.02	5.7	8	0.76	242	0.145	4.66	2.60	1.86	<0.5	21.0	16	2.1	21.1	2.6	<0.5	<5	9	2.9	<0.5
835936	Drill Core	0.03	5.5	9	0.84	312	0.185	4.47	2.35	1.99	<0.5	21.1	15	1.7	26.3	2.2	<0.5	<5	10	14.7	<0.5
835937	Drill Core	0.08	8.4	10	1.20	281	0.302	4.96	2.59	1.77	<0.5	17.4	24	2.5	34.3	3.5	<0.5	<5	10	11.1	<0.5
835938	Drill Core	0.02	5.2	6	0.81	177	0.185	4.52	3.39	1.04	<0.5	19.5	15	2.6	17.9	1.6	<0.5	<5	11	6.7	<0.5
835939	Drill Core	0.02	4.8	9	0.62	104	0.150	4.77	3.98	0.76	<0.5	16.2	14	0.9	17.1	1.8	<0.5	<5	9	3.5	<0.5
835940	Rock Pulp	0.07	6.0	92	2.57	252	0.454	5.90	1.46	0.68	24.5	12.9	14	12.0	16.3	3.2	<0.5	<5	23	22.9	7.5
835941	Drill Core	<0.01	8.2	9	0.30	11	0.103	5.06	5.07	0.14	<0.5	27.2	26	2.0	12.1	2.6	<0.5	<5	8	4.0	<0.5
835942	Drill Core	0.02	3.9	14	0.57	84	0.156	5.20	4.16	0.56	<0.5	20.1	12	0.7	17.2	1.7	<0.5	<5	10	7.6	<0.5
835943	Drill Core	0.02	3.5	11	0.54	101	0.160	4.98	4.08	0.82	<0.5	19.0	10	0.9	17.3	1.6	<0.5	<5	10	3.7	<0.5
835944	Drill Core	0.02	3.9	12	0.54	121	0.160	5.18	4.01	0.75	<0.5	16.2	12	0.8	14.7	1.2	<0.5	<5	10	6.4	<0.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 16, 2009

**Page:** 2 of 6 **Part** 3

## CERTIFICATE OF ANALYSIS

SMI09000296.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
835915	Drill Core	10.3	0.9
835916	Drill Core	6.7	0.7
835917	Drill Core	7.7	0.7
835918	Drill Core	12.0	1.2
835919	Drill Core	31.7	1.6
835920	Rock Pulp	22.5	0.5
835921	Drill Core	27.4	1.9
835922	Drill Core	18.2	1.2
835923	Drill Core	6.5	0.9
835924	Drill Core	20.9	0.6
835925	Drill Core	9.4	1.0
835926	Drill Core	21.6	0.9
835927	Drill Core	9.3	0.9
835928	Drill Core	39.9	1.0
835929	Drill Core	34.1	0.9
835930	Drill Core	36.4	1.1
835931	Drill Core	36.2	1.1
835932	Drill Core	38.4	4.3
835933	Drill Core	30.0	1.3
835934	Drill Core	18.9	5.0
835935	Drill Core	18.0	0.7
835936	Drill Core	19.6	0.7
835937	Drill Core	14.0	1.7
835938	Drill Core	9.3	<0.5
835939	Drill Core	6.0	<0.5
835940	Rock Pulp	18.9	<0.5
835941	Drill Core	0.9	0.8
835942	Drill Core	4.0	0.5
835943	Drill Core	8.0	<0.5
835944	Drill Core	4.6	0.7



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 3 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
835945	Drill Core	6.41	<2	1.8	10.7	5.8	91	<0.5	2.7	2	779	2.11	<5	<0.5	<0.5	47	<0.5	<0.5	<0.5	11	0.35
835946	Drill Core	7.34	<2	3.7	15.2	8.0	106	<0.5	2.1	5	1155	2.89	<5	<0.5	<0.5	62	<0.5	<0.5	<0.5	41	1.50
835947	Drill Core	6.21	<2	<0.5	4.9	3.0	134	<0.5	<0.5	<1	1194	2.28	<5	<0.5	<0.5	58	<0.5	<0.5	<0.5	<10	0.81
835948	Drill Core	6.40	<2	<0.5	7.3	1.6	133	<0.5	<0.5	<1	1231	2.65	<5	<0.5	0.5	27	<0.5	<0.5	<0.5	<10	0.85
835949	Drill Core	7.22	<2	6.7	8.2	2.8	121	<0.5	<0.5	<1	1135	2.76	<5	<0.5	0.7	58	<0.5	0.5	<0.5	<10	0.63
865300	Drill Core	6.03	<2	<0.5	8.2	1.8	65	<0.5	<0.5	<1	452	1.43	<5	<0.5	0.7	41	<0.5	<0.5	<0.5	<10	0.48
865301	Drill Core	6.53	<2	0.9	8.7	2.3	96	<0.5	0.8	<1	611	1.71	<5	<0.5	0.7	37	<0.5	<0.5	<0.5	<10	0.57
865302	Drill Core	6.90	<2	<0.5	6.4	2.9	146	<0.5	1.1	<1	1336	2.82	<5	0.7	0.6	39	0.6	<0.5	<0.5	<10	1.14
865303	Drill Core	6.55	<2	<0.5	8.6	2.9	124	<0.5	<0.5	1	1228	2.75	<5	0.5	0.5	63	<0.5	<0.5	<0.5	<10	1.49
865304	Drill Core	7.16	<2	<0.5	24.2	3.7	120	<0.5	3.1	13	2374	5.60	<5	<0.5	<0.5	104	<0.5	<0.5	<0.5	121	2.85
865305	Drill Core	6.71	5	<0.5	17.8	4.4	124	<0.5	2.9	12	1939	5.40	<5	0.5	<0.5	116	<0.5	<0.5	<0.5	95	2.07
865306	Drill Core	7.44	3	<0.5	21.1	3.3	125	<0.5	2.8	11	1781	4.85	<5	<0.5	<0.5	71	<0.5	<0.5	<0.5	94	1.93
865307	Drill Core	6.71	<2	<0.5	12.0	2.6	107	<0.5	1.9	9	1967	4.50	<5	<0.5	<0.5	73	<0.5	<0.5	<0.5	70	3.11
865308	Drill Core	7.06	2	<0.5	18.5	2.6	134	<0.5	2.9	12	1992	5.66	<5	<0.5	<0.5	76	<0.5	0.9	<0.5	102	2.33
865309	Drill Core	4.00	<2	<0.5	19.4	3.1	121	<0.5	5.0	10	1733	5.19	<5	<0.5	<0.5	104	<0.5	<0.5	<0.5	90	2.15
865310	Drill Core	7.10	<2	0.6	33.0	8.2	108	<0.5	5.7	9	1178	4.14	<5	1.0	1.0	56	1.1	<0.5	<0.5	87	1.14
865311	Rock Pulp	6.69	75	17.2	6143	7111	32888	23.7	59.1	65	1133	12.34	64	1.6	1.0	173	206.6	40.1	30.7	190	4.12
865312	Drill Core	7.10	<2	<0.5	28.3	5.2	100	<0.5	6.7	7	791	3.43	<5	0.8	1.3	107	<0.5	<0.5	<0.5	64	1.30
865313	Drill Core	0.11	21	1.9	57.3	87.3	540	0.8	31.9	9	695	4.12	50	<0.5	1.1	164	2.3	4.0	<0.5	65	1.15
865314	Drill Core	3.45	15	2.0	145.9	1204	1292	2.6	0.7	2	133	2.46	67	<0.5	0.8	77	6.1	15.5	<0.5	<10	0.09
865315	Drill Core	8.31	18	2.8	155.9	486.0	6825	2.0	1.1	1	104	3.90	82	<0.5	0.5	79	34.8	11.3	<0.5	<10	0.15
865316	Drill Core	7.20	5	3.1	53.1	126.3	1789	<0.5	<0.5	<1	512	2.40	35	<0.5	0.6	57	8.8	2.5	<0.5	<10	0.18
865317	Drill Core	7.49	5	2.9	84.1	136.9	1257	<0.5	<0.5	<1	465	2.56	36	<0.5	0.6	60	6.1	1.9	<0.5	<10	0.74
865318	Drill Core	8.18	9	2.3	318.4	581.6	3357	1.1	1.2	<1	1232	3.17	116	<0.5	<0.5	102	17.6	6.9	<0.5	<10	3.60
865319	Drill Core	6.69	8	1.7	163.9	488.2	2523	0.7	<0.5	<1	855	2.36	62	<0.5	<0.5	73	14.5	3.4	<0.5	<10	2.65
865320	Drill Core	0.92	<2	<0.5	7.6	25.9	104	<0.5	5.1	6	870	2.72	<5	4.2	7.6	767	<0.5	<0.5	<0.5	57	2.72
865321	Drill Core	7.94	6	1.3	53.6	155.3	782	<0.5	<0.5	<1	835	3.17	26	0.6	<0.5	72	4.5	0.9	<0.5	<10	2.29
865322	Drill Core	8.67	10	4.1	217.2	206.4	2744	1.0	1.3	2	445	2.89	85	<0.5	0.8	65	14.8	4.4	<0.5	12	0.71
865323	Drill Core	8.03	4	1.2	65.2	68.6	1516	<0.5	<0.5	<1	186	1.61	21	<0.5	0.6	56	8.8	2.1	<0.5	<10	0.18
865324	Drill Core	8.84	3	0.8	46.8	66.6	1074	<0.5	1.0	2	144	1.46	16	<0.5	0.6	50	6.7	1.9	<0.5	<10	0.11

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 3 of 6 Part 2

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	Analyte	Unit	MDL	7TX P	7TX La	7TX Cr	7TX Mg	7TX Ba	7TX Ti	7TX Al	7TX Na	7TX K	7TX W	7TX Zr	7TX Ce	7TX Sn	7TX Y	7TX Nb	7TX Ta	7TX Be	7TX Sc	7TX Li	7TX S
				%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
				0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5
835945	Drill Core			0.02	3.6	10	0.54	116	0.160	5.01	3.91	0.79	<0.5	14.5	11	1.3	12.9	1.1	<0.5	<5	10	2.0	<0.5
835946	Drill Core			0.03	5.1	11	1.15	215	0.226	5.71	2.41	1.43	<0.5	19.8	15	1.4	11.3	1.6	<0.5	<5	13	15.8	<0.5
835947	Drill Core			0.01	4.4	8	0.83	109	0.136	5.44	2.61	1.39	1.4	19.7	15	1.1	12.1	2.4	<0.5	<5	12	22.8	<0.5
835948	Drill Core			0.02	6.5	6	1.19	130	0.124	5.80	1.55	1.86	<0.5	245.0	19	1.6	20.5	9.9	1.2	<5	11	11.0	<0.5
835949	Drill Core			0.01	8.0	3	1.15	147	0.159	6.62	1.48	2.47	<0.5	181.9	25	2.3	34.3	6.0	46.1	<5	14	11.4	<0.5
865300	Drill Core			0.01	9.9	5	0.30	24	0.108	5.66	3.86	0.34	<0.5	54.3	26	1.3	28.8	2.4	<0.5	<5	9	6.6	<0.5
865301	Drill Core			0.01	7.2	6	0.36	21	0.112	5.92	4.26	0.25	<0.5	17.7	21	1.3	27.2	2.9	<0.5	<5	7	6.7	<0.5
865302	Drill Core			0.02	9.4	5	1.29	181	0.143	6.56	1.31	2.35	<0.5	117.3	28	1.3	44.8	3.3	<0.5	<5	14	10.8	<0.5
865303	Drill Core			0.02	7.2	4	1.22	143	0.144	5.24	1.51	1.38	<0.5	91.2	22	1.8	27.1	2.9	<0.5	<5	11	10.1	<0.5
865304	Drill Core			0.05	5.0	9	2.06	190	0.467	8.23	3.03	1.45	<0.5	60.8	13	0.8	26.4	1.8	<0.5	<5	22	13.1	<0.5
865305	Drill Core			0.08	4.7	8	1.85	167	0.440	8.49	3.71	1.18	<0.5	45.3	14	1.3	30.8	2.0	<0.5	<5	21	14.8	<0.5
865306	Drill Core			0.06	4.9	7	1.62	189	0.429	7.76	3.48	1.25	<0.5	118.1	13	0.8	25.1	2.5	<0.5	<5	19	11.7	<0.5
865307	Drill Core			0.07	5.4	4	1.39	178	0.451	7.69	4.02	1.15	0.7	59.0	15	1.2	21.0	2.1	<0.5	<5	17	9.0	<0.5
865308	Drill Core			0.07	5.5	4	1.85	131	0.569	8.39	3.51	1.73	2.2	27.1	15	1.0	26.8	2.7	<0.5	<5	23	24.1	<0.5
865309	Drill Core			0.08	6.4	10	1.80	226	0.484	7.91	3.40	1.34	<0.5	17.2	18	1.2	28.2	2.4	<0.5	<5	21	16.1	<0.5
865310	Drill Core			0.04	7.0	11	1.47	295	0.353	7.00	2.63	1.67	<0.5	82.7	16	0.8	42.4	2.2	<0.5	<5	15	10.6	<0.5
865311	Rock Pulp			0.06	6.2	95	2.57	319	0.462	5.96	1.45	0.71	29.2	14.3	14	15.2	16.6	3.3	<0.5	<5	22	22.1	7.1
865312	Drill Core			0.04	8.7	14	1.27	423	0.294	6.90	1.59	2.74	<0.5	42.7	20	0.8	29.9	2.7	1.0	<5	15	9.6	<0.5
865313	Drill Core			0.13	15.4	43	1.90	420	0.347	7.05	1.32	1.33	0.7	145.9	41	1.8	32.7	7.4	<0.5	<5	16	17.4	3.1
865314	Drill Core			0.02	8.5	4	0.56	328	0.132	5.70	1.35	1.25	<0.5	40.2	24	1.7	31.1	2.3	<0.5	<5	10	5.2	2.4
865315	Drill Core			0.02	7.3	3	0.45	268	0.130	5.18	1.00	1.23	<0.5	90.9	22	1.9	29.1	1.7	<0.5	<5	9	7.9	4.1
865316	Drill Core			0.03	11.2	4	1.26	206	0.168	6.40	2.58	0.90	<0.5	14.6	32	2.2	31.9	3.7	<0.5	<5	8	7.8	2.3
865317	Drill Core			0.05	8.5	4	0.88	248	0.177	6.09	1.82	1.37	<0.5	85.0	26	1.9	39.2	2.9	<0.5	<5	11	5.2	2.5
865318	Drill Core			0.04	5.8	3	1.12	232	0.182	5.45	0.85	1.37	<0.5	126.4	17	1.1	26.9	2.2	<0.5	<5	13	7.7	3.2
865319	Drill Core			0.03	5.5	5	0.72	195	0.142	5.11	1.44	0.98	<0.5	64.9	16	1.0	20.3	1.7	<0.5	<5	12	6.5	2.4
865320	Drill Core			0.10	24.9	14	0.76	1003	0.250	8.37	2.70	2.92	<0.5	19.0	49	1.7	15.4	25.1	1.4	<5	6	40.0	<0.5
865321	Drill Core			0.04	5.2	5	1.06	284	0.165	5.31	0.54	1.56	<0.5	117.9	16	1.1	32.3	2.0	<0.5	<5	12	7.7	3.1
865322	Drill Core			0.03	8.2	6	0.94	251	0.167	6.17	1.52	1.39	<0.5	41.9	23	2.3	20.7	2.2	<0.5	<5	10	6.2	2.9
865323	Drill Core			0.03	9.6	5	0.64	293	0.176	6.39	1.97	1.46	<0.5	16.1	29	2.5	11.4	3.3	<0.5	<5	9	5.1	1.6
865324	Drill Core			0.04	10.1	3	0.54	253	0.215	6.53	2.29	1.40	0.5	16.8	29	2.8	133.4	3.1	<0.5	<5	10	4.0	1.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 16, 2009

Page: 3 of 6 Part 3

CERTIFICATE OF ANALYSIS

SMI09000296.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (e.g., 835945) and sample types (e.g., Drill Core) with corresponding analytical results.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 4 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865325	Drill Core	8.34	4	1.7	34.9	85.7	1227	<0.5	<0.5	2	325	1.84	17	<0.5	0.5	44	6.6	1.6	<0.5	<10	0.17
865326	Drill Core	7.54	3	1.3	61.7	209.7	2153	<0.5	0.7	<1	380	1.19	24	<0.5	0.5	39	11.7	2.6	<0.5	<10	0.12
865327	Drill Core	7.55	5	1.5	26.2	171.6	677	<0.5	<0.5	<1	224	1.75	14	<0.5	0.6	40	4.5	1.1	<0.5	<10	0.10
865328	Drill Core	7.99	19	3.1	171.2	816.6	2510	2.2	1.3	3	189	3.47	67	1.0	<0.5	34	17.3	2.9	<0.5	17	0.16
865329	Drill Core	7.21	33	2.1	72.7	464.4	1117	1.1	0.9	2	438	2.29	18	<0.5	0.6	32	7.5	0.7	<0.5	11	0.27
865330	Drill Core	7.85	12	2.6	100.3	603.9	1863	1.4	0.8	2	397	2.82	15	<0.5	0.6	36	11.9	0.7	<0.5	18	0.15
865331	Rock Pulp	6.66	54	17.3	6109	7066	33217	23.7	64.0	65	1103	12.23	64	1.7	0.9	174	208.0	46.1	30.1	184	4.22
865332	Drill Core	7.58	10	4.1	49.9	96.0	943	0.7	2.3	4	590	2.80	14	<0.5	<0.5	31	7.4	0.8	<0.5	31	0.19
865333	Drill Core	6.91	11	2.5	66.6	97.3	550	0.7	1.9	5	599	3.13	27	<0.5	0.5	35	3.1	0.8	<0.5	45	0.17
865334	Drill Core	7.22	8	1.1	37.8	78.1	721	0.5	2.0	3	686	2.79	17	<0.5	<0.5	32	4.1	0.6	<0.5	31	0.14
865335	Drill Core	7.45	10	2.2	84.4	139.1	1462	0.7	1.9	4	710	3.28	20	<0.5	<0.5	56	8.7	<0.5	<0.5	44	0.29
865336	Drill Core	6.88	8	2.3	142.3	178.2	2371	0.6	2.9	3	491	3.11	8	<0.5	<0.5	88	12.8	<0.5	<0.5	12	0.44
865337	Drill Core	6.67	7	1.4	89.1	218.8	4011	<0.5	1.1	1	419	2.70	8	0.7	<0.5	66	24.8	<0.5	<0.5	11	0.26
865338	Drill Core	6.59	8	2.4	230.2	191.2	2667	0.7	4.2	3	1454	4.20	13	<0.5	<0.5	69	15.4	<0.5	<0.5	19	0.75
865339	Drill Core	6.97	8	1.6	162.9	251.4	2497	0.6	2.1	2	961	3.51	19	<0.5	0.6	88	14.8	0.7	<0.5	18	0.45
865340	Drill Core	6.92	5	0.7	53.5	79.4	745	<0.5	1.3	4	502	3.69	30	<0.5	<0.5	54	3.4	0.6	<0.5	59	0.12
865341	Drill Core	6.41	5	0.8	61.2	73.0	1424	<0.5	0.8	2	805	3.66	16	<0.5	<0.5	36	8.2	<0.5	<0.5	25	0.09
865342	Drill Core	6.78	4	2.3	71.9	26.8	1685	<0.5	0.9	1	757	3.18	16	<0.5	<0.5	32	9.2	<0.5	<0.5	<10	0.11
865343	Drill Core	6.77	6	0.7	127.2	51.0	2101	<0.5	0.7	<1	617	3.32	13	<0.5	<0.5	42	12.8	<0.5	<0.5	<10	0.10
865344	Drill Core	7.06	5	1.1	49.6	13.5	2069	<0.5	1.1	<1	816	3.16	9	<0.5	<0.5	38	13.3	<0.5	<0.5	<10	0.06
865345	Drill Core	6.10	5	1.0	211.4	12.0	1306	<0.5	2.5	5	2259	4.80	12	<0.5	<0.5	31	6.1	<0.5	<0.5	36	0.17
865346	Drill Core	7.20	4	0.9	41.7	11.9	478	<0.5	2.9	2	1958	4.59	9	<0.5	<0.5	33	1.4	<0.5	<0.5	<10	0.19
865347	Drill Core	7.09	5	2.2	208.8	58.3	869	<0.5	2.9	3	1130	4.20	14	<0.5	<0.5	46	9.6	<0.5	0.6	17	0.10
865348	Drill Core	6.97	4	1.2	53.8	30.4	286	<0.5	1.9	2	719	3.99	9	<0.5	0.5	50	0.9	<0.5	<0.5	<10	0.05
865349	Drill Core	6.96	4	1.7	69.7	109.9	982	<0.5	1.4	2	508	3.68	28	<0.5	<0.5	58	6.7	0.8	0.6	11	0.11
865350	Drill Core	7.16	5	1.1	97.2	54.3	2309	<0.5	0.6	2	892	4.52	40	<0.5	<0.5	35	16.3	1.6	2.2	<10	0.11
865351	Rock Pulp	0.17	73	16.6	6072	7038	32569	23.5	62.7	64	1108	12.13	65	1.8	1.0	172	202.4	40.4	32.2	185	4.10
865352	Drill Core	7.04	<2	2.3	224.0	21.1	759	0.5	1.3	2	480	3.69	63	<0.5	<0.5	39	4.9	2.0	4.0	14	0.08
865353	Drill Core	6.91	13	2.2	589.3	23.1	457	0.9	1.3	2	408	4.35	162	<0.5	<0.5	42	2.6	6.1	5.8	18	0.08
865354	Drill Core	6.91	5	1.6	303.3	38.4	457	0.8	1.4	3	1062	4.96	110	<0.5	<0.5	46	3.3	8.0	2.9	<10	0.12

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 4 of 6 Part 2

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865325	Drill Core	0.04	9.3	5	0.91	224	0.200	6.54	2.43	1.20	0.6	79.3	30	1.7	9.7	3.3	<0.5	<5	10	9.5	1.9
865326	Drill Core	0.04	12.3	3	1.00	237	0.193	6.86	2.68	1.32	<0.5	19.0	36	2.8	16.9	3.5	<0.5	<5	10	6.7	1.1
865327	Drill Core	0.04	11.1	5	0.79	281	0.180	6.60	1.96	1.71	0.6	15.6	32	2.0	7.7	3.8	<0.5	<5	10	3.3	1.7
865328	Drill Core	0.03	9.4	6	0.53	253	0.162	6.03	1.72	1.69	<0.5	79.8	27	2.2	13.7	2.1	<0.5	<5	11	3.3	3.5
865329	Drill Core	0.03	8.5	6	0.63	301	0.129	5.77	2.28	1.37	<0.5	20.4	25	1.2	10.5	1.7	<0.5	<5	9	3.9	2.2
865330	Drill Core	0.04	9.9	6	0.94	278	0.170	6.54	2.10	1.65	0.7	27.7	28	2.3	16.9	2.6	<0.5	<5	11	5.3	2.7
865331	Rock Pulp	0.06	6.5	95	2.56	379	0.465	5.94	1.44	0.70	29.4	15.7	14	15.7	16.8	3.4	<0.5	<5	23	20.7	7.1
865332	Drill Core	0.04	6.5	6	1.12	232	0.194	5.94	1.93	1.42	0.9	46.9	19	2.1	11.7	2.5	<0.5	<5	12	8.2	2.6
865333	Drill Core	0.05	7.9	5	1.30	243	0.243	6.16	1.50	1.52	0.9	52.7	22	1.7	9.6	2.9	0.7	<5	13	8.2	2.7
865334	Drill Core	0.04	7.2	4	1.58	252	0.176	6.24	1.30	1.63	0.7	62.4	19	1.9	9.6	2.3	<0.5	<5	12	10.3	2.4
865335	Drill Core	0.04	7.4	3	1.20	193	0.169	5.72	1.05	1.46	<0.5	39.3	21	1.9	12.2	1.8	<0.5	<5	12	5.4	3.1
865336	Drill Core	0.03	9.6	6	0.56	177	0.159	6.01	1.69	1.32	<0.5	32.2	26	1.8	14.1	1.7	<0.5	<5	10	4.4	3.1
865337	Drill Core	0.03	9.4	4	0.68	183	0.182	6.24	1.39	1.88	<0.5	78.4	24	2.1	17.2	2.6	<0.5	<5	11	7.6	2.7
865338	Drill Core	0.03	6.0	2	1.38	151	0.135	5.67	1.14	1.14	<0.5	84.0	16	1.2	11.1	1.1	<0.5	<5	11	7.7	4.0
865339	Drill Core	0.03	18.8	4	1.21	216	0.178	6.25	0.72	1.72	<0.5	92.4	52	2.2	16.0	2.1	<0.5	<5	12	7.0	3.3
865340	Drill Core	0.04	7.9	3	1.08	196	0.195	5.59	0.74	1.33	<0.5	107.5	21	1.8	17.4	1.5	<0.5	<5	13	6.8	3.5
865341	Drill Core	0.03	7.0	<1	1.55	141	0.148	5.65	1.43	0.98	<0.5	133.0	21	1.8	19.8	1.3	<0.5	<5	11	7.6	3.3
865342	Drill Core	0.03	6.4	6	1.24	76	0.105	5.15	2.09	0.59	<0.5	22.6	19	1.7	16.7	1.3	<0.5	<5	9	6.8	3.0
865343	Drill Core	0.02	7.0	7	1.02	101	0.099	5.24	1.81	0.74	<0.5	95.5	20	1.3	22.2	1.4	<0.5	<5	10	5.7	3.2
865344	Drill Core	0.01	6.5	3	1.40	94	0.085	5.15	1.55	0.79	<0.5	96.9	18	1.3	19.2	1.2	<0.5	<5	9	7.0	3.0
865345	Drill Core	0.05	7.4	3	2.26	157	0.217	6.09	1.15	1.16	<0.5	73.2	21	1.5	18.5	1.1	<0.5	<5	14	11.7	3.9
865346	Drill Core	0.05	7.5	2	2.16	176	0.184	6.72	1.26	1.46	<0.5	93.5	22	1.0	17.2	2.3	<0.5	<5	14	9.2	3.8
865347	Drill Core	0.03	8.9	4	1.39	185	0.167	6.46	1.00	1.63	<0.5	87.5	26	2.2	14.3	2.0	<0.5	<5	13	7.1	3.8
865348	Drill Core	0.02	8.1	7	1.27	166	0.133	6.06	1.14	1.30	<0.5	43.7	23	1.9	10.3	1.7	<0.5	<5	12	6.7	3.7
865349	Drill Core	0.03	8.5	5	1.13	167	0.167	6.58	1.25	1.49	<0.5	71.8	23	2.2	12.4	2.5	<0.5	<5	14	3.8	3.5
865350	Drill Core	0.05	7.1	5	2.34	161	0.141	6.22	0.83	1.39	<0.5	126.6	20	1.1	17.4	1.0	<0.5	<5	13	10.7	4.2
865351	Rock Pulp	0.06	6.6	91	2.55	307	0.448	5.93	1.44	0.69	28.7	15.8	14	13.0	16.4	3.1	<0.5	<5	22	17.9	7.0
865352	Drill Core	0.03	7.1	6	1.42	155	0.116	5.65	1.09	1.26	<0.5	31.1	19	1.6	14.0	1.4	<0.5	<5	9	6.2	3.5
865353	Drill Core	0.03	7.2	4	1.07	126	0.123	5.56	1.29	1.07	<0.5	26.6	21	2.5	21.5	1.6	<0.5	<5	9	4.2	4.2
865354	Drill Core	0.05	7.0	3	2.32	126	0.161	6.18	0.84	1.15	<0.5	125.1	19	1.5	16.3	1.5	<0.5	<5	13	13.6	4.7

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 16, 2009

Page: 4 of 6 Part 3

CERTIFICATE OF ANALYSIS

SMI09000296.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (e.g., 865325) and sample types (e.g., Drill Core, Rock Pulp) with corresponding concentration values.





Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 5 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865355	Drill Core	6.71	3	1.1	27.1	31.0	293	<0.5	0.6	2	1322	4.58	13	<0.5	<0.5	47	1.1	0.7	<0.5	<10	0.10
865356	Drill Core	7.29	3	0.7	58.6	12.2	549	<0.5	1.7	3	1066	4.87	15	0.7	<0.5	56	4.8	<0.5	<0.5	<10	0.12
865357	Drill Core	7.25	4	1.2	247.1	193.7	514	<0.5	0.8	2	1281	5.96	13	<0.5	<0.5	49	3.2	0.6	2.4	11	0.17
865358	Drill Core	6.79	2	1.1	154.0	9.6	807	<0.5	2.5	4	1256	4.91	10	<0.5	<0.5	49	6.7	<0.5	1.2	18	0.14
865359	Drill Core	6.89	3	1.2	99.4	6.0	568	<0.5	1.5	4	1375	4.60	8	<0.5	<0.5	47	4.1	<0.5	1.2	18	0.14
865360	Drill Core	6.96	<2	0.7	37.3	7.6	270	<0.5	0.6	4	1316	4.35	7	0.6	<0.5	62	<0.5	<0.5	<0.5	20	0.13
865361	Drill Core	7.14	2	1.2	43.5	12.5	518	<0.5	0.5	3	1194	4.07	9	<0.5	<0.5	46	3.5	<0.5	<0.5	<10	0.15
865362	Drill Core	7.11	3	1.0	73.7	12.6	1022	<0.5	1.1	2	1572	4.11	9	<0.5	<0.5	60	9.0	<0.5	<0.5	<10	0.17
865363	Drill Core	6.93	2	1.3	51.1	7.5	702	<0.5	0.9	3	1594	4.33	9	<0.5	<0.5	33	3.9	<0.5	<0.5	10	0.16
865364	Drill Core	7.05	2	1.2	62.7	13.3	1309	<0.5	1.4	3	1623	3.68	10	<0.5	<0.5	82	11.2	<0.5	<0.5	13	0.18
865365	Drill Core	6.97	4	0.9	20.4	11.4	908	<0.5	<0.5	2	1327	3.75	13	<0.5	<0.5	48	4.8	<0.5	<0.5	<10	0.13
865366	Drill Core	6.65	3	0.8	18.8	11.7	530	<0.5	<0.5	2	1493	4.44	9	<0.5	<0.5	44	1.9	<0.5	<0.5	<10	0.13
865367	Drill Core	7.62	<2	2.3	28.8	54.9	704	<0.5	0.9	2	1527	4.51	9	<0.5	<0.5	49	3.1	<0.5	<0.5	<10	0.21
865368	Drill Core	7.21	<2	<0.5	23.0	6.1	813	<0.5	1.9	2	1961	4.27	8	<0.5	<0.5	36	2.1	<0.5	<0.5	<10	0.13
865369	Drill Core	7.52	<2	1.1	27.6	10.7	845	<0.5	1.3	3	1499	4.17	<5	<0.5	<0.5	40	5.3	<0.5	<0.5	<10	0.12
865370	Drill Core	7.11	<2	1.7	22.6	10.7	690	<0.5	0.7	3	1311	3.62	<5	<0.5	<0.5	37	3.4	<0.5	<0.5	<10	0.13
865371	Rock Pulp	7.41	1728	29.8	9749	5503	20726	88.1	1371	143	1350	35.82	2543	1.8	0.7	22	119.5	285.7	45.6	19	0.89
865372	Drill Core	6.66	2	0.9	23.2	6.0	897	<0.5	1.1	2	2175	4.44	<5	<0.5	<0.5	38	4.8	<0.5	<0.5	<10	0.16
865373	Drill Core	6.88	3	0.8	28.1	9.4	844	<0.5	<0.5	2	1677	4.06	<5	<0.5	<0.5	30	2.8	<0.5	<0.5	<10	0.13
865374	Drill Core	6.35	5	1.5	59.1	48.6	1951	<0.5	5.5	4	1277	3.27	9	0.6	0.9	74	11.9	0.7	<0.5	25	0.54
865375	Drill Core	7.00	<2	0.8	6.6	8.0	224	<0.5	1.0	1	681	1.50	<5	1.5	3.8	155	<0.5	1.0	<0.5	<10	1.02
865376	Drill Core	6.73	2	1.1	51.3	16.7	3024	<0.5	<0.5	4	1352	4.93	7	<0.5	<0.5	49	17.3	0.7	<0.5	17	0.30
865377	Drill Core	6.90	<2	0.7	72.8	7.6	2176	<0.5	<0.5	4	1629	4.76	9	<0.5	<0.5	38	10.8	<0.5	<0.5	16	0.29
865378	Drill Core	6.73	<2	<0.5	90.5	7.8	2456	<0.5	0.6	4	1433	4.43	<5	<0.5	<0.5	54	14.1	<0.5	<0.5	15	0.28
865379	Drill Core	6.80	5	0.6	73.0	13.1	1240	<0.5	1.0	5	796	4.58	7	<0.5	<0.5	60	6.4	<0.5	<0.5	14	0.30
865380	Drill Core	6.70	3	0.7	41.0	10.0	353	<0.5	0.5	4	999	4.68	13	<0.5	<0.5	33	<0.5	<0.5	<0.5	14	0.29
865381	Drill Core	6.83	4	<0.5	48.1	6.1	353	<0.5	<0.5	2	711	3.23	8	<0.5	<0.5	44	1.2	<0.5	<0.5	<10	0.18
865382	Drill Core	6.61	<2	<0.5	21.2	3.0	47	<0.5	<0.5	<1	245	1.38	6	<0.5	<0.5	28	<0.5	<0.5	<0.5	<10	0.14
865383	Drill Core	6.64	<2	<0.5	33.5	3.4	44	<0.5	<0.5	<1	411	1.69	<5	<0.5	<0.5	30	<0.5	<0.5	<0.5	<10	0.24
865384	Drill Core	6.21	<2	<0.5	416.0	2.0	63	<0.5	1.4	<1	193	1.80	39	<0.5	<0.5	26	<0.5	5.2	<0.5	<10	0.09

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 5 of 6 Part 2

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865355	Drill Core	0.05	5.3	4	2.33	129	0.138	5.84	0.67	1.03	<0.5	85.0	15	1.6	17.7	0.9	<0.5	<5	12	14.6	4.2
865356	Drill Core	0.05	5.7	2	1.96	150	0.169	6.39	0.77	1.34	<0.5	118.5	17	2.1	19.2	1.1	<0.5	<5	15	10.6	4.6
865357	Drill Core	0.05	6.2	5	1.72	154	0.142	5.61	0.94	1.01	<0.5	110.5	17	1.2	15.7	0.8	<0.5	<5	12	11.6	5.6
865358	Drill Core	0.05	5.5	6	2.09	180	0.204	6.64	0.81	1.39	<0.5	132.3	16	2.5	12.7	1.2	<0.5	<5	15	8.8	4.5
865359	Drill Core	0.05	6.5	4	2.17	149	0.192	6.14	0.93	1.09	<0.5	91.0	19	1.3	16.0	1.5	<0.5	<5	13	10.7	4.0
865360	Drill Core	0.05	5.7	2	1.99	187	0.219	6.43	0.84	1.45	<0.5	117.1	17	1.8	21.6	1.4	<0.5	<5	15	9.1	3.8
865361	Drill Core	0.05	4.5	6	1.58	200	0.195	6.00	0.92	1.48	<0.5	45.1	13	1.8	13.4	1.2	<0.5	<5	13	7.1	3.6
865362	Drill Core	0.05	5.0	2	1.97	147	0.171	5.91	1.38	1.01	<0.5	40.5	15	1.5	12.8	1.3	<0.5	<5	11	10.6	3.5
865363	Drill Core	0.06	5.7	3	2.00	143	0.182	5.85	1.41	0.99	<0.5	46.4	17	2.0	13.2	1.3	<0.5	<5	12	9.6	3.7
865364	Drill Core	0.06	6.3	4	2.03	109	0.207	5.98	2.10	0.69	<0.5	76.8	18	1.8	14.9	1.3	<0.5	<5	13	7.4	3.0
865365	Drill Core	0.05	4.8	3	1.63	138	0.205	6.11	1.73	1.14	<0.5	76.8	14	2.1	11.8	1.2	<0.5	<5	14	5.9	2.9
865366	Drill Core	0.05	4.6	2	2.00	153	0.186	6.30	1.22	1.34	<0.5	68.6	14	1.4	16.6	1.0	<0.5	<5	14	6.5	3.6
865367	Drill Core	0.05	5.1	2	2.04	195	0.190	5.97	1.00	1.33	<0.5	56.7	15	1.7	13.9	1.0	<0.5	<5	13	11.5	3.7
865368	Drill Core	0.05	3.0	<1	2.46	135	0.139	4.17	0.84	1.30	<0.5	7.8	11	1.4	8.2	0.8	<0.5	<5	10	13.2	3.1
865369	Drill Core	0.05	2.5	4	1.85	136	0.128	3.64	1.22	1.32	<0.5	7.0	9	1.9	11.2	0.8	<0.5	<5	9	8.9	3.9
865370	Drill Core	0.04	3.4	1	1.56	135	0.156	3.49	1.46	1.39	<0.5	6.1	11	1.0	12.2	1.1	<0.5	<5	9	9.9	3.4
865371	Rock Pulp	0.02	4.5	991	0.81	61	0.011	0.78	<0.01	0.10	6.4	12.1	8	20.6	3.4	3.1	<0.5	<5	2	6.4	30.9
865372	Drill Core	0.05	3.0	9	2.47	104	0.138	4.37	1.39	1.09	<0.5	7.8	11	1.3	15.8	0.6	<0.5	<5	10	10.9	3.6
865373	Drill Core	0.05	3.3	5	2.18	117	0.137	4.06	1.34	1.16	<0.5	11.0	12	1.5	14.4	1.1	<0.5	<5	10	9.7	3.7
865374	Drill Core	0.05	6.0	11	1.71	178	0.163	3.99	1.31	1.35	<0.5	25.4	20	1.4	9.1	3.1	<0.5	<5	9	11.9	2.8
865375	Drill Core	0.06	11.9	3	0.80	693	0.157	6.14	2.59	1.54	1.0	55.9	25	0.8	8.7	9.9	0.6	<5	5	5.5	0.8
865376	Drill Core	0.13	2.9	2	2.16	177	0.252	4.47	1.80	1.29	<0.5	33.4	10	1.7	10.3	0.9	<0.5	<5	11	9.0	4.5
865377	Drill Core	0.12	3.9	5	2.34	53	0.212	4.90	2.68	0.43	<0.5	6.4	14	1.0	12.3	0.6	<0.5	<5	13	14.3	3.5
865378	Drill Core	0.13	4.2	3	2.14	108	0.270	5.14	2.23	0.96	<0.5	12.8	14	1.0	16.1	0.6	<0.5	<5	12	10.8	3.6
865379	Drill Core	0.13	3.7	6	1.29	164	0.272	4.72	1.99	1.40	<0.5	5.1	11	1.4	14.4	1.5	<0.5	<5	12	8.9	4.3
865380	Drill Core	0.14	2.1	7	1.14	41	0.251	3.73	3.69	0.47	<0.5	22.3	7	1.6	10.9	0.8	<0.5	<5	10	10.1	4.1
865381	Drill Core	0.08	4.4	2	0.92	137	0.200	3.57	3.14	0.86	<0.5	10.0	14	1.9	9.8	1.4	<0.5	<5	11	8.2	3.0
865382	Drill Core	0.03	4.6	5	0.36	46	0.146	3.39	4.45	0.49	<0.5	14.2	14	2.3	5.3	2.9	<0.5	<5	5	2.6	1.4
865383	Drill Core	0.03	5.7	5	0.38	56	0.135	3.53	4.02	0.61	<0.5	16.8	19	1.5	8.5	2.4	<0.5	<5	5	4.9	1.6
865384	Drill Core	0.03	5.0	7	0.26	44	0.132	2.68	4.22	0.53	<0.5	14.9	15	2.6	7.0	2.6	<0.5	<5	5	5.2	1.8

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 16, 2009

**Page:** 5 of 6 **Part** 3

## CERTIFICATE OF ANALYSIS

SMI09000296.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
865355	Drill Core	10.5	3.7
865356	Drill Core	14.6	3.4
865357	Drill Core	11.4	2.5
865358	Drill Core	13.8	2.9
865359	Drill Core	11.6	2.2
865360	Drill Core	13.3	3.7
865361	Drill Core	15.1	2.5
865362	Drill Core	11.6	2.6
865363	Drill Core	10.2	2.6
865364	Drill Core	6.7	3.0
865365	Drill Core	12.4	4.4
865366	Drill Core	13.9	1.5
865367	Drill Core	14.6	4.6
865368	Drill Core	10.2	<0.5
865369	Drill Core	13.9	<0.5
865370	Drill Core	16.1	<0.5
865371	Rock Pulp	5.3	0.8
865372	Drill Core	10.8	<0.5
865373	Drill Core	12.2	<0.5
865374	Drill Core	20.1	0.9
865375	Drill Core	39.5	2.0
865376	Drill Core	14.5	<0.5
865377	Drill Core	4.4	<0.5
865378	Drill Core	10.2	<0.5
865379	Drill Core	14.6	<0.5
865380	Drill Core	1.8	0.7
865381	Drill Core	6.1	<0.5
865382	Drill Core	2.9	0.6
865383	Drill Core	2.9	0.6
865384	Drill Core	2.6	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 6 of 6 Part 1

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865385	Drill Core	6.13	<2	<0.5	29.1	2.5	68	<0.5	<0.5	<1	268	1.56	5	<0.5	<0.5	25	<0.5	<0.5	<0.5	<10	0.14
865386	Drill Core	6.19	2	<0.5	79.7	3.0	46	<0.5	<0.5	<1	174	1.61	15	<0.5	<0.5	26	<0.5	<0.5	<0.5	<10	0.11
865387	Drill Core	5.96	<2	<0.5	39.4	1.9	59	<0.5	0.6	<1	200	1.78	6	<0.5	<0.5	25	<0.5	<0.5	<0.5	<10	0.12
865388	Drill Core	6.77	<2	0.7	42.1	6.8	420	<0.5	1.3	4	1418	4.39	7	<0.5	<0.5	46	<0.5	<0.5	<0.5	13	0.27
865389	Drill Core	6.47	4	0.6	58.1	6.9	152	<0.5	<0.5	4	1423	4.83	7	<0.5	<0.5	46	<0.5	<0.5	<0.5	14	0.29
865390	Drill Core	6.64	<2	1.4	36.3	3.4	78	<0.5	<0.5	1	669	2.39	6	<0.5	<0.5	45	<0.5	<0.5	<0.5	<10	0.28
865391	Rock Pulp	0.17	59	17.6	6016	7204	33381	24.4	61.0	67	1082	11.32	51	1.7	1.0	176	176.5	29.5	29.1	170	3.99
865392	Drill Core	5.81	4	1.3	55.7	7.4	113	<0.5	1.8	1	372	2.97	10	<0.5	<0.5	100	<0.5	<0.5	1.1	<10	0.20
865393	Drill Core	6.28	<2	<0.5	50.0	3.8	38	<0.5	<0.5	<1	139	1.83	13	<0.5	<0.5	30	<0.5	<0.5	<0.5	<10	0.16
865394	Drill Core	6.39	3	0.7	22.9	6.2	376	<0.5	<0.5	<1	188	1.86	5	<0.5	<0.5	40	4.3	<0.5	<0.5	<10	0.16
865395	Drill Core	6.81	3	<0.5	42.1	6.0	194	<0.5	<0.5	<1	439	2.69	11	<0.5	<0.5	35	2.1	<0.5	<0.5	<10	0.16
865396	Drill Core	6.29	16	<0.5	43.9	6.3	150	<0.5	<0.5	1	551	2.69	18	<0.5	<0.5	35	<0.5	<0.5	<0.5	<10	0.13
865397	Drill Core	6.04	2	0.6	14.0	7.5	313	<0.5	<0.5	2	1077	3.16	18	<0.5	<0.5	45	2.6	<0.5	<0.5	<10	0.17



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 6 of 6 Part 2

CERTIFICATE OF ANALYSIS

SMI09000296.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865385	Drill Core	0.03	5.3	8	0.39	46	0.136	3.08	4.51	0.46	<0.5	16.3	15	2.4	7.2	2.6	<0.5	<5	6	4.3	1.6
865386	Drill Core	0.03	5.4	8	0.27	46	0.138	3.44	4.64	0.52	<0.5	17.6	16	2.1	7.1	3.1	<0.5	<5	6	3.0	1.6
865387	Drill Core	0.03	4.8	7	0.30	43	0.133	3.41	4.51	0.49	<0.5	15.3	16	1.4	8.7	3.0	<0.5	<5	5	2.5	1.8
865388	Drill Core	0.12	4.3	9	1.65	57	0.265	4.71	2.79	0.59	<0.5	7.3	14	2.6	14.3	1.3	<0.5	<5	13	15.6	3.3
865389	Drill Core	0.12	4.7	5	1.82	61	0.237	4.28	2.41	0.57	<0.5	6.2	15	1.9	14.6	1.2	<0.5	<5	12	15.0	3.6
865390	Drill Core	0.05	2.5	8	0.74	39	0.144	3.00	3.14	0.38	<0.5	10.2	8	1.8	12.9	1.2	<0.5	<5	8	4.9	2.2
865391	Rock Pulp	0.06	6.3	95	2.53	1024	0.450	5.86	1.48	0.70	26.6	16.9	14	13.6	15.4	3.0	<0.5	<5	22	19.2	7.1
865392	Drill Core	0.05	6.5	34	0.72	161	0.144	4.58	2.43	1.13	<0.5	13.4	21	3.5	12.3	1.6	<0.5	<5	9	6.4	2.8
865393	Drill Core	0.03	5.4	4	0.20	53	0.124	3.25	4.21	0.63	<0.5	16.7	16	2.4	6.9	2.2	<0.5	<5	5	2.2	1.8
865394	Drill Core	0.02	7.6	5	0.31	145	0.106	4.18	2.97	1.11	<0.5	13.9	22	1.2	8.3	2.1	<0.5	<5	5	3.4	1.8
865395	Drill Core	0.01	5.7	2	0.60	167	0.060	4.23	1.53	1.34	<0.5	10.9	15	2.0	8.2	1.2	<0.5	<5	7	7.1	2.3
865396	Drill Core	0.02	5.3	3	0.54	193	0.094	4.87	1.71	1.41	<0.5	10.5	16	1.6	8.2	1.1	<0.5	<5	8	9.1	2.0
865397	Drill Core	0.06	4.3	2	0.71	166	0.151	5.20	2.43	1.29	<0.5	11.6	14	1.0	8.1	1.3	<0.5	<5	11	6.3	1.8



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 16, 2009

**Page:** 6 of 6 **Part** 3

## CERTIFICATE OF ANALYSIS

SMI09000296.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
865385	Drill Core	2.4	<0.5
865386	Drill Core	2.6	0.6
865387	Drill Core	3.0	<0.5
865388	Drill Core	5.6	<0.5
865389	Drill Core	6.8	<0.5
865390	Drill Core	2.9	<0.5
865391	Rock Pulp	19.8	<0.5
865392	Drill Core	12.3	<0.5
865393	Drill Core	4.5	0.5
865394	Drill Core	11.9	<0.5
865395	Drill Core	18.1	<0.5
865396	Drill Core	16.3	<0.5
865397	Drill Core	16.1	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Project: Bodine  
Report Date: October 16, 2009

Page: 1 of 3 Part 1

QUALITY CONTROL REPORT

SMI09000296.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
Pulp Duplicates																					
835921	Drill Core	0.91	<2	0.9	4.3	14.3	72	<0.5	<0.5	1	551	1.74	<5	<0.5	0.6	15	<0.5	<0.5	<0.5	<10	0.30
REP 835921	QC		<2																		
REP 835929	QC		<2																		
835939	Drill Core	6.70	<2	1.7	6.1	7.9	93	<0.5	<0.5	2	760	2.11	<5	<0.5	<0.5	33	<0.5	<0.5	<0.5	<10	0.30
REP 835939	QC			2.0	6.5	8.5	92	<0.5	<0.5	1	754	2.11	<5	<0.5	<0.5	34	<0.5	<0.5	<0.5	<10	0.31
865329	Drill Core	7.21	33	2.1	72.7	464.4	1117	1.1	0.9	2	438	2.29	18	<0.5	0.6	32	7.5	0.7	<0.5	11	0.27
REP 865329	QC			2.4	76.4	456.2	1058	1.1	<0.5	1	462	2.25	20	<0.5	0.5	31	7.9	0.6	<0.5	<10	0.27
865341	Drill Core	6.41	5	0.8	61.2	73.0	1424	<0.5	0.8	2	805	3.66	16	<0.5	<0.5	36	8.2	<0.5	<0.5	25	0.09
REP 865341	QC		6	1.3	60.0	75.0	1448	<0.5	<0.5	2	809	3.75	16	<0.5	<0.5	37	9.5	<0.5	<0.5	29	0.09
865380	Drill Core	6.70	3	0.7	41.0	10.0	353	<0.5	0.5	4	999	4.68	13	<0.5	<0.5	33	<0.5	<0.5	<0.5	14	0.29
REP 865380	QC		3																		
REP 865384	QC			<0.5	415.4	2.7	67	<0.5	1.1	<1	195	1.88	39	<0.5	<0.5	32	0.5	5.0	<0.5	<10	0.12
Core Reject Duplicates																					
835929	Drill Core	0.63	<2	4.6	9.2	4.9	104	<0.5	1.6	1	992	2.32	<5	<0.5	0.6	19	<0.5	<0.5	<0.5	18	0.19
DUP 835929	QC		<2	3.7	9.3	4.7	108	<0.5	0.7	2	912	2.30	<5	<0.5	0.7	18	<0.5	<0.5	<0.5	17	0.21
865314	Drill Core	3.45	15	2.0	145.9	1204	1292	2.6	0.7	2	133	2.46	67	<0.5	0.8	77	6.1	15.5	<0.5	<10	0.09
DUP 865314	QC	3.26	16	2.5	126.3	1169	1129	2.1	0.8	1	138	2.37	62	<0.5	0.7	73	6.0	14.8	<0.5	<10	0.11
865349	Drill Core	6.96	4	1.7	69.7	109.9	982	<0.5	1.4	2	508	3.68	28	<0.5	<0.5	58	6.7	0.8	0.6	11	0.11
DUP 865349	QC		6	1.7	73.7	108.1	996	<0.5	1.5	2	467	3.64	26	<0.5	0.5	56	7.0	1.0	0.6	13	0.10
865384	Drill Core	6.21	<2	<0.5	416.0	2.0	63	<0.5	1.4	<1	193	1.80	39	<0.5	<0.5	26	<0.5	5.2	<0.5	<10	0.09
DUP 865384	QC		<2	<0.5	497.6	2.9	62	<0.5	0.8	<1	184	1.86	34	<0.5	<0.5	30	<0.5	4.7	<0.5	<10	0.13
Reference Materials																					
STD OXE56	Standard		634																		
STD OXE56	Standard		628																		
STD OXE56	Standard		645																		
STD OXE56	Standard		634																		
STD OXE56	Standard		633																		
STD OXH55	Standard		1348																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 16, 2009

Page: 1 of 3 Part 2

QUALITY CONTROL REPORT

SMI09000296.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	5	1	0.5	0.5		
Pulp Duplicates																					
835921	Drill Core	0.01	4.3	3	1.36	272	0.143	5.10	1.20	3.16	<0.5	75.3	14	1.6	10.4	3.2	<0.5	<5	8	9.4	<0.5
REP 835921	QC																				
REP 835929	QC																				
835939	Drill Core	0.02	4.8	9	0.62	104	0.150	4.77	3.98	0.76	<0.5	16.2	14	0.9	17.1	1.8	<0.5	<5	9	3.5	<0.5
REP 835939	QC	0.02	4.5	9	0.60	99	0.145	4.63	3.88	0.76	<0.5	23.8	13	1.3	17.4	1.9	<0.5	<5	9	4.8	<0.5
865329	Drill Core	0.03	8.5	6	0.63	301	0.129	5.77	2.28	1.37	<0.5	20.4	25	1.2	10.5	1.7	<0.5	<5	9	3.9	2.2
REP 865329	QC	0.03	8.6	6	0.63	313	0.130	5.81	2.32	1.38	<0.5	20.1	25	1.6	9.4	2.4	<0.5	<5	8	2.9	2.2
865341	Drill Core	0.03	7.0	<1	1.55	141	0.148	5.65	1.43	0.98	<0.5	133.0	21	1.8	19.8	1.3	<0.5	<5	11	7.6	3.3
REP 865341	QC	0.03	7.1	3	1.54	142	0.154	5.67	1.43	1.00	<0.5	170.4	20	1.4	19.0	1.7	<0.5	<5	11	9.6	3.4
865380	Drill Core	0.14	2.1	7	1.14	41	0.251	3.73	3.69	0.47	<0.5	22.3	7	1.6	10.9	0.8	<0.5	<5	10	10.1	4.1
REP 865380	QC																				
REP 865384	QC	0.03	4.6	7	0.28	48	0.127	3.42	4.27	0.55	<0.5	16.4	15	1.8	7.0	2.5	<0.5	<5	7	5.5	1.9
Core Reject Duplicates																					
835929	Drill Core	0.02	6.1	8	1.57	303	0.165	5.47	0.84	3.32	<0.5	45.4	19	2.1	12.0	3.2	<0.5	<5	9	7.7	<0.5
DUP 835929	QC	0.02	6.6	5	1.53	320	0.160	5.38	0.79	3.24	<0.5	26.8	20	1.9	13.1	2.4	<0.5	<5	9	14.1	<0.5
865314	Drill Core	0.02	8.5	4	0.56	328	0.132	5.70	1.35	1.25	<0.5	40.2	24	1.7	31.1	2.3	<0.5	<5	10	5.2	2.4
DUP 865314	QC	0.02	8.7	3	0.52	315	0.124	5.44	1.32	1.19	<0.5	40.2	24	2.0	25.0	2.5	<0.5	<5	9	9.1	2.3
865349	Drill Core	0.03	8.5	5	1.13	167	0.167	6.58	1.25	1.49	<0.5	71.8	23	2.2	12.4	2.5	<0.5	<5	14	3.8	3.5
DUP 865349	QC	0.03	8.6	8	1.17	169	0.164	6.62	1.25	1.50	<0.5	38.5	23	1.7	12.7	1.9	<0.5	<5	14	5.1	3.5
865384	Drill Core	0.03	5.0	7	0.26	44	0.132	2.68	4.22	0.53	<0.5	14.9	15	2.6	7.0	2.6	<0.5	<5	5	5.2	1.8
DUP 865384	QC	0.03	5.2	13	0.29	49	0.131	3.03	4.30	0.56	<0.5	15.5	15	1.7	7.5	2.4	<0.5	<5	6	3.7	2.0
Reference Materials																					
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXH55	Standard																				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.





Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 16, 2009

**Page:** 1 of 3 **Part** 3

## QUALITY CONTROL REPORT

SMI09000296.1

	Method	7TX	7TX
Analyte		Rb	Hf
Unit		ppm	ppm
MDL		0.5	0.5
Pulp Duplicates			
835921	Drill Core	27.4	1.9
REP 835921	QC		
REP 835929	QC		
835939	Drill Core	6.0	<0.5
REP 835939	QC	5.6	0.5
865329	Drill Core	13.8	0.9
REP 865329	QC	13.1	0.6
865341	Drill Core	10.2	2.9
REP 865341	QC	9.5	2.7
865380	Drill Core	1.8	0.7
REP 865380	QC		
REP 865384	QC	4.1	<0.5
Core Reject Duplicates			
835929	Drill Core	34.1	0.9
DUP 835929	QC	32.7	1.2
865314	Drill Core	14.8	2.4
DUP 865314	QC	13.2	2.9
865349	Drill Core	14.9	1.6
DUP 865349	QC	15.7	1.9
865384	Drill Core	2.6	<0.5
DUP 865384	QC	3.6	<0.5
Reference Materials			
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXH55	Standard		







Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 16, 2009

**Page:** 2 of 3 **Part** 3

## QUALITY CONTROL REPORT

SMI09000296.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD SF-3T	Standard	61.4	0.6
STD SF-3T	Standard	56.5	0.6
STD SF-3T	Standard	54.8	0.5
STD SF-3T	Standard	52.7	1.0
STD SF-3T	Standard	91.5	0.6
STD SF-3T	Standard	90.1	0.6
STD SF-3T	Standard	87.0	0.6
STD SF-3T	Standard	87.9	0.5
STD OXE56 Expected			
STD OXH55 Expected			
STD SF-3T Expected		90.8	0.6
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank	<0.5	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 16, 2009

**Page:** 3 of 3 **Part** 1

**QUALITY CONTROL REPORT**

**SMI09000296.1**

		WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca
		kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%
		0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01
BLK	Blank		<2																		
BLK	Blank			<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01
Prep Wash																					
G1	Prep Blank		<2	<0.5	18.9	22.9	56	<0.5	4.9	5	781	2.36	<5	2.4	6.1	719	<0.5	<0.5	<0.5	54	2.43
G1	Prep Blank		<2	<0.5	5.9	23.4	59	<0.5	4.2	5	797	2.36	26	2.3	7.9	696	<0.5	<0.5	<0.5	53	2.39



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 16, 2009

**Page:** 3 of 3 **Part** 2

**QUALITY CONTROL REPORT**

**SMI09000296.1**

		7TX P %	7TX La ppm	7TX Cr ppm	7TX Mg %	7TX Ba ppm	7TX Ti %	7TX Al %	7TX Na %	7TX K %	7TX W ppm	7TX Zr ppm	7TX Ce ppm	7TX Sn ppm	7TX Y ppm	7TX Nb ppm	7TX Ta ppm	7TX Be ppm	7TX Sc ppm	7TX Li ppm	7TX S %
		0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5
BLK	Blank																				
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5
Prep Wash																					
G1	Prep Blank	0.09	17.8	10	0.64	1078	0.237	6.56	2.71	2.99	<0.5	7.1	37	2.2	11.6	22.7	1.4	<5	5	38.5	<0.5
G1	Prep Blank	0.09	16.7	11	0.65	1058	0.240	6.31	2.62	2.91	<0.5	7.8	37	1.1	11.4	22.9	1.1	<5	5	37.8	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 16, 2009

**Page:** 3 of 3 **Part** 3

## QUALITY CONTROL REPORT

SMI09000296.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
BLK	Blank		
BLK	Blank	<0.5	<0.5
Prep Wash			
G1	Prep Blank	100.5	0.7
G1	Prep Blank	97.7	<0.5



1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

Submitted By: Ted Oliver  
Receiving Lab: Canada-Smithers  
Received: September 29, 2009  
Report Date: October 20, 2009  
Page: 1 of 5

## CERTIFICATE OF ANALYSIS

SMI09000300.1

### CLIENT JOB INFORMATION

Project: Bodine  
Shipment ID:  
P.O. Number: VARR\_SSNB9012\_Sept2809  
Number of Samples: 103

### SAMPLE DISPOSAL

RTRN-PLP Return  
RTRN-RJT Return

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6  
Canada

CC:

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R150	98	Crush split and pulverize drill core to 200 mesh			VAN
3B	103	Fire assay fusion Au by ICP-ES	30	Completed	VAN
7TX	103	4 Acid Digestion Analysis by ICP-ES/ICP-MS	0.5	Completed	VAN
DIS-RJT	98	Warehouse handling / Disposition of reject			SMI

### ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.  
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.  
\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.





Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865398	Drill Core	3.59	<2	0.7	6.8	6.1	119	<0.5	3.8	4	1438	5.11	<5	<0.5	0.6	217	<0.5	<0.5	<0.5	29	2.10
865399	Drill Core	5.86	<2	<0.5	3.5	3.3	125	<0.5	3.8	3	1365	4.07	<5	<0.5	<0.5	118	<0.5	0.6	<0.5	14	1.41
865800	Drill Core	4.92	<2	<0.5	3.5	3.1	110	<0.5	0.6	3	1260	3.96	7	<0.5	<0.5	64	<0.5	5.5	<0.5	14	0.92
865801	Drill Core	7.06	<2	<0.5	2.8	2.1	123	<0.5	<0.5	3	940	4.28	<5	<0.5	0.6	76	<0.5	<0.5	<0.5	14	2.19
865802	Drill Core	6.72	<2	<0.5	1.8	2.8	113	<0.5	<0.5	3	1057	3.94	<5	<0.5	<0.5	102	<0.5	<0.5	<0.5	14	1.84
865803	Drill Core	6.38	<2	<0.5	8.5	2.4	111	<0.5	28.1	9	1390	4.43	23	<0.5	0.7	109	<0.5	0.7	<0.5	36	2.09
865804	Drill Core	6.93	<2	<0.5	9.4	3.7	104	<0.5	45.4	10	1166	4.26	<5	<0.5	1.0	183	<0.5	<0.5	<0.5	41	2.07
865805	Drill Core	8.09	<2	0.7	4.4	2.3	107	<0.5	6.2	3	958	3.34	<5	<0.5	<0.5	92	<0.5	<0.5	<0.5	<10	1.44
865806	Drill Core	5.79	<2	1.4	68.0	5.6	94	<0.5	271.3	47	1172	6.59	<5	1.3	3.8	2307	<0.5	<0.5	<0.5	220	7.33
865807	Drill Core	7.01	<2	1.2	52.1	4.0	92	<0.5	148.5	31	1183	5.84	<5	1.1	3.0	3128	<0.5	<0.5	<0.5	173	6.05
865808	Drill Core	6.56	<2	1.0	54.0	5.2	96	<0.5	206.1	43	1149	6.18	<5	1.2	3.8	3404	<0.5	<0.5	<0.5	188	7.08
865809	Drill Core	6.92	<2	<0.5	2.5	2.0	124	<0.5	<0.5	3	999	3.86	<5	<0.5	<0.5	107	<0.5	<0.5	<0.5	15	2.17
865810	Drill Core	6.83	<2	0.6	2.6	2.9	170	<0.5	<0.5	5	1553	5.30	7	<0.5	<0.5	76	<0.5	<0.5	<0.5	14	1.38
865811	Drill Core	6.04	<2	<0.5	0.8	1.5	112	<0.5	<0.5	3	1168	3.76	<5	<0.5	<0.5	62	<0.5	<0.5	<0.5	<10	1.03
865812	Drill Core	5.91	<2	<0.5	1.6	2.3	97	<0.5	0.6	3	1255	3.28	<5	<0.5	<0.5	90	<0.5	<0.5	<0.5	<10	1.24
865813	Drill Core	6.59	<2	<0.5	3.1	3.9	115	<0.5	<0.5	4	1538	3.81	<5	<0.5	<0.5	65	<0.5	<0.5	<0.5	14	1.00
865814	Drill Core	6.64	<2	<0.5	1.8	2.4	117	<0.5	<0.5	4	1435	4.08	<5	<0.5	<0.5	94	<0.5	<0.5	<0.5	16	1.14
865815	Drill Core	6.62	<2	<0.5	2.2	2.3	109	<0.5	<0.5	3	1187	3.37	<5	<0.5	<0.5	59	<0.5	<0.5	<0.5	13	0.87
865816	Rock Pulp	0.17	55	15.6	6018	6883	31729	24.1	62.5	67	1064	11.54	57	1.5	0.9	170	173.9	37.6	28.5	164	4.09
865817	Drill Core	6.07	<2	<0.5	7.9	2.8	108	<0.5	15.5	4	1055	3.40	27	<0.5	<0.5	99	<0.5	0.9	<0.5	23	1.32
865818	Drill Core	6.99	<2	0.6	9.9	2.6	109	<0.5	23.8	9	1147	3.54	63	<0.5	0.7	135	<0.5	1.5	<0.5	39	2.35
865819	Drill Core	6.13	<2	0.7	2.1	2.8	120	<0.5	1.1	4	1532	4.83	9	<0.5	<0.5	69	<0.5	<0.5	<0.5	18	1.29
865820	Drill Core	6.37	<2	<0.5	4.3	5.6	186	<0.5	0.8	4	1419	4.82	<5	<0.5	<0.5	74	<0.5	<0.5	<0.5	17	1.38
865821	Drill Core	4.91	<2	<0.5	2.4	<0.5	132	<0.5	<0.5	2	989	3.60	<5	<0.5	<0.5	52	<0.5	<0.5	<0.5	<10	0.87
865822	Drill Core	6.43	<2	<0.5	1.5	1.9	163	<0.5	<0.5	1	896	3.37	<5	<0.5	0.7	21	<0.5	<0.5	<0.5	<10	0.28
865823	Drill Core	6.22	<2	<0.5	2.0	2.0	155	<0.5	<0.5	1	849	3.29	<5	0.6	0.8	28	<0.5	<0.5	<0.5	<10	0.32
865824	Drill Core	6.38	<2	<0.5	2.2	3.4	154	<0.5	<0.5	1	683	3.02	<5	<0.5	0.7	36	<0.5	<0.5	<0.5	<10	0.53
865825	Drill Core	6.39	<2	0.7	5.0	4.7	127	<0.5	<0.5	1	504	2.82	22	<0.5	<0.5	57	<0.5	0.6	<0.5	<10	0.83
865826	Drill Core	6.44	<2	<0.5	4.5	1.2	126	<0.5	<0.5	1	467	2.82	54	<0.5	0.5	71	<0.5	1.0	<0.5	<10	0.92
865827	Drill Core	6.17	<2	3.2	3.9	1.3	104	<0.5	<0.5	1	433	2.56	37	0.5	<0.5	66	<0.5	1.1	<0.5	<10	0.74

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865398	Drill Core	0.13	5.8	5	1.61	50	0.537	7.37	2.99	0.68	<0.5	83.7	17	1.6	44.4	3.0	<0.5	<5	14	9.4	<0.5
865399	Drill Core	0.12	6.2	3	1.28	65	0.500	6.73	2.96	0.71	<0.5	47.9	18	1.8	41.9	3.0	<0.5	<5	15	13.5	<0.5
865800	Drill Core	0.11	6.5	1	0.89	62	0.499	6.86	2.43	0.79	0.6	36.8	18	0.9	29.7	2.5	<0.5	<5	16	29.8	<0.5
865801	Drill Core	0.12	7.0	<1	1.79	86	0.541	7.11	2.27	1.53	<0.5	117.8	19	1.4	45.0	2.7	<0.5	<5	17	9.0	<0.5
865802	Drill Core	0.11	5.9	3	1.50	71	0.490	6.64	2.73	1.03	<0.5	44.8	18	1.4	42.9	2.5	<0.5	<5	15	10.3	<0.5
865803	Drill Core	0.16	10.4	27	1.55	69	0.502	6.36	2.89	0.67	<0.5	77.5	26	1.4	29.8	4.6	<0.5	<5	16	14.0	<0.5
865804	Drill Core	0.18	12.6	40	2.36	189	0.520	6.56	3.20	0.65	<0.5	48.6	32	1.4	31.2	3.6	<0.5	<5	15	12.2	<0.5
865805	Drill Core	0.08	5.6	9	1.19	80	0.356	5.49	2.78	0.65	<0.5	16.6	16	1.3	25.5	2.4	<0.5	<5	13	6.9	<0.5
865806	Drill Core	0.57	46.7	200	6.95	1408	0.721	6.24	2.13	0.99	<0.5	121.3	104	0.9	14.8	19.2	0.8	<5	21	42.0	<0.5
865807	Drill Core	0.44	37.9	153	4.83	1066	0.663	6.42	2.54	1.19	<0.5	99.8	82	1.0	15.6	16.3	0.7	<5	20	38.0	<0.5
865808	Drill Core	0.53	46.0	170	6.07	1519	0.696	6.28	2.17	1.22	<0.5	107.4	101	1.1	17.7	17.8	0.7	<5	21	37.9	<0.5
865809	Drill Core	0.12	5.7	8	1.75	63	0.495	6.80	3.15	0.93	0.9	17.7	18	1.5	41.2	2.3	<0.5	<5	15	15.3	<0.5
865810	Drill Core	0.12	7.2	15	2.41	97	0.542	8.06	2.88	1.45	<0.5	123.1	21	1.4	42.1	2.7	<0.5	<5	18	17.2	<0.5
865811	Drill Core	0.10	5.7	5	1.44	39	0.380	6.26	3.11	0.69	<0.5	17.8	17	1.2	21.1	2.3	<0.5	<5	14	7.5	<0.5
865812	Drill Core	0.10	5.6	3	1.02	31	0.418	6.03	3.28	0.51	<0.5	10.6	17	1.5	27.2	2.1	<0.5	<5	12	10.2	<0.5
865813	Drill Core	0.12	5.5	4	1.26	45	0.479	6.70	3.51	0.75	<0.5	45.6	17	0.7	31.0	2.3	<0.5	<5	14	11.5	<0.5
865814	Drill Core	0.13	5.6	6	1.29	58	0.529	6.88	3.39	0.97	<0.5	44.8	18	1.5	41.6	2.2	<0.5	<5	15	10.8	<0.5
865815	Drill Core	0.11	5.4	5	1.02	38	0.463	6.49	3.72	0.56	<0.5	42.9	17	1.7	29.3	2.2	<0.5	<5	14	14.8	<0.5
865816	Rock Pulp	0.06	6.0	89	2.51	311	0.428	5.93	1.45	0.68	27.2	14.1	13	13.3	14.4	3.5	<0.5	<5	21	17.2	6.6
865817	Drill Core	0.11	6.3	16	0.91	69	0.457	6.08	3.14	0.93	0.9	10.0	19	1.3	18.1	3.1	<0.5	<5	13	17.3	0.6
865818	Drill Core	0.16	10.8	37	1.07	61	0.448	5.77	3.12	0.66	0.7	24.9	26	1.6	18.4	4.4	<0.5	<5	13	9.2	1.3
865819	Drill Core	0.12	5.9	5	1.81	58	0.556	7.36	3.55	0.65	<0.5	32.8	17	1.7	39.5	2.5	<0.5	<5	16	17.8	<0.5
865820	Drill Core	0.12	6.1	3	1.73	55	0.584	7.51	3.79	0.73	<0.5	159.6	19	1.3	43.0	2.8	<0.5	<5	15	14.9	<0.5
865821	Drill Core	0.08	6.6	5	1.52	117	0.358	6.53	2.44	1.34	<0.5	43.7	20	1.6	42.4	3.0	<0.5	<5	13	13.3	<0.5
865822	Drill Core	0.03	7.3	4	1.90	239	0.240	7.88	1.86	2.55	<0.5	57.4	24	2.2	45.0	3.3	<0.5	<5	15	30.6	<0.5
865823	Drill Core	0.03	9.7	5	1.56	210	0.235	7.86	2.34	2.43	<0.5	305.8	29	2.1	56.0	4.2	<0.5	<5	15	21.8	<0.5
865824	Drill Core	0.03	8.6	2	1.38	230	0.249	8.06	2.45	2.74	<0.5	61.4	27	1.7	47.9	3.5	<0.5	<5	16	23.4	<0.5
865825	Drill Core	0.03	8.0	2	0.79	119	0.211	6.88	3.39	1.32	<0.5	43.4	24	1.9	50.1	2.9	<0.5	<5	13	15.8	<0.5
865826	Drill Core	0.03	8.4	5	0.61	120	0.204	6.49	3.37	1.14	<0.5	29.4	24	2.1	47.5	3.2	<0.5	<5	13	14.3	<0.5
865827	Drill Core	0.02	6.2	5	0.56	146	0.185	5.94	2.98	1.15	<0.5	12.0	18	1.7	35.5	2.5	<0.5	<5	11	12.4	<0.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 20, 2009

Page: 2 of 5 Part 3

CERTIFICATE OF ANALYSIS

SMI09000300.1

Table with columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (e.g., 865398) and descriptions (e.g., Drill Core) with corresponding analytical results.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 3 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865828	Drill Core	5.67	<2	1.1	2.6	6.5	152	<0.5	<0.5	1	486	2.66	19	<0.5	0.6	47	<0.5	<0.5	<0.5	<10	0.63
865829	Drill Core	6.17	<2	1.3	3.6	0.9	197	<0.5	<0.5	1	615	2.44	11	<0.5	<0.5	45	<0.5	<0.5	<0.5	<10	0.44
865830	Drill Core	6.33	<2	1.3	3.6	2.7	185	<0.5	1.1	1	634	2.65	9	<0.5	<0.5	66	<0.5	<0.5	<0.5	<10	0.72
865831	Drill Core	2.21	<2	1.3	3.0	1.2	167	<0.5	<0.5	1	558	2.63	15	<0.5	<0.5	40	<0.5	0.5	<0.5	<10	0.35
865832	Drill Core	2.73	<2	1.5	19.4	1.5	223	<0.5	4.9	5	577	3.14	18	<0.5	<0.5	133	1.0	<0.5	<0.5	36	1.33
865833	Drill Core	7.51	<2	<0.5	38.9	1.3	118	<0.5	36.4	19	858	5.34	8	1.1	1.3	326	<0.5	<0.5	<0.5	184	3.60
865834	Drill Core	3.13	<2	<0.5	17.4	3.8	89	<0.5	27.3	15	1830	3.95	<5	2.1	1.6	1191	<0.5	<0.5	<0.5	105	12.88
865835	Drill Core	3.41	<2	4.9	66.6	12.5	91	<0.5	55.2	18	818	3.98	<5	1.7	1.7	1051	<0.5	<0.5	<0.5	144	10.89
865836	Rock Pulp	0.17	1401	32.4	10055	5627	21558	91.4	1435	146	1347	35.12	1025	1.6	0.7	21	131.1	219.2	45.9	22	0.90
865837	Drill Core	6.12	3	1.6	61.5	13.2	93	<0.5	58.3	16	667	3.73	<5	1.3	1.4	1117	<0.5	<0.5	<0.5	140	11.34
865838	Drill Core	6.64	<2	<0.5	73.7	6.7	73	<0.5	77.4	18	567	4.13	<5	1.2	1.3	983	<0.5	<0.5	<0.5	161	10.79
865839	Drill Core	6.81	2	<0.5	77.0	8.0	78	<0.5	84.1	19	638	4.03	<5	1.4	1.3	1237	<0.5	<0.5	<0.5	146	12.80
865840	Drill Core	6.65	<2	2.0	47.7	9.7	78	<0.5	60.0	17	791	3.82	<5	1.3	1.2	1217	<0.5	<0.5	<0.5	138	12.62
865841	Drill Core	6.73	<2	0.5	85.0	4.8	80	<0.5	140.8	27	777	5.18	<5	1.3	1.5	669	<0.5	<0.5	<0.5	185	7.61
865842	Drill Core	6.37	2	0.8	106.0	3.3	96	<0.5	108.9	25	743	5.42	19	1.1	1.9	395	<0.5	<0.5	<0.5	180	4.54
865843	Drill Core	6.58	<2	<0.5	87.4	3.8	100	<0.5	123.1	24	856	5.61	20	0.9	1.8	438	<0.5	<0.5	<0.5	189	5.18
865844	Drill Core	5.80	<2	<0.5	84.3	5.7	94	<0.5	107.7	24	794	5.29	21	1.0	1.6	405	<0.5	0.5	<0.5	182	4.74
865845	Drill Core	6.42	3	<0.5	99.8	5.1	100	<0.5	83.8	21	752	5.25	13	1.1	2.1	411	<0.5	<0.5	<0.5	176	4.43
865846	Drill Core	6.44	2	1.0	103.6	4.5	108	<0.5	102.3	24	809	5.29	13	1.2	2.0	450	<0.5	<0.5	<0.5	178	5.33
865847	Drill Core	6.60	3	<0.5	91.6	3.0	90	<0.5	83.3	21	761	4.98	14	1.1	1.9	426	<0.5	0.7	<0.5	168	4.96
865848	Drill Core	6.13	3	0.5	91.9	3.5	96	<0.5	90.9	21	788	5.08	<5	1.2	1.9	435	<0.5	<0.5	<0.5	176	4.78
865849	Drill Core	6.88	4	2.0	92.2	3.4	90	<0.5	95.1	23	852	4.58	15	1.1	1.9	626	<0.5	<0.5	<0.5	156	6.86
865850	Drill Core	6.46	<2	0.7	98.5	6.6	108	<0.5	90.4	22	715	5.07	<5	1.1	2.1	513	<0.5	<0.5	<0.5	176	5.63
865851	Drill Core	6.42	<2	1.2	81.7	6.9	78	<0.5	87.2	20	663	4.54	<5	1.2	1.6	792	<0.5	<0.5	<0.5	174	8.57
865852	Drill Core	6.38	<2	0.6	98.8	3.7	81	<0.5	87.3	21	552	4.67	<5	1.4	1.5	566	<0.5	<0.5	<0.5	170	6.67
865853	Drill Core	6.15	<2	1.0	68.9	2.8	73	<0.5	81.0	19	764	4.25	<5	1.4	1.8	853	<0.5	<0.5	<0.5	164	9.07
865854	Drill Core	6.27	17	0.8	74.0	1.1	80	<0.5	132.4	23	855	4.72	<5	0.9	1.3	693	<0.5	<0.5	<0.5	190	7.81
865855	Drill Core	6.06	4	0.6	86.4	4.0	80	<0.5	123.7	25	695	4.91	<5	1.0	1.6	627	<0.5	<0.5	<0.5	176	7.10
865856	Rock Pulp	0.18	54	16.2	6004	7060	32248	23.4	59.8	64	1005	11.70	9	1.6	0.9	172	176.2	30.8	29.5	181	4.03
865857	Drill Core	6.73	12	1.7	70.2	11.0	75	<0.5	68.9	17	606	4.03	10	1.2	1.5	936	<0.5	2.1	<0.5	158	10.04

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 3 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865828	Drill Core	0.03	7.9	9	0.85	264	0.207	6.70	2.81	1.79	<0.5	53.2	23	1.5	35.1	3.7	<0.5	<5	14	12.6	<0.5
865829	Drill Core	0.02	5.7	7	0.55	42	0.146	4.84	3.07	0.29	<0.5	39.5	17	1.2	24.5	2.2	<0.5	<5	9	6.9	<0.5
865830	Drill Core	0.02	6.8	5	0.71	175	0.170	5.70	2.89	0.90	<0.5	38.4	19	1.4	23.1	2.4	<0.5	<5	12	7.9	<0.5
865831	Drill Core	0.02	2.5	<1	0.65	64	0.159	3.14	3.34	0.29	<0.5	13.4	9	1.8	7.8	2.9	<0.5	<5	7	8.4	<0.5
865832	Drill Core	0.05	4.6	12	1.66	502	0.271	5.15	1.39	2.03	<0.5	17.6	15	1.8	22.9	3.0	<0.5	<5	12	23.3	<0.5
865833	Drill Core	0.10	9.8	67	3.46	1155	0.530	7.75	0.29	3.35	<0.5	79.8	22	1.0	23.8	4.2	<0.5	<5	20	43.7	<0.5
865834	Drill Core	0.07	6.9	21	6.80	315	0.327	5.90	0.04	1.05	<0.5	68.1	16	<0.5	17.3	3.1	<0.5	<5	16	60.0	<0.5
865835	Drill Core	0.09	10.6	61	3.58	737	0.365	6.11	0.10	2.71	<0.5	78.4	19	0.9	18.7	3.3	<0.5	<5	15	43.3	0.9
865836	Rock Pulp	0.01	4.5	1023	0.84	74	0.009	0.81	0.04	0.11	5.6	13.7	8	18.2	2.8	2.6	<0.5	<5	<1	5.7	32.4
865837	Drill Core	0.08	7.2	70	2.94	666	0.313	5.72	0.43	2.45	<0.5	62.2	13	0.9	15.0	3.5	<0.5	<5	15	34.8	1.0
865838	Drill Core	0.10	7.2	134	3.00	620	0.321	5.93	0.84	2.25	<0.5	51.1	14	0.8	13.2	2.8	<0.5	<5	15	38.4	1.1
865839	Drill Core	0.09	7.1	110	3.30	673	0.295	5.61	0.36	2.34	<0.5	52.1	12	0.8	13.7	3.4	<0.5	<5	15	42.5	1.4
865840	Drill Core	0.08	7.2	91	3.57	754	0.329	5.55	0.21	2.17	<0.5	65.6	15	0.5	14.4	3.2	<0.5	<5	15	37.2	1.4
865841	Drill Core	0.14	12.5	198	3.80	907	0.385	6.62	1.05	2.09	<0.5	60.3	24	0.9	13.9	3.9	<0.5	<5	18	45.1	0.9
865842	Drill Core	0.10	9.7	146	3.17	516	0.379	7.25	1.76	1.66	<0.5	63.0	18	1.2	15.2	3.7	<0.5	<5	18	30.1	<0.5
865843	Drill Core	0.10	10.2	162	3.38	525	0.394	7.48	1.76	1.67	<0.5	63.9	19	0.5	16.6	3.6	<0.5	<5	19	34.4	<0.5
865844	Drill Core	0.11	9.7	157	3.10	497	0.333	7.29	1.86	1.71	<0.5	69.8	18	0.7	11.8	3.4	<0.5	<5	19	32.1	<0.5
865845	Drill Core	0.10	11.6	127	2.95	422	0.321	7.22	2.22	1.42	<0.5	56.0	20	2.3	13.1	3.4	<0.5	<5	19	26.3	<0.5
865846	Drill Core	0.11	10.5	131	2.94	449	0.330	7.32	2.12	1.55	<0.5	70.2	18	0.8	11.2	2.8	<0.5	<5	18	35.9	<0.5
865847	Drill Core	0.11	9.3	120	2.79	507	0.324	7.02	1.78	1.83	<0.5	60.4	17	0.8	12.5	3.2	<0.5	<5	18	28.3	<0.5
865848	Drill Core	0.10	11.2	131	2.95	616	0.347	7.22	1.67	1.97	<0.5	66.4	21	1.2	12.6	4.2	<0.5	<5	20	32.1	<0.5
865849	Drill Core	0.10	10.2	111	2.75	552	0.314	6.59	1.59	1.72	<0.5	58.4	19	0.9	13.3	3.6	<0.5	<5	17	31.6	<0.5
865850	Drill Core	0.11	9.7	132	3.18	692	0.335	7.10	1.28	2.41	<0.5	65.2	19	0.7	12.9	3.2	<0.5	<5	18	33.0	0.8
865851	Drill Core	0.09	7.1	168	3.18	621	0.340	6.58	1.25	2.16	<0.5	55.8	15	1.1	14.0	3.2	<0.5	<5	16	37.4	0.9
865852	Drill Core	0.10	7.6	141	3.09	563	0.341	6.86	1.69	2.02	<0.5	60.0	14	0.5	15.1	3.5	<0.5	<5	17	36.1	0.9
865853	Drill Core	0.09	11.0	129	3.13	501	0.297	6.40	1.57	1.71	<0.5	59.0	20	0.8	14.3	2.9	<0.5	<5	15	37.1	0.6
865854	Drill Core	0.11	11.9	236	3.51	416	0.330	6.58	1.71	1.42	<0.5	46.3	20	<0.5	13.3	2.6	<0.5	<5	18	34.9	<0.5
865855	Drill Core	0.11	9.5	175	3.44	450	0.335	6.87	2.09	1.50	<0.5	56.3	16	0.6	13.9	2.9	<0.5	<5	16	39.3	1.4
865856	Rock Pulp	0.06	5.8	89	2.52	258	0.441	5.77	1.42	0.68	24.2	12.2	13	12.7	14.8	3.2	<0.5	<5	21	16.8	6.6
865857	Drill Core	0.08	8.9	106	2.84	560	0.337	5.77	1.08	1.99	<0.5	54.7	16	<0.5	13.6	3.0	<0.5	<5	14	31.9	2.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Amarc Resources
1020 - 800 W. Pender St.
Vancouver BC V6C 2V6 Canada

Project: Bodine
Report Date: October 20, 2009

Page: 3 of 5 Part 3

CERTIFICATE OF ANALYSIS

SMI09000300.1

Table with 4 columns: Method, Analyte, Unit, MDL, 7TX Rb ppm, 7TX Hf ppm. Rows include sample IDs (e.g., 865828) and sample types (e.g., Drill Core, Rock Pulp) with corresponding analytical values.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 4 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865858	Drill Core	3.00	9	3.7	37.8	14.7	89	<0.5	40.3	15	1065	3.73	14	1.2	1.4	1012	0.5	1.9	<0.5	123	11.03
865859	Drill Core	3.80	<2	<0.5	49.3	8.4	355	<0.5	3.8	9	972	4.84	<5	<0.5	<0.5	78	<0.5	<0.5	<0.5	94	1.05
865860	Drill Core	6.45	<2	<0.5	93.8	4.7	2688	<0.5	2.4	12	1808	5.75	<5	<0.5	<0.5	67	<0.5	<0.5	<0.5	127	0.93
865861	Drill Core	6.41	<2	<0.5	47.4	10.6	830	<0.5	1.5	5	1504	3.95	6	<0.5	<0.5	90	0.6	<0.5	<0.5	49	0.92
865862	Drill Core	8.11	<2	1.2	12.0	28.5	220	<0.5	<0.5	2	1423	3.42	15	<0.5	<0.5	103	1.9	<0.5	<0.5	<10	1.20
865863	Drill Core	4.87	<2	2.4	34.5	178.0	342	<0.5	2.2	6	2033	4.08	18	<0.5	<0.5	103	6.7	0.6	<0.5	47	1.64
865864	Drill Core	6.29	3	1.3	9.6	75.7	206	<0.5	<0.5	2	1664	3.24	14	<0.5	<0.5	54	1.1	<0.5	<0.5	<10	0.77
865865	Drill Core	6.45	3	0.8	15.8	59.5	206	<0.5	0.5	2	1693	3.49	20	<0.5	<0.5	63	1.4	<0.5	<0.5	<10	0.75
865866	Drill Core	6.98	3	0.8	7.2	11.7	120	<0.5	<0.5	2	1543	3.56	9	<0.5	<0.5	61	<0.5	<0.5	<0.5	<10	0.67
865867	Drill Core	6.57	<2	<0.5	5.9	7.9	115	<0.5	1.3	3	1319	3.77	<5	<0.5	<0.5	76	<0.5	<0.5	<0.5	12	1.02
865868	Drill Core	6.50	<2	<0.5	11.9	5.1	166	<0.5	2.7	5	1865	4.30	<5	<0.5	<0.5	92	<0.5	<0.5	<0.5	51	1.12
865869	Drill Core	6.78	<2	<0.5	26.2	26.7	851	<0.5	1.2	2	2471	3.76	<5	<0.5	<0.5	44	0.7	<0.5	<0.5	<10	0.41
865870	Drill Core	6.43	<2	<0.5	14.9	12.9	578	<0.5	0.6	2	1512	3.41	<5	<0.5	<0.5	44	0.6	0.8	<0.5	<10	0.42
865871	Drill Core	6.65	9	<0.5	60.5	39.6	855	<0.5	1.8	7	2902	4.70	<5	<0.5	<0.5	33	0.8	<0.5	<0.5	82	0.26
865872	Drill Core	6.91	<2	<0.5	29.6	12.4	431	<0.5	1.2	5	2271	4.24	<5	<0.5	<0.5	29	<0.5	<0.5	<0.5	58	0.24
865873	Drill Core	9.54	3	<0.5	45.6	28.2	372	<0.5	1.8	9	1773	4.72	<5	<0.5	<0.5	38	<0.5	<0.5	<0.5	75	0.22
865874	Drill Core	2.98	<2	<0.5	9.0	3.8	162	<0.5	<0.5	2	879	2.44	<5	<0.5	<0.5	31	<0.5	<0.5	<0.5	<10	0.17
865875	Drill Core	6.26	<2	<0.5	18.3	6.2	315	<0.5	0.9	5	2247	4.10	<5	<0.5	<0.5	42	<0.5	<0.5	<0.5	35	0.22
865876	Rock Pulp	0.16	1740	31.7	9917	5458	21587	88.9	1437	147	1479	36.02	2541	1.7	0.7	26	129.2	304.6	47.2	32	0.90
865877	Drill Core	6.11	<2	<0.5	1.9	<0.5	113	<0.5	2.0	2	1119	3.52	<5	<0.5	<0.5	37	<0.5	<0.5	<0.5	<10	0.18
865878	Drill Core	6.15	<2	<0.5	6.2	3.2	136	<0.5	0.8	3	1021	3.61	<5	<0.5	<0.5	45	<0.5	0.5	<0.5	11	0.26
865879	Drill Core	8.69	<2	<0.5	8.1	2.6	145	<0.5	2.1	6	1058	4.24	<5	<0.5	<0.5	54	<0.5	<0.5	<0.5	61	0.34
865880	Drill Core	4.19	<2	<0.5	102.4	12.8	132	<0.5	41.5	21	1360	5.32	<5	0.8	1.5	172	<0.5	<0.5	<0.5	136	2.56
865881	Drill Core	6.18	<2	<0.5	44.4	19.7	105	<0.5	28.6	31	1060	4.62	24	0.9	1.6	246	<0.5	<0.5	<0.5	198	3.24
865882	Drill Core	6.78	<2	<0.5	44.0	12.0	103	<0.5	29.3	17	813	4.86	7	0.8	1.8	287	<0.5	<0.5	<0.5	189	3.38
865883	Drill Core	6.94	<2	0.5	114.0	10.6	111	<0.5	36.1	23	1399	5.94	12	0.9	1.3	282	0.6	<0.5	<0.5	184	3.70
865884	Drill Core	0.69	<2	<0.5	3.2	20.2	78	<0.5	5.1	5	896	2.62	<5	3.5	5.8	747	<0.5	<0.5	<0.5	64	2.87
865885	Drill Core	3.99	<2	<0.5	39.2	8.3	117	<0.5	30.2	19	1370	5.58	<5	0.9	1.0	268	<0.5	<0.5	<0.5	152	3.37
865886	Drill Core	5.04	<2	3.9	59.0	24.3	78	<0.5	41.5	15	1493	3.90	<5	1.5	1.4	973	<0.5	<0.5	<0.5	138	11.57
865887	Drill Core	4.90	<2	7.9	52.5	88.5	137	<0.5	12.9	10	1371	5.06	30	0.6	0.6	437	0.6	<0.5	<0.5	141	5.24

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 4 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865858	Drill Core	0.07	8.0	49	2.97	573	0.333	5.55	0.95	1.92	<0.5	65.4	18	0.8	20.2	2.5	<0.5	<5	13	37.0	2.3
865859	Drill Core	0.08	4.4	5	2.46	546	0.572	6.72	2.13	1.89	<0.5	14.0	13	1.8	32.2	1.8	<0.5	<5	22	31.8	1.5
865860	Drill Core	0.08	5.3	6	2.16	535	0.558	6.48	1.89	1.56	<0.5	16.1	17	1.4	36.9	1.4	<0.5	<5	23	23.1	<0.5
865861	Drill Core	0.06	5.4	5	1.25	298	0.305	6.08	2.95	1.02	<0.5	6.3	19	0.8	40.5	1.6	<0.5	<5	17	14.5	<0.5
865862	Drill Core	0.05	5.5	6	1.01	315	0.251	6.09	2.76	1.48	<0.5	5.8	17	1.6	40.3	1.6	<0.5	<5	14	15.7	0.6
865863	Drill Core	0.06	4.5	4	1.10	291	0.382	6.00	2.47	1.60	<0.5	7.1	17	1.6	43.3	1.6	<0.5	<5	17	20.5	0.6
865864	Drill Core	0.04	6.0	<1	0.92	285	0.216	5.66	2.46	1.74	<0.5	6.6	19	1.8	26.8	1.7	<0.5	<5	14	19.9	0.8
865865	Drill Core	0.05	4.7	2	0.93	230	0.240	5.72	2.59	1.57	<0.5	8.5	16	2.0	28.0	1.7	<0.5	<5	14	19.1	1.1
865866	Drill Core	0.04	6.0	4	0.87	179	0.262	6.23	3.24	1.28	<0.5	12.1	17	1.9	32.8	2.2	<0.5	<5	14	13.8	0.6
865867	Drill Core	0.05	5.2	10	0.96	167	0.271	6.69	3.39	1.17	<0.5	25.8	17	4.6	33.6	2.4	<0.5	<5	15	10.6	<0.5
865868	Drill Core	0.05	5.2	3	1.70	113	0.358	6.49	3.51	0.69	<0.5	10.4	16	1.2	33.8	1.7	<0.5	<5	17	15.9	<0.5
865869	Drill Core	0.05	5.1	2	1.47	193	0.271	5.58	3.20	0.97	<0.5	11.6	16	2.1	32.8	2.0	<0.5	<5	12	13.2	<0.5
865870	Drill Core	0.05	4.6	3	1.31	220	0.246	5.18	3.20	1.06	<0.5	10.3	16	1.3	35.2	1.5	<0.5	<5	12	12.8	<0.5
865871	Drill Core	0.06	4.1	3	1.79	240	0.396	6.06	3.22	1.03	<0.5	12.5	14	1.9	26.9	1.9	<0.5	<5	17	19.2	<0.5
865872	Drill Core	0.05	4.5	5	1.98	183	0.329	6.12	3.39	0.80	<0.5	16.9	16	2.7	29.1	2.1	<0.5	<5	15	20.0	<0.5
865873	Drill Core	0.07	3.9	8	2.08	176	0.388	6.16	3.38	0.76	0.5	12.6	14	1.5	19.2	1.7	<0.5	<5	18	15.8	<0.5
865874	Drill Core	0.05	3.0	7	0.72	16	0.231	4.26	4.86	0.07	<0.5	8.9	11	2.3	12.1	1.6	<0.5	<5	9	6.2	<0.5
865875	Drill Core	0.06	5.1	9	1.77	92	0.321	6.07	4.26	0.19	<0.5	6.6	16	1.6	29.7	2.0	<0.5	<5	15	16.1	<0.5
865876	Rock Pulp	0.01	4.4	997	0.84	64	0.013	0.82	<0.01	0.12	7.6	19.9	8	21.7	4.9	3.7	<0.5	<5	2	6.9	31.5
865877	Drill Core	0.05	4.1	6	1.31	51	0.177	5.67	4.63	0.20	<0.5	7.1	13	1.7	18.7	1.3	<0.5	<5	12	13.5	<0.5
865878	Drill Core	0.05	2.6	14	1.29	63	0.212	5.32	4.50	0.24	<0.5	7.5	10	1.2	15.6	1.4	<0.5	<5	11	9.0	<0.5
865879	Drill Core	0.07	5.3	8	1.79	245	0.398	6.45	3.68	0.82	<0.5	10.5	16	1.5	31.0	2.5	<0.5	<5	17	14.9	<0.5
865880	Drill Core	0.09	8.5	67	3.00	687	0.501	8.07	2.02	2.13	<0.5	121.9	20	1.4	25.7	4.1	<0.5	<5	19	34.9	<0.5
865881	Drill Core	0.09	9.2	62	2.88	781	0.444	7.97	1.94	2.18	<0.5	65.9	21	1.1	27.6	4.9	<0.5	<5	18	38.9	<0.5
865882	Drill Core	0.10	9.2	60	2.87	1068	0.461	8.51	1.54	1.91	<0.5	74.9	23	1.4	21.1	4.4	<0.5	<5	19	36.4	<0.5
865883	Drill Core	0.09	8.4	73	3.35	796	0.549	7.80	1.40	2.00	<0.5	69.3	19	1.3	22.4	4.6	<0.5	<5	23	40.7	<0.5
865884	Drill Core	0.09	18.1	13	0.86	1037	0.249	7.32	2.68	1.95	<0.5	11.0	40	1.8	13.1	23.4	1.3	<5	5	48.1	<0.5
865885	Drill Core	0.08	8.9	76	3.13	727	0.538	7.73	1.69	1.87	<0.5	115.3	21	0.7	36.2	4.2	<0.5	<5	19	37.2	1.1
865886	Drill Core	0.07	8.0	64	2.63	550	0.260	5.73	1.02	1.63	1.5	57.3	16	0.5	16.4	2.7	<0.5	<5	13	27.1	0.9
865887	Drill Core	0.09	4.9	26	2.70	544	0.493	6.54	1.35	1.94	<0.5	84.4	14	1.0	42.8	2.9	<0.5	<5	17	33.3	1.4

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.





Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 20, 2009

**Page:** 4 of 5 **Part** 3

## CERTIFICATE OF ANALYSIS

SMI09000300.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
865858	Drill Core	35.8	2.3
865859	Drill Core	31.3	<0.5
865860	Drill Core	24.5	<0.5
865861	Drill Core	15.9	<0.5
865862	Drill Core	21.4	<0.5
865863	Drill Core	20.9	<0.5
865864	Drill Core	24.4	<0.5
865865	Drill Core	18.8	<0.5
865866	Drill Core	12.9	<0.5
865867	Drill Core	12.3	1.7
865868	Drill Core	7.1	<0.5
865869	Drill Core	9.9	<0.5
865870	Drill Core	9.7	<0.5
865871	Drill Core	11.4	<0.5
865872	Drill Core	7.9	0.5
865873	Drill Core	9.6	1.1
865874	Drill Core	0.5	<0.5
865875	Drill Core	2.2	<0.5
865876	Rock Pulp	3.7	<0.5
865877	Drill Core	2.4	<0.5
865878	Drill Core	1.7	<0.5
865879	Drill Core	12.5	<0.5
865880	Drill Core	35.6	2.1
865881	Drill Core	40.1	2.3
865882	Drill Core	34.0	2.3
865883	Drill Core	38.0	2.1
865884	Drill Core	59.6	0.7
865885	Drill Core	33.6	1.9
865886	Drill Core	29.8	1.7
865887	Drill Core	41.4	2.2



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 5 of 5 Part 1

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
865888	Drill Core	6.51	<2	1.1	43.2	29.4	208	<0.5	7.8	8	734	4.30	20	<0.5	0.5	190	1.1	<0.5	<0.5	85	1.86
865889	Drill Core	6.96	<2	<0.5	24.5	2.3	100	<0.5	26.1	15	921	4.34	9	0.7	1.1	218	<0.5	<0.5	<0.5	159	2.34
865890	Drill Core	7.07	<2	<0.5	36.9	5.1	99	<0.5	21.8	14	605	4.44	<5	<0.5	0.7	216	<0.5	<0.5	<0.5	140	2.07
865891	Drill Core	6.78	<2	0.6	49.1	3.8	113	<0.5	22.3	16	596	4.78	5	<0.5	0.9	123	<0.5	<0.5	<0.5	138	1.10
865892	Drill Core	6.75	<2	0.7	47.5	7.7	133	<0.5	22.3	19	1234	6.07	6	0.9	0.7	256	<0.5	<0.5	<0.5	174	2.83
865893	Drill Core	6.87	<2	<0.5	24.2	2.6	150	<0.5	9.2	11	1083	5.40	15	<0.5	<0.5	99	<0.5	<0.5	<0.5	131	0.95
865894	Drill Core	6.40	<2	<0.5	39.6	6.6	105	<0.5	31.9	17	877	4.92	19	0.5	1.4	114	<0.5	<0.5	<0.5	139	1.20
865895	Drill Core	6.60	<2	<0.5	66.9	1.3	101	<0.5	20.2	14	1047	4.74	13	<0.5	0.5	178	<0.5	<0.5	<0.5	165	2.03
865896	Rock Pulp	0.15	1687	29.9	9932	5462	21142	88.8	1416	146	1401	36.73	2571	1.9	0.7	24	130.9	289.0	47.5	33	0.90
865897	Drill Core	7.04	<2	<0.5	60.6	3.4	103	<0.5	28.3	18	791	5.24	23	<0.5	0.8	156	<0.5	<0.5	<0.5	169	1.52
865898	Drill Core	6.91	4	<0.5	59.9	4.8	109	<0.5	28.0	19	841	5.51	24	<0.5	0.9	146	<0.5	<0.5	<0.5	168	1.49
865899	Drill Core	9.07	<2	<0.5	49.3	1.9	96	<0.5	19.7	13	520	4.59	10	<0.5	0.6	117	<0.5	<0.5	<0.5	137	1.05
876900	Drill Core	2.84	<2	0.8	66.0	8.7	78	<0.5	63.1	19	894	4.11	<5	1.2	1.4	795	<0.5	<0.5	<0.5	165	9.89



Acme Analytical Laboratories (Vancouver) Ltd.  
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 5 of 5 Part 2

CERTIFICATE OF ANALYSIS

SMI09000300.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
865888	Drill Core	0.06	3.7	23	2.27	427	0.354	6.43	2.23	1.60	<0.5	65.6	10	1.4	16.1	2.5	<0.5	<5	15	28.4	1.3
865889	Drill Core	0.08	6.1	60	2.21	849	0.402	7.62	2.40	2.23	<0.5	62.0	15	0.9	19.0	3.2	<0.5	<5	17	27.3	<0.5
865890	Drill Core	0.08	6.2	61	2.09	528	0.497	7.22	2.63	1.73	<0.5	38.6	15	1.4	21.9	3.2	<0.5	<5	18	26.1	0.6
865891	Drill Core	0.09	8.0	53	2.11	440	0.508	7.35	3.25	1.53	<0.5	42.7	20	1.7	25.1	3.8	<0.5	<5	17	22.2	0.7
865892	Drill Core	0.09	7.5	53	2.65	499	0.631	7.24	2.28	1.65	<0.5	58.7	19	1.6	27.3	2.5	<0.5	<5	23	27.8	0.6
865893	Drill Core	0.08	5.9	24	2.53	641	0.449	6.88	1.94	1.96	<0.5	26.8	15	1.3	20.2	2.3	<0.5	<5	20	24.9	<0.5
865894	Drill Core	0.08	8.3	67	2.41	1064	0.428	8.48	2.25	2.64	<0.5	77.4	19	1.6	18.8	3.6	<0.5	<5	18	25.6	<0.5
865895	Drill Core	0.08	5.8	47	2.18	599	0.440	7.11	2.79	1.43	<0.5	40.1	15	1.2	19.8	3.1	<0.5	<5	17	19.8	<0.5
865896	Rock Pulp	0.01	4.1	855	0.80	61	0.012	0.79	<0.01	0.13	7.2	14.4	8	19.8	4.4	3.1	<0.5	<5	2	7.1	32.5
865897	Drill Core	0.08	6.0	72	2.14	727	0.511	7.69	2.90	1.67	<0.5	38.1	16	1.2	21.6	2.9	<0.5	<5	19	18.1	<0.5
865898	Drill Core	0.08	7.2	77	2.18	793	0.530	7.81	2.68	1.86	<0.5	56.5	18	1.2	21.6	2.9	<0.5	<5	21	18.7	<0.5
865899	Drill Core	0.07	6.0	40	1.56	418	0.466	7.37	3.60	1.02	<0.5	34.7	16	0.8	21.7	2.8	<0.5	<5	16	16.7	<0.5
876900	Drill Core	0.09	8.2	130	2.92	594	0.312	6.12	0.86	1.57	<0.5	50.9	15	<0.5	12.2	3.0	<0.5	<5	14	34.2	1.1



Acme Analytical Laboratories (Vancouver) Ltd.  
1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
1020 - 800 W. Pender St.  
Vancouver BC V6C 2V6 Canada

**Project:** Bodine  
**Report Date:** October 20, 2009

**Page:** 5 of 5 Part 3

## CERTIFICATE OF ANALYSIS

SMI09000300.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
865888	Drill Core	30.6	0.9
865889	Drill Core	41.2	2.3
865890	Drill Core	32.5	1.8
865891	Drill Core	31.3	1.1
865892	Drill Core	35.3	2.2
865893	Drill Core	38.6	1.1
865894	Drill Core	53.0	2.2
865895	Drill Core	21.4	0.9
865896	Rock Pulp	4.2	<0.5
865897	Drill Core	30.7	1.1
865898	Drill Core	34.1	1.3
865899	Drill Core	20.6	0.9
876900	Drill Core	34.3	1.6



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 1 of 2 Part 1

QUALITY CONTROL REPORT

SMI09000300.1

Method	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
Unit	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
Pulp Duplicates																					
865398	Drill Core	3.59	<2	0.7	6.8	6.1	119	<0.5	3.8	4	1438	5.11	<5	<0.5	0.6	217	<0.5	<0.5	<0.5	29	2.10
REP 865398	QC		<2	<0.5	5.9	7.1	119	<0.5	1.6	4	1434	5.07	<5	<0.5	0.6	211	<0.5	<0.5	<0.5	29	2.06
865844	Drill Core	5.80	<2	<0.5	84.3	5.7	94	<0.5	107.7	24	794	5.29	21	1.0	1.6	405	<0.5	0.5	<0.5	182	4.74
REP 865844	QC		<2																		
865848	Drill Core	6.13	3	0.5	91.9	3.5	96	<0.5	90.9	21	788	5.08	<5	1.2	1.9	435	<0.5	<0.5	<0.5	176	4.78
REP 865848	QC			0.7	96.5	4.3	96	<0.5	82.5	21	844	4.86	9	1.1	2.0	433	<0.5	<0.5	<0.5	175	4.82
865852	Drill Core	6.38	<2	0.6	98.8	3.7	81	<0.5	87.3	21	552	4.67	<5	1.4	1.5	566	<0.5	<0.5	<0.5	170	6.67
REP 865852	QC			0.6	90.1	3.4	87	<0.5	93.7	21	569	4.73	<5	0.9	1.8	568	<0.5	<0.5	<0.5	173	6.75
865893	Drill Core	6.87	<2	<0.5	24.2	2.6	150	<0.5	9.2	11	1083	5.40	15	<0.5	<0.5	99	<0.5	<0.5	<0.5	131	0.95
REP 865893	QC		<2																		
865898	Drill Core	6.91	4	<0.5	59.9	4.8	109	<0.5	28.0	19	841	5.51	24	<0.5	0.9	146	<0.5	<0.5	<0.5	168	1.49
REP 865898	QC		<2	<0.5	56.6	4.5	104	<0.5	28.3	19	824	5.56	22	0.7	1.0	146	<0.5	<0.5	<0.5	167	1.50
Core Reject Duplicates																					
865819	Drill Core	6.13	<2	0.7	2.1	2.8	120	<0.5	1.1	4	1532	4.83	9	<0.5	<0.5	69	<0.5	<0.5	<0.5	18	1.29
DUP 865819	QC		<2	0.7	2.4	3.0	126	<0.5	<0.5	4	1506	4.73	7	0.6	<0.5	72	<0.5	<0.5	<0.5	16	1.33
865854	Drill Core	6.27	17	0.8	74.0	1.1	80	<0.5	132.4	23	855	4.72	<5	0.9	1.3	693	<0.5	<0.5	<0.5	190	7.81
DUP 865854	QC		<2	1.1	62.5	1.0	80	<0.5	117.9	21	867	4.50	<5	0.9	1.3	712	<0.5	<0.5	<0.5	182	7.94
865889	Drill Core	6.96	<2	<0.5	24.5	2.3	100	<0.5	26.1	15	921	4.34	9	0.7	1.1	218	<0.5	<0.5	<0.5	159	2.34
DUP 865889	QC		<2	<0.5	27.7	2.0	94	<0.5	27.2	15	908	4.32	8	0.7	1.1	220	<0.5	<0.5	<0.5	158	2.34
Reference Materials																					
STD OXE56	Standard		623																		
STD OXE56	Standard		627																		
STD OXE56	Standard		617																		
STD OXE56	Standard		609																		
STD OXH55	Standard		1304																		
STD OXH55	Standard		1304																		
STD OXH55	Standard		1306																		
STD SF-3T	Standard		310.9	7552	8305	10685	50.5	3423	177	3820	7.98	41	3.9	4.6	412	47.3	9.0	4.7	118	3.98	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 1 of 2 Part 2

QUALITY CONTROL REPORT

SMI09000300.1

Method	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
Analyte	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	S	
Unit	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
MDL	0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	0.5	5	1	0.5	0.5	
Pulp Duplicates																					
865398	Drill Core	0.13	5.8	5	1.61	50	0.537	7.37	2.99	0.68	<0.5	83.7	17	1.6	44.4	3.0	<0.5	<5	14	9.4	<0.5
REP 865398	QC	0.13	5.7	6	1.58	69	0.549	7.24	2.94	0.68	<0.5	53.5	18	1.8	41.2	2.3	<0.5	<5	15	11.9	<0.5
865844	Drill Core	0.11	9.7	157	3.10	497	0.333	7.29	1.86	1.71	<0.5	69.8	18	0.7	11.8	3.4	<0.5	<5	19	32.1	<0.5
REP 865844	QC																				
865848	Drill Core	0.10	11.2	131	2.95	616	0.347	7.22	1.67	1.97	<0.5	66.4	21	1.2	12.6	4.2	<0.5	<5	20	32.1	<0.5
REP 865848	QC	0.09	11.2	129	2.93	600	0.357	7.31	1.65	1.41	<0.5	62.8	20	0.6	12.1	3.4	<0.5	<5	19	30.7	<0.5
865852	Drill Core	0.10	7.6	141	3.09	563	0.341	6.86	1.69	2.02	<0.5	60.0	14	0.5	15.1	3.5	<0.5	<5	17	36.1	0.9
REP 865852	QC	0.11	9.2	133	3.10	575	0.346	6.89	1.70	2.04	<0.5	56.3	16	<0.5	15.9	3.5	<0.5	<5	16	36.6	0.9
865893	Drill Core	0.08	5.9	24	2.53	641	0.449	6.88	1.94	1.96	<0.5	26.8	15	1.3	20.2	2.3	<0.5	<5	20	24.9	<0.5
REP 865893	QC																				
865898	Drill Core	0.08	7.2	77	2.18	793	0.530	7.81	2.68	1.86	<0.5	56.5	18	1.2	21.6	2.9	<0.5	<5	21	18.7	<0.5
REP 865898	QC	0.09	7.2	81	2.17	799	0.505	7.62	2.61	1.86	<0.5	59.8	18	1.1	19.7	2.9	<0.5	<5	19	23.7	<0.5
Core Reject Duplicates																					
865819	Drill Core	0.12	5.9	5	1.81	58	0.556	7.36	3.55	0.65	<0.5	32.8	17	1.7	39.5	2.5	<0.5	<5	16	17.8	<0.5
DUP 865819	QC	0.12	5.6	7	1.78	52	0.540	7.24	3.57	0.63	<0.5	74.2	18	1.0	35.4	2.2	<0.5	<5	15	11.8	<0.5
865854	Drill Core	0.11	11.9	236	3.51	416	0.330	6.58	1.71	1.42	<0.5	46.3	20	<0.5	13.3	2.6	<0.5	<5	18	34.9	<0.5
DUP 865854	QC	0.10	11.2	217	3.48	404	0.322	6.48	1.75	1.38	<0.5	46.1	21	0.9	14.1	2.0	<0.5	<5	18	35.7	<0.5
865889	Drill Core	0.08	6.1	60	2.21	849	0.402	7.62	2.40	2.23	<0.5	62.0	15	0.9	19.0	3.2	<0.5	<5	17	27.3	<0.5
DUP 865889	QC	0.07	6.5	60	2.23	837	0.423	7.77	2.45	2.22	<0.5	72.1	15	1.2	21.2	3.3	<0.5	<5	17	27.9	<0.5
Reference Materials																					
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXE56	Standard																				
STD OXH55	Standard																				
STD OXH55	Standard																				
STD OXH55	Standard																				
STD SF-3T	Standard	0.06	17.3	164	4.51	486	0.183	5.29	2.06	2.43	3.5	16.8	39	4.3	10.4	14.5	0.8	<5	7	25.9	3.7

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

[www.acmelab.com](http://www.acmelab.com)

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 20, 2009

**Page:** 1 of 2 **Part** 3

## QUALITY CONTROL REPORT

SMI09000300.1

	Method	7TX	7TX
	Analyte	Rb	Hf
	Unit	ppm	ppm
	MDL	0.5	0.5
Pulp Duplicates			
865398	Drill Core	6.8	3.2
REP 865398	QC	6.3	2.4
865844	Drill Core	41.7	2.1
REP 865844	QC		
865848	Drill Core	46.3	2.2
REP 865848	QC	30.3	2.0
865852	Drill Core	44.1	1.4
REP 865852	QC	45.4	1.6
865893	Drill Core	38.6	1.1
REP 865893	QC		
865898	Drill Core	34.1	1.3
REP 865898	QC	35.3	1.6
Core Reject Duplicates			
865819	Drill Core	5.3	1.5
DUP 865819	QC	4.9	2.0
865854	Drill Core	29.9	1.3
DUP 865854	QC	30.1	1.7
865889	Drill Core	41.2	2.3
DUP 865889	QC	41.6	2.1
Reference Materials			
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXE56	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD OXH55	Standard		
STD SF-3T	Standard	85.2	0.7



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 2 Part 1

QUALITY CONTROL REPORT

SMI09000300.1

	WGHT	3B	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	7TX	
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Th	Sr	Cd	Sb	Bi	V	Ca	
	kg	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	
	0.01	2	0.5	0.5	0.5	5	0.5	0.5	1	5	0.01	5	0.5	0.5	5	0.5	0.5	0.5	10	0.01	
STD SF-3T	Standard		315.0	7575	8502	10689	52.2	3437	178	3881	8.01	47	4.1	4.7	416	48.1	9.3	4.6	123	3.96	
STD SF-3T	Standard		323.3	7641	8319	10662	51.5	3462	180	4066	8.00	47	3.9	4.6	426	49.4	10.4	6.8	129	4.00	
STD SF-3T	Standard		316.3	7677	8553	10872	53.6	3517	183	4129	8.10	46	4.0	4.6	425	48.4	10.5	4.8	134	4.03	
STD SF-3T	Standard		322.5	7749	8533	10990	53.0	3516	186	4214	8.34	41	3.9	4.7	432	49.4	10.8	4.9	136	4.08	
STD SF-3T	Standard		319.1	7909	8710	11051	51.6	3514	190	4255	8.29	48	4.9	4.6	435	49.5	10.5	4.7	136	4.05	
STD SF-3T	Standard		326.8	7831	8994	11130	53.8	3576	188	4199	8.53	42	4.1	4.7	442	51.6	10.7	4.8	138	4.10	
STD SF-3T	Standard		317.7	7746	8751	10937	54.0	3526	184	4143	8.38	41	4.1	4.6	437	47.9	10.6	4.9	136	4.05	
STD OXH55 Expected		1282																			
STD OXE56 Expected		611																			
STD SF-3T Expected			320	7723	9610	10672	52	3500	181	4320	8.33	40	4	4.7	440	47.5	11.1	4.8	143	4.1	
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01	
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01	
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01	
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<2																		
BLK	Blank		<0.5	<0.5	<0.5	<5	<0.5	<0.5	<1	<5	<0.01	<5	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<10	<0.01	
Prep Wash																					
G1	Prep Blank		<2	<0.5	4.4	22.5	59	<0.5	3.4	5	784	2.51	<5	3.2	7.9	749	<0.5	<0.5	0.5	53	2.56
G1	Prep Blank		<2	<0.5	4.7	25.1	60	<0.5	4.1	6	764	2.42	<5	3.2	8.0	742	<0.5	<0.5	<0.5	53	2.52





Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

Project: Bodine  
 Report Date: October 20, 2009

Page: 2 of 2 Part 2

QUALITY CONTROL REPORT

SMI09000300.1

		7TX P %	7TX La ppm	7TX Cr ppm	7TX Mg %	7TX Ba ppm	7TX Ti %	7TX Al %	7TX Na %	7TX K %	7TX W ppm	7TX Zr ppm	7TX Ce ppm	7TX Sn ppm	7TX Y ppm	7TX Nb ppm	7TX Ta ppm	7TX Be ppm	7TX Sc ppm	7TX Li ppm	7TX S %
		0.01	0.5	1	0.01	5	0.001	0.01	0.01	0.01	0.5	0.5	5	0.5	0.5	0.5	5	1	1	0.5	0.5
STD SF-3T	Standard	0.06	17.9	178	4.55	484	0.186	5.32	2.05	2.44	4.1	17.8	40	6.2	11.1	15.3	0.7	<5	7	25.7	3.7
STD SF-3T	Standard	0.05	18.5	184	4.49	516	0.186	5.33	2.06	2.08	4.2	14.0	41	6.3	10.4	14.6	0.7	<5	7	24.1	3.7
STD SF-3T	Standard	0.06	17.7	184	4.55	478	0.187	5.35	2.06	1.88	3.6	14.5	39	5.6	10.7	15.5	0.9	<5	7	26.3	3.8
STD SF-3T	Standard	0.06	17.9	187	4.59	501	0.187	5.42	2.12	2.26	4.0	14.2	41	5.7	10.6	14.8	1.1	<5	7	20.4	3.8
STD SF-3T	Standard	0.06	18.5	196	4.61	510	0.190	5.47	2.08	2.31	4.1	13.6	41	6.2	11.2	15.4	0.9	<5	7	27.0	3.8
STD SF-3T	Standard	0.06	17.4	187	4.67	733	0.195	5.50	2.13	2.51	4.3	14.2	40	5.7	10.8	15.1	0.8	<5	7	23.1	3.8
STD SF-3T	Standard	0.06	18.4	198	4.58	612	0.191	5.42	2.10	2.47	2.7	14.3	39	4.4	10.6	14.7	0.8	<5	7	23.9	3.7
STD OXH55 Expected																					
STD OXE56 Expected																					
STD SF-3T Expected		0.06	17	207.4	4.67	508	0.19	5.43	2.06	2.47	4.3	14	38	5.8	11.5	15.1	0.9	2.4	7	19.1	3.5
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank																				
BLK	Blank	<0.01	<0.5	<1	<0.01	<5	<0.001	<0.01	<0.01	<0.01	<0.5	<0.5	<5	<0.5	<0.5	<0.5	<0.5	<5	<1	<0.5	<0.5
Prep Wash																					
G1	Prep Blank	0.09	28.8	13	0.75	1065	0.238	8.35	2.63	3.08	<0.5	8.4	54	1.4	14.5	24.5	1.3	<5	5	36.9	<0.5
G1	Prep Blank	0.09	27.8	9	0.70	1059	0.231	8.14	2.59	3.03	<0.5	12.6	53	0.7	15.0	23.8	1.4	<5	6	38.4	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

**Client:** **Amarc Resources**  
 1020 - 800 W. Pender St.  
 Vancouver BC V6C 2V6 Canada

**Project:** Bodine

**Report Date:** October 20, 2009


**Page:** 2 of 2 **Part** 3

## QUALITY CONTROL REPORT

SMI09000300.1

		7TX Rb ppm 0.5	7TX Hf ppm 0.5
STD SF-3T	Standard	86.5	0.6
STD SF-3T	Standard	72.1	0.5
STD SF-3T	Standard	69.3	0.5
STD SF-3T	Standard	76.6	0.7
STD SF-3T	Standard	78.6	0.5
STD SF-3T	Standard	91.3	0.7
STD SF-3T	Standard	88.2	0.6
STD OXH55 Expected			
STD OXE56 Expected			
STD SF-3T Expected		90.8	0.6
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank	<0.5	<0.5
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank		
BLK	Blank	<0.5	<0.5
Prep Wash			
G1	Prep Blank	131.2	0.6
G1	Prep Blank	123.2	0.5





Claim outline

Drill Holes

● Pre-existing

● 2009


★ Mineral occurrence



**Amarc Resources Ltd.**  
**BODINE - WARREN**  
**Drill Hole Locations**

HTB: 02/12; BC05: 02/02/2011 **Figure 9.1**  
 Date: March 29, 2010 Scale: 1:5,000  
 WARR\_Fig9\_1DrillHoles\_Mar2010.WOR  
 UTM NAD83, Zone 10 Printed by: GMD





9009  
0

100

200

300

400

422.5m

Welded

ppm Cu    ppm Zn  
 1 cm =    1 cm =  
 250 ppm    1,000 ppm

Maximum value plotted:  
 5,000 ppm    10,000 ppm


500    250    1000    2000

EDH

**Amarc Resources Ltd.**  
**BODINE - WARREN**  
**Cross Section 9009**

Figure 9.2  
 Date: March 29, 2010    Scale 1: 500  
 BodineWAR\_DD\sections\_Mar2010\WCR    Plotted by: GMD

0    25    50  
 metres



9010

9011

100

100

200



200




300

326.7m

382.8m

Amarc Resources Ltd.  
**BODINE - WARREN**  
 Cross Section 9010 & 9011  
 Figure 9.3  
 Date: March 25, 2010  
 Scale: 1:500  
 Model: WAK\_CDSection\_Mar2010.WOR  
 Plotted by: GAO





**Amarc Resources Ltd.**  
**BODINE - WARREN**  
**Cross Section 9012**  
 Figure 9.4  
 Date: March 29, 2010  
 Scale: 1:500  
 BodineWAR\_DD\sections\_Mar2010.WOR  
 Plotted by: GMD