ASSESSMENT REPORT

MINERAL TITLES BRANCH
File
Rec'd

SEP 2 1 2010

L.I.S.
VANCOUVER, B.C.

on the

Prospecting Survey

of the

BC Geological Survey Assessment Report 31670

Gold Cutter 1 & 2

(612004 & 612063)

Bonaparte Lake Area

Map Sheet 92P

Lat. 51 14' 43" N Long. 120 15' 23" W

Author: Ronald J. Bilquist

(Owner/Operator)

15 September 2010



Table of Contents

	Page
Introduction (Access and Location, The Property, History, Purpose and Summary of Work Done	1 & 2.)
Regional and Property Geology	2.
Technical Data and Interpretation	2 & 3.
Summary and Recommendations	4 & 5.
References	6.
Statement of Qualifications	7.
Cost Statement	Follows page 7.
Illustrations: Location and Claim Maps	Follow page 1.
Appendix:	
(i) Sample Preparation and Method of Analysis	
(ii) Certificate of Analysis	

Prospectors Map (Traverse and Sample Locations)

In the Pouch

Introduction:

Access and Location – The Gold Cutter 1 & 2 claims (612004 & 612063) are located approximately five kilometres east of Bonaparte Lake within the 92P Bonaparte Lake (1:250000) map sheet, approximately 75 kilometres north of Kamloops. Access to the property is via highway # 5 north from Kamloops along the North Thompson River to just south of Darfield where the Boulder Mountain Road (gravel) leads off to the west. At about five or six kilometres along this road the Bonaparte FSR road provides access right to the property, a distance of about another five kilometres.


The claims are at about 1200 meters elevation on the eastern edge of the Bonaparte Plateau overlooking the North Thompson River valley. The topography is generally gentle and rolling with one small active stream draining east to the North Thompson River. The forests are a mixture of fir, cedar, pine, spruce. A major forest fire swept through the area a few years back destroying a large percentage of the forest and subsequently there has been patchy logging carried out to remove marketable timber from the burn area.


The Property – The Gold Cutter property consists of two claims comprising 728.38 hectares acquired in July 2009. The record numbers for the claims this report will be concerned with are 612004, & 612063 (see claim information below). The current owner and operator is Ronald John Bilquist, the author of this report.

<u>Claim</u>	Record #	<u>Hectares</u>	Expiry Date
Gold Cutter 1	612004	323.70	2012 Aug 15*
Gold Cutter 2	612063	404.68	2012 Aug 15*

^{*}on acceptance of this report

History - During a regional prospecting program in 2002 the author and his wife took some prospector grab samples from angular proximal quartz float along newly constructed logging road spur road. These samples were very anomalous in gold, silver and base metals (lead, zinc and copper). The area was acquired as four 2-post claims in 2002 and prospecting was done at that time and a report was filed in 2003. The assessment report number is #27243. In 2003 a large forest fire burnt most of the forest in the area of the showings and created greater exposure for prospecting. Selective logging was also carried out in the area of the burn. These claims were allowed to lapse at that time and were open until 2009 when a large parcel of land was acquired to cover the original showings and the surrounding area.





Purpose – The main purpose of the prospecting program in 2009 was to locate and reassess the historic showings as well as to prospect out from these showings to determine if the forest fire and logging had exposed any new showings of significance.

Summary of Work Done – Five field days were spent on the Gold Cutter project. Three days were spent prospecting and two days were spent traveling to and from the property. One and one half days were spent researching and a further four and a half days were spent compiling data, drafting and writing this report.

Regional and Property Geology:

Regional Geology – R.B. Campbell and H.W. Tipper in GSC Memoir 363, 1971, describe the area underlying the Gold Cutter claims as metasediments of the Harper Ranch Group which includes limestone, siltstone, shale, volcaniclastic sandstone and local volcanic rocks as well as volcanic rocks of the Eocene Skull Hill Formation (Kamloops Group). The Skull Hill Formation is mainly dacite, trachyte, basalt, rhyolite and related breccias. The Metasediments are intruded by Mesozoic (?) age granites, diorites and syenites.

<u>Property Geology</u> – The predominate rock within the claims is the metasedimentary unit which varies from a grey to a rusty red color. The metasediments are intruded by an elongated, north to south, medium to coarse syenite. Proximal to the intrusions the sediments appear more 'cooked' and pyrite is more abundant resulting in the rusty red color. The intrusions display fracturing, predominately oriented in an approximate north south direction. Fractures are often flooded and filled with tiny quartz veinlets and are most noticeable proximal to where the large angular mineralized quartz boulders are found. Rip up clasts of sedimentary rock in syenite has been noted in one location (Photo #1).

Technical Data and Interpretation

Mineralization and Alteration: The mineralization at the Gold Cutter property is primarily and exclusively confined to quartz veins, veinlets and stockworks in at least three, and possibly four, distinct zones. These zones trend generally north south although one zone in the south east appears to be orientated in a north easterly direction. The veins are hosted in outcrops of crowded feldspar porphyry or syenite which is intruding grey to black hornfelsed sedimentary rocks (siltstones and fine sandstones). The quartz systems can be traced for about 1.2 kilometres north south and for about .6 kilometres east west. New zones of mineralized quartz float and veining were found proximal to the original showings as well out from them. The anomalous zones are open to the north, south and west with the most promising areas being to the south and west.

Minerals noted in the quartz veins are galena, chalcopyrite and pyrite. The galena and pyrite are quite coarse although finer galena was noted at two locations in quartz veinlets. Analysis shows anomalous gold, silver, molybdenum and rare elevated antimony and bismuth.

Alteration noted was the hornfelsing of the sediments proximal to the contact with the syenites. In the southern area of the anomalous quartz veining one outcrop of syenite was noted to have large rip up clasts of the older sedimentary rocks (Photo #1). Unfortunately, due to the gentle relief of the property rock exposure is limited mainly to the gentle knolls and those areas in between have a thin layer of glacial outwash overlying a thin layer of till. Due to the fact that these layers are thin it seems to be apparent that the angular quartz float that has been located and sampled is likely very close to source.



Photo #1
(Syenite with rip up clasts of sedimentary rock)

In the anomalous zones the syenite is quite fractured and often flooded with tiny quartz veinlets. These fractures and veinlets tend to align in a north south direction. The quartz veins seen also align north south except for one vein in the south. The syenite body also is elongated north south and may represent an intrusive coming up a north south structure. Subsequent and continuous movement has caused the fracturing creating a fairly large area for deposition from the mineralizing fluids.

Summary: The Gold Cutter property is a relatively new discovery which has had only preliminary prospecting surveys carried out. The key elements of interest are gold and silver in at least three 'clusters' of quartz veins and veinlets hosted in outcrops of fractured syenite which intrudes hornfelsed sediments of Harper Ranch Group. The vein and veinlet clusters appear to be of sufficient size and continuity to warrant further exploration. Within these clusters the veins also




Photo #2

(North south fractured syenite)

appear to be close enough (possible stockworks) to each other to possibly allow an open bit bulk tonnage style of mining.

The values of gold are very good with many in the multigram range and silver had a number of samples exceeding 1 once per ton.

Recommendations:

- 1. Establish a geological base map using gps and compass for control. The proposed scale would be at least 1:5000.
- 2. Compile all historic data for the property and the region.

- 3. More prospecting is needed along the trend of showings, particularly to the south and north. Some work should also be done west of the anomalous zones.
- 4. Mechanical trenching to expose known showings as well as to explore the areas of low relief between the anomalous areas.
- 5. A series of short drill holes orientated to cross the known mineralized zones.

Ron Bilquist

15 September 2010

References:

- **GSC Memoir 363** by R.B. Campbell and H.W. Tipper, 1971
- **Open File** 2002-4 Geology of the Nehalliston Plateau by P. Shiarizza, S. Israel, S. Heffernan and J. Zuber, 2002.
- **ARIS # 27343** Prospecting Survey on the Gold Cutter Property (NAHA 1-4 Mineral Claims by Ron Bilquist, September 2003
- MinFile reference numbers 092P 017.

STATEMENT OF QUALIFICATIONS:

- I have worked full time in mining exploration since 1968 (42 years). During this time I have been self employed as a prospector as well as employed by numerous exploration companies on both salary and contract basis. My work has been primarily prospecting but duties from time to time have also included trenching, trench mapping, drilling and blasting, claim staking, line cutting and grid construction, geochemical surveys, geophysical surveys, geological mapping, draughting, diamond drilling and drill supervision. I have also been involved with project generation and research within regional projects and have worked with a wide variety of geological models and concepts.
- During my career I have prospected throughout Canada, the Yukon and NWT as well as Argentina and Mexico.
- I have written an exam to qualify as a prospector for the Department of Mines and Petroleum Resources. This exam took place at the department office in Nanaimo in 1975 and was supervised by W.C. Robinson, P. Eng.
- In 1992 I successfully completed the *Petrology for Prospectors Course* sponsored by the Ministry of Energy, Mines and Petroleum Resources: course instructor T.A. Richards, Ph.D.
- In 1994 I took a short course on Drift Exploration in glaciated and mountainous terrain put on by the BCGS Branch Short Course, Cordilleran Roundup; January 24, 1994.
- I have been on a number of mine tours; copper porphyries include Island Copper in B.C., Bingham and Silver Bell North in Utah and Nevada, Escondida, Zaldivar, Spence and Chuquicamata in Chile. I have had tours of a number of smell epithermal gold mines in the Carlin Trend of Nevada as well as the Skukum Mine in the south west Yukon.

Signed

Ronald J. Bilquist

Dated at Gabriola B.C. this

15th day of September, 2010

Cost Statement

Exploration Work type	Comment	Days			Totals
Personnel (Name)* / Position	Field Days (list actual days)	Days	Rate	Subtotal*	
Ron Bilquist	August 11 to 14 & 17 2009	5		\$2,000.00	
				\$2,000.00	\$2,000.00
Office Studies	List Personnel (note - Office onl	y, do no	t include	field days	
Literature search	Ron Bilquist	0.5	\$400.00	\$200.00	
Database compilation		0.5	\$400.00	\$200.00	
Computer modelling			\$0.00	\$0.00	
Reprocessing of data			\$0.00	\$0.00	
General research	Ron Bilquist	1.0	\$400.00	\$400.00	
Report preparation	Ron Bilquist	4.0	\$400.00	\$1,600.00	
Other (specify)					
				\$2,400.00	\$2,400.00
Ground Exploration Surveys	Area in Hectares/List Personnel				
Prospect	728.38 / Ron Bilquist	field exp	penditures a	above	
a	l • • •	N-	Rate	Cubbatal	
Geochemical Surveying	Number of Samples	No.		Subtotal	
Rock	20	20.0	\$39.74	NAME AND ADDRESS OF THE OWNER, WHEN PERSON O	4704 77
				\$794.77	\$794.77
Transportation	4	No.	Rate	Subtotal	
truck rental	Aug 11, 12, 13,14 & 17 2009	5.00			
kilometers	4. 42.42.0.44.2000	2.00	\$0.00	and the same of th	
ATV	Aug 12,13 & 14, 2009	3.00			
fuel			\$0.00		+ T 00 40
		ı		\$798.49	\$798.49
Accommodation & Food	Rates per day			1011.00	
Hotel	Aug 10 (77.97 Aug 11 - 14 (233.91)		\$0.00	\$311.88	
Meals	actual costs	West State of the	\$0.00	\$0.00	
				\$311.88	\$311.88
Miscellaneous			140.00	450.00	*
Telephone	sat phone rental	5.00	\$10.00	\$50.00	
Other (Specify)				\$50.00	\$50.00
Equipment Rentals				\$30.00	φ 3 0.00
Field Gear (Specify)	gps, digital camera	3.00	\$7.00	\$21.00	
Other (Specify)			1	,	
(,)				\$21.00	\$21.00
TOTAL Franchistres					¢6 276 14
TOTAL Expenditures					\$6,376.14

Appendix (i)

(i) Sample Preparation and Analysis:

The rock samples were placed in poly ore bags. Where possible a witness sample of each rock sample was retained and is available for viewing. The samples were shipped by Greyhound directly to Acme Laboratories Limited of Vancouver, British Columbia, an ISO 9001 accredited laboratory. Acme Laboratories is located at 1020 Cordova St. East Vancouver BC, V6A 4A3. Their phone number is (604) 253-3158. Included with the shipment of samples was a request for analysis by their Group G as well as 1DX1, a 36 element ICP analysis.

All samples were crushed, split and pulverized to a 200 mesh size and the samples were then analysed using ACME system Code G which is a Fire Assay fusion for Gold (30 gram) by ICP-ES followed by ACME system Code 1DX1 which is a 1:1:1 Aqua Regia Digestion ICP-MS analysis on .5 gram of the pulverized sample for 36 elements.

Appendix (ii)

(ii) Certificate of Analysis (following pages):



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client:

Vintage Prospecting

1410 Degnen Rd

Gabrilola BC V0R 1X7 Canada

VAN09003852.1

Submitted By:

Ron Bilquist

Receiving Lab:

Canada-Vancouver August 26, 2009

Received: Report Date:

September 10, 2009

Page:

1 of 2

CERTIFICATE OF ANALYSIS

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

CLIENT JOB INFORMATION

GOLD CUTTER Project: Shipment ID: P.O. Number

Number of Samples:

20

SAMPLE DISPOSAL

STOR-PLP STOR-RJT

Store After 90 days Invoice for Storage Store After 90 days Invoice for Storage

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To:

Vintage Prospecting 1410 Degnen Rd Gabrilola BC V0R 1X7 Canada

CC:

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200	20	Crush, split and pulverize rock to 200 mesh			VAN
G6	20	Fire Assay fusion Au by ICP-ES	30	Completed	VAN
1DX1	20	1:1:1 Aqua Regia digestion ICP-MS analysis	0.5	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.

*** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



1020 Cordova St. East Vancouver BC V6A 4A3 Canada Phone (604) 253-3158 Fax (604) 253-1716

Vintage Prospecting 1410 Degnen Rd

Gabrilola BC V0R 1X7 Canada

Project:

Client:

GOLD CUTTER

Report Date:

September 10, 2009

www.acmelab.com

Page:

2 of 2

CERTIFIC	CATE OF AN	JALY	'SIS													VA	NOS	0003	852	.1	
	Method	WGHT	G6	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Мо	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
	Unit	kg	gm/mt	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm
	MDL	0.01	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2
GC-0001	Rock		3.20	11.4	161.1	2285	65	41.0	10.9	3.5	321	1.37	<0.5	<0.1	1755	0.1	55	1.8	7.7	11.4	45
GC-0002	Rock		0.06	59.5	9.5	46.7	15	0.9	5.0	1.8	162	1,00	1.3	0.4	44.0	0.6	17	0.3	0.2	1.7	3
GC-0003	Rock		17.23	6.6	264.3	>10000	8	66.8	1.7	0.6	57	5.42	<0.5	<0.1	79159	0.2	39	0.3	1.2	32.6	Ę
GC-0004	Rock		0.27	0.6	926.3	3773	2	21.4	1.4	0.3	40	0.67	<0.5	<0.1	170.1	<0.1	4	0.9	1.7	7.5	<2
GC-0005	Rock		0.56	0.5	10.9	130.5	<1	6.1	1.1	0.3	24	0.47	<0.5	<0.1	793.0	<0.1	1	<0.1	0.2	0.4	<2
GC-0006	Rock		6.32	0.6	412.4	2442	7	14.1	2.1	0.6	71	0.60	<0.5	<0.1	11385	<0.1	6	1.0	0.6	6.1	<2
GC-0007	Rock		7.40	1.6	1801	8292	11	31.2	3.9	1.2	36	1.26	<0.5	<0.1	18115	<0.1	5	3.5	2.4	6.3	<2
GC-0008	Rock		1.49	94.3	13.5	136.6	8	12.1	5.1	3.7	143	1.60	<0.5	0.3	1135	0.2	22	0.2	0.4	0.7	<2
GC-0009	Rock		4.35	45.6	1458	3506	20	58.9	10.1	3.9	42	4.72	<0.5	<0.1	4023	<0.1	8	2.7	38.8	13.8	<2
GC-0010	Rock		0.73	3.7	152.6	3284	18	24.5	7.1	2.4	320	2.33	<0.5	<0.1	1388	0.1	30	3.2	1.0	37.2	4
GC-0011	Rock		0.57	3.5	19.2	208.7	1	7.5	1.0	0.2	23	0.60	1.2	<0.1	450.8	<0.1	1	<0.1	0.3	2.0	2
GC-0012	Rock		0.13	2.5	56.1	638,1	<1	2.6	1.2	0,2	28	0.22	<0.5	<0.1	147.7	<0.1	<1	0.1	1.0	1.8	<2
GC-0013	Rock		0.34	14.7	315.6	832.7	2	10.8	0.9	0,2	20	0.31	<0.5	<0.1	215.5	<0.1	2	0.2	8.9	1.5	<2
GC-0014	Rock		1.72	16.9	4.6	64.2	6	6.6	2.9	1.4	91	0.73	<0.5	<0.1	452.7	0.1	11	0.1	0.2	0.7	4
GC-0015	Rock		0.57	77.5	14.0	169.6	25	7.3	12.2	7.0	521	1.85	10,1	0.2	422.4	0.2	74	0.6	0.5	2.5	Ę
GC-0016	Rock		0.08	110.1	11.1	24.2	10	1.1	4.1	2.5	303	0.83	1.2	<0.1	53.2	<0.1	250	0.5	1.0	1.5	<2
GC-0017	Rock		6.18	293.9	3.6	3227	3	57.0	1.6	0.5	92	0.80	<0.5	<0.1	5712	<0.1	54	0.6	3.2	18.7	<2
GC-0018	Rock		0.11	9.1	18.4	25.5	38	0.9	7.4	8.4	369	2.85	6.8	0,2	82.4	0.6	117	0.3	0.3	0.7	18
GC-0019	Rock	The second secon	0.04	0.8	101.5	59.7	172	11.0	3.5	2.1	74	0.56	17.8	<0.1	15,1	<0.1	58	1.5	36.2	1.5	<2
GC-0020	Rock		0.35	148.6	5.8	35.1	10	3.9	3.9	1.9	216	0.65	<0.5	<0.1	215.8	0.3	19	0.3	0.3	1.0	



1020 Cordova St. East Vancouver BC V6A 4A3 Canada Phone (604) 253-3158 Fax (604) 253-1716

Client:

Vintage Prospecting

1410 Degnen Rd

Gabrilola BC V0R 1X7 Canada

Project:

GOLD CUTTER

Report Date:

September 10, 2009

www.acmelab.com

Page:

2 of 2

CERTIE	CATE OF AN	JALY	'SIS													VA	/V/08	003	852
	Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Ca	P	La	Cr	Mg	Ba	Ti	8	Al	Na	K	W	Hg	Sc	TI	s	Ga	Se
	Unit	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm
	MDL	0.01	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5
GC-0001	Rock	0.25	0.008	1	45	0.30	94	0.024	<20	0.29	0.010	0.23	<0.1	0.04	3.2	0.1	0.64	2	11.0
GC-0002	Rock	0.08	0.022	3	18	0.03	73	<0.001	<20	0.07	0.031	0.03	0.2	<0.01	1.1	<0.1	0.23	<1	<0.5
GC-0003	Rock	<0.01	0.021	<1	24	0.01	88	0.008	<20	0.07	0.042	0.45	0.1	0.19	0.2	<0.1	1.60	<1	52.0
GC-0004	Rock	<0.01	<0.001	<1	40	<0.01	10	<0.001	<20	<0.01	0.001	<0.01	<0.1	0.02	<0.1	<0.1	0.29	<1	15.4
GC-0005	Rock	<0.01	<0.001	<1	33	<0.01	6	<0.001	<20	<0.01	<0.001	0.01	<0.1	<0.01	<0.1	<0.1	0.14	<1	1.3
GC-0006	Rock	0.02	<0.001	<1	41	<0.01	4	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.02	0.2	<0.1	0.32	<1	11.1
GC-0007	Rock	<0.01	<0.001	<1	34	<0.01	12	<0.001	<20	<0.01	<0.001	<0.01	<0.1	0.05	<0.1	<0.1	1.07	<1	27.5
GC-0008	Rock	0.06	0.017	2	32	0.02	59	0.001	<20	0.06	0.027	0.04	0.1	<0.01	1.3	<0.1	0.60	<1	1.7
GC-0009	Rock	0.04	<0.001	<1	39	<0.01	14	<0.001	<20	<0.01	<0.001	0.01	0.1	0.15	<0.1	<0.1	4.68	<1	22.3
GC-0010	Rock	0.15	<0.001	6	35	0.04	89	<0.001	<20	0.01	<0.001	<0.01	<0.1	0.03	<0.1	<0.1	1.91	<1	16.9
GC-0011	Rock	<0.01	<0.001	<1	24	<0.01	14	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	1.2
GC-0012	Rock	<0.01	0.002	<1	40	<0.01	2	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	3,1
GC-0013	Rock	<0.01	0.001	<1	31	<0.01	4	<0.001	<20	<0.01	<0.001	0.01	<0.1	0.02	<0.1	<0.1	0.11	<1	2.7
GC-0014	Rock	0.06	0.011	<1	32	0.04	26	0.002	<20	0.06	0.005	0.04	<0.1	0.02	0.6	<0.1	0.06	<1	<0.5
GC-0015	Rock	0,06	0.007	<1	33	0.12	243	0.005	<20	0.24	0.002	0,07	0.2	0.01	2.7	<0.1	0.40	<1	1.3
GC-0016	Rock	1.13	0.008	<1	26	0.07	108	<0.001	<20	0.04	0.006	0.01	0.3	<0.01	1.6	<0.1	0.21	<1	<0.5
GC-0017	Rock	0.32	0.005	<1	24	<0.01	17	<0.001	<20	<0.01	<0.001	<0.01	0.3	0.03	0.8	<0.1	0.08	<1	10.6
GC-0018	Rock	0.61	0.079	3	17	0.32	98	0.022	<20	0.28	0.059	0.18	0.3	<0.01	3.6	<0.1	0.88	1	0.8
GC-0019	Rock	0.14	0.002	<1	32	0.07	15	<0.001	<20	0.04	<0.001	0.02	<0.1	0.03	1.0	<0.1	0.12	<1	<0.5
GC-0020	Rock	0.13	0.014	2	27	0.03	43	<0.001	<20	0.04	0.011	0.01	0.1	<0.01	0.8	<0.1	0.15	<1	<0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada Phone (604) 253-3158 Fax (604) 253-1716 Client:

Vintage Prospecting

1410 Degnen Rd

Gabrilola BC V0R 1X7 Canada

Project:

GOLD CUTTER

Report Date:

September 10, 2009

www.acmelab.com

Page:

1 of 1

QUALITY CO	NTROL	REF	ORT													VA	N 09	003	352.	1	
	Method	WGHT	G6	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Wgt	Au	Мо	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
	Unit	kg	gm/mt	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppb	ppm	ppm	ppm	ppm	ppm	ppm
	MDL	0.01	0.01	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.5	0.1	0.5	0.1	1	0.1	0.1	0.1	2
Pulp Duplicates																					
GC-0002	Rock		0.06	59.5	9.5	46.7	15	0.9	5.0	1.8	162	1.00	1.3	0.4	44.0	0.6	17	0.3	0.2	1.7	3
REP GC-0002	QC		0.03					-													
GC-0020	Rock		0.35	148.6	5.8	35.1	10	3.9	3.9	1.9	216	0.65	<0.5	<0.1	215.8	0.3	19	0.3	0.3	1.0	3
REP GC-0020	QC		0.42																		
Reference Materials																					
STD DS7	Standard			22.0	106.3	65.8	390	8.0	54.9	9.3	658	2.49	55.0	4.9	50.4	4.1	71	6.5	3.7	4.5	83
STD DS7	Standard		•	20.8	97.6	63.2	379	0.7	50.7	8.5	601	2.30	51.9	4.9	43.9	4.2	78	6.8	3.9	5.0	75
STD OREAS45PA	Standard			0.9	606.2	17.8	120	0.3	304.2	109.5	1120	16.30	4.3	1.1	56.0	6.2	14	<0.1	<0.1	0.2	228
STD OREAS45PA	Standard			0.8	587.8	18.7	124	0.2	269,3	96.9	1088	16.42	3.9	1.2	35.3	6.5	14	0.1	<0.1	0.2	215
STD OXH55	Standard		1.31							A DOMESTIC OF THE PARTY OF THE											
STD OXH55	Standard		1.29																		
STD OXK69	Standard		3.58																		
STD OXK69	Standard		3.61																		
STD DS7 Expected				20.5	109	70.6	411	0.9	56	9.7	627	2.39	48.2	4.9	70	4.4	69	6.4	4.6	4.5	84
STD OREAS45PA Expected				0.9	600	19	119	0.3	281	104	1130	16.559	4.2	1.2	43	6	14	0.09	0.13	0.18	221
STD OXH55 Expected			1.282																		
STD OXK69 Expected			3.583																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2
BLK	Blank		<0.01																		
BLK	Blank		<0.01																		
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<0.01	<0.5	<0.1	<0.5	<0.1	<1	<0.1	<0.1	<0.1	<2
BLK	Blank		<0.01																		
BLK	Blank		<0.01																		
Prep Wash																					
G1	Prep Blank		<0.01	0.3	10.4	3.8	48	<0.1	3.7	4.3	552	1.90	0.6	1.8	<0.5	5.7	62	<0.1	<0.1	<0.1	3
G1	Prep Blank		<0.01	0.2	5.5	4.0	46	<0.1	3.1	3.8	512	1.85	<0.5	1,5	<0.5	4.7	52	<0.1	<0.1	0.1	. 3



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada Phone (604) 253-3158 Fax (604) 253-1716

Client:

Vintage Prospecting

1410 Degnen Rd

Gabrilola BC V0R 1X7 Canada

Project:

GOLD CUTTER

Report Date:


September 10, 2009

www.acmelab.com

Page:

1 of 1

QUALITY CON	NTROL	REP	ORT													VA	N090	103	352
	Method	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
	Analyte	Ca	P	La	Cr	Mg	Ва	Ti	В	Al	Na	K	w	Hg	Sc	TI	s	Ga	Se
	Unit	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm
	MDL	0.01	0.001	1	1	0.01	1	0.001	20	0.01	0.001	0.01	0.1	0.01	0.1	0.1	0.05	1	0.5
Pulp Duplicates						-													
GC-0002	Rock	0.08	0.022	3	18	0.03	73	<0.001	<20	0.07	0.031	0.03	0.2	<0.01	1.1	<0.1	0.23	<1	<0.5
REP GC-0002	QC																		
GC-0020	Rock	0.13	0.014	2	27	0.03	43	<0.001	<20	0.04	0.011	0.01	0.1	<0.01	8.0	<0.1	0.15	<1	<0.5
REP GC-0020	QC																		
Reference Materials																			
STD DS7	Standard	0.96	0.078	12	211	1.03	402	0.116	44	1.06	0.101	0.47	3.3	0.18	2.2	4.0	0.20	5	3.4
STD DS7	Standard	0.86	0.086	12	190	0.97	424	0.109	33	0.96	0.096	0.47	3.4	0.20	2.1	4.1	0.18	5	3.5
STD OREAS45PA	Standard	0.22	0.034	16	824	0.09	182	0.119	<20	3.45	0.009	0.07	<0.1	0.03	38.8	<0.1	<0.05	16	<0.5
STD OREAS45PA	Standard	0.24	0.034	16	758	0.10	203	0.120	<20	3.26	0.007	0.07	<0.1	0.03	39.4	<0.1	<0.05	18	<0.5
STD OXH55	Standard																		
STD OXH55	Standard			***************************************															
STD OXK69	Standard																		
STD OXK69	Standard																		
STD DS7 Expected		0.93	0.08	12	179	1.05	370	0.124	39	0.959	0.089	0.44	3.4	0.2	2.5	4.2	0.19	5	3.5
STD OREAS45PA Expected	A10.000	0.2411	0.034	16.2	873	0.095	187	0.124		3.34	0.011	0.0665	0.011	0.03	43	0.07	0.03	16.8	0.54
STD OXH55 Expected																			
STD OXK69 Expected	The second secon					,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,													
BLK	Blank	<0.01	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank																		
BLK	Blank																		
BLK	Blank	<0.01	<0.001	<1	<1	<0.01	<1	<0.001	<20	<0.01	<0.001	<0.01	<0.1	<0.01	<0.1	<0.1	<0.05	<1	<0.5
BLK	Blank						NAME OF THE OWNER O												
BLK	Blank										,								
Prep Wash																			
G1	Prep Blank	0.52	0.085	13	13	0.55	187	0.122	<20	0.90	0.081	0.50	1.2	<0.01	1.9	0.3	<0.05	5	<0.5
G1	Prep Blank	0.51	0.091	10	12	0.55	174	0.112	<20	0.85	0.068	0.50	0.1	<0.01	1.8	0.3	<0.05	4	<0.5




<u>Gold Cutter -select analysis</u> (for complete analysis see Certificate of Analysis)


Samp #	Au	Мо	Cu	Pb	Zn	Ag	Fe	Au	Sb	Bi	Ва	Hg
	GM/T	PPM	PPM	PPM	PPM	PPM	%	PPB	PPM	PPM	PPM	PPM
GC0001	3.2	11.4	161.1	2284.9	65	41	1.37	1755.2	7.7	11.4	94	0.04
GC0002	0.06	59.5	9.5	46.7	15	0.9	1	44	0.2	1.7	73	<0.01
GC0003	17.23	6.6	264.3	>10000.0	8	66.8	5.42	79159.5	1.2	32.6	88	0.19
GC0004	0.27	0.6	926.3	3772.8	2	21.4	0.67	170.1	1.7	7.5	10	0.02
GC0005	0.56	0.5	10.9	130.5	<1	6.1	0.47	793	0.2	0.4	6	<0.01
GC0006	6.32	0.6	412.4	2441.6	7	14.1	0.6	11385.5	0.6	6.1	4	0.02
GC0007	7.4	1.6	1801.3	8291.8	11	31.2	1.26	18115.3	2.4	6.3	12	0.05
GC0008	1.49	94.3	13.5	136.6	8	12.1	1.6	1135.2	0.4	0.7	59	<0.01
GC0009	4.35	45.6	1458.2	3506.5	20	58.9	4.72	4022.6	38.8	13.8	14	0.15
GC0010	0.73	3.7	152.6	3284	18	24.5	2.33	1387.9	1	37.2	89	0.03
GC0011	0.57	3.5	19.2	208.7	1	7.5	0.6	450.8	0.3	2	14	<0.01
GC0012	0.13	2.5	56.1	638.1	<1	2.6	0.22	147.7	1	1.8	2	<0.01
GC0013	0.34	14.7	315.6	832.7	2	10.8	0.31	215.5	8.9	1.5	4	0.02
GC0014	1.72	16.9	4.6	64.2	6	6.6	0.73	452.7	0.2	0.7	26	0.02
GC0015	0.57	77.5	14	169.6	25	7.3	1.85	422.4	0.5	2.5	243	0.01
GC0016	0.08	110.1	11.1	24.2	10	1.1	0.83	53.2	1	1.5	108	<0.01
GC0017	6.18	293.9	3.6	3227.2	3	57	0.8	5712.4	3.2	18.7	17	0.03
GC0018	0.11	9.1	18.4	25.5	38	0.9	2.85	82.4	0.3	0.7	98	<0.01
GC0019	0.04	0.8	101.5	59.7	172	11	0.56	15.1	36.2	1.5	15	0.03
GC0020	0.35	148.6	5.8	35.1	10	3.9	0.65	215.8	0.3	1	43	<0.01

Gold Cutter Rock Descriptions

Samp #	Description
GC0001	prox white qtz flt near old sample K234; pyrite and galena
GC0002	prox qtz flt; pyrite; recent logged area
GC0003	qtz in tree root w/lg (1 cm) boxworks; galena and pyrite
GC0004	prox qtz flt; galena and chalcopyrite
GC0005	subcrop white qtz w/py and trace galena; boxworks
GC0006	subcrop white qtz w/galena, pyrite +/- chalcopyrite
GC0007	subcrop white qtz w/pyrite, chalcopyrite and galena
GC0008	subcrop tan to buff colored qtz; limonite, pyrite and trace galena
GC0009	in fire break; subcrop white qtz w/pyrite, galena and chalcopyrite
GC0010	multiple prox flt w/pyrite, chalcopyrite and galena
GC0011	multiple prox flt w/pyrite, chalcopyrite and galena
GC0012	white to rosy subcrop qtz w/occas galena and pyrite
GC0013	prox white to rosy qtz w/occas pyrite, galena; syenite w/metamorph
GC0014	prox white-buff qtz; occas pyrite
GC0015	o/c white qtz w/occas pyrite and rare galena; same loc (?) as R304
	east side same o/c; similar w/no visible galena
	same o/c between last two samples; pyrite and galena
	o/c of white qtz w/limonite, pyrite
	white qtz subcrop; pyrite and trace galena
	white to grey qtz w/occas pyrite



GEOLOGICAL SURVEY BRANCH ASSESSMENT REPORT



Gold Cutter	Property	y .
Dun ein e alt e it	n a	LIBUNUN BX

Prospectors Map

Tenure #'s 612004 & 612063

DRAWING NUMBER