

Ministry of Forests, Mines and Lands  
BC Geological Survey

**ASSESSMENT REPORT**  
**TITLE PAGE AND SUMMARY**

TECHNICAL REPORT

TITLE OF REPORT [type of survey(s)] <u>REPORT ON 2010 DIAMOND DRILLING ON THE 97 BEV</u>	TOTAL COST <u>\$31,105.00</u>
---	----------------------------------

AUTHOR(S) CHRISTOPHER D. WHATLEY SIGNATURE(S) Chris Whatley

NOTICE OF WORK PERMIT NUMBER(S)/DATE(S) MX-5-503 1630046 YEAR OF WORK 2010

STATEMENT OF WORK - CASH PAYMENT EVENT NUMBER(S)/DATE(S) 4807649 START: 2010/JUN/18

STOP: 2010/NOV/02

PROPERTY NAME GOLD HILL / WATERLOO

CLAIM NAME(S) (on which work was done) 97 BEV, TENURE No. 359678

CORE SAMPLES (CUT) AND LOGGING OF CORE / 5150 14<sup>TH</sup> AVE HWY. 97 O.K. FALLS  
CORE STORED AT THIS LOCATION.

COMMODITIES SOUGHT AU, CU, NI, TALC, MAGNESIUM CARBONATE, AG, ZN, PT, PD,

MINERAL INVENTORY MINFILE NUMBER(S), IF KNOWN UNKNOWN

MINING DIVISION GREENWOOD NTS 82 E

LATITUDE 49 ° 8 ' 9 " LONGITUDE 119 ° 10 ' 59 " (at centre of work)

OWNER(S)

1) REGISTERED - CHRISTOPHER D. WHATLEY FMC NO. 128719 \* 2) BARRY SHERMAN

MAILING ADDRESS <u>PO. Box 197 O.K. FALLS B.C.</u> <u>VOH-1R0 1-250-497-5762</u>	<u>174 - 321 YORKTON AVE.</u> <u>PENTICTON B.C.</u> <u>V2A 3V6</u>
--	--

OPERATOR(S) [who paid for the work]

1) D. W. HERRISON 2) CHRISTOPHER D. WHATLEY

MAILING ADDRESS

<u>SITE 15, COMP. 4 R.R. 1</u> <u>CAWSTON, B.C. V0X 1C0</u>	<u>P.O. Box 197 O.K. FALLS B.C.</u> <u>5150 14<sup>TH</sup> AVE HWY 97 V0H-1R0</u>
--	---

PROPERTY GEOLOGY KEYWORDS (lithology, age, stratigraphy, structure, alteration, mineralization, size and attitude): SIZE UNDETERMINED

ANARCHIST GROUP, GREENSTONE, ARGILLITE, QUARTZITE, TUFF, KNOWN,  
SOAPSTONE (STEARITE), TALC, MAGNESIUM CARBONATE, DIORITE, QUARTZ VEIN,  
MASSIVE SULPHIDES (PYRRHOTITE, MAGNETITE, PYRITE), CHALCOPYRITE, TUNGSTON,  
SPHALERITE, BORNITE, GALENA, GOLD, CHLORITE, IRON - RARE EARTH ELEMENTS (PT, PE, TA, ZF)

REFERENCES TO PREVIOUS ASSESSMENT WORK AND ASSESSMENT REPORT NUMBERS 13768, 16168, 25789  
26133, 29300, 30371, 31225

TYPE OF WORK IN THIS REPORT	EXTENT OF WORK (IN METRIC UNITS)	ON WHICH CLAIMS	PROJECT COSTS APPORTIONED (incl. support)
<b>GEOLOGICAL (scale, area)</b>			
Ground, mapping			
Photo interpretation			
<b>GEOPHYSICAL (line-kilometres)</b>			
Ground			
Magnetic			
Electromagnetic			
Induced Polarization			
Radiometric			
Seismic			
Other			
Airborne			
<b>GEOCHEMICAL</b>			
(number of samples analysed for ...)			
Soil			
Silt			
Rock			
Other			
<b>DRILLING</b>			
(total metres; number of holes, size)			
Core	162.16 m, 2 HOLES, NQ	97 BEV, NO. 359678	\$ 23,580
Non-core	TRUCKS, MOTORHOME, BULLDOZER	FOR DRILLING OF	\$ -7,525
<b>RELATED TECHNICAL</b>			
PREPARE REPORT 97 BEV			
Sampling/assaying	26 SAMPLES DRILL CORE CUT WITH ROCK SAW	ACME LABS VAN. BC.	PAID BY
Petrographic	DRILL CORE STORED		THIRD PARTY
Mineralographic	AT C. WHATLEY PROPERTY		COST NOT
Metallurgic	IN O.K. FALLS, 5150, 14 <sup>TH</sup> AVE, HWY 97.		INCLUDED.
<b>PROSPECTING (scale, area)</b>			
NO CHARGE			
<b>PREPARATORY/PHYSICAL</b>			
Line/grid (kilometres)			
Topographic/Photogrammetric (scale, area)			
Legal surveys (scale, area)			
Road, local access (kilometres)/trail			
Trench (metres)			
Underground dev. (metres)			
Other			

TOTAL COST CLAIMED \$ 31,105.<sup>00</sup>/<sub>XX</sub>

**Report on 2010 Diamond Drilling**  
*On the*  
**97 Bev Claim,**  
**Gold Hill Group**

**Greenwood Mining Division**  
**British Columbia, Canada**

**NTS 82E/3E**

**BC Geological Survey**  
**Assessment Report**  
**31955**

**BCGS Map Sheet 082E015**

**Latitude 49° 08' 09" N      Longitude 119° 10' 59" W**

**Claim Worked On: 97 Bev, Tenure No. 359678**

**Owner: Christopher D. Whatley, FMC No. 128719**  
**P.O. Box 197**  
**Okanagan Falls, British Columbia**  
**V0H1R0**

**Permittee: C. D. Whatley, FMC No. 128719**  
**P.O. Box 197**  
**Okanagan Falls, British Columbia**  
**V0H1R0**

**&**  
**Operator: D. W. Herbison**  
**Site 15, Comp. 4, RR1**  
**Cawston, British Columbia**  
**V0X1C0**

**Report by Owner: Christopher D. Whatley, FMC No. 128719**  
**P.O. Box 197**  
**Okanagan Falls, British Columbia**  
**V0H1R0**

**December 9, 2010**

## Table of Contents

	P a g e
<b>Introduction</b> .....	1
Summary, claims and Ownership.....	1
Location, Physiograph, Access.....	1
History.....	1
Economic Assessment.....	2
<b>Geological Setting</b> .....	2
Regional and Local Geology.....	2
Property Mineralization.....	2
<b>Claim Information</b> .....	3
<b>Technical Data and Interpretation</b> .....	3
Purpose of work.....	3
Fieldwork Done.....	3
Analysis.....	3
Results.....	3
<b>Interpretation and Conclusions</b> .....	4
<b>References</b> .....	5
<b>Statement of qualifications</b> .....	6
<b>Table: 97 Bev Claim Information</b> .....	3

page

## List of Figures

	Following page :
<b>Figure 1:</b> Location Map, Camp McKinney.....	1
<b>Figure 2:</b> Index Map, 97 Bev Claim, Gold Hill Group, 1:250,000.....	1
<b>Figure 3:</b> Claim Map, 1:50,000.....	3
<b>Figure 4:</b> Site Plan with Locations of DDHs 1,2,3,3a,3c,4,5,6 with respect to local roads and workings 1:2,500.....	3
<b>Figure 5:</b> Section along DDH Talc #3C 1:500.....	3
<b>Figure 6:</b> Section along DDH Talc #6 1:500.....	3
<b>Appendix 1:</b> Expenditures Statements	
<b>Appendix 2:</b> Drillcore logs, Talc #3C and Talc #6	
<b>Appendix 3:</b> ACME assay results	

## Introduction

### Summary

This report was prepared for submission to the British Columbia Ministry of Energy and Mines as an Assessment Report, in support of a Statement of Work (Event Number 4807649) filed for work done on the 97Bev claim, tenure number 359678, which is part of the Gold Hill Group, situated in the Greenwood Mining Division. The costs being claimed for assessment credit relate to a diamond-drilling program completed in July of 2010 on the 97 Bev Claim, on behalf of C.D. Whatley, FMC No. 128719, of Okanagan Falls, B.C., who is owner of record for all claims in the Gold Hill Group. Fieldwork consisted of 162 meters of NQ diamond drilling, in two inclined holes. The drilling was conducted under Work Permit MX-5-503; operators were C.D. Whatley and D.W. Herbison, of Cawston, B.C.

### Location, Physiography, Access

The 97 Bev claim is located from 2 to 3 km north of the Cariboo-Amelia vein system at Camp McKinney, (see Figure 1). Rock Creek runs southerly through the center of the claim. Elevations range from 1215 to 1500 metres. The claim is forested with coniferous trees and has been partly logged. The claim is about 27 kilometres east-southeast of Oliver, and 15 kilometres north of the U.S. border in the southern interior of B.C. (Figure 1). The 97 Bev Claim is centered at 49° 8' 21" north latitude, and 119° 10' 26" west longitude (see Index Map, Figure 2).

The property may be accessed from Oliver, B.C. via a good two-lane gravel road, which also provides access for logging, for local residents, and for the Mt. Baldy ski area. This road continues 12 km to the southeast, where it links to Highway 3 at the Rock Creek Canyon Bridge.

### History


Camp McKinney is a well-known old gold mining camp. Placer gold was mined nearby, from Rock Creek and its tributaries, as early as 1860. Lode gold was found on upper Jolly Creek in 1884, and the Cariboo Vein was discovered three years later. Successful underground gold-silver mining operations were conducted intermittently on the Cariboo-Amelia vein system between 1894 and 1962.


Although some claims were located in the 97Bev area during the early search for gold ore in the Camp McKinney area, evidently little of lasting interest was found. Some trenching was done, but no records of this work are known. In 1985, an airborne VLF-electromagnetic and magnetometer survey was carried out over Camp McKinney that included the Bev97 area and indicated anomalous responses there (Assessment Report No. 13768). There is no record of any ground follow-up. In 1998 and 1999, brief field programs were conducted to examine old workings and alteration zones in the area; rock chip samples collected from these areas were assayed (Assessment Report Nos. 25789 and 26133).

A deposit of massive talc (soapstone, or steatite) occurs on the claim. Between 2003 and 2005, a small tonnage of soapstone was removed, to be used for the carving of sculptures. In 2004, a diamond drill hole, Talc #1, was drilled through the western (upper) talc body. From the surface, this hole intersected 70 metres (230') of talc.

In June 2007, two inclined NQ diamond drill holes, Talc #2 and Talc #3, were drilled to test two mineralized areas. A total of 89.8 metres (295 feet) of drilling was done (Assessment Report No. 29300). Later in 2007, Talc #3 was extended to 68 metres (223'). This extension was not logged; a few samples were later taken from the interval for analysis in 2008.

In May 2008 one NQ diamond drill hole, Talc #4, was drilled to further investigate promising mineralization found in Talc #3. In 2009, two more NQ drill holes ( talc-3A and talc-5 ) were






WASHINGTON

30'

15'

Oroville 10 km

Scale



Index Map

97 Bev Claim

Gold Hill Group

Scale 1 : 250,000

Drawn: W. J. Wilkinson

September, 2007

Figure 2

drilled, (see report #31225). The two holes drilled, were to investigate and delineate the massive sulphide zones and the intervals with gold content in d.d.h. Talc #3 Although the upper sulphide zone was traced to the north-west, the gold values were not repeated.(possible nugget effect?).

#### Economic Assessment

The Gold Hill Group occupies ground that was first explored in the 1880s. On the Waterloo Claim, high-grade gold ore was mined from stopes on three levels to a depth of 260'. On adjoining claims, the "Cariboo-Amelia" vein system was a substantial and successful underground gold mine, which was operated intermittently from 1894 to 1962. A main power line passes through Camp McKinney two kilometres south of the 97 Bev claim. Road access is good. Small creeks in the near vicinity should support exploration work, and an adequate water supply for mine operations should be available within the area.

The 97 Bev claim is of economic interest because of the presence of bodies of soapstone (steatite). Little exploration for metallic ore has been done. The claim could conceivably host a strong gold quartz vein system comparable to the nearby Cariboo-Amelia system. The massive sulphide (m.s.) mineralization found in hole Talc #3 is worth further investigation. Talc #4 did not intersect this m.s. mineralization, suggesting that if present, continuity in the m.s. is aligned with bedded metasediments dipping toward the north (see Figure 5).

#### Geological Setting

##### Regional and Local Geology

Camp McKinney lies within a relatively small (roughly 14 km by 5 km) window of metamorphosed sedimentary and volcanic Paleozoic rocks of the Anarchist Group, which is bounded to the south, west, north and northeast by very extensive Jurassic intrusives, and to the east by Eocene volcanics. A minor component of the metamorphosed Paleozoic rocks are small bodies of serpentized ultrabasic rocks.

Gold occurs in quartz veins, associated predominantly with iron pyrite, but free gold has been reported. Sulphide mineralization is sparse; a little sphalerite and galena, with traces of chalcopyrite, (tetrahedrite, pyrrhotite) occur with the pyrite. The veins occur within argillic quartzites and andesitic volcanics.

In the Cariboo-Amelia Mine, the vein was described as a near-vertical fissure vein oriented nearly east-west, essentially perpendicular to the strike of the wallrocks. Good ore shoots tended to occur where the vein traversed the volcanic rocks, which provided more competent boundaries, presumably facilitating the concentration of gold deposition within the main fissure ("The Camp McKinney Gold Mine", by H.L. Hill and L.P. Starck).

##### Property Mineralization

The 97 Bev claim hosts a relatively large body of soapstone, which is currently of economic interest. Soapstone of carving quality is also present. A mineralized quartz vein was exposed by roadwork. A gossan situated just south of the soapstone has been shown (Talc #3, 2007), to be underlain by several massive sulphide (horizons?), within the metamorphic rocks, containing potentially significant metal values, particularly in copper. Potentially significant gold assays were obtained from two previously unsampled intervals of Talc #3 in sampling done by Kinross Gold Corporation geologists in 2008.



### Claim Information

The 97 Bev Claim is a 450 hectare Four Post Claim. The claim expiry date shown below is pending acceptance of this Report.

**Table: 97 Bev Claim Information (Where work was done)**

<u>Claim Name</u>	<u>Tenure No.</u>	<u>Type</u>	<u>Area (Ha.)</u>	<u>Expiry Date</u>	<u>Registered Owner</u>
97 Bev	359678	4 Post	450	2013/Oct/02	Christopher D. Whatley

### Technical Data and Interpretation

#### Purpose of the work

The work was to twin drill hole Talc #3, as the 2009 drill hole Talc #3A, oriented towards drill hole Talc #4, was not parallel to Talc #3. Drill hole Talc #3 intersected massive sulphide and two intervals of potentially significant gold content (see assessment report #31225 and 29300.), and to delineate the massive sulphide zones.

#### Fieldwork done

Fieldwork consisted of two surface NQ diamond drill holes. Talc #3C, Azimuth 192\*, inclination -55\*, 2 meters north (192\*) of collar for drill hole Talc #3 (2007). The Drill hole, Talc #6 was Drilled to a depth of 62.5 meters. The second diamond drill hole drilled was Talc #6, azimuth 266\*, inclination -55, to a depth of 99.66 meters. The collar for drill hole Talc #6 is located 20 meters north (360\*), then 15 meters west (270\*) of the collar for drill hole Talc #3 (2007).

The work was started June 18 / 2010 and the drilling was completed July 4/2010, with a total of 9 days of work. The drilling was done by -Dwight Herbison, Cawston B.C.- Chris Whatley, Okanagan Falls B.C.- and Glen MacDonald, Penticton B.C. . The diamond drill core is stored on the Whatley property in O.K.Falls. Address - 5150 -14th Ave. Hyw.97 -O.K.Falls B.C. V0H 1R0 . The holes were drilled with a Boyles 14 ,with NQ steel. No Dip Tests were conducted in the drilling of the two drill holes.

#### Analysis


Sampling was carried out with both drill holes. Eleven samples from drill hole -Talc #3C ,and fifteen samples from drill hole - Talc #6 . The samples were assayed by ACME Labs. Vancouver B.C. . The analytical procedures are : FA fusion for Au Pt Pd, for 23 samples - AR digestion ICP-ES for 23 samples and-Whole Rock Analysis Majors and Trace Elements For 3 samples. These three samples are of the Talc /Steatite & Magnesium carbonate, encountered at the lower end of drill hole - Talc #6 .

#### Results

Drill hole Talc #3C intersected the same Anarchist metasedimentary rocks found in drill hole Talc #3 (greenstone, argillite, argillic hornfels) highly fractured and healed with quartz, intersected by diorite dikes, with some intervals of vein quartz. The massive sulphide found in Talc #3 was encountered in Talc #3C only located at the top (start of) the hole. This was not assayed as it had previously been done. The sampling of Talc #3C returned poor results for gold . The Kinross assays were not repeated, possible nugget effect ?. Drill hole Talc #6 did not encounter the massive sulphide and I believe that the hole was located too far west. Talc #6 intersected the same rock as above, less the M.S. and unexpectedly encountered The Talc/ Magnesium deposit. The whole rock assays came from the end (99 m.) of the hole.








Bev97 Claim, Gold Hill Group  
Drill Holes Talc #6

Section Along DDH : Talc #6  
With Geology

Scale 1:500 | December, 2010 | Drawn: WHATLEY.C | Figure 6



ddh Talc#6 2010

97 BEV  
359678

NORTH 82E/015  
SEP. 24 - 28 2005

SOAP STONE  
TALC (STEATITE)

	KNOWN CONTACT
	ASSUMED CONTACT
	TRENCH (OLD)
	PIT (OLD)
	TEST PIT MX5-501
	DD.HOLE MX5-503

0m 25m 50m 75m 100m




Figure 4: Site Plan  
Showing Location of DDH's Talc 3C - Talc 6  
With Respect To Local Roads and Workings  
Scale 1:2500 September, 2010

### Interpretation and Conclusions

Talc #3C was drilled 2 meters, on strike and dip, from Talc #3, which intersected 3 zones of massive sulphide with elevated levels of copper. Talc #3 also has 2 separate locations sampled with significant gold assays. The intervals sampled in Talc#3C did not reproduce the assays. It appears the hole was stopped short of the lower gold interval in Talc#3 (see figure #5). All the assays for gold were very low. The massive sulphide in Talc #3C was intersected only in the upper level of the hole, but the Iron content in the assays shows significant values in most of the samples with copper values (low), increasing with Iron % collectively. No dip tests were performed .

Talc #6 was drilled to investigate a magnetic high believed to be associated with the massive sulphide located in the other holes. No massive sulphide was intersected in this hole. I believe this hole was located too far west, and drilled away from the m.s. This hole (see figure 6) intersected mainly Greenstone and Diorite dykes similar to Talc #4 .The #6 hole and #4 hole could be showing strike and dip of the rock bedding. A three dimensional model of the drill holes with m.s. intervals delineated, would be useful for better locating drill targets to trace the massive sulphide. It was unexpected to intersect the talc at the bottom of talc 6. The size of the Talc (steatite) body keeps tending to be larger than thought. The size is undetermined, but more than 1 km long / 250-300m wide and has potential with nickel values found up to 1900 ppm. and magnesium carbonate (still under testing) in the 40% range. Drilling some deep (1000' and greater) holes below the talc to investigate the hydrothermal feed, has great potential for the presence of a large nickel and/or copper/gold deposit .

### References

- Hedley, M.S. (1940): Geology of Camp McKinney and of the Cariboo-Amelia Mine, *British Columbia Department of Mines, Bulletin No. 6*.
- Hill, H.L., and Starck, L.P.: The Camp McKinney Gold Mine, *A paper presented ... (at the) ... 66<sup>th</sup> Annual Convention, Northwest Mining Association, Spokane, Washington, 1960*.
- Little, H.W. (1957): Kettle River, B.C., Sheet 82E (West Half), *Geological Survey of Canada, Map 15-1961*.
- Miller, R.E., (1998): Geological Report on the 97 Bev Claims, Caramelia Project, *Assessment Report Number 25789*
- Miller, R.E., (1998): Geological Report on the 97 Bev Group, Caramelia Project, *Assessment Report Number 26133*
- Minfile, (2004): Capsule Geology and Bibliography, 082ESW020 (Cariboo-Amelia Mine), *Government of British Columbia Ministry of Energy and Mines, Minfile Website*  
<http://www.em.gov.bc.ca/Mining/Geolsurv/Minfile>
- Peto, Peter, (1986): Geological and Geophysical Assessment Report on the Gold Hill Group, *Assessment Report Number 16168*
- Pezzot, E.T. and White, G.E., (1985): Geophysical Report on an Airborne VLF-Electromagnetometer and Magnetometer Survey, Inkameep, Kettle, Pictou, North Star Claims, *Assessment Report Number 13768*
- Tempelman-Kluit, D. J. (1989): Geology, Penticton, British Columbia, *Geological Survey of Canada, Map 1736A, scale 1:250,000*
- Whatley, C.D. (2007; 2008): personal communications and private papers; Kinross data.
- Wilkinson, W.J. (2006): Diamond Drilling Report on the Waterloo Claim, Gold Hill Group, *Assessment Report Number 28526*
- Wilkinson, W.J. (2007): Diamond Drilling Report on the 97 Bev Claim, Gold Hill Group, *Assessment Report Number 29300*
- Wilkinson, W.J. (2008): Diamond Drilling Report on the 97 Bev Claim, Gold Hill Group, *Assessment Report Number 30371*
- Wilkinson, W.J. (2009): Diamond Drilling Report on the 97 Bev Claim, Gold Hill Group, *Assessment Report Number 31225*



Statement of Qualifications

Mineral tenure act , section 16 (2) (A)

I, Christopher Whatley, the recorded tenure owner, submit this Technical Report under the above section ,in the MTA . By direction from Allan Wilcox, Gov. Geologist.

# Appendix 1

## Expenditures Statement

97 Bev Claim,Goldhill Group

December 2010

(cost statement by C.D.Whatley)

Diamond drilling, two NQ drill holes 162.2 meters (532' feet)  
drilled June 18,19,20,27,28,29/July 2,3,and 4 ,Total of 9 days.  
Includes mobe. and demobe. and labour, fuel, bits, repairs etc.  
162.2m / 532' @45.00 /foot\_\_\_\_\_ \$23,940.<sup>00</sup>

Three 4x4 pickup trucks,@ \$125.<sup>00</sup> per day\_\_\_\_\_ \$3,375.<sup>00</sup>  
D-2 Caterpillar, 9 days,@ \$200.<sup>00</sup> per day\_\_\_\_\_ \$1,800.<sup>00</sup>  
One motorhome , 9 days @ \$150.<sup>00</sup> per day\_\_\_\_\_ \$1,350.<sup>00</sup>  
Logging drill core , cut samples and  
Prepare Report , approx, 14 days\_\_\_\_\_ \$1,000.<sup>00</sup>

Lab Analyses, cost paid by third party ,no invoice/no charge\_\_\_\_\_ \$0.<sup>00</sup>

Drill core stored, 5150 14<sup>th</sup> ave. hyw.97 Okanagan Falls B.C.  
note: drill core from all drill holes from 97 Bev Claim stored  
at this residence. No charge \_\_\_\_\_ \$0.<sup>00</sup>

**Total of Expenditures** \_\_\_\_\_ **\$31,465.<sup>00</sup>**  
**Total claimed** \_\_\_\_\_ **\$31,105.<sup>00</sup>**

  
\_\_\_\_\_

Christopher D. Whatley Fmc. # 128719

## **Appendix 2**

**D.Drill core log,**

**Talc #3C and Talc #6**

**97 Bev Claim 2010 drill project**

Core logged by Chris Whatley  
registered owner 97 Bev  
December 2010

Minerals and rock type, visible in the drill core of one or both holes;  
But not limited to:  
Anarchist group, Greenstone, agillite, Quartzite, Tuff, Talc  
(Steatite)/Magnesium carbonate, Diorite, Quartz Vein, Massive  
Sulfide/sulphide (Pyrrhotite, Magnetite, Pyrite), Chalcopyrite, Sphalerite,  
Galena, Chlorite and Iron.

Diamond Drill Log				Talc # 6		Location: 49°08' / 119°10'			Hole No. TALC-6					
Core Logged by: C.D. WHATLEY				97Bev Claim			Page 1 1 4							
Core Interval				Description		Camp McKinney								
Metres		Feet		Sample No.	(Metres)		Assays, ppm			Recovery (Ft)				
From	To	From	To		From-To	Length	Cu	Ni	Ag	Run	Short			
				97 BEV CLAIM, TENURE NO. 359678										
				D.D. HOLE TALC-6. LENGTH: 327' 99.66 M.										
				ELEVATION: 1405 M. AZIMUTH. INCLINATION - 55°										
				CORE SIZE - NQ. DATE DRILLED - JUNE 18-29/2010										
0.00	4.27	0.0	14.0	CASING - 2 FEET BROKEN RUBBLY FRAGMENTS.							0-14	14		
4.27	9.90	14.0	32.5	GREENSTONE - HARD, DARK GREEN, CALCITE AND QUARTZ IN FRACTURES, SMALL VEINS AND BLENDS. SULFIDES DISSEMINATED AT VEINLETS OF QUARTZ. 30' AND 31.5' MAX. WIDTH OF 20 CM.							14-21	0		
											21-25	0		
											25-33	0		
9.90	10.82	32.5	35.5	QUARTZ (VEIN?) LITTLE TO NO MINERALIZATION							33-35	0		
10.82	12.8	35.5	42.0	DIORITE PORPHYRY DIKE - HARD, GREY ROCK, ANHEDRAL TO SUBHEDRAL GREY WHITE FELDSPAR CRYSTALS. DISSEMINATED PYRITE INCREASING TO PATCHES AND VEINLETS AT LOWER CONTACT. - 45° TO CORE AXIS - UPPER CONTACT TOO POORLY DEFINED.										
12.8	15.84	42.0	52.0	GREENSTONE - SAME AS 14'-32.5'. @ 49' - 4 CM QUARTZ VEIN. DISSEMINATED SULFIDE IN ZONES ON UPPER SIDE OF VEIN CONTACT, IN THE GREENSTONE. VEIN IS APPROX 60° TO CORE AXIS.		20	15.8	16.4	60 cm	8	7	6.7	35-44	0
											44-51	0		
15.84	16.15	52.0	53.0	DIORITE DIKE										
16.15	17.06	53.0	56.0	QUARTZ VEIN - WHITE - GREY WITH GLASSY WHITE VEINLETS SULFIDES - DISSEMINATED, IN LAYERS, AND IN FRACTURES. UPTO 10% GREY FINE SULFIDE AND PYRITE CRYSTALS.										
17.06	18.89	56.0	62.0	DIORITE PORPHYRY DIKE - SAME AS 35.5' - 42.0'							51-60	0		
18.89	32.3	62.0	106.0	GREENSTONE - AS AT 14.0' - 32.5'. QUARTZ VEINS @ 76' TWO VEINLETS 6" APART 1" WIDE. 90' - 4" WIDE 91' - 1" WIDE DISSEMINATED PYRITE 2% THROUGH-OUT CORE WITH CONCENTRATIONS AT QUARTZ VEINLETS. NO MAGNETIZIM							60-68	0		
											68-73	0		
											73-79	0		
											79-89	0		
32.3	36.57	106.0	120.0	DIORITE PORPHYRY DIKE. UPPER CONTACT 45° TO CORE AXIS.							89-98	0		

Diamond Drill Log				Talc # 6		Location:			Hole No.				
Core Logged by:				C. D. WHATLEY		97Bev Claim			Page 214				
Core Interval				Description		Camp McKinney							
Metres		Feet				Sample No.	(Metres)		Assays, ppm			Recovery (Ft)	
From	To	From	To				From-To	Length	Cu	Ni	Ag	Run	Short
	CONT.												
32.3	36.57	106.0	120.0	FROM 116' TO 120' QUARTZ FLOODING WITH FRACTURES QUARTZ VEINLETS AND DISSEMINATED SULFIDES AND MASSES OF PYRITE. 45% LOWER CONTACT 45° TO CORE AXIS. NO MAGNETIC.	21	36	36.6	60 cm	38	21	6.8	98-108 0 108-116 0 116-124 0	
36.57	40.38	120.0	132.5	GREENSTONE - CALCITIC BANDING IN FRACTURES 20° TO CORE AXIS. 125' TO 127' STARTS QUARTZ VEIN 2" / 5 CM WIDE <del>125</del> 80° TO CORE AXIS 126.5' QUARTZ VEIN 1 CM. WIDE. 20° TO CORE AXIS. BOTH VEINS HAVE MASSIVE PYRITE - 125' - 10% 126.5' - 60%	22	38	38.7	60 cm	104	51	1.1	124-132 0 132-141 0	
40.38	40.69	132.5	133.5	QUARTZ VEIN - GREEN, CHLORITE IN FRACTURES VERY LITTLE PYRITE OR OTHER VISIBLE.									
40.69	42.97	133.5	141.0	GREENSTONE - HEAVY CALCITE IN BANDING - 50° TO 80° TO CORE AXIS, CALCITE BLEBS FILL BROKEN G. STONE UP TO 5 CM X 10 CM / 136' - 137.5' ALTERATION ZONE WITH 2 SMALL QUARTZ VEINS (1 CM EACH) DISSEMINATED PYRITE 5% TOP CONTACT UNDETERMINED FOR DEGREE TO CORE AXIS. LOWER CONTACT 45° TO CORE AXIS.								141-149 0	
42.97	43.28	141.0	142.0	QUARTZ - LITTLE MINERALIZATION TOP CONTACT AND LOWER 45° TO CORE AXIS									
43.28	44.19	142.0	145.0	GREENSTONE BRECCIA. WELDED WITH CALCITE AND QUARTZ - FINE GREY SULFIDE AND DISSEMINATED PYRITE + BLEBS - UP TO 20% CHLORITE ON THE FRACTURES. ROCK CRUSHED TO 2 CM AND LESS FROM 142.0' - 144.0'. LOWER CONTACT 45° TO CORE AXIS.	28	43.5	44.1	60 cm	11	48	<.3		
44.19	49.98	145.0	164.0	DIORITE PORPHYRY DIKE - YOUNG, HARD, GREY, GREY-WHITE FELDSPAR - DISSEMINATED PYRITE THROUGH OUT - 2% AND PYRITE FILLING IN FRACTURES UP TO 3 MM PYRITE BLEBS THROUGH OUT - UP TO 1.5 CM X 1 CM.								149-157 0 157-160 0 160-170 0	

Diamond Drill Log				Talc # 6	Location:	Hole No.								
Core Logged by: C. D. WHATLEY					97Bev Claim	Page 3 14								
Core Interval				Description	Camp McKinney									
Metres		Feet			Sample No.	(Metres)		Assays, ppm			Recovery (Ft)			
From	To	From	To			From-To	Length	Cu	Ni	Ag	Run	Short		
44.19	49.98	145.0	164.0	@ 156.0' FAULT @ 20° TO CORE AXIS, BROKEN ROCK ON LOWER SIDE WITH CALCITE FLOODING. 3 CM. WIDE 156.0' AND LOWER - MORE COARSE GRAINED, BROKEN DISSEMINATED PYRITE. 5% LARGE BLACK CRYSTALS 5MM X 10MM. CHLORITE ON FRACTURES				PPM	PPM	PPM				
				160.0' QUARTZ VEIN 4", 161.0' QUARTZ VEIN 2" ALTERATION ZONE FROM 159.5' TO 160.5'. HEAVY CONCENTRATION OF DISSEMINATED PYRITES > 40% @ 163.0' QUARTZ VEIN 2" WITH ALTERATION 4" EACH SIDE WITH SULFIDES SAME AS 160' AND 161'. LOWER CONTACT 30° TO CORE AXIS.										
49.98	52.12	164.0	171.0	GREENSTONE - SAME AS 142.0' - 145.0'	23	52.5	53	50 cm	506	69	0.7	170-174	0	
52.12	53.34	171.0	175.0	DIORITE PORPHYRY DIKE - SAME AS 145.0' - 164.0'								174-177	0	
53.34	53.79	175.0	176.5	GREENSTONE - SAME AS 142.0' - 145.0'										
53.79	54.25	176.5	178.0	DIORITE PORPHYRY DIKE - SAME AS 145.0' - 164.0'								177-184	0	
54.25	57.6	178.0	189.0	GREENSTONE - SAME AS 142.0' - 145.0', BUT MORE BLEBS OF SULFIDE (PYRITE?) LITTLE TO NO MAGNETICS. UP TO 40% PARTICULARLY 182.5' - 184.0' UPPER CONTACT 45° LOWER CONTACT IS 20° TO CORE AXIS.	29	56.3	56.9	60 cm	296	70	0.7	184-190	0	
57.6	58.82	189.0	193.0	QUARTZ - VEIN? WHITE - GREY - BLUE - BRECCIATED @ UPPER CONTACT FOR 30 CM. INFILLED WITH SULFIDE 40 TO 60% BRASSY COLOUR - FINE GREY SULFIDE UP TO 10% VERY MINOR SPHALERITE AND GALENA. THE REST ABOUT 20% SULFIDES; HEAVY BLACK CHLORITE IN FRACTURES. LOWER CONTACT 80° TO CORE AXIS.	30	60.3	61	70 cm	31	13	<.3		190-197	0
58.82	60.52	193.0	198.5	GREENSTONE - SAME AS 142.0' - 145.0'	27	61.5	62.5	1 m.	3	7	<.3	197-202	0	
60.52	65.53	198.5	215.0	IMPURE QUARTZ BRECCIA. BLUE-GREY, WHITE - BROKEN/VEIN? CRUSHED QUARTZITE, FLOODED WITH WHITE QUARTZ. DISSEMINATED SULFIDES THROUGH-OUT. SMALL ZONES OF MASSIVE SULFIDES SAME AS 189.0 - 193.0 THROUGH-OUT	24	61	61.5	50 cm	31	10	1.4	202-212	0	
					25	64	64.6	60 cm	8	7	<.3	212-222	0	
					26	64.6	65.5	90 cm	33	10	<.3			

Diamond Drill Log				Talc # 6		Location:			Hole No.				
Core Logged by:				CD WHATLEY		97Bev Claim			Page 4 14				
Core Interval				Description		Camp McKinney							
Metres		Feet				Sample No.	(Metres)		Assays, ppm			Recovery (Ft)	
From	To	From	To				From-To	Length	Cu	Ni	Ag	Run	Short
60.52	65.53	198.5	215.0	203' IS 2" BAND OF SULFIDE - NO MAGNETIC/CHLORITE BRASSY MASSES WITH FINE GREY SULFIDE MIX. IN FRACTURES								222-232	0
				UPPER CONTACT @ 45° LOWER @ 20° TO CORE AXIS.									
65.53	66.14	215.0	217.0	DIORITE PORPHYRY DIKE WITH A 10 CM THICK SEAM OF CALCITE @ 45° TO THE CORE AXIS. DISSEMINATED PYRITE 40% IN CALCITE. THE LOWER CONTACT IS NOT DEFINED.									
66.14	68.73	217.0	225.5	GREENSTONE - SAME AS 142.0' - 145.0'									
68.73	69.03	225.5	226.5	DIORITE - SAME AS 145.0' - 164.0'									
69.03	84.42	226.5	277.0	GREENSTONE - HEAVY FRACTURES WITH HEALING INFILL OF CALCITE. TOP CONTACT WELL DEFINED 45° TO CORE AXIS. DIRECTLY NEXT FAULT WITH 1.5" (4 CM) ROCK CLAY. DISSEMINATED AND BANDS UP TO 2 CM WIDE, BANDS MOSTLY 45° TO CORE AXIS. 264.0 FAULT, 90° TO CORE AXIS 2.5 CM ROCK CLAY. FROM HERE TO LOWER CONTACT A RED MINERAL (HEMATITE?) IS FOUND IN FRACTURES OF THE GREENSTONE AND MIXED WITH THE CALCITE. NO MAGNETICS. LOWER CONTACT 55° TO CORE AXIS.								232-242	0
												242-252	0
												252-258	0
												258-264	0
												264-269	0
												269-277	0
84.42	84.73	277.0	278.0	DIORITE - SAME AS 225.5' - 226.5'								277-282	2
84.73	85.64	278.0	281.0	TALC - CRUSHED - LOST, GROUND CORE. APPROX 2' FEET. CHLORITIC WITH MINOR PYRITE DISSEMINATION 1%								282-288	0
												288-298	0
85.64	89.3	281.0	293.0	GREENSTONE - SAME AS 226.5' - 277.0', BUT HEAVIER (MORE) RED ON THE FRACTURES. LOWER CONTACT 90° TO CORE AXIS.									
89.3	99.66	293.0	327.0	TALCOSE ROCK - STEATITE MASSIVE APPROX 50/50 TALC AND MAGNESIUM CARBONATE. (KNOWN FROM OTHER TEST)		TALC. CORE -						298-302	1.5
						AT END	98/99.6	1 m <sup>+</sup>	3	404	< 3	302-308	0
99.66	M.		327.0	END OF D.D. HOLE TALC #6 (NO DIP TEST)		2646	-01	WHOLE ROCK ANAL.				308-312	0
							-02	SEE ASSAYS SHEETS.				312-321	0
												321-327	0

Diamond Drill Log				Talc # 3C		Location: 49°08'/119°10'			Hole No. TALC-3C			
Core Logged by:				C. D. WHATLEY, TENURE OWNER		97Bev Claim			Page 115			
Core Interval				Description		Camp McKinney		Assays, ppm			Recovery (Ft)	
Metres		Feet				Sample No.	(Metres)		Cu	Ni	Ag	Run
From	To	From	To	From-To	Length							
				97 BEV CLAIM, TENURE NO. 359678								
				D.D. HOLE TALC - 3C LENGTH: 205' 62.5M,								
				ELEVATION: 1402 M. AZIMUTH 192° INCLINATION: -55°								
				CORE SIZE NQ. DATE DRILLED - JUNE 18-29/2010								
											0-14	14.0
0.00	4.27	0	14.0	CASING: 1 FOOT OF BROKEN, RUBBLY CORE FRAGMENTS							14-23	0.0
4.27	6.10	14.0	20.0	BROKEN, RUBBLY SILICEOUS ROCK AND VEIN QUARTZ, DISSEMINATED PYRITE > 10%								
				QUARTZ, BROKEN, INCREASING BLEBS AND PATCHES OF PYRITE UP TO CONTACT AT 20' WITH DIORITE PORPHYRY DIKE								
6.10	9.30	20.0	30.5	DIORITE PORPHYRY DIKE: HARD, GREY BROWN ROCK, ANHEDRAL TO SUBHEDRAL GREY-WHITE FELDSPAR CRYSTALS UP TO 3mm x 5mm, IN DARK GREY MATRIX UPPER CONTACT POORLY DEFINED, ABOUT 45 DEGREES TO CORE AXIS.							23-28	0.0
9.30	10.60	30.5	33.0	QUARTZ VEIN - CONTACT 45° TO CORE AXIS GREY-GREEN QUARTZ TO 32 FEET - WHITE TO 33' LOWER CONTACT ABOUT 45° TO CORE AXIS								
				WHITE QUARTZ, MINOR PYRITE, SPHALERITE AND GALENA								
10.6	11.12	33.0	36.5	MASSIVE SULPHIDE ZONE: > 50% SULPHIDES AND MAGNETITE. HIGHLY MAGNETIC ROCK. PREDOMINANT SULPHIDE IS A VERY FINE GRAINED PYRRHOTITE, BRONZE/MIDDLE BROWN COLOUR, 10% PYRITE CHALCOPYRITE MASSES (3mm x 5mm) AT 35.5'							28-34	0.0
11.12	12.34	36.5	40.5	HORNfelsic ALTERATION ZONE: GREY-GREEN HARD HORNfelsic ROCK WELL FRACTURED, WITH BLACK CHLORITE ON THE FRACTURES. THIS ROCK IS NON MAGNETIC AND CONTAINS NO SULFIDES EXCEPT FOR 1% PYRITE ON THE FRACTURES. THIS ROCK LOOKS THE SAME AS THE MASSIVE —							34-42	0.0





Diamond Drill Log				Talc # 3C		Location:			Hole No.				
Core Logged by:				C. WHATLEY		97Bev Claim			Page 315				
Core Interval				Description		Camp McKinney							
Metres		Feet				Sample No.	(Metres)		Assays, ppm			Recovery (Ft)	
From	To	From	To				From-To	Length	Cu	Ni	Ag	Run	Short
								PPM	PPM	PPM			
20.42	21.03	67.0	69.0	HORNFELSIC ALTERATION ZONE: HORNFELSIC ROCK CRUSHED AND FLOODED WITH QUARTZ. 67.5' TO 68.0' MASSIVE SULFIDE SAME AS 33'. LOWER CONTACT 20° TO CORE AXIS.									
21.03	21.94	69.0	72.0	QUARTZ BRECCIA: WHITE, GREY-GREEN, CRUSHED FILLED GREY QUARTZ AND SULFIDES + PYRITES 2-5% SOME SPHALERITE.		9	21.3-22	2190cm	83	24	0.4		
21.94	25.9	72.0	85.0	ALTERATION ZONE: GREY-GREEN-BROWN, APHANITIC ROCK. IRREGULAR QUARTZ FLOODING, MOST 74' TO 77' ABOUT 10% SULFIDES. CHLORITE PRESENT IN FRACTURES								74-81	0.0
												81-85	0.0
25.9	27.12	85.0	89.0	QUARTZ - SAME AS 69.0 UPPER CONTACT UNDETERMINED LOWER CONTACT @ 45° TO CORE AXIS.		11	26-26.5	50cm	66	3	1.0		
27.12	33.83	89.0	111.0	SAME AS 72.0' TO 85.0' (GREEN STONE)								85-91	0.0
33.83	35.66	111.0	117.0	QUARTZ VEIN: GREY-BLUE QUARTZ BLACK CHLORITIZED FRACTURES, DISSEMINATED PYRITE 1% UPPER CONTACT 60° TO CORE AXIS - LOWER CONTACT 80° TO CORE AXIS.								91-97	0.0
												97-104	0.0
35.66	38.4	117.0	126.0	DIORITE PORPHYRY DYKE: BROWN, HARD MEDIUM GRAINED. QUARTZ								104-112	0.0
												112-120	0.0
38.4	38.86	126.0	127.5	QUARTZ VEIN: BLUE-GREY. SULFIDES IN FRACTURES. MASSIVE - 40% SPHALERITE + GALENA < 1% PYRRHOTITE - PYRITE MOSTLY AND SOME CHALLOPYRITE. LOWER CONTACT 85° TO CORE AXIS. UPPER UNDETERMINED.		8	38.4 38.7	30cm	208	20	0.7	120-123	0.0
												123-127	0.0
38.86	39.92	127.5	131.0	GREENSTONE: LIGHT GREEN, HARD, APHANITIC ROCK. MASSIVE DISSEMINATED PYRITE. 129' QUARTZ VEIN 1" MASSIVE SULFIDE ON CONTACTS @ 45° TO CORE AXIS. 10% AND LESS SULFIDE		7	39.1 39.7	60cm	1576	81	1.4		
39.92	40.84	131.0	134.0	DIORITE PORPHYRY DIKE - PROGRESSING FROM FINE FELDSPAR CRYSTALS TO LARGE (33') FELDSPAR CRYSTALS. 3MM X 4MM								127-134	0.0

Diamond Drill Log				Talc # 3C		Location:			Hole No.				
Core Logged by:				C. WHATLEY		97Bev Claim			Page 415				
Core Interval				Description		Camp McKinney							
Metres		Feet				Sample No.	(Metres)		Assays, ppm			Recovery (Ft)	
From	To	From	To				From-To	Length	Cu	Ni	Ag	Run	Short
								PPM	PPM	PPM			
40.84	42.06	134.0	138.0	HORNfelsic ALTERATION ZONE: NO MINERAL VISIBLE.								134-138	0.0
42.06	42.67	138.0	140.0	DIORITE PORPHYRY DIKE - SAME AS 131.0'-134'. LARGE FELDSPAR CRYSTALS - UP TO 10mm x 10mm PYRITE DISSEMINATED AND IN FRACTURES 2% LOWER CONTACT 85° TO CORE AXIS.									
42.67	44.5	140.0	146.0	SAME AS 134.0'-138.0' UPPER CONTACT 80° FROM CORE AXIS - LOWER CONTACT 20° F.C. AXIS. LOWER CONTACT PYRITE PATCHES AND BANDS FROM 3mm x 40cm 10%								138-144	0.0
44.5	44.8	146.0	147.0	QUARTZ VEIN, BRECCIATED, CEMENTED, WHITE, GREY-BLUE QUARTZ FINE SULFIDES. 5% LOWER CONTACT GROUND.									
44.8	45.56	147.0	149.5	DIORITE PORPHYRY DIKE - SAME AS 138.0'-140.0'									
45.56	49.83	149.5	163.5	HIGHLY ALTERED, IRRREGULARLY BANDED GREENSTONE WITH QUARTZITE ZONES WITH DISSEMINATED PYRRHOTITE AND PYRITE UP TO 15%		6	458/463	50 cm	166	35	0.8	144-154	0.0
49.83	52.73	163.5	173.0	HORNfelsic ZONE SAME AS 134.0'-138.0' LITTLE MINERAL VISIBLE. UPPER AND LOWER CONTACTS @ APPROX. 80° TO CORE AXIS.								154-164	0.0
												164-169	0.0
52.73	59.18	173.0	174.5	DIORITE PORPHYRY DIKE - SAME AS 138' to 140'		5	53/53.6	60 cm	264	169	1.3		
53.18	55.32	174.5	181.5	HORNfels - BROWN - HARD, FINE BANDING @ 45°, WITH FINE PYRITIC SEAMS. 175'-175.5' QUARTZ VEIN CROSSES CORE @ 45° TO CORE AXIS 178'-179' LARGE BLEBS OF SULFIDE - PYRRHOTITE + PYRITE - 40% UPPER AND LOWER CONTACTS @ 45° T.C.A.		4	542/54.8	60 cm	460	174	0.9	169-179	0.0
55.32	56.23	181.5	184.5	QUARTZ VEIN: DARK-SMOKY-BLUE QUARTZ CUT BY WHITE QUARTZ VEIN. SULFIDE DISSEMINATED - FINE DARK GREY-? PYRRHOTITE - PYRITE AND CHALCOPYRITE. UPPER CONTACT 45° - LOWER CONTACT 85° FROM CORE AXIS.		2	55/55.7	60 cm	139	70	1.9	179-183	0.0

Diamond Drill Log				Talc # 3.C	Location: CAMP MCKINNEY	Hole No. TALC-30							
Core Logged by:				C. WHATLEY	97Bev Claim	Page 515							
Core Interval				Description	Camp McKinney								
Metres		Feet			Sample No.	(Metres)		Assays, ppm			Recovery (Ft)		
From	To	From	To			From-To	Length	Cu	Ni	Ag	Run	Short	
56.23	59.43	181.5	195.0	ARGILLITIC HORNFELS BANDED, BROWN - QUARTZ HEALED, BRECCIATED ROCK LITTLE MINERAL VISIBLE.	3	57.3	57.9	60cm	53	25	0.4	183-191	0.0
												191-194	0.0
59.43	61.87	195.0	203.0	QUARTZ VEIN: BRECCIATED RECEMENTED WHITE - SMOKEY - GREEN; FRACTURES (HLORITIZED) DISSEMINATED SULFIDES WITH SMALL BLEBS AND FRACTURE FILLING. SAME AS 181.5 - 184.5	1	59.2	59.7	50cm	26	20	0.5	194-200	0.0
61.87	62.48	203	205	SAME AS 184.5 - 195.0 HORNFEL BANDED NO MINERAL VISIBLE.								200-205	0.0
62.48	M.	205		END OF D.D.H. TALC 3.C.								205	END

## **Appendix 3**

### **Certificate of Analysis**

Of diamond drill core samples, NQ core, cut in half, from the 97 Bev merial claim.  
2010 drill project, Holes ; Talc 3c and Talc 6.  
26 samples- 23 FA fusion Au Pt Pd; 1:1:1 AR digestion ICP analysis, 3- Whole rock assays

Note; ACME mislabeled assays , then revised numbering of samples (identifacation)  
in the certificate, With some samples still mislabeled, as noted on the certificate.



# AcmeLabs

Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

www.acmelab.com

Client: **Sherman, Barry**  
174 - 321 Yorkton Ave.  
Penticton BC V2A 3V6 Canada

Submitted By: Barry Sherman  
Receiving Lab: Canada-Vancouver  
Received: August 31, 2010  
Report Date: November 04, 2010  
Page: 1 of 2

## CERTIFICATE OF ANALYSIS

VAN10004278.2

### CLIENT JOB INFORMATION

Project: None Given  
Shipment ID:  
P.O. Number  
Number of Samples: 26

### SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	23	Crush split and pulverize 250g drill core to 200 mesh			VAN
GEO4	23	FA fusion Au Pt Pd; 1:1:1 AR digestion ICP-ES analysis	30	Completed	VAN
4A4B	3	Whole Rock Analysis Majors and Trace Elements	0.2	Completed	VAN

### SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days  
DISP-RJT Dispose of Reject After 90 days

### ADDITIONAL COMMENTS

Version 2: Revised Sample IDs

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Westport Properties Ltd.  
407 - 1440 Creekside Drive  
Vancouver BC V6J 5B6  
Canada

CC: Barry Kaplan



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.  
All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only.  
\*\* asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: Sherman, Barry  
 174 - 321 Yorkton Ave.  
 Penticton BC V2A 3V6 Canada

Project: None Given  
 Report Date: November 04, 2010

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

VAN10004278.2

Method	WGHT	3B	3B	3B	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	
Unit	kg	ppb	ppb	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	2	3	2	1	1	3	1	0.3	1	1	2	0.01	2	8	2	2	1	0.5	3	
1 BEV 3-C 194.5-196 FT	Drill Core	1.41	14	<3	2	11	26	23	97	0.5	20	10	1169	2.11	17	<8	<2	<2	51	0.7	<3
2 BEV 3-C 181-183 FT	Drill Core	1.38	6	<3	<2	2	139	71	1350	1.9	70	30	1137	5.46	26	<8	<2	3	62	10.9	<3
3 BEV 3-C 188-190 FT	Drill Core	1.25	7	<3	<2	2	53	20	160	0.4	25	10	727	2.83	8	<8	<2	4	46	1.0	<3
4 BEV 3-C 178-180 FT	Drill Core	1.07	54	<3	<2	6	460	9	84	0.9	174	221	1357	12.37	13	<8	<2	<2	96	0.9	<3
5 BEV 3-C 174-176 FT	Drill Core	1.63	9	4	<2	2	264	28	382	1.3	169	52	1910	7.73	15	<8	<2	<2	84	2.9	<3
6 BEV 3-C 150.5-152 FT	Drill Core	1.32	28	<3	<2	7	166	18	222	0.8	35	48	1681	5.79	6	<8	<2	<2	81	1.9	<3
7 BEV 3-C 128.5-130.5 FT	Drill Core	1.59	44	27	8	10	1576	6	59	1.4	81	87	1310	18.29	4	<8	<2	2	15	<0.5	<3
8 BEV 3-C 126-127 FT	Drill Core	0.80	22	5	2	1	208	21	462	0.7	20	20	541	6.67	11	<8	<2	<2	20	3.4	<3
9 BEV 3-C 70-73 FT	Drill Core	1.57	10	<3	<2	5	83	11	55	0.4	24	17	908	3.51	5	<8	<2	<2	65	<0.5	<3
10 BEV 3-C 66-68 FT	Drill Core	1.47	8	5	3	3	342	15	272	1.1	86	23	1890	10.72	7	<8	<2	<2	40	1.8	<3
11 BEV 3-C 85-87 FT	Drill Core	1.66	15	<3	<2	1	66	45	237	1.0	3	8	918	2.41	7	<8	<2	<2	108	1.8	<3
20 BEV 6 52-54 FT	Drill Core	1.67	16	<3	<2	1	8	184	631	6.7	7	15	1393	3.62	19	<8	<2	<2	40	4.8	<3
21 BEV 6 118-120 FT	Drill Core	1.68	8	<3	<2	1	38	128	786	6.8	21	19	1026	4.46	34	<8	<2	<2	84	5.9	<3
22 BEV 6 125-127 FT	Drill Core	1.68	13	<3	<2	4	104	14	809	1.1	51	38	1060	6.01	14	<8	<2	<2	51	6.4	<3
23 BEV 6 172.5-174 FT	Drill Core	1.19	62	7	12	8	506	5	72	0.7	69	58	1231	6.52	6	<8	<2	<2	68	0.5	<3
24 BEV 6 192-194 FT x	Drill Core	1.49	19	<3	<2	<1	31	17	251	1.4	10	13	857	5.63	27	<8	<2	<2	109	2.0	<3
25 BEV 6 202-204 FT x	Drill Core	1.12	10	<3	<2	3	8	9	48	<0.3	7	10	684	2.83	7	<8	<2	<2	95	<0.5	<3
26 BEV 6 204-207 FT x	Drill Core	2.38	12	<3	<2	4	33	<3	36	<0.3	10	12	1368	3.00	4	<8	<2	<2	130	<0.5	<3
27 BEV 6 195-197 FT x	Drill Core	1.09	5	<3	<2	4	3	4	35	<0.3	7	9	701	2.86	6	<8	<2	<2	112	<0.5	<3
28 BEV 6 143-145 FT	Drill Core	1.24	10	5	10	11	11	9	275	<0.3	48	33	1235	5.18	10	<8	<2	<2	109	2.2	<3
29 BEV 6 177-179 FT x	Drill Core	1.18	33	5	<2	20	296	22	240	0.7	70	40	1255	7.40	8	<8	<2	<2	96	2.1	<3
30 BEV 6 190-192 FT x	Drill Core	1.45	9	<3	<2	3	31	3	68	<0.3	13	18	882	4.24	9	<8	<2	<2	123	<0.5	<3
TALC CORE	Drill Core	0.29	4	5	5	<1	3	<3	7	<0.3	404	50	1063	2.60	<2	<8	<2	<2	33	<0.5	<3
2646-01 TALC CON	Rock Pulp	0.03	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
2646-02 TALC CON	Rock Pulp	0.05	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
TALC S	Rock Pulp	0.04	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.

NOTE : \* INDICATES SAMPLE # OF FT INCORRECT ADD 8 FT TO EACH SAMPLE FT#.

NOTE : ACME SECOND REVISED # STILL INCORRECT.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client:

Sherman, Barry

174 - 321 Yorkton Ave.

Penticton BC V2A 3V6 Canada

Project:

None Given

Report Date:

November 04, 2010

Page:

2 of 2

Part 2

CERTIFICATE OF ANALYSIS

VAN10004278.2

Method	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B
Analyte	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	S	SiO2	Al2O3	Fe2O3	MgO	CaO	
Unit	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	%	%	%	%	%	%	
MDL	3	1	0.01	0.001	1	1	0.01	1	0.01	20	0.01	0.01	0.01	2	0.05	0.01	0.01	0.04	0.01	0.01	
1 BEV 3-C 194.5-196 FT	Drill Core	<3	8	1.93	0.027	2	21	0.33	39	<0.01	<20	0.38	<0.01	0.16	<2	1.92	N.A.	N.A.	N.A.	N.A.	N.A.
2 BEV 3-C 181-183 FT	Drill Core	7	71	2.28	0.063	3	87	1.47	171	0.16	<20	1.99	<0.01	0.87	<2	3.01	N.A.	N.A.	N.A.	N.A.	N.A.
3 BEV 3-C 188-190 FT	Drill Core	<3	30	1.39	0.036	7	26	1.21	64	<0.01	<20	1.47	0.01	0.24	<2	0.68	N.A.	N.A.	N.A.	N.A.	N.A.
4 BEV 3-C 178-180 FT	Drill Core	<3	176	3.24	0.120	3	222	3.24	48	0.33	<20	4.85	0.01	1.92	<2	5.20	N.A.	N.A.	N.A.	N.A.	N.A.
5 BEV 3-C 174-176 FT	Drill Core	<3	122	3.79	0.149	4	190	2.30	176	0.25	<20	3.00	<0.01	1.47	2	2.85	N.A.	N.A.	N.A.	N.A.	N.A.
6 BEV 3-C 150.5-152 FT	Drill Core	<3	74	4.15	0.073	3	98	2.21	155	0.17	<20	2.71	0.01	0.87	<2	2.44	N.A.	N.A.	N.A.	N.A.	N.A.
7 BEV 3-C 128.5-130.5 FT	Drill Core	<3	139	1.57	0.468	11	32	1.53	65	0.10	<20	2.53	0.07	0.54	2	8.11	N.A.	N.A.	N.A.	N.A.	N.A.
8 BEV 3-C 126-127 FT	Drill Core	4	35	1.43	0.057	2	12	0.19	16	<0.01	<20	0.34	<0.01	0.06	<2	4.17	N.A.	N.A.	N.A.	N.A.	N.A.
9 BEV 3-C 70-73 FT	Drill Core	<3	38	2.58	0.067	6	17	1.01	31	<0.01	<20	1.43	0.02	0.21	<2	1.52	N.A.	N.A.	N.A.	N.A.	N.A.
10 BEV 3-C 66-68 FT	Drill Core	6	91	1.87	0.111	6	60	1.99	71	0.11	<20	2.75	<0.01	0.88	<2	4.71	N.A.	N.A.	N.A.	N.A.	N.A.
11 BEV 3-C 85-87 FT	Drill Core	4	11	3.48	0.067	5	4	0.50	46	<0.01	<20	0.76	0.02	0.29	<2	1.78	N.A.	N.A.	N.A.	N.A.	N.A.
20 BEV 6 52-54 FT	Drill Core	26	18	1.51	0.055	2	5	1.12	101	<0.01	<20	1.05	<0.01	0.61	<2	3.48	N.A.	N.A.	N.A.	N.A.	N.A.
21 BEV 6 118-120 FT	Drill Core	44	28	1.80	0.062	2	16	1.61	89	0.02	<20	1.23	0.01	0.76	<2	4.15	N.A.	N.A.	N.A.	N.A.	N.A.
22 BEV 6 125-127 FT	Drill Core	11	110	2.47	0.092	2	112	2.24	202	0.33	<20	2.33	0.05	1.00	<2	2.77	N.A.	N.A.	N.A.	N.A.	N.A.
23 BEV 6 172.5-174 FT	Drill Core	5	125	3.12	0.016	<1	93	2.75	207	0.12	<20	2.73	0.04	0.71	<2	2.37	N.A.	N.A.	N.A.	N.A.	N.A.
24 BEV 6 192-194 FT	Drill Core	13	31	3.23	0.068	3	3	0.76	63	<0.01	<20	0.75	0.03	0.23	<2	5.52	N.A.	N.A.	N.A.	N.A.	N.A.
25 BEV 6 202-204 FT	Drill Core	<3	29	2.82	0.075	4	4	1.03	73	<0.01	<20	1.08	0.03	0.22	<2	1.92	N.A.	N.A.	N.A.	N.A.	N.A.
26 BEV 6 204-207 FT	Drill Core	<3	46	4.30	0.077	4	13	1.30	73	0.02	<20	1.08	0.04	0.38	<2	2.01	N.A.	N.A.	N.A.	N.A.	N.A.
27 BEV 6 195-197 FT	Drill Core	<3	44	2.95	0.076	5	5	1.22	266	<0.01	<20	1.18	0.04	0.26	<2	1.37	N.A.	N.A.	N.A.	N.A.	N.A.
28 BEV 6 143-145 FT	Drill Core	4	135	4.28	0.036	2	98	2.47	200	0.10	<20	2.09	0.04	0.97	<2	2.50	N.A.	N.A.	N.A.	N.A.	N.A.
29 BEV 6 177-179 FT	Drill Core	<3	88	3.31	0.142	6	48	1.75	79	0.02	<20	2.36	0.02	0.31	<2	4.21	N.A.	N.A.	N.A.	N.A.	N.A.
30 BEV 6 190-192 FT	Drill Core	<3	91	3.68	0.096	3	16	1.68	42	0.01	<20	1.63	0.04	0.23	<2	2.09	N.A.	N.A.	N.A.	N.A.	N.A.
TALC CORE	Drill Core	<3	22	1.69	0.002	<1	394	7.13	<1	<0.01	<20	0.58	<0.01	<0.01	<2	0.48	N.A.	N.A.	N.A.	N.A.	N.A.
2646-01 TALC CON	Rock Pulp	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	58.87	0.34	2.93	29.65	0.28
2646-02 TALC CON	Rock Pulp	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	58.94	0.29	3.03	30.21	0.28
TALC S	Rock Pulp	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	55.81	0.92	2.79	30.88	0.39





# AcmeLabs

Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Sherman, Barry**  
174 - 321 Yorkton Ave.  
Penticton BC V2A 3V6 Canada

Project: None Given  
Report Date: November 04, 2010

Page: 2 of 2 Part 3

## CERTIFICATE OF ANALYSIS

## VAN10004278.2

Method	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	
Analyte	Na2O	K2O	TiO2	P2O5	MnO	Cr2O3	Ni	Sc	LOI	Sum	Ba	Be	Co	Cs	Ga	Hf	Nb	Rb	Sn	Sr	
Unit	%	%	%	%	%	%	ppm	ppm	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.01	0.01	0.01	0.01	0.002	20	1	-5.1	0.01	1	1	0.2	0.1	0.5	0.1	0.1	0.1	1	0.5	
1 BEV 3-C 194.5-196 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
2 BEV 3-C 181-183 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
3 BEV 3-C 188-190 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
4 BEV 3-C 178-180 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
5 BEV 3-C 174-176 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
6 BEV 3-C 150.5-152 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
7 BEV 3-C 128.5-130.5 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
8 BEV 3-C 126-127 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
9 BEV 3-C 70-73 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
10 BEV 3-C 66-68 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
11 BEV 3-C 85-87 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
20 BEV 6 52-54 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
21 BEV 6 118-120 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
22 BEV 6 125-127 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
23 BEV 6 172.5-174 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
24 BEV 6 192-194 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
25 BEV 6 202-204 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
26 BEV 6 204-207 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
27 BEV 6 195-197 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
28 BEV 6 143-145 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
29 BEV 6 177-179 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
30 BEV 6 190-192 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
TALC CORE	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.
2646-01 TALC CON	Rock Pulp	<0.01	<0.01	0.01	<0.01	0.02	0.094	1688	2	7.1	99.53	2	<1	41.3	0.1	0.6	<0.1	4.6	0.6	<1	4.7
2646-02 TALC CON	Rock Pulp	<0.01	<0.01	0.01	<0.01	0.02	0.101	1661	2	6.4	99.52	2	<1	43.1	0.2	0.5	<0.1	0.6	0.5	<1	4.8
TALC S	Rock Pulp	<0.01	<0.01	0.01	<0.01	0.03	0.077	2315	4	8.3	99.49	1	<1	60.4	<0.1	0.9	<0.1	70.3	<0.1	<1	5.3



1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Sherman, Barry**  
 174 - 321 Yorkton Ave.  
 Penticton BC V2A 3V6 Canada

Project: None Given  
 Report Date: November 04, 2010

Page: 2 of 2 Part 4

CERTIFICATE OF ANALYSIS

VAN10004278.2

Method	Analyte	Unit	MDL	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B		
				Ta	Th	U	V	W	Zr	Y	La	Ce	Pr	Nd	Sm	Eu	Gd	Tb	Dy	Ho	Er	Tm	Yb
				ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
				0.1	0.2	0.1	8	0.5	0.1	0.1	0.1	0.1	0.02	0.3	0.05	0.02	0.05	0.01	0.05	0.02	0.03	0.01	0.05
1 BEV 3-C 194.5-196 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
2 BEV 3-C 181-183 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
3 BEV 3-C 188-190 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
4 BEV 3-C 178-180 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
5 BEV 3-C 174-176 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
6 BEV 3-C 150.5-152 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
7 BEV 3-C 128.5-130.5 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
8 BEV 3-C 126-127 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
9 BEV 3-C 70-73 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
10 BEV 3-C 66-68 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
11 BEV 3-C 85-87 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
20 BEV 6 52-54 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
21 BEV 6 118-120 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
22 BEV 6 125-127 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
23 BEV 6 172.5-174 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
24 BEV 6 192-194 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
25 BEV 6 202-204 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
26 BEV 6 204-207 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
27 BEV 6 195-197 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
28 BEV 6 143-145 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
29 BEV 6 177-179 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
30 BEV 6 190-192 FT	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
TALC CORE	Drill Core			N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
2646-01 TALC CON	Rock Pulp			0.5	<0.2	<0.1	10	<0.5	2.4	<0.1	<0.1	<0.1	<0.02	<0.3	<0.05	<0.02	<0.05	<0.01	<0.05	<0.02	<0.03	<0.01	<0.05
2646-02 TALC CON	Rock Pulp			<0.1	<0.2	<0.1	12	<0.5	1.2	0.1	<0.1	0.1	<0.02	<0.3	<0.05	<0.02	<0.05	<0.01	<0.05	<0.02	<0.03	<0.01	<0.05
TALC S	Rock Pulp			8.4	<0.2	<0.1	18	<0.5	1.1	0.2	0.3	0.2	0.02	<0.3	<0.05	<0.02	<0.05	<0.01	<0.05	<0.02	<0.03	<0.01	<0.05



1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
Phone (604) 253-3158 Fax (604) 253-1716

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Sherman, Barry**  
174 - 321 Yorkton Ave.  
Penticton BC V2A 3V6 Canada

Project: None Given  
Report Date: November 04, 2010

Page: 2 of 2 Part 5

CERTIFICATE OF ANALYSIS

VAN10004278.2

Method	4A-4B	2A	Leco	2A	Leco	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX	1DX
Analyte	Lu	TOT/C	TOT/S	Mo	Cu	Pb	Zn	Ni	As	Cd	Sb	Bi	Ag	Au	Hg	Tl	Se	
Unit	ppm	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppb	ppm	ppm	ppm	
MDL	0.01	0.02	0.02	0.1	0.1	0.1	1	0.1	0.5	0.1	0.1	0.1	0.1	0.5	0.01	0.1	0.5	
1 BEV 3-C 194.5-196 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
2 BEV 3-C 181-183 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
3 BEV 3-C 188-190 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
4 BEV 3-C 178-180 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
5 BEV 3-C 174-176 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
6 BEV 3-C 150.5-152 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
7 BEV 3-C 128.5-130.5 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
8 BEV 3-C 126-127 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
9 BEV 3-C 70-73 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
10 BEV 3-C 66-68 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
11 BEV 3-C 85-87 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
20 BEV 6 52-54 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
21 BEV 6 118-120 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
22 BEV 6 125-127 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
23 BEV 6 172.5-174 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
24 BEV 6 192-194 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
25 BEV 6 202-204 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
26 BEV 6 204-207 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
27 BEV 6 195-197 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
28 BEV 6 143-145 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
29 BEV 6 177-179 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
30 BEV 6 190-192 FT	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
TALC CORE	Drill Core	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	N.A.	
2646-01 TALC CON	Rock Pulp	<0.01	0.31	0.02	<0.1	16.0	3.5	14	157.6	1.0	0.2	0.2	<0.1	<0.1	37.9	<0.01	<0.1	<0.5
2646-02 TALC CON	Rock Pulp	<0.01	0.49	0.03	1.5	19.1	23.3	22	144.4	0.5	0.1	<0.1	0.1	<0.1	2.5	<0.01	<0.1	<0.5
TALC S	Rock Pulp	<0.01	0.87	<0.02	<0.1	5.5	5.6	36	347.6	<0.5	<0.1	<0.1	0.2	<0.1	2.7	0.01	<0.1	<0.5



# AcmeLabs

Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Sherman, Barry**  
174 - 321 Yorkton Ave.  
Penticton BC V2A 3V6 Canada

Project: None Given

Report Date: November 04, 2010

Page: 1 of 2 Part 2

## QUALITY CONTROL REPORT

VAN10004278.2

Method	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	4A-4B	4A-4B	4A-4B	4A-4B	4A-4B
Analyte	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	S	SiO2	Al2O3	Fe2O3	MgO	CaO
Unit	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	%	%	%	%	%	%
MDL	3	1	0.01	0.001	1	1	0.01	1	0.01	20	0.01	0.01	0.01	2	0.05	0.01	0.01	0.04	0.01	0.01
Pulp Duplicates																				
REP G1	QC															67.55	15.57	3.41	1.13	3.52
9 BEV 3-C 70-73 FT	Drill Core	<3	38	2.58	0.067	6	17	1.01	31	<0.01	<20	1.43	0.02	0.21	<2	1.52	N.A.	N.A.	N.A.	N.A.
REP 9 BEV 3-C 70-73 FT	QC	<3	39	2.63	0.069	7	18	1.03	32	<0.01	<20	1.46	0.02	0.22	<2	1.53				
30 BEV 6 190-192 FT	Drill Core	<3	91	3.68	0.096	3	16	1.68	42	0.01	<20	1.63	0.04	0.23	<2	2.09	N.A.	N.A.	N.A.	N.A.
30 BEV 6 190-192 FT	QC	<3	88	3.57	0.093	3	15	1.63	40	0.01	<20	1.57	0.04	0.22	<2	2.05				
Core Reject Duplicates																				
8 BEV 3-C 126-127 FT	Drill Core	4	35	1.43	0.057	2	12	0.19	16	<0.01	<20	0.34	<0.01	0.06	<2	4.17	N.A.	N.A.	N.A.	N.A.
8 BEV 3-C 126-127 FT	QC	<3	34	1.42	0.056	2	12	0.19	15	<0.01	<20	0.34	<0.01	0.06	<2	4.21	N.A.	N.A.	N.A.	N.A.
Reference Materials																				
STD CDN-PGMS-15	Standard																			
STD CDN-PGMS-15	Standard																			
STD CSC	Standard																			
STD DS7	Standard	3	83	0.98	0.076	13	202	1.05	410	0.12	36	1.06	0.10	0.46	2	0.20				
STD DS7	Standard	<3	75	0.87	0.070	11	161	0.97	385	0.11	36	0.93	0.09	0.43	2	0.18				
STD DS7	Standard																			
STD OREAS45PA	Standard	<3	215	0.24	0.037	16	836	0.11	178	0.14	<20	3.67	<0.01	0.07	<2	<0.05				
STD OREAS45PA	Standard	<3	197	0.22	0.035	15	765	0.09	167	0.12	<20	3.23	<0.01	0.07	<2	<0.05				
STD OREAS45PA	Standard																			
STD OREAS76A	Standard																			
STD PD1	Standard																			
STD PD1	Standard																			
STD SO-18	Standard															58.13	14.10	7.60	3.34	6.35
STD SO-18	Standard															58.25	14.04	7.57	3.33	6.34
STD CSC Expected																				
STD OREAS76A Expected																				
STD DS7 Expected		5	84	0.93	0.08	13	179	1.05	410	0.124	39	0.959	0.073	0.44	4	0.19				
STD OREAS45PA Expected		0.18	221	0.2411	0.034	16.2	873	0.095	187	0.124		3.34	0.011	0.0665	0.011	0.03				
STD SO-18 Expected																58.47	14.23	7.67	3.35	6.42

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada  
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Sherman, Barry**  
 174 - 321 Yorkton Ave.  
 Penticton BC V2A 3V6 Canada

Project: None Given  
 Report Date: November 04, 2010

Page: 1 of 2 Part 1

QUALITY CONTROL REPORT

VAN10004278.2

Method	WGHT	3B	3B	3B	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D	1D				
Analyte	Wgt	Au	Pt	Pd	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb				
Unit	kg	ppb	ppb	ppb	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm				
MDL	0.01	2	3	2	1	1	3	1	0.3	1	1	2	0.01	2	8	2	2	1	0.5	3				
Pulp Duplicates																								
REP G1	QC																							
9 BEV 3-C 70-73 FT	Drill Core	1.57	10	<3	<2	5	83	11	55	0.4	24	17	908	3.51	5	<8	<2	<2	65	<0.5	<3			
REP 9 BEV 3-C 70-73 FT	QC					5	85	12	53	0.4	24	17	919	3.54	6	<8	<2	<2	66	<0.5	<3			
30 BEV 6 190-192 FT	Drill Core	1.45	9	<3	<2	3	31	3	68	<0.3	13	18	882	4.24	9	<8	<2	<2	123	<0.5	<3			
30 BEV 6 190-192 FT	QC					3	30	<3	65	<0.3	12	17	855	4.08	8	<8	<2	<2	118	<0.5	<3			
Core Reject Duplicates																								
8 BEV 3-C 126-127 FT	Drill Core	0.80	22	5	2	1	208	21	462	0.7	20	20	541	6.67	11	<8	<2	<2	20	3.4	<3			
8 BEV 3-C 126-127 FT	QC					21	3	<2	2	204	18	450	0.8	20	20	546	6.78	11	<8	<2	<2	20	3.3	<3
Reference Materials																								
STD CDN-PGMS-15	Standard		394	114	470																			
STD CDN-PGMS-15	Standard		359	92	422																			
STD CSC	Standard																							
STD DS7	Standard					22	102	69	408	1.0	55	9	627	2.40	54	<8	<2	5	79	5.9	<3			
STD DS7	Standard					19	100	61	376	0.9	48	8	577	2.21	47	<8	<2	5	67	5.4	4			
STD DS7	Standard																							
STD OREAS45PA	Standard					2	617	18	117	0.5	303	106	1063	16.58	6	<8	2	7	14	<0.5	<3			
STD OREAS45PA	Standard					1	569	14	109	0.3	274	100	1006	15.49	3	<8	3	7	13	<0.5	<3			
STD OREAS45PA	Standard																							
STD OREAS76A	Standard																							
STD PD1	Standard		553	468	573																			
STD PD1	Standard		564	491	594																			
STD SO-18	Standard																							
STD SO-18	Standard																							
STD CSC Expected																								
STD OREAS76A Expected																								
STD DS7 Expected						21	109	71	411	0.9	56	10	627	2.39	48	5	0.07	4	68	6.4	5			
STD OREAS45PA Expected						0.9	600	19	119	0.3	281	104	1130	16.559	4.2	1.2	0.043	6	14	0.09	0.13			
STD SO-18 Expected																								

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.