

ASSESSMENT REPORT

**BC Geological Survey
Assessment Report
33392**

TASEKO MINERAL PROPERTY TASEKO LAKES, BC, CANADA

CLAIM TENURES:

**208502, 208503, 208505, 208506, 208507, 208567, 208580,
208581, 208582, 208583, 208584, 208585, 208586, 208587,
208588, 208589, 208590, 208591, 208601, 209791, 209156,
560973, and 758528**

**CLINTON MINING DIVISION
MAP SHEET: NTS 0920.03
LATITUDE N 51° 06', LONGITUDE W 123° 24'**

**RECORDED OWNER:
OPERATOR:
AUTHOR:
DATE:**

**GREAT QUEST METALS LTD.
GRANITE CREEK GOLD LTD.
DR. MATHIAS W. WESTPHAL, P.GEO.
MARCH 30, 2012**

1 TABLE OF CONTENTS

1	TABLE OF CONTENTS	1
	SUMMARY	3
2	INTRODUCTION.....	6
2.1	TERMS OF REFERENCE.....	6
2.2	EXPLORATION PROGRAM 2011	6
2.3	SITE VISIT.....	6
3	RELIANCE ON OTHER EXPERTS	6
4	PROPERTY DESCRIPTION AND LOCATION	7
4.1	LOCATION	7
4.2	CLAIMS.....	7
5	ACCESSIBILITY, CLIMATE, PHYSIOGRAPHY, LOCAL RESOURCES AND INFRASTRUCTURE.....	8
5.1	ACCESSIBILITY	8
5.2	PHYSIOGRAPHY, VEGETATION AND CLIMATE.....	12
5.3	LOCAL RESOURCES AND INFRASTRUCTURE.....	12
6	HISTORY	12
7	GEOLOGICAL SETTING	13
7.1	REGIONAL GEOLOGY.....	13
7.2	PROPERTY GEOLOGY	13
7.2.1	<i>Structure</i>	14
7.2.2	<i>Geochronology</i>	14
8	DEPOSIT TYPES	17
9	ALTERATION AND MINERALIZATION	17
9.1	ALTERATION.....	17
9.2	MINERALIZATION	18
10	DRILLING AND EXPLORATION PROGRAM 2011.....	19
11	INTERPRETATION AND CONCLUSIONS	19
12	RECOMMENDATIONS.....	20
13	STATEMENT OF COSTS.....	21
14	REFERENCCESS	24

LIST OF TABLES

Table 1	Taseko property claims.....	8
Table 2	Selected mineralized Cu-Ag-Au sections from Drilling 2011.....	18
Table 3	Assay results from Rowbottom rock samples.....	19
Table 4	Collar data for Drilling 2011	19
Table 5	Breakdown of Costs 2011	21

LIST OF FIGURES

Figure 1. Taseko property location map.	10
Figure 2. Taseko property claim map.	11
Figure 3. Property geology map.....	15
Figure 4. Work Area Geology with 2011 drill hole locations.	16

APPENDIX I Assays

APPENDIX II Analytical Certificate

APPENDIX III Drill Logs

APPENDIX IV Drill Cross Sections

Summary

The Taseko property (the “Property”) is a 2,781.2 hectare mineral tenure located approximately 200 kilometers north of Vancouver, British Columbia. The registered owner of the Property is Great Quest Metals Ltd. (the “Property Owner”). The Property is located in prospective ground, based upon metal content and alteration, with partially defined copper-silver-gold and copper-molybdenum-silver-gold porphyry deposits. Exploration programs in the past have identified numerous exploration targets, including copper and gold soil anomalies.

The Property has four known showings: Empress [MINFILE 092O 033], Rowbottom [MINFILE 092O 029], Mohawk [MINFILE 092O 001], and Buzzer [MINFILE 092O 038].

The Empress prospect is considered to be an LO4 calc-alkaline porphyry Cu ± Mo ± Au classic-type deposit as defined by the BC Geological Survey’s Mineral Deposit Profiles. This has been the primary deposit being targeted on the Property so far. Several mineralized zones are hosted by volcano-sedimentary strata from the Taylor-Creek Group and is underlain by a barren quartz-monzonite-granodiorite of the Coast Plutonic Complex (CPC).

The Rowbottom, Mohawk, and Buzzer prospects are also considered as a LO4 calc-alkaline porphyry Cu ± Mo ± Au classic-type deposit as defined by the BC Geological Survey’s Mineral Deposit Profiles. In all three showings the porphyry copper-molybdenum-silver-gold mineralization is hosted by a biotite granodiorite, which is co-genetic to the above mentioned intrusive of the CPC at the Empress (Madeisky, 1994).

In addition, results from the recently flown ZTEM geophysical survey and the presence of adjacent MMI™ soil geochemical anomalies suggests the potential to expand the known Empress and Buzzer Zones mineralization and discover additional mineralized zones mainly between them on the Taseko property including copper, molybdenum, gold and silver.

Between 1909 and 1920, many large bog-iron deposits were discovered in the Taseko Lakes area (Crossland, 1920). The Taylor Windfall vein and conglomerate gold deposit north of the property was discovered 1920. The Buzzer, Rowbottom, Spokane (west of the property), and Mohawk followed 1928, and the Empress 1935. The whole area was explored intermittently by a number of operators until 2010. Programs carried out on the Property during this period included geological mapping, soil sampling, geophysics, and drilling lead to the discovery of Buzzer-West, East, and Granite Creek anomalies.

The Property was acquired by the Property Owners in 1989 from Westley Mines Ltd. and Alpine Exploration Corporation, affiliated companies. Many alteration zones within the Property were identified by drilling (Lambert/MacNeill, 1988-2008), soil sampling (Osbourne, 1998), and an EM survey (Windels, 1991). Westpine Metals Ltd. changed the name to Great Metal Quest Ltd. in 1998. In 1990 the Odin tenure has been acquired by

staking, 2007 the Mohawk tenure has been acquired from Speebo Inc, and in 2010 the GQ Fraction tenure has been acquired by staking.

In August 24th 2010, Granite Creek Gold Ltd. (“Granite Creek”) acquired the right to earn a 51% interest in the Property.

A seven week drilling program has been conducted from September 16 to November 3, 2011. Bad weather conditions delayed the start of the actual drilling, which was performed from October 7 to 27, 2011. More Core from Stewart, BC, has been contracted for the drilling, and Ranex Exploration Ltd. has been contracted to do the expediting, core logging/splitting/sampling, and the assessment report. Six drill holes from three drill pads have been performed totalizing 1290.5 meter, and 485 samples and 5 rock samples have been shipped to Acme Laboratories, Smithers, BC, and analyzed by Acme Laboratories, Vancouver, BC.

The region is underlain by Middle Jurassic to Upper Cretaceous marine and non-marine coarse clastic sediments and interfingering volcanic rocks that collected in a successor basin called the Tyaughton-Methow Trough (McLaren & Rouse, 1989). During the Late Cretaceous uplift of the area, a number of significant northwest-trending strike-slip and compressional faults occurred. Intrusive rocks of the Coast Plutonic Complex of Jurassic to Eocene age were emplaced in the south portions of the region and underlie most of the area of the Taseko claim group.

The northern portion of the property is part of the Taylor Creek Group and covered by tilt. However, mapping (Tipper, 1978; Glover et al, 1986; Glover and Schiarizza, 1987; McLaren and Rouse, 1989; Allen, 1991) indicates a series of rhyolitic to andesitic tuffs. Drilling results east and west of the Empress indicate that the altered volcanoclastic-sedimentary unit is sitting on a shelf of granitic rock extending for more than 10 km in an east-west direction. Since the protolith in this zone on the property is hard to identify due to the intense alteration overprint, Lambert/MacNeill (1988, 1989, 1991, 2008) distinguished four units defined by the type of alteration.

The main intrusive rock type on the southern and eastern portions of the property is a medium to coarse-grained quartz-granodiorite. Mapping in 1991 showed that there are two varieties of the CPC, a barren quartz-monzonite-granodiorite (Phase 1) and a mineralized biotite granodiorite (Phase 2) (Allen, 1991). The mineralization shows a porphyry copper-molybdenum-silver-gold style. The molybdenum is unique to this unit on the property.

Drilling results from the recent program confirm the southern limit of the mineralization at Buzzer West coincide the contact of the two different intrusives. The Buzzer zone shows some 30-40m sections with Cu 0.27% and Mo 0.01%, also some low grade Ag sections 40-50m, and patchy Au and Mo occurrences. In addition, the southern limit of the mineralization could be defined.

Rock samples from the Rowbottom showing show encouraging Cu, Au, and Zn values.

Further exploration work is recommended at the Rowbottom including rock sampling and MMI soil sampling program. Also MMI soil sampling is recommended in order to define the zone between Buzzer and Empress. Further drilling is recommended for the Buzzer Zone in order to define the western and southern extensions.

The total cost of the 2011 drilling and exploration program including site visit, core and rock sampling program (490 samples) with related expenditures is **\$1,199,381**.

2 Introduction

2.1 Terms of Reference

This report was commissioned by Granite Creek Gold Ltd. (“Granite Creek”) to assess exploration work in 2011 including drilling and rock sampling on the Taseko copper-molybdenum porphyry property in the Clinton Mining Division, British Columbia, and to make recommendations for an ongoing exploration program.

2.2 Exploration Program 2011

A seven week drilling program has been conducted from September 16 to November 3, 2011. Bad weather conditions delayed the start of the actual drilling, which was performed from October 7 to 27, 2011. More Core from Stewart, BC, has been contracted for the drilling, and Ranex Exploration Ltd. has been contracted to do the expediting, core logging/splitting/sampling, and the assessment report. Six drill holes from three drill pads have been performed totalizing 1290.5 meter, and 485 samples and 5 rock samples have been shipped to Acme Laboratories, Smithers, BC, and analyzed by Acme Laboratories, Vancouver, BC.

Two drill holes were located at the Buzzer West, and four drill holes were located in the Buzzer Zone.

In addition, 5 rock samples have been taken from outcrops at the Rowbottom showing. Helicopter from Whitesaddle, BC, Tatla Lake, and Mustang, AB, staging from Gold Bridge, BC, supported the program.

2.3 Site Visit

The author, Mathias Westphal, P.Geo., supervised the program including core logging, and was on site from October 2 to 30, 2011.

3 Reliance on Other Experts

The author has compiled this report with all due care and reviewed all available reports, listed at the end of this report under References. It is believed that the information contained within this report is accurate and reliable. Experienced exploration personnel have undertaken all previous work programs on the property, and qualified professionals wrote the referenced reports cited.

4 Property Description and Location

4.1 Location

The Taseko property is located 150 kilometers southwest of Williams Lake, British Columbia and 200 kilometers north of Vancouver as shown in Figure 1.

The Taseko property lies within the First Nation claims of the Esketemc National Government. Exploration permits must be obtained from the British Columbia Ministry of Forests, Mines and Land prior to carrying out further mechanized exploration on the property.

The property is in the Clinton Mining Division, within map sheet 092O.003. The coordinates of the center of the claim block are approximately 471,995mE and 5,661,516mN (UTM NAD83) or 51° 06' N latitude and 123° 24' W longitude.

4.2 Claims

The Taseko property is comprised of twenty-six Mineral Titles Online (MTO) mineral claim blocks, which total 2,781.2 hectares. The claims are owned Great Quest Metals Ltd. The claim statistics are listed in Table 1 and located in Figure 2.

Table 1 Taseko property claims

Tenure Number	Claim Name	Issue Date	Good to Date	Area in Hectares
208502	New Gold 3	Sept. 12, 1988	Nov. 1, 2014	300.00
208503	New Gold 2	Aug. 30, 1988	Nov. 1, 2014	250.00
208505	New Buzz	Sept. 26, 1988	Nov. 1, 2014	375.00
208506	New Gold 1	Sept. 24, 1988	Nov. 1, 2014	150.00
208507	New Gold 4	Sept. 24, 1988	Nov. 1, 2014	200.00
208567	Mars 1	Oct. 21, 1988	Nov. 1, 2014	25.00
208580	Mars 2	Oct. 21, 1988	Nov. 1, 2014	25.00
208581	Mars 3	Oct. 21, 1988	Nov. 1, 2014	25.00
208582	Mars 4	Oct. 21, 1988	Nov. 1, 2014	25.00
208583	Mars 5	Oct. 21, 1988	Nov. 1, 2014	25.00
208584	Mars 6	Oct. 21, 1988	Nov. 1, 2014	25.00
208585	Mars 7	Oct. 21, 1988	Nov. 1, 2014	25.00
208586	Mars 8	Oct. 21, 1988	Nov. 1, 2014	25.00
208587	Mars 9	Oct. 21, 1988	Nov. 1, 2014	25.00
208588	Mars 10	Oct. 21, 1988	Nov. 1, 2014	25.00
208589	Mars 11	Oct. 21, 1988	Nov. 1, 2014	25.00
208590	Mars 19	Oct. 21, 1988	Nov. 1, 2014	25.00
208591	Mars 20	Oct. 21, 1988	Nov. 1, 2014	25.00
208601	Syn	Nov. 4, 1988	Nov. 1, 2014	200.00
208791	Row	Aug. 14, 1988	Nov. 1, 2014	400.00
209156	Odin	July 13, 1990	Nov. 1, 2014	500.00
560973	Mohawk	June 20, 2007	Nov. 20, 2014	40.60
758528	GQ Fraction	Apr. 26, 2010	Apr. 26, 2014	40.60

5 Accessibility, Climate, Physiography, Local Resources and Infrastructure

5.1 Accessibility

Road access to the property is obtained by traveling 80 kilometers west of Williams Lake on paved provincial highway 20 to Hanceville. A 170 kilometer gravel four-wheel drive road leads southwest from Hanceville past the east side of Taseko Lakes. At the south-end of the lakes the road parallels the Taseko River to the east to the Granite Creek road and from there onto the property (Figure 1). The Ministry of Forests, Mines, and Land has blocked the access, approximately 7 km south of the Taseko Lake Lodge, due to a washout and a related fatal accident in 2007. The Property Owner, along with other resource property owners in the area like HighPointe Exploration Inc., intend to lobby government to allow reopening of this important (Beece Creek) resource access road, which was originally built by mining and mineral exploration companies.

Helicopter service is the only access for now and is available from Pemberton (approx. 60 min), Lillooet (approx. 40 min) or Gold Bridge (approx. 15 min). The Property can also be accessed using the Whitesaddle helicopter service at King Ranch on Tatla Lake (130km NW of the Property, approx. 55 min).

Figure 1. Taseko property location map.

Figure 1

LOCATION





Figure 2. Taseko property claim map.



5.2 *Physiography, Vegetation and Climate*

The property is situated in the alpine regions of the coast mountain ranges and exhibits typical U-shaped valleys and ragged ridgelines. The elevation ranges from 1450 meters on Taseko River to 2,350 meters at the highest peaks on the south side of the property. Because of the effects of glaciations, the relief is steep to rugged on the ridges and flat in the Taseko River and Granite Creek valley floors.

Vegetation consists of Lodgepole Pine, Engelmann Spruce and Whitebark Pine in the Granite Creek valley with sub alpine fir, Common Juniper, Soapberry, Kinnikinnick, Lichen and various grasses at higher elevations (Valentine, 1983).

The climate is cold in winter and hot in the summer with limited precipitation and frequently high wind conditions. Work season is mid June to late September. The Atmospheric Environment Service climate stations in the area (Dog Creek) record a mean annual temperature of 4.0°C, a mean annual total precipitation of 39 cm and a mean snowfall of 180 cm (Valentine et al, 1987).

5.3 *Local Resources and Infrastructure*

A network of drill roads provides access to the slope of the Empress, and the upper and central part of the property, and along the Granite Creek.

The area is relatively isolated with little infrastructure at present. The nearest settlement is a series of hunting and fishing lodges on and near Taseko Lake. The Taseko Lake Lodge owned by Taseko Lake Outfitters (www.tasekolake.com) provides the closest accommodation for the Tasco project. At the south-end of Taseko Lake a 4x4 road parallels the Taseko River to the east to the Granite Creek road and from there onto the property, but Ministry of Forests, Mines, and Land blocked the access approximately 7 km south of the Taseko Lake Lodge, due to a washout. As a result, helicopter support is required for now.

6 *History*

The Property covers four known Cu+/-Mo+/-Ag+/-Au showings: Empress [MINFILE 092O 033], Rowbottom [MINFILE 092O 029], Mohawk [MINFILE 092O 001], and Buzzer [MINFILE 092O 038].

Between 1909 and 1920, many large bog-iron deposits were discovered in the Taseko Lakes area (Crossland, 1920). The Taylor Windfall vein and conglomerate gold deposit north of the property was discovered in 1920. The Buzzer, Rowbottom, Spokane (west of the property), and Mohawk followed in 1928, and the Empress 1935. The whole area was

explored intermittently by a number of operators until 2010. Programs carried out on the Property during this period included geological mapping, soil sampling, geophysics, and drilling lead to the discovery of Buzzer-West, East, and Granite Creek anomalies.

The Property was acquired by the Property Owners in 1989 from Westley Mines Ltd. and Alpine Exploration Corporation, affiliated companies. Several additional mineralized alteration zones within the Property were identified by drilling (1988-2008), mapping (1991), soil sampling (1998) and an EM survey (1991). Westpine Metals Ltd. changed the name to Great Metal Quest Ltd. in 1998. In 1990 the Odin tenure has been acquired by staking, 2007 the Mohawk tenure has been acquired from Speebo Inc, and in 2010 the GQ Fraction tenure has been acquired by staking.

In August 24th 2010, Granite Creek Gold Ltd. (“Granite Creek”) acquired the right to earn a 51% interest in the Property.

7 Geological Setting

7.1 Regional Geology

The region is underlain by Middle Jurassic (~160 Ma) to Upper Cretaceous (~110 Ma) marine and non-marine coarse clastic sediments and interfingering volcanic rocks that collected in a successor basin called the Tyaughton-Methow Trough (McLaren & Rouse, 1989). During the Late Cretaceous (~70 Ma) uplift of the area, a number of significant northwest-trending strike-slip and compressional faults occurred. Intrusive rocks of the Coast Plutonic Complex (“CPC”) of Jurassic to Eocene age were emplaced in the south and southwest portions of the region (see Figure 3).

The Taseko property is located within the CPC and its contact with the Late Cretaceous volcanoclastic/sedimentary units of the Tyaughton-Methow Trough at Taseko River. The intrusive complex consists of quartz diorite to granodiorite, which have been subsequently crosscut by a series of quartz-rich felsic porphyritic stocks and dykes. The Tyaughton-Methow Trough units closest to the property are part of the Upper Cretaceous Powell Creek Formation and the Lower Cretaceous Taylor Creek Group (McLaren & Rouse, 1989). The Powell Creek Formation consists of intermediate to felsic pyroclastics and flows with minor laminations of argillites, quartz-rich siltstones and sandstones. The Taylor Creek Group is characterized by rhyolitic to basaltic tuffs and flows and interlaminated argillites and sandstones. These lithologic sequences represent a volcanic island arc environment (McLaren & Rouse, 1989).

7.2 Property Geology

The main intrusive rock type on the southern portions of the property is a medium to coarse-grained quartz-granodiorite (Figure 4). Mapping in 1991 showed that there are

two co-genetic varieties of the CPC, a barren quartz-monzonite-granodiorite (Phase 1) and a mineralized biotite granodiorite (Phase 2) (Allen, 1991). The mineralization shows a porphyry copper-molybdenum-silver-gold style. The molybdenum is unique to this unit on the property.

The northern portion of the property is part of the Taylor Creek Group and covered by tilt. However, mapping (Tipper, 1978; Glover et al, 1986; Glover and Schiarizza, 1987; McLaren and Rouse, 1989; Allen, 1991) indicates a series of rhyolitic to andesitic tuffs. Drilling results east and west of the Empress indicate that the altered volcanoclastic-sedimentary unit is sitting on a shelf of granitic rock extending for more than 10 km in an east-west direction.

A series of dikes is associated with the granodiorites (Allen, 1991).

7.2.1 Structure

The major structure in the area is the Tchaikazan Fault (see Figure 3). It trends to the northwest and typically separates Lower and Upper Cretaceous rocks in the Tyaughton-Methow Trough. This fault has been mapped to have a dextral transcurrent movement of more than 30 kilometers (McLaren & Rouse, 1989), but has not been identified on the property due to tilt overburden. Other major faults that are parallel to the Tchaikazan Fault and within the Tyaughton-Methow Trough sediment package are the Chita Creek Fault and the Yalakom Fault.

7.2.2 Geochronology

Argon age dating from McMillan (1976) from biotite in granodiorite gave 86.2 \pm 2.5 Ma, from sericite from the altered Mohawk gave 84.9 \pm 2.5 Ma, and biotite from a postmineral dike gave 84.7 \pm 2.5 Ma. Argon-argon plateau age determination from Panteleyev on sericite and alunite from McLure Creek, N-W of the property, gave 85.9 \pm 1 Ma and 85.3.3 \pm 1 Ma, respectively (Osbourne and Allen, 1998). This data is well within the error range and a slightly older age for the intrusive than the alteration zone of approximately 1 Ma, which is in accordance with standard cooling rates for batholiths with associated convecting porphyry systems. A system this size without water involved and, therefore, only based on conduction will take 4-5 Ma to cool (Westphal et al., 2003).

Figure 3. Property geology map.





Figure 4. Work Area Geology with 2011 drill hole locations.



8 Deposit Types

Mineralized showings within the CPC include disseminated porphyry-type (i.e. Empress [MINFILE 092O 033], Rowbottom [MINFILE 092O 029], Mohawk [MINFILE 092O 001], Buzzer [MINFILE 092O 038], and Copper Zone [MINFILE 092O 025]), vein and fracture controlled (i.e. Spokane [MINFILE 092O 004], Massena [MINFILE 092O 067] and Top [MINFILE 092O 037]) and intrusive breccia-type (i.e. Mohawk [MINFILE 092O 001]) deposits.

To the north of the CPC and within the volcanics several copper and gold deposits (i.e. the Taylor-Windfall [MINFILE 092O 028] vein deposit and Empress [MINFILE 092O 033]) porphyry deposit have been discovered.

The major metals in these CPC deposits are copper, molybdenum and gold with minor silver. In the Tyaughton-Methow Trough, the major metals are copper and gold with minor zinc and lead mineralization (McLaren & Rouse, 1989).

The Property has four known showings: Empress [MINFILE 092O 033], Rowbottom [MINFILE 092O 029], Mohawk [MINFILE 092O 001], and Buzzer [MINFILE 092O 038].

The Empress prospect is considered to be an LO4 calc-alkaline porphyry Cu ± Mo ± Au classic-type deposit as defined by the BC Geological Survey's Mineral Deposit Profiles. This has been the primary deposit being targeted on the Property so far.

The Rowbottom, Mohawk, and Buzzer prospects are also considered as a LO4 calc-alkaline porphyry Cu ± Mo ± Au classic-type deposit as defined by the BC Geological Survey's Mineral Deposit Profiles.

9 Alteration and Mineralization

9.1 Alteration

The alteration of the two co-genetic granodiorites is in general weak sericitic of the feldspars with some chlorite alteration of the mafic minerals. In fracture zones there is strong sericitic alteration with also strong chloritic alteration noticed. In fault zones and gouges there is sericitic to clay alteration. However, the alteration pattern does not seem to correlate with mineralization.

9.2 Mineralization

The mineralization within the Buzzer are described in drill core logs and occurs within the medium-grained biotite granodiorite. Chalcopyrite is the primary sulphide mineral and appears within biotite pods <1cm and disseminated. Also, it occurs on fracture surfaces as dry veins as well as with quartz veins up to 2cm. Quartz veins with and without pyrite and/or chalcopyrite are noticed to be up to 10cm. Molybdenite occurs as irregular pods and in dry veins and localized quartz veinlets with or without Chalcopyrite within the biotite granodiorite. Some Molybdenite veins are with pyrite only. Molybdenite occurs with Chalcopyrite in hole GC11-74 over the same interval over 57m with 0.01% Mo. However, higher grade Mo values ranging from 0.04 to 0.2% are restricted to narrow zones from 1 to 4m in holes GC11-74 and 75, and do not seem to correlate with other elements, with some minor overlaps though (see assays in Appendix). Apparently, the Chalcopyrite values decrease with increasing pyrite values. The Ag values in hole GC11-75 do not correlate with other metal values, but indicate a possible extension to the West. In general, the results of GC11-74 indicate a possible extension to the east.

Drilling GC11-78 to the south and GC11-79 to the west defines the borders of the Buzzer zone. GC11-79 shows some Cu and Ag values, but needs to be followed up with more drilling to the west.

Drilling at the Buzzer West showing is two-folded. The vertical hole GC11-76 hit some intersections at 35 and 50m depth of about 5m not true width with increased Au, Ag, and Cu values, which presumably produced the soil anomaly noticed in previous surveys. The hole GC11-77 was drilled into the barren granodiorite in order to determine the possible chance to hit the mineralized phase II granodiorite at depth.

Table 2 Selected mineralized Cu-Ag-Au sections from Drilling 2011

Hole #	Au			Cu			Ag		
	from [m]	to [m]	g/T	from [m]	to [m]	[%]	from [m]	to [m]	g/T
GC11-74	11.4-69	57.6	0.17	11.4-69	57.6	0.237	11.4-69	57.6	1.52
GC11-75	14.1-42	27.9	0.11	14.1-51	33.9	0.14	12-53	41	0.98
	68-96	28	0.09	72-87	15	0.19	60-108	48	0.49
GC11-76	33-41	8	0.15	33-38	5	0.23	33-38	5	0.58
	46-54	5	0.14	46-54	5	0.19	46-54	5	0.42
GC11-77	no significant sections								
GC11-78	no significant sections								
GC11-79	no significant results			25-34	9	0.11	21-34	13	0.43
				101.4-103	1.6	0.31			
				140-145	5	0.24	140-145	5	0.58

The mineralization at the Rowbottom showing occurs in two shear zones, each 5 to 6 meters wide and 100m apart, hosted in propylitic and sericitic altered biotite granodiorite. The mineralization comprises of disseminated pyrite, chalcopyrite, sphalerite, galena, and locally Au and Ag (Table 3).

Table 3 Assay results from Rowbottom rock samples

	Au	Cu	Pb	Zn	Ag
Sample #	g/T	PPM	PPM	PPM	g/T
318513	<0.005	17.1	18	108	0.1
318514	1.153	657.4	4356.8	696	8.4
318515	0.117	42.4	492.7	105	3.5
318516	1.222	239.6	2797.7	3188	14.1
318517	0.052	74.7	708.7	1143	10.9

10 Drilling and Exploration Program 2011

A seven week drilling program has been conducted from September 16 to November 3, 2011. Bad weather conditions delayed the start of the actual drilling, which was performed from October 7 to 27, 2011. More Core from Stewart, BC, has been contracted for the drilling, and Ranex Exploration Ltd. has been contracted to do the expediting, core logging/splitting/sampling, and the assessment report. Six drill holes from three drill pads have been performed totalizing 1290.5 meter, and 485 samples and 5 rock samples have been shipped to Acme Laboratories, Smithers, BC, and analyzed by Acme Laboratories, Vancouver, BC.

Table 4 Collar data for Drilling 2011

	E	N	Az	Dip	Depth [m]
GC11-74	475340	5661094		-90	204
GC11-75	475340	5661094	254	-55	177
GC11-76	474977	5660803		-90	110.5
GC11-77	474977	5660803	231	-60	399
GC11-78	475320	5660946	205	-60	192
GC11-79	475320	5660946	287	-60	208
				total	1290.5

Two drill holes were located at the Buzzer West (GC11-76 and GC11-77), and four drill holes (GC11-74/75 and GC11-78/79) were located in the Buzzer Zone (Figure 4). In addition, 5 rock samples have been taken from outcrops at the Rowbottom showing.

11 Interpretation and Conclusions

Drilling results from the recent program confirm the southern limit of the mineralization at Buzzer West coincide the contact of the two different intrusives. The Buzzer zone shows some 30-40m sections with Cu 0.27% and Mo 0.01%, also some low grade Ag sections 40-50m, and patchy Au and Mo occurrences. In addition, the southern limit of the mineralization could be defined in both zone, the Buzzer West and Buzzer Zone.

Rock samples from the Rowbottom showing show encouraging Cu, Au, Ag, and Zn values.

12 Recommendations

Further exploration work is recommended at the Rowbottom including rock sampling and MMI soil sampling program. Also MMI soil sampling is recommended in order to define the Zone between Buzzer and Empress. Further drilling is recommended for the Buzzer Zone in order to define the eastern, western, and southern extensions.

13 Statement of Costs

The total cost of the 2011 drilling and exploration program including site visit, core and rock sampling program (490 samples) with related expenditures is **\$1,041,881**. See Table 5 for the breakdown of costs.

Table 5 Breakdown of Costs 2011

<i>Wages</i>				
Title	Days Worked	Rate (\$) per day	Period	Total Paid
Labourer	24	\$ 350.00	September 1 - October 15, 2011	\$ 8,400
Labourer	20	\$ 350.00	September 1 - October 15, 2011	\$ 7,000
Camp Builder	21.5	\$ 400.00	September 1 - October 15, 2011	\$ 8,600
Core Cutter	19.5	\$ 350.00	September 1 - October 15, 2011	\$ 6,825
Driver	16.5	\$ 350.00	September 1 - October 15, 2011	\$ 5,775
Labourer	11	\$ 350.00	September 1 - October 15, 2011	\$ 3,850
Pad Builder	17	\$ 400.00	September 1 - October 15, 2011	\$ 6,800
Pad Builder Helper	13	\$ 350.00	September 1 - October 15, 2011	\$ 4,550
Labourer	15	\$ 350.00	September 1 - October 15, 2011	\$ 5,250
Labourer	8	\$ 400.00	October 16 - November 4, 2011	\$ 3,200
Labourer	8	\$ 350.00	October 16 - November 4, 2011	\$ 2,800
Labourer	9	\$ 350.00	October 16 - November 4, 2011	\$ 3,150
Labourer	8	\$ 400.00	October 16 - November 4, 2011	\$ 3,200
Labourer	17	\$ 350.00	October 16 - November 4, 2011	\$ 5,950
Labourer	12	\$ 350.00	October 16 - November 4, 2011	\$ 4,200
Core Cutter	18	\$ 350.00	October 16 - November 4, 2011	\$ 6,300
Core Cutter	8	\$ 400.00	October 16 - November 4, 2011	\$ 3,200

\$ 89,050

Other fees

Work Type	Description	Amount
Travel & Lodging	Mackenzie Travel, Sandman Inn, White Saddle Ranch,	\$ 14,862
Helicopter	White Saddle Air , Sarvair Aviation Ltd., Mustang Helicopters, CC Helicopters	\$ 297,501
Drilling	More Core Diamond Drilling, Castle Fuels, Treeline, Smithers Lumber,	\$ 324,606
	David West	
Food	Well-Done Cook Agency	\$ 32,462
Shipping/Expediting	Overland, SES Jack, Tyler's Towing/Bandstra, Rod Johnson/Greyhound	\$ 28,649
Camp	Tyak Wilderness Resort, White Saddle Ranch Country Inn	\$ 34,251
Camp Supplies	BV Home Centre, Evergreen, Midway Services, Jade,	\$ 15,090
	Tower Communications, Steve Soby	
Truck/Trailer		\$ 35,600
		\$ 883,021

Assay Costs - Acme Labs

Work Type	Description	Amount
Crush and Pulverize 250 g	482 samples @ \$6.15 per sample	\$ 2,964
Overweight prep charges 100 g	23,402 samples @ \$0.06 per sample	\$ 1,404
30g Au Fire Assay	490 samples @ \$13.73 per sample	\$ 6,728
0.25g Acid Digestion	490 samples @ \$16.06 per sample	\$ 7,869
Disposal Costs		\$ 170
		\$19,135

Planning, supervision and report writing fees

Title	Hours Worked	Rate (\$) per hour	Period	Total Paid
Geologist	72	\$ 60.00	August 1, 2011 - January 31, 2012	\$ 4,320

Title	Days Worked	Rate (\$) per day	Period	Total Paid
Geologist	30	\$ 475.00	August 1, 2011 - January 31, 2012	\$ 14,250
				\$ 18,570

Office Overhead	Ranex Exploration Admin fees	\$ 132,105
------------------------	------------------------------	-------------------

TOTAL EXPENSES:			\$ 1,041,881
------------------------	--	--	---------------------

14 References

- Allen, D.G., 1991, Geological and Geochemical Report on the Taseko Alteration Zone. Internal report for ASARCO Exploration Company of Canada and Westpine Metals Ltd.
- Crossland, F.J., 1920, Taseko Valley Iron-Ore Deposits; in: BC Minister of Mines Annual Report, 1920, p. 175-181.
- Glover, J.K., Schiarizza, P., Unhoefer, P., and Garver, J., 1986, Geology of the Warner Pass Area, NTS 92O/3, BCGS Open File Map 1987/3.
- Glover, J.K., and Schiarizza, P., 1987, Geology and Mineral Potential of the Warner Pass Map Sheet, in: Geological Fieldwork 1986, BC MEMPR Paper, 1987-1, p. 157-169.
- James Askew Associates Inc., 1991, ASARCO Incorporated, Taseko Project – British Columbia, Canada, pre-feasibility study. Unpublished company report, ASARCO Inc.
- Lambert, E., 1988, Report on the 1988 Exploration Program of the Taseko Property; Alpine Exploration Corp., Assessment Report #18,921.
- Lambert, E., 1989a, Geology, Geochemistry and Mineralization of the Taseko Property; Prospectus Report for Westpine Metals Ltd.
- Lambert, E., 1989b, Geochemical and Diamond Drilling Program of the Taseko Property; Westpine Metals Ltd., Assessment Report #19,350.
- Lambert, E., 1991a, Diamond Drilling Program of the Taseko Property; Westpine Metals Ltd., Assessment Report #20,889.
- Lambert, E., 1991b, 1991 Diamond Drilling Program of the Taseko Property; Westpine Metals Ltd., BC Ministry of Energy, Mines and Mineral Resources, Assessment Report #21,985.
- Lambert, E., 1996, Report on the 1996 Corundum Exploration Program of the Taseko Property; Westpine Metals Ltd., Assessment Report #24,753.
- MacNeill, E., 2008, 2007 Diamond Drilling Program on the Taseko Property; Great Quest Metals Ltd., Assessment Report #30,169.
- McLaren, G. P. and Rouse J. N., 1989, Geology and Mineral Occurrences in the Vicinity of Taseko Lakes (92O/3 – 6), BCMEMPR Geological Fieldwork 1988, Paper 1989-1.

- Madeisky, H.D., 1994, Lithochemical Data Analysis, Taseko Porphyry Copper-Gold Project, Central B.C., internal company report, Westpine Metals Ltd.
- Madeisky, H.D., 1998, Lithochemical Data Analysis, Taseko Porphyry Copper-Gold Project, Central B.C., internal company report, Westpine Metals Ltd.
- McMillan, W.J., 1976, Granite Creek Porphyry, 92O/3W; BC MEMPR, Geological Fieldwork 1976, p. 67-84.
- Osbourne, W.W., and Allen, D.G., 1998, The Taseko Copper-Gold-Molybdenum Deposits, Central British Columbia, in: Canadian Institute of Mining, Special Volume 46, p. 441-450.
- Osbourne, W.W., 1998, Report on the 1998 Exploration Program of the Taseko Property, Assessment Report 25,759.
- Osbourne, W.W., 1999, Report on the Evaluation of the Gem Quality of Sapphires on the Taseko Property, 1999.
- Tipper, H.W., 1978, Taseko Lakes (92O) Map Area; Geological Survey of Canada, Open File Map 534.
- Uchida, K., Nakashima, K., Shibuya, A, Robert, I., Aoki, K., 1970, Geological Survey, Taseko Property; 1 in = 1000 ft. Map for Sumitomo Metal Mining Canada Ltd.
- Valentine, K. W. G., Watt, W. and Bedwany, A. I., 1987, Soils of the Taseko Lakes area, British Columbia, Report No. 36, British Columbia Soil Survey, Agriculture Canada.
- Visser, S., 1995, Induced Polarization Survey, Geophysical Report on the Taseko Property, internal company report for Westpine Metals Ltd.
- Westphal, M., Schumacher, J.C., and Boschert, S., 2003. High-Temperature Metamorphism and the Role of Magmatic Heat Sources at the Rogaland Anorthosite Complex in Southwestern Norway. *Journal of Petrology*, 44, 1145-1162.
- Windels, C.O., 1991, Dighem IV Interpretation, for ASARCO Inc. and Westpine Metals Inc., internal companies report.

www.sgs.com/geochem

15 Certificate of Author



White North West Consulting
Dr. Mathias Westphal
3712 1st Avenue, Smithers, B.C., Canada
Po Box 2575 V0J 2N0
phone: (250) 469 – 9024
Cell : (250) 877-9322
e-mail: mathiasw@xplornet.com

I, Dr. Mathias W. Westphal, P.Geo., do hereby certify that:

1. I am principal of:
White North West Consulting
3712 1st Avenue
Po Box 2575
Smithers, B.C., Canada
V0J 2N0
2. I graduated with a Masters of Science degree in Mineralogy from Albert-Ludwigs-University at Freiburg, Germany in 1994. In addition, I have obtained a Masters of Arts degree in Geography from Albert-Ludwigs-University at Freiburg, Germany in 1992.

Since 1998 I hold a Ph.D. in Mineralogy from Albert-Ludwigs-University at Freiburg, Germany.
3. I am a member of the:
 - APEGBC – Association of Professional Engineers and Geoscientists
 - DMG – German Mineralogical Society (Deutsche Mineralogische Gesellschaft).
4. I have worked as a Mineralogist/Geologist for a total of 17 years since my Masters of Science graduation from university.
5. I am the author of this Assessment Report titled “Assessment Report, Taseko Mineral Property” and dated March 30, 2012, and take responsibility for the entire report (the “Assessment Report”).
6. I am not aware of any material fact or material change with respect to the subject matter of the Assessment Report that is not reflected in the Assessment Report, of which the omission to disclose would make the Assessment Report misleading.

Dated at 30th Day of March 2012.



Dr. Mathias Westphal, P.Geol.

APPENDIX I

Assays

Taseko Property Technical Report

GC-11-74			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni
Sample #	From	To	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM
			MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1
			Standards	section							
1041301	11.37	13	1.63	3.92	0.155	56.1	2879.7	6.2	37	1.4	25.2
1041302	13	15	2	3.9	0.089	55.7	1527.9	5.1	34	1	24.6
1041303	15	17	2	4.28	0.154	161.7	2843	5.9	30	1.5	30.7
1041304	17	18	1	2.86	0.363	400.2	4425.5	9.6	34	3.5	37.1
1041305	17	18 Duplicate	1	2.84	0.185	358.8	4684.3	10.3	36	3	36
1041306	18	21	3	5.27	0.56	212.9	5723.4	11.3	36	3.2	32.3
1041307	21	24	3	6.29	0.248	119.2	3668.5	7.8	37	2.7	30.5
1041308	24	27	3	5.71	0.125	201.3	3603.9	6.9	34	2.3	28.8
1041309	27	30	3	7.42	0.126	97.3	1711.8	8.4	36	1.1	27.3
1041310	30	33	3	7.53	0.113	215.4	4274.8	7.7	36	2.5	31.2
1041311	33	36	3	6.47	0.239	67.7	2138.9	11.3	40	1.7	30.2
1041312	36	39	3	6.82	0.089	94	1491.3	6.3	32	0.9	27.5
1041313	39	42	3	7.23	0.67	2.2	2753.8	6.8	33	1.8	28.6
1041314	42	45	3	7.62	0.114	141.8	1657.7	6.1	31	1.3	26.3
1041315	45	48	3	6.56	0.084	4.1	1669.9	6.4	37	1	26.2
1041316	48	51	3	6.68	0.041	17.5	1144.2	6.1	34	0.8	26.6
1041317	51	52.2	1.2	2.72	0.239	9.9	3103.6	6.8	35	2.5	26.4
1041318	52.2	52.95	0.75	1.86	<0.005	1.4	146.4	3.8	80	0.2	30.6
1041319	52.95	55	2.05	4.51	0.037	2.1	674.9	6.9	31	0.5	23
1041320	55	55 Cm-2	0	0.07	1.436	289.2	9806.5	82	135	5.1	35.6
1041321	55	57	2	5.35	0.017	7.6	657.3	8.1	31	0.5	21.6
1041322	57	60	3	6.89	0.129	12.1	1810.9	7.6	39	1.3	24.7
1041323	60	62.66	2.66	6.67	0.024	7.3	879.8	8.6	31	0.7	22.6
1041324	62.66	64.17	1.51	3.93	<0.005	1	36.6	3.2	91	0.1	31.5
1041325	64.17	66	1.83	5.3	0.054	18.8	1496.5	7	31	1.2	23.8
1041326	66	68.65	2.65	6.5	0.257	7.4	4182.4	11.3	33	2	20.3
1041327	68.65	70.3	1.65	4.41	<0.005	1.6	74	4	94	0.1	31.7
1041328	70.3	72	1.7	4.15	0.015	3.2	458.4	8.4	37	0.4	22.4
1041329	72	75	3	7.74	<0.005	3.4	119.2	10.3	42	0.2	19.8
1041330	75	77	2	4.98	0.008	6	468.5	8.9	40	<0.1	22
1041331	77	79	2	5.17	<0.005	28.2	663.7	8.7	39	0.2	22.2
1041332	79	81.9	2.9	7.63	0.029	3.1	1226.4	7.6	35	0.5	21
1041333	81.9	82.75	0.85	1.09	<0.005	1.1	165.8	10.9	69	0.2	29.7
1041334	82.75	85	2.25	5.96	0.059	3.5	1561.5	7.5	37	0.6	22.4
1041335	85	87	2	4.84	0.018	2.9	493.4	6.2	45	0.2	17.9
1041336	87	90	3	8.05	0.009	2.8	249.7	7.9	42	<0.1	19.8
1041337	90	93	3	7.68	<0.005	2.1	290.9	7.1	28	0.1	13.9
1041338	93	96	3	7.86	0.075	2.5	562.7	7.3	32	0.4	17.7
1041339	96	99	3	6.7	0.015	4.3	700	6.1	28	0.4	16.2
1041340	99	99 Blank	0	0.24	<0.005	0.8	18.9	30	3	<0.1	0.3
1041341	99	102	3	7.84	<0.005	3.4	236.8	7.3	29	0.1	16.1
1041342	102	104	2	6.09	<0.005	4.9	123.1	6.5	29	<0.1	17.3
1041343	104	106.15	2.15	6.54	<0.005	2.8	243.8	7.2	39	0.1	18.2
1041344	106.15	107.3	1.15	2.88	<0.005	1	46.8	10.5	61	<0.1	17.8
1041345	107.3	109	1.7	4.51	<0.005	5.9	101.5	7.4	29	<0.1	12.3

Taseko Property Technical Report

GC-11-74	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001
Sample #														
1041301	8.4	217	2.03	6	1.8	<0.1	7.5	456	<0.1	0.5	0.5	90	1.75	0.055
1041302	8.3	192	1.77	6	2.8	<0.1	9.3	455	0.2	0.6	0.4	81	1.23	0.052
1041303	8.5	181	1.83	9	2.7	<0.1	8.9	472	<0.1	0.6	0.3	76	1.55	0.054
1041304	10.6	160	1.91	6	5.5	1.2	9.2	445	0.3	0.6	0.6	71	1.44	0.044
1041305	10	159	2	6	6.4	<0.1	9	413	<0.1	0.6	0.8	72	1.29	0.05
1041306	10.4	158	2.17	3	13.8	0.1	12	279	0.6	0.5	0.6	79	0.55	0.046
1041307	9.4	195	2	5	10.1	<0.1	9.6	428	0.4	0.7	0.5	75	1.36	0.054
1041308	9.3	184	1.89	6	17.1	0.1	9.9	409	0.2	0.7	0.6	70	1.16	0.056
1041309	9.6	214	1.79	5	3.8	<0.1	8.9	427	0.1	0.5	0.4	82	1.69	0.052
1041310	10.1	206	2.14	6	4.8	0.3	8.8	461	<0.1	0.5	0.4	82	1.86	0.061
1041311	11	238	2.31	6	1.5	0.1	8.9	410	<0.1	0.7	0.8	108	1.5	0.05
1041312	11.1	210	2.35	6	1.2	<0.1	8.9	462	<0.1	0.5	0.4	100	1.94	0.057
1041313	10.2	219	2.23	6	2.2	<0.1	9	402	<0.1	0.5	0.5	84	1.37	0.054
1041314	9.2	232	3.4	7	1.2	0.2	8.3	435	<0.1	0.4	0.4	119	1.67	0.05
1041315	10	287	3.02	7	2.4	<0.1	8.4	396	<0.1	0.6	0.4	81	1.08	0.048
1041316	9.4	256	3.19	6	1.3	<0.1	8.6	395	<0.1	0.5	0.2	91	1.46	0.051
1041317	9.6	274	3.97	8	2	<0.1	8.9	446	<0.1	0.4	0.4	106	1.59	0.049
1041318	35.6	1146	6.91	39	2.1	<0.1	2	490	0.2	1.6	<0.1	217	4.7	0.123
1041319	8.5	254	3.03	7	1.6	<0.1	8.2	471	<0.1	0.5	0.2	84	1.86	0.05
1041320	21.5	393	4.92	33	5.3	1.8	10.2	199	3.2	20.8	3.3	101	1.61	0.077
1041321	8.3	220	2.65	7	1.6	<0.1	9.7	466	<0.1	0.5	<0.1	84	1.81	0.05
1041322	8.8	263	3.18	8	1.9	<0.1	9.1	417	0.1	0.5	0.5	98	1.31	0.05
1041323	8.3	243	2.55	10	1.8	<0.1	10.4	446	0.3	0.6	0.2	73	1.7	0.055
1041324	43	1140	6.94	105	0.6	<0.1	0.8	510	0.3	2.4	<0.1	225	6.95	0.135
1041325	8.3	248	2.97	8	3.5	0.1	8.7	488	0.1	0.6	0.1	91	1.77	0.044
1041326	8.5	218	2.56	11	2.5	0.3	12.1	458	<0.1	0.6	0.2	71	1.49	0.039
1041327	42.1	1096	7.02	85	0.8	<0.1	1.3	434	0.3	2.2	<0.1	223	6.17	0.125
1041328	8.9	299	3.09	10	2.5	<0.1	9.6	353	<0.1	0.7	0.2	87	0.85	0.045
1041329	9.8	353	2.68	10	2.5	<0.1	10.4	410	0.2	0.8	<0.1	74	1.67	0.045
1041330	8.8	322	2.73	9	2.5	<0.1	9	354	<0.1	0.7	0.2	77	0.95	0.04
1041331	9.8	260	3.22	10	1.4	<0.1	8.9	452	<0.1	0.6	0.1	93	1.51	0.05
1041332	8.8	230	2.82	10	1.7	<0.1	9	463	<0.1	0.6	0.1	97	1.58	0.047
1041333	32.6	489	5.03	37	6.8	<0.1	1	535	1	3.5	<0.1	236	2.07	0.157
1041334	8.1	228	2.6	10	1.1	<0.1	8.9	439	0.3	0.8	0.5	105	1.26	0.038
1041335	8	365	2.48	7	5.5	<0.1	8.6	333	0.2	0.8	0.2	74	1.07	0.039
1041336	8.9	286	2.52	9	1.5	<0.1	8.8	433	0.1	0.7	0.2	70	1.31	0.041
1041337	7	206	2.39	8	1.3	<0.1	9.5	445	0.2	0.6	0.2	62	1.69	0.038
1041338	7.4	206	2.49	7	1.7	<0.1	9.9	432	0.1	0.7	0.2	69	1.41	0.044
1041339	6.6	179	2.5	5	1.5	<0.1	10.1	461	<0.1	0.6	0.2	74	1.51	0.035
1041340	0.4	27	0.2	9	2	<0.1	0.2	4340	<0.1	0.2	<0.1	4	35.72	0.006
1041341	6.9	218	2.48	7	2.1	<0.1	9.2	324	<0.1	0.7	<0.1	68	1.01	0.037
1041342	7.7	202	2.54	7	1.8	<0.1	9.1	398	0.1	0.7	0.2	72	1.02	0.041
1041343	7.5	224	2.48	7	1.7	<0.1	8.5	388	0.2	0.8	0.2	70	0.93	0.041
1041344	9.4	481	2.7	16	1.3	<0.1	2.1	551	0.2	1.4	<0.1	70	0.42	0.059
1041345	6.2	208	1.87	6	1.8	<0.1	8.4	325	<0.1	0.6	<0.1	54	0.62	0.033

Taseko Property Technical Report

GC-11-74	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb
	PPM	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM
	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1
Sample #														
1041301	7	29	1.14	482	0.325	7.59	3.436	1.35	1.6	19.8	15	3	5.8	3.2
1041302	6.4	27	1.14	457	0.305	8.33	3.594	1.43	0.9	22.3	13	2.2	6.4	2.9
1041303	6.8	29	1.11	434	0.319	8.39	3.528	1.31	0.8	20.4	14	2.1	5.9	3.4
1041304	7.9	29	1.1	416	0.325	8.29	3.403	1.3	2.1	19.3	15	2.5	5.6	3.1
1041305	8.1	29	1.1	399	0.333	8.38	3.349	1.4	2.4	19	17	2.3	5.7	3.2
1041306	10.8	25	1.21	192	0.283	7.96	3.389	1.33	2.5	12.9	20	2	7.9	2.6
1041307	18.7	30	1.12	391	0.324	8.54	3.451	1.44	2	20.3	40	2.1	7	3.4
1041308	6.6	28	1.13	349	0.319	8.16	3.639	1.35	2.6	18.3	14	1.7	6.3	3
1041309	6.4	28	1.1	424	0.298	7.57	3.479	1.19	1.7	15.8	13	2.1	5.2	3
1041310	6.7	30	1.13	434	0.318	8.25	3.495	1.25	2.1	14.6	13	1.9	5.5	3.1
1041311	9.5	26	1.06	415	0.293	8.02	3.483	1.25	1.5	13.5	21	1.9	5.4	2.9
1041312	7.8	29	1.07	413	0.306	8.13	3.348	1.26	1.6	12.5	17	1.9	5.4	2.8
1041313	8.9	29	1.17	365	0.302	6.94	3.368	1.26	3.3	11.7	18	2.2	5.2	2.9
1041314	6	31	0.96	397	0.286	7.07	3.402	1.25	2	11.1	12	1.7	4.9	2.9
1041315	7	28	1	365	0.289	8	3.749	1.31	11.2	13.8	13	2.4	5.9	3
1041316	6.3	30	1.01	383	0.296	8.02	3.421	1.33	2.1	12.8	13	2	6.6	3.3
1041317	6.7	31	0.95	355	0.303	7.47	3.443	1.15	0.6	11.8	13	2.2	8	3.1
1041318	12.7	31	2.41	562	1.153	8.52	2.553	0.71	0.3	154.4	30	1.7	26.8	7.6
1041319	7.4	30	0.98	398	0.315	8.26	3.43	1.23	0.6	13.2	17	2.5	11.9	3.7
1041320	29.1	105	0.95	95	0.214	6.85	0.793	3.38	18.6	26.1	54	4	11.6	3.1
1041321	12.1	30	0.96	422	0.309	8.05	3.422	1.22	0.8	11.9	28	2.2	10.5	3.3
1041322	6.6	32	0.96	388	0.287	7.85	3.445	1.35	0.9	17.2	13	2.2	8.9	3.2
1041323	7	27	0.99	387	0.299	8.35	3.629	1.36	0.8	15.2	16	2.2	9.5	3.3
1041324	13.8	33	2.27	175	1.275	8.27	2.014	0.37	0.4	177.2	35	1.8	32.2	8.5
1041325	5.7	28	0.91	330	0.289	7.8	3.561	1.12	2.3	10.9	12	2	9.5	2.9
1041326	22.1	27	1.02	365	0.286	7.67	3.48	1.29	1.3	13.1	63	3.9	26.4	4.5
1041327	13.1	31	2.34	199	1.226	8.5	2.283	0.41	0.5	164.9	32	1.4	29.8	8.2
1041328	5.3	29	1	374	0.287	7.47	3.685	1.46	2.4	14.7	12	2.1	8.1	3.1
1041329	9.4	29	0.95	719	0.291	7.79	3.163	2.14	1.5	16.6	22	1.7	10.9	3.5
1041330	5.6	28	0.96	362	0.284	7.88	3.778	1.55	3.6	12.8	11	2.2	10.4	3.3
1041331	7.8	31	1.02	418	0.307	7.84	3.508	1.35	0.6	10.8	18	2	7.7	3
1041332	8.2	28	0.95	394	0.294	6.99	3.459	1.27	0.9	9.9	18	2.2	8.9	3.1
1041333	11	43	2.05	271	1.473	8.44	3.302	0.63	3.2	75.9	29	1.8	22.4	9.1
1041334	9.4	24	0.97	319	0.256	6.78	3.617	1.12	0.5	11.5	10	1.7	4.4	2.2
1041335	7	25	0.85	529	0.25	7.3	2.763	1.93	3.9	14.5	14	1.7	11.6	2.7
1041336	8.6	25	0.95	563	0.248	7.18	3.474	1.74	1.7	12.5	20	1.8	9.7	3
1041337	11.2	21	0.82	393	0.243	7.09	3.347	1.29	1.4	12	32	3.1	18	3.4
1041338	9.9	22	0.84	385	0.243	7.14	3.544	1.34	0.8	12.6	28	2.9	15	3.6
1041339	11	23	0.82	276	0.254	7.27	3.721	0.98	0.8	11.6	32	3.6	20.7	3.8
1041340	1.3	<1	1.41	33	0.019	0.41	0.05	0.07	0.1	2.9	2	26.4	1.3	0.3
1041341	8.3	24	0.83	471	0.244	7.18	3.382	1.75	1.2	11.5	22	2.3	12.7	3.3
1041342	6.9	23	0.86	426	0.255	7.17	3.346	1.43	0.8	11.1	18	1.9	8.3	2.8
1041343	9.5	26	0.87	412	0.25	7.36	3.696	1.47	1	9.5	24	1.7	10.2	3
1041344	10.4	10	0.67	973	0.279	8.31	4.41	2.48	1.7	48.3	24	0.7	15	2.7
1041345	7.6	19	0.64	638	0.203	6.93	3.353	2.37	1.2	12.7	18	1.3	7.7	2.5

Taseko Property Technical Report

	Ta	Be	Sc	Li	S	Rb	Hf	
	PPM	PPM	PPM	PPM	%	PPM	PPM	
	0.1	1	1	0.1	0.1	0.1	0.1	
Sample #								
1041301	0.2	<1		8	24.2	0.3	71.2	0.8
1041302	0.2	<1		8	24.5	0.1	92.5	0.9
1041303	0.3	<1		8	25.8	0.3	80.7	0.7
1041304	0.3	<1		7	25	0.5	82.2	0.6
1041305	0.3	<1		7	25.7	0.5	87.8	0.7
1041306	0.2	<1		8	27	0.6	110.8	0.4
1041307	0.3	1		8	26	0.4	89.4	0.8
1041308	0.3	1		9	26.3	0.4	88.4	0.7
1041309	0.3	<1		7	24.7	0.2	65.9	0.6
1041310	0.3	1		8	26	0.4	79.4	0.6
1041311	0.2	1		8	24.2	0.2	82.5	0.5
1041312	0.3	<1		9	23.4	0.2	80	0.5
1041313	0.3	<1		9	23.1	0.3	80.8	0.5
1041314	0.3	<1		7	20.5	0.2	80.5	0.5
1041315	0.3	1		7	21	0.2	84.5	0.6
1041316	0.3	1		8	22.2	0.1	87.6	0.5
1041317	0.3	1		8	22.5	0.3	79.8	0.5
1041318	0.5	1	27	67.1	<0.1	46.6	3.6	
1041319	0.3	1	10	22.7	<0.1	71.8	0.5	
1041320	0.2	2	11	14.6	2.6	127.5	0.8	
1041321	0.3	<1	10	22.6	<0.1	72.8	0.4	
1041322	0.3	<1	8	20.4	0.2	88.9	0.7	
1041323	0.3	1	11	22.9	<0.1	80.4	0.6	
1041324	0.5	1	29	91.6	0.2	36.8	4.4	
1041325	0.3	1	7	21.6	0.2	71.8	0.4	
1041326	0.4	1	11	21.6	0.4	83.3	0.6	
1041327	0.5	2	29	83.3	0.2	31.8	3.5	
1041328	0.3	1	8	21.4	<0.1	96.3	0.6	
1041329	0.3	1	9	18.7	<0.1	93.7	0.6	
1041330	0.3	1	9	19.5	<0.1	98.3	0.5	
1041331	0.3	<1	9	20.4	<0.1	80.4	0.5	
1041332	0.3	1	7	19.6	0.1	72	0.4	
1041333	0.6	1	22	92.5	0.2	36.8	1.9	
1041334	0.2	1	5	18.7	0.2	74.7	0.5	
1041335	0.2	1	7	22.4	<0.1	124.9	0.6	
1041336	0.2	<1	7	15.6	<0.1	93.7	0.5	
1041337	0.3	1	8	15.3	<0.1	84	0.5	
1041338	0.3	<1	7	16	<0.1	88.5	0.6	
1041339	0.3	<1	8	16.6	<0.1	77.4	0.7	
1041340	<0.1	<1	<1	1.1	0.1	4.4	0.2	
1041341	0.3	<1	7	17.8	<0.1	101.5	0.6	
1041342	0.3	1	7	17.4	<0.1	90.1	0.5	
1041343	0.3	<1	7	19.7	<0.1	91.9	0.4	
1041344	0.2	1	8	35.4	<0.1	127.8	1.5	
1041345	0.2	<1	5	17.6	<0.1	89.9	0.6	

GC-11-74				Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni
Sample #	From	To	Standards	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM
			section	MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1
1041346	109	111		2	5.53	<0.005	9.1	66	10.2	45	<0.1	13.6
1041347	111	114		3	8.12	0.044	12.7	252.8	8.2	37	0.1	15.7
1041348	114	116.35		2.35	5.85	0.043	9.5	531.4	6	43	0.1	20.9
1041349	116.35	117		0.65	1.99	<0.005	1.4	49.3	3	73	0.1	29.9
1041350	117	119.4		2.4	7.4	<0.005	1.8	123.1	5.5	80	0.1	30.7
1041351	119.4	122.2		2.8	7.64	<0.005	1.6	38.6	9.1	46	<0.1	17.9
1041352	122.2	123.6		1.4	3.04	0.014	23.7	324.6	6.4	33	<0.1	19.5
1041353	123.6	126		2.4	5.97	<0.005	2	76.5	9.6	43	<0.1	16.1
1041354	126	129		3	8.02	<0.005	0.3	50.8	8	49	0.1	18.4
1041355	129	131.12		2.12	5.45	<0.005	0.5	39.4	11.6	45	<0.1	18.9
1041356	131.12	133		1.88	4.94	0.014	7.1	135.2	6.4	27	<0.1	23.2
1041357	133	135		2	5.69	0.009	4.8	104.3	5.7	30	<0.1	22.7
1041358	135	138		3	8.92	<0.005	6	58.9	7.2	32	<0.1	20
1041359	138	139		1	2.77	0.008	5.7	40.6	7.9	29	<0.1	15.9
1041360	138	139	Duplicate	1	2.99	0.006	4.8	45.2	8	26	<0.1	16.8
1041361	139	141		2	5.14	<0.005	10.2	21.8	8.1	29	<0.1	17.2
1041362	141	144		3	7.19	0.013	17.6	465.9	8.1	30	<0.1	17.1
1041363	144	147		3	7.65	0.057	7.7	70.9	9.2	32	<0.1	14.8
1041364	147	150		3	6.91	<0.005	8	183	9.5	33	0.1	15.5
1041365	150	153		3	7.86	<0.005	5.9	90.7	7.6	31	<0.1	15.9
1041366	153	156		3	8.31	<0.005	5.1	32.6	6.7	30	<0.1	14.8
1041367	156	159		3	7.23	0.01	18.7	159.6	9	31	<0.1	18.8
1041368	159	162		3	7.6	0.018	19.8	420.1	9.8	29	0.2	19.3
1041369	162	165		3	7.08	0.031	10.8	64	8.9	30	<0.1	17
1041370	165	168		3	7.84	0.013	4.7	34.8	8	28	<0.1	17.1
1041371	168	171		3	8.05	<0.005	4	132.6	9.5	34	<0.1	18.1
1041372	171	174		3	7.95	<0.005	1.5	96	7.6	36	<0.1	19.7
1041373	174	177		3	7.41	0.009	3.1	33.3	9.7	37	<0.1	18.7
1041374	177	180		3	8.33	<0.005	3.4	37	10.4	35	<0.1	19.7
1041375	180	183		3	8.46	<0.005	3.3	14.1	9.5	45	<0.1	17.3
1041376	183	186		3	7.09	<0.005	2.8	13.1	9.5	32	<0.1	18.3
1041377	186	189		3	8.12	<0.005	4.3	41.6	9.4	31	<0.1	16.3
1041378	189	192		3	7.73	<0.005	5.1	53.7	8	32	<0.1	16.3
1041379	192	195		3	7.76	0.008	3.9	41	9.2	30	<0.1	15.1
1041380	195	195	Cm-2	0	0.08	1.351	268.6	9537.3	78.7	127	4.8	32.2
1041381	195	198		3	7.37	0.008	4.5	182	8.4	35	<0.1	16.4
1041382	198	201		3	7.35	0.008	4.2	251.6	8.9	40	0.1	18.3
1041383	201	204		3	7.66	0.011	4	196	8.3	34	0.3	16.4

EOH

Taseko Property Technical Report

GC-11-74	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001
1041346	7.2	230	2.29	7	2	<0.1	9.3	414	0.2	0.7	<0.1	61	0.88	0.041
1041347	8.1	257	2.37	11	1.6	<0.1	8.3	365	<0.1	0.8	0.2	61	1.27	0.038
1041348	13.5	449	3.63	29	1.6	<0.1	6.9	446	0.1	1.2	0.2	94	2.04	0.057
1041349	39	1260	6.72	79	0.5	<0.1	2	496	0.2	3.5	<0.1	188	5.65	0.115
1041350	36	986	6.82	138	4.9	<0.1	2	438	0.1	3.1	<0.1	190	4.53	0.126
1041351	8.4	360	2.4	26	1.3	<0.1	1.5	609	0.1	0.8	<0.1	69	0.58	0.057
1041352	7.7	251	2.39	9	1.7	<0.1	9.4	367	<0.1	0.6	<0.1	68	0.69	0.043
1041353	8	365	2.45	26	1.4	<0.1	2.4	659	<0.1	0.9	<0.1	69	0.49	0.062
1041354	8.8	407	2.65	22	1.3	<0.1	2.3	693	<0.1	0.8	<0.1	71	0.46	0.061
1041355	8.6	372	2.29	23	1.2	<0.1	2.2	685	0.2	0.8	<0.1	68	0.81	0.057
1041356	10.1	302	2.55	11	2	<0.1	9.1	396	<0.1	0.8	<0.1	72	2.48	0.049
1041357	9.2	279	2.58	7	1.8	<0.1	9.2	394	<0.1	0.6	<0.1	76	2.06	0.051
1041358	8.5	283	2.49	8	2	<0.1	9.1	421	<0.1	0.4	<0.1	68	1.98	0.043
1041359	7.6	214	2.07	9	1.7	<0.1	8.7	412	<0.1	0.5	<0.1	60	1.88	0.04
1041360	7.2	204	2.05	8	1.6	<0.1	7.9	408	0.1	0.5	<0.1	59	1.76	0.038
1041361	7.7	220	2.19	7	1.5	<0.1	8.5	368	<0.1	0.6	<0.1	63	1.67	0.04
1041362	7.1	205	2.03	8	1.5	<0.1	8.7	315	<0.1	0.5	<0.1	59	0.87	0.038
1041363	7.9	224	2.13	8	1.7	<0.1	8.6	395	<0.1	0.6	0.1	57	1.4	0.038
1041364	7.7	225	2.46	10	1.7	<0.1	9.2	417	0.1	0.6	<0.1	65	1.49	0.039
1041365	8.2	225	2.52	8	1.4	<0.1	8.7	311	0.1	0.6	<0.1	62	1.62	0.04
1041366	7.2	247	2.08	7	1.9	<0.1	9.1	350	<0.1	0.7	<0.1	57	1.91	0.036
1041367	7.8	236	2.14	8	2.3	<0.1	7.3	345	0.2	0.8	0.4	61	2.08	0.042
1041368	8	224	2.14	12	1.3	<0.1	6.7	268	<0.1	0.9	0.3	65	2.27	0.042
1041369	8	242	2.48	8	2.2	<0.1	7.8	447	0.2	0.7	0.3	66	2.38	0.039
1041370	7.6	199	2.23	8	1.9	<0.1	7.3	446	0.1	0.5	0.2	61	2.16	0.04
1041371	9.1	237	2.62	8	1.5	<0.1	7.3	384	0.1	0.6	0.1	76	2.01	0.043
1041372	10.2	255	2.55	9	1.8	<0.1	7.4	493	<0.1	0.7	0.1	92	2.3	0.05
1041373	9.6	308	2.52	6	2	<0.1	7.5	417	0.1	0.6	0.1	79	2.61	0.047
1041374	9.2	295	2.51	7	2.2	<0.1	6.7	462	<0.1	0.6	<0.1	79	2.45	0.046
1041375	8.7	316	2.17	10	1.6	<0.1	9	472	<0.1	0.9	<0.1	72	1.61	0.039
1041376	8.2	265	2.42	12	1.7	<0.1	9.2	500	0.1	0.5	<0.1	73	1.76	0.046
1041377	8.2	291	2.36	5	2.3	<0.1	6.9	439	<0.1	0.5	0.1	68	2.07	0.042
1041378	7.4	262	2.2	7	3.5	<0.1	7.9	397	0.1	0.6	0.1	62	1.94	0.038
1041379	7.4	259	2.16	7	2.8	<0.1	8.8	446	<0.1	0.6	<0.1	61	1.84	0.037
1041380	20.1	366	4.79	34	5	2	10.7	192	2.4	19.9	3.3	95	1.49	0.075
1041381	7.9	265	2.14	7	2	<0.1	8.2	366	<0.1	1	<0.1	61	1.96	0.04
1041382	8.6	282	2.45	8	1.9	<0.1	8.3	419	<0.1	0.9	<0.1	71	1.85	0.045
1041383	8.7	257	2.12	8	2.4	<0.1	9.3	354	<0.1	1	<0.1	60	1.95	0.037

Taseko Property Technical Report

GC-11-74	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb
	PPM	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM
	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1
1041346	8.7	22	0.7	735	0.242	7.45	3.327	2.71	2.3	12.7	20	1.7	8.8	3
1041347	7.8	22	0.85	682	0.239	7.28	3.381	2.57	1.9	10.6	18	1.9	8.6	2.9
1041348	9.3	27	1.41	731	0.405	7.59	3.019	1.83	1.4	24.1	23	1.8	11.5	3.6
1041349	12.3	32	3.37	207	0.997	8.26	2.46	0.34	0.4	151.9	31	1.6	22.8	7
1041350	13.7	29	3.38	369	1.044	8.42	2.659	0.64	2	149.6	33	1.2	24.1	7.6
1041351	8.7	8	0.75	1007	0.262	7.77	4.665	1.82	1.6	51.5	20	0.5	6.6	2.5
1041352	7.8	23	1.02	279	0.25	7.39	4.313	1.05	1.6	11.1	16	1.6	6	2.7
1041353	9	10	0.63	1088	0.265	8.24	4.604	2.28	1.5	65.1	21	0.6	8.6	2.7
1041354	12.3	9	0.73	1201	0.279	8.5	4.875	2.41	1.6	76.2	27	0.6	9.7	2.6
1041355	11.6	8	0.76	1056	0.26	8.24	4.933	1.89	0.7	73.3	26	0.7	7.2	2.5
1041356	8.6	28	1.03	368	0.284	7.7	3.451	1.57	1.7	11.8	20	2.1	8.9	2.9
1041357	7.4	27	0.98	358	0.284	7.87	3.65	1.13	1.4	12	20	2.7	10.1	3
1041358	7.5	23	1.04	466	0.25	7.61	3.699	1.41	0.9	11.9	19	2	9.9	3
1041359	6.5	22	0.84	638	0.22	7.46	3.347	1.9	0.8	12.4	15	1.3	6.6	2.8
1041360	6.1	20	0.84	569	0.22	7.21	3.315	1.78	0.9	12.7	14	1.1	5.9	2.6
1041361	6.2	20	0.89	636	0.225	7.23	3.21	1.99	0.9	12.2	14	1.5	6.6	2.9
1041362	6.6	19	0.82	500	0.225	7.12	3.52	1.64	1.8	12	14	1.2	5.1	2.7
1041363	7.4	20	0.84	665	0.212	7.35	3.118	2.31	1.3	11.2	16	1.4	7	2.9
1041364	9.5	22	0.84	541	0.231	7.34	3.601	1.54	1	13.7	21	1.6	8.6	3
1041365	7.8	22	0.96	367	0.223	7.51	3.679	1.26	1.4	10.7	18	1.6	8.7	3.2
1041366	8.5	19	0.81	612	0.214	7.26	3.229	2.37	2	11.8	20	1.1	8.6	3
1041367	7.4	22	0.78	822	0.241	7.75	2.947	2.24	2.6	10.7	13	1.4	6.3	2.9
1041368	5.3	18	0.84	672	0.251	7.73	3.138	1.94	2.1	7.1	13	1.6	6.5	2.9
1041369	7.8	20	0.83	894	0.233	6.94	2.919	2.3	0.9	10.4	14	1.5	7.9	2.7
1041370	5.9	20	0.82	831	0.224	6.89	3.044	2.3	0.5	10.9	13	1.5	7.1	2.7
1041371	7.1	23	0.99	479	0.252	6.99	3.29	1.61	0.7	10.1	19	2.4	11.6	2.9
1041372	10	29	1.29	303	0.31	7.23	3.465	1.1	0.5	10.1	35	4	24.2	3.4
1041373	7.6	26	1.1	623	0.278	6.86	2.932	1.73	0.7	9.3	19	1.6	10.6	2.8
1041374	6.9	28	1.05	767	0.294	6.98	3.024	1.7	0.7	9.9	18	1.8	10.6	2.8
1041375	11.3	23	1	572	0.279	7.06	3.382	1.57	1	10.7	26	2.5	12.7	3
1041376	8.1	25	0.96	572	0.291	7.94	3.46	1.61	0.7	11.8	21	2.5	11.8	3
1041377	7.5	22	1	838	0.249	6.78	2.946	2.41	0.7	11.7	17	1.1	8.7	2.8
1041378	6	21	0.89	789	0.23	6.87	3.163	2.14	1	12.6	15	1.5	8.5	2.6
1041379	7.6	18	0.85	842	0.239	6.57	2.982	2.62	1.1	13.9	20	1.7	9.1	3.1
1041380	28.8	96	0.94	84	0.207	6.65	0.742	3.13	18.8	24.8	53	3.7	11	2.9
1041381	6	22	0.79	786	0.246	6.51	2.916	2.42	1.7	11.5	15	1.5	8.2	2.8
1041382	7.2	20	0.95	682	0.254	6.7	3.24	2.13	1.2	10.4	18	1.6	9.7	3
1041383	7.9	21	0.82	722	0.239	6.71	2.858	2.52	5.7	10.8	20	1.4	9.5	3.2

GC-11-74	Ta	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	PPM	%	PPM	PPM
	0.1	1	1	0.1	0.1	0.1	0.1
1041346	0.3	<1	6	19.3	<0.1	106.1	0.5
1041347	0.2	<1	6	34	<0.1	103.2	0.5
1041348	0.3	<1	11	55.4	0.1	75.7	0.9
1041349	0.5	1	25	67.4	0.1	22.2	3.6
1041350	0.5	<1	26	108.7	0.3	35	3.7
1041351	0.2	2	6	39.3	<0.1	73.5	1.4
1041352	0.3	<1	7	26.2	<0.1	76.9	0.5
1041353	0.2	1	6	28.2	<0.1	93.4	1.8
1041354	0.2	1	7	29.9	<0.1	90.1	2.1
1041355	0.2	1	6	30	<0.1	81.2	1.9
1041356	0.2	1	9	25.7	<0.1	109.3	0.6
1041357	0.3	<1	8	23.3	<0.1	103.1	0.6
1041358	0.3	<1	8	22.8	<0.1	85.9	0.6
1041359	0.2	<1	6	18.4	<0.1	84.1	0.6
1041360	0.2	<1	6	19.1	<0.1	83.3	0.4
1041361	0.3	<1	6	19.5	<0.1	93.2	0.5
1041362	0.2	<1	6	18.2	<0.1	96.1	0.4
1041363	0.2	<1	6	21	<0.1	97.2	0.5
1041364	0.3	<1	6	22	<0.1	96.1	0.6
1041365	0.3	1	6	21.3	<0.1	89.2	0.6
1041366	0.3	<1	6	19.4	<0.1	103	0.5
1041367	0.3	1	7	21.3	<0.1	82.6	0.6
1041368	0.3	<1	7	22.9	<0.1	95.8	0.4
1041369	0.3	<1	6	27.9	<0.1	80.1	0.5
1041370	0.3	<1	6	27.3	<0.1	73.8	0.6
1041371	0.2	<1	7	27.8	<0.1	68.9	0.5
1041372	0.3	<1	9	30	<0.1	59.8	0.5
1041373	0.2	<1	8	31.9	<0.1	53.8	0.4
1041374	0.2	<1	8	24.8	<0.1	54.6	0.5
1041375	0.3	1	7	23	<0.1	70.1	0.5
1041376	0.2	<1	7	25.9	<0.1	69.4	0.5
1041377	0.2	1	7	21.8	<0.1	67.5	0.6
1041378	0.2	1	6	26.1	<0.1	67	0.6
1041379	0.3	1	6	22.8	<0.1	78.2	0.6
1041380	0.2	2	10	13.3	2.5	108.1	0.8
1041381	0.3	1	6	20.1	<0.1	81.8	0.6
1041382	0.3	1	6	21.7	<0.1	74.9	0.5
1041383	0.3	1	6	23.5	<0.1	82.6	0.5

Taseko Property Technical Report

GC 11-75			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
			Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	
			MDL	0.01	0.005	0.1		0.1	0.1	1	0.1	
Sample #	From	To	Standards	section								
1041384	8	10		2	4.35	0.007	5	86.6	7.8	40	0.2	20.5
1041385	10	12		2	4.49	0.009	1.6	92.1	7.2	35	0.1	21.3
1041386	12	14.1		2.1	4.77	<0.005	26.5	189.6	7.3	37	0.7	22.3
1041387	14.1	16		1.9	4.33	0.169	89.7	1327.1	7	36	0.8	24
1041388	16	18		2	3.53	0.303	29.8	1413.6	5.6	32	2	25.5
1041389	18	21		3	6.14	0.093	87.7	1680.9	6.2	26	1.1	26.2
1041390	21	24		3	6.71	0.125	60.8	2481.6	6.2	23	2	25.5
1041391	24	27		3	7.74	0.117	61	1782	7.9	24	1.3	25.1
1041392	27	30		3	6.52	0.078	38	668.5	7	29	1.5	24.2
1041393	30	33		3	7.31	0.039	183.6	812.1	4.8	31	0.3	24.6
1041394	33	36		3	6.39	0.089	105	658.4	9.9	31	0.6	24.6
1041395	36	39		3	5.56	0.066	89.9	1666.2	6.2	36	0.7	26.9
1041396	39	42		3	7.72	0.111	170.9	2472.6	10.9	29	1.1	26.6
1041397	42	45		3	6.79	0.043	272.3	1200.9	4.6	27	0.7	27.1
1041398	45	48		3	7.53	0.053	124.1	1186.3	5.4	31	0.7	27.8
1041399	48	51		3	6.74	0.021	74.5	1199.4	6.3	26	0.7	25
1041400	51	51	Blank	0	1.09	<0.005	0.5	9.3	<0.1	<1	<0.1	0.2
1041401	51	53		2	5.26	0.223	303.1	976.1	19	23	0.5	24.6
1041402	53	55		2	4.03	0.025	596.2	81.2	6.5	25	<0.1	21.2
1041403	55	57		2	5.26	0.057	31.7	628.9	10.4	31	0.1	25.9
1041404	57	60		3	7.49	0.06	156.3	103.9	8.2	37	<0.1	24.9
1041405	60	63		3	7.83	0.045	5.9	868.5	12	35	0.4	24.9
1041406	63	66		3	7.34	0.52	24	397.8	8.9	39	0.4	27.3
1041407	66	68		2	4.53	0.061	2.3	156.7	9	37	0.1	26.8
1041408	68	70		2	4.61	0.101	2.9	367.7	8.9	36	0.3	25.4
1041409	70	72		2	5.07	0.039	3.9	921.2	8.8	37	0.4	25.2
1041410	72	75		3	8.02	0.071	3.4	1828.1	9	40	0.9	32.2
1041411	75	78		3	8.76	0.156	3.6	1453.1	9.1	40	0.8	28.7
1041412	78	81		3	7.85	0.115	2.2	1866.6	9.2	36	1	29
1041413	81	84		3	8.58	0.168	2.6	2848	8.8	35	1.3	29.2
1041414	84	87		3	7.48	0.069	236.4	1369.5	7.5	33	0.5	30.4
1041415	87	90		3	8.01	0.037	11.1	481.1	8.7	34	0.3	30.1
1041416	90	93		3	6.97	0.039	3.7	405.7	7.3	28	0.2	24.8
1041417	93	96		3	7.43	0.105	51.4	894.9	7.6	28	0.5	25
1041418	96	99		3	7.69	0.024	151.3	767.8	7.3	26	0.3	20.3
1041419	99	100		1	2.8	0.011	256.4	396.5	7.8	30	0.2	19.5
1041420	99	100	Duplicate	1	2.71	0.039	226.2	455.6	7.7	27	0.2	22.6
1041421	100	101		1	2.16	0.026	317	274	7.1	25	0.2	14.5
1041422	101	103		2	4.35	0.019	200.6	515.4	7.4	28	0.1	17.9
1041423	103	105		2	5.16	0.009	410.5	619.5	8.1	30	0.2	19.3
1041424	105	108		3	6.54	0.025	84.5	908.3	7.5	26	0.3	17.7
1041425	108	111		3	7.59	0.008	123.3	394.7	7.8	32	0.2	20
1041426	111	113		2	4.31	0.006	3.2	269.1	8.4	32	0.1	23.6
1041427	113	115		2	5.15	<0.005	3.5	249.6	8.3	33	<0.1	20.4
1041428	115	117		2	5.57	0.01	11.1	23.7	10.6	39	<0.1	24.4

Taseko Property Technical Report

GC11-75	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #															
1041384	11.4	358	2.61	7	2.6	<0.1	6.6	395	0.1	0.4	0.2	94	2.4	0.048	9
1041385	11.9	329	2.69	7	2.9	<0.1	7.5	402	<0.1	0.4	<0.1	95	2.33	0.051	9.6
1041386	11.9	327	2.72	9	3.4	<0.1	7.7	428	<0.1	0.4	0.1	103	2.36	0.051	10.5
1041387	9.4	219	1.8	8	3.2	<0.1	8.4	470	<0.1	0.7	0.4	85	1.54	0.049	6.9
1041388	12	228	1.86	9	2.5	<0.1	8.6	425	<0.1	0.6	0.3	89	1.48	0.05	6.5
1041389	9	162	1.58	6	4.5	<0.1	8.3	431	<0.1	0.4	0.2	74	1.24	0.05	5.9
1041390	8.4	144	1.59	7	3.3	<0.1	8	453	0.1	0.4	0.4	69	1.69	0.049	5.5
1041391	8.9	143	1.5	10	2.9	0.1	8	449	<0.1	0.5	0.4	66	1.58	0.061	5.4
1041392	9	167	1.54	10	6.2	2.4	8.6	451	<0.1	0.5	0.2	71	1.41	0.052	5.6
1041393	7.9	168	1.52	8	4.6	<0.1	8.9	443	<0.1	0.6	0.2	69	1.47	0.053	6
1041394	9.4	170	1.5	7	8.9	<0.1	8.9	343	0.1	0.9	0.6	68	0.84	0.043	10.3
1041395	8.9	179	1.66	6	2.8	<0.1	8.6	358	<0.1	0.6	0.4	68	1.13	0.052	6.3
1041396	9.5	181	1.7	7	3.1	<0.1	6.8	305	0.2	0.6	0.3	68	2.2	0.047	21.9
1041397	8.5	156	1.63	5	2.5	<0.1	7.8	398	<0.1	0.3	0.2	65	1.29	0.05	8.2
1041398	7.7	165	1.62	5	1.7	<0.1	8.9	419	<0.1	0.4	0.2	71	1.71	0.041	9.1
1041399	8.7	159	1.66	8	2.8	<0.1	8.2	412	<0.1	0.4	0.2	75	1.56	0.05	6.6
1041400	0.2	23	0.11	<1	1.7	<0.1	<0.1	4361	<0.1	<0.1	<0.1	2	39.38	0.005	0.9
1041401	8.3	160	1.61	6	2	<0.1	7.1	371	<0.1	0.4	0.2	65	1.9	0.052	5.2
1041402	7.7	151	1.44	7	2.3	<0.1	8.5	419	0.2	0.3	<0.1	64	1.75	0.033	5.7
1041403	9.2	210	1.71	7	2.3	<0.1	8.6	428	0.1	0.5	0.2	81	1.9	0.049	7.6
1041404	8.3	193	1.6	7	5.2	<0.1	8.8	378	<0.1	0.3	<0.1	68	2.07	0.023	9.1
1041405	8.1	196	1.67	11	24.9	<0.1	11.3	440	0.2	0.4	0.4	72	2.3	0.028	80.5
1041406	9	207	1.86	9	8.2	<0.1	11	423	0.2	0.3	0.2	79	1.73	0.056	12.1
1041407	8.9	212	1.69	9	5.2	<0.1	12.3	441	0.2	0.3	<0.1	72	2.11	0.054	10
1041408	9.2	220	1.76	16	2.7	<0.1	11.5	418	0.1	0.4	0.1	71	2.27	0.046	6.4
1041409	9.4	230	1.98	12	3.1	<0.1	11.8	436	<0.1	0.4	<0.1	84	2.13	0.047	8.2
1041410	10.8	237	2.44	8	1.3	<0.1	12.8	439	<0.1	0.2	0.2	113	2.53	0.051	44.3
1041411	9.7	238	2.92	8	2	<0.1	11.8	418	<0.1	0.4	0.1	139	2.28	0.048	6.9
1041412	10.4	232	2.41	9	4.4	0.3	11	407	<0.1	0.4	0.2	118	2.22	0.053	7.1
1041413	10.1	211	2.29	11	2.7	0.1	11.2	393	<0.1	0.4	0.2	114	2.64	0.059	6.7
1041414	10.2	217	2.84	9	1.9	<0.1	10.9	405	<0.1	0.3	<0.1	198	2.38	0.05	15.5
1041415	9.7	215	2.7	8	1.5	<0.1	10.6	442	<0.1	0.3	<0.1	203	2.62	0.053	9.1
1041416	9.6	217	1.87	9	1.7	<0.1	11	433	<0.1	0.3	<0.1	84	2.53	0.054	12.6
1041417	8.9	203	1.68	10	1.9	<0.1	10.8	427	<0.1	0.3	0.2	72	2.68	0.054	11.1
1041418	7.2	242	1.49	10	2	<0.1	10.2	427	<0.1	0.3	0.1	66	2.98	0.058	12
1041419	7.3	241	1.39	14	2	<0.1	10.1	411	<0.1	0.3	<0.1	63	2.9	0.056	9.5
1041420	7.3	257	1.44	15	2	<0.1	10.5	404	<0.1	0.3	<0.1	66	2.92	0.055	10.1
1041421	6	232	1.24	5	2	<0.1	9.9	407	0.2	0.3	<0.1	54	3.04	0.038	12.4
1041422	7.2	246	1.54	8	2.2	0.1	11.4	416	<0.1	0.3	<0.1	67	2.92	0.055	16.3
1041423	7.7	252	1.61	7	1.8	<0.1	10.1	415	0.2	0.3	<0.1	64	3.04	0.062	12.8
1041424	6.9	248	1.55	4	2	<0.1	9.3	409	<0.1	0.2	<0.1	64	3.19	0.065	13.6
1041425	8.8	201	1.74	5	1.5	<0.1	9.7	407	<0.1	0.3	<0.1	84	2.56	0.051	9.9
1041426	10.1	203	1.97	5	1.6	<0.1	11.3	451	<0.1	0.3	<0.1	89	2.81	0.06	10.1
1041427	9.7	202	1.95	6	1.8	<0.1	10.4	449	<0.1	0.3	<0.1	97	2.6	0.051	10.7
1041428	10.7	227	1.9	10	3.3	<0.1	10	425	<0.1	0.5	<0.1	97	2.6	0.059	13.4

Taseko Property Technical Report

GC11-75	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #														
1041384	27	1.25	593	0.35	7.02	2.783	2.2	0.9	11.3	22	1.3	11.8	3.4	0.3
1041385	30	1.24	622	0.359	7.01	2.857	1.89	1	11.7	22	1.5	12.7	3.7	0.3
1041386	29	1.32	605	0.379	7.34	2.917	2.07	2.2	13.9	23	1.6	12.3	3.7	0.3
1041387	28	1.1	432	0.312	8.19	3.583	1.41	0.9	22.9	14	1.9	6.5	3.2	0.3
1041388	26	1.12	456	0.315	8.11	3.499	1.38	1.4	22.3	13	2.1	6	3.2	0.3
1041389	24	1.12	422	0.299	6.89	3.393	1.28	0.9	18.4	12	1.7	5.8	3.1	0.3
1041390	23	1.1	387	0.294	6.62	3.431	1.13	0.6	15.1	11	1.4	4.8	2.9	0.3
1041391	23	1.1	403	0.278	7.05	3.408	1.19	0.7	15.3	11	1.2	4.4	2.7	0.2
1041392	23	1.16	425	0.304	7.42	3.475	1.19	0.7	15.5	11	1.5	4.3	2.8	0.3
1041393	25	1.12	409	0.301	8.07	3.567	1.21	1	14.3	11	1.4	4.5	2.7	0.2
1041394	25	1.06	326	0.296	8.04	3.633	1.35	3.8	16.5	17	1.8	7.2	2.9	0.3
1041395	27	1.06	369	0.319	8.42	3.348	1.37	5.3	16.3	12	1.5	5	3	0.3
1041396	23	0.89	453	0.298	6.85	3.05	1.27	4.3	11.7	44	1.4	6.3	2.9	0.2
1041397	26	1.12	351	0.29	6.67	3.442	1.11	1.1	13.5	17	1.3	4.2	2.5	0.2
1041398	24	1.08	394	0.28	6.86	3.415	1.09	0.7	12.9	19	1.5	3.9	2.7	0.2
1041399	25	1.12	371	0.281	6.84	3.441	1.13	1.4	11.8	13	1.5	4.2	2.4	0.2
1041400	<1	1.67	8	0.009	0.15	0.016	0.02	<0.1	1.2	<1	<0.1	0.4	0.2	<0.1
1041401	26	1.15	372	0.294	6.71	3.388	1.11	0.3	9.3	11	1.5	3.7	2.6	0.3
1041402	22	1.1	342	0.28	6.53	3.405	1.09	0.4	10.6	11	1.4	3.7	2.8	0.3
1041403	25	1.11	426	0.303	8.08	3.463	1.32	1.7	11.7	15	1.6	5.8	2.9	0.2
1041404	25	1.05	369	0.316	9.89	3.535	1.3	9.8	14.3	14	1.9	7.9	3.4	0.3
1041405	26	1.02	432	0.326	9.54	3.626	1.26	6.6	14	127	2.7	25.5	4.6	0.5
1041406	28	1.24	458	0.316	9.6	3.907	1.36	2.3	13	19	2.3	12.2	3.1	0.3
1041407	27	1.15	416	0.307	9.66	3.653	1.22	2.1	14.1	18	2.4	15.6	3.6	0.3
1041408	26	1.11	437	0.295	9.58	3.783	1.21	1.4	16.9	11	1.9	7.9	3.2	0.3
1041409	25	1.07	536	0.319	9.97	3.888	1.37	1.5	21.6	14	1.9	6.8	3.3	0.3
1041410	28	1.13	480	0.333	10.76	3.467	1.28	2.5	18.7	88	2.5	9.7	3.1	0.3
1041411	29	1.04	461	0.323	9.82	3.511	1.38	7.7	17	14	2.5	9.7	3.2	0.3
1041412	29	1.13	475	0.322	9.65	3.568	1.58	3.2	14.9	14	2.1	9.2	3.1	0.3
1041413	28	1.2	403	0.31	10.66	3.422	1.42	4	14.4	14	2.2	8.7	3.3	0.3
1041414	29	1.19	387	0.331	9.66	3.405	1.24	1.4	13.6	35	2.8	14.8	3.3	0.3
1041415	28	1.17	424	0.328	10.17	3.578	1.28	0.6	14.9	22	3.2	15.9	3.1	0.3
1041416	24	1.24	342	0.303	7.65	3.481	1.01	0.7	13.9	35	4.2	24.1	3.7	0.3
1041417	24	1.3	325	0.297	8.03	3.507	0.91	0.5	15	32	4	29.1	3.8	0.3
1041418	23	1.28	279	0.3	7.23	3.82	0.68	0.5	13.1	38	5.3	36.9	4.2	0.3
1041419	23	1.31	253	0.28	7.1	3.787	0.7	0.5	14	31	5.5	35.1	4	0.3
1041420	24	1.35	256	0.298	7.49	3.788	0.71	0.5	13.9	32	5.8	37.4	4.1	0.3
1041421	20	1.14	261	0.271	6.7	3.642	0.48	0.4	14.1	39	4.9	39	4.5	0.3
1041422	21	1.22	271	0.341	7.03	3.722	0.63	0.5	14.8	53	6.2	49.8	6.4	0.5
1041423	25	1.33	290	0.308	7.07	3.553	0.7	0.9	12.9	40	5.8	40.1	4.7	0.3
1041424	24	1.25	271	0.304	7.1	3.536	0.58	1.1	13.4	40	6.8	38.3	4.6	0.3
1041425	27	1.22	341	0.303	7.98	3.538	1.13	1	11.3	27	4.5	27.2	3.9	0.3
1041426	30	1.26	413	0.348	10.81	3.457	1.32	0.9	13.2	26	3.8	22.9	3.8	0.4
1041427	27	1.24	421	0.32	9.32	3.396	1.32	0.6	12.1	26	3.5	21.2	3.4	0.3
1041428	31	1.4	380	0.34	10.24	3.54	1.48	2.2	10.9	29	2.8	14	3	0.2

Taseko Property Technical Report

GC11-75	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041384	<1	9	23.7	<0.1	67.6	0.5
1041385	1	9	24.3	<0.1	62.7	0.5
1041386	1	10	24.3	<0.1	68.1	0.6
1041387	<1	7	26.6	0.1	81	0.8
1041388	<1	8	26.7	0.2	75.4	0.8
1041389	1	6	23.9	0.2	77.3	0.6
1041390	1	6	23.9	0.3	66.3	0.6
1041391	1	7	28.1	0.2	71.8	0.6
1041392	1	7	26.2	<0.1	70.2	0.6
1041393	1	7	26.6	<0.1	74.5	0.6
1041394	1	7	23	<0.1	87.2	0.6
1041395	<1	6	25.5	0.2	89.6	0.7
1041396	1	7	25.5	0.3	86.2	0.5
1041397	1	7	24.8	0.1	61.9	0.4
1041398	<1	6	24.3	0.1	65	0.5
1041399	1	8	25.5	0.1	69.1	0.4
1041400	<1	<1	0.4	<0.1	1	<0.1
1041401	1	6	23	0.1	59.4	0.4
1041402	<1	5	24.1	<0.1	66.7	0.5
1041403	1	7	24.8	<0.1	78.1	0.5
1041404	1	8	31.6	<0.1	80.6	0.5
1041405	1	9	25.6	<0.1	72.3	0.6
1041406	<1	9	30	<0.1	93.4	0.6
1041407	1	10	28.9	<0.1	79.6	0.7
1041408	<1	10	29.1	<0.1	68.1	0.7
1041409	<1	8	26.5	<0.1	74.9	0.8
1041410	1	9	24.6	0.2	74.7	0.7
1041411	1	9	25.7	0.1	76.5	0.6
1041412	<1	9	30	0.2	102.4	0.5
1041413	<1	9	30.5	0.3	88.1	0.5
1041414	<1	9	30.3	0.1	77.6	0.6
1041415	1	9	27.7	<0.1	72.7	0.6
1041416	<1	9	21.6	<0.1	53.2	0.7
1041417	<1	9	21.1	<0.1	48.9	0.6
1041418	1	10	16.6	<0.1	29	0.7
1041419	1	10	18.1	<0.1	28.7	0.7
1041420	1	11	17	<0.1	28.8	0.6
1041421	1	9	11.9	<0.1	18	0.7
1041422	1	10	14.6	<0.1	24.8	0.8
1041423	1	10	16.9	<0.1	28.5	0.5
1041424	1	10	12	<0.1	21.5	0.6
1041425	1	9	21.9	<0.1	58.2	0.5
1041426	1	10	24.4	<0.1	74.4	0.6
1041427	<1	9	23.5	<0.1	72.7	0.6
1041428	2	11	31.6	<0.1	84.5	0.5

Taseko Property Technical Report

GC 11-75			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
Sample #	From	To	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	
			MDL	0.01	0.005	0.1		0.1	0.1	1	0.1	
			Standards	section								
1041429	117	120		3	7.76	0.02	18.2	27.3	11.7	43	<0.1	24.6
1041430	120	123		3	8.68	<0.005	9.7	23.7	10.6	39	<0.1	22
1041431	123	126		3	7.94	<0.005	4.9	9.4	12.5	36	<0.1	18.4
1041432	126	129		3	7.72	0.008	3.4	578.1	10.8	43	0.2	19.5
1041433	129	132		3	7.93	0.008	14	167.8	12.9	52	<0.1	22.7
1041434	132	135		3	7.66	<0.005	11.1	8.9	15.8	71	<0.1	17.3
1041435	135	138		3	8.01	<0.005	1.5	59.6	11	51	0.1	19.7
1041436	138	141		3	7.94	<0.005	2	185.3	10.4	34	<0.1	17.8
1041437	141	143		2	5.83	0.006	1.4	332.9	10.4	37	<0.1	18.5
1041438	143	144		1	2.71	0.015	1	467	10.4	41	0.2	16.9
1041439	144	145		1	3.09	<0.005	1.4	119.9	8.3	32	<0.1	13.7
1041440	145	145	C m2	0	0.13	1.493	290.6	>10000.0	76	129	2.4	32.3
1041441	145	146		1	2.61	0.008	2.6	201.8	7.6	34	<0.1	16.3
1041442	146	148		2	5.59	<0.005	1	14	7.6	34	<0.1	16.6
1041443	148	150		2	5.78	<0.005	8	11.3	8.7	33	<0.1	16.5
1041444	150	152		2	5.43	0.007	1	136.8	7.1	29	<0.1	15.2
1041445	152	154		2	5.83	0.013	25	32.3	8.9	32	<0.1	15.3
1041446	154	156		2	4.97	0.006	2.2	72.7	7.9	31	<0.1	16.3
1041447	156	159		3	8.4	0.007	1	418.3	7.9	30	<0.1	17.8
1041448	159	162		3	8.63	0.007	0.8	116.9	9	26	<0.1	17.3
1041449	162	165		3	7.77	0.006	1.1	99	7	26	<0.1	19.6
1041450	165	168		3	7.93	<0.005	1	59.6	7.4	25	<0.1	18.8
1041451	168	171		3	8.78	0.016	1.6	38.1	8	27	<0.1	21.3
1041452	171	174		3	7.95	0.018	1.7	64.7	7.9	25	<0.1	19.8
1041453	174	177		3	7.17	0.043	0.9	348.3	8.2	31	<0.1	19.6

EOH

Taseko Property Technical Report

GC11-75	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #															
1041429	10.1	239	1.83	9	4.6	<0.1	11.4	431	0.1	0.4	<0.1	86	2.54	0.061	4.7
1041430	8.7	209	1.59	8	2.5	<0.1	11	415	<0.1	0.3	<0.1	77	2.28	0.059	7.7
1041431	8.9	203	1.72	5	3.2	<0.1	10.7	390	<0.1	0.3	<0.1	84	2.36	0.055	21.2
1041432	9.8	272	2.43	7	2.1	<0.1	11.3	429	<0.1	0.4	<0.1	94	2.67	0.052	24.5
1041433	10.6	279	1.92	8	2.4	<0.1	12.7	468	0.1	0.5	<0.1	89	2.65	0.058	17.8
1041434	8	351	1.56	8	5.3	<0.1	10.5	476	<0.1	1.2	<0.1	72	2.46	0.016	17.6
1041435	11.2	270	2.61	9	2.3	<0.1	11.1	442	<0.1	0.6	<0.1	94	2.54	0.055	13.3
1041436	9	232	2.59	7	2.1	<0.1	10.4	407	<0.1	0.4	<0.1	112	2.44	0.051	8.5
1041437	10	221	2.87	6	1.8	<0.1	11	419	<0.1	0.3	<0.1	138	2.52	0.051	9.4
1041438	9.8	234	2.55	7	2.5	<0.1	11.2	450	<0.1	0.3	<0.1	106	2.66	0.049	9.8
1041439	8.4	219	2.51	8	1.8	<0.1	9.8	423	0.1	0.4	0.4	95	2.09	0.043	11.1
1041440	19.4	366	4.81	29	5.3	2.5	9.9	180	2.1	20	3.7	104	1.51	0.072	25
1041441	9.2	228	2.33	10	2.1	<0.1	9.4	405	<0.1	0.5	<0.1	85	2	0.052	10.6
1041442	9.4	245	2.23	9	1.7	<0.1	8.6	427	<0.1	0.5	<0.1	91	2.05	0.046	9.9
1041443	8.9	284	2.22	11	3.4	<0.1	9.9	454	<0.1	0.7	<0.1	89	2.29	0.042	10.7
1041444	8.7	256	2.81	9	2.4	<0.1	8.1	455	<0.1	0.5	<0.1	93	2.61	0.044	7.1
1041445	7.5	266	2.07	8	4	<0.1	9	416	<0.1	0.8	<0.1	75	2.29	0.042	9.9
1041446	8.9	285	2.42	7	2.1	<0.1	9.3	440	0.1	0.5	<0.1	81	2.25	0.044	7.1
1041447	9.4	212	2.51	8	1.4	<0.1	8.3	446	<0.1	0.4	<0.1	93	2.15	0.045	14.4
1041448	9.3	206	2.16	8	1.8	<0.1	7.8	430	<0.1	0.4	<0.1	86	2.13	0.042	6.6
1041449	8.3	250	2.22	7	1.7	<0.1	6.2	472	<0.1	0.3	<0.1	99	2.77	0.052	6.7
1041450	8.9	263	2.6	8	1.5	<0.1	6.8	478	<0.1	0.5	<0.1	105	2.64	0.047	5.7
1041451	9.8	317	2.88	5	1.7	<0.1	7.6	485	<0.1	0.4	0.1	94	2.84	0.049	6.6
1041452	8.3	271	2.64	6	2	<0.1	8.9	473	<0.1	0.6	0.1	81	2.54	0.043	6.7
1041453	9	243	2.43	6	2.2	0.1	6.3	457	<0.1	0.6	<0.1	89	2.57	0.051	7.4

GC11-75	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #														
1041429	30	1.39	365	0.321	10.36	3.281	1.39	3.5	11.3	9	2.6	12.5	3.2	0.3
1041430	23	1.22	321	0.264	8.12	3.357	1.23	1.1	11.1	16	2.7	17.2	2.7	0.2
1041431	22	1.22	334	0.269	6.89	3.299	1.26	1.1	10.4	45	3.4	24.1	2.9	0.2
1041432	30	1.12	492	0.3	10.22	3.367	1.68	1.1	12.2	55	3.3	24.9	3.4	0.3
1041433	30	1.3	376	0.332	10.75	3.55	1.45	1.3	13.5	39	4.1	29.9	3.5	0.2
1041434	30	1.06	388	0.316	9.77	3.803	1.2	1.7	13.5	37	4.8	50.4	4.2	0.3
1041435	33	1.32	367	0.362	9.84	3.421	1.41	0.5	12.5	38	6.5	38.9	4.6	0.4
1041436	28	1.11	382	0.319	8.09	3.453	1.14	1.9	12.5	26	4.7	31.8	4.1	0.3
1041437	30	1.15	375	0.32	8.32	3.386	1.07	0.8	12.1	28	4.2	26.5	3.6	0.4
1041438	26	1.16	356	0.317	9.67	3.588	1.29	0.6	12.1	29	4.4	29.6	3.8	0.3
1041439	24	1.09	262	0.272	6.84	3.485	1.04	0.5	10.2	31	5.1	31.6	3.6	0.3
1041440	103	0.97	58	0.197	6.66	0.75	3.59	18.4	25.8	49	4	10.6	3.2	0.2
1041441	27	1.21	307	0.282	7.16	3.527	1.22	0.3	9.9	31	3.6	22.5	3.8	0.3
1041442	27	1.21	319	0.262	6.75	3.437	1.11	0.4	9.6	29	2.7	17.8	2.8	0.3
1041443	26	1.05	534	0.25	6.88	3.352	1.58	0.8	10.9	26	2.2	17.2	2.9	0.3
1041444	26	1.01	342	0.256	6.68	3.435	1.05	0.6	9.1	22	3.2	22.7	3.1	0.3
1041445	25	0.86	631	0.254	7.04	3.183	2.11	1.7	9.7	22	2.6	16.1	3	0.3
1041446	27	1.03	483	0.265	6.72	3.485	1.42	0.5	10.2	17	2	10.8	2.9	0.3
1041447	26	1.13	331	0.285	7.1	3.571	1.12	0.3	9.1	38	2.7	16.1	2.9	0.3
1041448	26	1.16	330	0.271	7.1	3.537	1.14	0.5	9	20	2.8	13.8	2.4	0.2
1041449	31	1.35	348	0.319	7.27	3.629	0.89	0.6	10	24	4.5	20	3.1	0.3
1041450	32	1.19	398	0.282	7.04	3.431	1.03	0.5	10.4	18	3.9	11.5	2.8	0.2
1041451	35	1.34	716	0.289	7.02	3.008	2.21	0.6	11.9	18	1.8	11.5	3.2	0.3
1041452	29	1.14	573	0.264	6.96	3.36	1.56	0.7	11.1	18	2.5	10.6	3	0.3
1041453	28	1.24	330	0.299	7.12	3.534	0.95	0.9	10.3	24	4	16.8	3.4	0.3

GC11-75	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041429	2	12	31.5	<0.1	79.1	0.5
1041430	<1	10	26.5	<0.1	70.2	0.5
1041431	1	9	23.1	0.2	69.3	0.5
1041432	2	10	22.3	<0.1	84.4	0.6
1041433	1	11	27.4	<0.1	78	0.6
1041434	2	10	21.8	<0.1	70.9	0.5
1041435	2	12	26.9	<0.1	79.6	0.6
1041436	1	9	24.1	<0.1	62.6	0.6
1041437	1	9	22.2	<0.1	58.1	0.5
1041438	2	10	24.6	<0.1	77.3	0.5
1041439	<1	8	20	<0.1	77.2	0.5
1041440	<1	10	13.7	2.4	160.1	0.8
1041441	<1	7	24.4	<0.1	91.4	0.4
1041442	1	7	25.5	<0.1	65.3	0.4
1041443	2	7	28.1	<0.1	86.9	0.5
1041444	1	8	25.5	<0.1	62.5	0.4
1041445	<1	6	22.1	<0.1	90.3	0.5
1041446	<1	7	20.1	<0.1	70.9	0.4
1041447	1	8	23.6	<0.1	68.5	0.4
1041448	1	7	23.4	<0.1	66.5	0.4
1041449	1	9	20.7	<0.1	35.9	0.4
1041450	<1	8	18.2	<0.1	34.4	0.5
1041451	<1	9	17.6	<0.1	54.6	0.5
1041452	<1	7	20.5	<0.1	59.4	0.4
1041453	1	8	27.8	<0.1	39.1	0.5

Taseko Property Technical Report

GC 11-76			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
Sample #	From	To	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	
			MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	
			Standards	section								
1041454	4.85	7	2.15	5.26	0.006	1	80.2	8.3	31	<0.1	14.5	
1041455	7	9	2	4.97	0.007	2.1	73.4	9.1	36	<0.1	19	
1041456	9	12	3	7.58	0.029	95.5	89.7	6.9	31	<0.1	14.7	
1041457	12	15	3	7.16	0.02	3.7	349	7.9	33	0.1	17.4	
1041458	15	18	3	6.69	0.019	2.6	109.5	8.7	42	<0.1	15.4	
1041459	18	21	3	7.35	0.016	15	252.2	8.1	29	<0.1	15.5	
1041460	21	21	Blank	0	0.68	<0.005	0.2	1.6	0.3	2	<0.1	<0.1
1041461	21	24	3	6.37	0.015	2.7	85.2	9.5	31	<0.1	15.4	
1041462	24	27	3	6.58	0.014	1.6	140.2	11.7	48	<0.1	19.3	
1041463	27	30	3	7.59	0.007	1.6	48	9	35	<0.1	18.8	
1041464	30	33	3	5.42	0.05	4.2	408.8	7.6	31	<0.1	15.8	
1041465	33	34	1	3.06	0.253	14.5	1858.2	9.3	36	0.9	18.3	
1041466	34	35	1	2.87	0.291	17	4996.2	9.5	35	0.9	18.1	
1041467	35	36	1	2.88	0.121	3.9	1729.4	6.6	33	0.5	18.6	
1041468	36	38	2	2.41	0.092	19.7	1403	7.3	30	0.3	17.3	
1041469	38	41	3	6.09	0.106	10.6	178.1	16.6	63	<0.1	17.2	
1041470	41	43	2	4.78	<0.005	1.3	169	12.3	39	<0.1	16.7	
1041471	43	44	1	2.38	0.007	5.7	186.7	10.1	45	0.2	19.9	
1041472	44	46	2	5.03	0.007	1.6	83.2	8.3	32	<0.1	18.3	
1041473	46	49	3	6.76	0.026	6.5	269.3	10.1	51	0.2	14.6	
1041474	49	51	2	5.25	0.087	39.9	681.3	6.8	22	0.3	11.5	
1041475	51	54	3	6.18	0.173	17.6	1027.7	7.5	34	0.5	14.3	
1041476	54	57	3	6.02	0.007	1.9	88.3	5.9	27	<0.1	15.4	
1041477	57	60	3	5.64	<0.005	1.7	53.3	6.7	25	<0.1	16.3	
1041478	60	63	3	5.43	<0.005	6.1	118.4	6.3	27	0.2	16.4	
1041479	63	64	1	2.5	0.022	8.3	338.9	5.1	24	0.2	16.2	
1041480	63	64	Duplicate	1	2.01	0.038	13.3	470.5	5.7	26	0.3	16.4
1041481	64	66	2	4.84	0.097	18.7	660.5	7	28	0.3	19.1	
1041482	66	69	3	8.11	0.01	4.2	117.1	5.9	28	0.1	17.7	
1041483	69	72	3	8.1	0.007	2.7	91.5	7.8	29	<0.1	17.6	
1041484	72	75	3	7.77	<0.005	3.3	69.3	7.3	28	<0.1	17.7	
1041485	75	78	3	7.27	0.006	3	67	7.7	29	<0.1	16.4	
1041486	78	81	3	8.77	0.007	4.8	101.1	8	28	<0.1	17	
1041487	81	84	3	6.58	0.055	10.4	523	7.2	30	0.2	19.2	
1041488	84	87	3	7.11	<0.005	6.2	139.4	8.8	39	<0.1	17.6	
1041489	87	90	3	7.39	<0.005	2.4	45.8	8.6	30	<0.1	19	
1041490	90	92	2	5.38	0.017	15.6	73.4	7.8	36	<0.1	17.9	
1041491	92	94	2	4.76	0.028	21	692.9	7.3	42	0.5	20.2	
1041492	94	96	2	5.77	<0.005	8.9	150.2	10.5	43	<0.1	21.4	
1041493	96	99	3	8.11	0.005	49.9	266.4	6.4	36	0.1	20.4	
1041494	99	102	3	8.15	<0.005	5.4	87.6	8.6	36	<0.1	18.7	
1041495	102	105	3	7.85	<0.005	2.7	43.3	9.3	46	<0.1	16.2	
1041496	105	106.8	1.8	4.1	<0.005	1.9	49.3	10.4	66	0.1	7.5	
1041497	106.8	110.5	3.7	5.01	<0.005	2.7	104	7.4	54	17.4	11	
EOH												

Taseko Property Technical Report

GC11-76	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #															
1041454	7.6	327	2.58	3	1	<0.1	7.1	408	<0.1	0.6	0.1	78	2.97	0.034	7.3
1041455	9.5	297	2.66	3	1	<0.1	6.9	399	<0.1	0.8	<0.1	88	2.75	0.047	7.3
1041456	8.2	280	2.19	17	1.1	<0.1	5.8	240	<0.1	2.4	0.1	73	2.67	0.034	5.6
1041457	8.4	254	2.57	11	1.5	<0.1	8.2	356	0.2	1.2	0.1	82	2.17	0.048	6.4
1041458	9.6	480	2.73	18	1.2	<0.1	7.1	240	0.2	6.4	<0.1	66	4.79	0.036	7.6
1041459	7.5	290	2.31	12	1.3	<0.1	7.2	327	<0.1	4	<0.1	76	2.44	0.044	5.7
1041460	<0.2	38	0.03	<1	1.3	<0.1	<0.1	3903	<0.1	<0.1	<0.1	1	36.85	0.003	0.4
1041461	8.4	307	2.43	7	1.4	<0.1	7.9	389	<0.1	1.8	<0.1	76	2.69	0.045	7.2
1041462	9.6	361	2.83	9	2.7	<0.1	7.4	381	0.2	3.4	0.1	84	2.85	0.049	8.1
1041463	8.7	321	2.67	6	1.5	<0.1	7.2	473	<0.1	1.3	<0.1	85	2.51	0.051	7.5
1041464	8.4	270	2.2	8	1.9	<0.1	7	343	<0.1	3.8	<0.1	78	2.29	0.051	7.7
1041465	9.2	321	2.14	15	2.8	3.5	7.7	316	0.2	6.3	0.2	73	2.68	0.053	7.5
1041466	8.9	239	2.37	11	1.9	0.1	6.7	338	0.4	2.5	0.5	73	1.96	0.05	4.6
1041467	9.4	234	2.32	4	1.7	0.2	7.8	404	<0.1	0.9	0.3	86	2.04	0.053	5.9
1041468	11.2	223	2.04	6	1.9	<0.1	7.4	372	<0.1	1.2	0.2	80	1.84	0.053	4.6
1041469	8.4	424	2.32	7	1.4	<0.1	6.6	256	0.1	1.9	0.1	64	3.31	0.037	5.6
1041470	7.3	287	2.34	7	1.2	<0.1	6.8	363	0.1	1.6	<0.1	76	2.99	0.045	5.7
1041471	9.1	337	2.58	5	2.5	<0.1	7	375	<0.1	1.3	0.2	77	3.09	0.045	6.7
1041472	9.3	272	2.54	5	1.9	<0.1	7.2	418	<0.1	0.9	<0.1	79	2.52	0.048	6.8
1041473	8.1	281	2.04	7	1.4	<0.1	8.1	388	0.1	1.7	<0.1	71	2.8	0.045	8.5
1041474	8.8	135	1.14	6	3.8	<0.1	12.6	300	<0.1	1.2	<0.1	45	1.27	0.02	6
1041475	7.7	253	1.78	9	4.4	<0.1	11.7	265	0.1	1.5	<0.1	53	1.34	0.031	8.7
1041476	7.3	220	2.41	6	2.1	<0.1	9.4	445	<0.1	1.3	<0.1	79	1.68	0.048	11.2
1041477	8	218	2.22	6	1.8	<0.1	8.4	433	<0.1	1.2	<0.1	80	2.16	0.046	10.3
1041478	8.2	252	2.3	4	1.8	<0.1	8.1	388	0.1	0.8	<0.1	76	2.4	0.045	9.8
1041479	8	226	1.88	9	1.8	<0.1	8.2	335	<0.1	0.8	0.3	72	1.99	0.044	10.6
1041480	9	230	2.04	11	2.1	<0.1	8.4	337	<0.1	0.9	0.2	74	1.88	0.041	11.7
1041481	10.1	259	2.22	16	2.7	<0.1	8	314	0.1	0.9	0.2	73	2.41	0.045	11
1041482	9.3	259	2.4	8	3	<0.1	9.3	384	<0.1	0.6	<0.1	74	2.39	0.045	9.7
1041483	9.4	266	2.61	6	2.7	<0.1	9.2	406	0.1	0.5	0.1	74	2.24	0.044	10.7
1041484	9.6	257	2.63	7	2.9	<0.1	9.1	451	<0.1	0.6	<0.1	75	2.28	0.042	12.3
1041485	9.4	255	2.55	9	3.8	<0.1	9.5	469	<0.1	0.7	<0.1	75	2.3	0.042	10.4
1041486	9.7	272	2.45	6	3.3	<0.1	9.3	428	<0.1	0.6	<0.1	73	2.31	0.041	11.2
1041487	10.3	247	2.33	9	3.2	<0.1	9.4	374	0.1	0.7	<0.1	77	2.29	0.045	12.9
1041488	9.7	252	2.54	5	2.5	<0.1	8.9	392	<0.1	0.6	<0.1	79	2.42	0.044	10.3
1041489	10.1	307	2.69	5	2.6	<0.1	8.9	384	0.2	0.9	<0.1	78	2.89	0.044	11.8
1041490	9.9	326	2.47	6	2.8	<0.1	9.1	375	0.1	1	<0.1	75	2.66	0.044	11.5
1041491	11.1	323	2.69	18	1.8	<0.1	9.2	254	0.1	1.6	0.2	77	2.19	0.049	16.1
1041492	12.2	341	2.68	8	2.2	<0.1	9.4	405	<0.1	0.8	<0.1	82	2.64	0.052	13.2
1041493	11.2	317	2.58	8	2.7	<0.1	9.2	289	<0.1	0.9	<0.1	80	2.23	0.043	12.3
1041494	10.5	447	2.43	13	3	<0.1	9.4	342	0.2	1.6	<0.1	77	3.42	0.042	10.7
1041495	10	417	2.25	7	3.3	<0.1	8.9	322	<0.1	1.7	0.1	74	3.11	0.038	10.2
1041496	5.4	407	1.78	7	2.7	<0.1	3.5	164	<0.1	5.3	<0.1	49	1.87	0.045	14.7
1041497	11.4	421	1.86	6	1.3	<0.1	2.6	197	<0.1	3.9	<0.1	51	1.89	0.051	15.4

Taseko Property Technical Report

GC11-76	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
Sample #	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
1041454	31	0.96	375	0.264	7.52	3.516	0.89	0.6	9	20	1.6	13.3	2.9	0.3
1041455	30	0.96	537	0.275	7.42	3.141	1.62	0.5	8.1	20	1.4	12.3	2.9	0.2
1041456	24	0.9	453	0.234	6.44	2.43	1.32	1.1	7.4	13	1.3	9.9	2.6	0.2
1041457	32	1	591	0.279	7.07	2.958	1.52	0.6	12.3	17	1.4	11	3.2	0.3
1041458	30	1.48	478	0.221	6.27	1.87	1.52	1.6	9.5	19	0.9	11.2	2.4	0.2
1041459	27	0.53	537	0.263	6.69	2.524	1.85	2.5	12.6	16	1.4	9.6	3	0.2
1041460	<1	1.53	6	0.003	0.1	0.011	0.02	<0.1	0.4	<1	<0.1	0.5	<0.1	<0.1
1041461	28	0.67	849	0.253	7.06	2.862	2.32	7.7	14.4	19	1.3	9.5	2.8	0.2
1041462	38	0.62	811	0.275	7.22	2.582	2.25	10.6	13.1	21	1.4	11	3	0.2
1041463	34	0.74	746	0.288	7.17	2.976	2.07	8.3	14.1	20	1.3	9.3	3.2	0.3
1041464	29	0.62	515	0.277	6.74	2.787	1.86	6	11.4	20	1.7	9.3	3	0.2
1041465	31	0.77	418	0.264	6.69	2.733	1.55	2.4	10.6	20	1.7	11.2	3	0.2
1041466	41	1.02	386	0.281	6.42	3.071	1.45	1.2	11.8	12	1.9	7.9	3.3	0.2
1041467	32	1.23	509	0.298	6.84	3.086	1.72	0.7	12.3	15	2	9	3.6	0.3
1041468	37	1	402	0.285	6.83	3.098	1.51	1.6	12.5	11	1.4	7.9	3.5	0.3
1041469	23	0.66	576	0.224	6.1	2.35	2	3	11.5	15	1.3	9.9	2.7	0.2
1041470	35	0.57	633	0.263	6.54	2.552	2.03	2.8	12.2	17	1.5	9.7	3	0.2
1041471	31	0.85	614	0.274	6.65	2.798	1.91	2	12.5	18	1.4	10.8	3	0.2
1041472	43	0.9	694	0.268	6.94	2.962	2.13	2.1	11.4	18	1.2	9.7	3.3	0.3
1041473	25	0.75	673	0.247	7.43	2.734	1.91	4.3	10.8	22	1.3	9.8	3.2	0.3
1041474	10	0.66	690	0.175	6.95	3.341	1.65	1.6	17.3	13	1.3	5.2	2.5	0.3
1041475	13	0.66	797	0.191	7.03	2.48	2.83	3.2	20.8	20	1.2	8.7	2.6	0.3
1041476	25	0.78	731	0.27	7.8	2.936	2.36	5.5	28.3	28	2.4	9.1	3.4	0.3
1041477	24	0.76	683	0.265	7.63	3.009	2.24	2.6	25.7	27	1.4	8.9	2.8	0.2
1041478	21	0.92	673	0.26	7.42	2.9	2.3	3	21.5	24	1.8	8.6	2.8	0.3
1041479	20	0.93	666	0.251	7.79	2.869	2.28	2	20.9	25	1.9	8.4	2.8	0.3
1041480	23	0.93	668	0.267	7.66	2.697	2.08	2.3	21.1	26	1.6	8.9	3	0.3
1041481	19	1.05	561	0.259	7.5	2.721	1.93	1.7	18.9	26	1.4	9.2	2.8	0.2
1041482	21	0.94	703	0.255	7.47	2.875	2.37	1.1	21.1	24	1.5	9.1	2.8	0.3
1041483	22	1	720	0.249	7.45	3.054	2.14	1.3	21.8	27	1.7	10	2.8	0.3
1041484	21	0.97	766	0.255	7.43	2.939	2.26	1.3	25.6	29	1.7	10.7	2.8	0.3
1041485	22	1	772	0.262	7.58	2.982	2.32	1.7	30.7	26	1.5	10.3	2.9	0.3
1041486	22	1	699	0.241	7.45	2.969	2.25	0.8	26.1	26	1.3	9.4	2.7	0.3
1041487	22	1.13	632	0.268	7.5	2.864	2.32	1	22.5	30	1.4	9.3	3.1	0.3
1041488	26	1.02	713	0.256	7.56	2.777	2.28	0.9	20.9	25	1.3	10.2	2.8	0.2
1041489	23	1.04	688	0.258	7.65	2.781	2.41	0.9	21.4	29	1.5	10.5	2.8	0.3
1041490	22	0.98	635	0.26	7.78	2.708	2.42	0.9	20.8	28	1.5	9.7	2.9	0.3
1041491	24	1.25	954	0.314	8.39	2.639	2.79	1.8	19.9	34	1.9	8.8	3.1	0.3
1041492	28	1.11	855	0.318	9.13	2.859	2.75	1	27.2	30	1.5	10.3	3.1	0.3
1041493	23	1.19	734	0.266	7.47	2.728	2.54	1.4	20.8	26	2.1	9.3	2.9	0.2
1041494	23	0.83	803	0.26	7.03	2.633	1.99	1.9	22.4	23	1.1	9.8	2.9	0.2
1041495	21	0.59	589	0.226	7.14	2.662	1.8	1.5	24.6	24	1.1	10.5	3.3	0.3
1041496	12	0.61	446	0.196	7.45	1.728	1.86	2.5	57.6	32	1	8.2	5.1	0.4
1041497	30	0.54	462	0.206	7.41	2.369	2.08	165.1	56.2	33	1.3	8.3	4.3	0.3

Taseko Property Technical Report

GC11-76	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041454	2	8	27.5	<0.1	32.8	0.4
1041455	<1	8	28.6	<0.1	48.1	0.3
1041456	1	7	38.6	<0.1	60.4	0.3
1041457	1	8	29.1	<0.1	63.2	0.6
1041458	<1	7	132.4	<0.1	72.4	0.5
1041459	1	7	27.5	<0.1	63.3	0.5
1041460	<1	<1	0.7	<0.1	1	<0.1
1041461	<1	7	22.1	<0.1	73.5	0.6
1041462	1	8	27.3	<0.1	70.6	0.6
1041463	<1	7	18.8	<0.1	62.1	0.7
1041464	<1	7	22.5	<0.1	76.6	0.4
1041465	<1	8	20.1	0.2	73.5	0.8
1041466	1	7	24	0.5	58.4	0.5
1041467	1	8	26.4	0.2	70.8	0.5
1041468	1	8	24	0.2	64.5	0.5
1041469	1	6	28.9	<0.1	70	0.5
1041470	<1	7	16	<0.1	59.5	0.6
1041471	<1	8	18.6	<0.1	57.6	0.5
1041472	1	7	19.1	<0.1	56.5	0.6
1041473	1	8	18.5	<0.1	80.1	0.4
1041474	1	4	18.4	0.2	75.5	0.8
1041475	<1	5	18.8	0.1	101.7	0.7
1041476	<1	8	18.4	<0.1	94	0.9
1041477	1	8	22	<0.1	87.9	1
1041478	1	8	25.1	<0.1	96.7	0.7
1041479	<1	8	28.1	<0.1	100.2	0.8
1041480	1	8	31.3	<0.1	92.5	0.8
1041481	<1	8	33	<0.1	100.1	0.6
1041482	<1	8	27.4	<0.1	94.5	0.9
1041483	1	8	29.8	<0.1	75.7	0.9
1041484	1	8	24.3	<0.1	80.2	1
1041485	<1	8	26.3	<0.1	85.6	1.1
1041486	1	8	27.3	<0.1	80.6	1
1041487	1	8	28.6	<0.1	104	1
1041488	<1	8	24.2	<0.1	87	1
1041489	1	9	26.5	<0.1	84.8	0.9
1041490	1	8	26.1	<0.1	95.3	0.8
1041491	1	9	34.6	<0.1	104	1
1041492	1	10	29.9	<0.1	88.8	1.2
1041493	<1	8	25.9	<0.1	94.4	0.8
1041494	<1	8	27.1	<0.1	69.6	0.9
1041495	1	8	25.8	<0.1	65.2	1.1
1041496	2	5	65.9	<0.1	82.3	1.7
1041497	2	5	61.4	<0.1	81.4	1.7

Taseko Property Technical Report

GC 11-77				Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co
Sample #	From	To	Standards	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	PPM
				MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2
				section									
1041498	5.85	8		2.15	5.53	0.013	2.5	100.8	11.2	49	0.2	20.2	10.1
1041499	8	10		2	4.1	0.01	1.5	59.5	9.8	49	0.1	20.2	9.4
1041500	10	10	Cm2	0	0.1	1.238	276.6	9668.6	84.1	125	4.5	31.2	18.6
1041501	10	12		2	4.62	0.017	1.8	84	10.1	49	<0.1	23.7	10.6
1041502	12	15		3	7.8	0.014	3.9	192.1	9.3	46	0.1	21.6	10.9
1041503	15	18		3	8.14	0.007	2.8	73.1	9.4	49	<0.1	23	11
1041504	18	21		3	7.33	<0.005	5	82.5	8.6	39	0.1	18.7	9.4
1041505	21	24		3	6.35	<0.005	8.3	67.6	11.5	45	<0.1	19.1	8.5
1041506	24	27		3	5.93	<0.005	3.2	88.6	10.3	40	<0.1	18.1	8.2
1041507	27	30		3	5.28	<0.005	2.6	89.7	14.2	63	<0.1	18.9	8.5
1041508	30	33		3	6.62	0.062	33.6	472.9	28	67	0.2	18.8	9.7
1041509	33	36		3	7.55	<0.005	2	56.4	11.8	47	<0.1	19.3	9.6
1041510	36	39		3	6.2	<0.005	4.3	61.2	14	49	<0.1	19.4	10
1041511	39	42		3	4.99	<0.005	2	41	12.7	74	<0.1	25.6	14.1
1041512	42	45		3	8.51	0.008	1.7	108.7	9.8	45	<0.1	18.2	8.8
1041513	45	48		3	6.6	<0.005	1.1	71.1	10	35	<0.1	16.2	8.2
1041514	48	51		3	6.97	<0.005	1.4	42.5	9.6	41	<0.1	18.5	8.5
1041515	51	54		3	7.04	<0.005	1.9	50	10.9	69	<0.1	20	9.8
1041516	54	57		3	8.1	<0.005	1.1	39.1	9.5	39	<0.1	20.1	8.9
1041517	57	60		3	8.07	<0.005	1.1	41.4	11.1	44	0.1	19.5	9.9
1041518	60	63		3	7.32	<0.005	1	50.2	11.2	44	<0.1	19.1	10
1041519	63	64		1	2.51	0.023	1.1	78.7	10.5	48	<0.1	23.2	12.1
1041520	63	64	Duplicate	1	2.34	0.026	1.1	103.9	11.8	56	<0.1	26.4	13.6
1041521	64	66		2	5.47	0.023	4.6	111.7	10.9	47	<0.1	23	11
1041522	66	69		3	7.87	0.022	1.4	79.4	10.2	40	<0.1	20.3	10.2
1041523	69	72		3	8.26	0.027	8.6	101.8	8.7	26	<0.1	10.8	6.1
1041524	72	75		3	5.51	0.008	59.7	381.4	7.2	30	0.1	13.8	7.7
1041525	75	78		3	6.7	0.005	13.3	198.3	5.6	27	<0.1	11.7	6
1041526	78	81		3	6.42	0.03	24.5	190.9	6.1	23	0.1	12	5.9
1041527	81	84		3	7.19	0.006	18.1	98	7	31	0.1	14.7	8.4
1041528	84	87		3	7.25	<0.005	2.1	59.6	8.3	31	<0.1	19.6	10.1
1041529	87	90		3	8.38	0.022	35.7	212.1	9.5	33	0.1	19.2	10.6
1041530	90	93		3	7.06	0.012	12.9	328.8	8.9	42	0.1	22.2	12.3
1041531	93	96		3	6.48	0.021	6.8	213.8	8.5	30	0.2	17.8	9.6
1041532	96	99		3	4.39	0.054	9.1	358.6	7.7	36	0.1	21.4	11.6
1041533	99	102		3	7.13	0.014	15.9	287.8	7.9	31	0.1	17.7	9.9
1041534	102	105		3	7.72	<0.005	6.1	92.7	7.3	26	<0.1	16.7	8.9
1041535	105	108		3	5.58	0.011	50.6	381	7.6	31	0.3	18.5	10.8
1041536	108	111		3	8.17	0.007	8.2	109.7	7.2	30	<0.1	18.1	9.9
1041537	111	114		3	7.3	0.007	8	292.7	8.2	36	0.3	18.3	9.3
1041538	114	117		3	7.64	<0.005	4.8	153.5	7.2	30	<0.1	17.5	10.1
1041539	117	120		3	8.15	0.005	11.6	176.4	7.4	26	<0.1	18.8	10
1041540	120	120	Blank	0	0.62	<0.005	<0.1	0.5	<0.1	<1	<0.1	0.5	<0.2
1041541	120	123		3	7.4	0.009	2.3	131.1	7.4	26	<0.1	18.6	9.8
1041542	123	126		3	8.13	0.01	3.5	119.9	7.7	27	<0.1	17.4	9.7

Taseko Property Technical Report

GC11-77	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #														
1041498	330	2.88	5	1.3	<0.1	8.9	412	0.1	0.9	0.1	90	2.67	0.049	9.4
1041499	305	2.76	5	1	<0.1	9.2	329	<0.1	1.8	<0.1	89	2.64	0.049	9.5
1041500	323	4.66	32	5.7	1.3	11.2	166	3.3	22.1	2.3	92	1.49	0.062	31
1041501	311	2.93	5	1.2	<0.1	7.7	387	<0.1	0.9	<0.1	89	2.78	0.053	10.4
1041502	273	3.26	6	1.3	<0.1	8.8	396	<0.1	0.8	<0.1	106	2.45	0.061	9.1
1041503	315	3.01	7	1.5	<0.1	10.3	358	<0.1	0.8	<0.1	107	2.53	0.057	10.3
1041504	366	2.54	11	1.1	<0.1	6.4	203	0.1	3.5	<0.1	85	3.43	0.043	8.2
1041505	230	2.49	11	2.3	<0.1	9.5	305	<0.1	1.6	<0.1	80	1.9	0.048	9.8
1041506	283	2.61	13	1.6	<0.1	9.5	246	<0.1	4.1	<0.1	78	2.16	0.046	8.7
1041507	276	2.49	10	1.7	<0.1	9.8	309	<0.1	2.7	<0.1	78	2.12	0.052	9.1
1041508	335	2.41	12	1.7	<0.1	8.3	329	0.2	4.8	<0.1	76	2.56	0.044	8.5
1041509	316	2.38	8	1.6	<0.1	9.1	380	<0.1	1.1	<0.1	77	2.48	0.047	10
1041510	405	2.63	9	1.5	<0.1	8	356	<0.1	1.9	<0.1	73	3.37	0.048	8.5
1041511	622	3.26	13	6.3	<0.1	8.1	285	<0.1	3.6	<0.1	53	5.9	0.033	9.5
1041512	349	2.2	10	1.6	<0.1	8.6	275	<0.1	3.4	<0.1	70	2.4	0.042	6.9
1041513	260	2.07	10	1.5	<0.1	10.6	285	<0.1	4.4	<0.1	72	1.99	0.042	7.7
1041514	293	2.08	11	1.1	<0.1	8	273	<0.1	4.1	<0.1	71	2.3	0.046	7.5
1041515	358	2.65	8	1.7	<0.1	9.1	398	<0.1	2.2	<0.1	76	2.82	0.052	8.7
1041516	279	2.37	7	1.8	<0.1	9.2	404	<0.1	0.7	<0.1	70	2.37	0.044	7.8
1041517	308	2.73	8	1.6	<0.1	9.1	408	<0.1	1.5	<0.1	86	2.84	0.052	8.6
1041518	330	2.53	8	1.5	<0.1	8.8	370	<0.1	2.1	<0.1	76	2.86	0.05	9.4
1041519	414	2.88	11	1.5	<0.1	8	265	<0.1	5.6	<0.1	75	4.16	0.044	9.5
1041520	532	3.29	12	2.7	<0.1	8	291	<0.1	4.4	<0.1	71	5.39	0.045	11.3
1041521	324	2.84	9	2.5	<0.1	9	404	0.1	2	<0.1	84	3.01	0.056	11.6
1041522	284	2.54	7	2.7	<0.1	9.5	391	<0.1	0.5	<0.1	75	2.36	0.048	8.7
1041523	170	1.67	8	2.2	<0.1	13.9	300	<0.1	1.4	<0.1	49	1.65	0.029	6.5
1041524	263	1.69	13	2.3	<0.1	12.3	181	0.2	5.3	<0.1	48	2.7	0.024	6.6
1041525	236	1.62	12	1.6	<0.1	11.5	180	<0.1	2.2	<0.1	51	2.57	0.029	7.7
1041526	163	1.58	9	1.8	<0.1	12.3	208	0.1	1.3	<0.1	51	1.8	0.029	15.2
1041527	232	1.98	7	2	<0.1	12.5	191	0.1	1.5	<0.1	54	2.03	0.033	10.5
1041528	263	2.63	6	2.5	<0.1	10.5	330	0.2	1.1	<0.1	72	2.76	0.045	12.7
1041529	262	2.61	6	3.2	<0.1	10.2	360	0.1	0.8	0.1	83	2.4	0.047	15.5
1041530	395	2.94	15	3.9	<0.1	9	342	0.1	2	<0.1	80	3.85	0.048	11.7
1041531	253	2.52	22	2.1	0.2	9.3	354	0.3	4.5	0.2	80	2.56	0.049	10.8
1041532	368	2.39	23	4.6	<0.1	7.8	160	0.1	6.3	0.1	68	2.66	0.043	7.9
1041533	258	2.3	22	3.9	<0.1	9.2	256	<0.1	7.2	<0.1	71	2.4	0.045	9.1
1041534	251	2.48	9	2.1	<0.1	9.9	397	<0.1	1.1	<0.1	71	2.07	0.043	8.9
1041535	278	2.35	21	2.4	<0.1	8.3	285	<0.1	3.8	0.1	69	2.6	0.044	7.3
1041536	270	2.46	10	2.8	<0.1	9.7	318	<0.1	1.6	<0.1	70	2.4	0.044	8.8
1041537	282	2.42	12	2.8	<0.1	9.4	334	<0.1	3.6	0.3	71	2.64	0.043	10.1
1041538	360	2.55	12	2.1	<0.1	7.7	251	0.1	1.9	<0.1	72	3.06	0.046	9.5
1041539	230	2.66	6	3	<0.1	9.8	431	<0.1	0.6	<0.1	75	2.29	0.043	9.3
1041540	23	<0.01	16	1.5	<0.1	<0.1	4713	<0.1	<0.1	<0.1	<1	35.42	0.003	0.6
1041541	245	2.57	8	3.4	<0.1	9.2	360	<0.1	0.6	<0.1	72	2.46	0.044	8.5
1041542	265	2.57	7	3.3	<0.1	10.2	429	<0.1	0.5	<0.1	72	2.54	0.042	10.9

Taseko Property Technical Report

GC11-77	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #														
1041498	44	0.9	1139	0.319	7.4	2.919	1.87	4	10	24	1.7	15.8	3.1	0.3
1041499	34	1.01	549	0.304	7.18	2.896	1.9	0.8	8.4	23	1.5	16	3.1	0.3
1041500	97	0.93	126	0.194	6.67	0.725	3.77	17.4	23	54	3.7	12.2	2.8	0.2
1041501	45	1.14	415	0.345	7.57	3.143	1.33	1.1	9.2	26	1.9	18.5	3.6	0.3
1041502	40	1.28	448	0.367	7.52	3.208	1.29	1.4	9.6	27	2.4	21.4	3.8	0.3
1041503	51	1.11	701	0.352	7.14	2.787	1.95	0.7	10.9	28	2	18.9	3.6	0.3
1041504	31	1.19	692	0.286	6.59	1.88	1.95	3.1	7.5	22	1.4	16.8	3.1	0.2
1041505	39	0.7	636	0.315	7.2	2.64	1.98	1.1	13.1	23	1.3	15.3	3.1	0.3
1041506	31	0.76	502	0.311	7.33	2.069	1.95	2.7	12.5	23	1.6	14.8	3.2	0.2
1041507	38	0.76	631	0.308	6.92	2.576	2.22	2	12.8	22	1.3	12.1	3.2	0.3
1041508	30	0.95	649	0.288	6.91	2.52	1.97	1	12.2	20	1.1	12.6	3.2	0.2
1041509	38	0.74	784	0.307	6.75	2.681	2.4	2.2	13	24	1	10.9	3.2	0.3
1041510	30	0.89	677	0.287	6.6	2.465	1.88	4.3	10.7	21	1	12.3	2.9	0.2
1041511	25	2.01	579	0.2	5.66	1.58	1.82	2.2	9.7	22	1.3	17.8	2.3	0.2
1041512	29	0.74	492	0.281	6.53	2.361	1.98	2.9	10	18	1.3	12.2	3	0.3
1041513	28	0.58	667	0.28	7	2.331	2.44	4.1	10.7	19	1.3	11.1	2.8	0.2
1041514	30	0.72	471	0.288	7.03	2.505	1.84	2	9.7	20	1.6	12.6	3.2	0.3
1041515	33	0.94	777	0.322	7.33	2.794	2.08	1.5	12.5	21	1.2	13.9	3.5	0.3
1041516	28	0.9	772	0.284	7.24	2.866	2.2	0.9	12	19	1.1	12	3.1	0.2
1041517	35	0.89	713	0.309	7.28	2.903	2.04	1.1	11.7	22	1.2	14.1	3.3	0.3
1041518	31	0.83	748	0.303	6.86	2.645	2.17	2.7	10.5	23	1	12.6	3.1	0.2
1041519	32	1.28	1278	0.271	6.9	1.999	1.83	2	7.8	22	1.2	14.2	3	0.2
1041520	30	1.57	951	0.261	6.75	1.846	1.68	2.2	7.3	25	1.3	17	2.8	0.2
1041521	42	0.93	745	0.324	7.57	2.708	2	1.1	10	29	1.4	15.7	3.4	0.2
1041522	32	1.07	728	0.293	7.08	2.832	2.19	0.5	10.7	22	1.3	13.5	3.5	0.3
1041523	25	0.51	833	0.209	6.75	2.565	2.84	1.5	16.4	15	1	9.2	3.3	0.3
1041524	13	0.81	786	0.195	6.06	1.67	2.85	1.2	16.5	13	0.8	8	2.6	0.3
1041525	18	0.58	758	0.217	6.19	1.594	2.97	1.8	16.1	17	1.1	9.2	3.1	0.3
1041526	15	0.48	813	0.221	6.5	1.979	3.04	5	15.7	31	0.9	7.5	3.1	0.3
1041527	21	0.62	984	0.23	6.46	1.999	2.8	1.6	12.6	23	0.9	9.6	3	0.3
1041528	25	1.04	797	0.277	6.86	2.426	2.65	1.1	15.2	31	1.9	12.8	3.1	0.3
1041529	39	0.98	774	0.303	6.9	2.759	2.57	0.8	14.9	35	2.1	12.9	3.2	0.3
1041530	28	0.82	769	0.289	7.3	2.207	2.45	1.9	13.6	28	1.3	14.8	2.8	0.3
1041531	32	0.8	745	0.275	6.98	2.507	2.69	3.6	12.2	24	1.7	9.8	2.9	0.3
1041532	22	1.08	544	0.246	6.2	1.549	2.41	1.7	12.6	18	1.3	10.3	2.6	0.2
1041533	30	0.82	514	0.256	6.85	1.992	2.61	1.6	11.9	20	1.5	8.4	2.8	0.3
1041534	26	0.8	734	0.248	6.62	2.708	2.73	1.8	15.2	21	1.9	9.6	2.9	0.3
1041535	28	0.91	632	0.254	6.54	2.361	2.35	1.4	12.7	17	1.4	9.2	2.7	0.2
1041536	24	0.89	694	0.259	6.67	2.62	2.62	1	14.5	20	1.7	9.4	2.9	0.3
1041537	32	0.84	769	0.256	6.62	2.48	2.59	1.2	15.3	22	1.4	9.7	2.8	0.3
1041538	23	0.94	666	0.251	6.73	2.146	2.4	1.2	13.4	22	1.3	10.1	2.4	0.2
1041539	33	1.02	750	0.262	6.85	2.79	2.73	0.7	13.9	22	1.5	10	3	0.3
1041540	<1	1.63	4	0.001	0.02	0.003	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1
1041541	34	1	770	0.263	6.81	2.736	2.84	0.5	14.1	20	1.4	10.6	3	0.2
1041542	25	0.95	829	0.26	6.58	2.697	2.8	0.6	15.3	25	1.4	10.5	3.1	0.3

GC11-77	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041498	1	8	28.5	<0.1	57.3	0.4
1041499	<1	8	35.3	<0.1	61.8	0.5
1041500	1	10	12.3	2.3	136.7	0.8
1041501	1	9	36	<0.1	50.4	0.5
1041502	1	10	33.2	<0.1	55.2	0.5
1041503	1	9	26.3	<0.1	63.2	0.6
1041504	<1	8	47.9	<0.1	82	0.4
1041505	<1	8	30.6	<0.1	62.3	0.7
1041506	1	7	68.5	<0.1	61.2	0.7
1041507	1	7	24.7	<0.1	73.8	0.7
1041508	1	8	26.9	<0.1	59.3	0.5
1041509	1	7	20.3	<0.1	66	0.6
1041510	1	7	22.6	<0.1	57	0.5
1041511	1	6	45.6	<0.1	71.7	0.4
1041512	1	8	35.3	<0.1	65.6	0.5
1041513	1	8	28.4	<0.1	70.6	0.6
1041514	<1	7	46.3	<0.1	59.9	0.4
1041515	<1	7	27.4	<0.1	66.4	0.6
1041516	<1	7	29.8	<0.1	66.5	0.5
1041517	1	9	28.8	<0.1	59	0.6
1041518	<1	8	27.3	<0.1	68.5	0.5
1041519	1	8	44.4	<0.1	64.6	0.4
1041520	<1	7	43.4	<0.1	66.6	0.4
1041521	<1	9	27.8	<0.1	65.8	0.5
1041522	1	7	28.4	<0.1	66.3	0.6
1041523	1	5	19	<0.1	75.3	0.7
1041524	<1	4	67	<0.1	91.4	0.7
1041525	1	5	48.6	<0.1	88.7	0.6
1041526	<1	5	22.5	<0.1	89.2	0.7
1041527	1	5	29.9	<0.1	91.8	0.6
1041528	1	7	23.9	<0.1	79.6	0.7
1041529	1	8	23.1	<0.1	78	0.8
1041530	1	8	22.8	<0.1	77.7	0.6
1041531	1	9	22.9	<0.1	73.9	0.6
1041532	1	8	66.3	<0.1	90	0.6
1041533	1	8	36.4	<0.1	81.2	0.6
1041534	<1	7	18.4	<0.1	72.2	0.7
1041535	<1	7	29.4	<0.1	74.4	0.6
1041536	<1	8	22	<0.1	78.6	0.7
1041537	1	8	26.9	<0.1	71.9	0.6
1041538	<1	8	45.9	<0.1	67.9	0.6
1041539	<1	8	22.5	<0.1	71.8	0.7
1041540	<1	<1	0.3	<0.1	0.1	<0.1
1041541	1	8	26.7	<0.1	73.9	0.6
1041542	<1	8	20.7	<0.1	74.5	0.7

Taseko Property Technical Report

GC 11-77				Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co
Sample #	From	To	Standards	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	PPM
			section	MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2
1041543	126	129		3	6.96	<0.005	4.6	139.4	7.4	25	<0.1	18.1	9.6
1041544	129	132		3	7.52	<0.005	2	27.9	7.3	27	<0.1	19.2	9.6
1041545	132	135		3	8.29	<0.005	2.2	54.1	6.8	27	<0.1	19.5	10.2
1041546	135	138		3	8.07	<0.005	1.3	31.1	7.3	24	<0.1	19.4	10.5
1041547	138	141		3	7.66	<0.005	2	26.5	7.3	27	<0.1	18.9	9.3
1041548	141	144		3	8.35	<0.005	1.8	48	7	23	<0.1	17.4	9.4
1041549	144	147		3	6.79	0.013	2	91.4	10.6	34	<0.1	18.2	9.7
1041550	147	150		3	7.87	<0.005	2.1	90.4	7.8	30	<0.1	19.8	11.1
1041551	150	153		3	7.56	0.018	3.5	120.7	7.1	28	<0.1	18.7	10.5
1041552	153	156		3	8.32	0.015	2.4	147.8	6.7	26	<0.1	19.4	11.1
1041553	156	159		3	7.89	0.005	1.7	70.4	7.8	28	<0.1	18.6	11.5
1041554	159	160		1	2.93	0.034	3.4	141.4	7.7	35	0.2	16.4	10.5
1041555	160	162		2	4.84	<0.005	2.1	61.8	7.3	30	<0.1	21.5	11.9
1041556	162	165		3	7.61	0.006	4	78.7	6.4	25	<0.1	21.8	10.8
1041557	165	168		3	6.66	0.015	4.5	177.3	6.6	27	<0.1	21.2	10.9
1041558	168	171		3	6.23	<0.005	14.1	60.5	6.2	24	<0.1	18.3	9.5
1041559	171	174		3	5.25	<0.005	1.9	132.1	7.4	25	<0.1	16.4	9.7
1041560	174	174	C m2	0	0.11	1.59	281.1	9610.2	76.3	128	5.1	33.4	19.7
1041561	174	177		3	7.19	0.01	1.3	142.6	7	23	<0.1	14.9	8.6
1041562	177	180		3	5.64	0.011	6.1	164.2	7.7	30	0.1	14.8	7.7
1041563	180	183		3	7.33	<0.005	1.5	91.3	8.7	37	<0.1	16.1	8.5
1041564	183	186		3	6.83	<0.005	1.3	83.1	8.2	28	<0.1	16.3	8.7
1041565	186	189		3	7.12	<0.005	1.1	29.6	9.4	41	0.1	16.9	10.1
1041566	189	192		3	5.99	0.038	1.5	147.9	9.6	34	<0.1	13.6	7.8
1041567	192	195		3	8.18	<0.005	1.8	53.8	7.2	30	<0.1	16.7	9.7
1041568	195	198		3	7.86	0.038	2.7	79.6	8	33	<0.1	18.7	10.4
1041569	198	201		3	8.34	0.015	3.2	89.2	7.7	33	<0.1	18.6	11.7
1041570	201	204		3	7.64	<0.005	1.6	35.1	7.1	30	<0.1	17	10.3
1041571	204	207		3	6.97	<0.005	1.4	54	7.1	20	<0.1	10.2	5.8
1041572	207	210		3	7.73	0.007	1.3	54.6	9.1	33	<0.1	17.8	10
1041573	210	213		3	7	<0.005	1.1	47.9	8	32	<0.1	19.5	10.4
1041574	213	216		3	6.19	<0.005	0.9	58.4	8.8	25	<0.1	15.4	8.6
1041575	216	219		3	7.22	0.052	1.2	59.4	7.7	24	<0.1	14.5	8.2
1041576	219	222		3	7.85	0.019	1.6	98.8	7	25	<0.1	13.7	7.9
1041577	222	225		3	6.64	0.014	2.1	78.4	7.3	26	<0.1	13.9	8.8
1041578	225	228		3	7.29	0.059	9.1	379.3	8.3	27	0.2	13.4	8.7
1041579	228	229		1	2.89	0.007	1.2	43.9	7.4	25	<0.1	14.9	8.4
1041580	228	229	Duplicate	1	2.66	0.005	1.1	55.6	7.3	26	<0.1	15.4	8.3
1041581	229	231		2	5.65	0.027	1.7	204.2	7.6	27	0.5	15	10.1
1041582	231	234		3	7.73	0.006	1.3	47	8.3	36	<0.1	15.6	8.6
1041583	234	237		3	7.51	0.008	1.5	113.7	8.6	36	0.1	17.5	9.2
1041584	237	240		3	8.04	<0.005	1.7	86.2	7.9	75	0.4	15.7	10.3
1041585	240	243		3	7.93	0.006	2.5	166.6	8.9	34	<0.1	14.9	9.2
1041586	243	246		3	7.32	<0.005	1.5	50.7	7.2	24	<0.1	14.9	8.3

Taseko Property Technical Report

GC11-77	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #														
1041543	249	2.51	7	2.1	<0.1	9.8	393	<0.1	0.6	<0.1	76	2.53	0.044	8.2
1041544	274	2.59	5	3.1	<0.1	9.6	433	<0.1	0.5	<0.1	75	2.53	0.046	9.2
1041545	300	2.84	9	2.8	<0.1	8	481	<0.1	0.8	<0.1	83	2.73	0.05	12.7
1041546	280	2.78	8	2.5	<0.1	8.3	456	<0.1	0.7	<0.1	80	2.8	0.046	9.2
1041547	287	2.65	9	2.4	<0.1	8.8	406	<0.1	0.8	0.1	76	2.77	0.046	8.3
1041548	255	2.51	8	1.9	<0.1	7.9	396	<0.1	0.8	<0.1	73	2.52	0.042	6.8
1041549	278	2.49	10	2	<0.1	7.6	386	<0.1	2.2	<0.1	78	2.88	0.049	10.8
1041550	312	2.7	12	1.8	<0.1	7.1	400	<0.1	1.8	<0.1	82	2.97	0.046	9.5
1041551	326	2.68	11	2.7	<0.1	6.9	437	<0.1	1.7	<0.1	78	3.24	0.047	9.6
1041552	279	2.76	9	2	<0.1	7	406	<0.1	1.3	<0.1	82	2.94	0.05	10.4
1041553	338	2.74	10	2.5	<0.1	7.5	445	<0.1	1.4	<0.1	82	3.3	0.051	9.8
1041554	460	2.5	15	4.4	<0.1	9.8	298	0.2	3.8	0.3	62	3.67	0.037	9.2
1041555	305	2.78	6	2.1	<0.1	7.1	457	<0.1	1.4	<0.1	83	2.75	0.052	9.4
1041556	300	2.87	8	2.1	<0.1	6.8	493	<0.1	1.1	<0.1	89	2.6	0.051	9.6
1041557	297	2.99	7	2	<0.1	6.7	440	<0.1	1.5	<0.1	87	2.89	0.051	10.4
1041558	273	2.6	6	1.9	<0.1	7.3	528	0.1	1.1	<0.1	85	2.72	0.053	9.1
1041559	362	2.39	10	2	<0.1	8.5	380	0.1	1.8	<0.1	70	3.73	0.043	7.7
1041560	350	4.78	33	5.4	1.7	10.3	186	2.8	21	3.9	95	1.46	0.077	29.2
1041561	283	2.14	9	1.6	<0.1	7.9	331	0.1	2.3	<0.1	69	3	0.042	6.5
1041562	274	2.04	11	1.6	<0.1	8.5	422	<0.1	2	<0.1	73	3.09	0.044	7
1041563	274	2.33	8	1.8	<0.1	8.5	376	<0.1	2	<0.1	70	2.6	0.042	7.2
1041564	273	2.3	8	1.9	<0.1	8.8	365	<0.1	2.8	<0.1	72	2.68	0.043	8.5
1041565	444	2.41	11	1.4	<0.1	8	256	<0.1	3.3	<0.1	62	3.86	0.041	8.1
1041566	256	1.92	15	2.7	<0.1	8.2	326	0.1	1.4	0.1	58	2.56	0.037	8.4
1041567	312	2.45	4	3.4	<0.1	9.2	409	<0.1	0.3	0.3	76	2.52	0.044	13
1041568	339	2.49	3	3.7	<0.1	9.1	404	0.1	0.3	0.3	78	2.42	0.042	11
1041569	357	2.59	5	3.8	<0.1	9.4	414	<0.1	0.5	0.2	80	2.58	0.044	13.9
1041570	347	2.43	3	3	<0.1	9.4	378	<0.1	0.7	0.1	75	2.66	0.04	12.4
1041571	181	1.63	5	5.4	<0.1	15.7	289	<0.1	0.9	<0.1	45	1.6	0.027	11.9
1041572	333	2.33	7	4.9	<0.1	12	371	<0.1	1.7	0.1	71	2.87	0.04	13.8
1041573	332	2.6	7	2.8	<0.1	7.9	352	<0.1	3.9	<0.1	80	3.11	0.044	9.5
1041574	232	2.13	7	3.1	<0.1	9.9	394	<0.1	1	<0.1	74	2.13	0.041	10.8
1041575	218	2.01	5	3.2	<0.1	13.3	365	<0.1	1.5	<0.1	66	1.86	0.038	12
1041576	231	2.01	6	4.7	<0.1	12.6	346	<0.1	0.6	<0.1	58	1.82	0.037	13.8
1041577	257	2.06	9	3.6	<0.1	12	294	<0.1	1.2	<0.1	57	2.14	0.034	10.4
1041578	273	2.11	10	3.3	<0.1	9.9	272	<0.1	1.5	<0.1	63	2.51	0.038	13.2
1041579	240	2.24	7	4	<0.1	10.5	382	<0.1	0.6	<0.1	65	2.04	0.036	10.6
1041580	249	2.2	7	4.2	<0.1	9.7	394	<0.1	0.5	<0.1	64	2.15	0.035	12
1041581	244	2.17	6	3.8	0.8	11.3	384	<0.1	0.5	<0.1	64	2.04	0.037	12
1041582	281	2.13	6	2.9	<0.1	11	370	<0.1	1.2	<0.1	65	2.22	0.041	13.1
1041583	331	2.31	9	5.1	<0.1	10.8	288	<0.1	2.8	<0.1	64	2.71	0.035	12.6
1041584	297	2.25	5	4.5	0.9	11	353	<0.1	0.9	<0.1	67	2.38	0.038	14.2
1041585	295	2.05	9	4	<0.1	12.4	316	0.1	2.8	<0.1	62	2.17	0.033	13.6
1041586	265	2.03	5	2.7	<0.1	10.2	355	<0.1	1.1	<0.1	62	2.08	0.035	11.5

Taseko Property Technical Report

GC11-77	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #														
1041543	33	0.88	698	0.259	6.57	2.743	2.48	0.8	13.2	20	1.4	9.4	3	0.3
1041544	26	1.01	763	0.255	6.87	2.76	2.67	0.6	13.6	21	1.3	10.3	2.9	0.2
1041545	39	1.16	752	0.278	7.03	2.897	2.54	0.7	12.9	29	1.4	10.7	3	0.2
1041546	27	1.1	749	0.265	6.83	2.813	2.56	0.4	12.1	22	1.3	9.7	2.7	0.2
1041547	36	1.08	813	0.263	6.82	2.662	2.55	0.7	11.7	21	1.3	9.7	2.7	0.2
1041548	24	0.94	698	0.252	6.84	2.705	2.34	0.8	10.6	17	1.5	9.3	2.7	0.2
1041549	30	0.88	774	0.282	6.8	2.527	2.31	1.8	12.9	24	1.8	9.8	2.9	0.2
1041550	29	0.99	705	0.27	6.69	2.715	2.54	2.7	15.6	23	1.4	9.3	2.6	0.2
1041551	31	1.25	757	0.252	6.84	2.72	2.27	1.9	13.1	22	1.3	9.6	2.5	0.2
1041552	28	1.04	704	0.268	6.75	2.663	2.27	1.9	13.2	24	1.5	9.4	2.6	0.2
1041553	31	1.02	785	0.257	7.03	2.704	2.32	1.5	13.5	23	1.2	10.1	2.5	0.2
1041554	18	1.33	1004	0.2	6.19	2.333	2.46	1.5	14.8	21	0.9	11.2	2.3	0.3
1041555	32	1.08	735	0.266	7.23	2.99	2.26	2	13	22	1.1	10.2	2.5	0.2
1041556	29	1.25	817	0.288	6.89	2.993	2.44	1.5	11.9	23	1.5	9.9	2.6	0.2
1041557	29	1.07	794	0.278	7.12	2.888	2.25	1.2	12.7	25	1.7	9.7	2.8	0.2
1041558	27	0.95	748	0.287	7.05	3	2.33	4.3	14	22	1.3	9.4	2.8	0.2
1041559	23	1.01	885	0.238	6.53	2.342	2.18	3.5	9.4	19	1.1	11.7	2.5	0.2
1041560	102	0.95	77	0.194	6.56	0.761	3.58	18.6	24.9	54	4.1	11	3.3	0.2
1041561	22	0.81	561	0.233	6.69	2.622	1.89	1.7	8.4	17	1.4	9.4	2.4	0.2
1041562	23	0.73	521	0.244	6.9	2.956	1.53	3.9	9.5	19	2.2	10.1	2.6	0.2
1041563	23	0.63	918	0.242	6.65	2.577	2.47	2.4	10.3	18	1.3	8.3	2.7	0.3
1041564	24	0.76	693	0.244	6.68	2.54	2.55	3.2	9.6	21	1.1	8.4	2.7	0.3
1041565	19	1.12	756	0.214	6.15	1.916	2.22	1.9	8.9	20	0.9	9.6	2.4	0.2
1041566	17	0.68	723	0.211	6.37	2.395	2.48	0.6	11.2	20	0.7	8.4	2.6	0.2
1041567	21	0.96	767	0.278	7.19	2.688	2.71	1	15.7	26	1.1	11	3.5	0.3
1041568	25	1.03	787	0.275	7.13	2.654	2.2	0.7	14.3	24	0.8	10.4	3.1	0.3
1041569	24	1.06	788	0.271	7.67	2.672	2.68	0.8	13.1	31	0.9	11.6	3.2	0.2
1041570	23	0.86	755	0.257	7.31	2.585	2.63	0.8	10.3	27	0.8	11.7	2.9	0.3
1041571	14	0.46	672	0.191	6.73	2.418	3.34	1.9	15.8	26	0.9	8.8	3.8	0.4
1041572	20	0.81	708	0.251	7.18	2.455	2.81	3.7	13.1	32	1.1	12.3	3.3	0.3
1041573	23	1.05	1095	0.273	7.37	2.232	2.45	1.2	11.6	24	1.5	11.4	2.8	0.3
1041574	22	0.66	711	0.258	7.08	2.652	2.68	3	14.9	25	1.4	8.7	3.3	0.3
1041575	20	0.56	698	0.24	7.4	2.67	2.9	3	16.6	26	1.1	8.3	3.6	0.3
1041576	19	0.72	720	0.219	7.01	2.733	3.1	1.2	16.1	30	1.2	8.8	3.1	0.3
1041577	18	0.53	692	0.219	6.86	2.369	3.02	1.8	17	25	1.2	9.8	3.2	0.4
1041578	19	0.63	626	0.229	6.91	2.242	2.85	1	18.9	30	1.1	10.1	3.2	0.3
1041579	27	0.86	727	0.237	6.84	2.49	2.91	0.7	18.6	25	1.2	10.2	3.1	0.3
1041580	20	0.84	731	0.232	6.83	2.458	2.96	0.7	21	28	1.5	11.2	3.3	0.3
1041581	20	0.73	745	0.235	6.87	2.573	2.93	1.6	17.6	27	1.2	9.4	3.2	0.3
1041582	26	0.73	796	0.247	8.12	2.887	2.98	1.5	17.9	30	1.1	11	3.3	0.3
1041583	20	0.77	844	0.229	7.01	2.238	2.79	1.2	17.4	28	1	11.1	2.9	0.3
1041584	27	0.91	825	0.241	7.29	2.499	2.91	0.8	17.1	31	1	10.8	3	0.3
1041585	19	0.77	662	0.226	7.29	2.357	2.93	1	17.3	29	1	10.7	3.2	0.3
1041586	26	0.73	777	0.233	7.31	2.55	3	1.8	17.8	28	0.8	9.8	3	0.3

GC11-77	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041543	<1	8	20	<0.1	65.7	0.7
1041544	1	8	21.4	<0.1	66.6	0.6
1041545	<1	9	28.2	<0.1	70.5	0.6
1041546	<1	8	22.9	<0.1	62.8	0.6
1041547	1	8	23	<0.1	62.9	0.6
1041548	<1	7	21.7	<0.1	63.1	0.5
1041549	<1	8	24.2	<0.1	71.4	0.6
1041550	<1	8	19.5	<0.1	65	0.7
1041551	<1	8	28.3	<0.1	62.9	0.6
1041552	<1	9	26.7	<0.1	63	0.6
1041553	<1	9	23.2	<0.1	62.2	0.7
1041554	<1	7	28.5	<0.1	72.3	0.7
1041555	<1	9	27.3	<0.1	65.1	0.6
1041556	<1	9	25	<0.1	67.4	0.6
1041557	<1	9	23.8	<0.1	67.8	0.5
1041558	<1	9	21.8	<0.1	69.9	0.6
1041559	<1	7	27.3	<0.1	63.7	0.4
1041560	1	10	13.5	2.4	130.3	0.8
1041561	<1	8	28.7	<0.1	59	0.4
1041562	<1	8	25	<0.1	52.6	0.5
1041563	<1	7	19	<0.1	68.7	0.5
1041564	<1	8	40.6	<0.1	71.8	0.5
1041565	<1	7	44.7	<0.1	72.3	0.4
1041566	<1	6	23.8	<0.1	70.5	0.5
1041567	1	8	19.4	<0.1	80.2	0.6
1041568	1	8	22.4	<0.1	69.5	0.7
1041569	1	8	20.7	<0.1	94.2	0.6
1041570	1	8	19.7	<0.1	84.3	0.5
1041571	1	4	16	<0.1	105.7	0.6
1041572	1	7	21.9	<0.1	87.1	0.7
1041573	<1	8	24.5	<0.1	89.2	0.6
1041574	<1	7	16.4	<0.1	81.8	0.7
1041575	1	6	16.1	<0.1	92.3	0.7
1041576	<1	6	19.1	<0.1	91.3	0.7
1041577	<1	6	17.6	<0.1	88.6	0.8
1041578	<1	7	17.3	<0.1	90.8	0.7
1041579	1	7	23.4	<0.1	85.3	0.8
1041580	<1	7	23.7	<0.1	87.2	1
1041581	<1	6	21	<0.1	85.1	0.8
1041582	2	7	20	<0.1	91.8	0.8
1041583	1	7	19.9	<0.1	91.8	0.9
1041584	1	7	29.8	<0.1	94.6	0.6
1041585	<1	7	19.8	<0.1	100	0.8
1041586	<1	7	21.1	<0.1	101.3	0.7

Taseko Property Technical Report

GC11-77				Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co
Sample #	From	To	Standards	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	PPM
			section	MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2
1041587	246	249		3	7.14	<0.005	1.9	43.2	7.6	30	0.1	13.5	9.7
1041588	249	252		3	7.48	<0.005	1.9	73.4	7.5	30	<0.1	16.1	9.5
1041589	252	255		3	8.6	<0.005	2.2	59.2	8.9	31	<0.1	17.8	10.1
1041590	255	258		3	7.07	<0.005	1.6	33.8	8.4	30	<0.1	15.5	9.2
1041591	258	261		3	7.13	<0.005	1.9	80.7	8.4	32	<0.1	18.9	9.8
1041592	261	264		3	7.67	<0.005	2.4	37.5	9.3	38	<0.1	21	11.7
1041593	264	267		3	7.25	<0.005	2.4	38	10.7	42	<0.1	20.7	10.6
1041594	267	270		3	6.71	<0.005	3.7	58.1	13.9	40	<0.1	17.8	11

GC11-77															
Sample #	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	
	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	
	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1	
1041587	559	2.17	6	12.6	<0.1	10.7	323	0.1	2.2	<0.1	55	4.34	0.03	12.9	
1041588	342	2.3	4	3.5	<0.1	10	383	<0.1	1	<0.1	70	2.38	0.04	12.1	
1041589	420	2.29	6	4.9	<0.1	12.8	328	0.1	3.2	<0.1	61	2.99	0.037	12.1	
1041590	504	2.01	6	6.3	<0.1	10.7	296	<0.1	2.5	<0.1	60	3.72	0.035	10.9	
1041591	361	2.41	6	2.5	<0.1	9.5	394	0.1	2	<0.1	75	2.33	0.045	10.5	
1041592	503	2.66	4	3.2	<0.1	8.3	411	<0.1	1.9	<0.1	82	3.24	0.045	11.7	
1041593	404	2.64	5	3.1	<0.1	8.5	442	<0.1	1.4	<0.1	89	2.86	0.049	10.6	
1041594	406	2.3	5	2.9	<0.1	9.2	369	0.2	1.6	<0.1	74	3.05	0.043	10.7	

GC11-77															
Sample #	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041587	16	1.2	740	0.196	6.52	2.129	2.59	3.2	16.9	28	0.7	12.5	2.9	0.3	
1041588	28	0.94	737	0.245	7.29	2.547	2.72	1.1	17	28	0.8	10.5	3.1	0.3	
1041589	19	0.85	762	0.219	6.81	2.411	2.74	1.6	15.4	27	0.6	10.5	3.2	0.3	
1041590	21	0.72	641	0.213	6.72	2.262	2.56	3.3	13	25	0.6	9	2.6	0.2	
1041591	22	0.68	767	0.238	7.21	2.631	2.55	2.5	13.4	25	0.8	8.8	2.7	0.2	
1041592	31	0.91	733	0.257	7.55	2.631	2.37	2.6	13.7	28	0.7	11	2.7	0.2	
1041593	26	1	738	0.278	7.62	2.711	2.37	5.3	14.1	24	0.9	9.3	3	0.2	
1041594	23	0.73	750	0.257	7.57	2.337	2.65	13.7	13.4	25	0.9	8.7	2.7	0.3	

GC11-77	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1

Sample #

1041587	<1	6	16.9	<0.1	93.5	0.7
1041588	<1	7	23.9	<0.1	92.1	0.7
1041589	<1	6	24.8	<0.1	95.6	0.7
1041590	<1	6	17.9	<0.1	92.7	0.6
1041591	1	7	17.2	<0.1	85.4	0.6
1041592	<1	8	24.3	<0.1	78	0.7
1041593	<1	9	20.4	<0.1	76.6	0.7
1041594	<1	7	20.3	<0.1	95.2	0.6

Taseko Property Technical Report

GC 11-78			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
			Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	
			MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	
Sample #	From	To	Standards	section								
1041642	15	18		3	5.42	0.023	5.7	633.8	9.8	39	<0.1	21.7
1041643	18	21		3	8.1	0.016	5	300.2	8.2	35	<0.1	21.8
1041644	21	24		3	7.81	0.01	4.5	148.4	8.3	37	<0.1	22.2
1041645	24	27		3	7.49	0.031	8.6	525	8.5	36	<0.1	22.5
1041646	27	30		3	7.14	0.024	4.4	262.9	8.2	38	<0.1	21.3
1041647	30	31.5		1.5	4.12	0.012	4.6	203.1	7	30	<0.1	21.4
1041648	31.5	33		1.5	3.52	0.011	5.4	120.1	6.5	25	<0.1	18.4
1041649	33	36		3	8.13	0.014	9	195.4	7.1	24	<0.1	20.3
1041650	36	39		3	5.63	0.014	28.8	238.5	7	19	<0.1	13.1
1041651	39	40		1	2.49	<0.005	1.9	52.6	6.2	21	<0.1	12.2
1041652	40	41		1	2.17	0.028	39.1	406	7.7	25	<0.1	17.8
1041653	41	42		1	2.54	0.009	3.3	228.6	7.3	27	<0.1	18.4
1041654	42	43		1	2.28	0.015	4.9	285.1	7.4	25	<0.1	18.8
1041655	43	45		2	4.05	<0.005	1.4	156.2	6.7	26	<0.1	19.8
1041656	45	47		2	4.81	<0.005	1.5	56.1	7	28	<0.1	18.9
1041657	47	48		1	2.31	0.006	1.8	182.2	7.3	33	<0.1	18.6
1041658	48	49.5		1.5	3.58	0.009	11.9	208.2	6.9	25	<0.1	20.9
1041659	49.5	52		2.5	3.56	0.007	4	191.2	6.6	23	<0.1	20.2
1041660	52	51	Blank	-1	0.72	<0.005	<0.1	0.6	<0.1	<1	<0.1	0.4
1041661	51	54		3	7.55	0.054	1.2	378.8	6.9	24	<0.1	21.1
1041662	54	57		3	7.9	0.022	1.7	303.8	6.3	27	<0.1	21.2
1041663	57	60		3	6.62	0.007	20.5	187.8	7.3	29	<0.1	19.8
1041664	60	63		3	8.88	<0.005	1.5	21.7	7	27	<0.1	19.1
1041665	63	66		3	7.73	0.018	2	262.1	8.1	29	<0.1	19.9
1041666	66	68		2	6.07	0.021	46.5	750.1	7.7	34	0.2	22.7
1041667	68	71		3	7.23	0.016	1.4	137.3	7.2	31	<0.1	21.1
1041668	71	73		2	5.79	0.024	2.1	468.4	7.9	35	<0.1	23.2
1041669	73	75		2	4.49	0.016	3.9	195.5	5.4	32	<0.1	20.6
1041670	75	76		1	2.75	0.043	17.9	1339.1	6.3	29	0.1	20.1
1041671	76	78		2	4.58	0.024	2.9	537.3	13.7	44	<0.1	21.6
1041672	78	80		2	5.82	0.054	13	954.8	7.3	28	0.1	20
1041673	80	82		2	5.38	0.018	2.4	206.9	6.7	34	<0.1	23.1
1041674	82	84		2	5.1	0.063	1.8	645.3	6.6	27	<0.1	22.9
1041675	84	87		3	8.52	0.009	0.9	138.1	5.9	31	<0.1	24.9
1041676	87	90		3	9.72	0.023	1.3	329.4	8.2	33	<0.1	22
1041677	90	92		2	5.63	0.012	1	277.7	5.9	28	<0.1	22.9
1041678	92	93		1	2.75	0.006	1.3	49.4	5.5	27	<0.1	23.1
1041679	93	94		1	2.75	0.007	1	86	5.2	28	<0.1	22.6
1041680	94	94	C m-2	0	0.1	1.514	289.2	9662.2	89.4	135	4.8	34.2
1041681	94	95		1	2.93	0.038	3.8	1416	5.5	31	0.4	22
1041682	95	96		1	2.69	0.014	1.3	330.9	5.2	27	<0.1	22.1
1041683	96	99		3	8.55	0.006	0.8	104	7.1	44	<0.1	23.1
1041684	99	102		3	8.51	0.005	0.9	79	5.4	34	<0.1	23.8
1041685	102	104		2	5.89	<0.005	1	41.4	7.1	35	<0.1	23.3
1041686	104	107		3	7.86	0.012	1.2	230.7	5.9	31	<0.1	20.4

Taseko Property Technical Report

GC11-78	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001
Sample #														
1041642	10.9	302	2.49	8	4.2	<0.1	9.1	368	<0.1	0.3	0.1	100	2.01	0.046
1041643	11.5	317	2.51	9	2.4	<0.1	7.6	390	<0.1	0.3	<0.1	103	2.19	0.048
1041644	11.7	297	2.57	9	2.5	<0.1	7.8	380	<0.1	0.4	<0.1	107	2.09	0.051
1041645	10.8	266	2.39	9	4	<0.1	6.8	349	0.1	0.4	0.1	105	1.61	0.051
1041646	11.1	308	2.47	8	3.5	<0.1	6.2	379	<0.1	0.4	<0.1	102	1.92	0.047
1041647	10	203	2.08	9	4.1	<0.1	12.8	327	<0.1	0.4	<0.1	101	1.55	0.046
1041648	8.9	165	1.53	10	2.5	<0.1	11.2	414	<0.1	0.3	<0.1	80	1.65	0.044
1041649	8.7	158	1.6	13	1.9	<0.1	9	402	<0.1	0.2	<0.1	73	1.78	0.042
1041650	6	105	1.1	10	4.2	<0.1	14.2	329	<0.1	0.3	<0.1	52	1.1	0.033
1041651	6	131	1.49	5	2.6	<0.1	11.5	341	<0.1	0.2	<0.1	55	1.11	0.032
1041652	8.5	173	1.78	8	2.2	<0.1	9.9	399	<0.1	0.2	<0.1	77	1.82	0.046
1041653	9.2	202	2.07	6	1.9	<0.1	8.8	394	<0.1	0.2	<0.1	82	2.08	0.039
1041654	8.7	171	1.81	12	2.7	<0.1	10.1	408	<0.1	0.2	<0.1	89	1.82	0.055
1041655	9	200	2.15	8	1.6	<0.1	8	391	<0.1	0.2	<0.1	85	2.12	0.046
1041656	9.4	208	2.1	6	1.6	<0.1	9.4	402	<0.1	0.2	<0.1	89	2.18	0.044
1041657	9.1	205	1.94	5	1.5	<0.1	8.6	369	<0.1	0.1	<0.1	76	2.08	0.043
1041658	9.4	185	1.89	4	1.5	<0.1	8.5	381	<0.1	0.2	<0.1	85	2.17	0.042
1041659	9.5	184	1.82	6	1.7	<0.1	9.1	398	<0.1	0.2	<0.1	79	2.1	0.046
1041660	<0.2	26	<0.01	7	1.3	<0.1	<0.1	4135	<0.1	<0.1	<0.1	<1	34.71	0.003
1041661	9.1	171	1.84	5	1.8	<0.1	9	368	<0.1	0.2	<0.1	83	2.27	0.041
1041662	9.4	188	1.9	8	2.3	<0.1	10.3	397	<0.1	0.2	<0.1	89	2.06	0.043
1041663	9.5	209	1.96	9	2.3	<0.1	9.4	416	<0.1	0.3	<0.1	85	1.91	0.049
1041664	9.2	239	2.07	7	1.9	<0.1	9	401	<0.1	0.2	<0.1	78	2.1	0.041
1041665	9.5	202	1.93	7	4.4	<0.1	9.2	411	<0.1	0.3	<0.1	80	1.93	0.043
1041666	10.9	246	2.46	8	1.7	<0.1	8	433	0.1	0.3	0.1	92	2.15	0.051
1041667	10.4	215	2.21	7	1.9	<0.1	8.1	426	<0.1	0.4	<0.1	88	2.26	0.054
1041668	11.5	244	2.65	10	2.1	<0.1	7.7	403	<0.1	0.4	<0.1	100	2.29	0.107
1041669	10	224	2.39	8	1.9	<0.1	8.2	356	<0.1	0.4	<0.1	96	2.04	0.05
1041670	9.7	185	2.17	10	4.5	0.1	11.7	309	0.1	0.5	0.1	85	1.21	0.047
1041671	9.9	182	2.25	12	2.1	0.1	9.8	337	<0.1	0.6	<0.1	99	1.35	0.049
1041672	9.5	208	2.14	7	2.4	<0.1	8.9	374	<0.1	0.4	0.1	88	2.09	0.046
1041673	10.7	253	2.38	7	2	<0.1	7.6	343	<0.1	0.5	<0.1	96	2.63	0.046
1041674	10.6	222	2.38	8	1.9	<0.1	8.2	399	<0.1	0.4	<0.1	97	2.13	0.045
1041675	11.9	262	3.06	7	1.5	<0.1	7.1	440	0.2	0.4	0.2	107	2.43	0.052
1041676	10.9	338	2.84	6	1.5	<0.1	7.6	418	<0.1	0.3	<0.1	92	2.56	0.05
1041677	11.5	308	2.78	6	2.4	<0.1	6.5	447	0.1	0.3	<0.1	97	2.63	0.057
1041678	10.9	332	2.94	7	2.5	<0.1	7.2	520	<0.1	0.2	<0.1	99	2.81	0.055
1041679	9.9	301	2.67	5	3.5	<0.1	6.1	457	<0.1	0.3	<0.1	91	3.02	0.05
1041680	20.7	446	5.07	29	6.3	1.4	11.6	225	2.8	20.6	3.6	98	1.67	0.081
1041681	10.5	281	2.69	6	1.7	<0.1	6.3	450	0.1	0.3	<0.1	91	2.45	0.054
1041682	10.5	261	2.53	6	1.9	<0.1	7.6	413	0.1	0.3	<0.1	88	2.33	0.052
1041683	10.3	367	2.89	5	1.7	<0.1	6.4	418	<0.1	0.4	<0.1	101	2.79	0.054
1041684	11.1	335	3.11	7	1.7	<0.1	7.5	427	<0.1	0.3	<0.1	109	2.64	0.055
1041685	10.7	413	3.04	6	2.3	<0.1	7.1	451	<0.1	0.3	<0.1	99	2.84	0.055
1041686	9.6	281	2.6	11	1.8	<0.1	6.9	335	<0.1	0.4	<0.1	95	2.36	0.057

Taseko Property Technical Report

GC11-78	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #															
1041642	10.6	37	1.27	622	0.298	7.21	2.682	2.39	0.9	7.5	24	1.5	13	3.2	0.2
1041643	9.1	39	1.34	600	0.313	7.26	2.683	2.42	0.6	6.9	21	1.5	12.5	3	0.2
1041644	9.5	41	1.29	641	0.334	7.37	2.726	2.48	0.8	7.7	22	1.6	12.4	3.2	0.2
1041645	9.2	43	1.34	545	0.338	7.44	2.901	1.93	1.7	7.7	20	1.6	10	3.4	0.2
1041646	8.2	42	1.32	630	0.323	7.48	2.804	2.33	1.2	8.1	19	1.5	10.7	3	0.2
1041647	7.7	38	1.35	395	0.325	7.4	3.185	1.69	0.6	9.3	17	1.5	9.6	3.7	0.3
1041648	5.7	30	1.14	355	0.299	7.24	3.292	1.39	0.4	12	11	1	6.5	3.2	0.3
1041649	5.1	32	1.17	304	0.312	6.7	3.157	1.31	0.4	11.9	10	0.9	5.6	3.2	0.3
1041650	6	16	0.74	338	0.215	6.85	3.312	1.44	0.7	13.2	10	0.7	4.8	2.9	0.3
1041651	6.4	17	0.67	686	0.199	6.64	2.809	2.49	0.4	12.8	12	0.6	5.7	3.3	0.3
1041652	5.8	27	1.01	613	0.272	6.73	2.861	2.09	0.6	13.1	12	1	8.4	3.5	0.3
1041653	5.9	33	1.12	536	0.282	6.95	2.861	1.81	0.4	12	13	1	9.1	3.5	0.3
1041654	6.1	33	1.13	483	0.307	7.13	2.977	1.69	0.9	12.5	13	1.2	8.5	3.6	0.3
1041655	5.2	32	1.14	536	0.29	6.91	2.901	1.81	0.3	11.3	12	1	8.5	3.1	0.3
1041656	6	31	1.11	525	0.274	7.01	2.885	1.67	0.3	11.4	14	0.9	9.4	3.4	0.3
1041657	5.5	31	1.06	489	0.271	6.7	2.834	1.74	0.3	10.9	13	1	8.3	3.3	0.3
1041658	5.6	33	1.17	465	0.296	6.85	2.848	1.7	0.3	11.5	12	1	8.4	3.4	0.3
1041659	5.7	33	1.2	423	0.311	6.78	3.019	1.51	0.3	11.4	12	1.1	7.4	3.6	0.3
1041660	0.3	<1	1.72	5	<0.001	0.03	0.003	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1
1041661	5.7	30	1.12	394	0.303	6.87	3.033	1.42	0.4	10.2	12	1.2	7	3.1	0.3
1041662	6.2	29	1.19	344	0.306	7.06	3.083	1.31	0.8	10.1	13	1.4	7.8	3.1	0.3
1041663	6.3	30	1.14	458	0.3	7.07	3.035	1.69	1.6	11.1	14	1.3	10.4	3.2	0.3
1041664	7.1	31	1.22	454	0.298	7.11	3.02	1.46	0.4	9.9	18	1.7	13.7	3.2	0.3
1041665	8.5	33	1.19	383	0.309	7.37	3.123	1.43	0.8	10	19	1.9	16.2	3.3	0.3
1041666	7.1	41	1.36	499	0.323	7.31	3.102	1.74	0.8	9.3	19	1.6	10.7	3.5	0.3
1041667	6	44	1.27	403	0.331	7.61	3.251	1.3	0.7	8.4	17	1.9	11.9	3.7	0.3
1041668	7.2	42	1.37	498	0.324	7.09	2.957	1.66	0.7	8	21	1.8	15.4	3.8	0.3
1041669	6.5	38	1.05	709	0.307	7.28	2.801	2.02	1.1	7.5	17	1.3	10.6	3.3	0.3
1041670	8.1	29	1.07	432	0.284	7.51	2.921	1.73	1	6.6	18	1.2	10.3	3	0.2
1041671	10.6	35	1.08	451	0.318	7.51	2.865	1.71	1.3	6.9	24	1.6	10.2	3.4	0.3
1041672	6.8	30	1.22	457	0.299	7.02	2.865	1.62	0.8	6.6	15	1.3	9.9	3.2	0.3
1041673	9.5	33	1.21	457	0.304	7.09	2.83	1.95	2	5.8	23	1.4	10.5	3.1	0.3
1041674	7.6	35	1.31	493	0.311	7.08	2.927	1.8	0.6	5.9	18	1.3	9.1	3.2	0.2
1041675	8.8	40	1.46	415	0.408	6.91	2.837	1.59	0.4	8.1	23	1.8	13.9	3.4	0.3
1041676	8.9	36	1.4	542	0.366	6.7	2.773	1.88	0.4	8.2	22	1.2	13.5	3.1	0.2
1041677	7	38	1.49	562	0.396	6.91	2.754	1.95	2	8.4	19	1.5	13	3.2	0.2
1041678	8.3	38	1.49	624	0.396	7.6	3.025	2.15	0.4	8.4	23	1.4	16	3.3	0.2
1041679	6.8	34	1.42	486	0.368	7.32	2.878	1.7	2.1	7	19	1.2	14	2.9	0.2
1041680	31.1	109	1	98	0.242	7.25	0.868	4.03	17.5	23.4	60	3.8	15	3.3	0.2
1041681	7.6	36	1.43	530	0.375	7.49	2.915	2.01	71.7	6.2	19	1.5	12.6	3	0.2
1041682	6.9	35	1.45	397	0.362	7.44	3.013	1.63	1.6	6.2	18	1.3	11.8	3.1	0.2
1041683	7.1	35	1.42	497	0.371	7.19	2.972	1.69	0.8	7.1	20	1.6	14.7	2.9	0.2
1041684	7.5	43	1.54	479	0.394	7.18	3.054	1.73	0.5	7.8	22	1.6	17.1	3.4	0.2
1041685	8.2	41	1.47	605	0.383	6.87	2.901	2.08	0.4	8	22	1.5	15.2	3.1	0.2
1041686	8.3	38	1.27	387	0.366	7.55	3.063	1.41	1.3	6.6	24	2.1	15.8	3.1	0.2

Taseko Property Technical Report

GC11-78	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041642	1	10	20	<0.1	80.9	0.3
1041643	<1	11	21.9	<0.1	86.9	0.3
1041644	1	10	23.3	<0.1	81.9	0.3
1041645	<1	10	26	<0.1	82.8	0.3
1041646	<1	10	22.6	<0.1	86.4	0.3
1041647	1	10	25.8	<0.1	83	0.5
1041648	1	8	25	<0.1	73.6	0.5
1041649	1	8	26.2	<0.1	67.8	0.5
1041650	<1	5	19	<0.1	77	0.5
1041651	<1	5	16.8	<0.1	82	0.4
1041652	<1	8	21.7	<0.1	71.1	0.5
1041653	<1	8	20.6	<0.1	65.4	0.6
1041654	1	8	22.9	<0.1	75.1	0.5
1041655	<1	8	19.6	<0.1	63.2	0.4
1041656	<1	8	19.1	<0.1	63.6	0.5
1041657	1	8	17.1	<0.1	62.7	0.5
1041658	1	9	20	<0.1	64.9	0.5
1041659	<1	9	22.4	<0.1	70.3	0.5
1041660	<1	<1	0.2	<0.1	<0.1	<0.1
1041661	1	8	22.9	<0.1	61	0.5
1041662	1	8	25.7	<0.1	63.1	0.4
1041663	<1	8	25.9	<0.1	68.3	0.5
1041664	<1	9	21.6	<0.1	57	0.5
1041665	1	9	24.7	<0.1	68.9	0.4
1041666	1	10	24.8	<0.1	68.4	0.5
1041667	<1	10	24.1	<0.1	46.3	0.4
1041668	1	9	26.8	<0.1	51.3	0.4
1041669	<1	9	26.5	<0.1	91.7	0.4
1041670	<1	9	26.8	0.1	85.9	0.3
1041671	1	9	26.1	<0.1	84.2	0.3
1041672	<1	9	29.1	<0.1	64.1	0.3
1041673	1	9	30.1	<0.1	80.2	0.3
1041674	<1	9	27	<0.1	70.1	0.3
1041675	1	10	31	<0.1	72.3	0.3
1041676	1	9	31.3	<0.1	62.5	0.4
1041677	1	9	30	<0.1	62	0.4
1041678	<1	10	28.3	<0.1	64.6	0.4
1041679	1	10	33.4	<0.1	54.7	0.3
1041680	1	10	16.9	2.5	156	0.7
1041681	1	9	34.4	0.1	69.7	0.3
1041682	<1	10	34.3	<0.1	63.1	0.3
1041683	1	9	30.6	<0.1	56.3	0.3
1041684	<1	11	36.8	<0.1	53.8	0.4
1041685	1	10	28.4	<0.1	59.9	0.4
1041686	1	10	34.8	<0.1	65.4	0.3

Taseko Property Technical Report

GC 11-78			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni
Sample #	From	To	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM
			MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1
			Standards	section							
1041687	107	109	2	5.63	0.009	1.2	82	5.6	27	<0.1	19.7
1041688	109	111	2	5.86	0.006	0.9	78	6	26	<0.1	19.5
1041689	111	114	3	7.81	0.032	11.9	643.2	7.3	30	<0.1	18.6
1041690	114	117	3	9.09	0.011	27.1	158.3	6.6	30	<0.1	17.9
1041691	117	120	3	8.95	0.026	0.8	271.4	6.4	26	0.1	14.6
1041692	120	123	3	7.58	0.031	1.8	670.4	6	34	<0.1	21.5
1041693	123	126	3	8.29	0.007	5.3	115.2	6.2	34	<0.1	21.3
1041694	126	129	3	8	0.017	1.1	189.8	6.4	33	<0.1	20.7
1041695	129	132	3	8.36	0.008	1	64.7	6.1	29	<0.1	19.2
1041696	132	135	3	7.96	0.007	1.3	77	6.1	29	<0.1	20.3
1041697	135	138	3	8.71	0.008	1.1	76.1	5.8	29	<0.1	22.3
1041698	138	141	3	8.17	0.008	1.4	104.8	5.6	30	<0.1	20.1
1041699	141	142	1	2.74	0.006	1.1	61.4	6.3	28	<0.1	22.2
1041700	141	142	1	2.75	<0.005	0.9	57.1	6.5	27	<0.1	21.4
1041701	142	144	2	5.43	0.006	1	81.5	7.3	30	<0.1	21.1
1041702	144	146	2	5.4	<0.005	1	81	6.1	33	<0.1	20.8
1041703	146	148	2	6.03	0.011	0.9	70.7	6.8	33	<0.1	23.4
1041704	148	149	1	2.67	0.01	3.2	141.7	7.4	29	<0.1	21.1
1041705	149	150	1	2.86	0.007	0.9	65.5	7.6	37	<0.1	22.7
1041706	150	153	3	7.97	0.012	0.8	77.3	9.6	40	<0.1	23.9
1041707	153	156	3	8.96	0.007	1.3	95.7	8.1	39	<0.1	20.2
1041708	156	159	3	8.09	0.008	1.1	63.5	9.4	41	<0.1	20.3
1041709	159	162	3	8.05	0.008	1.2	76	7.6	35	<0.1	17.1
1041710	162	163	1	2.8	0.037	1.7	442.3	10.6	52	0.1	23.1
1041711	163	164	1	2.29	0.04	8.8	1544.4	8.6	57	0.3	21.2
1041712	164	165	1	2.52	0.029	5.8	710	9.1	44	0.2	20.1
1041713	165	166	1	2.55	0.019	4	289.7	6.4	36	0.2	17.4
1041714	166	168	2	5.66	0.009	1.5	71.9	10.4	42	<0.1	21.9
1041715	168	170	2	5.96	0.008	2.5	88.6	8.9	43	<0.1	18.9
1041716	170	171.75	1.75	6.27	0.018	6.9	362.1	8.7	39	0.3	16.7
1041717	171.75	174.6	2.85	6.64	<0.005	0.4	26.9	8.9	28	<0.1	17.6
1041718	174.6	177.3	2.7	6.99	<0.005	0.3	41.2	8.1	38	<0.1	17.6
1041719	177.3	179	1.7	4.58	0.01	3.5	320.4	16.5	40	<0.1	18.6
1041720	179	179	0	0.56	<0.005	<0.1	2.1	1.7	1	<0.1	0.9
1041721	179	182	3	8.32	0.01	1.1	169.9	6.6	34	0.1	20.7
1041722	182	184.1	2.1	6.07	0.014	2.8	228.9	5.8	27	0.1	16.3
1041723	184.1	184.75	0.65	1.88	0.039	11.1	433.3	7.9	15	0.5	4.7
1041724	184.75	186	1.25	2.87	0.049	3.3	407.3	10.9	47	0.3	34.6
1041725	186	189	3	8.4	0.16	8.3	681.8	6.6	25	0.3	15.9
1041726	189	192	3	7.63	0.033	2.8	351.5	6.5	23	0.1	13.6

EOH

Taseko Property Technical Report

GC11-78	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001
Sample #														
1041687	9.1	309	2.29	7	2.1	<0.1	8.3	363	<0.1	0.3	<0.1	79	3.45	0.136
1041688	8.9	274	2.41	6	2.8	<0.1	10.1	409	<0.1	0.3	<0.1	87	2.65	0.056
1041689	9.6	266	2.18	5	2.7	<0.1	10.4	350	<0.1	0.5	<0.1	74	2.57	0.041
1041690	9	290	2.5	8	2.7	<0.1	9.5	333	<0.1	0.5	<0.1	79	2.32	0.045
1041691	7.5	212	1.8	6	2.3	<0.1	9.1	351	<0.1	0.3	<0.1	64	2.02	0.035
1041692	10.2	247	2.28	11	3.2	0.2	7.8	309	<0.1	0.5	<0.1	86	2.11	0.05
1041693	10.5	272	2.53	7	2.4	<0.1	8	375	<0.1	0.3	<0.1	89	2.43	0.053
1041694	10.3	298	2.78	12	2.1	<0.1	8.8	342	<0.1	0.5	<0.1	87	2.2	0.046
1041695	9.3	255	2.59	10	1.7	<0.1	8.7	401	<0.1	0.3	<0.1	89	1.9	0.046
1041696	9.6	296	2.65	8	1.7	<0.1	8	392	<0.1	0.4	<0.1	92	2.28	0.047
1041697	10.8	293	2.79	7	2.4	<0.1	8.1	402	<0.1	0.5	<0.1	94	2.59	0.05
1041698	10	287	2.43	11	3.6	<0.1	8.2	308	0.1	1.9	<0.1	85	2.71	0.049
1041699	10.3	257	2.58	6	1.9	<0.1	6.9	356	0.1	0.5	<0.1	87	2.4	0.05
1041700	10	256	2.62	5	1.9	<0.1	7.3	356	<0.1	0.4	<0.1	90	2.41	0.05
1041701	10	311	2.62	7	2.3	<0.1	7.5	402	0.1	0.3	<0.1	87	2.49	0.045
1041702	10.5	364	2.78	8	2.5	<0.1	7.7	441	<0.1	0.3	<0.1	89	2.69	0.052
1041703	11.6	364	3.07	5	2	<0.1	8.4	413	<0.1	0.3	<0.1	97	2.69	0.053
1041704	9.7	301	2.66	6	3.4	<0.1	7.3	448	<0.1	0.5	<0.1	90	2.88	0.061
1041705	11.4	426	3.05	4	2.5	<0.1	9.2	404	0.1	0.4	<0.1	90	2.71	0.055
1041706	11.7	404	3.13	4	2.4	<0.1	8.2	401	<0.1	0.9	<0.1	95	2.76	0.051
1041707	10.9	369	2.68	5	2.6	<0.1	8.7	364	0.1	1	<0.1	86	2.59	0.049
1041708	10.5	374	2.83	8	2.4	<0.1	9.3	355	0.2	2.2	<0.1	91	1.96	0.05
1041709	8.7	378	2.62	17	1.7	<0.1	8.2	256	0.7	5.2	<0.1	78	2.66	0.046
1041710	12.7	310	2.66	16	3.7	<0.1	11	261	0.5	4.1	0.4	82	1.41	0.078
1041711	10.4	208	2.45	41	3.1	<0.1	8	228	1.2	9.7	0.4	80	1.14	0.216
1041712	9.6	210	2.27	31	2.3	<0.1	8.5	303	0.8	8.2	0.3	81	1.31	0.094
1041713	8.9	372	2.06	31	1.6	<0.1	7.7	200	1	7.2	0.2	76	1.98	0.042
1041714	10.2	311	2.62	16	2	<0.1	8.3	249	0.3	2.3	0.1	88	1.8	0.048
1041715	10.2	387	2.73	14	2.1	<0.1	9.5	331	0.4	2.5	0.2	91	2.53	0.05
1041716	9.1	279	2.34	24	2.6	<0.1	8.3	337	0.2	3	0.2	77	1.74	0.043
1041717	7.9	402	2.09	13	0.7	<0.1	1.7	206	0.2	1.7	0.1	65	2.51	0.054
1041718	7.6	372	2.05	14	0.9	<0.1	2.1	279	0.1	1.7	0.1	65	2.38	0.054
1041719	10.1	304	2.12	12	8	<0.1	8.1	348	0.3	2.4	0.2	66	2.53	0.036
1041720	<0.2	29	0.06	9	1.1	<0.1	<0.1	4697	<0.1	<0.1	<0.1	2	35.67	0.004
1041721	9.7	268	2.54	8	1.6	<0.1	8.7	269	<0.1	1.6	<0.1	84	2.6	0.045
1041722	6.9	182	2.16	4	1.1	<0.1	7.7	332	<0.1	0.8	0.1	69	1.7	0.035
1041723	3.1	134	0.72	16	6	<0.1	22.8	160	1.8	9.5	<0.1	14	0.9	0.007
1041724	15.3	528	3.62	8	9.7	<0.1	5.9	247	0.6	3.9	0.2	98	3.38	0.086
1041725	9.5	185	1.77	6	2.5	<0.1	11.1	268	0.2	1.6	0.2	60	1.5	0.029
1041726	6.9	156	1.91	6	2.7	<0.1	15.2	283	0.1	0.9	<0.1	58	1.15	0.03

Taseko Property Technical Report

GC11-78	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #															
1041687	9.2	35	1.33	253	0.354	7.25	3.205	1.01	0.7	5.7	28	2	24.4	3.1	0.2
1041688	7.3	32	1.35	429	0.334	7.13	3.061	1.62	0.3	7.8	21	1.5	18.1	3	0.2
1041689	6.5	30	1.13	321	0.328	7.08	3.108	1.5	1.9	7.6	18	1.5	14.4	2.9	0.2
1041690	7.1	30	1.09	508	0.319	7.1	2.695	2.42	0.8	9	19	1.1	13.9	3.1	0.2
1041691	6.9	24	1	434	0.296	7.08	3.08	1.91	2.1	6.8	19	1.2	12.7	2.9	0.2
1041692	10.8	35	1.36	383	0.366	7.27	2.936	1.62	1.2	5.6	28	1.6	18.4	3.4	0.2
1041693	7.2	36	1.38	452	0.363	7.15	2.908	1.81	0.6	7.8	20	1.6	16.7	3.2	0.2
1041694	8.1	36	1.22	549	0.358	7.35	2.889	2.48	0.8	7.1	22	1.3	14.5	3.3	0.2
1041695	6.8	35	1.26	566	0.352	7.07	2.907	2.44	0.4	6.3	20	1.6	15.1	3.3	0.2
1041696	7.6	37	1.26	602	0.356	7.16	2.941	2.36	0.5	6.2	22	1.5	15.8	3.3	0.2
1041697	7.9	38	1.39	617	0.364	7.3	2.81	2.35	0.3	6.8	24	1.5	16.2	3.2	0.2
1041698	6.5	36	1.12	750	0.356	7.2	2.353	2.35	1.9	5.9	19	1.1	13.6	3.1	0.2
1041699	6.9	37	1.28	458	0.355	7.12	2.686	2.15	0.6	6.3	20	1.4	14.4	3.1	0.2
1041700	7.2	37	1.31	516	0.355	7.31	2.939	2.23	0.3	6.4	22	1.4	15.1	3.2	0.2
1041701	7.3	34	1.32	542	0.356	7.16	2.832	2.2	0.3	6.4	21	1.4	15.1	3	0.2
1041702	8.4	37	1.37	627	0.357	7.16	2.83	2.49	0.4	7	24	1.2	15.8	3	0.2
1041703	9.1	40	1.4	683	0.382	7.55	2.886	2.57	0.2	6.8	26	1.7	16.5	3.2	0.2
1041704	7.6	35	1.4	414	0.332	7.17	2.936	1.79	0.3	6	23	1.3	16.7	2.9	0.2
1041705	9.3	37	1.41	691	0.365	7.67	2.788	2.7	0.3	6.3	25	1.3	15.8	3.3	0.2
1041706	9.1	41	1.3	638	0.374	7.05	2.814	2.58	0.5	6.5	25	1.3	16.8	3.3	0.2
1041707	9.1	34	1.32	553	0.328	7.24	2.753	2.24	0.5	5.9	23	1.1	14.8	3	0.2
1041708	8.9	39	1.12	561	0.354	7.16	2.696	2.54	1.1	6	25	1.1	15.1	3.1	0.3
1041709	8.2	34	0.99	1013	0.301	7.24	1.979	2.44	2.3	5	23	0.8	12.4	2.7	0.2
1041710	43	34	1.21	991	0.255	7.75	2.934	2.43	2.6	5.9	94	1.2	17	3.2	0.3
1041711	45.7	35	1.09	391	0.291	7.55	3.068	1.85	1.9	6	111	1.6	24.6	3.3	0.3
1041712	20.3	37	0.78	502	0.295	7.84	2.963	1.61	1.4	6.7	51	1.7	15.9	3.4	0.3
1041713	8.8	34	0.95	920	0.268	7.76	2.615	2.14	2.2	5.7	23	1.4	8.6	3	0.3
1041714	11.5	34	0.77	640	0.258	7.56	2.608	2.22	2.5	6.1	30	1.4	10.5	2.8	0.2
1041715	11.2	36	0.93	696	0.28	7.5	2.59	2.16	1.6	7.2	29	1.1	12.9	3	0.3
1041716	12.6	29	0.72	477	0.282	8.01	2.821	2.27	1	15.7	30	1.3	11.2	3.4	0.3
1041717	9	8	1.03	856	0.22	7.97	2.8	2.49	0.6	39.4	22	0.7	5.2	2.4	0.2
1041718	8.9	8	0.97	1359	0.228	8.07	2.925	2.43	0.5	41.6	22	0.6	5.2	2.6	0.2
1041719	16.8	29	0.96	937	0.274	7.41	2.897	1.89	1.7	8.7	40	1.7	13.2	3.8	0.3
1041720	0.9	<1	1.51	16	0.003	0.13	0.038	0.04	<0.1	0.8	2	<0.1	0.7	0.1	<0.1
1041721	8.9	31	1.12	524	0.263	7.26	2.901	2.18	1.9	7.5	24	1.4	11	3.1	0.2
1041722	5.6	20	0.85	371	0.217	7.13	3.056	1.78	1.5	7	14	1.2	7.2	2.4	0.2
1041723	2.8	3	0.41	415	0.069	5.92	2.884	1.74	1.6	11.9	7	1.1	5.9	1.2	0.2
1041724	10	52	1.89	1057	0.297	6.86	2.328	1.56	3.9	9.9	28	1.8	11.9	3	0.2
1041725	5.2	19	0.87	359	0.214	7.23	2.935	1.84	2.6	15.1	13	1	5.7	2.6	0.2
1041726	6.4	16	0.76	865	0.196	7.14	2.658	2.22	1.9	18.2	14	0.8	4.2	2.4	0.3

GC11-78	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041687	1	9	28.7	<0.1	46.1	0.3
1041688	<1	9	26.2	<0.1	52.5	0.4
1041689	1	9	31.2	<0.1	56.2	0.4
1041690	<1	8	25.6	<0.1	71.2	0.4
1041691	1	7	26.1	<0.1	61.2	0.3
1041692	2	10	39.6	<0.1	62.2	0.3
1041693	2	10	36.1	<0.1	65	0.3
1041694	1	8	39.7	<0.1	75.5	0.3
1041695	<1	9	36.6	<0.1	67.6	0.3
1041696	1	9	38.8	<0.1	66.4	0.3
1041697	1	9	32.2	<0.1	65	0.4
1041698	1	9	35.3	<0.1	77.2	0.3
1041699	<1	9	35.7	<0.1	63.5	0.3
1041700	<1	9	33.8	<0.1	62	0.3
1041701	1	9	44.5	<0.1	58.4	0.3
1041702	1	10	41.3	<0.1	59.9	0.3
1041703	1	10	33.2	<0.1	66.4	0.4
1041704	<1	9	41.8	<0.1	52.5	0.3
1041705	<1	10	30.3	<0.1	67.2	0.3
1041706	1	10	43.2	<0.1	70.6	0.3
1041707	1	9	41.1	<0.1	63.4	0.3
1041708	<1	10	51.3	<0.1	79.9	0.4
1041709	1	9	126.7	<0.1	71.1	0.3
1041710	<1	9	66	<0.1	123.7	0.4
1041711	<1	9	35.4	0.1	114.3	0.3
1041712	1	8	43.4	<0.1	91.1	0.3
1041713	<1	9	28.5	<0.1	125.1	0.3
1041714	<1	10	41.3	<0.1	99.8	0.3
1041715	1	10	30.5	<0.1	97	0.4
1041716	<1	8	27.1	<0.1	109.1	0.5
1041717	1	6	22.4	<0.1	127.4	1
1041718	1	6	20	<0.1	128.1	1.2
1041719	1	8	21.7	<0.1	100.8	0.3
1041720	<1	<1	0.5	<0.1	2.6	<0.1
1041721	<1	10	25.8	<0.1	101.5	0.4
1041722	<1	7	25.3	<0.1	89.9	0.4
1041723	<1	1	9.3	<0.1	86.3	0.6
1041724	1	10	30.4	<0.1	90.5	0.5
1041725	<1	6	18	0.1	95.7	0.7
1041726	<1	5	20.7	<0.1	91.1	0.7

Taseko Property Technical Report

GC 11-79			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni
Sample #	From	To	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM
			MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1
			Standards	section							
1041727	15	17	2	3.27	0.027	4.8	338.1	7.8	33	0.4	22.7
1041728	17	19	2	5.4	0.024	3.6	459.9	7.4	33	0.2	25.3
1041729	19	21	2	4.55	0.048	5.1	752	7	29	0.4	21.1
1041730	21	22	1	2.23	0.28	3.4	851.1	7.2	31	0.5	23.4
1041731	22	24	2	4.94	0.08	2.5	755.2	6.4	30	0.3	23.4
1041732	24	25	1	2.2	0.052	15	1163	6.2	26	0.5	26.9
1041733	25	27	2	4.57	0.08	19.4	1363.1	6.6	30	0.5	25.2
1041734	27	29	2	4.65	0.052	12.4	1202.5	6.2	31	0.5	28.3
1041735	29	30	1	2.92	0.032	9.1	815.5	10.9	42	0.4	27
1041736	30	32	2	4.98	0.03	2.7	462.8	22.6	104	0.2	27.3
1041737	32	34	2	5.46	0.067	4	1454.1	7.6	34	0.6	28.7
1041738	34	36	2	4.85	0.015	3.9	268.8	8	42	0.1	26.5
1041739	36	38	2	5.04	0.012	3.7	106.6	8.9	47	<0.1	26.2
1041740	38	38	0	0.09	1.447	294.6	9864.4	84.4	131	5.2	34.8
1041741	38	39.7	1.7	4.93	0.01	4.5	133.1	8.7	41	<0.1	25
1041742	39.7	42	2.3	5.85	0.023	5.1	486.1	6.6	32	0.3	26.1
1041743	42	45	3	7.38	0.03	1.2	501.1	6.5	29	0.2	26.2
1041744	45	46	1	2.91	0.029	1.1	635.8	6.1	32	0.3	27.2
1041745	46	48	2	4.05	0.019	9.9	406.5	4.9	25	0.4	20
1041746	48	50	2	5.13	0.012	6.3	412.9	5.6	22	0.2	20.8
1041747	50	51	1	2.53	0.023	33.7	751.7	7.7	24	0.4	20.4
1041748	51	52	1	2.23	0.02	14.8	482.5	5.5	23	0.2	19.7
1041749	52	53	1	3.11	0.069	23.5	1260.5	6.2	24	0.6	20.4
1041750	53	55	2	4.38	0.02	84	555.9	5.7	25	0.3	20.1
1041751	55	57	2	3.57	0.034	4	606.9	6.6	22	0.2	22.4
1041752	57	58	1	3.08	0.025	12.4	712.6	6.5	25	0.3	21.5
1041753	58	59	1	3.97	0.039	22.2	679.6	7.6	23	0.3	21.7
1041754	59	60	1	2.28	0.016	139.1	391.8	5.7	29	0.2	22.8
1041755	60	61	1	2.88	0.009	2.4	407.6	6	29	0.2	22.4
1041756	61	63	2	4.73	0.016	11.5	626.6	5.7	27	0.3	20.6
1041757	63	66	3	8.2	0.028	3.1	674.1	6.3	26	0.2	23.1
1041758	66	69	3	6.84	0.022	2.1	589.1	6.2	28	0.2	21.7
1041759	69	70	1	3.05	0.012	1	84.7	5.9	26	<0.1	21.7
1041760	69	70	1	2.6	0.009	0.8	179.3	5.4	30	<0.1	19.6
1041761	70	71	1	2.61	0.015	13.2	97.3	6.6	29	<0.1	14.9
1041762	71	72	1	2.32	<0.005	23.2	13.4	5.3	21	<0.1	10.8
1041763	72	75	3	7.25	0.008	12.7	52	6.6	26	<0.1	19.5
1041764	75	76	1	2.63	0.033	9.6	36.2	7.2	24	0.1	16.6
1041765	76	78	2	5.21	0.055	0.8	757.5	7.5	27	0.3	21.2
1041766	78	80	2	5.74	0.025	0.8	354.6	7.1	27	0.2	20.7
1041767	80	81	1	2.66	0.008	1.1	175.9	6.2	29	0.4	20
1041768	81	82	1	2.39	0.014	0.7	443.4	7.9	30	0.2	23.3
1041769	82	84	2	5.03	0.02	1	276.5	6.3	31	0.1	19.3
1041770	84	87	3	7.05	0.007	1.1	154.9	6.3	26	<0.1	20.2
1041771	87	88	1	2.62	0.018	0.8	328.7	5.2	26	0.2	22

Taseko Property Technical Report

GC11-79	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #															
1041727	11.3	318	2.83	15	2.2	0.3	8.5	371	<0.1	0.6	0.2	96	2.26	0.05	9.1
1041728	12	329	3	6	2	<0.1	8.1	378	<0.1	0.4	0.2	108	2.36	0.051	8.6
1041729	9.9	210	2.2	8	3.1	<0.1	6.9	360	0.1	0.4	0.1	101	1.68	0.05	9.3
1041730	10.6	247	2.5	11	7.2	<0.1	7.8	377	<0.1	0.4	0.1	103	1.71	0.051	14.1
1041731	10.8	261	2.53	10	3.8	<0.1	8.6	398	<0.1	0.3	0.1	109	1.82	0.051	10.3
1041732	10	215	2.18	11	3.7	<0.1	8.3	390	<0.1	0.4	0.1	105	1.88	0.055	6
1041733	10.4	209	2.1	6	4.1	<0.1	8.7	353	<0.1	0.4	0.1	106	1.69	0.052	7.5
1041734	10.8	210	2.21	5	4.3	<0.1	7.8	351	<0.1	0.3	0.1	110	1.65	0.066	5.4
1041735	11.8	291	2.69	9	2.8	<0.1	7.7	384	0.1	0.5	0.2	114	2.27	0.055	8.7
1041736	12.2	391	3.05	9	2.6	<0.1	7.5	370	0.2	0.4	0.2	117	2.72	0.053	10.1
1041737	14.8	276	2.62	8	3	<0.1	7.5	394	0.1	0.4	0.5	111	1.93	0.056	9.6
1041738	13.3	398	3.22	8	3.2	<0.1	8.7	382	<0.1	0.6	0.4	117	2.52	0.052	10.9
1041739	13.3	456	3.06	8	2.6	<0.1	8.2	397	0.1	0.5	<0.1	103	2.88	0.053	9.8
1041740	20.2	351	4.91	37	5.7	1.3	10.1	190	3	18.3	3.5	99	1.6	0.077	28.3
1041741	13.8	428	3.1	8	2.4	<0.1	7.6	417	<0.1	0.5	<0.1	105	2.73	0.054	10.1
1041742	11.7	275	2.94	12	4.1	<0.1	7.1	409	<0.1	0.4	0.2	106	2.91	0.051	9.4
1041743	15.3	236	3.07	6	1.6	<0.1	7.6	363	<0.1	0.4	0.4	118	2.39	0.055	8.7
1041744	13.7	192	2.55	8	2.3	<0.1	6.7	343	<0.1	0.3	0.2	132	2.43	0.065	7.7
1041745	9.1	182	1.73	7	5.4	<0.1	8.6	354	<0.1	0.3	<0.1	82	2.78	0.052	5.8
1041746	9.1	151	1.57	8	3.2	<0.1	9.6	392	<0.1	0.4	<0.1	79	2.31	0.079	7.6
1041747	9	165	1.59	8	6.3	<0.1	9	414	0.1	0.3	<0.1	79	2.28	0.044	5.5
1041748	8.7	166	1.67	6	2.5	<0.1	8.5	373	<0.1	0.3	<0.1	81	2.12	0.045	4.5
1041749	9.3	165	1.63	8	4.4	<0.1	9.3	399	<0.1	0.4	<0.1	73	2.12	0.043	4.5
1041750	9.1	170	1.77	8	2.9	<0.1	9.4	392	<0.1	0.3	<0.1	78	2	0.046	6
1041751	11.4	169	1.81	7	2.3	<0.1	8.2	409	<0.1	0.3	<0.1	105	2.33	0.053	9.8
1041752	12.3	159	1.82	7	2.4	<0.1	8.3	395	<0.1	0.3	0.1	87	2.22	0.053	8.3
1041753	13.3	161	1.8	8	2.4	<0.1	8.6	382	0.2	0.3	0.1	85	2.05	0.054	7.9
1041754	10.5	159	1.82	8	4.7	<0.1	7.2	404	0.2	0.2	<0.1	79	2.34	0.08	4.9
1041755	9.8	160	1.76	9	1.3	<0.1	7.4	424	<0.1	0.3	<0.1	83	2.14	0.058	6.6
1041756	9.6	212	2.09	8	2.3	<0.1	9.2	394	<0.1	0.3	<0.1	81	2.14	0.043	6.4
1041757	11.6	204	2.26	6	2	<0.1	9.2	384	<0.1	0.3	0.1	95	2.04	0.047	10.1
1041758	12.2	215	2.65	7	3.3	<0.1	14.3	376	<0.1	0.2	<0.1	105	1.99	0.069	10.2
1041759	9.6	242	2.88	7	1.8	<0.1	10.1	384	<0.1	0.2	<0.1	105	2.2	0.053	7.7
1041760	9.6	224	2.81	7	1.3	<0.1	7.9	395	<0.1	0.3	0.5	102	2.09	0.048	10.1
1041761	7.4	171	1.63	5	3.1	<0.1	8.4	353	<0.1	0.2	0.3	65	1.4	0.032	6.3
1041762	5.5	108	1.09	7	4	<0.1	8.8	384	<0.1	0.2	0.3	41	1.24	0.026	4.5
1041763	9.5	182	2.18	6	2.4	<0.1	10.4	392	0.1	0.3	0.2	98	1.94	0.049	7.8
1041764	10.5	137	1.41	7	4.9	<0.1	10.2	379	<0.1	0.3	0.2	63	1.72	0.032	7.1
1041765	13.9	177	2.18	7	2.3	<0.1	9	400	<0.1	0.2	0.2	95	1.97	0.055	8.4
1041766	10.6	204	2.65	7	1.2	<0.1	8.7	426	<0.1	0.3	0.2	104	2.02	0.05	7.9
1041767	10.3	208	2.69	7	1	<0.1	9.1	408	<0.1	0.2	0.2	100	1.86	0.05	6.7
1041768	11.1	218	2.63	8	1.2	<0.1	8.8	429	<0.1	0.2	0.2	112	2.06	0.064	10.8
1041769	10	218	2.16	9	1.6	<0.1	8.6	414	<0.1	0.3	0.1	85	2.24	0.05	7.4
1041770	9.7	211	2.72	8	1.1	<0.1	7.3	391	<0.1	0.2	<0.1	100	2.04	0.052	7.3
1041771	11.2	202	2.67	7	1.2	<0.1	8.3	396	<0.1	0.2	<0.1	117	2.03	0.052	6.9

Taseko Property Technical Report

GC11-79	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #														
1041727	39	1.33	602	0.369	7.11	2.91	2.29	1.2	8.3	23	1.7	14.6	3.5	0.3
1041728	44	1.43	584	0.366	7.1	2.898	2.35	0.6	8.3	22	1.9	14.2	3.6	0.2
1041729	34	1.27	535	0.357	7.01	3.064	2.18	0.8	7.7	23	1.9	11.3	3.2	0.2
1041730	41	1.33	588	0.362	7.3	2.951	2	0.8	7.9	33	2.2	14.5	3.3	0.2
1041731	40	1.4	536	0.371	6.84	2.895	2.16	0.6	9	27	2	15.4	3.4	0.3
1041732	38	1.51	357	0.374	6.95	2.975	1.53	0.7	7.6	14	1.6	10.5	3.4	0.3
1041733	39	1.59	357	0.374	7.09	3.077	1.59	2.7	6.5	17	2	9.5	3.3	0.2
1041734	41	1.74	333	0.4	6.9	3.006	1.59	1.3	6.4	13	1.9	10.2	3.4	0.2
1041735	44	1.55	490	0.381	7.26	3.054	1.95	0.8	8.1	21	2	13.6	3.4	0.3
1041736	44	1.4	403	0.381	7.38	3.054	1.64	1.2	7.4	27	2.1	16.8	3.4	0.2
1041737	44	1.66	474	0.386	7.29	3.056	1.87	0.8	7.6	24	2.3	14.4	3.3	0.2
1041738	47	1.57	592	0.381	7.31	2.899	1.98	0.9	8	29	2	14.8	3.4	0.3
1041739	41	1.48	631	0.361	7.27	2.839	2.3	0.8	8.8	25	1.3	14.9	3.2	0.2
1041740	105	1.01	44	0.175	7.14	0.787	3.73	17.6	22.3	56	3.6	12.3	2.6	0.2
1041741	42	1.5	671	0.369	7.59	3.279	2.52	0.9	7.5	26	1.4	15.5	3.4	0.2
1041742	45	1.53	329	0.384	6.86	2.909	1.62	1.3	5.9	25	2	15.1	3.3	0.2
1041743	42	1.55	290	0.388	7.54	3.154	1.32	4.9	5.5	23	2.3	15	3.6	0.3
1041744	45	1.67	284	0.347	7.24	3.082	1.26	1.5	5	21	2.4	13.8	3.8	0.3
1041745	31	1.25	305	0.311	7	3.099	1.66	1.5	8.2	14	1.2	10.5	3.1	0.2
1041746	30	1.27	307	0.323	7.08	3.123	1.23	0.4	11.9	17	1.1	7.7	3	0.3
1041747	31	1.27	315	0.318	7.13	3.229	1.26	0.5	12	12	1.4	6.9	3.2	0.3
1041748	31	1.22	388	0.306	7.02	3.008	1.41	0.9	11.4	10	1.2	7.1	2.9	0.3
1041749	29	1.2	347	0.308	6.93	3.25	1.34	1.1	11.8	10	1.2	7	3.1	0.2
1041750	28	1.24	409	0.305	6.72	3.261	1.48	0.4	11.9	14	1.2	7.9	3.2	0.3
1041751	33	1.39	281	0.332	7.32	3.226	1.28	0.5	10.5	23	1.7	11.5	3.3	0.3
1041752	31	1.31	326	0.318	6.9	3.212	1.31	0.8	10.8	21	1.7	11.2	3.1	0.2
1041753	32	1.3	317	0.326	6.92	3.267	1.3	2.5	10.6	18	1.3	7.9	2.9	0.2
1041754	39	1.42	281	0.309	6.89	3.32	1.3	0.8	10	13	1.4	9.4	3.5	0.3
1041755	38	1.4	300	0.308	6.96	3.201	1.53	0.4	8.6	17	1.4	8.8	3.3	0.3
1041756	33	1.3	451	0.324	7.16	3.064	1.63	0.5	11.4	16	1.4	8.8	3.1	0.3
1041757	37	1.36	331	0.346	7.14	3.387	1.47	0.5	10.2	25	1.7	10.8	3.3	0.3
1041758	35	1.28	383	0.34	7.56	3.452	1.5	1.3	12.4	29	2.5	21.8	3.9	0.3
1041759	39	1.21	419	0.332	6.98	3.164	1.47	0.5	13.1	21	2	17.8	3.5	0.3
1041760	32	1.17	389	0.276	6.5	2.849	1.39	0.6	12.2	16	2.1	12.3	3.1	0.3
1041761	20	0.82	464	0.218	6.35	2.963	1.5	1.5	14.1	13	1.1	7.6	2.5	0.2
1041762	14	0.69	320	0.178	7.03	3.698	1.24	1.8	16.2	8	1.1	5.7	2.1	0.2
1041763	29	1.26	285	0.291	7.45	3.263	1.23	1	12.1	20	1.9	12	3.3	0.2
1041764	21	0.94	357	0.244	7.2	3.507	1.41	1.3	12.8	15	1.6	14.5	3	0.3
1041765	35	1.4	279	0.335	7.42	3.293	1.32	0.4	11.3	23	2.1	13	3.7	0.3
1041766	35	1.29	374	0.313	7.31	3.216	1.43	0.7	10.9	22	2.2	13.3	3.6	0.2
1041767	35	1.23	489	0.31	7.13	2.899	1.75	0.4	10.4	17	1.9	10.1	3.5	0.2
1041768	35	1.4	302	0.345	7.3	3.271	1.26	0.5	11	30	2.3	14.3	4	0.3
1041769	33	1.29	313	0.318	7.31	3.454	1.19	0.4	10.8	22	3	15.8	3.8	0.3
1041770	34	1.21	323	0.304	6.75	3.251	1.27	0.3	9.9	21	2.3	12	3.4	0.3
1041771	34	1.33	215	0.318	6.73	3.308	0.94	0.2	11	22	3.4	16.5	3.8	0.3

GC11-79	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041727	<1	11	24.4	<0.1	76.1	0.4
1041728	<1	11	20	<0.1	71.7	0.5
1041729	<1	10	22.8	<0.1	89	0.3
1041730	<1	10	24.7	<0.1	78	0.4
1041731	<1	11	25.6	<0.1	81.2	0.4
1041732	<1	11	30.6	<0.1	80.7	0.3
1041733	<1	11	26.3	0.1	94.3	0.3
1041734	<1	12	29	0.1	77.7	0.3
1041735	1	12	23.2	<0.1	81.6	0.3
1041736	<1	12	27.1	<0.1	81.5	0.4
1041737	1	11	29.4	0.2	84.9	0.3
1041738	1	12	25.8	<0.1	67.6	0.4
1041739	<1	11	25.5	<0.1	66.4	0.5
1041740	1	11	14.1	2.4	163.6	0.8
1041741	<1	12	22.4	<0.1	74.7	0.3
1041742	<1	11	33	<0.1	90.4	0.3
1041743	<1	11	28.3	0.1	69.7	0.3
1041744	1	12	37.3	<0.1	56.7	0.2
1041745	<1	9	28.5	<0.1	93.3	0.3
1041746	1	8	26.9	<0.1	69.3	0.5
1041747	1	8	29.7	<0.1	69.3	0.6
1041748	1	8	25	<0.1	65.5	0.5
1041749	1	8	28.3	0.1	69.5	0.5
1041750	<1	8	30.1	<0.1	68.6	0.6
1041751	<1	10	27.3	<0.1	67.9	0.5
1041752	<1	9	26.4	0.2	68.4	0.5
1041753	<1	9	25.9	0.3	75	0.5
1041754	1	10	30.6	<0.1	57	0.5
1041755	<1	9	28	<0.1	71.8	0.4
1041756	<1	9	25.5	<0.1	77	0.6
1041757	<1	9	28	<0.1	76.8	0.4
1041758	<1	10	24.7	0.1	79.6	0.5
1041759	1	10	20	<0.1	61.5	0.6
1041760	<1	9	19.8	<0.1	63.6	0.5
1041761	1	6	19	<0.1	81.3	0.5
1041762	<1	4	16.5	<0.1	89.6	0.6
1041763	<1	9	22.5	0.1	92.6	0.5
1041764	1	7	19.9	<0.1	88.3	0.5
1041765	1	10	28.9	0.1	91.1	0.5
1041766	<1	9	24.6	<0.1	86.7	0.6
1041767	<1	9	23.1	<0.1	92.8	0.4
1041768	<1	10	26.5	<0.1	77.7	0.5
1041769	1	10	23.7	<0.1	59.6	0.6
1041770	<1	9	22.6	<0.1	56.4	0.5
1041771	1	10	23.9	<0.1	48.9	0.5

Taseko Property Technical Report

GC 11-79			Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
Sample #	From	To	Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	
			MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	
			Standards	section								
1041772	88	89	1	2.7	0.016	1.5	170.9	6.4	28	<0.1	23.1	
1041773	89	92	3	8.12	0.012	1	189.4	6.3	29	0.1	20.8	
1041774	92	95	3	6.82	0.026	1	309.8	5.8	26	0.2	18.3	
1041775	95	98	3	5.84	0.01	0.9	82.4	6	32	<0.1	19.6	
1041776	98	99.5	1.5	3.39	0.02	8.6	973.8	7.6	32	0.3	17.3	
1041777	99.5	100.5	1	2.61	0.005	2362.4	92.1	54.8	29	0.4	11	
1041778	100.5	101.4	0.9	2.7	0.009	5.2	389.6	7	28	0.2	20.9	
1041779	101.4	103	1.6	3.34	0.223	5.6	3087.2	7.2	25	1.2	12.8	
1041780	103	103	Blank	0	0.54	<0.005	0.2	2.8	<0.1	<1	<0.1	0.2
1041781	103	105	2	5.48	0.005	6.7	165.2	5.9	27	<0.1	14.8	
1041782	105	108	3	5.96	<0.005	22.4	146.8	5.3	21	<0.1	10.3	
1041783	108	110	2	4.52	0.008	6.2	72.9	5.4	17	<0.1	10.7	
1041784	110	111	1	2.72	0.006	17	193.6	7	19	<0.1	10.7	
1041785	111	114	3	7.24	0.006	6.6	120.9	7.5	29	0.1	16.6	
1041786	114	117	3	8.18	0.007	1.6	94	4.7	26	<0.1	21.2	
1041787	117	118.2	1.2	3.15	0.016	2.9	239.1	6.1	32	0.1	19.8	
1041788	118.2	120	1.8	4.4	0.025	14.1	576.7	5.9	29	0.2	20.5	
1041789	120	122	2	5.07	0.011	2.2	141.3	5.3	27	<0.1	21	
1041790	122	124	2	6.75	0.019	33.9	341.7	5.6	26	<0.1	21.7	
1041791	124	126	2	4.27	0.015	7.1	315.7	5.6	25	<0.1	19.4	
1041792	126	127	1	2.4	0.02	3.2	447.7	6.8	32	0.2	23.5	
1041793	127	129	2	5.56	<0.005	0.9	66.4	5.9	31	<0.1	20	
1041794	129	131	2	5.76	0.007	2.5	222.6	6.5	28	<0.1	21.1	
1041795	131	133	2	5.17	<0.005	1.3	89.6	6.2	23	<0.1	15.1	
1041796	133	135	2	4.59	0.027	1.7	804.1	5.8	27	0.4	14.4	
1041797	135	138	3	8.78	0.007	0.8	127	5.6	26	<0.1	20.9	
1041798	138	140	2	5.42	0.013	2	167.1	6.3	25	<0.1	20.5	
1041799	140	142	2	5.61	0.092	23.9	2644.6	8	25	0.7	9.7	
1041800	142	142	Cm2	0	0.08	1.725	289.7	9743.3	81.2	127	4.9	33.4
1041801	142	143	1	3.63	0.032	4	600.3	5.8	26	0.1	13.4	
1041802	143	145	2	3.9	0.086	36.9	3068	6.6	28	0.7	12.8	
1041803	145	147	2	5.18	0.025	3	813.7	7.1	27	0.2	12.9	
1041804	147	149	2	5.69	0.034	4.1	556.8	6.5	23	0.2	12.4	
1041805	149	151	2	4.69	0.024	15.3	809.9	5.5	28	0.1	13.8	
1041806	151	153	2	5.08	0.025	1.6	586.1	6.4	25	0.2	12.9	
1041807	153	155	2	5.93	0.036	3.4	698.6	7.4	27	0.2	14.1	
1041808	155	157	2	5.51	0.009	3.4	189.7	6.8	29	<0.1	16.6	
1041809	157	159	2	4.52	0.019	4.1	742.4	6	27	0.3	12.9	
1041810	159	160	1	2.36	0.007	12.3	249.4	7.3	32	0.1	16.8	
1041811	160	162	2	5.27	0.035	12.7	1244.8	6.1	31	0.2	19.9	
1041812	162	165	3	7.4	0.008	2.1	218.1	6.6	33	<0.1	16.4	
1041813	165	168	3	7.19	<0.005	1.8	200.5	7.3	30	<0.1	20	
1041814	168	171	3	7.9	<0.005	3.8	72.8	8.3	35	<0.1	17.6	
1041815	171	174	3	8.42	0.013	6	180.6	7.8	32	<0.1	18.2	

Taseko Property Technical Report

GC11-79	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #															
1041772	11.1	207	2.49	7	1	<0.1	9.9	419	<0.1	0.2	<0.1	100	2.13	0.05	7.9
1041773	10.6	212	2.53	9	1.6	<0.1	8.8	401	<0.1	0.4	<0.1	104	2.07	0.053	6.5
1041774	9.6	170	1.83	5	1.4	<0.1	7.4	369	<0.1	0.3	0.1	81	1.74	0.042	6.5
1041775	11.3	237	2.46	9	2.1	<0.1	9.3	416	<0.1	0.3	<0.1	100	2.24	0.049	7.1
1041776	9.6	193	1.69	10	3.3	<0.1	8.2	433	<0.1	0.5	<0.1	71	2.16	0.037	12
1041777	21.1	130	2.45	16	31.4	<0.1	7.6	427	<0.1	0.8	0.8	51	1.5	0.016	9.8
1041778	9.3	170	1.74	7	2.9	<0.1	8.3	389	<0.1	0.3	0.3	75	2.15	0.046	5.3
1041779	7.8	121	1.37	7	2	0.3	7.3	383	0.2	0.4	0.1	51	1.9	0.021	17.5
1041780	<0.2	20	0.03	15	1.2	<0.1	<0.1	4627	<0.1	<0.1	<0.1	<1	34.6	0.003	0.5
1041781	7.3	191	1.62	7	3.8	<0.1	10.1	311	<0.1	0.4	<0.1	63	1.74	0.036	7.2
1041782	5.4	102	0.94	7	4.5	<0.1	14.3	293	<0.1	0.6	<0.1	39	1.24	0.023	4.5
1041783	5.2	111	1.05	6	3.5	<0.1	16.1	245	<0.1	0.6	<0.1	42	1.71	0.022	5
1041784	5.2	115	1.08	6	2.7	<0.1	10.7	265	0.1	0.5	<0.1	35	2.11	0.015	4.1
1041785	8.9	188	2.11	6	2.5	<0.1	8.7	334	<0.1	0.5	<0.1	75	1.9	0.04	4.9
1041786	10	206	2.17	6	2.2	<0.1	9.2	392	0.1	0.4	<0.1	82	2.37	0.039	4.9
1041787	10.2	211	2.17	9	2.2	<0.1	8.8	346	<0.1	0.7	<0.1	81	2.31	0.04	5.4
1041788	10.3	207	2.13	6	4	<0.1	10	354	0.1	0.5	<0.1	83	2.22	0.042	5.7
1041789	10.3	207	2.39	7	2.3	<0.1	11.2	450	0.2	0.3	<0.1	91	2.25	0.043	6.9
1041790	11.2	212	2.36	7	2.3	<0.1	9.1	445	<0.1	0.3	<0.1	87	2.24	0.053	6.4
1041791	10.1	201	2.17	8	1.5	<0.1	9	334	<0.1	0.5	<0.1	80	2.48	0.043	5.7
1041792	12.6	295	2.61	17	4.2	<0.1	10.3	147	0.2	2.6	<0.1	87	4.35	0.042	7.5
1041793	10.4	241	2.49	6	1.9	<0.1	6.8	339	<0.1	0.5	<0.1	89	2.71	0.041	5.5
1041794	9.7	213	2.29	5	1.8	<0.1	8.4	311	<0.1	0.5	<0.1	85	2.16	0.042	5.7
1041795	6.8	176	1.87	5	2	<0.1	10.8	280	0.1	0.6	0.7	63	1.6	0.027	8.9
1041796	7.4	215	1.79	19	2	<0.1	11.1	309	<0.1	2	0.6	62	2.55	0.023	8.1
1041797	10.2	229	2.3	5	2	<0.1	9.7	329	<0.1	0.7	0.3	85	2.57	0.051	6.9
1041798	8.9	233	2.39	7	2.1	<0.1	8.5	413	<0.1	0.6	0.3	88	2.34	0.047	5.9
1041799	5.4	133	1.37	9	3.3	<0.1	6.6	472	0.2	0.6	0.3	53	2	0.011	10.4
1041800	19.5	385	4.87	34	5.3	1.4	10.8	196	1.9	20.8	3.6	99	1.57	0.077	31.4
1041801	7.6	231	1.5	5	2	<0.1	6.7	407	0.2	0.6	0.1	55	2.74	0.017	10.1
1041802	7.7	211	1.89	13	2.2	0.6	5.9	412	0.1	2.1	0.2	76	2.5	0.022	8
1041803	7.1	251	1.55	10	2.8	<0.1	6.1	422	<0.1	0.6	0.1	61	3.31	0.041	7
1041804	5.9	238	1.41	6	2.1	<0.1	6.9	438	<0.1	0.5	<0.1	61	3.12	0.054	8.3
1041805	6.9	181	1.4	6	2.6	<0.1	6.3	348	<0.1	0.8	0.2	62	2.36	0.039	9.5
1041806	6.5	197	1.48	6	1.9	<0.1	7.1	409	<0.1	0.5	<0.1	58	2.79	0.039	8
1041807	6.7	234	1.68	6	2	<0.1	6.4	439	<0.1	0.6	0.1	61	2.74	0.041	7.1
1041808	8	240	1.92	6	1.9	<0.1	5.9	398	<0.1	0.3	<0.1	69	2.48	0.043	5.7
1041809	7.5	223	1.48	24	1.8	<0.1	6.9	330	0.2	2.3	<0.1	66	3.18	0.041	7.1
1041810	7.5	269	2.16	7	2.1	<0.1	6.8	413	<0.1	0.6	<0.1	81	2.5	0.042	6.4
1041811	8.4	237	2.17	6	1.7	<0.1	5.7	468	<0.1	0.5	0.1	87	2.28	0.042	6.3
1041812	8.2	230	1.86	7	2.3	<0.1	6.7	393	<0.1	1.3	<0.1	74	2.48	0.045	5.8
1041813	9.4	251	2.22	5	2	<0.1	6.7	421	<0.1	0.7	<0.1	84	2.49	0.045	5.9
1041814	9.2	304	2.38	6	2.5	<0.1	6.5	437	<0.1	0.5	<0.1	79	2.26	0.046	6.6
1041815	8.3	282	2.16	6	2.7	<0.1	6.8	414	<0.1	0.6	<0.1	75	2.3	0.042	6.7

Taseko Property Technical Report

GC11-79	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
Sample #	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
1041772	35	1.41	331	0.323	7.42	3.241	1.38	0.4	9.5	20	1.7	9.8	3.4	0.3
1041773	31	1.17	376	0.307	7.29	3.21	1.35	0.6	10.6	18	1.8	11.3	3.3	0.3
1041774	29	1.18	226	0.287	6.81	3.334	1.03	0.5	10.1	19	1.9	10.3	3.1	0.3
1041775	32	1.27	389	0.296	7.1	3.153	1.31	0.5	11.1	20	1.8	11.7	3.7	0.3
1041776	33	1.23	277	0.284	6.96	3.462	1.16	1.8	9.1	29	2.5	18.5	3.6	0.2
1041777	31	0.5	435	0.274	8.59	5.156	1.45	9.2	11.6	18	4.1	43.9	4.8	0.4
1041778	31	1.3	230	0.285	6.57	3.363	1.06	1.2	8.6	12	1.7	13	3.2	0.2
1041779	24	0.72	221	0.224	6.38	3.447	0.79	1.3	10	47	2.9	27.1	3.2	0.2
1041780	<1	1.71	11	<0.001	0.04	0.007	<0.01	<0.1	0.2	<1	<0.1	0.5	0.2	<0.1
1041781	21	0.99	389	0.226	6.61	3.014	1.44	0.7	10.8	16	1.2	9.1	2.9	0.3
1041782	14	0.68	176	0.182	6.64	3.468	1.02	1.5	9.5	9	0.8	5	2.4	0.3
1041783	13	0.57	332	0.177	6.31	2.845	1.59	1.3	10.1	10	0.6	4.2	2.9	0.3
1041784	14	0.56	139	0.171	6.06	3.124	0.87	1.8	8.4	9	0.8	5.5	2.3	0.2
1041785	23	1.01	502	0.242	6.41	2.778	1.91	1.2	8.1	13	0.8	8.3	3.1	0.3
1041786	29	1.22	361	0.299	6.43	2.977	1.34	0.5	7.5	12	1.4	8.4	3.6	0.3
1041787	28	1.07	499	0.279	6.63	2.791	1.87	1.5	7.7	14	1.1	9.4	3.4	0.3
1041788	26	1.24	395	0.285	6.67	2.823	1.59	2.4	6.7	15	1.3	10.2	3.4	0.4
1041789	30	1.33	488	0.306	7.2	2.886	1.73	1.1	6.7	17	1.4	11.3	3.4	0.3
1041790	32	1.38	403	0.312	6.92	3.088	1.54	0.7	7.4	16	1.5	9.9	3.5	0.3
1041791	30	1.21	357	0.298	6.64	2.811	1.37	0.7	6.8	16	1.4	9.8	3.3	0.3
1041792	31	0.86	1264	0.279	6.51	1.241	2.57	3.3	7.5	20	1.4	13.9	3.3	0.3
1041793	31	1.12	484	0.306	6.81	2.77	1.79	0.8	6.9	16	1.5	11	3.2	0.3
1041794	29	1.2	422	0.306	6.65	2.86	1.75	0.8	6.6	15	1.3	9.2	3.2	0.3
1041795	21	0.85	550	0.228	6.36	2.643	2.24	1.3	9.3	13	1.1	7.7	2.5	0.3
1041796	18	0.97	446	0.197	7.66	3.541	1.5	1.6	10.9	19	1.5	10.5	2.4	0.3
1041797	36	1.28	730	0.308	6.93	3.075	1.04	1.1	8.4	17	1.7	9.8	3.3	0.3
1041798	30	1.23	386	0.296	6.5	3.101	1.19	0.4	9.6	17	2.2	12	3.5	0.3
1041799	23	0.66	240	0.22	6.65	3.583	0.78	1.3	8.5	35	4.1	30.7	3.1	0.2
1041800	105	0.97	236	0.2	6.81	0.764	2.84	18.1	24.2	59	3.7	11.4	3.1	0.2
1041801	23	1.16	211	0.259	6.61	3.532	0.61	0.8	9.8	31	4	22.8	3.7	0.3
1041802	27	1	256	0.268	6.35	3.463	0.84	1.1	10.3	29	4.8	26.3	4.1	0.3
1041803	25	1	215	0.29	6.44	3.744	0.57	0.7	9.5	27	4.6	20.9	3.7	0.3
1041804	23	1.14	215	0.273	6.23	3.605	0.46	0.5	9	32	4.4	22.8	3.8	0.3
1041805	24	0.89	192	0.26	6.05	3.307	0.83	1.8	8.8	30	3.9	18.9	3.5	0.3
1041806	25	1	230	0.264	6.59	3.604	0.7	0.4	8.8	28	4	22.7	3.7	0.3
1041807	26	1.04	285	0.256	6.15	3.516	0.78	0.6	10.1	25	3.2	17.7	3.2	0.2
1041808	26	1.04	408	0.266	6.35	3.206	1.18	0.5	8.2	18	1.9	13.3	3.3	0.3
1041809	23	0.98	361	0.267	6.28	3.093	0.98	1	8.9	25	2.9	19	3.7	0.3
1041810	26	1.04	471	0.252	6.47	3.204	1.32	0.8	7	17	1.7	9.7	2.9	0.2
1041811	29	1.09	427	0.28	6.3	3.309	1.12	1.2	9	19	2.2	11.4	3.1	0.3
1041812	24	0.99	389	0.263	6.26	3.032	1.19	0.8	8.4	18	2.1	12	3.2	0.3
1041813	26	1.14	476	0.28	6.55	3.119	1.33	0.8	10.1	16	1.5	10.3	2.9	0.3
1041814	27	1.15	651	0.265	6.16	2.871	1.93	0.6	9	18	1.1	9.7	2.9	0.2
1041815	25	1.05	513	0.254	6.47	2.903	1.67	0.8	9	17	1	9.4	3	0.3

GC11-79	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041772	<1	10	26.3	<0.1	90.3	0.5
1041773	1	9	20.6	<0.1	77.6	0.6
1041774	1	8	25.2	<0.1	59.1	0.5
1041775	<1	9	27.7	<0.1	67.2	0.5
1041776	1	9	29.6	0.2	57.6	0.5
1041777	2	8	12.1	2.2	140	0.6
1041778	1	9	30.9	0.3	57.1	0.3
1041779	1	6	22.7	0.4	50.4	0.3
1041780	<1	<1	0.4	<0.1	<0.1	<0.1
1041781	1	7	23.9	<0.1	77.3	0.4
1041782	1	4	18	<0.1	75.5	0.5
1041783	<1	5	16.1	<0.1	88.5	0.5
1041784	1	4	16.2	0.2	61.2	0.4
1041785	<1	7	21.7	<0.1	80.2	0.4
1041786	1	9	26	<0.1	50.2	0.3
1041787	<1	8	27.1	<0.1	67.6	0.4
1041788	1	9	31.3	0.1	67	0.3
1041789	<1	9	29.7	0.1	82.1	0.4
1041790	1	9	30.7	0.2	63.5	0.3
1041791	2	9	27.3	<0.1	56.3	0.4
1041792	<1	9	29.2	0.2	135.8	0.4
1041793	2	9	23.4	<0.1	62.7	0.4
1041794	1	8	31.2	<0.1	65.8	0.3
1041795	1	6	22.8	<0.1	84.5	0.5
1041796	1	8	27.8	<0.1	78.5	0.4
1041797	<1	9	30.2	<0.1	53.8	0.5
1041798	<1	8	27.2	<0.1	43.1	0.5
1041799	<1	6	20.5	0.3	38.9	0.4
1041800	2	10	12.3	2.5	124.2	0.8
1041801	<1	9	23.2	<0.1	21.6	0.5
1041802	<1	8	21.2	0.3	24.7	0.5
1041803	1	7	22.3	<0.1	17.6	0.5
1041804	<1	8	19.6	<0.1	12.1	0.5
1041805	<1	7	25.5	<0.1	31.2	0.4
1041806	<1	7	28.5	<0.1	26.9	0.5
1041807	1	7	25.7	<0.1	23.8	0.5
1041808	1	7	27.3	<0.1	34.5	0.4
1041809	<1	8	24.6	<0.1	44.8	0.4
1041810	<1	7	22.1	<0.1	44.4	0.3
1041811	1	7	25.1	0.1	34.5	0.4
1041812	1	7	20.9	<0.1	52.2	0.5
1041813	1	7	22.8	<0.1	43.5	0.5
1041814	<1	7	21.4	<0.1	59.8	0.4
1041815	<1	7	20.4	<0.1	53.4	0.5

GC11-79				Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	
				Unit	KG	GM/T	PPM	PPM	PPM	PPM	PPM	PPM	
				MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	
Sample #	From	To	Standards	section									
1041816	174	177			3	7.8	0.029	4.8	290.8	5.9	34	0.1	18.9
1041817	177	180			3	8.13	0.019	5.8	315.6	5.6	24	<0.1	19.5
1041818	180	183			3	8.51	0.007	8.9	192	6.7	30	<0.1	20
1041819	183	184			1	2.39	0.008	6.1	137.6	8	33	<0.1	19.4
1041820	183	184	Duplicate		1	2.82	<0.005	5.1	95	8	34	<0.1	19.8
1041821	184	186			2	5.23	<0.005	2.8	50.8	7.8	31	<0.1	17.9
1041822	186	189			3	8.84	0.007	3.8	148	6.3	25	0.1	17.4
1041823	189	192			3	7.9	0.015	3.6	252.6	6.3	30	<0.1	19.2
1041824	192	194			2	5.34	0.01	3.6	174.3	6.5	29	0.1	17.5
1041825	194	196			2	5.55	<0.005	4	136.5	6.2	27	<0.1	18.5
1041826	196	198			2	5.42	0.011	5	133.9	4.6	24	<0.1	17.2
1041827	198	200			2	5.72	0.011	2.2	120.3	6.7	30	<0.1	16.2
1041828	200	203			3	9.11	0.017	12.3	191.4	7.4	33	<0.1	19.2
1041829	203	204			1	2.86	0.026	2.1	305.7	6.5	34	0.1	18.6
1041830	204	206			2	5.58	0.016	1.5	117.6	7	32	<0.1	18.5
1041831	206	208			2	5.73	0.014	1.6	97.1	8.4	32	<0.1	15.9
1041832	208	210			2	5.32	0.013	1.6	80.8	8	38	0.1	17.4

EOH

GC11-79	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La
	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM
	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	0.01	0.001	0.1
Sample #															
1041816	7.8	175	1.95	5	1.4	<0.1	6.2	490	<0.1	0.4	<0.1	86	2.13	0.042	4.7
1041817	8.1	190	1.88	6	1.7	<0.1	7.1	300	0.2	0.9	<0.1	72	2.43	0.047	4.8
1041818	8.8	239	2.3	5	1.9	<0.1	6.5	372	<0.1	0.8	<0.1	78	2.43	0.045	6.5
1041819	9.6	284	2.48	4	2.6	<0.1	7	390	<0.1	0.5	<0.1	80	2.39	0.041	6.8
1041820	9.6	295	2.57	4	2.8	<0.1	6.9	379	<0.1	0.4	<0.1	81	2.46	0.045	7.8
1041821	9.2	300	2.36	5	2.2	<0.1	6.4	395	<0.1	0.4	<0.1	76	2.25	0.042	7.2
1041822	9.2	214	2.22	5	1.7	<0.1	5.6	400	<0.1	0.3	<0.1	76	2.23	0.038	5
1041823	8.5	230	2.31	5	1.5	<0.1	6.1	413	<0.1	0.3	<0.1	81	2.14	0.046	5.9
1041824	8.8	228	2.25	5	2	<0.1	6.8	387	<0.1	0.4	<0.1	75	2.12	0.043	5.8
1041825	9.3	218	2.12	6	1.9	<0.1	7.5	511	<0.1	0.6	<0.1	74	2.31	0.051	6.5
1041826	7.7	250	1.92	6	2.1	<0.1	7	275	0.2	1.8	<0.1	71	1.86	0.045	4.4
1041827	8.5	414	2.02	7	1.9	<0.1	8.4	508	0.3	1.3	<0.1	65	4.22	0.04	7.7
1041828	9.4	303	2.31	6	2.9	<0.1	6.5	458	<0.1	0.8	0.1	76	2.61	0.072	7.2
1041829	8.9	262	2.21	5	1.7	<0.1	6.6	433	<0.1	0.3	0.2	75	2.43	0.048	7.1
1041830	9.1	287	2.65	5	1.8	<0.1	6.9	495	<0.1	0.3	0.1	74	2.57	0.041	7.6
1041831	9.2	304	2.6	4	1.6	<0.1	6.4	469	<0.1	0.3	<0.1	66	2.4	0.035	6.6
1041832	9	348	2.83	4	2.1	<0.1	7.9	452	<0.1	0.3	<0.1	86	2.41	0.044	7.6

GC11-79	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta
	PPM	%	PPM	%	%	%	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM
	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1
Sample #														
1041816	23	1.06	318	0.259	6.27	3.067	0.97	0.5	7	13	1.1	8.7	2.9	0.2
1041817	25	0.94	343	0.259	6.56	2.506	1.56	1.4	6.8	13	0.9	6.9	2.8	0.2
1041818	26	1.07	499	0.253	6.6	2.627	1.76	0.7	9.6	16	1.1	8	2.7	0.2
1041819	26	1.17	667	0.271	6.43	2.592	2.16	0.8	10	19	1.3	9.4	2.6	0.3
1041820	26	1.15	657	0.262	6.72	2.654	2.17	0.8	11.1	21	1.2	9.9	2.9	0.2
1041821	24	1.03	644	0.255	6.35	2.651	2.23	0.7	9.4	18	1	8.5	2.8	0.2
1041822	25	1.06	498	0.257	6.09	2.85	1.54	0.6	7.6	13	1.2	7.8	2.5	0.2
1041823	25	1.1	586	0.266	6.17	2.767	1.77	0.7	7.2	15	0.9	8.5	2.7	0.3
1041824	24	1.08	576	0.249	6.36	2.742	1.79	0.5	7.5	15	1.2	7.6	2.6	0.2
1041825	24	1.12	495	0.264	6.7	2.82	1.66	0.6	7.1	17	1.1	9.2	2.9	0.2
1041826	23	1.05	438	0.248	7	2.51	1.81	1.1	6.6	12	1.1	6.1	2.7	0.2
1041827	21	1.14	711	0.222	6.13	2.221	1.75	1	8	22	0.9	11.4	2.7	0.2
1041828	28	1.04	605	0.259	6.42	2.853	1.7	1.1	9.5	20	1.2	10.2	2.8	0.2
1041829	24	1.11	502	0.281	6.47	3.122	1.39	0.6	9.3	19	1.5	10	3.1	0.2
1041830	29	1.28	471	0.291	6.93	3.233	1.13	0.5	8.7	19	1.4	9.4	3.1	0.2
1041831	27	1.12	520	0.274	6.86	3.082	1.16	0.4	8	16	1	7	3.1	0.3
1041832	27	1.1	631	0.257	6.79	3.069	1.27	0.6	9.6	19	1.3	10.4	3	0.2

GC11-79	Be	Sc	Li	S	Rb	Hf
	PPM	PPM	PPM	%	PPM	PPM
	1	1	0.1	0.1	0.1	0.1
Sample #						
1041816	<1	7	23.2	<0.1	40.2	0.4
1041817	<1	7	20.7	<0.1	73.3	0.3
1041818	1	7	24.3	<0.1	63.9	0.4
1041819	<1	7	25.1	<0.1	68.7	0.5
1041820	<1	7	23.6	<0.1	67.6	0.5
1041821	<1	7	20.1	<0.1	55.5	0.4
1041822	1	7	21.4	<0.1	49	0.4
1041823	<1	7	22.3	<0.1	55	0.4
1041824	<1	7	23	<0.1	59.8	0.4
1041825	1	7	24	<0.1	67.4	0.3
1041826	1	7	21.1	<0.1	84.7	0.3
1041827	1	7	19.9	<0.1	79.6	0.4
1041828	<1	7	21.6	<0.1	56.7	0.6
1041829	1	7	21.3	<0.1	49.3	0.4
1041830	<1	8	22.2	<0.1	38.3	0.3
1041831	1	7	20.6	<0.1	33.3	0.4
1041832	1	7	19	<0.1	36.7	0.5

APPENDIX II

Certificates



1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Submitted By: Tim Johnson
Receiving Lab: Canada-Vancouver
Received: October 31, 2011
Report Date: December 06, 2011
Page: 1 of 7

CERTIFICATE OF ANALYSIS

VAN11005878.1

CLIENT JOB INFORMATION

Project: Taseko
Shipment ID:
P.O. Number
Number of Samples: 172

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0
Canada

CC: Mathius Westphal

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	169	Crush, split and pulverize 250 g rock to 200 mesh			VAN
G601	172	Fire Assay fusion Au by ICP-ES	30	Completed	VAN
1EX	172	4 Acid digestion ICP-MS analysis	0.25	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 2 of 7 Part 1

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041301	Drill Core	3.92	0.155	56.1	2880	6.2	37	1.4	25.2	8.4	217	2.03	6	1.8	<0.1	7.5	456	<0.1	0.5	0.5	90
1041302	Drill Core	3.90	0.089	55.7	1528	5.1	34	1.0	24.6	8.3	192	1.77	6	2.8	<0.1	9.3	455	0.2	0.6	0.4	81
1041303	Drill Core	4.28	0.154	161.7	2843	5.9	30	1.5	30.7	8.5	181	1.83	9	2.7	<0.1	8.9	472	<0.1	0.6	0.3	76
1041304	Drill Core	2.86	0.363	400.2	4425	9.6	34	3.5	37.1	10.6	160	1.91	6	5.5	1.2	9.2	445	0.3	0.6	0.6	71
1041305	Drill Core	2.84	0.185	358.8	4684	10.3	36	3.0	36.0	10.0	159	2.00	6	6.4	<0.1	9.0	413	<0.1	0.6	0.8	72
1041306	Drill Core	5.27	0.560	212.9	5723	11.3	36	3.2	32.3	10.4	158	2.17	3	13.8	0.1	12.0	279	0.6	0.5	0.6	79
1041307	Drill Core	6.29	0.248	119.2	3669	7.8	37	2.7	30.5	9.4	195	2.00	5	10.1	<0.1	9.6	428	0.4	0.7	0.5	75
1041308	Drill Core	5.71	0.125	201.3	3604	6.9	34	2.3	28.8	9.3	184	1.89	6	17.1	0.1	9.9	409	0.2	0.7	0.6	70
1041309	Drill Core	7.42	0.126	97.3	1712	8.4	36	1.1	27.3	9.6	214	1.79	5	3.8	<0.1	8.9	427	0.1	0.5	0.4	82
1041310	Drill Core	7.53	0.113	215.4	4275	7.7	36	2.5	31.2	10.1	206	2.14	6	4.8	0.3	8.8	461	<0.1	0.5	0.4	82
1041311	Drill Core	6.47	0.239	67.7	2139	11.3	40	1.7	30.2	11.0	238	2.31	6	1.5	0.1	8.9	410	<0.1	0.7	0.8	108
1041312	Drill Core	6.82	0.089	94.0	1491	6.3	32	0.9	27.5	11.1	210	2.35	6	1.2	<0.1	8.9	462	<0.1	0.5	0.4	100
1041313	Drill Core	7.23	0.670	2.2	2754	6.8	33	1.8	28.6	10.2	219	2.23	6	2.2	<0.1	9.0	402	<0.1	0.5	0.5	84
1041314	Drill Core	7.62	0.114	141.8	1658	6.1	31	1.3	26.3	9.2	232	3.40	7	1.2	0.2	8.3	435	<0.1	0.4	0.4	119
1041315	Drill Core	6.56	0.084	4.1	1670	6.4	37	1.0	26.2	10.0	287	3.02	7	2.4	<0.1	8.4	396	<0.1	0.6	0.4	81
1041316	Drill Core	6.68	0.041	17.5	1144	6.1	34	0.8	26.6	9.4	256	3.19	6	1.3	<0.1	8.6	395	<0.1	0.5	0.2	91
1041317	Drill Core	2.72	0.239	9.9	3104	6.8	35	2.5	26.4	9.6	274	3.97	8	2.0	<0.1	8.9	446	<0.1	0.4	0.4	106
1041318	Drill Core	1.86	<0.005	1.4	146.4	3.8	80	0.2	30.6	35.6	1146	6.91	39	2.1	<0.1	2.0	490	0.2	1.6	<0.1	217
1041319	Drill Core	4.51	0.037	2.1	674.9	6.9	31	0.5	23.0	8.5	254	3.03	7	1.6	<0.1	8.2	471	<0.1	0.5	0.2	84
1041320	Rock Pulp	0.07	1.436	289.2	9807	82.0	135	5.1	35.6	21.5	393	4.92	33	5.3	1.8	10.2	199	3.2	20.8	3.3	101
1041321	Drill Core	5.35	0.017	7.6	657.3	8.1	31	0.5	21.6	8.3	220	2.65	7	1.6	<0.1	9.7	466	<0.1	0.5	<0.1	84
1041322	Drill Core	6.89	0.129	12.1	1811	7.6	39	1.3	24.7	8.8	263	3.18	8	1.9	<0.1	9.1	417	0.1	0.5	0.5	98
1041323	Drill Core	6.67	0.024	7.3	879.8	8.6	31	0.7	22.6	8.3	243	2.55	10	1.8	<0.1	10.4	446	0.3	0.6	0.2	73
1041324	Drill Core	3.93	<0.005	1.0	36.6	3.2	91	0.1	31.5	43.0	1140	6.94	105	0.6	<0.1	0.8	510	0.3	2.4	<0.1	225
1041325	Drill Core	5.30	0.054	18.8	1497	7.0	31	1.2	23.8	8.3	248	2.97	8	3.5	0.1	8.7	488	0.1	0.6	0.1	91
1041326	Drill Core	6.50	0.257	7.4	4182	11.3	33	2.0	20.3	8.5	218	2.56	11	2.5	0.3	12.1	458	<0.1	0.6	0.2	71
1041327	Drill Core	4.41	<0.005	1.6	74.0	4.0	94	0.1	31.7	42.1	1096	7.02	85	0.8	<0.1	1.3	434	0.3	2.2	<0.1	223
1041328	Drill Core	4.15	0.015	3.2	458.4	8.4	37	0.4	22.4	8.9	299	3.09	10	2.5	<0.1	9.6	353	<0.1	0.7	0.2	87
1041329	Drill Core	7.74	<0.005	3.4	119.2	10.3	42	0.2	19.8	9.8	353	2.68	10	2.5	<0.1	10.4	410	0.2	0.8	<0.1	74
1041330	Drill Core	4.98	0.008	6.0	468.5	8.9	40	<0.1	22.0	8.8	322	2.73	9	2.5	<0.1	9.0	354	<0.1	0.7	0.2	77

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 2 of 7 Part 2

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041301	Drill Core	1.75	0.055	7.0	29	1.14	482	0.325	7.59	3.436	1.35	1.6	19.8	15	3.0	5.8	3.2	0.2	<1	8	24.2
1041302	Drill Core	1.23	0.052	6.4	27	1.14	457	0.305	8.33	3.594	1.43	0.9	22.3	13	2.2	6.4	2.9	0.2	<1	8	24.5
1041303	Drill Core	1.55	0.054	6.8	29	1.11	434	0.319	8.39	3.528	1.31	0.8	20.4	14	2.1	5.9	3.4	0.3	<1	8	25.8
1041304	Drill Core	1.44	0.044	7.9	29	1.10	416	0.325	8.29	3.403	1.30	2.1	19.3	15	2.5	5.6	3.1	0.3	<1	7	25.0
1041305	Drill Core	1.29	0.050	8.1	29	1.10	399	0.333	8.38	3.349	1.40	2.4	19.0	17	2.3	5.7	3.2	0.3	<1	7	25.7
1041306	Drill Core	0.55	0.046	10.8	25	1.21	192	0.283	7.96	3.389	1.33	2.5	12.9	20	2.0	7.9	2.6	0.2	<1	8	27.0
1041307	Drill Core	1.36	0.054	18.7	30	1.12	391	0.324	8.54	3.451	1.44	2.0	20.3	40	2.1	7.0	3.4	0.3	1	8	26.0
1041308	Drill Core	1.16	0.056	6.6	28	1.13	349	0.319	8.16	3.639	1.35	2.6	18.3	14	1.7	6.3	3.0	0.3	1	9	26.3
1041309	Drill Core	1.69	0.052	6.4	28	1.10	424	0.298	7.57	3.479	1.19	1.7	15.8	13	2.1	5.2	3.0	0.3	<1	7	24.7
1041310	Drill Core	1.86	0.061	6.7	30	1.13	434	0.318	8.25	3.495	1.25	2.1	14.6	13	1.9	5.5	3.1	0.3	1	8	26.0
1041311	Drill Core	1.50	0.050	9.5	26	1.06	415	0.293	8.02	3.483	1.25	1.5	13.5	21	1.9	5.4	2.9	0.2	1	8	24.2
1041312	Drill Core	1.94	0.057	7.8	29	1.07	413	0.306	8.13	3.348	1.26	1.6	12.5	17	1.9	5.4	2.8	0.3	<1	9	23.4
1041313	Drill Core	1.37	0.054	8.9	29	1.17	365	0.302	6.94	3.368	1.26	3.3	11.7	18	2.2	5.2	2.9	0.3	<1	9	23.1
1041314	Drill Core	1.67	0.050	6.0	31	0.96	397	0.286	7.07	3.402	1.25	2.0	11.1	12	1.7	4.9	2.9	0.3	<1	7	20.5
1041315	Drill Core	1.08	0.048	7.0	28	1.00	365	0.289	8.00	3.749	1.31	11.2	13.8	13	2.4	5.9	3.0	0.3	1	7	21.0
1041316	Drill Core	1.46	0.051	6.3	30	1.01	383	0.296	8.02	3.421	1.33	2.1	12.8	13	2.0	6.6	3.3	0.3	1	8	22.2
1041317	Drill Core	1.59	0.049	6.7	31	0.95	355	0.303	7.47	3.443	1.15	0.6	11.8	13	2.2	8.0	3.1	0.3	1	8	22.5
1041318	Drill Core	4.70	0.123	12.7	31	2.41	562	1.153	8.52	2.553	0.71	0.3	154.4	30	1.7	26.8	7.6	0.5	1	27	67.1
1041319	Drill Core	1.86	0.050	7.4	30	0.98	398	0.315	8.26	3.430	1.23	0.6	13.2	17	2.5	11.9	3.7	0.3	1	10	22.7
1041320	Rock Pulp	1.61	0.077	29.1	105	0.95	95	0.214	6.85	0.793	3.38	18.6	26.1	54	4.0	11.6	3.1	0.2	2	11	14.6
1041321	Drill Core	1.81	0.050	12.1	30	0.96	422	0.309	8.05	3.422	1.22	0.8	11.9	28	2.2	10.5	3.3	0.3	<1	10	22.6
1041322	Drill Core	1.31	0.050	6.6	32	0.96	388	0.287	7.85	3.445	1.35	0.9	17.2	13	2.2	8.9	3.2	0.3	<1	8	20.4
1041323	Drill Core	1.70	0.055	7.0	27	0.99	387	0.299	8.35	3.629	1.36	0.8	15.2	16	2.2	9.5	3.3	0.3	1	11	22.9
1041324	Drill Core	6.95	0.135	13.8	33	2.27	175	1.275	8.27	2.014	0.37	0.4	177.2	35	1.8	32.2	8.5	0.5	1	29	91.6
1041325	Drill Core	1.77	0.044	5.7	28	0.91	330	0.289	7.80	3.561	1.12	2.3	10.9	12	2.0	9.5	2.9	0.3	1	7	21.6
1041326	Drill Core	1.49	0.039	22.1	27	1.02	365	0.286	7.67	3.480	1.29	1.3	13.1	63	3.9	26.4	4.5	0.4	1	11	21.6
1041327	Drill Core	6.17	0.125	13.1	31	2.34	199	1.226	8.50	2.283	0.41	0.5	164.9	32	1.4	29.8	8.2	0.5	2	29	83.3
1041328	Drill Core	0.85	0.045	5.3	29	1.00	374	0.287	7.47	3.685	1.46	2.4	14.7	12	2.1	8.1	3.1	0.3	1	8	21.4
1041329	Drill Core	1.67	0.045	9.4	29	0.95	719	0.291	7.79	3.163	2.14	1.5	16.6	22	1.7	10.9	3.5	0.3	1	9	18.7
1041330	Drill Core	0.95	0.040	5.6	28	0.96	362	0.284	7.88	3.778	1.55	3.6	12.8	11	2.2	10.4	3.3	0.3	1	9	19.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 2 of 7 Part 3

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041301	Drill Core	0.3	71.2	0.8
1041302	Drill Core	0.1	92.5	0.9
1041303	Drill Core	0.3	80.7	0.7
1041304	Drill Core	0.5	82.2	0.6
1041305	Drill Core	0.5	87.8	0.7
1041306	Drill Core	0.6	110.8	0.4
1041307	Drill Core	0.4	89.4	0.8
1041308	Drill Core	0.4	88.4	0.7
1041309	Drill Core	0.2	65.9	0.6
1041310	Drill Core	0.4	79.4	0.6
1041311	Drill Core	0.2	82.5	0.5
1041312	Drill Core	0.2	80.0	0.5
1041313	Drill Core	0.3	80.8	0.5
1041314	Drill Core	0.2	80.5	0.5
1041315	Drill Core	0.2	84.5	0.6
1041316	Drill Core	0.1	87.6	0.5
1041317	Drill Core	0.3	79.8	0.5
1041318	Drill Core	<0.1	46.6	3.6
1041319	Drill Core	<0.1	71.8	0.5
1041320	Rock Pulp	2.6	127.5	0.8
1041321	Drill Core	<0.1	72.8	0.4
1041322	Drill Core	0.2	88.9	0.7
1041323	Drill Core	<0.1	80.4	0.6
1041324	Drill Core	0.2	36.8	4.4
1041325	Drill Core	0.2	71.8	0.4
1041326	Drill Core	0.4	83.3	0.6
1041327	Drill Core	0.2	31.8	3.5
1041328	Drill Core	<0.1	96.3	0.6
1041329	Drill Core	<0.1	93.7	0.6
1041330	Drill Core	<0.1	98.3	0.5



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 3 of 7 Part 1

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041331	Drill Core	5.17	<0.005	28.2	663.7	8.7	39	0.2	22.2	9.8	260	3.22	10	1.4	<0.1	8.9	452	<0.1	0.6	0.1	93
1041332	Drill Core	7.63	0.029	3.1	1226	7.6	35	0.5	21.0	8.8	230	2.82	10	1.7	<0.1	9.0	463	<0.1	0.6	0.1	97
1041333	Drill Core	1.09	<0.005	1.1	165.8	10.9	69	0.2	29.7	32.6	489	5.03	37	6.8	<0.1	1.0	535	1.0	3.5	<0.1	236
1041334	Drill Core	5.96	0.059	3.5	1561	7.5	37	0.6	22.4	8.1	228	2.60	10	1.1	<0.1	8.9	439	0.3	0.8	0.5	105
1041335	Drill Core	4.84	0.018	2.9	493.4	6.2	45	0.2	17.9	8.0	365	2.48	7	5.5	<0.1	8.6	333	0.2	0.8	0.2	74
1041336	Drill Core	8.05	0.009	2.8	249.7	7.9	42	<0.1	19.8	8.9	286	2.52	9	1.5	<0.1	8.8	433	0.1	0.7	0.2	70
1041337	Drill Core	7.68	<0.005	2.1	290.9	7.1	28	0.1	13.9	7.0	206	2.39	8	1.3	<0.1	9.5	445	0.2	0.6	0.2	62
1041338	Drill Core	7.86	0.075	2.5	562.7	7.3	32	0.4	17.7	7.4	206	2.49	7	1.7	<0.1	9.9	432	0.1	0.7	0.2	69
1041339	Drill Core	6.70	0.015	4.3	700.0	6.1	28	0.4	16.2	6.6	179	2.50	5	1.5	<0.1	10.1	461	<0.1	0.6	0.2	74
1041340	Rock	0.24	<0.005	0.8	18.9	30.0	3	<0.1	0.3	0.4	27	0.20	9	2.0	<0.1	0.2	4340	<0.1	0.2	<0.1	4
1041341	Drill Core	7.84	<0.005	3.4	236.8	7.3	29	0.1	16.1	6.9	218	2.48	7	2.1	<0.1	9.2	324	<0.1	0.7	<0.1	68
1041342	Drill Core	6.09	<0.005	4.9	123.1	6.5	29	<0.1	17.3	7.7	202	2.54	7	1.8	<0.1	9.1	398	0.1	0.7	0.2	72
1041343	Drill Core	6.54	<0.005	2.8	243.8	7.2	39	0.1	18.2	7.5	224	2.48	7	1.7	<0.1	8.5	388	0.2	0.8	0.2	70
1041344	Drill Core	2.88	<0.005	1.0	46.8	10.5	61	<0.1	17.8	9.4	481	2.70	16	1.3	<0.1	2.1	551	0.2	1.4	<0.1	70
1041345	Drill Core	4.51	<0.005	5.9	101.5	7.4	29	<0.1	12.3	6.2	208	1.87	6	1.8	<0.1	8.4	325	<0.1	0.6	<0.1	54
1041346	Drill Core	5.53	<0.005	9.1	66.0	10.2	45	<0.1	13.6	7.2	230	2.29	7	2.0	<0.1	9.3	414	0.2	0.7	<0.1	61
1041347	Drill Core	8.12	0.044	12.7	252.8	8.2	37	0.1	15.7	8.1	257	2.37	11	1.6	<0.1	8.3	365	<0.1	0.8	0.2	61
1041348	Drill Core	5.85	0.043	9.5	531.4	6.0	43	0.1	20.9	13.5	449	3.63	29	1.6	<0.1	6.9	446	0.1	1.2	0.2	94
1041349	Drill Core	1.99	<0.005	1.4	49.3	3.0	73	0.1	29.9	39.0	1260	6.72	79	0.5	<0.1	2.0	496	0.2	3.5	<0.1	188
1041350	Drill Core	7.40	<0.005	1.8	123.1	5.5	80	0.1	30.7	36.0	986	6.82	138	4.9	<0.1	2.0	438	0.1	3.1	<0.1	190
1041351	Drill Core	7.64	<0.005	1.6	38.6	9.1	46	<0.1	17.9	8.4	360	2.40	26	1.3	<0.1	1.5	609	0.1	0.8	<0.1	69
1041352	Drill Core	3.04	0.014	23.7	324.6	6.4	33	<0.1	19.5	7.7	251	2.39	9	1.7	<0.1	9.4	367	<0.1	0.6	<0.1	68
1041353	Drill Core	5.97	<0.005	2.0	76.5	9.6	43	<0.1	16.1	8.0	365	2.45	26	1.4	<0.1	2.4	659	<0.1	0.9	<0.1	69
1041354	Drill Core	8.02	<0.005	0.3	50.8	8.0	49	0.1	18.4	8.8	407	2.65	22	1.3	<0.1	2.3	693	<0.1	0.8	<0.1	71
1041355	Drill Core	5.45	<0.005	0.5	39.4	11.6	45	<0.1	18.9	8.6	372	2.29	23	1.2	<0.1	2.2	685	0.2	0.8	<0.1	68
1041356	Drill Core	4.94	0.014	7.1	135.2	6.4	27	<0.1	23.2	10.1	302	2.55	11	2.0	<0.1	9.1	396	<0.1	0.8	<0.1	72
1041357	Drill Core	5.69	0.009	4.8	104.3	5.7	30	<0.1	22.7	9.2	279	2.58	7	1.8	<0.1	9.2	394	<0.1	0.6	<0.1	76
1041358	Drill Core	8.92	<0.005	6.0	58.9	7.2	32	<0.1	20.0	8.5	283	2.49	8	2.0	<0.1	9.1	421	<0.1	0.4	<0.1	68
1041359	Drill Core	2.77	0.008	5.7	40.6	7.9	29	<0.1	15.9	7.6	214	2.07	9	1.7	<0.1	8.7	412	<0.1	0.5	<0.1	60
1041360	Drill Core	2.99	0.006	4.8	45.2	8.0	26	<0.1	16.8	7.2	204	2.05	8	1.6	<0.1	7.9	408	0.1	0.5	<0.1	59



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 3 of 7 Part 2

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041331	Drill Core	1.51	0.050	7.8	31	1.02	418	0.307	7.84	3.508	1.35	0.6	10.8	18	2.0	7.7	3.0	0.3	<1	9	20.4
1041332	Drill Core	1.58	0.047	8.2	28	0.95	394	0.294	6.99	3.459	1.27	0.9	9.9	18	2.2	8.9	3.1	0.3	1	7	19.6
1041333	Drill Core	2.07	0.157	11.0	43	2.05	271	1.473	8.44	3.302	0.63	3.2	75.9	29	1.8	22.4	9.1	0.6	1	22	92.5
1041334	Drill Core	1.26	0.038	9.4	24	0.97	319	0.256	6.78	3.617	1.12	0.5	11.5	10	1.7	4.4	2.2	0.2	1	5	18.7
1041335	Drill Core	1.07	0.039	7.0	25	0.85	529	0.250	7.30	2.763	1.93	3.9	14.5	14	1.7	11.6	2.7	0.2	1	7	22.4
1041336	Drill Core	1.31	0.041	8.6	25	0.95	563	0.248	7.18	3.474	1.74	1.7	12.5	20	1.8	9.7	3.0	0.2	<1	7	15.6
1041337	Drill Core	1.69	0.038	11.2	21	0.82	393	0.243	7.09	3.347	1.29	1.4	12.0	32	3.1	18.0	3.4	0.3	1	8	15.3
1041338	Drill Core	1.41	0.044	9.9	22	0.84	385	0.243	7.14	3.544	1.34	0.8	12.6	28	2.9	15.0	3.6	0.3	<1	7	16.0
1041339	Drill Core	1.51	0.035	11.0	23	0.82	276	0.254	7.27	3.721	0.98	0.8	11.6	32	3.6	20.7	3.8	0.3	<1	8	16.6
1041340	Rock	35.72	0.006	1.3	<1	1.41	33	0.019	0.41	0.050	0.07	0.1	2.9	2	26.4	1.3	0.3	<0.1	<1	<1	1.1
1041341	Drill Core	1.01	0.037	8.3	24	0.83	471	0.244	7.18	3.382	1.75	1.2	11.5	22	2.3	12.7	3.3	0.3	<1	7	17.8
1041342	Drill Core	1.02	0.041	6.9	23	0.86	426	0.255	7.17	3.346	1.43	0.8	11.1	18	1.9	8.3	2.8	0.3	1	7	17.4
1041343	Drill Core	0.93	0.041	9.5	26	0.87	412	0.250	7.36	3.696	1.47	1.0	9.5	24	1.7	10.2	3.0	0.3	<1	7	19.7
1041344	Drill Core	0.42	0.059	10.4	10	0.67	973	0.279	8.31	4.410	2.48	1.7	48.3	24	0.7	15.0	2.7	0.2	1	8	35.4
1041345	Drill Core	0.62	0.033	7.6	19	0.64	638	0.203	6.93	3.353	2.37	1.2	12.7	18	1.3	7.7	2.5	0.2	<1	5	17.6
1041346	Drill Core	0.88	0.041	8.7	22	0.70	735	0.242	7.45	3.327	2.71	2.3	12.7	20	1.7	8.8	3.0	0.3	<1	6	19.3
1041347	Drill Core	1.27	0.038	7.8	22	0.85	682	0.239	7.28	3.381	2.57	1.9	10.6	18	1.9	8.6	2.9	0.2	<1	6	34.0
1041348	Drill Core	2.04	0.057	9.3	27	1.41	731	0.405	7.59	3.019	1.83	1.4	24.1	23	1.8	11.5	3.6	0.3	<1	11	55.4
1041349	Drill Core	5.65	0.115	12.3	32	3.37	207	0.997	8.26	2.460	0.34	0.4	151.9	31	1.6	22.8	7.0	0.5	1	25	67.4
1041350	Drill Core	4.53	0.126	13.7	29	3.38	369	1.044	8.42	2.659	0.64	2.0	149.6	33	1.2	24.1	7.6	0.5	<1	26	108.7
1041351	Drill Core	0.58	0.057	8.7	8	0.75	1007	0.262	7.77	4.665	1.82	1.6	51.5	20	0.5	6.6	2.5	0.2	2	6	39.3
1041352	Drill Core	0.69	0.043	7.8	23	1.02	279	0.250	7.39	4.313	1.05	1.6	11.1	16	1.6	6.0	2.7	0.3	<1	7	26.2
1041353	Drill Core	0.49	0.062	9.0	10	0.63	1088	0.265	8.24	4.604	2.28	1.5	65.1	21	0.6	8.6	2.7	0.2	1	6	28.2
1041354	Drill Core	0.46	0.061	12.3	9	0.73	1201	0.279	8.50	4.875	2.41	1.6	76.2	27	0.6	9.7	2.6	0.2	1	7	29.9
1041355	Drill Core	0.81	0.057	11.6	8	0.76	1056	0.260	8.24	4.933	1.89	0.7	73.3	26	0.7	7.2	2.5	0.2	1	6	30.0
1041356	Drill Core	2.48	0.049	8.6	28	1.03	368	0.284	7.70	3.451	1.57	1.7	11.8	20	2.1	8.9	2.9	0.2	1	9	25.7
1041357	Drill Core	2.06	0.051	7.4	27	0.98	358	0.284	7.87	3.650	1.13	1.4	12.0	20	2.7	10.1	3.0	0.3	<1	8	23.3
1041358	Drill Core	1.98	0.043	7.5	23	1.04	466	0.250	7.61	3.699	1.41	0.9	11.9	19	2.0	9.9	3.0	0.3	<1	8	22.8
1041359	Drill Core	1.88	0.040	6.5	22	0.84	638	0.220	7.46	3.347	1.90	0.8	12.4	15	1.3	6.6	2.8	0.2	<1	6	18.4
1041360	Drill Core	1.76	0.038	6.1	20	0.84	569	0.220	7.21	3.315	1.78	0.9	12.7	14	1.1	5.9	2.6	0.2	<1	6	19.1



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 3 of 7 **Part** 3

CERTIFICATE OF ANALYSIS

VAN11005878.1

	Method	1EX	1EX	1EX
	Analyte	S	Rb	Hf
	Unit	%	ppm	ppm
	MDL	0.1	0.1	0.1
1041331	Drill Core	<0.1	80.4	0.5
1041332	Drill Core	0.1	72.0	0.4
1041333	Drill Core	0.2	36.8	1.9
1041334	Drill Core	0.2	74.7	0.5
1041335	Drill Core	<0.1	124.9	0.6
1041336	Drill Core	<0.1	93.7	0.5
1041337	Drill Core	<0.1	84.0	0.5
1041338	Drill Core	<0.1	88.5	0.6
1041339	Drill Core	<0.1	77.4	0.7
1041340	Rock	0.1	4.4	0.2
1041341	Drill Core	<0.1	101.5	0.6
1041342	Drill Core	<0.1	90.1	0.5
1041343	Drill Core	<0.1	91.9	0.4
1041344	Drill Core	<0.1	127.8	1.5
1041345	Drill Core	<0.1	89.9	0.6
1041346	Drill Core	<0.1	106.1	0.5
1041347	Drill Core	<0.1	103.2	0.5
1041348	Drill Core	0.1	75.7	0.9
1041349	Drill Core	0.1	22.2	3.6
1041350	Drill Core	0.3	35.0	3.7
1041351	Drill Core	<0.1	73.5	1.4
1041352	Drill Core	<0.1	76.9	0.5
1041353	Drill Core	<0.1	93.4	1.8
1041354	Drill Core	<0.1	90.1	2.1
1041355	Drill Core	<0.1	81.2	1.9
1041356	Drill Core	<0.1	109.3	0.6
1041357	Drill Core	<0.1	103.1	0.6
1041358	Drill Core	<0.1	85.9	0.6
1041359	Drill Core	<0.1	84.1	0.6
1041360	Drill Core	<0.1	83.3	0.4



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 4 of 7 Part 1

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041361	Drill Core	5.14	<0.005	10.2	21.8	8.1	29	<0.1	17.2	7.7	220	2.19	7	1.5	<0.1	8.5	368	<0.1	0.6	<0.1	63
1041362	Drill Core	7.19	0.013	17.6	465.9	8.1	30	<0.1	17.1	7.1	205	2.03	8	1.5	<0.1	8.7	315	<0.1	0.5	<0.1	59
1041363	Drill Core	7.65	0.057	7.7	70.9	9.2	32	<0.1	14.8	7.9	224	2.13	8	1.7	<0.1	8.6	395	<0.1	0.6	0.1	57
1041364	Drill Core	6.91	<0.005	8.0	183.0	9.5	33	0.1	15.5	7.7	225	2.46	10	1.7	<0.1	9.2	417	0.1	0.6	<0.1	65
1041365	Drill Core	7.86	<0.005	5.9	90.7	7.6	31	<0.1	15.9	8.2	225	2.52	8	1.4	<0.1	8.7	311	0.1	0.6	<0.1	62
1041366	Drill Core	8.31	<0.005	5.1	32.6	6.7	30	<0.1	14.8	7.2	247	2.08	7	1.9	<0.1	9.1	350	<0.1	0.7	<0.1	57
1041367	Drill Core	7.23	0.010	18.7	159.6	9.0	31	<0.1	18.8	7.8	236	2.14	8	2.3	<0.1	7.3	345	0.2	0.8	0.4	61
1041368	Drill Core	7.60	0.018	19.8	420.1	9.8	29	0.2	19.3	8.0	224	2.14	12	1.3	<0.1	6.7	268	<0.1	0.9	0.3	65
1041369	Drill Core	7.08	0.031	10.8	64.0	8.9	30	<0.1	17.0	8.0	242	2.48	8	2.2	<0.1	7.8	447	0.2	0.7	0.3	66
1041370	Drill Core	7.84	0.013	4.7	34.8	8.0	28	<0.1	17.1	7.6	199	2.23	8	1.9	<0.1	7.3	446	0.1	0.5	0.2	61
1041371	Drill Core	8.05	<0.005	4.0	132.6	9.5	34	<0.1	18.1	9.1	237	2.62	8	1.5	<0.1	7.3	384	0.1	0.6	0.1	76
1041372	Drill Core	7.95	<0.005	1.5	96.0	7.6	36	<0.1	19.7	10.2	255	2.55	9	1.8	<0.1	7.4	493	<0.1	0.7	0.1	92
1041373	Drill Core	7.41	0.009	3.1	33.3	9.7	37	<0.1	18.7	9.6	308	2.52	6	2.0	<0.1	7.5	417	0.1	0.6	0.1	79
1041374	Drill Core	8.33	<0.005	3.4	37.0	10.4	35	<0.1	19.7	9.2	295	2.51	7	2.2	<0.1	6.7	462	<0.1	0.6	<0.1	79
1041375	Drill Core	8.46	<0.005	3.3	14.1	9.5	45	<0.1	17.3	8.7	316	2.17	10	1.6	<0.1	9.0	472	<0.1	0.9	<0.1	72
1041376	Drill Core	7.09	<0.005	2.8	13.1	9.5	32	<0.1	18.3	8.2	265	2.42	12	1.7	<0.1	9.2	500	0.1	0.5	<0.1	73
1041377	Drill Core	8.12	<0.005	4.3	41.6	9.4	31	<0.1	16.3	8.2	291	2.36	5	2.3	<0.1	6.9	439	<0.1	0.5	0.1	68
1041378	Drill Core	7.73	<0.005	5.1	53.7	8.0	32	<0.1	16.3	7.4	262	2.20	7	3.5	<0.1	7.9	397	0.1	0.6	0.1	62
1041379	Drill Core	7.76	0.008	3.9	41.0	9.2	30	<0.1	15.1	7.4	259	2.16	7	2.8	<0.1	8.8	446	<0.1	0.6	<0.1	61
1041380	Rock Pulp	0.08	1.351	268.6	9537	78.7	127	4.8	32.2	20.1	366	4.79	34	5.0	2.0	10.7	192	2.4	19.9	3.3	95
1041381	Drill Core	7.37	0.008	4.5	182.0	8.4	35	<0.1	16.4	7.9	265	2.14	7	2.0	<0.1	8.2	366	<0.1	1.0	<0.1	61
1041382	Drill Core	7.35	0.008	4.2	251.6	8.9	40	0.1	18.3	8.6	282	2.45	8	1.9	<0.1	8.3	419	<0.1	0.9	<0.1	71
1041383	Drill Core	7.66	0.011	4.0	196.0	8.3	34	0.3	16.4	8.7	257	2.12	8	2.4	<0.1	9.3	354	<0.1	1.0	<0.1	60
1041384	Drill Core	4.35	0.007	5.0	86.6	7.8	40	0.2	20.5	11.4	358	2.61	7	2.6	<0.1	6.6	395	0.1	0.4	0.2	94
1041385	Drill Core	4.49	0.009	1.6	92.1	7.2	35	0.1	21.3	11.9	329	2.69	7	2.9	<0.1	7.5	402	<0.1	0.4	<0.1	95
1041386	Drill Core	4.77	<0.005	26.5	189.6	7.3	37	0.7	22.3	11.9	327	2.72	9	3.4	<0.1	7.7	428	<0.1	0.4	0.1	103
1041387	Drill Core	4.33	0.169	89.7	1327	7.0	36	0.8	24.0	9.4	219	1.80	8	3.2	<0.1	8.4	470	<0.1	0.7	0.4	85
1041388	Drill Core	3.53	0.303	29.8	1414	5.6	32	2.0	25.5	12.0	228	1.86	9	2.5	<0.1	8.6	425	<0.1	0.6	0.3	89
1041389	Drill Core	6.14	0.093	87.7	1681	6.2	26	1.1	26.2	9.0	162	1.58	6	4.5	<0.1	8.3	431	<0.1	0.4	0.2	74
1041390	Drill Core	6.71	0.125	60.8	2482	6.2	23	2.0	25.5	8.4	144	1.59	7	3.3	<0.1	8.0	453	0.1	0.4	0.4	69

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 4 of 7 Part 2

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041361	Drill Core	1.67	0.040	6.2	20	0.89	636	0.225	7.23	3.210	1.99	0.9	12.2	14	1.5	6.6	2.9	0.3	<1	6	19.5
1041362	Drill Core	0.87	0.038	6.6	19	0.82	500	0.225	7.12	3.520	1.64	1.8	12.0	14	1.2	5.1	2.7	0.2	<1	6	18.2
1041363	Drill Core	1.40	0.038	7.4	20	0.84	665	0.212	7.35	3.118	2.31	1.3	11.2	16	1.4	7.0	2.9	0.2	<1	6	21.0
1041364	Drill Core	1.49	0.039	9.5	22	0.84	541	0.231	7.34	3.601	1.54	1.0	13.7	21	1.6	8.6	3.0	0.3	<1	6	22.0
1041365	Drill Core	1.62	0.040	7.8	22	0.96	367	0.223	7.51	3.679	1.26	1.4	10.7	18	1.6	8.7	3.2	0.3	1	6	21.3
1041366	Drill Core	1.91	0.036	8.5	19	0.81	612	0.214	7.26	3.229	2.37	2.0	11.8	20	1.1	8.6	3.0	0.3	<1	6	19.4
1041367	Drill Core	2.08	0.042	7.4	22	0.78	822	0.241	7.75	2.947	2.24	2.6	10.7	13	1.4	6.3	2.9	0.3	1	7	21.3
1041368	Drill Core	2.27	0.042	5.3	18	0.84	672	0.251	7.73	3.138	1.94	2.1	7.1	13	1.6	6.5	2.9	0.3	<1	7	22.9
1041369	Drill Core	2.38	0.039	7.8	20	0.83	894	0.233	6.94	2.919	2.30	0.9	10.4	14	1.5	7.9	2.7	0.3	<1	6	27.9
1041370	Drill Core	2.16	0.040	5.9	20	0.82	831	0.224	6.89	3.044	2.30	0.5	10.9	13	1.5	7.1	2.7	0.3	<1	6	27.3
1041371	Drill Core	2.01	0.043	7.1	23	0.99	479	0.252	6.99	3.290	1.61	0.7	10.1	19	2.4	11.6	2.9	0.2	<1	7	27.8
1041372	Drill Core	2.30	0.050	10.0	29	1.29	303	0.310	7.23	3.465	1.10	0.5	10.1	35	4.0	24.2	3.4	0.3	<1	9	30.0
1041373	Drill Core	2.61	0.047	7.6	26	1.10	623	0.278	6.86	2.932	1.73	0.7	9.3	19	1.6	10.6	2.8	0.2	<1	8	31.9
1041374	Drill Core	2.45	0.046	6.9	28	1.05	767	0.294	6.98	3.024	1.70	0.7	9.9	18	1.8	10.6	2.8	0.2	<1	8	24.8
1041375	Drill Core	1.61	0.039	11.3	23	1.00	572	0.279	7.06	3.382	1.57	1.0	10.7	26	2.5	12.7	3.0	0.3	1	7	23.0
1041376	Drill Core	1.76	0.046	8.1	25	0.96	572	0.291	7.94	3.460	1.61	0.7	11.8	21	2.5	11.8	3.0	0.2	<1	7	25.9
1041377	Drill Core	2.07	0.042	7.5	22	1.00	838	0.249	6.78	2.946	2.41	0.7	11.7	17	1.1	8.7	2.8	0.2	1	7	21.8
1041378	Drill Core	1.94	0.038	6.0	21	0.89	789	0.230	6.87	3.163	2.14	1.0	12.6	15	1.5	8.5	2.6	0.2	1	6	26.1
1041379	Drill Core	1.84	0.037	7.6	18	0.85	842	0.239	6.57	2.982	2.62	1.1	13.9	20	1.7	9.1	3.1	0.3	1	6	22.8
1041380	Rock Pulp	1.49	0.075	28.8	96	0.94	84	0.207	6.65	0.742	3.13	18.8	24.8	53	3.7	11.0	2.9	0.2	2	10	13.3
1041381	Drill Core	1.96	0.040	6.0	22	0.79	786	0.246	6.51	2.916	2.42	1.7	11.5	15	1.5	8.2	2.8	0.3	1	6	20.1
1041382	Drill Core	1.85	0.045	7.2	20	0.95	682	0.254	6.70	3.240	2.13	1.2	10.4	18	1.6	9.7	3.0	0.3	1	6	21.7
1041383	Drill Core	1.95	0.037	7.9	21	0.82	722	0.239	6.71	2.858	2.52	5.7	10.8	20	1.4	9.5	3.2	0.3	1	6	23.5
1041384	Drill Core	2.40	0.048	9.0	27	1.25	593	0.350	7.02	2.783	2.20	0.9	11.3	22	1.3	11.8	3.4	0.3	<1	9	23.7
1041385	Drill Core	2.33	0.051	9.6	30	1.24	622	0.359	7.01	2.857	1.89	1.0	11.7	22	1.5	12.7	3.7	0.3	1	9	24.3
1041386	Drill Core	2.36	0.051	10.5	29	1.32	605	0.379	7.34	2.917	2.07	2.2	13.9	23	1.6	12.3	3.7	0.3	1	10	24.3
1041387	Drill Core	1.54	0.049	6.9	28	1.10	432	0.312	8.19	3.583	1.41	0.9	22.9	14	1.9	6.5	3.2	0.3	<1	7	26.6
1041388	Drill Core	1.48	0.050	6.5	26	1.12	456	0.315	8.11	3.499	1.38	1.4	22.3	13	2.1	6.0	3.2	0.3	<1	8	26.7
1041389	Drill Core	1.24	0.050	5.9	24	1.12	422	0.299	6.89	3.393	1.28	0.9	18.4	12	1.7	5.8	3.1	0.3	1	6	23.9
1041390	Drill Core	1.69	0.049	5.5	23	1.10	387	0.294	6.62	3.431	1.13	0.6	15.1	11	1.4	4.8	2.9	0.3	1	6	23.9



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 4 of 7 Part 3

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041361	Drill Core	<0.1	93.2	0.5
1041362	Drill Core	<0.1	96.1	0.4
1041363	Drill Core	<0.1	97.2	0.5
1041364	Drill Core	<0.1	96.1	0.6
1041365	Drill Core	<0.1	89.2	0.6
1041366	Drill Core	<0.1	103.0	0.5
1041367	Drill Core	<0.1	82.6	0.6
1041368	Drill Core	<0.1	95.8	0.4
1041369	Drill Core	<0.1	80.1	0.5
1041370	Drill Core	<0.1	73.8	0.6
1041371	Drill Core	<0.1	68.9	0.5
1041372	Drill Core	<0.1	59.8	0.5
1041373	Drill Core	<0.1	53.8	0.4
1041374	Drill Core	<0.1	54.6	0.5
1041375	Drill Core	<0.1	70.1	0.5
1041376	Drill Core	<0.1	69.4	0.5
1041377	Drill Core	<0.1	67.5	0.6
1041378	Drill Core	<0.1	67.0	0.6
1041379	Drill Core	<0.1	78.2	0.6
1041380	Rock Pulp	2.5	108.1	0.8
1041381	Drill Core	<0.1	81.8	0.6
1041382	Drill Core	<0.1	74.9	0.5
1041383	Drill Core	<0.1	82.6	0.5
1041384	Drill Core	<0.1	67.6	0.5
1041385	Drill Core	<0.1	62.7	0.5
1041386	Drill Core	<0.1	68.1	0.6
1041387	Drill Core	0.1	81.0	0.8
1041388	Drill Core	0.2	75.4	0.8
1041389	Drill Core	0.2	77.3	0.6
1041390	Drill Core	0.3	66.3	0.6



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 5 of 7 Part 1

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041391	Drill Core	7.74	0.117	61.0	1782	7.9	24	1.3	25.1	8.9	143	1.50	10	2.9	0.1	8.0	449	<0.1	0.5	0.4	66
1041392	Drill Core	6.52	0.078	38.0	668.5	7.0	29	1.5	24.2	9.0	167	1.54	10	6.2	2.4	8.6	451	<0.1	0.5	0.2	71
1041393	Drill Core	7.31	0.039	183.6	812.1	4.8	31	0.3	24.6	7.9	168	1.52	8	4.6	<0.1	8.9	443	<0.1	0.6	0.2	69
1041394	Drill Core	6.39	0.089	105.0	658.4	9.9	31	0.6	24.6	9.4	170	1.50	7	8.9	<0.1	8.9	343	0.1	0.9	0.6	68
1041395	Drill Core	5.56	0.066	89.9	1666	6.2	36	0.7	26.9	8.9	179	1.66	6	2.8	<0.1	8.6	358	<0.1	0.6	0.4	68
1041396	Drill Core	7.72	0.111	170.9	2473	10.9	29	1.1	26.6	9.5	181	1.70	7	3.1	<0.1	6.8	305	0.2	0.6	0.3	68
1041397	Drill Core	6.79	0.043	272.3	1201	4.6	27	0.7	27.1	8.5	156	1.63	5	2.5	<0.1	7.8	398	<0.1	0.3	0.2	65
1041398	Drill Core	7.53	0.053	124.1	1186	5.4	31	0.7	27.8	7.7	165	1.62	5	1.7	<0.1	8.9	419	<0.1	0.4	0.2	71
1041399	Drill Core	6.74	0.021	74.5	1199	6.3	26	0.7	25.0	8.7	159	1.66	8	2.8	<0.1	8.2	412	<0.1	0.4	0.2	75
1041400	Rock	1.09	<0.005	0.5	9.3	<0.1	<1	<0.1	0.2	0.2	23	0.11	<1	1.7	<0.1	<0.1	4361	<0.1	<0.1	<0.1	2
1041401	Drill Core	5.26	0.223	303.1	976.1	19.0	23	0.5	24.6	8.3	160	1.61	6	2.0	<0.1	7.1	371	<0.1	0.4	0.2	65
1041402	Drill Core	4.03	0.025	596.2	81.2	6.5	25	<0.1	21.2	7.7	151	1.44	7	2.3	<0.1	8.5	419	0.2	0.3	<0.1	64
1041403	Drill Core	5.26	0.057	31.7	628.9	10.4	31	0.1	25.9	9.2	210	1.71	7	2.3	<0.1	8.6	428	0.1	0.5	0.2	81
1041404	Drill Core	7.49	0.060	156.3	103.9	8.2	37	<0.1	24.9	8.3	193	1.60	7	5.2	<0.1	8.8	378	<0.1	0.3	<0.1	68
1041405	Drill Core	7.83	0.045	5.9	868.5	12.0	35	0.4	24.9	8.1	196	1.67	11	24.9	<0.1	11.3	440	0.2	0.4	0.4	72
1041406	Drill Core	7.34	0.520	24.0	397.8	8.9	39	0.4	27.3	9.0	207	1.86	9	8.2	<0.1	11.0	423	0.2	0.3	0.2	79
1041407	Drill Core	4.53	0.061	2.3	156.7	9.0	37	0.1	26.8	8.9	212	1.69	9	5.2	<0.1	12.3	441	0.2	0.3	<0.1	72
1041408	Drill Core	4.61	0.101	2.9	367.7	8.9	36	0.3	25.4	9.2	220	1.76	16	2.7	<0.1	11.5	418	0.1	0.4	0.1	71
1041409	Drill Core	5.07	0.039	3.9	921.2	8.8	37	0.4	25.2	9.4	230	1.98	12	3.1	<0.1	11.8	436	<0.1	0.4	<0.1	84
1041410	Drill Core	8.02	0.071	3.4	1828	9.0	40	0.9	32.2	10.8	237	2.44	8	1.3	<0.1	12.8	439	<0.1	0.2	0.2	113
1041411	Drill Core	8.76	0.156	3.6	1453	9.1	40	0.8	28.7	9.7	238	2.92	8	2.0	<0.1	11.8	418	<0.1	0.4	0.1	139
1041412	Drill Core	7.85	0.115	2.2	1867	9.2	36	1.0	29.0	10.4	232	2.41	9	4.4	0.3	11.0	407	<0.1	0.4	0.2	118
1041413	Drill Core	8.58	0.168	2.6	2848	8.8	35	1.3	29.2	10.1	211	2.29	11	2.7	0.1	11.2	393	<0.1	0.4	0.2	114
1041414	Drill Core	7.48	0.069	236.4	1369	7.5	33	0.5	30.4	10.2	217	2.84	9	1.9	<0.1	10.9	405	<0.1	0.3	<0.1	198
1041415	Drill Core	8.01	0.037	11.1	481.1	8.7	34	0.3	30.1	9.7	215	2.70	8	1.5	<0.1	10.6	442	<0.1	0.3	<0.1	203
1041416	Drill Core	6.97	0.039	3.7	405.7	7.3	28	0.2	24.8	9.6	217	1.87	9	1.7	<0.1	11.0	433	<0.1	0.3	<0.1	84
1041417	Drill Core	7.43	0.105	51.4	894.9	7.6	28	0.5	25.0	8.9	203	1.68	10	1.9	<0.1	10.8	427	<0.1	0.3	0.2	72
1041418	Drill Core	7.69	0.024	151.3	767.8	7.3	26	0.3	20.3	7.2	242	1.49	10	2.0	<0.1	10.2	427	<0.1	0.3	0.1	66
1041419	Drill Core	2.80	0.011	256.4	396.5	7.8	30	0.2	19.5	7.3	241	1.39	14	2.0	<0.1	10.1	411	<0.1	0.3	<0.1	63
1041420	Drill Core	2.71	0.039	226.2	455.6	7.7	27	0.2	22.6	7.3	257	1.44	15	2.0	<0.1	10.5	404	<0.1	0.3	<0.1	66

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 5 of 7 Part 2

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041391	Drill Core	1.58	0.061	5.4	23	1.10	403	0.278	7.05	3.408	1.19	0.7	15.3	11	1.2	4.4	2.7	0.2	1	7	28.1
1041392	Drill Core	1.41	0.052	5.6	23	1.16	425	0.304	7.42	3.475	1.19	0.7	15.5	11	1.5	4.3	2.8	0.3	1	7	26.2
1041393	Drill Core	1.47	0.053	6.0	25	1.12	409	0.301	8.07	3.567	1.21	1.0	14.3	11	1.4	4.5	2.7	0.2	1	7	26.6
1041394	Drill Core	0.84	0.043	10.3	25	1.06	326	0.296	8.04	3.633	1.35	3.8	16.5	17	1.8	7.2	2.9	0.3	1	7	23.0
1041395	Drill Core	1.13	0.052	6.3	27	1.06	369	0.319	8.42	3.348	1.37	5.3	16.3	12	1.5	5.0	3.0	0.3	<1	6	25.5
1041396	Drill Core	2.20	0.047	21.9	23	0.89	453	0.298	6.85	3.050	1.27	4.3	11.7	44	1.4	6.3	2.9	0.2	1	7	25.5
1041397	Drill Core	1.29	0.050	8.2	26	1.12	351	0.290	6.67	3.442	1.11	1.1	13.5	17	1.3	4.2	2.5	0.2	1	7	24.8
1041398	Drill Core	1.71	0.041	9.1	24	1.08	394	0.280	6.86	3.415	1.09	0.7	12.9	19	1.5	3.9	2.7	0.2	<1	6	24.3
1041399	Drill Core	1.56	0.050	6.6	25	1.12	371	0.281	6.84	3.441	1.13	1.4	11.8	13	1.5	4.2	2.4	0.2	1	8	25.5
1041400	Rock	39.38	0.005	0.9	<1	1.67	8	0.009	0.15	0.016	0.02	<0.1	1.2	<1	<0.1	0.4	0.2	<0.1	<1	<1	0.4
1041401	Drill Core	1.90	0.052	5.2	26	1.15	372	0.294	6.71	3.388	1.11	0.3	9.3	11	1.5	3.7	2.6	0.3	1	6	23.0
1041402	Drill Core	1.75	0.033	5.7	22	1.10	342	0.280	6.53	3.405	1.09	0.4	10.6	11	1.4	3.7	2.8	0.3	<1	5	24.1
1041403	Drill Core	1.90	0.049	7.6	25	1.11	426	0.303	8.08	3.463	1.32	1.7	11.7	15	1.6	5.8	2.9	0.2	1	7	24.8
1041404	Drill Core	2.07	0.023	9.1	25	1.05	369	0.316	9.89	3.535	1.30	9.8	14.3	14	1.9	7.9	3.4	0.3	1	8	31.6
1041405	Drill Core	2.30	0.028	80.5	26	1.02	432	0.326	9.54	3.626	1.26	6.6	14.0	127	2.7	25.5	4.6	0.5	1	9	25.6
1041406	Drill Core	1.73	0.056	12.1	28	1.24	458	0.316	9.60	3.907	1.36	2.3	13.0	19	2.3	12.2	3.1	0.3	<1	9	30.0
1041407	Drill Core	2.11	0.054	10.0	27	1.15	416	0.307	9.66	3.653	1.22	2.1	14.1	18	2.4	15.6	3.6	0.3	1	10	28.9
1041408	Drill Core	2.27	0.046	6.4	26	1.11	437	0.295	9.58	3.783	1.21	1.4	16.9	11	1.9	7.9	3.2	0.3	<1	10	29.1
1041409	Drill Core	2.13	0.047	8.2	25	1.07	536	0.319	9.97	3.888	1.37	1.5	21.6	14	1.9	6.8	3.3	0.3	<1	8	26.5
1041410	Drill Core	2.53	0.051	44.3	28	1.13	480	0.333	10.76	3.467	1.28	2.5	18.7	88	2.5	9.7	3.1	0.3	1	9	24.6
1041411	Drill Core	2.28	0.048	6.9	29	1.04	461	0.323	9.82	3.511	1.38	7.7	17.0	14	2.5	9.7	3.2	0.3	1	9	25.7
1041412	Drill Core	2.22	0.053	7.1	29	1.13	475	0.322	9.65	3.568	1.58	3.2	14.9	14	2.1	9.2	3.1	0.3	<1	9	30.0
1041413	Drill Core	2.64	0.059	6.7	28	1.20	403	0.310	10.66	3.422	1.42	4.0	14.4	14	2.2	8.7	3.3	0.3	<1	9	30.5
1041414	Drill Core	2.38	0.050	15.5	29	1.19	387	0.331	9.66	3.405	1.24	1.4	13.6	35	2.8	14.8	3.3	0.3	<1	9	30.3
1041415	Drill Core	2.62	0.053	9.1	28	1.17	424	0.328	10.17	3.578	1.28	0.6	14.9	22	3.2	15.9	3.1	0.3	1	9	27.7
1041416	Drill Core	2.53	0.054	12.6	24	1.24	342	0.303	7.65	3.481	1.01	0.7	13.9	35	4.2	24.1	3.7	0.3	<1	9	21.6
1041417	Drill Core	2.68	0.054	11.1	24	1.30	325	0.297	8.03	3.507	0.91	0.5	15.0	32	4.0	29.1	3.8	0.3	<1	9	21.1
1041418	Drill Core	2.98	0.058	12.0	23	1.28	279	0.300	7.23	3.820	0.68	0.5	13.1	38	5.3	36.9	4.2	0.3	1	10	16.6
1041419	Drill Core	2.90	0.056	9.5	23	1.31	253	0.280	7.10	3.787	0.70	0.5	14.0	31	5.5	35.1	4.0	0.3	1	10	18.1
1041420	Drill Core	2.92	0.055	10.1	24	1.35	256	0.298	7.49	3.788	0.71	0.5	13.9	32	5.8	37.4	4.1	0.3	1	11	17.0

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 5 of 7 Part 3

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041391	Drill Core	0.2	71.8	0.6
1041392	Drill Core	<0.1	70.2	0.6
1041393	Drill Core	<0.1	74.5	0.6
1041394	Drill Core	<0.1	87.2	0.6
1041395	Drill Core	0.2	89.6	0.7
1041396	Drill Core	0.3	86.2	0.5
1041397	Drill Core	0.1	61.9	0.4
1041398	Drill Core	0.1	65.0	0.5
1041399	Drill Core	0.1	69.1	0.4
1041400	Rock	<0.1	1.0	<0.1
1041401	Drill Core	0.1	59.4	0.4
1041402	Drill Core	<0.1	66.7	0.5
1041403	Drill Core	<0.1	78.1	0.5
1041404	Drill Core	<0.1	80.6	0.5
1041405	Drill Core	<0.1	72.3	0.6
1041406	Drill Core	<0.1	93.4	0.6
1041407	Drill Core	<0.1	79.6	0.7
1041408	Drill Core	<0.1	68.1	0.7
1041409	Drill Core	<0.1	74.9	0.8
1041410	Drill Core	0.2	74.7	0.7
1041411	Drill Core	0.1	76.5	0.6
1041412	Drill Core	0.2	102.4	0.5
1041413	Drill Core	0.3	88.1	0.5
1041414	Drill Core	0.1	77.6	0.6
1041415	Drill Core	<0.1	72.7	0.6
1041416	Drill Core	<0.1	53.2	0.7
1041417	Drill Core	<0.1	48.9	0.6
1041418	Drill Core	<0.1	29.0	0.7
1041419	Drill Core	<0.1	28.7	0.7
1041420	Drill Core	<0.1	28.8	0.6



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 6 of 7 Part 1

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041421	Drill Core	2.16	0.026	317.0	274.0	7.1	25	0.2	14.5	6.0	232	1.24	5	2.0	<0.1	9.9	407	0.2	0.3	<0.1	54
1041422	Drill Core	4.35	0.019	200.6	515.4	7.4	28	0.1	17.9	7.2	246	1.54	8	2.2	0.1	11.4	416	<0.1	0.3	<0.1	67
1041423	Drill Core	5.16	0.009	410.5	619.5	8.1	30	0.2	19.3	7.7	252	1.61	7	1.8	<0.1	10.1	415	0.2	0.3	<0.1	64
1041424	Drill Core	6.54	0.025	84.5	908.3	7.5	26	0.3	17.7	6.9	248	1.55	4	2.0	<0.1	9.3	409	<0.1	0.2	<0.1	64
1041425	Drill Core	7.59	0.008	123.3	394.7	7.8	32	0.2	20.0	8.8	201	1.74	5	1.5	<0.1	9.7	407	<0.1	0.3	<0.1	84
1041426	Drill Core	4.31	0.006	3.2	269.1	8.4	32	0.1	23.6	10.1	203	1.97	5	1.6	<0.1	11.3	451	<0.1	0.3	<0.1	89
1041427	Drill Core	5.15	<0.005	3.5	249.6	8.3	33	<0.1	20.4	9.7	202	1.95	6	1.8	<0.1	10.4	449	<0.1	0.3	<0.1	97
1041428	Drill Core	5.57	0.010	11.1	23.7	10.6	39	<0.1	24.4	10.7	227	1.90	10	3.3	<0.1	10.0	425	<0.1	0.5	<0.1	97
1041429	Drill Core	7.76	0.020	18.2	27.3	11.7	43	<0.1	24.6	10.1	239	1.83	9	4.6	<0.1	11.4	431	0.1	0.4	<0.1	86
1041430	Drill Core	8.68	<0.005	9.7	23.7	10.6	39	<0.1	22.0	8.7	209	1.59	8	2.5	<0.1	11.0	415	<0.1	0.3	<0.1	77
1041431	Drill Core	7.94	<0.005	4.9	9.4	12.5	36	<0.1	18.4	8.9	203	1.72	5	3.2	<0.1	10.7	390	<0.1	0.3	<0.1	84
1041432	Drill Core	7.72	0.008	3.4	578.1	10.8	43	0.2	19.5	9.8	272	2.43	7	2.1	<0.1	11.3	429	<0.1	0.4	<0.1	94
1041433	Drill Core	7.93	0.008	14.0	167.8	12.9	52	<0.1	22.7	10.6	279	1.92	8	2.4	<0.1	12.7	468	0.1	0.5	<0.1	89
1041434	Drill Core	7.66	<0.005	11.1	8.9	15.8	71	<0.1	17.3	8.0	351	1.56	8	5.3	<0.1	10.5	476	<0.1	1.2	<0.1	72
1041435	Drill Core	8.01	<0.005	1.5	59.6	11.0	51	0.1	19.7	11.2	270	2.61	9	2.3	<0.1	11.1	442	<0.1	0.6	<0.1	94
1041436	Drill Core	7.94	<0.005	2.0	185.3	10.4	34	<0.1	17.8	9.0	232	2.59	7	2.1	<0.1	10.4	407	<0.1	0.4	<0.1	112
1041437	Drill Core	5.83	0.006	1.4	332.9	10.4	37	<0.1	18.5	10.0	221	2.87	6	1.8	<0.1	11.0	419	<0.1	0.3	<0.1	138
1041438	Drill Core	2.71	0.015	1.0	467.0	10.4	41	0.2	16.9	9.8	234	2.55	7	2.5	<0.1	11.2	450	<0.1	0.3	<0.1	106
1041439	Drill Core	3.09	<0.005	1.4	119.9	8.3	32	<0.1	13.7	8.4	219	2.51	8	1.8	<0.1	9.8	423	0.1	0.4	0.4	95
1041440	Rock Pulp	0.13	1.493	290.6	>10000	76.0	129	2.4	32.3	19.4	366	4.81	29	5.3	2.5	9.9	180	2.1	20.0	3.7	104
1041441	Drill Core	2.61	0.008	2.6	201.8	7.6	34	<0.1	16.3	9.2	228	2.33	10	2.1	<0.1	9.4	405	<0.1	0.5	<0.1	85
1041442	Drill Core	5.59	<0.005	1.0	14.0	7.6	34	<0.1	16.6	9.4	245	2.23	9	1.7	<0.1	8.6	427	<0.1	0.5	<0.1	91
1041443	Drill Core	5.78	<0.005	8.0	11.3	8.7	33	<0.1	16.5	8.9	284	2.22	11	3.4	<0.1	9.9	454	<0.1	0.7	<0.1	89
1041444	Drill Core	5.43	0.007	1.0	136.8	7.1	29	<0.1	15.2	8.7	256	2.81	9	2.4	<0.1	8.1	455	<0.1	0.5	<0.1	93
1041445	Drill Core	5.83	0.013	25.0	32.3	8.9	32	<0.1	15.3	7.5	266	2.07	8	4.0	<0.1	9.0	416	<0.1	0.8	<0.1	75
1041446	Drill Core	4.97	0.006	2.2	72.7	7.9	31	<0.1	16.3	8.9	285	2.42	7	2.1	<0.1	9.3	440	0.1	0.5	<0.1	81
1041447	Drill Core	8.40	0.007	1.0	418.3	7.9	30	<0.1	17.8	9.4	212	2.51	8	1.4	<0.1	8.3	446	<0.1	0.4	<0.1	93
1041448	Drill Core	8.63	0.007	0.8	116.9	9.0	26	<0.1	17.3	9.3	206	2.16	8	1.8	<0.1	7.8	430	<0.1	0.4	<0.1	86
1041449	Drill Core	7.77	0.006	1.1	99.0	7.0	26	<0.1	19.6	8.3	250	2.22	7	1.7	<0.1	6.2	472	<0.1	0.3	<0.1	99
1041450	Drill Core	7.93	<0.005	1.0	59.6	7.4	25	<0.1	18.8	8.9	263	2.60	8	1.5	<0.1	6.8	478	<0.1	0.5	<0.1	105

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 6 of 7 Part 2

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041421	Drill Core	3.04	0.038	12.4	20	1.14	261	0.271	6.70	3.642	0.48	0.4	14.1	39	4.9	39.0	4.5	0.3	1	9	11.9
1041422	Drill Core	2.92	0.055	16.3	21	1.22	271	0.341	7.03	3.722	0.63	0.5	14.8	53	6.2	49.8	6.4	0.5	1	10	14.6
1041423	Drill Core	3.04	0.062	12.8	25	1.33	290	0.308	7.07	3.553	0.70	0.9	12.9	40	5.8	40.1	4.7	0.3	1	10	16.9
1041424	Drill Core	3.19	0.065	13.6	24	1.25	271	0.304	7.10	3.536	0.58	1.1	13.4	40	6.8	38.3	4.6	0.3	1	10	12.0
1041425	Drill Core	2.56	0.051	9.9	27	1.22	341	0.303	7.98	3.538	1.13	1.0	11.3	27	4.5	27.2	3.9	0.3	1	9	21.9
1041426	Drill Core	2.81	0.060	10.1	30	1.26	413	0.348	10.81	3.457	1.32	0.9	13.2	26	3.8	22.9	3.8	0.4	1	10	24.4
1041427	Drill Core	2.60	0.051	10.7	27	1.24	421	0.320	9.32	3.396	1.32	0.6	12.1	26	3.5	21.2	3.4	0.3	<1	9	23.5
1041428	Drill Core	2.60	0.059	13.4	31	1.40	380	0.340	10.24	3.540	1.48	2.2	10.9	29	2.8	14.0	3.0	0.2	2	11	31.6
1041429	Drill Core	2.54	0.061	4.7	30	1.39	365	0.321	10.36	3.281	1.39	3.5	11.3	9	2.6	12.5	3.2	0.3	2	12	31.5
1041430	Drill Core	2.28	0.059	7.7	23	1.22	321	0.264	8.12	3.357	1.23	1.1	11.1	16	2.7	17.2	2.7	0.2	<1	10	26.5
1041431	Drill Core	2.36	0.055	21.2	22	1.22	334	0.269	6.89	3.299	1.26	1.1	10.4	45	3.4	24.1	2.9	0.2	1	9	23.1
1041432	Drill Core	2.67	0.052	24.5	30	1.12	492	0.300	10.22	3.367	1.68	1.1	12.2	55	3.3	24.9	3.4	0.3	2	10	22.3
1041433	Drill Core	2.65	0.058	17.8	30	1.30	376	0.332	10.75	3.550	1.45	1.3	13.5	39	4.1	29.9	3.5	0.2	1	11	27.4
1041434	Drill Core	2.46	0.016	17.6	30	1.06	388	0.316	9.77	3.803	1.20	1.7	13.5	37	4.8	50.4	4.2	0.3	2	10	21.8
1041435	Drill Core	2.54	0.055	13.3	33	1.32	367	0.362	9.84	3.421	1.41	0.5	12.5	38	6.5	38.9	4.6	0.4	2	12	26.9
1041436	Drill Core	2.44	0.051	8.5	28	1.11	382	0.319	8.09	3.453	1.14	1.9	12.5	26	4.7	31.8	4.1	0.3	1	9	24.1
1041437	Drill Core	2.52	0.051	9.4	30	1.15	375	0.320	8.32	3.386	1.07	0.8	12.1	28	4.2	26.5	3.6	0.4	1	9	22.2
1041438	Drill Core	2.66	0.049	9.8	26	1.16	356	0.317	9.67	3.588	1.29	0.6	12.1	29	4.4	29.6	3.8	0.3	2	10	24.6
1041439	Drill Core	2.09	0.043	11.1	24	1.09	262	0.272	6.84	3.485	1.04	0.5	10.2	31	5.1	31.6	3.6	0.3	<1	8	20.0
1041440	Rock Pulp	1.51	0.072	25.0	103	0.97	58	0.197	6.66	0.750	3.59	18.4	25.8	49	4.0	10.6	3.2	0.2	<1	10	13.7
1041441	Drill Core	2.00	0.052	10.6	27	1.21	307	0.282	7.16	3.527	1.22	0.3	9.9	31	3.6	22.5	3.8	0.3	<1	7	24.4
1041442	Drill Core	2.05	0.046	9.9	27	1.21	319	0.262	6.75	3.437	1.11	0.4	9.6	29	2.7	17.8	2.8	0.3	1	7	25.5
1041443	Drill Core	2.29	0.042	10.7	26	1.05	534	0.250	6.88	3.352	1.58	0.8	10.9	26	2.2	17.2	2.9	0.3	2	7	28.1
1041444	Drill Core	2.61	0.044	7.1	26	1.01	342	0.256	6.68	3.435	1.05	0.6	9.1	22	3.2	22.7	3.1	0.3	1	8	25.5
1041445	Drill Core	2.29	0.042	9.9	25	0.86	631	0.254	7.04	3.183	2.11	1.7	9.7	22	2.6	16.1	3.0	0.3	<1	6	22.1
1041446	Drill Core	2.25	0.044	7.1	27	1.03	483	0.265	6.72	3.485	1.42	0.5	10.2	17	2.0	10.8	2.9	0.3	<1	7	20.1
1041447	Drill Core	2.15	0.045	14.4	26	1.13	331	0.285	7.10	3.571	1.12	0.3	9.1	38	2.7	16.1	2.9	0.3	1	8	23.6
1041448	Drill Core	2.13	0.042	6.6	26	1.16	330	0.271	7.10	3.537	1.14	0.5	9.0	20	2.8	13.8	2.4	0.2	1	7	23.4
1041449	Drill Core	2.77	0.052	6.7	31	1.35	348	0.319	7.27	3.629	0.89	0.6	10.0	24	4.5	20.0	3.1	0.3	1	9	20.7
1041450	Drill Core	2.64	0.047	5.7	32	1.19	398	0.282	7.04	3.431	1.03	0.5	10.4	18	3.9	11.5	2.8	0.2	<1	8	18.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 6 of 7 Part 3

CERTIFICATE OF ANALYSIS

VAN11005878.1

	Method	1EX	1EX	1EX
	Analyte	S	Rb	Hf
	Unit	%	ppm	ppm
	MDL	0.1	0.1	0.1
1041421	Drill Core	<0.1	18.0	0.7
1041422	Drill Core	<0.1	24.8	0.8
1041423	Drill Core	<0.1	28.5	0.5
1041424	Drill Core	<0.1	21.5	0.6
1041425	Drill Core	<0.1	58.2	0.5
1041426	Drill Core	<0.1	74.4	0.6
1041427	Drill Core	<0.1	72.7	0.6
1041428	Drill Core	<0.1	84.5	0.5
1041429	Drill Core	<0.1	79.1	0.5
1041430	Drill Core	<0.1	70.2	0.5
1041431	Drill Core	0.2	69.3	0.5
1041432	Drill Core	<0.1	84.4	0.6
1041433	Drill Core	<0.1	78.0	0.6
1041434	Drill Core	<0.1	70.9	0.5
1041435	Drill Core	<0.1	79.6	0.6
1041436	Drill Core	<0.1	62.6	0.6
1041437	Drill Core	<0.1	58.1	0.5
1041438	Drill Core	<0.1	77.3	0.5
1041439	Drill Core	<0.1	77.2	0.5
1041440	Rock Pulp	2.4	160.1	0.8
1041441	Drill Core	<0.1	91.4	0.4
1041442	Drill Core	<0.1	65.3	0.4
1041443	Drill Core	<0.1	86.9	0.5
1041444	Drill Core	<0.1	62.5	0.4
1041445	Drill Core	<0.1	90.3	0.5
1041446	Drill Core	<0.1	70.9	0.4
1041447	Drill Core	<0.1	68.5	0.4
1041448	Drill Core	<0.1	66.5	0.4
1041449	Drill Core	<0.1	35.9	0.4
1041450	Drill Core	<0.1	34.4	0.5



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 7 of 7 Part 1

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041451	Drill Core	8.78	0.016	1.6	38.1	8.0	27	<0.1	21.3	9.8	317	2.88	5	1.7	<0.1	7.6	485	<0.1	0.4	0.1	94
1041452	Drill Core	7.95	0.018	1.7	64.7	7.9	25	<0.1	19.8	8.3	271	2.64	6	2.0	<0.1	8.9	473	<0.1	0.6	0.1	81
1041453	Drill Core	7.17	0.043	0.9	348.3	8.2	31	<0.1	19.6	9.0	243	2.43	6	2.2	0.1	6.3	457	<0.1	0.6	<0.1	89
1041454	Drill Core	5.26	0.006	1.0	80.2	8.3	31	<0.1	14.5	7.6	327	2.58	3	1.0	<0.1	7.1	408	<0.1	0.6	0.1	78
1041455	Drill Core	4.97	0.007	2.1	73.4	9.1	36	<0.1	19.0	9.5	297	2.66	3	1.0	<0.1	6.9	399	<0.1	0.8	<0.1	88
1041456	Drill Core	7.58	0.029	95.5	89.7	6.9	31	<0.1	14.7	8.2	280	2.19	17	1.1	<0.1	5.8	240	<0.1	2.4	0.1	73
1041457	Drill Core	7.16	0.020	3.7	349.0	7.9	33	0.1	17.4	8.4	254	2.57	11	1.5	<0.1	8.2	356	0.2	1.2	0.1	82
1041458	Drill Core	6.69	0.019	2.6	109.5	8.7	42	<0.1	15.4	9.6	480	2.73	18	1.2	<0.1	7.1	240	0.2	6.4	<0.1	66
1041459	Drill Core	7.35	0.016	15.0	252.2	8.1	29	<0.1	15.5	7.5	290	2.31	12	1.3	<0.1	7.2	327	<0.1	4.0	<0.1	76
1041460	Rock	0.68	<0.005	0.2	1.6	0.3	2	<0.1	<0.1	<0.2	38	0.03	<1	1.3	<0.1	<0.1	3903	<0.1	<0.1	<0.1	1
1041461	Drill Core	6.37	0.015	2.7	85.2	9.5	31	<0.1	15.4	8.4	307	2.43	7	1.4	<0.1	7.9	389	<0.1	1.8	<0.1	76
1041462	Drill Core	6.58	0.014	1.6	140.2	11.7	48	<0.1	19.3	9.6	361	2.83	9	2.7	<0.1	7.4	381	0.2	3.4	0.1	84
1041463	Drill Core	7.59	0.007	1.6	48.0	9.0	35	<0.1	18.8	8.7	321	2.67	6	1.5	<0.1	7.2	473	<0.1	1.3	<0.1	85
1041464	Drill Core	5.42	0.050	4.2	408.8	7.6	31	<0.1	15.8	8.4	270	2.20	8	1.9	<0.1	7.0	343	<0.1	3.8	<0.1	78
1041465	Drill Core	3.06	0.253	14.5	1858	9.3	36	0.9	18.3	9.2	321	2.14	15	2.8	3.5	7.7	316	0.2	6.3	0.2	73
1041466	Drill Core	2.87	0.291	17.0	4996	9.5	35	0.9	18.1	8.9	239	2.37	11	1.9	0.1	6.7	338	0.4	2.5	0.5	73
1041467	Drill Core	2.88	0.121	3.9	1729	6.6	33	0.5	18.6	9.4	234	2.32	4	1.7	0.2	7.8	404	<0.1	0.9	0.3	86
1041468	Drill Core	2.41	0.092	19.7	1403	7.3	30	0.3	17.3	11.2	223	2.04	6	1.9	<0.1	7.4	372	<0.1	1.2	0.2	80
1041469	Drill Core	6.09	0.106	10.6	178.1	16.6	63	<0.1	17.2	8.4	424	2.32	7	1.4	<0.1	6.6	256	0.1	1.9	0.1	64
1041470	Drill Core	4.78	<0.005	1.3	169.0	12.3	39	<0.1	16.7	7.3	287	2.34	7	1.2	<0.1	6.8	363	0.1	1.6	<0.1	76
1041471	Drill Core	2.38	0.007	5.7	186.7	10.1	45	0.2	19.9	9.1	337	2.58	5	2.5	<0.1	7.0	375	<0.1	1.3	0.2	77
1041472	Drill Core	5.03	0.007	1.6	83.2	8.3	32	<0.1	18.3	9.3	272	2.54	5	1.9	<0.1	7.2	418	<0.1	0.9	<0.1	79



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 06, 2011

Page: 7 of 7 Part 2

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041451	Drill Core	2.84	0.049	6.6	35	1.34	716	0.289	7.02	3.008	2.21	0.6	11.9	18	1.8	11.5	3.2	0.3	<1	9	17.6
1041452	Drill Core	2.54	0.043	6.7	29	1.14	573	0.264	6.96	3.360	1.56	0.7	11.1	18	2.5	10.6	3.0	0.3	<1	7	20.5
1041453	Drill Core	2.57	0.051	7.4	28	1.24	330	0.299	7.12	3.534	0.95	0.9	10.3	24	4.0	16.8	3.4	0.3	1	8	27.8
1041454	Drill Core	2.97	0.034	7.3	31	0.96	375	0.264	7.52	3.516	0.89	0.6	9.0	20	1.6	13.3	2.9	0.3	2	8	27.5
1041455	Drill Core	2.75	0.047	7.3	30	0.96	537	0.275	7.42	3.141	1.62	0.5	8.1	20	1.4	12.3	2.9	0.2	<1	8	28.6
1041456	Drill Core	2.67	0.034	5.6	24	0.90	453	0.234	6.44	2.430	1.32	1.1	7.4	13	1.3	9.9	2.6	0.2	1	7	38.6
1041457	Drill Core	2.17	0.048	6.4	32	1.00	591	0.279	7.07	2.958	1.52	0.6	12.3	17	1.4	11.0	3.2	0.3	1	8	29.1
1041458	Drill Core	4.79	0.036	7.6	30	1.48	478	0.221	6.27	1.870	1.52	1.6	9.5	19	0.9	11.2	2.4	0.2	<1	7	132.4
1041459	Drill Core	2.44	0.044	5.7	27	0.53	537	0.263	6.69	2.524	1.85	2.5	12.6	16	1.4	9.6	3.0	0.2	1	7	27.5
1041460	Rock	36.85	0.003	0.4	<1	1.53	6	0.003	0.10	0.011	0.02	<0.1	0.4	<1	<0.1	0.5	<0.1	<0.1	<1	<1	0.7
1041461	Drill Core	2.69	0.045	7.2	28	0.67	849	0.253	7.06	2.862	2.32	7.7	14.4	19	1.3	9.5	2.8	0.2	<1	7	22.1
1041462	Drill Core	2.85	0.049	8.1	38	0.62	811	0.275	7.22	2.582	2.25	10.6	13.1	21	1.4	11.0	3.0	0.2	1	8	27.3
1041463	Drill Core	2.51	0.051	7.5	34	0.74	746	0.288	7.17	2.976	2.07	8.3	14.1	20	1.3	9.3	3.2	0.3	<1	7	18.8
1041464	Drill Core	2.29	0.051	7.7	29	0.62	515	0.277	6.74	2.787	1.86	6.0	11.4	20	1.7	9.3	3.0	0.2	<1	7	22.5
1041465	Drill Core	2.68	0.053	7.5	31	0.77	418	0.264	6.69	2.733	1.55	2.4	10.6	20	1.7	11.2	3.0	0.2	<1	8	20.1
1041466	Drill Core	1.96	0.050	4.6	41	1.02	386	0.281	6.42	3.071	1.45	1.2	11.8	12	1.9	7.9	3.3	0.2	1	7	24.0
1041467	Drill Core	2.04	0.053	5.9	32	1.23	509	0.298	6.84	3.086	1.72	0.7	12.3	15	2.0	9.0	3.6	0.3	1	8	26.4
1041468	Drill Core	1.84	0.053	4.6	37	1.00	402	0.285	6.83	3.098	1.51	1.6	12.5	11	1.4	7.9	3.5	0.3	1	8	24.0
1041469	Drill Core	3.31	0.037	5.6	23	0.66	576	0.224	6.10	2.350	2.00	3.0	11.5	15	1.3	9.9	2.7	0.2	1	6	28.9
1041470	Drill Core	2.99	0.045	5.7	35	0.57	633	0.263	6.54	2.552	2.03	2.8	12.2	17	1.5	9.7	3.0	0.2	<1	7	16.0
1041471	Drill Core	3.09	0.045	6.7	31	0.85	614	0.274	6.65	2.798	1.91	2.0	12.5	18	1.4	10.8	3.0	0.2	<1	8	18.6
1041472	Drill Core	2.52	0.048	6.8	43	0.90	694	0.268	6.94	2.962	2.13	2.1	11.4	18	1.2	9.7	3.3	0.3	1	7	19.1



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 7 of 7 Part 3

CERTIFICATE OF ANALYSIS

VAN11005878.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041451	Drill Core	<0.1	54.6	0.5
1041452	Drill Core	<0.1	59.4	0.4
1041453	Drill Core	<0.1	39.1	0.5
1041454	Drill Core	<0.1	32.8	0.4
1041455	Drill Core	<0.1	48.1	0.3
1041456	Drill Core	<0.1	60.4	0.3
1041457	Drill Core	<0.1	63.2	0.6
1041458	Drill Core	<0.1	72.4	0.5
1041459	Drill Core	<0.1	63.3	0.5
1041460	Rock	<0.1	1.0	<0.1
1041461	Drill Core	<0.1	73.5	0.6
1041462	Drill Core	<0.1	70.6	0.6
1041463	Drill Core	<0.1	62.1	0.7
1041464	Drill Core	<0.1	76.6	0.4
1041465	Drill Core	0.2	73.5	0.8
1041466	Drill Core	0.5	58.4	0.5
1041467	Drill Core	0.2	70.8	0.5
1041468	Drill Core	0.2	64.5	0.5
1041469	Drill Core	<0.1	70.0	0.5
1041470	Drill Core	<0.1	59.5	0.6
1041471	Drill Core	<0.1	57.6	0.5
1041472	Drill Core	<0.1	56.5	0.6



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 1 of 4 Part 1

QUALITY CONTROL REPORT

VAN11005878.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
Pulp Duplicates																					
1041302	Drill Core	3.90	0.089	55.7	1528	5.1	34	1.0	24.6	8.3	192	1.77	6	2.8	<0.1	9.3	455	0.2	0.6	0.4	81
REP 1041302	QC			53.1	1529	5.4	35	1.3	25.4	8.7	203	1.81	6	3.0	<0.1	9.0	464	0.2	0.6	0.4	83
1041319	Drill Core	4.51	0.037	2.1	674.9	6.9	31	0.5	23.0	8.5	254	3.03	7	1.6	<0.1	8.2	471	<0.1	0.5	0.2	84
REP 1041319	QC		0.033																		
1041341	Drill Core	7.84	<0.005	3.4	236.8	7.3	29	0.1	16.1	6.9	218	2.48	7	2.1	<0.1	9.2	324	<0.1	0.7	<0.1	68
REP 1041341	QC			3.0	235.5	7.1	28	0.1	16.7	7.1	215	2.47	6	2.3	<0.1	9.4	364	0.2	0.6	0.1	69
1041377	Drill Core	8.12	<0.005	4.3	41.6	9.4	31	<0.1	16.3	8.2	291	2.36	5	2.3	<0.1	6.9	439	<0.1	0.5	0.1	68
REP 1041377	QC		<0.005																		
1041383	Drill Core	7.66	0.011	4.0	196.0	8.3	34	0.3	16.4	8.7	257	2.12	8	2.4	<0.1	9.3	354	<0.1	1.0	<0.1	60
REP 1041383	QC			4.5	195.3	7.7	33	0.5	16.1	8.4	258	2.13	8	2.3	<0.1	9.2	376	<0.1	1.0	<0.1	61
1041412	Drill Core	7.85	0.115	2.2	1867	9.2	36	1.0	29.0	10.4	232	2.41	9	4.4	0.3	11.0	407	<0.1	0.4	0.2	118
REP 1041412	QC		0.102																		
1041431	Drill Core	7.94	<0.005	4.9	9.4	12.5	36	<0.1	18.4	8.9	203	1.72	5	3.2	<0.1	10.7	390	<0.1	0.3	<0.1	84
REP 1041431	QC			4.9	9.3	12.4	33	<0.1	17.2	8.4	197	1.66	6	2.7	<0.1	10.0	389	<0.1	0.3	<0.1	82
1041435	Drill Core	8.01	<0.005	1.5	59.6	11.0	51	0.1	19.7	11.2	270	2.61	9	2.3	<0.1	11.1	442	<0.1	0.6	<0.1	94
REP 1041435	QC		0.007																		
1041454	Drill Core	5.26	0.006	1.0	80.2	8.3	31	<0.1	14.5	7.6	327	2.58	3	1.0	<0.1	7.1	408	<0.1	0.6	0.1	78
REP 1041454	QC			1.4	80.0	8.0	31	<0.1	14.9	7.8	327	2.50	3	1.0	<0.1	6.8	395	<0.1	0.5	<0.1	78
1041456	Drill Core	7.58	0.029	95.5	89.7	6.9	31	<0.1	14.7	8.2	280	2.19	17	1.1	<0.1	5.8	240	<0.1	2.4	0.1	73
REP 1041456	QC		0.020																		
Core Reject Duplicates																					
1041329	Drill Core	7.74	<0.005	3.4	119.2	10.3	42	0.2	19.8	9.8	353	2.68	10	2.5	<0.1	10.4	410	0.2	0.8	<0.1	74
DUP 1041329	QC		<0.005	3.7	111.5	9.4	38	<0.1	18.9	9.3	333	2.62	9	2.2	<0.1	10.0	406	<0.1	0.7	<0.1	74
1041364	Drill Core	6.91	<0.005	8.0	183.0	9.5	33	0.1	15.5	7.7	225	2.46	10	1.7	<0.1	9.2	417	0.1	0.6	<0.1	65
DUP 1041364	QC		<0.005	5.4	168.6	8.8	32	<0.1	16.1	7.7	226	2.46	9	1.8	<0.1	9.0	393	<0.1	0.6	<0.1	64
1041399	Drill Core	6.74	0.021	74.5	1199	6.3	26	0.7	25.0	8.7	159	1.66	8	2.8	<0.1	8.2	412	<0.1	0.4	0.2	75
DUP 1041399	QC		0.067	75.1	1342	6.4	27	0.6	24.2	8.3	160	1.66	7	2.8	0.2	8.1	404	<0.1	0.5	0.2	74
1041434	Drill Core	7.66	<0.005	11.1	8.9	15.8	71	<0.1	17.3	8.0	351	1.56	8	5.3	<0.1	10.5	476	<0.1	1.2	<0.1	72



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 06, 2011

Page: 1 of 4 Part 2

QUALITY CONTROL REPORT

VAN11005878.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1	
Pulp Duplicates																					
1041302	Drill Core	1.23	0.052	6.4	27	1.14	457	0.305	8.33	3.594	1.43	0.9	22.3	13	2.2	6.4	2.9	0.2	<1	8	24.5
REP 1041302	QC	1.26	0.052	6.7	30	1.12	474	0.328	8.42	3.595	1.51	0.9	23.2	13	2.4	6.1	3.1	0.3	1	8	24.4
1041319	Drill Core	1.86	0.050	7.4	30	0.98	398	0.315	8.26	3.430	1.23	0.6	13.2	17	2.5	11.9	3.7	0.3	1	10	22.7
REP 1041319	QC																				
1041341	Drill Core	1.01	0.037	8.3	24	0.83	471	0.244	7.18	3.382	1.75	1.2	11.5	22	2.3	12.7	3.3	0.3	<1	7	17.8
REP 1041341	QC	0.97	0.040	8.7	22	0.83	472	0.246	7.18	3.451	1.75	1.1	11.1	24	2.1	12.7	3.2	0.3	1	7	17.7
1041377	Drill Core	2.07	0.042	7.5	22	1.00	838	0.249	6.78	2.946	2.41	0.7	11.7	17	1.1	8.7	2.8	0.2	1	7	21.8
REP 1041377	QC																				
1041383	Drill Core	1.95	0.037	7.9	21	0.82	722	0.239	6.71	2.858	2.52	5.7	10.8	20	1.4	9.5	3.2	0.3	1	6	23.5
REP 1041383	QC	1.93	0.038	7.8	21	0.82	745	0.243	6.46	2.867	2.54	5.9	11.0	20	1.4	9.5	3.3	0.3	1	6	24.4
1041412	Drill Core	2.22	0.053	7.1	29	1.13	475	0.322	9.65	3.568	1.58	3.2	14.9	14	2.1	9.2	3.1	0.3	<1	9	30.0
REP 1041412	QC																				
1041431	Drill Core	2.36	0.055	21.2	22	1.22	334	0.269	6.89	3.299	1.26	1.1	10.4	45	3.4	24.1	2.9	0.2	1	9	23.1
REP 1041431	QC	2.31	0.051	21.9	23	1.17	327	0.260	6.94	3.502	1.20	1.1	10.3	48	3.3	23.5	2.7	0.2	1	8	24.8
1041435	Drill Core	2.54	0.055	13.3	33	1.32	367	0.362	9.84	3.421	1.41	0.5	12.5	38	6.5	38.9	4.6	0.4	2	12	26.9
REP 1041435	QC																				
1041454	Drill Core	2.97	0.034	7.3	31	0.96	375	0.264	7.52	3.516	0.89	0.6	9.0	20	1.6	13.3	2.9	0.3	2	8	27.5
REP 1041454	QC	3.02	0.034	6.7	33	0.94	366	0.269	7.27	3.479	0.86	0.5	8.5	18	1.8	13.0	2.9	0.3	<1	8	27.1
1041456	Drill Core	2.67	0.034	5.6	24	0.90	453	0.234	6.44	2.430	1.32	1.1	7.4	13	1.3	9.9	2.6	0.2	1	7	38.6
REP 1041456	QC																				
Core Reject Duplicates																					
1041329	Drill Core	1.67	0.045	9.4	29	0.95	719	0.291	7.79	3.163	2.14	1.5	16.6	22	1.7	10.9	3.5	0.3	1	9	18.7
DUP 1041329	QC	1.65	0.043	9.2	27	0.93	706	0.290	7.45	3.143	2.11	1.3	15.9	21	1.7	10.8	3.2	0.3	1	8	18.6
1041364	Drill Core	1.49	0.039	9.5	22	0.84	541	0.231	7.34	3.601	1.54	1.0	13.7	21	1.6	8.6	3.0	0.3	<1	6	22.0
DUP 1041364	QC	1.46	0.039	8.7	22	0.84	590	0.226	7.31	3.544	1.59	0.9	13.7	20	1.6	8.6	2.9	0.3	<1	6	20.5
1041399	Drill Core	1.56	0.050	6.6	25	1.12	371	0.281	6.84	3.441	1.13	1.4	11.8	13	1.5	4.2	2.4	0.2	1	8	25.5
DUP 1041399	QC	1.52	0.049	7.0	25	1.11	367	0.288	6.78	3.342	1.08	1.4	11.8	14	1.5	4.4	2.7	0.2	1	8	24.7
1041434	Drill Core	2.46	0.016	17.6	30	1.06	388	0.316	9.77	3.803	1.20	1.7	13.5	37	4.8	50.4	4.2	0.3	2	10	21.8



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 1 of 4 **Part** 3

QUALITY CONTROL REPORT

VAN11005878.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
Pulp Duplicates				
1041302	Drill Core	0.1	92.5	0.9
REP 1041302	QC	0.2	89.5	0.9
1041319	Drill Core	<0.1	71.8	0.5
REP 1041319	QC			
1041341	Drill Core	<0.1	101.5	0.6
REP 1041341	QC	<0.1	101.6	0.5
1041377	Drill Core	<0.1	67.5	0.6
REP 1041377	QC			
1041383	Drill Core	<0.1	82.6	0.5
REP 1041383	QC	<0.1	84.2	0.5
1041412	Drill Core	0.2	102.4	0.5
REP 1041412	QC			
1041431	Drill Core	0.2	69.3	0.5
REP 1041431	QC	0.1	69.6	0.5
1041435	Drill Core	<0.1	79.6	0.6
REP 1041435	QC			
1041454	Drill Core	<0.1	32.8	0.4
REP 1041454	QC	<0.1	28.5	0.5
1041456	Drill Core	<0.1	60.4	0.3
REP 1041456	QC			
Core Reject Duplicates				
1041329	Drill Core	<0.1	93.7	0.6
DUP 1041329	QC	<0.1	89.9	0.7
1041364	Drill Core	<0.1	96.1	0.6
DUP 1041364	QC	<0.1	93.2	0.5
1041399	Drill Core	0.1	69.1	0.4
DUP 1041399	QC	0.1	69.7	0.4
1041434	Drill Core	<0.1	70.9	0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 2 of 4 Part 1

QUALITY CONTROL REPORT

VAN11005878.1

		WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1
DUP 1041434	QC	<0.005	9.5	8.3	17.7	70	<0.1	15.4	8.1	343	1.46	8	5.4	<0.1	9.9	473	<0.1	1.3	<0.1	71	
1041469	Drill Core	6.09	0.106	10.6	178.1	16.6	63	<0.1	17.2	8.4	424	2.32	7	1.4	<0.1	6.6	256	0.1	1.9	0.1	64
DUP 1041469	QC	0.008	9.1	182.1	16.2	64	<0.1	17.3	8.5	420	2.37	7	1.5	<0.1	6.5	257	0.1	1.9	<0.1	67	
Reference Materials																					
STD OREAS24P	Standard		1.3	45.7	2.9	109	<0.1	134.3	43.7	1116	7.00	2	0.6	<0.1	2.9	379	<0.1	<0.1	<0.1	163	
STD OREAS24P	Standard		1.8	53.5	2.8	120	<0.1	147.7	50.3	1115	7.41	2	0.7	<0.1	3.0	380	<0.1	<0.1	<0.1	164	
STD OREAS24P	Standard		1.3	48.8	2.5	110	0.1	138.6	43.7	1100	7.18	2	0.7	<0.1	2.9	366	0.1	<0.1	<0.1	155	
STD OREAS24P	Standard		1.6	49.3	3.4	115	<0.1	134.8	42.0	1056	7.31	<1	0.7	<0.1	2.9	326	<0.1	<0.1	<0.1	159	
STD OREAS24P	Standard		1.2	46.8	2.8	117	<0.1	144.0	45.2	1106	7.35	3	0.7	<0.1	2.8	390	0.1	0.1	<0.1	150	
STD OREAS24P	Standard		1.7	51.2	2.9	111	0.1	152.2	44.9	1135	7.47	3	0.8	<0.1	3.2	414	0.1	0.2	0.3	164	
STD OREAS45C	Standard		1.8	632.5	24.7	80	0.2	332.6	102.8	1196	17.60	11	2.4	<0.1	10.8	33	0.1	0.9	0.3	288	
STD OREAS45C	Standard		2.1	604.0	27.6	83	0.4	326.9	99.0	1127	16.92	11	2.4	<0.1	11.4	39	0.2	1.0	0.3	266	
STD OREAS45C	Standard		2.5	615.3	26.1	81	0.3	323.1	102.8	1160	17.44	11	2.4	<0.1	10.8	37	0.2	0.9	0.3	268	
STD OREAS45C	Standard		2.0	612.0	29.5	92	0.3	339.2	100.5	1084	17.24	12	2.7	<0.1	12.1	36	0.2	0.6	0.2	273	
STD OREAS45C	Standard		2.1	608.0	25.0	80	0.2	328.3	105.6	1202	18.37	11	2.3	<0.1	10.4	36	0.4	0.9	0.3	271	
STD OREAS45C	Standard		2.0	610.5	24.6	80	0.3	338.3	97.0	1138	16.91	11	2.3	<0.1	10.6	38	0.1	0.9	0.2	252	
STD OXH82	Standard		1.325																		
STD OXH82	Standard		1.329																		
STD OXH82	Standard		1.306																		
STD OXH82	Standard		1.341																		
STD OXH82	Standard		1.268																		
STD OXH82	Standard		1.346																		
STD OXH82	Standard		1.282																		
STD OXH82	Standard		1.292																		
STD OXK79	Standard		3.660																		
STD OXK79	Standard		3.698																		
STD OXK79	Standard		3.722																		
STD OXK79	Standard		3.669																		
STD OXK79	Standard		3.373																		

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 2 of 4 Part 2

QUALITY CONTROL REPORT

VAN11005878.1

		1EX Ca %	1EX P %	1EX La ppm	1EX Cr ppm	1EX Mg %	1EX Ba ppm	1EX Ti %	1EX Al %	1EX Na %	1EX K %	1EX W ppm	1EX Zr ppm	1EX Ce ppm	1EX Sn ppm	1EX Y ppm	1EX Nb ppm	1EX Ta ppm	1EX Be ppm	1EX Sc ppm	1EX Li ppm
		0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1
DUP 1041434	QC	2.39	0.016	14.9	29	1.03	391	0.318	10.04	3.763	1.22	1.9	13.3	32	4.9	52.5	4.1	0.3	1	9	20.7
1041469	Drill Core	3.31	0.037	5.6	23	0.66	576	0.224	6.10	2.350	2.00	3.0	11.5	15	1.3	9.9	2.7	0.2	1	6	28.9
DUP 1041469	QC	3.23	0.038	5.8	24	0.68	582	0.222	6.19	2.299	2.06	2.8	11.6	16	1.2	9.9	2.8	0.2	<1	6	29.3
Reference Materials																					
STD OREAS24P	Standard	5.91	0.130	17.5	210	4.03	268	1.133	7.75	2.368	0.66	0.4	131.5	36	1.5	20.3	18.6	1.1	1	19	8.1
STD OREAS24P	Standard	6.33	0.131	18.8	198	4.07	294	1.145	7.77	2.399	0.65	0.5	140.1	39	1.5	22.8	19.9	1.1	2	20	8.0
STD OREAS24P	Standard	5.72	0.131	18.1	188	3.94	263	1.065	7.33	2.328	0.62	0.4	131.5	36	1.6	21.1	18.1	1.0	1	19	7.3
STD OREAS24P	Standard	5.73	0.124	18.3	193	3.91	282	1.029	7.53	2.390	0.64	0.5	128.4	36	1.5	22.3	18.6	1.0	1	20	7.7
STD OREAS24P	Standard	5.81	0.133	18.3	199	3.96	272	1.044	7.46	2.467	0.65	0.5	135.7	37	1.6	20.2	18.7	1.1	<1	20	8.3
STD OREAS24P	Standard	6.01	0.139	18.4	181	4.14	278	1.047	7.85	2.422	0.67	0.4	136.2	37	1.5	21.1	19.0	1.1	2	21	8.3
STD OREAS45C	Standard	0.47	0.050	24.4	980	0.26	281	1.258	7.19	0.107	0.34	1.2	171.5	50	2.8	11.9	23.0	1.5	1	57	16.1
STD OREAS45C	Standard	0.47	0.052	25.5	881	0.27	279	1.206	7.06	0.101	0.33	1.0	168.2	50	3.3	12.8	21.7	1.5	1	59	16.2
STD OREAS45C	Standard	0.49	0.054	26.5	902	0.27	272	1.200	7.01	0.105	0.35	1.2	163.9	51	2.8	13.0	22.3	1.4	1	60	15.9
STD OREAS45C	Standard	0.48	0.051	27.9	877	0.27	290	1.170	7.32	0.112	0.36	1.2	173.1	49	3.1	13.4	23.2	1.5	<1	61	17.1
STD OREAS45C	Standard	0.50	0.052	26.0	947	0.29	283	1.210	7.39	0.119	0.34	1.2	176.3	52	2.8	12.4	23.2	1.5	2	60	16.3
STD OREAS45C	Standard	0.46	0.051	25.4	889	0.27	274	1.132	7.32	0.111	0.33	1.1	156.3	51	2.9	11.9	20.7	1.4	<1	60	15.7
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXK79	Standard																				
STD OXK79	Standard																				
STD OXK79	Standard																				
STD OXK79	Standard																				
STD OXK79	Standard																				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 2 of 4 Part 3

QUALITY CONTROL REPORT

VAN11005878.1

		1EX S %	1EX Rb ppm	1EX Hf ppm
		0.1	0.1	0.1
DUP 1041434	QC	<0.1	68.0	0.6
1041469	Drill Core	<0.1	70.0	0.5
DUP 1041469	QC	<0.1	75.1	0.4
Reference Materials				
STD OREAS24P	Standard	<0.1	27.0	3.3
STD OREAS24P	Standard	<0.1	23.2	3.4
STD OREAS24P	Standard	<0.1	22.0	3.4
STD OREAS24P	Standard	<0.1	20.6	3.6
STD OREAS24P	Standard	<0.1	27.5	3.4
STD OREAS24P	Standard	<0.1	23.3	3.7
STD OREAS45C	Standard	<0.1	25.3	4.5
STD OREAS45C	Standard	<0.1	24.6	4.3
STD OREAS45C	Standard	<0.1	24.3	4.2
STD OREAS45C	Standard	<0.1	23.2	4.5
STD OREAS45C	Standard	<0.1	27.3	4.6
STD OREAS45C	Standard	<0.1	22.6	3.9
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXK79	Standard			

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 3 of 4 Part 1

QUALITY CONTROL REPORT

VAN11005878.1

		WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
STD OXK79	Standard	3.773																			
STD OXK79	Standard	3.551																			
STD OXK79	Standard	3.760																			
STD OXH82 Expected		1.278																			
STD OXK79 Expected		3.532																			
STD OREAS24P Expected				1.5	52	2.9	119	0.06	141	44	1100	7.53	1.2	0.75		2.85	403	0.15	0.09		158
STD OREAS45C Expected				2.26	620	24	83	0.28	333	104	1160	18.33	10.1	2.4	0.045	10.2	36.4	0.15	0.79	0.21	270
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
Prep Wash																					

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 3 of 4 **Part** 3

QUALITY CONTROL REPORT

VAN11005878.1

		1EX S %	1EX Rb ppm	1EX Hf ppm
		0.1	0.1	0.1
STD OXK79	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXH82	Expected			
STD OXK79	Expected			
STD OREAS24P	Expected		22.4	3.6
STD OREAS45C	Expected	0.021	24	4.27
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
Prep Wash				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 4 of 4 Part 1

QUALITY CONTROL REPORT

VAN11005878.1

		WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
G1	Prep Blank	<0.01	<0.005	0.2	2.5	22.6	58	<0.1	2.9	5.5	800	2.30	<1	2.5	<0.1	8.1	799	0.1	0.3	0.5	48
G1	Prep Blank	<0.01	<0.005	0.2	2.4	22.5	55	<0.1	3.2	5.4	830	2.33	<1	2.5	<0.1	9.3	778	<0.1	0.2	0.3	49



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 4 of 4 Part 2

QUALITY CONTROL REPORT

VAN11005878.1

		1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li
		%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1
G1	Prep Blank	2.39	0.077	26.1	5	0.58	1271	0.278	8.31	2.719	3.31	0.2	12.5	55	2.0	15.1	25.6	1.5	3	5	40.1
G1	Prep Blank	2.52	0.085	29.1	5	0.60	1222	0.285	8.55	2.754	3.28	0.2	12.6	62	2.0	15.7	27.6	1.5	3	5	38.2



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 06, 2011

Page: 4 of 4 Part 3

QUALITY CONTROL REPORT

VAN11005878.1

		1EX	1EX	1EX
		S	Rb	Hf
		%	ppm	ppm
		0.1	0.1	0.1
G1	Prep Blank	<0.1	138.8	0.6
G1	Prep Blank	<0.1	140.3	0.6



1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Submitted By: Tim Johnson
Receiving Lab: Canada-Vancouver
Received: November 01, 2011
Report Date: December 05, 2011
Page: 1 of 5

CERTIFICATE OF ANALYSIS

VAN11005904.1

CLIENT JOB INFORMATION

Project: Taseko
Shipment ID:
P.O. Number
Number of Samples: 97

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0
Canada

CC: Mathius Westphal

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	95	Crush, split and pulverize 250 g rock to 200 mesh			VAN
G601	97	Fire Assay fusion Au by ICP-ES	30	Completed	VAN
1EX	97	4 Acid digestion ICP-MS analysis	0.25	Completed	VAN

ADDITIONAL COMMENTS



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 2 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041498	Drill Core	5.53	0.013	2.5	100.8	11.2	49	0.2	20.2	10.1	330	2.88	5	1.3	<0.1	8.9	412	0.1	0.9	0.1	90
1041499	Drill Core	4.10	0.010	1.5	59.5	9.8	49	0.1	20.2	9.4	305	2.76	5	1.0	<0.1	9.2	329	<0.1	1.8	<0.1	89
1041500	Rock Pulp	0.10	1.238	276.6	9669	84.1	125	4.5	31.2	18.6	323	4.66	32	5.7	1.3	11.2	166	3.3	22.1	2.3	92
1041501	Drill Core	4.62	0.017	1.8	84.0	10.1	49	<0.1	23.7	10.6	311	2.93	5	1.2	<0.1	7.7	387	<0.1	0.9	<0.1	89
1041502	Drill Core	7.80	0.014	3.9	192.1	9.3	46	0.1	21.6	10.9	273	3.26	6	1.3	<0.1	8.8	396	<0.1	0.8	<0.1	106
1041503	Drill Core	8.14	0.007	2.8	73.1	9.4	49	<0.1	23.0	11.0	315	3.01	7	1.5	<0.1	10.3	358	<0.1	0.8	<0.1	107
1041504	Drill Core	7.33	<0.005	5.0	82.5	8.6	39	0.1	18.7	9.4	366	2.54	11	1.1	<0.1	6.4	203	0.1	3.5	<0.1	85
1041505	Drill Core	6.35	<0.005	8.3	67.6	11.5	45	<0.1	19.1	8.5	230	2.49	11	2.3	<0.1	9.5	305	<0.1	1.6	<0.1	80
1041506	Drill Core	5.93	<0.005	3.2	88.6	10.3	40	<0.1	18.1	8.2	283	2.61	13	1.6	<0.1	9.5	246	<0.1	4.1	<0.1	78
1041507	Drill Core	5.28	<0.005	2.6	89.7	14.2	63	<0.1	18.9	8.5	276	2.49	10	1.7	<0.1	9.8	309	<0.1	2.7	<0.1	78
1041508	Drill Core	6.62	0.062	33.6	472.9	28.0	67	0.2	18.8	9.7	335	2.41	12	1.7	<0.1	8.3	329	0.2	4.8	<0.1	76
1041509	Drill Core	7.55	<0.005	2.0	56.4	11.8	47	<0.1	19.3	9.6	316	2.38	8	1.6	<0.1	9.1	380	<0.1	1.1	<0.1	77
1041510	Drill Core	6.20	<0.005	4.3	61.2	14.0	49	<0.1	19.4	10.0	405	2.63	9	1.5	<0.1	8.0	356	<0.1	1.9	<0.1	73
1041511	Drill Core	4.99	<0.005	2.0	41.0	12.7	74	<0.1	25.6	14.1	622	3.26	13	6.3	<0.1	8.1	285	<0.1	3.6	<0.1	53
1041512	Drill Core	8.51	0.008	1.7	108.7	9.8	45	<0.1	18.2	8.8	349	2.20	10	1.6	<0.1	8.6	275	<0.1	3.4	<0.1	70
1041513	Drill Core	6.60	<0.005	1.1	71.1	10.0	35	<0.1	16.2	8.2	260	2.07	10	1.5	<0.1	10.6	285	<0.1	4.4	<0.1	72
1041514	Drill Core	6.97	<0.005	1.4	42.5	9.6	41	<0.1	18.5	8.5	293	2.08	11	1.1	<0.1	8.0	273	<0.1	4.1	<0.1	71
1041515	Drill Core	7.04	<0.005	1.9	50.0	10.9	69	<0.1	20.0	9.8	358	2.65	8	1.7	<0.1	9.1	398	<0.1	2.2	<0.1	76
1041516	Drill Core	8.10	<0.005	1.1	39.1	9.5	39	<0.1	20.1	8.9	279	2.37	7	1.8	<0.1	9.2	404	<0.1	0.7	<0.1	70
1041517	Drill Core	8.07	<0.005	1.1	41.4	11.1	44	0.1	19.5	9.9	308	2.73	8	1.6	<0.1	9.1	408	<0.1	1.5	<0.1	86
1041518	Drill Core	7.32	<0.005	1.0	50.2	11.2	44	<0.1	19.1	10.0	330	2.53	8	1.5	<0.1	8.8	370	<0.1	2.1	<0.1	76
1041519	Drill Core	2.51	0.023	1.1	78.7	10.5	48	<0.1	23.2	12.1	414	2.88	11	1.5	<0.1	8.0	265	<0.1	5.6	<0.1	75
1041520	Drill Core	2.34	0.026	1.1	103.9	11.8	56	<0.1	26.4	13.6	532	3.29	12	2.7	<0.1	8.0	291	<0.1	4.4	<0.1	71
1041521	Drill Core	5.47	0.023	4.6	111.7	10.9	47	<0.1	23.0	11.0	324	2.84	9	2.5	<0.1	9.0	404	0.1	2.0	<0.1	84
1041522	Drill Core	7.87	0.022	1.4	79.4	10.2	40	<0.1	20.3	10.2	284	2.54	7	2.7	<0.1	9.5	391	<0.1	0.5	<0.1	75
1041523	Drill Core	8.26	0.027	8.6	101.8	8.7	26	<0.1	10.8	6.1	170	1.67	8	2.2	<0.1	13.9	300	<0.1	1.4	<0.1	49
1041524	Drill Core	5.51	0.008	59.7	381.4	7.2	30	0.1	13.8	7.7	263	1.69	13	2.3	<0.1	12.3	181	0.2	5.3	<0.1	48
1041525	Drill Core	6.70	0.005	13.3	198.3	5.6	27	<0.1	11.7	6.0	236	1.62	12	1.6	<0.1	11.5	180	<0.1	2.2	<0.1	51
1041526	Drill Core	6.42	0.030	24.5	190.9	6.1	23	0.1	12.0	5.9	163	1.58	9	1.8	<0.1	12.3	208	0.1	1.3	<0.1	51
1041527	Drill Core	7.19	0.006	18.1	98.0	7.0	31	0.1	14.7	8.4	232	1.98	7	2.0	<0.1	12.5	191	0.1	1.5	<0.1	54

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 2 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.01	0.1	0.1	1	0.1	0.1	0.1	1	1	1	
1041498	Drill Core	2.67	0.049	9.4	44	0.90	1139	0.319	7.40	2.919	1.87	4.0	10.0	24	1.7	15.8	3.1	0.3	1	8	28.5
1041499	Drill Core	2.64	0.049	9.5	34	1.01	549	0.304	7.18	2.896	1.90	0.8	8.4	23	1.5	16.0	3.1	0.3	<1	8	35.3
1041500	Rock Pulp	1.49	0.062	31.0	97	0.93	126	0.194	6.67	0.725	3.77	17.4	23.0	54	3.7	12.2	2.8	0.2	1	10	12.3
1041501	Drill Core	2.78	0.053	10.4	45	1.14	415	0.345	7.57	3.143	1.33	1.1	9.2	26	1.9	18.5	3.6	0.3	1	9	36.0
1041502	Drill Core	2.45	0.061	9.1	40	1.28	448	0.367	7.52	3.208	1.29	1.4	9.6	27	2.4	21.4	3.8	0.3	1	10	33.2
1041503	Drill Core	2.53	0.057	10.3	51	1.11	701	0.352	7.14	2.787	1.95	0.7	10.9	28	2.0	18.9	3.6	0.3	1	9	26.3
1041504	Drill Core	3.43	0.043	8.2	31	1.19	692	0.286	6.59	1.880	1.95	3.1	7.5	22	1.4	16.8	3.1	0.2	<1	8	47.9
1041505	Drill Core	1.90	0.048	9.8	39	0.70	636	0.315	7.20	2.640	1.98	1.1	13.1	23	1.3	15.3	3.1	0.3	<1	8	30.6
1041506	Drill Core	2.16	0.046	8.7	31	0.76	502	0.311	7.33	2.069	1.95	2.7	12.5	23	1.6	14.8	3.2	0.2	1	7	68.5
1041507	Drill Core	2.12	0.052	9.1	38	0.76	631	0.308	6.92	2.576	2.22	2.0	12.8	22	1.3	12.1	3.2	0.3	1	7	24.7
1041508	Drill Core	2.56	0.044	8.5	30	0.95	649	0.288	6.91	2.520	1.97	1.0	12.2	20	1.1	12.6	3.2	0.2	1	8	26.9
1041509	Drill Core	2.48	0.047	10.0	38	0.74	784	0.307	6.75	2.681	2.40	2.2	13.0	24	1.0	10.9	3.2	0.3	1	7	20.3
1041510	Drill Core	3.37	0.048	8.5	30	0.89	677	0.287	6.60	2.465	1.88	4.3	10.7	21	1.0	12.3	2.9	0.2	1	7	22.6
1041511	Drill Core	5.90	0.033	9.5	25	2.01	579	0.200	5.66	1.580	1.82	2.2	9.7	22	1.3	17.8	2.3	0.2	1	6	45.6
1041512	Drill Core	2.40	0.042	6.9	29	0.74	492	0.281	6.53	2.361	1.98	2.9	10.0	18	1.3	12.2	3.0	0.3	1	8	35.3
1041513	Drill Core	1.99	0.042	7.7	28	0.58	667	0.280	7.00	2.331	2.44	4.1	10.7	19	1.3	11.1	2.8	0.2	1	8	28.4
1041514	Drill Core	2.30	0.046	7.5	30	0.72	471	0.288	7.03	2.505	1.84	2.0	9.7	20	1.6	12.6	3.2	0.3	<1	7	46.3
1041515	Drill Core	2.82	0.052	8.7	33	0.94	777	0.322	7.33	2.794	2.08	1.5	12.5	21	1.2	13.9	3.5	0.3	<1	7	27.4
1041516	Drill Core	2.37	0.044	7.8	28	0.90	772	0.284	7.24	2.866	2.20	0.9	12.0	19	1.1	12.0	3.1	0.2	<1	7	29.8
1041517	Drill Core	2.84	0.052	8.6	35	0.89	713	0.309	7.28	2.903	2.04	1.1	11.7	22	1.2	14.1	3.3	0.3	1	9	28.8
1041518	Drill Core	2.86	0.050	9.4	31	0.83	748	0.303	6.86	2.645	2.17	2.7	10.5	23	1.0	12.6	3.1	0.2	<1	8	27.3
1041519	Drill Core	4.16	0.044	9.5	32	1.28	1278	0.271	6.90	1.999	1.83	2.0	7.8	22	1.2	14.2	3.0	0.2	1	8	44.4
1041520	Drill Core	5.39	0.045	11.3	30	1.57	951	0.261	6.75	1.846	1.68	2.2	7.3	25	1.3	17.0	2.8	0.2	<1	7	43.4
1041521	Drill Core	3.01	0.056	11.6	42	0.93	745	0.324	7.57	2.708	2.00	1.1	10.0	29	1.4	15.7	3.4	0.2	<1	9	27.8
1041522	Drill Core	2.36	0.048	8.7	32	1.07	728	0.293	7.08	2.832	2.19	0.5	10.7	22	1.3	13.5	3.5	0.3	1	7	28.4
1041523	Drill Core	1.65	0.029	6.5	25	0.51	833	0.209	6.75	2.565	2.84	1.5	16.4	15	1.0	9.2	3.3	0.3	1	5	19.0
1041524	Drill Core	2.70	0.024	6.6	13	0.81	786	0.195	6.06	1.670	2.85	1.2	16.5	13	0.8	8.0	2.6	0.3	<1	4	67.0
1041525	Drill Core	2.57	0.029	7.7	18	0.58	758	0.217	6.19	1.594	2.97	1.8	16.1	17	1.1	9.2	3.1	0.3	1	5	48.6
1041526	Drill Core	1.80	0.029	15.2	15	0.48	813	0.221	6.50	1.979	3.04	5.0	15.7	31	0.9	7.5	3.1	0.3	<1	5	22.5
1041527	Drill Core	2.03	0.033	10.5	21	0.62	984	0.230	6.46	1.999	2.80	1.6	12.6	23	0.9	9.6	3.0	0.3	1	5	29.9

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 05, 2011

Page: 2 of 5 **Part** 3

CERTIFICATE OF ANALYSIS

VAN11005904.1

	Method	1EX	1EX	1EX
	Analyte	S	Rb	Hf
	Unit	%	ppm	ppm
	MDL	0.1	0.1	0.1
1041498	Drill Core	<0.1	57.3	0.4
1041499	Drill Core	<0.1	61.8	0.5
1041500	Rock Pulp	2.3	136.7	0.8
1041501	Drill Core	<0.1	50.4	0.5
1041502	Drill Core	<0.1	55.2	0.5
1041503	Drill Core	<0.1	63.2	0.6
1041504	Drill Core	<0.1	82.0	0.4
1041505	Drill Core	<0.1	62.3	0.7
1041506	Drill Core	<0.1	61.2	0.7
1041507	Drill Core	<0.1	73.8	0.7
1041508	Drill Core	<0.1	59.3	0.5
1041509	Drill Core	<0.1	66.0	0.6
1041510	Drill Core	<0.1	57.0	0.5
1041511	Drill Core	<0.1	71.7	0.4
1041512	Drill Core	<0.1	65.6	0.5
1041513	Drill Core	<0.1	70.6	0.6
1041514	Drill Core	<0.1	59.9	0.4
1041515	Drill Core	<0.1	66.4	0.6
1041516	Drill Core	<0.1	66.5	0.5
1041517	Drill Core	<0.1	59.0	0.6
1041518	Drill Core	<0.1	68.5	0.5
1041519	Drill Core	<0.1	64.6	0.4
1041520	Drill Core	<0.1	66.6	0.4
1041521	Drill Core	<0.1	65.8	0.5
1041522	Drill Core	<0.1	66.3	0.6
1041523	Drill Core	<0.1	75.3	0.7
1041524	Drill Core	<0.1	91.4	0.7
1041525	Drill Core	<0.1	88.7	0.6
1041526	Drill Core	<0.1	89.2	0.7
1041527	Drill Core	<0.1	91.8	0.6



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 3 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041528	Drill Core	7.25	<0.005	2.1	59.6	8.3	31	<0.1	19.6	10.1	263	2.63	6	2.5	<0.1	10.5	330	0.2	1.1	<0.1	72
1041529	Drill Core	8.38	0.022	35.7	212.1	9.5	33	0.1	19.2	10.6	262	2.61	6	3.2	<0.1	10.2	360	0.1	0.8	0.1	83
1041530	Drill Core	7.06	0.012	12.9	328.8	8.9	42	0.1	22.2	12.3	395	2.94	15	3.9	<0.1	9.0	342	0.1	2.0	<0.1	80
1041531	Drill Core	6.48	0.021	6.8	213.8	8.5	30	0.2	17.8	9.6	253	2.52	22	2.1	0.2	9.3	354	0.3	4.5	0.2	80
1041532	Drill Core	4.39	0.054	9.1	358.6	7.7	36	0.1	21.4	11.6	368	2.39	23	4.6	<0.1	7.8	160	0.1	6.3	0.1	68
1041533	Drill Core	7.13	0.014	15.9	287.8	7.9	31	0.1	17.7	9.9	258	2.30	22	3.9	<0.1	9.2	256	<0.1	7.2	<0.1	71
1041534	Drill Core	7.72	<0.005	6.1	92.7	7.3	26	<0.1	16.7	8.9	251	2.48	9	2.1	<0.1	9.9	397	<0.1	1.1	<0.1	71
1041535	Drill Core	5.58	0.011	50.6	381.0	7.6	31	0.3	18.5	10.8	278	2.35	21	2.4	<0.1	8.3	285	<0.1	3.8	0.1	69
1041536	Drill Core	8.17	0.007	8.2	109.7	7.2	30	<0.1	18.1	9.9	270	2.46	10	2.8	<0.1	9.7	318	<0.1	1.6	<0.1	70
1041537	Drill Core	7.30	0.007	8.0	292.7	8.2	36	0.3	18.3	9.3	282	2.42	12	2.8	<0.1	9.4	334	<0.1	3.6	0.3	71
1041538	Drill Core	7.64	<0.005	4.8	153.5	7.2	30	<0.1	17.5	10.1	360	2.55	12	2.1	<0.1	7.7	251	0.1	1.9	<0.1	72
1041539	Drill Core	8.15	0.005	11.6	176.4	7.4	26	<0.1	18.8	10.0	230	2.66	6	3.0	<0.1	9.8	431	<0.1	0.6	<0.1	75
1041540	Rock	0.62	<0.005	<0.1	0.5	<0.1	<1	<0.1	0.5	<0.2	23	<0.01	16	1.5	<0.1	<0.1	4713	<0.1	<0.1	<0.1	<1
1041541	Drill Core	7.40	0.009	2.3	131.1	7.4	26	<0.1	18.6	9.8	245	2.57	8	3.4	<0.1	9.2	360	<0.1	0.6	<0.1	72
1041542	Drill Core	8.13	0.010	3.5	119.9	7.7	27	<0.1	17.4	9.7	265	2.57	7	3.3	<0.1	10.2	429	<0.1	0.5	<0.1	72
1041543	Drill Core	6.96	<0.005	4.6	139.4	7.4	25	<0.1	18.1	9.6	249	2.51	7	2.1	<0.1	9.8	393	<0.1	0.6	<0.1	76
1041544	Drill Core	7.52	<0.005	2.0	27.9	7.3	27	<0.1	19.2	9.6	274	2.59	5	3.1	<0.1	9.6	433	<0.1	0.5	<0.1	75
1041545	Drill Core	8.29	<0.005	2.2	54.1	6.8	27	<0.1	19.5	10.2	300	2.84	9	2.8	<0.1	8.0	481	<0.1	0.8	<0.1	83
1041546	Drill Core	8.07	<0.005	1.3	31.1	7.3	24	<0.1	19.4	10.5	280	2.78	8	2.5	<0.1	8.3	456	<0.1	0.7	<0.1	80
1041547	Drill Core	7.66	<0.005	2.0	26.5	7.3	27	<0.1	18.9	9.3	287	2.65	9	2.4	<0.1	8.8	406	<0.1	0.8	0.1	76
1041548	Drill Core	8.35	<0.005	1.8	48.0	7.0	23	<0.1	17.4	9.4	255	2.51	8	1.9	<0.1	7.9	396	<0.1	0.8	<0.1	73
1041549	Drill Core	6.79	0.013	2.0	91.4	10.6	34	<0.1	18.2	9.7	278	2.49	10	2.0	<0.1	7.6	386	<0.1	2.2	<0.1	78
1041550	Drill Core	7.87	<0.005	2.1	90.4	7.8	30	<0.1	19.8	11.1	312	2.70	12	1.8	<0.1	7.1	400	<0.1	1.8	<0.1	82
1041551	Drill Core	7.56	0.018	3.5	120.7	7.1	28	<0.1	18.7	10.5	326	2.68	11	2.7	<0.1	6.9	437	<0.1	1.7	<0.1	78
1041552	Drill Core	8.32	0.015	2.4	147.8	6.7	26	<0.1	19.4	11.1	279	2.76	9	2.0	<0.1	7.0	406	<0.1	1.3	<0.1	82
1041553	Drill Core	7.89	0.005	1.7	70.4	7.8	28	<0.1	18.6	11.5	338	2.74	10	2.5	<0.1	7.5	445	<0.1	1.4	<0.1	82
1041554	Drill Core	2.93	0.034	3.4	141.4	7.7	35	0.2	16.4	10.5	460	2.50	15	4.4	<0.1	9.8	298	0.2	3.8	0.3	62
1041555	Drill Core	4.84	<0.005	2.1	61.8	7.3	30	<0.1	21.5	11.9	305	2.78	6	2.1	<0.1	7.1	457	<0.1	1.4	<0.1	83
1041556	Drill Core	7.61	0.006	4.0	78.7	6.4	25	<0.1	21.8	10.8	300	2.87	8	2.1	<0.1	6.8	493	<0.1	1.1	<0.1	89
1041557	Drill Core	6.66	0.015	4.5	177.3	6.6	27	<0.1	21.2	10.9	297	2.99	7	2.0	<0.1	6.7	440	<0.1	1.5	<0.1	87

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 3 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041528	Drill Core	2.76	0.045	12.7	25	1.04	797	0.277	6.86	2.426	2.65	1.1	15.2	31	1.9	12.8	3.1	0.3	1	7	23.9
1041529	Drill Core	2.40	0.047	15.5	39	0.98	774	0.303	6.90	2.759	2.57	0.8	14.9	35	2.1	12.9	3.2	0.3	1	8	23.1
1041530	Drill Core	3.85	0.048	11.7	28	0.82	769	0.289	7.30	2.207	2.45	1.9	13.6	28	1.3	14.8	2.8	0.3	1	8	22.8
1041531	Drill Core	2.56	0.049	10.8	32	0.80	745	0.275	6.98	2.507	2.69	3.6	12.2	24	1.7	9.8	2.9	0.3	1	9	22.9
1041532	Drill Core	2.66	0.043	7.9	22	1.08	544	0.246	6.20	1.549	2.41	1.7	12.6	18	1.3	10.3	2.6	0.2	1	8	66.3
1041533	Drill Core	2.40	0.045	9.1	30	0.82	514	0.256	6.85	1.992	2.61	1.6	11.9	20	1.5	8.4	2.8	0.3	1	8	36.4
1041534	Drill Core	2.07	0.043	8.9	26	0.80	734	0.248	6.62	2.708	2.73	1.8	15.2	21	1.9	9.6	2.9	0.3	<1	7	18.4
1041535	Drill Core	2.60	0.044	7.3	28	0.91	632	0.254	6.54	2.361	2.35	1.4	12.7	17	1.4	9.2	2.7	0.2	<1	7	29.4
1041536	Drill Core	2.40	0.044	8.8	24	0.89	694	0.259	6.67	2.620	2.62	1.0	14.5	20	1.7	9.4	2.9	0.3	<1	8	22.0
1041537	Drill Core	2.64	0.043	10.1	32	0.84	769	0.256	6.62	2.480	2.59	1.2	15.3	22	1.4	9.7	2.8	0.3	1	8	26.9
1041538	Drill Core	3.06	0.046	9.5	23	0.94	666	0.251	6.73	2.146	2.40	1.2	13.4	22	1.3	10.1	2.4	0.2	<1	8	45.9
1041539	Drill Core	2.29	0.043	9.3	33	1.02	750	0.262	6.85	2.790	2.73	0.7	13.9	22	1.5	10.0	3.0	0.3	<1	8	22.5
1041540	Rock	35.42	0.003	0.6	<1	1.63	4	0.001	0.02	0.003	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1	<1	<1	0.3
1041541	Drill Core	2.46	0.044	8.5	34	1.00	770	0.263	6.81	2.736	2.84	0.5	14.1	20	1.4	10.6	3.0	0.2	1	8	26.7
1041542	Drill Core	2.54	0.042	10.9	25	0.95	829	0.260	6.58	2.697	2.80	0.6	15.3	25	1.4	10.5	3.1	0.3	<1	8	20.7
1041543	Drill Core	2.53	0.044	8.2	33	0.88	698	0.259	6.57	2.743	2.48	0.8	13.2	20	1.4	9.4	3.0	0.3	<1	8	20.0
1041544	Drill Core	2.53	0.046	9.2	26	1.01	763	0.255	6.87	2.760	2.67	0.6	13.6	21	1.3	10.3	2.9	0.2	1	8	21.4
1041545	Drill Core	2.73	0.050	12.7	39	1.16	752	0.278	7.03	2.897	2.54	0.7	12.9	29	1.4	10.7	3.0	0.2	<1	9	28.2
1041546	Drill Core	2.80	0.046	9.2	27	1.10	749	0.265	6.83	2.813	2.56	0.4	12.1	22	1.3	9.7	2.7	0.2	<1	8	22.9
1041547	Drill Core	2.77	0.046	8.3	36	1.08	813	0.263	6.82	2.662	2.55	0.7	11.7	21	1.3	9.7	2.7	0.2	1	8	23.0
1041548	Drill Core	2.52	0.042	6.8	24	0.94	698	0.252	6.84	2.705	2.34	0.8	10.6	17	1.5	9.3	2.7	0.2	<1	7	21.7
1041549	Drill Core	2.88	0.049	10.8	30	0.88	774	0.282	6.80	2.527	2.31	1.8	12.9	24	1.8	9.8	2.9	0.2	<1	8	24.2
1041550	Drill Core	2.97	0.046	9.5	29	0.99	705	0.270	6.69	2.715	2.54	2.7	15.6	23	1.4	9.3	2.6	0.2	<1	8	19.5
1041551	Drill Core	3.24	0.047	9.6	31	1.25	757	0.252	6.84	2.720	2.27	1.9	13.1	22	1.3	9.6	2.5	0.2	<1	8	28.3
1041552	Drill Core	2.94	0.050	10.4	28	1.04	704	0.268	6.75	2.663	2.27	1.9	13.2	24	1.5	9.4	2.6	0.2	<1	9	26.7
1041553	Drill Core	3.30	0.051	9.8	31	1.02	785	0.257	7.03	2.704	2.32	1.5	13.5	23	1.2	10.1	2.5	0.2	<1	9	23.2
1041554	Drill Core	3.67	0.037	9.2	18	1.33	1004	0.200	6.19	2.333	2.46	1.5	14.8	21	0.9	11.2	2.3	0.3	<1	7	28.5
1041555	Drill Core	2.75	0.052	9.4	32	1.08	735	0.266	7.23	2.990	2.26	2.0	13.0	22	1.1	10.2	2.5	0.2	<1	9	27.3
1041556	Drill Core	2.60	0.051	9.6	29	1.25	817	0.288	6.89	2.993	2.44	1.5	11.9	23	1.5	9.9	2.6	0.2	<1	9	25.0
1041557	Drill Core	2.89	0.051	10.4	29	1.07	794	0.278	7.12	2.888	2.25	1.2	12.7	25	1.7	9.7	2.8	0.2	<1	9	23.8

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 3 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041528	Drill Core	<0.1	79.6	0.7
1041529	Drill Core	<0.1	78.0	0.8
1041530	Drill Core	<0.1	77.7	0.6
1041531	Drill Core	<0.1	73.9	0.6
1041532	Drill Core	<0.1	90.0	0.6
1041533	Drill Core	<0.1	81.2	0.6
1041534	Drill Core	<0.1	72.2	0.7
1041535	Drill Core	<0.1	74.4	0.6
1041536	Drill Core	<0.1	78.6	0.7
1041537	Drill Core	<0.1	71.9	0.6
1041538	Drill Core	<0.1	67.9	0.6
1041539	Drill Core	<0.1	71.8	0.7
1041540	Rock	<0.1	0.1	<0.1
1041541	Drill Core	<0.1	73.9	0.6
1041542	Drill Core	<0.1	74.5	0.7
1041543	Drill Core	<0.1	65.7	0.7
1041544	Drill Core	<0.1	66.6	0.6
1041545	Drill Core	<0.1	70.5	0.6
1041546	Drill Core	<0.1	62.8	0.6
1041547	Drill Core	<0.1	62.9	0.6
1041548	Drill Core	<0.1	63.1	0.5
1041549	Drill Core	<0.1	71.4	0.6
1041550	Drill Core	<0.1	65.0	0.7
1041551	Drill Core	<0.1	62.9	0.6
1041552	Drill Core	<0.1	63.0	0.6
1041553	Drill Core	<0.1	62.2	0.7
1041554	Drill Core	<0.1	72.3	0.7
1041555	Drill Core	<0.1	65.1	0.6
1041556	Drill Core	<0.1	67.4	0.6
1041557	Drill Core	<0.1	67.8	0.5



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 4 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041558	Drill Core	6.23	<0.005	14.1	60.5	6.2	24	<0.1	18.3	9.5	273	2.60	6	1.9	<0.1	7.3	528	0.1	1.1	<0.1	85
1041559	Drill Core	5.25	<0.005	1.9	132.1	7.4	25	<0.1	16.4	9.7	362	2.39	10	2.0	<0.1	8.5	380	0.1	1.8	<0.1	70
1041560	Rock Pulp	0.11	1.590	281.1	9610	76.3	128	5.1	33.4	19.7	350	4.78	33	5.4	1.7	10.3	186	2.8	21.0	3.9	95
1041561	Drill Core	7.19	0.010	1.3	142.6	7.0	23	<0.1	14.9	8.6	283	2.14	9	1.6	<0.1	7.9	331	0.1	2.3	<0.1	69
1041562	Drill Core	5.64	0.011	6.1	164.2	7.7	30	0.1	14.8	7.7	274	2.04	11	1.6	<0.1	8.5	422	<0.1	2.0	<0.1	73
1041563	Drill Core	7.33	<0.005	1.5	91.3	8.7	37	<0.1	16.1	8.5	274	2.33	8	1.8	<0.1	8.5	376	<0.1	2.0	<0.1	70
1041564	Drill Core	6.83	<0.005	1.3	83.1	8.2	28	<0.1	16.3	8.7	273	2.30	8	1.9	<0.1	8.8	365	<0.1	2.8	<0.1	72
1041565	Drill Core	7.12	<0.005	1.1	29.6	9.4	41	0.1	16.9	10.1	444	2.41	11	1.4	<0.1	8.0	256	<0.1	3.3	<0.1	62
1041566	Drill Core	5.99	0.038	1.5	147.9	9.6	34	<0.1	13.6	7.8	256	1.92	15	2.7	<0.1	8.2	326	0.1	1.4	0.1	58
1041567	Drill Core	8.18	<0.005	1.8	53.8	7.2	30	<0.1	16.7	9.7	312	2.45	4	3.4	<0.1	9.2	409	<0.1	0.3	0.3	76
1041568	Drill Core	7.86	0.038	2.7	79.6	8.0	33	<0.1	18.7	10.4	339	2.49	3	3.7	<0.1	9.1	404	0.1	0.3	0.3	78
1041569	Drill Core	8.34	0.015	3.2	89.2	7.7	33	<0.1	18.6	11.7	357	2.59	5	3.8	<0.1	9.4	414	<0.1	0.5	0.2	80
1041570	Drill Core	7.64	<0.005	1.6	35.1	7.1	30	<0.1	17.0	10.3	347	2.43	3	3.0	<0.1	9.4	378	<0.1	0.7	0.1	75
1041571	Drill Core	6.97	<0.005	1.4	54.0	7.1	20	<0.1	10.2	5.8	181	1.63	5	5.4	<0.1	15.7	289	<0.1	0.9	<0.1	45
1041572	Drill Core	7.73	0.007	1.3	54.6	9.1	33	<0.1	17.8	10.0	333	2.33	7	4.9	<0.1	12.0	371	<0.1	1.7	0.1	71
1041573	Drill Core	7.00	<0.005	1.1	47.9	8.0	32	<0.1	19.5	10.4	332	2.60	7	2.8	<0.1	7.9	352	<0.1	3.9	<0.1	80
1041574	Drill Core	6.19	<0.005	0.9	58.4	8.8	25	<0.1	15.4	8.6	232	2.13	7	3.1	<0.1	9.9	394	<0.1	1.0	<0.1	74
1041575	Drill Core	7.22	0.052	1.2	59.4	7.7	24	<0.1	14.5	8.2	218	2.01	5	3.2	<0.1	13.3	365	<0.1	1.5	<0.1	66
1041576	Drill Core	7.85	0.019	1.6	98.8	7.0	25	<0.1	13.7	7.9	231	2.01	6	4.7	<0.1	12.6	346	<0.1	0.6	<0.1	58
1041577	Drill Core	6.64	0.014	2.1	78.4	7.3	26	<0.1	13.9	8.8	257	2.06	9	3.6	<0.1	12.0	294	<0.1	1.2	<0.1	57
1041578	Drill Core	7.29	0.059	9.1	379.3	8.3	27	0.2	13.4	8.7	273	2.11	10	3.3	<0.1	9.9	272	<0.1	1.5	<0.1	63
1041579	Drill Core	2.89	0.007	1.2	43.9	7.4	25	<0.1	14.9	8.4	240	2.24	7	4.0	<0.1	10.5	382	<0.1	0.6	<0.1	65
1041580	Drill Core	2.66	0.005	1.1	55.6	7.3	26	<0.1	15.4	8.3	249	2.20	7	4.2	<0.1	9.7	394	<0.1	0.5	<0.1	64
1041581	Drill Core	5.65	0.027	1.7	204.2	7.6	27	0.5	15.0	10.1	244	2.17	6	3.8	0.8	11.3	384	<0.1	0.5	<0.1	64
1041582	Drill Core	7.73	0.006	1.3	47.0	8.3	36	<0.1	15.6	8.6	281	2.13	6	2.9	<0.1	11.0	370	<0.1	1.2	<0.1	65
1041583	Drill Core	7.51	0.008	1.5	113.7	8.6	36	0.1	17.5	9.2	331	2.31	9	5.1	<0.1	10.8	288	<0.1	2.8	<0.1	64
1041584	Drill Core	8.04	<0.005	1.7	86.2	7.9	75	0.4	15.7	10.3	297	2.25	5	4.5	0.9	11.0	353	<0.1	0.9	<0.1	67
1041585	Drill Core	7.93	0.006	2.5	166.6	8.9	34	<0.1	14.9	9.2	295	2.05	9	4.0	<0.1	12.4	316	0.1	2.8	<0.1	62
1041586	Drill Core	7.32	<0.005	1.5	50.7	7.2	24	<0.1	14.9	8.3	265	2.03	5	2.7	<0.1	10.2	355	<0.1	1.1	<0.1	62
1041587	Drill Core	7.14	<0.005	1.9	43.2	7.6	30	0.1	13.5	9.7	559	2.17	6	12.6	<0.1	10.7	323	0.1	2.2	<0.1	55

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 4 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041558	Drill Core	2.72	0.053	9.1	27	0.95	748	0.287	7.05	3.000	2.33	4.3	14.0	22	1.3	9.4	2.8	0.2	<1	9	21.8
1041559	Drill Core	3.73	0.043	7.7	23	1.01	885	0.238	6.53	2.342	2.18	3.5	9.4	19	1.1	11.7	2.5	0.2	<1	7	27.3
1041560	Rock Pulp	1.46	0.077	29.2	102	0.95	77	0.194	6.56	0.761	3.58	18.6	24.9	54	4.1	11.0	3.3	0.2	1	10	13.5
1041561	Drill Core	3.00	0.042	6.5	22	0.81	561	0.233	6.69	2.622	1.89	1.7	8.4	17	1.4	9.4	2.4	0.2	<1	8	28.7
1041562	Drill Core	3.09	0.044	7.0	23	0.73	521	0.244	6.90	2.956	1.53	3.9	9.5	19	2.2	10.1	2.6	0.2	<1	8	25.0
1041563	Drill Core	2.60	0.042	7.2	23	0.63	918	0.242	6.65	2.577	2.47	2.4	10.3	18	1.3	8.3	2.7	0.3	<1	7	19.0
1041564	Drill Core	2.68	0.043	8.5	24	0.76	693	0.244	6.68	2.540	2.55	3.2	9.6	21	1.1	8.4	2.7	0.3	<1	8	40.6
1041565	Drill Core	3.86	0.041	8.1	19	1.12	756	0.214	6.15	1.916	2.22	1.9	8.9	20	0.9	9.6	2.4	0.2	<1	7	44.7
1041566	Drill Core	2.56	0.037	8.4	17	0.68	723	0.211	6.37	2.395	2.48	0.6	11.2	20	0.7	8.4	2.6	0.2	<1	6	23.8
1041567	Drill Core	2.52	0.044	13.0	21	0.96	767	0.278	7.19	2.688	2.71	1.0	15.7	26	1.1	11.0	3.5	0.3	1	8	19.4
1041568	Drill Core	2.42	0.042	11.0	25	1.03	787	0.275	7.13	2.654	2.20	0.7	14.3	24	0.8	10.4	3.1	0.3	1	8	22.4
1041569	Drill Core	2.58	0.044	13.9	24	1.06	788	0.271	7.67	2.672	2.68	0.8	13.1	31	0.9	11.6	3.2	0.2	1	8	20.7
1041570	Drill Core	2.66	0.040	12.4	23	0.86	755	0.257	7.31	2.585	2.63	0.8	10.3	27	0.8	11.7	2.9	0.3	1	8	19.7
1041571	Drill Core	1.60	0.027	11.9	14	0.46	672	0.191	6.73	2.418	3.34	1.9	15.8	26	0.9	8.8	3.8	0.4	1	4	16.0
1041572	Drill Core	2.87	0.040	13.8	20	0.81	708	0.251	7.18	2.455	2.81	3.7	13.1	32	1.1	12.3	3.3	0.3	1	7	21.9
1041573	Drill Core	3.11	0.044	9.5	23	1.05	1095	0.273	7.37	2.232	2.45	1.2	11.6	24	1.5	11.4	2.8	0.3	<1	8	24.5
1041574	Drill Core	2.13	0.041	10.8	22	0.66	711	0.258	7.08	2.652	2.68	3.0	14.9	25	1.4	8.7	3.3	0.3	<1	7	16.4
1041575	Drill Core	1.86	0.038	12.0	20	0.56	698	0.240	7.40	2.670	2.90	3.0	16.6	26	1.1	8.3	3.6	0.3	1	6	16.1
1041576	Drill Core	1.82	0.037	13.8	19	0.72	720	0.219	7.01	2.733	3.10	1.2	16.1	30	1.2	8.8	3.1	0.3	<1	6	19.1
1041577	Drill Core	2.14	0.034	10.4	18	0.53	692	0.219	6.86	2.369	3.02	1.8	17.0	25	1.2	9.8	3.2	0.4	<1	6	17.6
1041578	Drill Core	2.51	0.038	13.2	19	0.63	626	0.229	6.91	2.242	2.85	1.0	18.9	30	1.1	10.1	3.2	0.3	<1	7	17.3
1041579	Drill Core	2.04	0.036	10.6	27	0.86	727	0.237	6.84	2.490	2.91	0.7	18.6	25	1.2	10.2	3.1	0.3	1	7	23.4
1041580	Drill Core	2.15	0.035	12.0	20	0.84	731	0.232	6.83	2.458	2.96	0.7	21.0	28	1.5	11.2	3.3	0.3	<1	7	23.7
1041581	Drill Core	2.04	0.037	12.0	20	0.73	745	0.235	6.87	2.573	2.93	1.6	17.6	27	1.2	9.4	3.2	0.3	<1	6	21.0
1041582	Drill Core	2.22	0.041	13.1	26	0.73	796	0.247	8.12	2.887	2.98	1.5	17.9	30	1.1	11.0	3.3	0.3	2	7	20.0
1041583	Drill Core	2.71	0.035	12.6	20	0.77	844	0.229	7.01	2.238	2.79	1.2	17.4	28	1.0	11.1	2.9	0.3	1	7	19.9
1041584	Drill Core	2.38	0.038	14.2	27	0.91	825	0.241	7.29	2.499	2.91	0.8	17.1	31	1.0	10.8	3.0	0.3	1	7	29.8
1041585	Drill Core	2.17	0.033	13.6	19	0.77	662	0.226	7.29	2.357	2.93	1.0	17.3	29	1.0	10.7	3.2	0.3	<1	7	19.8
1041586	Drill Core	2.08	0.035	11.5	26	0.73	777	0.233	7.31	2.550	3.00	1.8	17.8	28	0.8	9.8	3.0	0.3	<1	7	21.1
1041587	Drill Core	4.34	0.030	12.9	16	1.20	740	0.196	6.52	2.129	2.59	3.2	16.9	28	0.7	12.5	2.9	0.3	<1	6	16.9

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 05, 2011

Page: 4 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041558	Drill Core	<0.1	69.9	0.6
1041559	Drill Core	<0.1	63.7	0.4
1041560	Rock Pulp	2.4	130.3	0.8
1041561	Drill Core	<0.1	59.0	0.4
1041562	Drill Core	<0.1	52.6	0.5
1041563	Drill Core	<0.1	68.7	0.5
1041564	Drill Core	<0.1	71.8	0.5
1041565	Drill Core	<0.1	72.3	0.4
1041566	Drill Core	<0.1	70.5	0.5
1041567	Drill Core	<0.1	80.2	0.6
1041568	Drill Core	<0.1	69.5	0.7
1041569	Drill Core	<0.1	94.2	0.6
1041570	Drill Core	<0.1	84.3	0.5
1041571	Drill Core	<0.1	105.7	0.6
1041572	Drill Core	<0.1	87.1	0.7
1041573	Drill Core	<0.1	89.2	0.6
1041574	Drill Core	<0.1	81.8	0.7
1041575	Drill Core	<0.1	92.3	0.7
1041576	Drill Core	<0.1	91.3	0.7
1041577	Drill Core	<0.1	88.6	0.8
1041578	Drill Core	<0.1	90.8	0.7
1041579	Drill Core	<0.1	85.3	0.8
1041580	Drill Core	<0.1	87.2	1.0
1041581	Drill Core	<0.1	85.1	0.8
1041582	Drill Core	<0.1	91.8	0.8
1041583	Drill Core	<0.1	91.8	0.9
1041584	Drill Core	<0.1	94.6	0.6
1041585	Drill Core	<0.1	100.0	0.8
1041586	Drill Core	<0.1	101.3	0.7
1041587	Drill Core	<0.1	93.5	0.7



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 5 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041588	Drill Core	7.48	<0.005	1.9	73.4	7.5	30	<0.1	16.1	9.5	342	2.30	4	3.5	<0.1	10.0	383	<0.1	1.0	<0.1	70
1041589	Drill Core	8.60	<0.005	2.2	59.2	8.9	31	<0.1	17.8	10.1	420	2.29	6	4.9	<0.1	12.8	328	0.1	3.2	<0.1	61
1041590	Drill Core	7.07	<0.005	1.6	33.8	8.4	30	<0.1	15.5	9.2	504	2.01	6	6.3	<0.1	10.7	296	<0.1	2.5	<0.1	60
1041591	Drill Core	7.13	<0.005	1.9	80.7	8.4	32	<0.1	18.9	9.8	361	2.41	6	2.5	<0.1	9.5	394	0.1	2.0	<0.1	75
1041592	Drill Core	7.67	<0.005	2.4	37.5	9.3	38	<0.1	21.0	11.7	503	2.66	4	3.2	<0.1	8.3	411	<0.1	1.9	<0.1	82
1041593	Drill Core	7.25	<0.005	2.4	38.0	10.7	42	<0.1	20.7	10.6	404	2.64	5	3.1	<0.1	8.5	442	<0.1	1.4	<0.1	89
1041594	Drill Core	6.71	<0.005	3.7	58.1	13.9	40	<0.1	17.8	11.0	406	2.30	5	2.9	<0.1	9.2	369	0.2	1.6	<0.1	74



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 5 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005904.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041588	Drill Core	2.38	0.040	12.1	28	0.94	737	0.245	7.29	2.547	2.72	1.1	17.0	28	0.8	10.5	3.1	0.3	<1	7	23.9
1041589	Drill Core	2.99	0.037	12.1	19	0.85	762	0.219	6.81	2.411	2.74	1.6	15.4	27	0.6	10.5	3.2	0.3	<1	6	24.8
1041590	Drill Core	3.72	0.035	10.9	21	0.72	641	0.213	6.72	2.262	2.56	3.3	13.0	25	0.6	9.0	2.6	0.2	<1	6	17.9
1041591	Drill Core	2.33	0.045	10.5	22	0.68	767	0.238	7.21	2.631	2.55	2.5	13.4	25	0.8	8.8	2.7	0.2	1	7	17.2
1041592	Drill Core	3.24	0.045	11.7	31	0.91	733	0.257	7.55	2.631	2.37	2.6	13.7	28	0.7	11.0	2.7	0.2	<1	8	24.3
1041593	Drill Core	2.86	0.049	10.6	26	1.00	738	0.278	7.62	2.711	2.37	5.3	14.1	24	0.9	9.3	3.0	0.2	<1	9	20.4
1041594	Drill Core	3.05	0.043	10.7	23	0.73	750	0.257	7.57	2.337	2.65	13.7	13.4	25	0.9	8.7	2.7	0.3	<1	7	20.3



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 05, 2011

Page: 5 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005904.1

	Method	1EX	1EX	1EX
	Analyte	S	Rb	Hf
	Unit	%	ppm	ppm
	MDL	0.1	0.1	0.1
1041588	Drill Core	<0.1	92.1	0.7
1041589	Drill Core	<0.1	95.6	0.7
1041590	Drill Core	<0.1	92.7	0.6
1041591	Drill Core	<0.1	85.4	0.6
1041592	Drill Core	<0.1	78.0	0.7
1041593	Drill Core	<0.1	76.6	0.7
1041594	Drill Core	<0.1	95.2	0.6



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 05, 2011

Page: 1 of 2 Part 1

QUALITY CONTROL REPORT

VAN11005904.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
Pulp Duplicates																					
1041504	Drill Core	7.33	<0.005	5.0	82.5	8.6	39	0.1	18.7	9.4	366	2.54	11	1.1	<0.1	6.4	203	0.1	3.5	<0.1	85
REP 1041504	QC			4.5	84.7	8.9	38	0.1	17.6	8.9	362	2.60	10	1.2	<0.1	6.6	200	<0.1	3.8	<0.1	83
1041535	Drill Core	5.58	0.011	50.6	381.0	7.6	31	0.3	18.5	10.8	278	2.35	21	2.4	<0.1	8.3	285	<0.1	3.8	0.1	69
REP 1041535	QC			40.9	371.3	7.7	33	0.3	18.6	10.5	264	2.31	20	2.6	<0.1	8.5	290	<0.1	3.6	<0.1	69
1041560	Rock Pulp	0.11	1.590	281.1	9610	76.3	128	5.1	33.4	19.7	350	4.78	33	5.4	1.7	10.3	186	2.8	21.0	3.9	95
REP 1041560	QC		1.511																		
1041579	Drill Core	2.89	0.007	1.2	43.9	7.4	25	<0.1	14.9	8.4	240	2.24	7	4.0	<0.1	10.5	382	<0.1	0.6	<0.1	65
REP 1041579	QC			1.1	43.5	7.4	26	<0.1	15.0	8.8	246	2.32	8	4.4	<0.1	10.7	398	<0.1	0.6	<0.1	67
1041589	Drill Core	8.60	<0.005	2.2	59.2	8.9	31	<0.1	17.8	10.1	420	2.29	6	4.9	<0.1	12.8	328	0.1	3.2	<0.1	61
REP 1041589	QC		<0.005																		
Core Reject Duplicates																					
1041525	Drill Core	6.70	0.005	13.3	198.3	5.6	27	<0.1	11.7	6.0	236	1.62	12	1.6	<0.1	11.5	180	<0.1	2.2	<0.1	51
DUP 1041525	QC		<0.005	16.8	194.4	6.2	25	0.1	12.8	5.8	234	1.66	11	1.7	<0.1	11.5	186	0.2	2.7	<0.1	51
Reference Materials																					
STD OREAS24P	Standard			1.4	50.0	2.4	122	0.1	135.8	42.3	1085	7.28	4	0.7	<0.1	3.0	328	0.2	<0.1	<0.1	150
STD OREAS24P	Standard			1.3	47.2	2.9	110	<0.1	133.3	42.6	1088	7.29	2	0.6	<0.1	2.7	348	0.1	0.1	<0.1	161
STD OREAS24P	Standard			1.3	47.8	2.8	109	<0.1	132.0	42.3	1045	7.06	4	0.7	<0.1	3.0	358	0.1	<0.1	<0.1	147
STD OREAS45C	Standard			2.0	623.4	30.1	90	0.3	330.2	99.1	1135	16.74	12	2.9	<0.1	12.4	36	0.3	0.9	0.2	256
STD OREAS45C	Standard			2.0	611.6	23.4	78	0.3	321.2	101.2	1109	17.09	11	2.2	<0.1	10.1	35	0.2	0.8	0.2	266
STD OREAS45C	Standard			1.9	577.2	25.0	82	0.3	303.2	95.0	1125	16.40	12	2.4	<0.1	10.8	38	0.2	0.8	0.2	242
STD OXH82	Standard		1.275																		
STD OXH82	Standard		1.316																		
STD OXH82	Standard		1.344																		
STD OXH82	Standard		1.300																		
STD OXH82	Standard		1.292																		
STD OXK79	Standard		3.663																		
STD OXK79	Standard		3.615																		
STD OXK79	Standard		3.569																		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 05, 2011

Page: 1 of 2 Part 2

QUALITY CONTROL REPORT

VAN11005904.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1	
Pulp Duplicates																					
1041504	Drill Core	3.43	0.043	8.2	31	1.19	692	0.286	6.59	1.880	1.95	3.1	7.5	22	1.4	16.8	3.1	0.2	<1	8	47.9
REP 1041504	QC	3.30	0.044	8.3	30	1.14	673	0.286	6.38	1.960	1.94	2.8	7.8	21	1.6	16.1	3.0	0.2	1	8	45.3
1041535	Drill Core	2.60	0.044	7.3	28	0.91	632	0.254	6.54	2.361	2.35	1.4	12.7	17	1.4	9.2	2.7	0.2	<1	7	29.4
REP 1041535	QC	2.62	0.047	7.6	27	0.91	638	0.247	6.61	2.353	2.37	1.3	13.1	18	1.4	9.2	2.7	0.2	<1	7	29.5
1041560	Rock Pulp	1.46	0.077	29.2	102	0.95	77	0.194	6.56	0.761	3.58	18.6	24.9	54	4.1	11.0	3.3	0.2	1	10	13.5
REP 1041560	QC																				
1041579	Drill Core	2.04	0.036	10.6	27	0.86	727	0.237	6.84	2.490	2.91	0.7	18.6	25	1.2	10.2	3.1	0.3	1	7	23.4
REP 1041579	QC	2.12	0.035	10.6	28	0.89	758	0.241	7.33	2.624	3.01	0.7	20.0	26	1.2	10.8	3.2	0.3	1	7	23.2
1041589	Drill Core	2.99	0.037	12.1	19	0.85	762	0.219	6.81	2.411	2.74	1.6	15.4	27	0.6	10.5	3.2	0.3	<1	6	24.8
REP 1041589	QC																				
Core Reject Duplicates																					
1041525	Drill Core	2.57	0.029	7.7	18	0.58	758	0.217	6.19	1.594	2.97	1.8	16.1	17	1.1	9.2	3.1	0.3	1	5	48.6
DUP 1041525	QC	2.51	0.028	6.8	16	0.59	793	0.213	6.17	1.647	2.97	1.8	15.9	15	1.0	9.2	2.8	0.3	<1	4	51.0
Reference Materials																					
STD OREAS24P	Standard	5.65	0.128	18.6	205	3.94	272	1.114	7.44	2.284	0.66	0.4	127.1	36	1.6	23.3	18.4	1.1	<1	19	7.4
STD OREAS24P	Standard	5.53	0.130	17.4	205	4.07	262	1.063	7.52	2.367	0.64	0.4	129.6	36	1.6	20.2	18.7	1.0	1	20	7.3
STD OREAS24P	Standard	5.53	0.128	18.3	192	3.89	276	1.065	7.29	2.387	0.61	0.5	127.5	35	1.5	20.3	18.1	1.1	1	19	7.4
STD OREAS45C	Standard	0.50	0.048	27.7	865	0.27	296	1.216	7.10	0.107	0.36	1.1	162.5	52	2.8	14.3	22.4	1.4	<1	57	16.2
STD OREAS45C	Standard	0.48	0.051	24.2	934	0.26	268	1.182	7.05	0.101	0.34	0.9	163.8	49	3.0	12.8	22.5	1.3	<1	59	15.6
STD OREAS45C	Standard	0.44	0.050	26.3	895	0.23	282	1.127	6.82	0.095	0.32	1.0	165.3	50	3.1	12.5	21.6	1.4	<1	56	15.5
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXK79	Standard																				
STD OXK79	Standard																				
STD OXK79	Standard																				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 05, 2011

Page: 1 of 2 **Part** 3

QUALITY CONTROL REPORT

VAN11005904.1

Method	1EX	1EX	1EX
Analyte	S	Rb	Hf
Unit	%	ppm	ppm
MDL	0.1	0.1	0.1
Pulp Duplicates			
1041504	Drill Core	<0.1	82.0 0.4
REP 1041504	QC	<0.1	78.7 0.3
1041535	Drill Core	<0.1	74.4 0.6
REP 1041535	QC	<0.1	78.2 0.6
1041560	Rock Pulp	2.4	130.3 0.8
REP 1041560	QC		
1041579	Drill Core	<0.1	85.3 0.8
REP 1041579	QC	<0.1	91.4 0.9
1041589	Drill Core	<0.1	95.6 0.7
REP 1041589	QC		
Core Reject Duplicates			
1041525	Drill Core	<0.1	88.7 0.6
DUP 1041525	QC	<0.1	87.5 0.6
Reference Materials			
STD OREAS24P	Standard	<0.1	20.1 3.2
STD OREAS24P	Standard	<0.1	20.9 3.5
STD OREAS24P	Standard	<0.1	20.0 3.3
STD OREAS45C	Standard	<0.1	22.7 4.4
STD OREAS45C	Standard	<0.1	23.1 4.3
STD OREAS45C	Standard	<0.1	23.8 4.1
STD OXH82	Standard		
STD OXH82	Standard		
STD OXH82	Standard		
STD OXH82	Standard		
STD OXH82	Standard		
STD OXK79	Standard		
STD OXK79	Standard		
STD OXK79	Standard		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 05, 2011

Page: 2 of 2 Part 1

QUALITY CONTROL REPORT

VAN11005904.1

		WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
STD OXK79	Standard	3.338																			
STD OXK79	Standard	3.760																			
STD OXH82 Expected		1.278																			
STD OXK79 Expected		3.532																			
STD OREAS24P Expected				1.5	52	2.9	119	0.06	141	44	1100	7.53	1.2	0.75		2.85	403	0.15	0.09		158
STD OREAS45C Expected				2.26	620	24	83	0.28	333	104	1160	18.33	10.1	2.4	0.045	10.2	36.4	0.15	0.79	0.21	270
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank	<0.005																			
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
Prep Wash																					
G1	Prep Blank	<0.01	0.010	0.3	4.3	22.1	59	<0.1	2.4	4.8	807	2.27	2	3.3	<0.1	10.1	836	<0.1	<0.1	0.2	45
G1	Prep Blank	<0.01	0.006	0.1	3.7	22.5	59	<0.1	2.3	4.9	802	2.36	2	3.1	<0.1	11.4	802	<0.1	<0.1	0.2	46



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 05, 2011

Page: 2 of 2 **Part** 3

QUALITY CONTROL REPORT

VAN11005904.1

		1EX S %	1EX Rb ppm	1EX Hf ppm
		0.1	0.1	0.1
STD OXK79	Standard			
STD OXK79	Standard			
STD OXH82 Expected				
STD OXK79 Expected				
STD OREAS24P Expected			22.4	3.6
STD OREAS45C Expected		0.021	24	4.27
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
Prep Wash				
G1	Prep Blank	<0.1	131.4	0.7
G1	Prep Blank	<0.1	125.8	0.7



1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Submitted By: Tim Johnson
Receiving Lab: Canada-Vancouver
Received: November 01, 2011
Report Date: December 08, 2011
Page: 1 of 5

CERTIFICATE OF ANALYSIS

VAN11005905.1

CLIENT JOB INFORMATION

Project: Taseko
Shipment ID:
P.O. Number
Number of Samples: 110

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	109	Crush, split and pulverize 250 g rock to 200 mesh			VAN
G601	110	Fire Assay fusion Au by ICP-ES	30	Completed	VAN
1EX	110	4 Acid digestion ICP-MS analysis	0.25	Completed	VAN

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0
Canada

CC: Mathius Westphal



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 2 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041642	Drill Core	5.42	0.023	5.7	633.8	9.8	39	<0.1	21.7	10.9	302	2.49	8	4.2	<0.1	9.1	368	<0.1	0.3	0.1	100
1041643	Drill Core	8.10	0.016	5.0	300.2	8.2	35	<0.1	21.8	11.5	317	2.51	9	2.4	<0.1	7.6	390	<0.1	0.3	<0.1	103
1041644	Drill Core	7.81	0.010	4.5	148.4	8.3	37	<0.1	22.2	11.7	297	2.57	9	2.5	<0.1	7.8	380	<0.1	0.4	<0.1	107
1041645	Drill Core	7.49	0.031	8.6	525.0	8.5	36	<0.1	22.5	10.8	266	2.39	9	4.0	<0.1	6.8	349	0.1	0.4	0.1	105
1041646	Drill Core	7.14	0.024	4.4	262.9	8.2	38	<0.1	21.3	11.1	308	2.47	8	3.5	<0.1	6.2	379	<0.1	0.4	<0.1	102
1041647	Drill Core	4.12	0.012	4.6	203.1	7.0	30	<0.1	21.4	10.0	203	2.08	9	4.1	<0.1	12.8	327	<0.1	0.4	<0.1	101
1041648	Drill Core	3.52	0.011	5.4	120.1	6.5	25	<0.1	18.4	8.9	165	1.53	10	2.5	<0.1	11.2	414	<0.1	0.3	<0.1	80
1041649	Drill Core	8.13	0.014	9.0	195.4	7.1	24	<0.1	20.3	8.7	158	1.60	13	1.9	<0.1	9.0	402	<0.1	0.2	<0.1	73
1041650	Drill Core	5.63	0.014	28.8	238.5	7.0	19	<0.1	13.1	6.0	105	1.10	10	4.2	<0.1	14.2	329	<0.1	0.3	<0.1	52
1041651	Drill Core	2.49	<0.005	1.9	52.6	6.2	21	<0.1	12.2	6.0	131	1.49	5	2.6	<0.1	11.5	341	<0.1	0.2	<0.1	55
1041652	Drill Core	2.17	0.028	39.1	406.0	7.7	25	<0.1	17.8	8.5	173	1.78	8	2.2	<0.1	9.9	399	<0.1	0.2	<0.1	77
1041653	Drill Core	2.54	0.009	3.3	228.6	7.3	27	<0.1	18.4	9.2	202	2.07	6	1.9	<0.1	8.8	394	<0.1	0.2	<0.1	82
1041654	Drill Core	2.28	0.015	4.9	285.1	7.4	25	<0.1	18.8	8.7	171	1.81	12	2.7	<0.1	10.1	408	<0.1	0.2	<0.1	89
1041655	Drill Core	4.05	<0.005	1.4	156.2	6.7	26	<0.1	19.8	9.0	200	2.15	8	1.6	<0.1	8.0	391	<0.1	0.2	<0.1	85
1041656	Drill Core	4.81	<0.005	1.5	56.1	7.0	28	<0.1	18.9	9.4	208	2.10	6	1.6	<0.1	9.4	402	<0.1	0.2	<0.1	89
1041657	Drill Core	2.31	0.006	1.8	182.2	7.3	33	<0.1	18.6	9.1	205	1.94	5	1.5	<0.1	8.6	369	<0.1	0.1	<0.1	76
1041658	Drill Core	3.58	0.009	11.9	208.2	6.9	25	<0.1	20.9	9.4	185	1.89	4	1.5	<0.1	8.5	381	<0.1	0.2	<0.1	85
1041659	Drill Core	3.56	0.007	4.0	191.2	6.6	23	<0.1	20.2	9.5	184	1.82	6	1.7	<0.1	9.1	398	<0.1	0.2	<0.1	79
1041660	Rock	0.72	<0.005	<0.1	0.6	<0.1	<1	<0.1	0.4	<0.2	26	<0.01	7	1.3	<0.1	<0.1	4135	<0.1	<0.1	<0.1	<1
1041661	Drill Core	7.55	0.054	1.2	378.8	6.9	24	<0.1	21.1	9.1	171	1.84	5	1.8	<0.1	9.0	368	<0.1	0.2	<0.1	83
1041662	Drill Core	7.90	0.022	1.7	303.8	6.3	27	<0.1	21.2	9.4	188	1.90	8	2.3	<0.1	10.3	397	<0.1	0.2	<0.1	89
1041663	Drill Core	6.62	0.007	20.5	187.8	7.3	29	<0.1	19.8	9.5	209	1.96	9	2.3	<0.1	9.4	416	<0.1	0.3	<0.1	85
1041664	Drill Core	8.88	<0.005	1.5	21.7	7.0	27	<0.1	19.1	9.2	239	2.07	7	1.9	<0.1	9.0	401	<0.1	0.2	<0.1	78
1041665	Drill Core	7.73	0.018	2.0	262.1	8.1	29	<0.1	19.9	9.5	202	1.93	7	4.4	<0.1	9.2	411	<0.1	0.3	<0.1	80
1041666	Drill Core	6.07	0.021	46.5	750.1	7.7	34	0.2	22.7	10.9	246	2.46	8	1.7	<0.1	8.0	433	0.1	0.3	0.1	92
1041667	Drill Core	7.23	0.016	1.4	137.3	7.2	31	<0.1	21.1	10.4	215	2.21	7	1.9	<0.1	8.1	426	<0.1	0.4	<0.1	88
1041668	Drill Core	5.79	0.024	2.1	468.4	7.9	35	<0.1	23.2	11.5	244	2.65	10	2.1	<0.1	7.7	403	<0.1	0.4	<0.1	100
1041669	Drill Core	4.49	0.016	3.9	195.5	5.4	32	<0.1	20.6	10.0	224	2.39	8	1.9	<0.1	8.2	356	<0.1	0.4	<0.1	96
1041670	Drill Core	2.75	0.043	17.9	1339	6.3	29	0.1	20.1	9.7	185	2.17	10	4.5	0.1	11.7	309	0.1	0.5	0.1	85
1041671	Drill Core	4.58	0.024	2.9	537.3	13.7	44	<0.1	21.6	9.9	182	2.25	12	2.1	0.1	9.8	337	<0.1	0.6	<0.1	99

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 2 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041642	Drill Core	2.01	0.046	10.6	37	1.27	622	0.298	7.21	2.682	2.39	0.9	7.5	24	1.5	13.0	3.2	0.2	1	10	20.0
1041643	Drill Core	2.19	0.048	9.1	39	1.34	600	0.313	7.26	2.683	2.42	0.6	6.9	21	1.5	12.5	3.0	0.2	<1	11	21.9
1041644	Drill Core	2.09	0.051	9.5	41	1.29	641	0.334	7.37	2.726	2.48	0.8	7.7	22	1.6	12.4	3.2	0.2	1	10	23.3
1041645	Drill Core	1.61	0.051	9.2	43	1.34	545	0.338	7.44	2.901	1.93	1.7	7.7	20	1.6	10.0	3.4	0.2	<1	10	26.0
1041646	Drill Core	1.92	0.047	8.2	42	1.32	630	0.323	7.48	2.804	2.33	1.2	8.1	19	1.5	10.7	3.0	0.2	<1	10	22.6
1041647	Drill Core	1.55	0.046	7.7	38	1.35	395	0.325	7.40	3.185	1.69	0.6	9.3	17	1.5	9.6	3.7	0.3	1	10	25.8
1041648	Drill Core	1.65	0.044	5.7	30	1.14	355	0.299	7.24	3.292	1.39	0.4	12.0	11	1.0	6.5	3.2	0.3	1	8	25.0
1041649	Drill Core	1.78	0.042	5.1	32	1.17	304	0.312	6.70	3.157	1.31	0.4	11.9	10	0.9	5.6	3.2	0.3	1	8	26.2
1041650	Drill Core	1.10	0.033	6.0	16	0.74	338	0.215	6.85	3.312	1.44	0.7	13.2	10	0.7	4.8	2.9	0.3	<1	5	19.0
1041651	Drill Core	1.11	0.032	6.4	17	0.67	686	0.199	6.64	2.809	2.49	0.4	12.8	12	0.6	5.7	3.3	0.3	<1	5	16.8
1041652	Drill Core	1.82	0.046	5.8	27	1.01	613	0.272	6.73	2.861	2.09	0.6	13.1	12	1.0	8.4	3.5	0.3	<1	8	21.7
1041653	Drill Core	2.08	0.039	5.9	33	1.12	536	0.282	6.95	2.861	1.81	0.4	12.0	13	1.0	9.1	3.5	0.3	<1	8	20.6
1041654	Drill Core	1.82	0.055	6.1	33	1.13	483	0.307	7.13	2.977	1.69	0.9	12.5	13	1.2	8.5	3.6	0.3	1	8	22.9
1041655	Drill Core	2.12	0.046	5.2	32	1.14	536	0.290	6.91	2.901	1.81	0.3	11.3	12	1.0	8.5	3.1	0.3	<1	8	19.6
1041656	Drill Core	2.18	0.044	6.0	31	1.11	525	0.274	7.01	2.885	1.67	0.3	11.4	14	0.9	9.4	3.4	0.3	<1	8	19.1
1041657	Drill Core	2.08	0.043	5.5	31	1.06	489	0.271	6.70	2.834	1.74	0.3	10.9	13	1.0	8.3	3.3	0.3	1	8	17.1
1041658	Drill Core	2.17	0.042	5.6	33	1.17	465	0.296	6.85	2.848	1.70	0.3	11.5	12	1.0	8.4	3.4	0.3	1	9	20.0
1041659	Drill Core	2.10	0.046	5.7	33	1.20	423	0.311	6.78	3.019	1.51	0.3	11.4	12	1.1	7.4	3.6	0.3	<1	9	22.4
1041660	Rock	34.71	0.003	0.3	<1	1.72	5	<0.001	0.03	0.003	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1	<1	<1	0.2
1041661	Drill Core	2.27	0.041	5.7	30	1.12	394	0.303	6.87	3.033	1.42	0.4	10.2	12	1.2	7.0	3.1	0.3	1	8	22.9
1041662	Drill Core	2.06	0.043	6.2	29	1.19	344	0.306	7.06	3.083	1.31	0.8	10.1	13	1.4	7.8	3.1	0.3	1	8	25.7
1041663	Drill Core	1.91	0.049	6.3	30	1.14	458	0.300	7.07	3.035	1.69	1.6	11.1	14	1.3	10.4	3.2	0.3	<1	8	25.9
1041664	Drill Core	2.10	0.041	7.1	31	1.22	454	0.298	7.11	3.020	1.46	0.4	9.9	18	1.7	13.7	3.2	0.3	<1	9	21.6
1041665	Drill Core	1.93	0.043	8.5	33	1.19	383	0.309	7.37	3.123	1.43	0.8	10.0	19	1.9	16.2	3.3	0.3	1	9	24.7
1041666	Drill Core	2.15	0.051	7.1	41	1.36	499	0.323	7.31	3.102	1.74	0.8	9.3	19	1.6	10.7	3.5	0.3	1	10	24.8
1041667	Drill Core	2.26	0.054	6.0	44	1.27	403	0.331	7.61	3.251	1.30	0.7	8.4	17	1.9	11.9	3.7	0.3	<1	10	24.1
1041668	Drill Core	2.29	0.107	7.2	42	1.37	498	0.324	7.09	2.957	1.66	0.7	8.0	21	1.8	15.4	3.8	0.3	1	9	26.8
1041669	Drill Core	2.04	0.050	6.5	38	1.05	709	0.307	7.28	2.801	2.02	1.1	7.5	17	1.3	10.6	3.3	0.3	<1	9	26.5
1041670	Drill Core	1.21	0.047	8.1	29	1.07	432	0.284	7.51	2.921	1.73	1.0	6.6	18	1.2	10.3	3.0	0.2	<1	9	26.8
1041671	Drill Core	1.35	0.049	10.6	35	1.08	451	0.318	7.51	2.865	1.71	1.3	6.9	24	1.6	10.2	3.4	0.3	1	9	26.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 08, 2011

Page: 2 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041642	Drill Core	<0.1	80.9	0.3
1041643	Drill Core	<0.1	86.9	0.3
1041644	Drill Core	<0.1	81.9	0.3
1041645	Drill Core	<0.1	82.8	0.3
1041646	Drill Core	<0.1	86.4	0.3
1041647	Drill Core	<0.1	83.0	0.5
1041648	Drill Core	<0.1	73.6	0.5
1041649	Drill Core	<0.1	67.8	0.5
1041650	Drill Core	<0.1	77.0	0.5
1041651	Drill Core	<0.1	82.0	0.4
1041652	Drill Core	<0.1	71.1	0.5
1041653	Drill Core	<0.1	65.4	0.6
1041654	Drill Core	<0.1	75.1	0.5
1041655	Drill Core	<0.1	63.2	0.4
1041656	Drill Core	<0.1	63.6	0.5
1041657	Drill Core	<0.1	62.7	0.5
1041658	Drill Core	<0.1	64.9	0.5
1041659	Drill Core	<0.1	70.3	0.5
1041660	Rock	<0.1	<0.1	<0.1
1041661	Drill Core	<0.1	61.0	0.5
1041662	Drill Core	<0.1	63.1	0.4
1041663	Drill Core	<0.1	68.3	0.5
1041664	Drill Core	<0.1	57.0	0.5
1041665	Drill Core	<0.1	68.9	0.4
1041666	Drill Core	<0.1	68.4	0.5
1041667	Drill Core	<0.1	46.3	0.4
1041668	Drill Core	<0.1	51.3	0.4
1041669	Drill Core	<0.1	91.7	0.4
1041670	Drill Core	0.1	85.9	0.3
1041671	Drill Core	<0.1	84.2	0.3



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 3 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041672	Drill Core	5.82	0.054	13.0	954.8	7.3	28	0.1	20.0	9.5	208	2.14	7	2.4	<0.1	8.9	374	<0.1	0.4	0.1	88
1041673	Drill Core	5.38	0.018	2.4	206.9	6.7	34	<0.1	23.1	10.7	253	2.38	7	2.0	<0.1	7.6	343	<0.1	0.5	<0.1	96
1041674	Drill Core	5.10	0.063	1.8	645.3	6.6	27	<0.1	22.9	10.6	222	2.38	8	1.9	<0.1	8.2	399	<0.1	0.4	<0.1	97
1041675	Drill Core	8.52	0.009	0.9	138.1	5.9	31	<0.1	24.9	11.9	262	3.06	7	1.5	<0.1	7.1	440	0.2	0.4	0.2	107
1041676	Drill Core	9.72	0.023	1.3	329.4	8.2	33	<0.1	22.0	10.9	338	2.84	6	1.5	<0.1	7.6	418	<0.1	0.3	<0.1	92
1041677	Drill Core	5.63	0.012	1.0	277.7	5.9	28	<0.1	22.9	11.5	308	2.78	6	2.4	<0.1	6.5	447	0.1	0.3	<0.1	97
1041678	Drill Core	2.75	0.006	1.3	49.4	5.5	27	<0.1	23.1	10.9	332	2.94	7	2.5	<0.1	7.2	520	<0.1	0.2	<0.1	99
1041679	Drill Core	2.75	0.007	1.0	86.0	5.2	28	<0.1	22.6	9.9	301	2.67	5	3.5	<0.1	6.1	457	<0.1	0.3	<0.1	91
1041680	Rock Pulp	0.10	1.514	289.2	9662	89.4	135	4.8	34.2	20.7	446	5.07	29	6.3	1.4	11.6	225	2.8	20.6	3.6	98
1041681	Drill Core	2.93	0.038	3.8	1416	5.5	31	0.4	22.0	10.5	281	2.69	6	1.7	<0.1	6.3	450	0.1	0.3	<0.1	91
1041682	Drill Core	2.69	0.014	1.3	330.9	5.2	27	<0.1	22.1	10.5	261	2.53	6	1.9	<0.1	7.6	413	0.1	0.3	<0.1	88
1041683	Drill Core	8.55	0.006	0.8	104.0	7.1	44	<0.1	23.1	10.3	367	2.89	5	1.7	<0.1	6.4	418	<0.1	0.4	<0.1	101
1041684	Drill Core	8.51	0.005	0.9	79.0	5.4	34	<0.1	23.8	11.1	335	3.11	7	1.7	<0.1	7.5	427	<0.1	0.3	<0.1	109
1041685	Drill Core	5.89	<0.005	1.0	41.4	7.1	35	<0.1	23.3	10.7	413	3.04	6	2.3	<0.1	7.1	451	<0.1	0.3	<0.1	99
1041686	Drill Core	7.86	0.012	1.2	230.7	5.9	31	<0.1	20.4	9.6	281	2.60	11	1.8	<0.1	6.9	335	<0.1	0.4	<0.1	95
1041687	Drill Core	5.63	0.009	1.2	82.0	5.6	27	<0.1	19.7	9.1	309	2.29	7	2.1	<0.1	8.3	363	<0.1	0.3	<0.1	79
1041688	Drill Core	5.86	0.006	0.9	78.0	6.0	26	<0.1	19.5	8.9	274	2.41	6	2.8	<0.1	10.1	409	<0.1	0.3	<0.1	87
1041689	Drill Core	7.81	0.032	11.9	643.2	7.3	30	<0.1	18.6	9.6	266	2.18	5	2.7	<0.1	10.4	350	<0.1	0.5	<0.1	74
1041690	Drill Core	9.09	0.011	27.1	158.3	6.6	30	<0.1	17.9	9.0	290	2.50	8	2.7	<0.1	9.5	333	<0.1	0.5	<0.1	79
1041691	Drill Core	8.95	0.026	0.8	271.4	6.4	26	0.1	14.6	7.5	212	1.80	6	2.3	<0.1	9.1	351	<0.1	0.3	<0.1	64
1041692	Drill Core	7.58	0.031	1.8	670.4	6.0	34	<0.1	21.5	10.2	247	2.28	11	3.2	0.2	7.8	309	<0.1	0.5	<0.1	86
1041693	Drill Core	8.29	0.007	5.3	115.2	6.2	34	<0.1	21.3	10.5	272	2.53	7	2.4	<0.1	8.0	375	<0.1	0.3	<0.1	89
1041694	Drill Core	8.00	0.017	1.1	189.8	6.4	33	<0.1	20.7	10.3	298	2.78	12	2.1	<0.1	8.8	342	<0.1	0.5	<0.1	87
1041695	Drill Core	8.36	0.008	1.0	64.7	6.1	29	<0.1	19.2	9.3	255	2.59	10	1.7	<0.1	8.7	401	<0.1	0.3	<0.1	89
1041696	Drill Core	7.96	0.007	1.3	77.0	6.1	29	<0.1	20.3	9.6	296	2.65	8	1.7	<0.1	8.0	392	<0.1	0.4	<0.1	92
1041697	Drill Core	8.71	0.008	1.1	76.1	5.8	29	<0.1	22.3	10.8	293	2.79	7	2.4	<0.1	8.1	402	<0.1	0.5	<0.1	94
1041698	Drill Core	8.17	0.008	1.4	104.8	5.6	30	<0.1	20.1	10.0	287	2.43	11	3.6	<0.1	8.2	308	0.1	1.9	<0.1	85
1041699	Drill Core	2.74	0.006	1.1	61.4	6.3	28	<0.1	22.2	10.3	257	2.58	6	1.9	<0.1	6.9	356	0.1	0.5	<0.1	87
1041700	Drill Core	2.75	<0.005	0.9	57.1	6.5	27	<0.1	21.4	10.0	256	2.62	5	1.9	<0.1	7.3	356	<0.1	0.4	<0.1	90
1041701	Drill Core	5.43	0.006	1.0	81.5	7.3	30	<0.1	21.1	10.0	311	2.62	7	2.3	<0.1	7.5	402	0.1	0.3	<0.1	87

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 3 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041672	Drill Core	2.09	0.046	6.8	30	1.22	457	0.299	7.02	2.865	1.62	0.8	6.6	15	1.3	9.9	3.2	0.3	<1	9	29.1
1041673	Drill Core	2.63	0.046	9.5	33	1.21	457	0.304	7.09	2.830	1.95	2.0	5.8	23	1.4	10.5	3.1	0.3	1	9	30.1
1041674	Drill Core	2.13	0.045	7.6	35	1.31	493	0.311	7.08	2.927	1.80	0.6	5.9	18	1.3	9.1	3.2	0.2	<1	9	27.0
1041675	Drill Core	2.43	0.052	8.8	40	1.46	415	0.408	6.91	2.837	1.59	0.4	8.1	23	1.8	13.9	3.4	0.3	1	10	31.0
1041676	Drill Core	2.56	0.050	8.9	36	1.40	542	0.366	6.70	2.773	1.88	0.4	8.2	22	1.2	13.5	3.1	0.2	1	9	31.3
1041677	Drill Core	2.63	0.057	7.0	38	1.49	562	0.396	6.91	2.754	1.95	2.0	8.4	19	1.5	13.0	3.2	0.2	1	9	30.0
1041678	Drill Core	2.81	0.055	8.3	38	1.49	624	0.396	7.60	3.025	2.15	0.4	8.4	23	1.4	16.0	3.3	0.2	<1	10	28.3
1041679	Drill Core	3.02	0.050	6.8	34	1.42	486	0.368	7.32	2.878	1.70	2.1	7.0	19	1.2	14.0	2.9	0.2	1	10	33.4
1041680	Rock Pulp	1.67	0.081	31.1	109	1.00	98	0.242	7.25	0.868	4.03	17.5	23.4	60	3.8	15.0	3.3	0.2	1	10	16.9
1041681	Drill Core	2.45	0.054	7.6	36	1.43	530	0.375	7.49	2.915	2.01	71.7	6.2	19	1.5	12.6	3.0	0.2	1	9	34.4
1041682	Drill Core	2.33	0.052	6.9	35	1.45	397	0.362	7.44	3.013	1.63	1.6	6.2	18	1.3	11.8	3.1	0.2	<1	10	34.3
1041683	Drill Core	2.79	0.054	7.1	35	1.42	497	0.371	7.19	2.972	1.69	0.8	7.1	20	1.6	14.7	2.9	0.2	1	9	30.6
1041684	Drill Core	2.64	0.055	7.5	43	1.54	479	0.394	7.18	3.054	1.73	0.5	7.8	22	1.6	17.1	3.4	0.2	<1	11	36.8
1041685	Drill Core	2.84	0.055	8.2	41	1.47	605	0.383	6.87	2.901	2.08	0.4	8.0	22	1.5	15.2	3.1	0.2	1	10	28.4
1041686	Drill Core	2.36	0.057	8.3	38	1.27	387	0.366	7.55	3.063	1.41	1.3	6.6	24	2.1	15.8	3.1	0.2	1	10	34.8
1041687	Drill Core	3.45	0.136	9.2	35	1.33	253	0.354	7.25	3.205	1.01	0.7	5.7	28	2.0	24.4	3.1	0.2	1	9	28.7
1041688	Drill Core	2.65	0.056	7.3	32	1.35	429	0.334	7.13	3.061	1.62	0.3	7.8	21	1.5	18.1	3.0	0.2	<1	9	26.2
1041689	Drill Core	2.57	0.041	6.5	30	1.13	321	0.328	7.08	3.108	1.50	1.9	7.6	18	1.5	14.4	2.9	0.2	1	9	31.2
1041690	Drill Core	2.32	0.045	7.1	30	1.09	508	0.319	7.10	2.695	2.42	0.8	9.0	19	1.1	13.9	3.1	0.2	<1	8	25.6
1041691	Drill Core	2.02	0.035	6.9	24	1.00	434	0.296	7.08	3.080	1.91	2.1	6.8	19	1.2	12.7	2.9	0.2	1	7	26.1
1041692	Drill Core	2.11	0.050	10.8	35	1.36	383	0.366	7.27	2.936	1.62	1.2	5.6	28	1.6	18.4	3.4	0.2	2	10	39.6
1041693	Drill Core	2.43	0.053	7.2	36	1.38	452	0.363	7.15	2.908	1.81	0.6	7.8	20	1.6	16.7	3.2	0.2	2	10	36.1
1041694	Drill Core	2.20	0.046	8.1	36	1.22	549	0.358	7.35	2.889	2.48	0.8	7.1	22	1.3	14.5	3.3	0.2	1	8	39.7
1041695	Drill Core	1.90	0.046	6.8	35	1.26	566	0.352	7.07	2.907	2.44	0.4	6.3	20	1.6	15.1	3.3	0.2	<1	9	36.6
1041696	Drill Core	2.28	0.047	7.6	37	1.26	602	0.356	7.16	2.941	2.36	0.5	6.2	22	1.5	15.8	3.3	0.2	1	9	38.8
1041697	Drill Core	2.59	0.050	7.9	38	1.39	617	0.364	7.30	2.810	2.35	0.3	6.8	24	1.5	16.2	3.2	0.2	1	9	32.2
1041698	Drill Core	2.71	0.049	6.5	36	1.12	750	0.356	7.20	2.353	2.35	1.9	5.9	19	1.1	13.6	3.1	0.2	1	9	35.3
1041699	Drill Core	2.40	0.050	6.9	37	1.28	458	0.355	7.12	2.686	2.15	0.6	6.3	20	1.4	14.4	3.1	0.2	<1	9	35.7
1041700	Drill Core	2.41	0.050	7.2	37	1.31	516	0.355	7.31	2.939	2.23	0.3	6.4	22	1.4	15.1	3.2	0.2	<1	9	33.8
1041701	Drill Core	2.49	0.045	7.3	34	1.32	542	0.356	7.16	2.832	2.20	0.3	6.4	21	1.4	15.1	3.0	0.2	1	9	44.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 08, 2011

Page: 3 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041672	Drill Core	<0.1	64.1	0.3
1041673	Drill Core	<0.1	80.2	0.3
1041674	Drill Core	<0.1	70.1	0.3
1041675	Drill Core	<0.1	72.3	0.3
1041676	Drill Core	<0.1	62.5	0.4
1041677	Drill Core	<0.1	62.0	0.4
1041678	Drill Core	<0.1	64.6	0.4
1041679	Drill Core	<0.1	54.7	0.3
1041680	Rock Pulp	2.5	156.0	0.7
1041681	Drill Core	0.1	69.7	0.3
1041682	Drill Core	<0.1	63.1	0.3
1041683	Drill Core	<0.1	56.3	0.3
1041684	Drill Core	<0.1	53.8	0.4
1041685	Drill Core	<0.1	59.9	0.4
1041686	Drill Core	<0.1	65.4	0.3
1041687	Drill Core	<0.1	46.1	0.3
1041688	Drill Core	<0.1	52.5	0.4
1041689	Drill Core	<0.1	56.2	0.4
1041690	Drill Core	<0.1	71.2	0.4
1041691	Drill Core	<0.1	61.2	0.3
1041692	Drill Core	<0.1	62.2	0.3
1041693	Drill Core	<0.1	65.0	0.3
1041694	Drill Core	<0.1	75.5	0.3
1041695	Drill Core	<0.1	67.6	0.3
1041696	Drill Core	<0.1	66.4	0.3
1041697	Drill Core	<0.1	65.0	0.4
1041698	Drill Core	<0.1	77.2	0.3
1041699	Drill Core	<0.1	63.5	0.3
1041700	Drill Core	<0.1	62.0	0.3
1041701	Drill Core	<0.1	58.4	0.3



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 4 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041702	Drill Core	5.40	<0.005	1.0	81.0	6.1	33	<0.1	20.8	10.5	364	2.78	8	2.5	<0.1	7.7	441	<0.1	0.3	<0.1	89
1041703	Drill Core	6.03	0.011	0.9	70.7	6.8	33	<0.1	23.4	11.6	364	3.07	5	2.0	<0.1	8.4	413	<0.1	0.3	<0.1	97
1041704	Drill Core	2.67	0.010	3.2	141.7	7.4	29	<0.1	21.1	9.7	301	2.66	6	3.4	<0.1	7.3	448	<0.1	0.5	<0.1	90
1041705	Drill Core	2.86	0.007	0.9	65.5	7.6	37	<0.1	22.7	11.4	426	3.05	4	2.5	<0.1	9.2	404	0.1	0.4	<0.1	90
1041706	Drill Core	7.97	0.012	0.8	77.3	9.6	40	<0.1	23.9	11.7	404	3.13	4	2.4	<0.1	8.2	401	<0.1	0.9	<0.1	95
1041707	Drill Core	8.96	0.007	1.3	95.7	8.1	39	<0.1	20.2	10.9	369	2.68	5	2.6	<0.1	8.7	364	0.1	1.0	<0.1	86
1041708	Drill Core	8.09	0.008	1.1	63.5	9.4	41	<0.1	20.3	10.5	374	2.83	8	2.4	<0.1	9.3	355	0.2	2.2	<0.1	91
1041709	Drill Core	8.05	0.008	1.2	76.0	7.6	35	<0.1	17.1	8.7	378	2.62	17	1.7	<0.1	8.2	256	0.7	5.2	<0.1	78
1041710	Drill Core	2.80	0.037	1.7	442.3	10.6	52	0.1	23.1	12.7	310	2.66	16	3.7	<0.1	11.0	261	0.5	4.1	0.4	82
1041711	Drill Core	2.29	0.040	8.8	1544	8.6	57	0.3	21.2	10.4	208	2.45	41	3.1	<0.1	8.0	228	1.2	9.7	0.4	80
1041712	Drill Core	2.52	0.029	5.8	710.0	9.1	44	0.2	20.1	9.6	210	2.27	31	2.3	<0.1	8.5	303	0.8	8.2	0.3	81
1041713	Drill Core	2.55	0.019	4.0	289.7	6.4	36	0.2	17.4	8.9	372	2.06	31	1.6	<0.1	7.7	200	1.0	7.2	0.2	76
1041714	Drill Core	5.66	0.009	1.5	71.9	10.4	42	<0.1	21.9	10.2	311	2.62	16	2.0	<0.1	8.3	249	0.3	2.3	0.1	88
1041715	Drill Core	5.96	0.008	2.5	88.6	8.9	43	<0.1	18.9	10.2	387	2.73	14	2.1	<0.1	9.5	331	0.4	2.5	0.2	91
1041716	Drill Core	6.27	0.018	6.9	362.1	8.7	39	0.3	16.7	9.1	279	2.34	24	2.6	<0.1	8.3	337	0.2	3.0	0.2	77
1041717	Drill Core	6.64	<0.005	0.4	26.9	8.9	28	<0.1	17.6	7.9	402	2.09	13	0.7	<0.1	1.7	206	0.2	1.7	0.1	65
1041718	Drill Core	6.99	<0.005	0.3	41.2	8.1	38	<0.1	17.6	7.6	372	2.05	14	0.9	<0.1	2.1	279	0.1	1.7	0.1	65
1041719	Drill Core	4.58	0.010	3.5	320.4	16.5	40	<0.1	18.6	10.1	304	2.12	12	8.0	<0.1	8.1	348	0.3	2.4	0.2	66
1041720	Rock	0.56	<0.005	<0.1	2.1	1.7	1	<0.1	0.9	<0.2	29	0.06	9	1.1	<0.1	<0.1	4697	<0.1	<0.1	<0.1	2
1041721	Drill Core	8.32	0.010	1.1	169.9	6.6	34	0.1	20.7	9.7	268	2.54	8	1.6	<0.1	8.7	269	<0.1	1.6	<0.1	84
1041722	Drill Core	6.07	0.014	2.8	228.9	5.8	27	0.1	16.3	6.9	182	2.16	4	1.1	<0.1	7.7	332	<0.1	0.8	0.1	69
1041723	Drill Core	1.88	0.039	11.1	433.3	7.9	15	0.5	4.7	3.1	134	0.72	16	6.0	<0.1	22.8	160	1.8	9.5	<0.1	14
1041724	Drill Core	2.87	0.049	3.3	407.3	10.9	47	0.3	34.6	15.3	528	3.62	8	9.7	<0.1	5.9	247	0.6	3.9	0.2	98
1041725	Drill Core	8.40	0.160	8.3	681.8	6.6	25	0.3	15.9	9.5	185	1.77	6	2.5	<0.1	11.1	268	0.2	1.6	0.2	60
1041726	Drill Core	7.63	0.033	2.8	351.5	6.5	23	0.1	13.6	6.9	156	1.91	6	2.7	<0.1	15.2	283	0.1	0.9	<0.1	58
1041473	Drill Core	6.76	0.026	6.5	269.3	10.1	51	0.2	14.6	8.1	281	2.04	7	1.4	<0.1	8.1	388	0.1	1.7	<0.1	71
1041474	Drill Core	5.25	0.087	39.9	681.3	6.8	22	0.3	11.5	8.8	135	1.14	6	3.8	<0.1	12.6	300	<0.1	1.2	<0.1	45
1041475	Drill Core	6.18	0.173	17.6	1028	7.5	34	0.5	14.3	7.7	253	1.78	9	4.4	<0.1	11.7	265	0.1	1.5	<0.1	53
1041476	Drill Core	6.02	0.007	1.9	88.3	5.9	27	<0.1	15.4	7.3	220	2.41	6	2.1	<0.1	9.4	445	<0.1	1.3	<0.1	79
1041477	Drill Core	5.64	<0.005	1.7	53.3	6.7	25	<0.1	16.3	8.0	218	2.22	6	1.8	<0.1	8.4	433	<0.1	1.2	<0.1	80

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 4 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041702	Drill Core	2.69	0.052	8.4	37	1.37	627	0.357	7.16	2.830	2.49	0.4	7.0	24	1.2	15.8	3.0	0.2	1	10	41.3
1041703	Drill Core	2.69	0.053	9.1	40	1.40	683	0.382	7.55	2.886	2.57	0.2	6.8	26	1.7	16.5	3.2	0.2	1	10	33.2
1041704	Drill Core	2.88	0.061	7.6	35	1.40	414	0.332	7.17	2.936	1.79	0.3	6.0	23	1.3	16.7	2.9	0.2	<1	9	41.8
1041705	Drill Core	2.71	0.055	9.3	37	1.41	691	0.365	7.67	2.788	2.70	0.3	6.3	25	1.3	15.8	3.3	0.2	<1	10	30.3
1041706	Drill Core	2.76	0.051	9.1	41	1.30	638	0.374	7.05	2.814	2.58	0.5	6.5	25	1.3	16.8	3.3	0.2	1	10	43.2
1041707	Drill Core	2.59	0.049	9.1	34	1.32	553	0.328	7.24	2.753	2.24	0.5	5.9	23	1.1	14.8	3.0	0.2	1	9	41.1
1041708	Drill Core	1.96	0.050	8.9	39	1.12	561	0.354	7.16	2.696	2.54	1.1	6.0	25	1.1	15.1	3.1	0.3	<1	10	51.3
1041709	Drill Core	2.66	0.046	8.2	34	0.99	1013	0.301	7.24	1.979	2.44	2.3	5.0	23	0.8	12.4	2.7	0.2	1	9	126.7
1041710	Drill Core	1.41	0.078	43.0	34	1.21	991	0.255	7.75	2.934	2.43	2.6	5.9	94	1.2	17.0	3.2	0.3	<1	9	66.0
1041711	Drill Core	1.14	0.216	45.7	35	1.09	391	0.291	7.55	3.068	1.85	1.9	6.0	111	1.6	24.6	3.3	0.3	<1	9	35.4
1041712	Drill Core	1.31	0.094	20.3	37	0.78	502	0.295	7.84	2.963	1.61	1.4	6.7	51	1.7	15.9	3.4	0.3	1	8	43.4
1041713	Drill Core	1.98	0.042	8.8	34	0.95	920	0.268	7.76	2.615	2.14	2.2	5.7	23	1.4	8.6	3.0	0.3	<1	9	28.5
1041714	Drill Core	1.80	0.048	11.5	34	0.77	640	0.258	7.56	2.608	2.22	2.5	6.1	30	1.4	10.5	2.8	0.2	<1	10	41.3
1041715	Drill Core	2.53	0.050	11.2	36	0.93	696	0.280	7.50	2.590	2.16	1.6	7.2	29	1.1	12.9	3.0	0.3	1	10	30.5
1041716	Drill Core	1.74	0.043	12.6	29	0.72	477	0.282	8.01	2.821	2.27	1.0	15.7	30	1.3	11.2	3.4	0.3	<1	8	27.1
1041717	Drill Core	2.51	0.054	9.0	8	1.03	856	0.220	7.97	2.800	2.49	0.6	39.4	22	0.7	5.2	2.4	0.2	1	6	22.4
1041718	Drill Core	2.38	0.054	8.9	8	0.97	1359	0.228	8.07	2.925	2.43	0.5	41.6	22	0.6	5.2	2.6	0.2	1	6	20.0
1041719	Drill Core	2.53	0.036	16.8	29	0.96	937	0.274	7.41	2.897	1.89	1.7	8.7	40	1.7	13.2	3.8	0.3	1	8	21.7
1041720	Rock	35.67	0.004	0.9	<1	1.51	16	0.003	0.13	0.038	0.04	<0.1	0.8	2	<0.1	0.7	0.1	<0.1	<1	<1	0.5
1041721	Drill Core	2.60	0.045	8.9	31	1.12	524	0.263	7.26	2.901	2.18	1.9	7.5	24	1.4	11.0	3.1	0.2	<1	10	25.8
1041722	Drill Core	1.70	0.035	5.6	20	0.85	371	0.217	7.13	3.056	1.78	1.5	7.0	14	1.2	7.2	2.4	0.2	<1	7	25.3
1041723	Drill Core	0.90	0.007	2.8	3	0.41	415	0.069	5.92	2.884	1.74	1.6	11.9	7	1.1	5.9	1.2	0.2	<1	1	9.3
1041724	Drill Core	3.38	0.086	10.0	52	1.89	1057	0.297	6.86	2.328	1.56	3.9	9.9	28	1.8	11.9	3.0	0.2	1	10	30.4
1041725	Drill Core	1.50	0.029	5.2	19	0.87	359	0.214	7.23	2.935	1.84	2.6	15.1	13	1.0	5.7	2.6	0.2	<1	6	18.0
1041726	Drill Core	1.15	0.030	6.4	16	0.76	865	0.196	7.14	2.658	2.22	1.9	18.2	14	0.8	4.2	2.4	0.3	<1	5	20.7
1041473	Drill Core	2.80	0.045	8.5	25	0.75	673	0.247	7.43	2.734	1.91	4.3	10.8	22	1.3	9.8	3.2	0.3	1	8	18.5
1041474	Drill Core	1.27	0.020	6.0	10	0.66	690	0.175	6.95	3.341	1.65	1.6	17.3	13	1.3	5.2	2.5	0.3	1	4	18.4
1041475	Drill Core	1.34	0.031	8.7	13	0.66	797	0.191	7.03	2.480	2.83	3.2	20.8	20	1.2	8.7	2.6	0.3	<1	5	18.8
1041476	Drill Core	1.68	0.048	11.2	25	0.78	731	0.270	7.80	2.936	2.36	5.5	28.3	28	2.4	9.1	3.4	0.3	<1	8	18.4
1041477	Drill Core	2.16	0.046	10.3	24	0.76	683	0.265	7.63	3.009	2.24	2.6	25.7	27	1.4	8.9	2.8	0.2	1	8	22.0

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 08, 2011

Page: 4 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX
Analyte	S	Rb	Hf
Unit	%	ppm	ppm
MDL	0.1	0.1	0.1
1041702	Drill Core	<0.1	59.9 0.3
1041703	Drill Core	<0.1	66.4 0.4
1041704	Drill Core	<0.1	52.5 0.3
1041705	Drill Core	<0.1	67.2 0.3
1041706	Drill Core	<0.1	70.6 0.3
1041707	Drill Core	<0.1	63.4 0.3
1041708	Drill Core	<0.1	79.9 0.4
1041709	Drill Core	<0.1	71.1 0.3
1041710	Drill Core	<0.1	123.7 0.4
1041711	Drill Core	0.1	114.3 0.3
1041712	Drill Core	<0.1	91.1 0.3
1041713	Drill Core	<0.1	125.1 0.3
1041714	Drill Core	<0.1	99.8 0.3
1041715	Drill Core	<0.1	97.0 0.4
1041716	Drill Core	<0.1	109.1 0.5
1041717	Drill Core	<0.1	127.4 1.0
1041718	Drill Core	<0.1	128.1 1.2
1041719	Drill Core	<0.1	100.8 0.3
1041720	Rock	<0.1	2.6 <0.1
1041721	Drill Core	<0.1	101.5 0.4
1041722	Drill Core	<0.1	89.9 0.4
1041723	Drill Core	<0.1	86.3 0.6
1041724	Drill Core	<0.1	90.5 0.5
1041725	Drill Core	0.1	95.7 0.7
1041726	Drill Core	<0.1	91.1 0.7
1041473	Drill Core	<0.1	80.1 0.4
1041474	Drill Core	0.2	75.5 0.8
1041475	Drill Core	0.1	101.7 0.7
1041476	Drill Core	<0.1	94.0 0.9
1041477	Drill Core	<0.1	87.9 1.0



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 5 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041478	Drill Core	5.43	<0.005	6.1	118.4	6.3	27	0.2	16.4	8.2	252	2.30	4	1.8	<0.1	8.1	388	0.1	0.8	<0.1	76
1041479	Drill Core	2.50	0.022	8.3	338.9	5.1	24	0.2	16.2	8.0	226	1.88	9	1.8	<0.1	8.2	335	<0.1	0.8	0.3	72
1041480	Drill Core	2.01	0.038	13.3	470.5	5.7	26	0.3	16.4	9.0	230	2.04	11	2.1	<0.1	8.4	337	<0.1	0.9	0.2	74
1041481	Drill Core	4.84	0.097	18.7	660.5	7.0	28	0.3	19.1	10.1	259	2.22	16	2.7	<0.1	8.0	314	0.1	0.9	0.2	73
1041482	Drill Core	8.11	0.010	4.2	117.1	5.9	28	0.1	17.7	9.3	259	2.40	8	3.0	<0.1	9.3	384	<0.1	0.6	<0.1	74
1041483	Drill Core	8.10	0.007	2.7	91.5	7.8	29	<0.1	17.6	9.4	266	2.61	6	2.7	<0.1	9.2	406	0.1	0.5	0.1	74
1041484	Drill Core	7.77	<0.005	3.3	69.3	7.3	28	<0.1	17.7	9.6	257	2.63	7	2.9	<0.1	9.1	451	<0.1	0.6	<0.1	75
1041485	Drill Core	7.27	0.006	3.0	67.0	7.7	29	<0.1	16.4	9.4	255	2.55	9	3.8	<0.1	9.5	469	<0.1	0.7	<0.1	75
1041486	Drill Core	8.77	0.007	4.8	101.1	8.0	28	<0.1	17.0	9.7	272	2.45	6	3.3	<0.1	9.3	428	<0.1	0.6	<0.1	73
1041487	Drill Core	6.58	0.055	10.4	523.0	7.2	30	0.2	19.2	10.3	247	2.33	9	3.2	<0.1	9.4	374	0.1	0.7	<0.1	77
1041488	Drill Core	7.11	<0.005	6.2	139.4	8.8	39	<0.1	17.6	9.7	252	2.54	5	2.5	<0.1	8.9	392	<0.1	0.6	<0.1	79
1041489	Drill Core	7.39	<0.005	2.4	45.8	8.6	30	<0.1	19.0	10.1	307	2.69	5	2.6	<0.1	8.9	384	0.2	0.9	<0.1	78
1041490	Drill Core	5.38	0.017	15.6	73.4	7.8	36	<0.1	17.9	9.9	326	2.47	6	2.8	<0.1	9.1	375	0.1	1.0	<0.1	75
1041491	Drill Core	4.76	0.028	21.0	692.9	7.3	42	0.5	20.2	11.1	323	2.69	18	1.8	<0.1	9.2	254	0.1	1.6	0.2	77
1041492	Drill Core	5.77	<0.005	8.9	150.2	10.5	43	<0.1	21.4	12.2	341	2.68	8	2.2	<0.1	9.4	405	<0.1	0.8	<0.1	82
1041493	Drill Core	8.11	0.005	49.9	266.4	6.4	36	0.1	20.4	11.2	317	2.58	8	2.7	<0.1	9.2	289	<0.1	0.9	<0.1	80
1041494	Drill Core	8.15	<0.005	5.4	87.6	8.6	36	<0.1	18.7	10.5	447	2.43	13	3.0	<0.1	9.4	342	0.2	1.6	<0.1	77
1041495	Drill Core	7.85	<0.005	2.7	43.3	9.3	46	<0.1	16.2	10.0	417	2.25	7	3.3	<0.1	8.9	322	<0.1	1.7	0.1	74
1041496	Drill Core	4.10	<0.005	1.9	49.3	10.4	66	0.1	7.5	5.4	407	1.78	7	2.7	<0.1	3.5	164	<0.1	5.3	<0.1	49
1041497	Drill Core	5.01	<0.005	2.7	104.0	7.4	54	17.4	11.0	11.4	421	1.86	6	1.3	<0.1	2.6	197	<0.1	3.9	<0.1	51



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 5 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.01	0.1	0.1	1	0.1	0.1	0.1	1	1	1	
1041478	Drill Core	2.40	0.045	9.8	21	0.92	673	0.260	7.42	2.900	2.30	3.0	21.5	24	1.8	8.6	2.8	0.3	1	8	25.1
1041479	Drill Core	1.99	0.044	10.6	20	0.93	666	0.251	7.79	2.869	2.28	2.0	20.9	25	1.9	8.4	2.8	0.3	<1	8	28.1
1041480	Drill Core	1.88	0.041	11.7	23	0.93	668	0.267	7.66	2.697	2.08	2.3	21.1	26	1.6	8.9	3.0	0.3	1	8	31.3
1041481	Drill Core	2.41	0.045	11.0	19	1.05	561	0.259	7.50	2.721	1.93	1.7	18.9	26	1.4	9.2	2.8	0.2	<1	8	33.0
1041482	Drill Core	2.39	0.045	9.7	21	0.94	703	0.255	7.47	2.875	2.37	1.1	21.1	24	1.5	9.1	2.8	0.3	<1	8	27.4
1041483	Drill Core	2.24	0.044	10.7	22	1.00	720	0.249	7.45	3.054	2.14	1.3	21.8	27	1.7	10.0	2.8	0.3	1	8	29.8
1041484	Drill Core	2.28	0.042	12.3	21	0.97	766	0.255	7.43	2.939	2.26	1.3	25.6	29	1.7	10.7	2.8	0.3	1	8	24.3
1041485	Drill Core	2.30	0.042	10.4	22	1.00	772	0.262	7.58	2.982	2.32	1.7	30.7	26	1.5	10.3	2.9	0.3	<1	8	26.3
1041486	Drill Core	2.31	0.041	11.2	22	1.00	699	0.241	7.45	2.969	2.25	0.8	26.1	26	1.3	9.4	2.7	0.3	1	8	27.3
1041487	Drill Core	2.29	0.045	12.9	22	1.13	632	0.268	7.50	2.864	2.32	1.0	22.5	30	1.4	9.3	3.1	0.3	1	8	28.6
1041488	Drill Core	2.42	0.044	10.3	26	1.02	713	0.256	7.56	2.777	2.28	0.9	20.9	25	1.3	10.2	2.8	0.2	<1	8	24.2
1041489	Drill Core	2.89	0.044	11.8	23	1.04	688	0.258	7.65	2.781	2.41	0.9	21.4	29	1.5	10.5	2.8	0.3	1	9	26.5
1041490	Drill Core	2.66	0.044	11.5	22	0.98	635	0.260	7.78	2.708	2.42	0.9	20.8	28	1.5	9.7	2.9	0.3	1	8	26.1
1041491	Drill Core	2.19	0.049	16.1	24	1.25	954	0.314	8.39	2.639	2.79	1.8	19.9	34	1.9	8.8	3.1	0.3	1	9	34.6
1041492	Drill Core	2.64	0.052	13.2	28	1.11	855	0.318	9.13	2.859	2.75	1.0	27.2	30	1.5	10.3	3.1	0.3	1	10	29.9
1041493	Drill Core	2.23	0.043	12.3	23	1.19	734	0.266	7.47	2.728	2.54	1.4	20.8	26	2.1	9.3	2.9	0.2	<1	8	25.9
1041494	Drill Core	3.42	0.042	10.7	23	0.83	803	0.260	7.03	2.633	1.99	1.9	22.4	23	1.1	9.8	2.9	0.2	<1	8	27.1
1041495	Drill Core	3.11	0.038	10.2	21	0.59	589	0.226	7.14	2.662	1.80	1.5	24.6	24	1.1	10.5	3.3	0.3	1	8	25.8
1041496	Drill Core	1.87	0.045	14.7	12	0.61	446	0.196	7.45	1.728	1.86	2.5	57.6	32	1.0	8.2	5.1	0.4	2	5	65.9
1041497	Drill Core	1.89	0.051	15.4	30	0.54	462	0.206	7.41	2.369	2.08	165.1	56.2	33	1.3	8.3	4.3	0.3	2	5	61.4



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 08, 2011

Page: 5 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005905.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041478	Drill Core	<0.1	96.7	0.7
1041479	Drill Core	<0.1	100.2	0.8
1041480	Drill Core	<0.1	92.5	0.8
1041481	Drill Core	<0.1	100.1	0.6
1041482	Drill Core	<0.1	94.5	0.9
1041483	Drill Core	<0.1	75.7	0.9
1041484	Drill Core	<0.1	80.2	1.0
1041485	Drill Core	<0.1	85.6	1.1
1041486	Drill Core	<0.1	80.6	1.0
1041487	Drill Core	<0.1	104.0	1.0
1041488	Drill Core	<0.1	87.0	1.0
1041489	Drill Core	<0.1	84.8	0.9
1041490	Drill Core	<0.1	95.3	0.8
1041491	Drill Core	<0.1	104.0	1.0
1041492	Drill Core	<0.1	88.8	1.2
1041493	Drill Core	<0.1	94.4	0.8
1041494	Drill Core	<0.1	69.6	0.9
1041495	Drill Core	<0.1	65.2	1.1
1041496	Drill Core	<0.1	82.3	1.7
1041497	Drill Core	<0.1	81.4	1.7



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 08, 2011

Page: 1 of 3 Part 1

QUALITY CONTROL REPORT

VAN11005905.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
Pulp Duplicates																					
REP G1	QC	<0.005																			
REP 1041660	QC	<0.1 <0.1 <0.1 <1 <0.1 <0.1 <0.2 28 <0.01 7 1.5 <0.1 <0.1 4100 <0.1 <0.1 <0.1 <1																			
1041684	Drill Core	8.51	0.005	0.9	79.0	5.4	34	<0.1	23.8	11.1	335	3.11	7	1.7	<0.1	7.5	427	<0.1	0.3	<0.1	109
REP 1041684	QC	0.007																			
1041703	Drill Core	6.03	0.011	0.9	70.7	6.8	33	<0.1	23.4	11.6	364	3.07	5	2.0	<0.1	8.4	413	<0.1	0.3	<0.1	97
REP 1041703	QC	0.9 63.8 6.4 32 <0.1 22.6 11.0 363 3.07 6 1.9 <0.1 7.8 404 <0.1 0.2 <0.1 95																			
1041709	Drill Core	8.05	0.008	1.2	76.0	7.6	35	<0.1	17.1	8.7	378	2.62	17	1.7	<0.1	8.2	256	0.7	5.2	<0.1	78
REP 1041709	QC	0.007																			
1041713	Drill Core	2.55	0.019	4.0	289.7	6.4	36	0.2	17.4	8.9	372	2.06	31	1.6	<0.1	7.7	200	1.0	7.2	0.2	76
REP 1041713	QC	3.3 287.5 6.0 37 0.2 18.2 8.4 364 1.98 30 1.5 <0.1 7.6 189 0.8 7.0 0.2 76																			
Core Reject Duplicates																					
1041660	Rock	0.72	<0.005	<0.1	0.6	<0.1	<1	<0.1	0.4	<0.2	26	<0.01	7	1.3	<0.1	<0.1	4135	<0.1	<0.1	<0.1	<1
DUP 1041660	QC	<0.005 <0.1 <0.1 <0.1 <1 <0.1 0.7 <0.2 30 <0.01 6 1.5 <0.1 <0.1 3897 <0.1 <0.1 <0.1 <1																			
1041695	Drill Core	8.36	0.008	1.0	64.7	6.1	29	<0.1	19.2	9.3	255	2.59	10	1.7	<0.1	8.7	401	<0.1	0.3	<0.1	89
DUP 1041695	QC	0.007 1.0 58.0 6.0 25 <0.1 17.1 9.0 259 2.53 9 1.6 <0.1 8.3 390 <0.1 0.5 <0.1 88																			
1041476	Drill Core	6.02	0.007	1.9	88.3	5.9	27	<0.1	15.4	7.3	220	2.41	6	2.1	<0.1	9.4	445	<0.1	1.3	<0.1	79
DUP 1041476	QC	0.005 2.6 71.8 6.1 26 <0.1 14.8 6.9 206 2.32 7 2.1 <0.1 8.9 454 <0.1 1.1 <0.1 76																			
Reference Materials																					
STD OREAS24P	Standard	1.4 50.3 3.2 111 <0.1 145.0 45.6 1090 7.09 2 0.7 <0.1 2.9 377 0.1 0.1 <0.1 161																			
STD OREAS24P	Standard	1.4 48.3 2.9 107 <0.1 136.7 43.3 993 6.81 2 0.7 <0.1 3.0 366 <0.1 <0.1 <0.1 153																			
STD OREAS24P	Standard	1.5 48.1 3.3 115 <0.1 135.4 46.2 1125 7.41 5 0.7 <0.1 2.9 373 0.1 <0.1 <0.1 166																			
STD OREAS24P	Standard	1.3 48.0 2.9 106 <0.1 139.0 43.3 1060 7.27 4 0.6 <0.1 2.8 402 0.2 <0.1 <0.1 151																			
STD OREAS24P	Standard	1.3 50.6 2.4 117 <0.1 133.0 42.6 1087 7.30 3 0.7 <0.1 2.8 367 <0.1 0.1 <0.1 154																			
STD OREAS24P	Standard	1.8 56.6 2.9 112 <0.1 138.3 44.1 1099 7.17 3 0.7 <0.1 2.8 387 0.3 <0.1 <0.1 156																			
STD OREAS45C	Standard	2.1 643.5 27.1 85 0.4 350.0 102.5 1170 17.88 12 2.6 <0.1 11.7 36 0.2 0.9 0.2 284																			
STD OREAS45C	Standard	2.1 602.1 26.2 76 0.1 309.1 97.2 1068 16.97 10 2.5 <0.1 11.6 37 0.1 0.8 0.2 250																			
STD OREAS45C	Standard	2.3 618.5 25.5 82 0.4 340.3 101.0 1170 17.10 12 2.5 <0.1 11.4 38 0.1 0.7 0.2 271																			
STD OREAS45C	Standard	1.8 595.3 23.9 79 0.3 322.6 96.6 1166 17.55 12 2.3 <0.1 10.3 40 0.1 0.8 0.3 262																			



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 08, 2011

Page: 1 of 3 Part 2

QUALITY CONTROL REPORT

VAN11005905.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1	
Pulp Duplicates																					
REP G1	QC																				
REP 1041660	QC	34.81	0.004	0.1	<1	1.72	8	<0.001	0.06	0.002	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1	<1	<1	0.2
1041684	Drill Core	2.64	0.055	7.5	43	1.54	479	0.394	7.18	3.054	1.73	0.5	7.8	22	1.6	17.1	3.4	0.2	<1	11	36.8
REP 1041684	QC																				
1041703	Drill Core	2.69	0.053	9.1	40	1.40	683	0.382	7.55	2.886	2.57	0.2	6.8	26	1.7	16.5	3.2	0.2	1	10	33.2
REP 1041703	QC	2.70	0.053	8.7	41	1.37	681	0.370	7.44	2.788	2.56	0.2	6.4	24	1.5	15.7	3.1	0.2	1	10	32.3
1041709	Drill Core	2.66	0.046	8.2	34	0.99	1013	0.301	7.24	1.979	2.44	2.3	5.0	23	0.8	12.4	2.7	0.2	1	9	126.7
REP 1041709	QC																				
1041713	Drill Core	1.98	0.042	8.8	34	0.95	920	0.268	7.76	2.615	2.14	2.2	5.7	23	1.4	8.6	3.0	0.3	<1	9	28.5
REP 1041713	QC	2.00	0.041	8.1	34	0.97	893	0.265	7.59	2.616	2.23	2.0	4.9	21	1.3	8.1	3.0	0.2	1	9	26.8
Core Reject Duplicates																					
1041660	Rock	34.71	0.003	0.3	<1	1.72	5	<0.001	0.03	0.003	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1	<1	<1	0.2
DUP 1041660	QC	34.92	0.004	0.1	<1	1.73	5	<0.001	0.04	0.001	<0.01	<0.1	0.2	<1	<0.1	0.2	<0.1	<0.1	<1	<1	0.1
1041695	Drill Core	1.90	0.046	6.8	35	1.26	566	0.352	7.07	2.907	2.44	0.4	6.3	20	1.6	15.1	3.3	0.2	<1	9	36.6
DUP 1041695	QC	1.87	0.042	6.8	34	1.22	545	0.332	7.15	2.866	2.38	0.3	6.0	19	1.3	14.4	3.1	0.2	1	9	33.8
1041476	Drill Core	1.68	0.048	11.2	25	0.78	731	0.270	7.80	2.936	2.36	5.5	28.3	28	2.4	9.1	3.4	0.3	<1	8	18.4
DUP 1041476	QC	1.63	0.043	10.4	22	0.74	721	0.265	7.72	2.951	2.16	5.3	26.9	27	2.3	8.5	2.9	0.3	1	8	19.1
Reference Materials																					
STD OREAS24P	Standard	5.88	0.130	18.8	192	4.13	275	1.047	7.85	2.491	0.63	0.6	130.2	35	1.6	20.7	18.8	1.1	1	20	7.9
STD OREAS24P	Standard	5.50	0.125	18.8	191	3.88	272	0.987	7.42	2.344	0.60	0.4	125.6	36	1.6	20.7	18.4	1.0	1	18	7.3
STD OREAS24P	Standard	5.85	0.136	20.3	197	4.10	273	1.115	7.65	2.476	0.68	0.4	135.2	39	1.6	22.1	20.2	1.1	1	20	8.3
STD OREAS24P	Standard	5.65	0.128	16.8	188	3.92	262	1.015	7.54	2.398	0.64	0.5	128.2	36	1.4	20.4	17.9	1.1	1	20	8.0
STD OREAS24P	Standard	5.62	0.128	17.1	187	3.99	254	1.055	7.45	2.240	0.68	0.4	124.6	35	1.5	25.0	18.6	1.0	1	18	8.0
STD OREAS24P	Standard	5.78	0.132	18.1	204	3.99	287	1.025	7.61	2.377	0.65	0.4	129.3	36	1.5	21.4	18.5	1.1	<1	20	8.0
STD OREAS45C	Standard	0.49	0.050	28.0	980	0.23	287	1.153	7.52	0.105	0.35	1.2	165.5	52	3.2	12.6	22.3	1.4	1	63	16.6
STD OREAS45C	Standard	0.46	0.047	28.7	924	0.22	281	1.126	7.27	0.093	0.32	1.0	160.6	52	3.1	12.6	21.2	1.3	<1	56	14.5
STD OREAS45C	Standard	0.48	0.054	26.9	884	0.28	286	1.241	7.46	0.119	0.34	1.2	165.2	52	3.1	12.8	22.6	1.5	<1	60	16.7
STD OREAS45C	Standard	0.49	0.052	23.4	903	0.28	275	1.183	7.42	0.116	0.34	1.1	165.0	51	3.1	11.8	22.3	1.5	1	58	16.3

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 1 of 3 **Part** 3

QUALITY CONTROL REPORT

VAN11005905.1

Method	1EX	1EX	1EX
Analyte	S	Rb	Hf
Unit	%	ppm	ppm
MDL	0.1	0.1	0.1
Pulp Duplicates			
REP G1	QC		
REP 1041660	QC	<0.1	<0.1
1041684	Drill Core	<0.1	53.8
REP 1041684	QC		
1041703	Drill Core	<0.1	66.4
REP 1041703	QC	<0.1	63.2
1041709	Drill Core	<0.1	71.1
REP 1041709	QC		
1041713	Drill Core	<0.1	125.1
REP 1041713	QC	<0.1	123.2
Core Reject Duplicates			
1041660	Rock	<0.1	<0.1
DUP 1041660	QC	<0.1	<0.1
1041695	Drill Core	<0.1	67.6
DUP 1041695	QC	<0.1	65.1
1041476	Drill Core	<0.1	94.0
DUP 1041476	QC	<0.1	86.1
Reference Materials			
STD OREAS24P	Standard	<0.1	16.4
STD OREAS24P	Standard	<0.1	20.2
STD OREAS24P	Standard	<0.1	23.8
STD OREAS24P	Standard	<0.1	27.7
STD OREAS24P	Standard	<0.1	19.9
STD OREAS24P	Standard	<0.1	21.0
STD OREAS45C	Standard	<0.1	23.5
STD OREAS45C	Standard	<0.1	23.2
STD OREAS45C	Standard	<0.1	21.7
STD OREAS45C	Standard	<0.1	25.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 2 of 3 Part 1

QUALITY CONTROL REPORT

VAN11005905.1

	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX
	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
STD OREAS45C	Standard		1.8	620.6	26.0	94	0.2	316.6	101.8	1155	18.06	10	2.5	<0.1	11.7	41	0.2	0.8	0.3	251
STD OREAS45C	Standard		2.2	629.7	26.5	90	0.5	352.7	103.5	1201	17.46	12	2.3	<0.1	11.0	40	0.4	0.6	0.3	279
STD OXH82	Standard	1.400																		
STD OXH82	Standard	1.312																		
STD OXH82	Standard	1.305																		
STD OXH82	Standard	1.300																		
STD OXH82	Standard	1.269																		
STD OXK79	Standard	3.870																		
STD OXK79	Standard	3.680																		
STD OXK79	Standard	3.585																		
STD OXK79	Standard	3.446																		
STD OXH82 Expected		1.278																		
STD OXK79 Expected		3.532																		
STD OREAS24P Expected			1.5	52	2.9	119	0.06	141	44	1100	7.53	1.2	0.75		2.85	403	0.15	0.09		158
STD OREAS45C Expected			2.26	620	24	83	0.28	333	104	1160	18.33	10.1	2.4	0.045	10.2	36.4	0.15	0.79	0.21	270
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 2 of 3 Part 2

QUALITY CONTROL REPORT

VAN11005905.1

		1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX		
		Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
		%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
		0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	0.1
STD OREAS45C	Standard	0.50	0.052	26.7	968	0.30	277	1.162	6.96	0.112	0.36	1.1	164.1	54	2.9	15.5	23.9	1.4	1	55	16.3	
STD OREAS45C	Standard	0.49	0.053	26.4	942	0.26	307	1.224	7.55	0.104	0.36	1.0	168.6	55	3.2	13.1	22.0	1.5	<1	61	16.7	
STD OXH82	Standard																					
STD OXH82	Standard																					
STD OXH82	Standard																					
STD OXH82	Standard																					
STD OXH82	Standard																					
STD OXK79	Standard																					
STD OXK79	Standard																					
STD OXK79	Standard																					
STD OXK79	Standard																					
STD OXH82 Expected																						
STD OXK79 Expected																						
STD OREAS24P Expected		5.83	0.136	17.4	196	4.13	285	1.1	7.66	2.34	0.7	0.5	141	37.6	1.6	21.3	21	1.04		20	8.7	
STD OREAS45C Expected		0.482	0.051	26.2	962	0.25	270	1.1313	7.59	0.097	0.36	1.06	169.7	54	2.9	12.9	23.05	1.43		59.03	15.69	
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank																					
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<1	<0.1	
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<1	<0.1	
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<1	<0.1	
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<1	<0.1	
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<1	<0.1	

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 2 of 3 Part 3

QUALITY CONTROL REPORT

VAN11005905.1

		1EX S %	1EX Rb ppm	1EX Hf ppm
		0.1	0.1	0.1
STD OREAS45C	Standard	<0.1	23.1	4.2
STD OREAS45C	Standard	<0.1	25.3	4.5
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXH82	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXK79	Standard			
STD OXH82 Expected				
STD OXK79 Expected				
STD OREAS24P Expected			22.4	3.6
STD OREAS45C Expected		0.021	24	4.27
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank			
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 3 of 3 Part 1

QUALITY CONTROL REPORT

VAN11005905.1

		WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
Prep Wash																					
G1	Prep Blank	<0.01	<0.005	0.1	3.4	20.1	52	<0.1	2.7	4.4	742	2.26	<1	2.8	<0.1	8.9	736	0.2	0.1	0.2	49
G1	Prep Blank	<0.01		0.2	2.9	20.2	51	<0.1	2.7	4.5	742	2.35	<1	2.7	<0.1	8.9	695	<0.1	<0.1	0.1	50
G1	Prep Blank		<0.005																		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 3 of 3 Part 2

QUALITY CONTROL REPORT

VAN11005905.1

		1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li
		%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1
Prep Wash																					
G1	Prep Blank	2.39	0.076	22.4	4	0.56	966	0.243	7.58	2.788	3.09	0.1	9.8	48	1.7	13.6	24.5	1.4	3	5	34.4
G1	Prep Blank	2.32	0.081	25.1	4	0.56	930	0.248	7.13	2.659	3.00	0.1	9.8	53	1.7	13.9	25.2	1.4	3	5	34.7
G1	Prep Blank																				



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 08, 2011

Page: 3 of 3 Part 3

QUALITY CONTROL REPORT

VAN11005905.1

		1EX	1EX	1EX
		S	Rb	Hf
		%	ppm	ppm
		0.1	0.1	0.1
Prep Wash				
G1	Prep Blank	<0.1	103.8	0.5
G1	Prep Blank	<0.1	103.1	0.6
G1	Prep Blank			



1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Acme Analytical Laboratories (Vancouver) Ltd.

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Submitted By: Tim Johnson
Receiving Lab: Canada-Vancouver
Received: November 01, 2011
Report Date: December 07, 2011
Page: 1 of 5

CERTIFICATE OF ANALYSIS

VAN11005906.1

CLIENT JOB INFORMATION

Project: Taseko
Shipment ID:
P.O. Number
Number of Samples: 106

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	104	Crush, split and pulverize 250 g rock to 200 mesh			VAN
G601	106	Fire Assay fusion Au by ICP-ES	30	Completed	VAN
1EX	106	4 Acid digestion ICP-MS analysis	0.25	Completed	VAN

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0
Canada

CC: Mathius Westphal



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 2 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
1041727	Drill Core	3.27	0.027	4.8	338.1	7.8	33	0.4	22.7	11.3	318	2.83	15	2.2	0.3	8.5	371	<0.1	0.6	0.2	96
1041728	Drill Core	5.40	0.024	3.6	459.9	7.4	33	0.2	25.3	12.0	329	3.00	6	2.0	<0.1	8.1	378	<0.1	0.4	0.2	108
1041729	Drill Core	4.55	0.048	5.1	752.0	7.0	29	0.4	21.1	9.9	210	2.20	8	3.1	<0.1	6.9	360	0.1	0.4	0.1	101
1041730	Drill Core	2.23	0.280	3.4	851.1	7.2	31	0.5	23.4	10.6	247	2.50	11	7.2	<0.1	7.8	377	<0.1	0.4	0.1	103
1041731	Drill Core	4.94	0.080	2.5	755.2	6.4	30	0.3	23.4	10.8	261	2.53	10	3.8	<0.1	8.6	398	<0.1	0.3	0.1	109
1041732	Drill Core	2.20	0.052	15.0	1163	6.2	26	0.5	26.9	10.0	215	2.18	11	3.7	<0.1	8.3	390	<0.1	0.4	0.1	105
1041733	Drill Core	4.57	0.080	19.4	1363	6.6	30	0.5	25.2	10.4	209	2.10	6	4.1	<0.1	8.7	353	<0.1	0.4	0.1	106
1041734	Drill Core	4.65	0.052	12.4	1203	6.2	31	0.5	28.3	10.8	210	2.21	5	4.3	<0.1	7.8	351	<0.1	0.3	0.1	110
1041735	Drill Core	2.92	0.032	9.1	815.5	10.9	42	0.4	27.0	11.8	291	2.69	9	2.8	<0.1	7.7	384	0.1	0.5	0.2	114
1041736	Drill Core	4.98	0.030	2.7	462.8	22.6	104	0.2	27.3	12.2	391	3.05	9	2.6	<0.1	7.5	370	0.2	0.4	0.2	117
1041737	Drill Core	5.46	0.067	4.0	1454	7.6	34	0.6	28.7	14.8	276	2.62	8	3.0	<0.1	7.5	394	0.1	0.4	0.5	111
1041738	Drill Core	4.85	0.015	3.9	268.8	8.0	42	0.1	26.5	13.3	398	3.22	8	3.2	<0.1	8.7	382	<0.1	0.6	0.4	117
1041739	Drill Core	5.04	0.012	3.7	106.6	8.9	47	<0.1	26.2	13.3	456	3.06	8	2.6	<0.1	8.2	397	0.1	0.5	<0.1	103
1041740	Rock Pulp	0.09	1.447	294.6	9864	84.4	131	5.2	34.8	20.2	351	4.91	37	5.7	1.3	10.1	190	3.0	18.3	3.5	99
1041741	Drill Core	4.93	0.010	4.5	133.1	8.7	41	<0.1	25.0	13.8	428	3.10	8	2.4	<0.1	7.6	417	<0.1	0.5	<0.1	105
1041742	Drill Core	5.85	0.023	5.1	486.1	6.6	32	0.3	26.1	11.7	275	2.94	12	4.1	<0.1	7.1	409	<0.1	0.4	0.2	106
1041743	Drill Core	7.38	0.030	1.2	501.1	6.5	29	0.2	26.2	15.3	236	3.07	6	1.6	<0.1	7.6	363	<0.1	0.4	0.4	118
1041744	Drill Core	2.91	0.029	1.1	635.8	6.1	32	0.3	27.2	13.7	192	2.55	8	2.3	<0.1	6.7	343	<0.1	0.3	0.2	132
1041745	Drill Core	4.05	0.019	9.9	406.5	4.9	25	0.4	20.0	9.1	182	1.73	7	5.4	<0.1	8.6	354	<0.1	0.3	<0.1	82
1041746	Drill Core	5.13	0.012	6.3	412.9	5.6	22	0.2	20.8	9.1	151	1.57	8	3.2	<0.1	9.6	392	<0.1	0.4	<0.1	79
1041747	Drill Core	2.53	0.023	33.7	751.7	7.7	24	0.4	20.4	9.0	165	1.59	8	6.3	<0.1	9.0	414	0.1	0.3	<0.1	79
1041748	Drill Core	2.23	0.020	14.8	482.5	5.5	23	0.2	19.7	8.7	166	1.67	6	2.5	<0.1	8.5	373	<0.1	0.3	<0.1	81
1041749	Drill Core	3.11	0.069	23.5	1261	6.2	24	0.6	20.4	9.3	165	1.63	8	4.4	<0.1	9.3	399	<0.1	0.4	<0.1	73
1041750	Drill Core	4.38	0.020	84.0	555.9	5.7	25	0.3	20.1	9.1	170	1.77	8	2.9	<0.1	9.4	392	<0.1	0.3	<0.1	78
1041751	Drill Core	3.57	0.034	4.0	606.9	6.6	22	0.2	22.4	11.4	169	1.81	7	2.3	<0.1	8.2	409	<0.1	0.3	<0.1	105
1041752	Drill Core	3.08	0.025	12.4	712.6	6.5	25	0.3	21.5	12.3	159	1.82	7	2.4	<0.1	8.3	395	<0.1	0.3	0.1	87
1041753	Drill Core	3.97	0.039	22.2	679.6	7.6	23	0.3	21.7	13.3	161	1.80	8	2.4	<0.1	8.6	382	0.2	0.3	0.1	85
1041754	Drill Core	2.28	0.016	139.1	391.8	5.7	29	0.2	22.8	10.5	159	1.82	8	4.7	<0.1	7.2	404	0.2	0.2	<0.1	79
1041755	Drill Core	2.88	0.009	2.4	407.6	6.0	29	0.2	22.4	9.8	160	1.76	9	1.3	<0.1	7.4	424	<0.1	0.3	<0.1	83
1041756	Drill Core	4.73	0.016	11.5	626.6	5.7	27	0.3	20.6	9.6	212	2.09	8	2.3	<0.1	9.2	394	<0.1	0.3	<0.1	81

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 2 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041727	Drill Core	2.26	0.050	9.1	39	1.33	602	0.369	7.11	2.910	2.29	1.2	8.3	23	1.7	14.6	3.5	0.3	<1	11	24.4
1041728	Drill Core	2.36	0.051	8.6	44	1.43	584	0.366	7.10	2.898	2.35	0.6	8.3	22	1.9	14.2	3.6	0.2	<1	11	20.0
1041729	Drill Core	1.68	0.050	9.3	34	1.27	535	0.357	7.01	3.064	2.18	0.8	7.7	23	1.9	11.3	3.2	0.2	<1	10	22.8
1041730	Drill Core	1.71	0.051	14.1	41	1.33	588	0.362	7.30	2.951	2.00	0.8	7.9	33	2.2	14.5	3.3	0.2	<1	10	24.7
1041731	Drill Core	1.82	0.051	10.3	40	1.40	536	0.371	6.84	2.895	2.16	0.6	9.0	27	2.0	15.4	3.4	0.3	<1	11	25.6
1041732	Drill Core	1.88	0.055	6.0	38	1.51	357	0.374	6.95	2.975	1.53	0.7	7.6	14	1.6	10.5	3.4	0.3	<1	11	30.6
1041733	Drill Core	1.69	0.052	7.5	39	1.59	357	0.374	7.09	3.077	1.59	2.7	6.5	17	2.0	9.5	3.3	0.2	<1	11	26.3
1041734	Drill Core	1.65	0.066	5.4	41	1.74	333	0.400	6.90	3.006	1.59	1.3	6.4	13	1.9	10.2	3.4	0.2	<1	12	29.0
1041735	Drill Core	2.27	0.055	8.7	44	1.55	490	0.381	7.26	3.054	1.95	0.8	8.1	21	2.0	13.6	3.4	0.3	1	12	23.2
1041736	Drill Core	2.72	0.053	10.1	44	1.40	403	0.381	7.38	3.054	1.64	1.2	7.4	27	2.1	16.8	3.4	0.2	<1	12	27.1
1041737	Drill Core	1.93	0.056	9.6	44	1.66	474	0.386	7.29	3.056	1.87	0.8	7.6	24	2.3	14.4	3.3	0.2	1	11	29.4
1041738	Drill Core	2.52	0.052	10.9	47	1.57	592	0.381	7.31	2.899	1.98	0.9	8.0	29	2.0	14.8	3.4	0.3	1	12	25.8
1041739	Drill Core	2.88	0.053	9.8	41	1.48	631	0.361	7.27	2.839	2.30	0.8	8.8	25	1.3	14.9	3.2	0.2	<1	11	25.5
1041740	Rock Pulp	1.60	0.077	28.3	105	1.01	44	0.175	7.14	0.787	3.73	17.6	22.3	56	3.6	12.3	2.6	0.2	1	11	14.1
1041741	Drill Core	2.73	0.054	10.1	42	1.50	671	0.369	7.59	3.279	2.52	0.9	7.5	26	1.4	15.5	3.4	0.2	<1	12	22.4
1041742	Drill Core	2.91	0.051	9.4	45	1.53	329	0.384	6.86	2.909	1.62	1.3	5.9	25	2.0	15.1	3.3	0.2	<1	11	33.0
1041743	Drill Core	2.39	0.055	8.7	42	1.55	290	0.388	7.54	3.154	1.32	4.9	5.5	23	2.3	15.0	3.6	0.3	<1	11	28.3
1041744	Drill Core	2.43	0.065	7.7	45	1.67	284	0.347	7.24	3.082	1.26	1.5	5.0	21	2.4	13.8	3.8	0.3	1	12	37.3
1041745	Drill Core	2.78	0.052	5.8	31	1.25	305	0.311	7.00	3.099	1.66	1.5	8.2	14	1.2	10.5	3.1	0.2	<1	9	28.5
1041746	Drill Core	2.31	0.079	7.6	30	1.27	307	0.323	7.08	3.123	1.23	0.4	11.9	17	1.1	7.7	3.0	0.3	1	8	26.9
1041747	Drill Core	2.28	0.044	5.5	31	1.27	315	0.318	7.13	3.229	1.26	0.5	12.0	12	1.4	6.9	3.2	0.3	1	8	29.7
1041748	Drill Core	2.12	0.045	4.5	31	1.22	388	0.306	7.02	3.008	1.41	0.9	11.4	10	1.2	7.1	2.9	0.3	1	8	25.0
1041749	Drill Core	2.12	0.043	4.5	29	1.20	347	0.308	6.93	3.250	1.34	1.1	11.8	10	1.2	7.0	3.1	0.2	1	8	28.3
1041750	Drill Core	2.00	0.046	6.0	28	1.24	409	0.305	6.72	3.261	1.48	0.4	11.9	14	1.2	7.9	3.2	0.3	<1	8	30.1
1041751	Drill Core	2.33	0.053	9.8	33	1.39	281	0.332	7.32	3.226	1.28	0.5	10.5	23	1.7	11.5	3.3	0.3	<1	10	27.3
1041752	Drill Core	2.22	0.053	8.3	31	1.31	326	0.318	6.90	3.212	1.31	0.8	10.8	21	1.7	11.2	3.1	0.2	<1	9	26.4
1041753	Drill Core	2.05	0.054	7.9	32	1.30	317	0.326	6.92	3.267	1.30	2.5	10.6	18	1.3	7.9	2.9	0.2	<1	9	25.9
1041754	Drill Core	2.34	0.080	4.9	39	1.42	281	0.309	6.89	3.320	1.30	0.8	10.0	13	1.4	9.4	3.5	0.3	1	10	30.6
1041755	Drill Core	2.14	0.058	6.6	38	1.40	300	0.308	6.96	3.201	1.53	0.4	8.6	17	1.4	8.8	3.3	0.3	<1	9	28.0
1041756	Drill Core	2.14	0.043	6.4	33	1.30	451	0.324	7.16	3.064	1.63	0.5	11.4	16	1.4	8.8	3.1	0.3	<1	9	25.5

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 07, 2011

Page: 2 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041727	Drill Core	<0.1	76.1	0.4
1041728	Drill Core	<0.1	71.7	0.5
1041729	Drill Core	<0.1	89.0	0.3
1041730	Drill Core	<0.1	78.0	0.4
1041731	Drill Core	<0.1	81.2	0.4
1041732	Drill Core	<0.1	80.7	0.3
1041733	Drill Core	0.1	94.3	0.3
1041734	Drill Core	0.1	77.7	0.3
1041735	Drill Core	<0.1	81.6	0.3
1041736	Drill Core	<0.1	81.5	0.4
1041737	Drill Core	0.2	84.9	0.3
1041738	Drill Core	<0.1	67.6	0.4
1041739	Drill Core	<0.1	66.4	0.5
1041740	Rock Pulp	2.4	163.6	0.8
1041741	Drill Core	<0.1	74.7	0.3
1041742	Drill Core	<0.1	90.4	0.3
1041743	Drill Core	0.1	69.7	0.3
1041744	Drill Core	<0.1	56.7	0.2
1041745	Drill Core	<0.1	93.3	0.3
1041746	Drill Core	<0.1	69.3	0.5
1041747	Drill Core	<0.1	69.3	0.6
1041748	Drill Core	<0.1	65.5	0.5
1041749	Drill Core	0.1	69.5	0.5
1041750	Drill Core	<0.1	68.6	0.6
1041751	Drill Core	<0.1	67.9	0.5
1041752	Drill Core	0.2	68.4	0.5
1041753	Drill Core	0.3	75.0	0.5
1041754	Drill Core	<0.1	57.0	0.5
1041755	Drill Core	<0.1	71.8	0.4
1041756	Drill Core	<0.1	77.0	0.6



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 3 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041757	Drill Core	8.20	0.028	3.1	674.1	6.3	26	0.2	23.1	11.6	204	2.26	6	2.0	<0.1	9.2	384	<0.1	0.3	0.1	95
1041758	Drill Core	6.84	0.022	2.1	589.1	6.2	28	0.2	21.7	12.2	215	2.65	7	3.3	<0.1	14.3	376	<0.1	0.2	<0.1	105
1041759	Drill Core	3.05	0.012	1.0	84.7	5.9	26	<0.1	21.7	9.6	242	2.88	7	1.8	<0.1	10.1	384	<0.1	0.2	<0.1	105
1041760	Drill Core	2.60	0.009	0.8	179.3	5.4	30	<0.1	19.6	9.6	224	2.81	7	1.3	<0.1	7.9	395	<0.1	0.3	0.5	102
1041761	Drill Core	2.61	0.015	13.2	97.3	6.6	29	<0.1	14.9	7.4	171	1.63	5	3.1	<0.1	8.4	353	<0.1	0.2	0.3	65
1041762	Drill Core	2.32	<0.005	23.2	13.4	5.3	21	<0.1	10.8	5.5	108	1.09	7	4.0	<0.1	8.8	384	<0.1	0.2	0.3	41
1041763	Drill Core	7.25	0.008	12.7	52.0	6.6	26	<0.1	19.5	9.5	182	2.18	6	2.4	<0.1	10.4	392	0.1	0.3	0.2	98
1041764	Drill Core	2.63	0.033	9.6	36.2	7.2	24	0.1	16.6	10.5	137	1.41	7	4.9	<0.1	10.2	379	<0.1	0.3	0.2	63
1041765	Drill Core	5.21	0.055	0.8	757.5	7.5	27	0.3	21.2	13.9	177	2.18	7	2.3	<0.1	9.0	400	<0.1	0.2	0.2	95
1041766	Drill Core	5.74	0.025	0.8	354.6	7.1	27	0.2	20.7	10.6	204	2.65	7	1.2	<0.1	8.7	426	<0.1	0.3	0.2	104
1041767	Drill Core	2.66	0.008	1.1	175.9	6.2	29	0.4	20.0	10.3	208	2.69	7	1.0	<0.1	9.1	408	<0.1	0.2	0.2	100
1041768	Drill Core	2.39	0.014	0.7	443.4	7.9	30	0.2	23.3	11.1	218	2.63	8	1.2	<0.1	8.8	429	<0.1	0.2	0.2	112
1041769	Drill Core	5.03	0.020	1.0	276.5	6.3	31	0.1	19.3	10.0	218	2.16	9	1.6	<0.1	8.6	414	<0.1	0.3	0.1	85
1041770	Drill Core	7.05	0.007	1.1	154.9	6.3	26	<0.1	20.2	9.7	211	2.72	8	1.1	<0.1	7.3	391	<0.1	0.2	<0.1	100
1041771	Drill Core	2.62	0.018	0.8	328.7	5.2	26	0.2	22.0	11.2	202	2.67	7	1.2	<0.1	8.3	396	<0.1	0.2	<0.1	117
1041772	Drill Core	2.70	0.016	1.5	170.9	6.4	28	<0.1	23.1	11.1	207	2.49	7	1.0	<0.1	9.9	419	<0.1	0.2	<0.1	100
1041773	Drill Core	8.12	0.012	1.0	189.4	6.3	29	0.1	20.8	10.6	212	2.53	9	1.6	<0.1	8.8	401	<0.1	0.4	<0.1	104
1041774	Drill Core	6.82	0.026	1.0	309.8	5.8	26	0.2	18.3	9.6	170	1.83	5	1.4	<0.1	7.4	369	<0.1	0.3	0.1	81
1041775	Drill Core	5.84	0.010	0.9	82.4	6.0	32	<0.1	19.6	11.3	237	2.46	9	2.1	<0.1	9.3	416	<0.1	0.3	<0.1	100
1041776	Drill Core	3.39	0.020	8.6	973.8	7.6	32	0.3	17.3	9.6	193	1.69	10	3.3	<0.1	8.2	433	<0.1	0.5	<0.1	71
1041777	Drill Core	2.61	0.005	2362	92.1	54.8	29	0.4	11.0	21.1	130	2.45	16	31.4	<0.1	7.6	427	<0.1	0.8	0.8	51
1041778	Drill Core	2.70	0.009	5.2	389.6	7.0	28	0.2	20.9	9.3	170	1.74	7	2.9	<0.1	8.3	389	<0.1	0.3	0.3	75
1041779	Drill Core	3.34	0.223	5.6	3087	7.2	25	1.2	12.8	7.8	121	1.37	7	2.0	0.3	7.3	383	0.2	0.4	0.1	51
1041780	Rock	0.54	<0.005	0.2	2.8	<0.1	<1	<0.1	0.2	<0.2	20	0.03	15	1.2	<0.1	<0.1	4627	<0.1	<0.1	<0.1	<1
1041781	Drill Core	5.48	0.005	6.7	165.2	5.9	27	<0.1	14.8	7.3	191	1.62	7	3.8	<0.1	10.1	311	<0.1	0.4	<0.1	63
1041782	Drill Core	5.96	<0.005	22.4	146.8	5.3	21	<0.1	10.3	5.4	102	0.94	7	4.5	<0.1	14.3	293	<0.1	0.6	<0.1	39
1041783	Drill Core	4.52	0.008	6.2	72.9	5.4	17	<0.1	10.7	5.2	111	1.05	6	3.5	<0.1	16.1	245	<0.1	0.6	<0.1	42
1041784	Drill Core	2.72	0.006	17.0	193.6	7.0	19	<0.1	10.7	5.2	115	1.08	6	2.7	<0.1	10.7	265	0.1	0.5	<0.1	35
1041785	Drill Core	7.24	0.006	6.6	120.9	7.5	29	0.1	16.6	8.9	188	2.11	6	2.5	<0.1	8.7	334	<0.1	0.5	<0.1	75
1041786	Drill Core	8.18	0.007	1.6	94.0	4.7	26	<0.1	21.2	10.0	206	2.17	6	2.2	<0.1	9.2	392	0.1	0.4	<0.1	82

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 3 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041757	Drill Core	2.04	0.047	10.1	37	1.36	331	0.346	7.14	3.387	1.47	0.5	10.2	25	1.7	10.8	3.3	0.3	<1	9	28.0
1041758	Drill Core	1.99	0.069	10.2	35	1.28	383	0.340	7.56	3.452	1.50	1.3	12.4	29	2.5	21.8	3.9	0.3	<1	10	24.7
1041759	Drill Core	2.20	0.053	7.7	39	1.21	419	0.332	6.98	3.164	1.47	0.5	13.1	21	2.0	17.8	3.5	0.3	1	10	20.0
1041760	Drill Core	2.09	0.048	10.1	32	1.17	389	0.276	6.50	2.849	1.39	0.6	12.2	16	2.1	12.3	3.1	0.3	<1	9	19.8
1041761	Drill Core	1.40	0.032	6.3	20	0.82	464	0.218	6.35	2.963	1.50	1.5	14.1	13	1.1	7.6	2.5	0.2	1	6	19.0
1041762	Drill Core	1.24	0.026	4.5	14	0.69	320	0.178	7.03	3.698	1.24	1.8	16.2	8	1.1	5.7	2.1	0.2	<1	4	16.5
1041763	Drill Core	1.94	0.049	7.8	29	1.26	285	0.291	7.45	3.263	1.23	1.0	12.1	20	1.9	12.0	3.3	0.2	<1	9	22.5
1041764	Drill Core	1.72	0.032	7.1	21	0.94	357	0.244	7.20	3.507	1.41	1.3	12.8	15	1.6	14.5	3.0	0.3	1	7	19.9
1041765	Drill Core	1.97	0.055	8.4	35	1.40	279	0.335	7.42	3.293	1.32	0.4	11.3	23	2.1	13.0	3.7	0.3	1	10	28.9
1041766	Drill Core	2.02	0.050	7.9	35	1.29	374	0.313	7.31	3.216	1.43	0.7	10.9	22	2.2	13.3	3.6	0.2	<1	9	24.6
1041767	Drill Core	1.86	0.050	6.7	35	1.23	489	0.310	7.13	2.899	1.75	0.4	10.4	17	1.9	10.1	3.5	0.2	<1	9	23.1
1041768	Drill Core	2.06	0.064	10.8	35	1.40	302	0.345	7.30	3.271	1.26	0.5	11.0	30	2.3	14.3	4.0	0.3	<1	10	26.5
1041769	Drill Core	2.24	0.050	7.4	33	1.29	313	0.318	7.31	3.454	1.19	0.4	10.8	22	3.0	15.8	3.8	0.3	1	10	23.7
1041770	Drill Core	2.04	0.052	7.3	34	1.21	323	0.304	6.75	3.251	1.27	0.3	9.9	21	2.3	12.0	3.4	0.3	<1	9	22.6
1041771	Drill Core	2.03	0.052	6.9	34	1.33	215	0.318	6.73	3.308	0.94	0.2	11.0	22	3.4	16.5	3.8	0.3	1	10	23.9
1041772	Drill Core	2.13	0.050	7.9	35	1.41	331	0.323	7.42	3.241	1.38	0.4	9.5	20	1.7	9.8	3.4	0.3	<1	10	26.3
1041773	Drill Core	2.07	0.053	6.5	31	1.17	376	0.307	7.29	3.210	1.35	0.6	10.6	18	1.8	11.3	3.3	0.3	1	9	20.6
1041774	Drill Core	1.74	0.042	6.5	29	1.18	226	0.287	6.81	3.334	1.03	0.5	10.1	19	1.9	10.3	3.1	0.3	1	8	25.2
1041775	Drill Core	2.24	0.049	7.1	32	1.27	389	0.296	7.10	3.153	1.31	0.5	11.1	20	1.8	11.7	3.7	0.3	<1	9	27.7
1041776	Drill Core	2.16	0.037	12.0	33	1.23	277	0.284	6.96	3.462	1.16	1.8	9.1	29	2.5	18.5	3.6	0.2	1	9	29.6
1041777	Drill Core	1.50	0.016	9.8	31	0.50	435	0.274	8.59	5.156	1.45	9.2	11.6	18	4.1	43.9	4.8	0.4	2	8	12.1
1041778	Drill Core	2.15	0.046	5.3	31	1.30	230	0.285	6.57	3.363	1.06	1.2	8.6	12	1.7	13.0	3.2	0.2	1	9	30.9
1041779	Drill Core	1.90	0.021	17.5	24	0.72	221	0.224	6.38	3.447	0.79	1.3	10.0	47	2.9	27.1	3.2	0.2	1	6	22.7
1041780	Rock	34.60	0.003	0.5	<1	1.71	11	<0.001	0.04	0.007	<0.01	<0.1	0.2	<1	<0.1	0.5	0.2	<0.1	<1	<1	0.4
1041781	Drill Core	1.74	0.036	7.2	21	0.99	389	0.226	6.61	3.014	1.44	0.7	10.8	16	1.2	9.1	2.9	0.3	1	7	23.9
1041782	Drill Core	1.24	0.023	4.5	14	0.68	176	0.182	6.64	3.468	1.02	1.5	9.5	9	0.8	5.0	2.4	0.3	1	4	18.0
1041783	Drill Core	1.71	0.022	5.0	13	0.57	332	0.177	6.31	2.845	1.59	1.3	10.1	10	0.6	4.2	2.9	0.3	<1	5	16.1
1041784	Drill Core	2.11	0.015	4.1	14	0.56	139	0.171	6.06	3.124	0.87	1.8	8.4	9	0.8	5.5	2.3	0.2	1	4	16.2
1041785	Drill Core	1.90	0.040	4.9	23	1.01	502	0.242	6.41	2.778	1.91	1.2	8.1	13	0.8	8.3	3.1	0.3	<1	7	21.7
1041786	Drill Core	2.37	0.039	4.9	29	1.22	361	0.299	6.43	2.977	1.34	0.5	7.5	12	1.4	8.4	3.6	0.3	1	9	26.0

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 07, 2011

Page: 3 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041757	Drill Core	<0.1	76.8	0.4
1041758	Drill Core	0.1	79.6	0.5
1041759	Drill Core	<0.1	61.5	0.6
1041760	Drill Core	<0.1	63.6	0.5
1041761	Drill Core	<0.1	81.3	0.5
1041762	Drill Core	<0.1	89.6	0.6
1041763	Drill Core	0.1	92.6	0.5
1041764	Drill Core	<0.1	88.3	0.5
1041765	Drill Core	0.1	91.1	0.5
1041766	Drill Core	<0.1	86.7	0.6
1041767	Drill Core	<0.1	92.8	0.4
1041768	Drill Core	<0.1	77.7	0.5
1041769	Drill Core	<0.1	59.6	0.6
1041770	Drill Core	<0.1	56.4	0.5
1041771	Drill Core	<0.1	48.9	0.5
1041772	Drill Core	<0.1	90.3	0.5
1041773	Drill Core	<0.1	77.6	0.6
1041774	Drill Core	<0.1	59.1	0.5
1041775	Drill Core	<0.1	67.2	0.5
1041776	Drill Core	0.2	57.6	0.5
1041777	Drill Core	2.2	140.0	0.6
1041778	Drill Core	0.3	57.1	0.3
1041779	Drill Core	0.4	50.4	0.3
1041780	Rock	<0.1	<0.1	<0.1
1041781	Drill Core	<0.1	77.3	0.4
1041782	Drill Core	<0.1	75.5	0.5
1041783	Drill Core	<0.1	88.5	0.5
1041784	Drill Core	0.2	61.2	0.4
1041785	Drill Core	<0.1	80.2	0.4
1041786	Drill Core	<0.1	50.2	0.3



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 4 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041787	Drill Core	3.15	0.016	2.9	239.1	6.1	32	0.1	19.8	10.2	211	2.17	9	2.2	<0.1	8.8	346	<0.1	0.7	<0.1	81
1041788	Drill Core	4.40	0.025	14.1	576.7	5.9	29	0.2	20.5	10.3	207	2.13	6	4.0	<0.1	10.0	354	0.1	0.5	<0.1	83
1041789	Drill Core	5.07	0.011	2.2	141.3	5.3	27	<0.1	21.0	10.3	207	2.39	7	2.3	<0.1	11.2	450	0.2	0.3	<0.1	91
1041790	Drill Core	6.75	0.019	33.9	341.7	5.6	26	<0.1	21.7	11.2	212	2.36	7	2.3	<0.1	9.1	445	<0.1	0.3	<0.1	87
1041791	Drill Core	4.27	0.015	7.1	315.7	5.6	25	<0.1	19.4	10.1	201	2.17	8	1.5	<0.1	9.0	334	<0.1	0.5	<0.1	80
1041792	Drill Core	2.40	0.020	3.2	447.7	6.8	32	0.2	23.5	12.6	295	2.61	17	4.2	<0.1	10.3	147	0.2	2.6	<0.1	87
1041793	Drill Core	5.56	<0.005	0.9	66.4	5.9	31	<0.1	20.0	10.4	241	2.49	6	1.9	<0.1	6.8	339	<0.1	0.5	<0.1	89
1041794	Drill Core	5.76	0.007	2.5	222.6	6.5	28	<0.1	21.1	9.7	213	2.29	5	1.8	<0.1	8.4	311	<0.1	0.5	<0.1	85
1041795	Drill Core	5.17	<0.005	1.3	89.6	6.2	23	<0.1	15.1	6.8	176	1.87	5	2.0	<0.1	10.8	280	0.1	0.6	0.7	63
1041796	Drill Core	4.59	0.027	1.7	804.1	5.8	27	0.4	14.4	7.4	215	1.79	19	2.0	<0.1	11.1	309	<0.1	2.0	0.6	62
1041797	Drill Core	8.78	0.007	0.8	127.0	5.6	26	<0.1	20.9	10.2	229	2.30	5	2.0	<0.1	9.7	329	<0.1	0.7	0.3	85
1041798	Drill Core	5.42	0.013	2.0	167.1	6.3	25	<0.1	20.5	8.9	233	2.39	7	2.1	<0.1	8.5	413	<0.1	0.6	0.3	88
1041799	Drill Core	5.61	0.092	23.9	2645	8.0	25	0.7	9.7	5.4	133	1.37	9	3.3	<0.1	6.6	472	0.2	0.6	0.3	53
1041800	Rock Pulp	0.08	1.725	289.7	9743	81.2	127	4.9	33.4	19.5	385	4.87	34	5.3	1.4	10.8	196	1.9	20.8	3.6	99
1041801	Drill Core	3.63	0.032	4.0	600.3	5.8	26	0.1	13.4	7.6	231	1.50	5	2.0	<0.1	6.7	407	0.2	0.6	0.1	55
1041802	Drill Core	3.90	0.086	36.9	3068	6.6	28	0.7	12.8	7.7	211	1.89	13	2.2	0.6	5.9	412	0.1	2.1	0.2	76
1041803	Drill Core	5.18	0.025	3.0	813.7	7.1	27	0.2	12.9	7.1	251	1.55	10	2.8	<0.1	6.1	422	<0.1	0.6	0.1	61
1041804	Drill Core	5.69	0.034	4.1	556.8	6.5	23	0.2	12.4	5.9	238	1.41	6	2.1	<0.1	6.9	438	<0.1	0.5	<0.1	61
1041805	Drill Core	4.69	0.024	15.3	809.9	5.5	28	0.1	13.8	6.9	181	1.40	6	2.6	<0.1	6.3	348	<0.1	0.8	0.2	62
1041806	Drill Core	5.08	0.025	1.6	586.1	6.4	25	0.2	12.9	6.5	197	1.48	6	1.9	<0.1	7.1	409	<0.1	0.5	<0.1	58
1041807	Drill Core	5.93	0.036	3.4	698.6	7.4	27	0.2	14.1	6.7	234	1.68	6	2.0	<0.1	6.4	439	<0.1	0.6	0.1	61
1041808	Drill Core	5.51	0.009	3.4	189.7	6.8	29	<0.1	16.6	8.0	240	1.92	6	1.9	<0.1	5.9	398	<0.1	0.3	<0.1	69
1041809	Drill Core	4.52	0.019	4.1	742.4	6.0	27	0.3	12.9	7.5	223	1.48	24	1.8	<0.1	6.9	330	0.2	2.3	<0.1	66
1041810	Drill Core	2.36	0.007	12.3	249.4	7.3	32	0.1	16.8	7.5	269	2.16	7	2.1	<0.1	6.8	413	<0.1	0.6	<0.1	81
1041811	Drill Core	5.27	0.035	12.7	1245	6.1	31	0.2	19.9	8.4	237	2.17	6	1.7	<0.1	5.7	468	<0.1	0.5	0.1	87
1041812	Drill Core	7.40	0.008	2.1	218.1	6.6	33	<0.1	16.4	8.2	230	1.86	7	2.3	<0.1	6.7	393	<0.1	1.3	<0.1	74
1041813	Drill Core	7.19	<0.005	1.8	200.5	7.3	30	<0.1	20.0	9.4	251	2.22	5	2.0	<0.1	6.7	421	<0.1	0.7	<0.1	84
1041814	Drill Core	7.90	<0.005	3.8	72.8	8.3	35	<0.1	17.6	9.2	304	2.38	6	2.5	<0.1	6.5	437	<0.1	0.5	<0.1	79
1041815	Drill Core	8.42	0.013	6.0	180.6	7.8	32	<0.1	18.2	8.3	282	2.16	6	2.7	<0.1	6.8	414	<0.1	0.6	<0.1	75
1041816	Drill Core	7.80	0.029	4.8	290.8	5.9	34	0.1	18.9	7.8	175	1.95	5	1.4	<0.1	6.2	490	<0.1	0.4	<0.1	86

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 4 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041787	Drill Core	2.31	0.040	5.4	28	1.07	499	0.279	6.63	2.791	1.87	1.5	7.7	14	1.1	9.4	3.4	0.3	<1	8	27.1
1041788	Drill Core	2.22	0.042	5.7	26	1.24	395	0.285	6.67	2.823	1.59	2.4	6.7	15	1.3	10.2	3.4	0.4	1	9	31.3
1041789	Drill Core	2.25	0.043	6.9	30	1.33	488	0.306	7.20	2.886	1.73	1.1	6.7	17	1.4	11.3	3.4	0.3	<1	9	29.7
1041790	Drill Core	2.24	0.053	6.4	32	1.38	403	0.312	6.92	3.088	1.54	0.7	7.4	16	1.5	9.9	3.5	0.3	1	9	30.7
1041791	Drill Core	2.48	0.043	5.7	30	1.21	357	0.298	6.64	2.811	1.37	0.7	6.8	16	1.4	9.8	3.3	0.3	2	9	27.3
1041792	Drill Core	4.35	0.042	7.5	31	0.86	1264	0.279	6.51	1.241	2.57	3.3	7.5	20	1.4	13.9	3.3	0.3	<1	9	29.2
1041793	Drill Core	2.71	0.041	5.5	31	1.12	484	0.306	6.81	2.770	1.79	0.8	6.9	16	1.5	11.0	3.2	0.3	2	9	23.4
1041794	Drill Core	2.16	0.042	5.7	29	1.20	422	0.306	6.65	2.860	1.75	0.8	6.6	15	1.3	9.2	3.2	0.3	1	8	31.2
1041795	Drill Core	1.60	0.027	8.9	21	0.85	550	0.228	6.36	2.643	2.24	1.3	9.3	13	1.1	7.7	2.5	0.3	1	6	22.8
1041796	Drill Core	2.55	0.023	8.1	18	0.97	446	0.197	7.66	3.541	1.50	1.6	10.9	19	1.5	10.5	2.4	0.3	1	8	27.8
1041797	Drill Core	2.57	0.051	6.9	36	1.28	730	0.308	6.93	3.075	1.04	1.1	8.4	17	1.7	9.8	3.3	0.3	<1	9	30.2
1041798	Drill Core	2.34	0.047	5.9	30	1.23	386	0.296	6.50	3.101	1.19	0.4	9.6	17	2.2	12.0	3.5	0.3	<1	8	27.2
1041799	Drill Core	2.00	0.011	10.4	23	0.66	240	0.220	6.65	3.583	0.78	1.3	8.5	35	4.1	30.7	3.1	0.2	<1	6	20.5
1041800	Rock Pulp	1.57	0.077	31.4	105	0.97	236	0.200	6.81	0.764	2.84	18.1	24.2	59	3.7	11.4	3.1	0.2	2	10	12.3
1041801	Drill Core	2.74	0.017	10.1	23	1.16	211	0.259	6.61	3.532	0.61	0.8	9.8	31	4.0	22.8	3.7	0.3	<1	9	23.2
1041802	Drill Core	2.50	0.022	8.0	27	1.00	256	0.268	6.35	3.463	0.84	1.1	10.3	29	4.8	26.3	4.1	0.3	<1	8	21.2
1041803	Drill Core	3.31	0.041	7.0	25	1.00	215	0.290	6.44	3.744	0.57	0.7	9.5	27	4.6	20.9	3.7	0.3	1	7	22.3
1041804	Drill Core	3.12	0.054	8.3	23	1.14	215	0.273	6.23	3.605	0.46	0.5	9.0	32	4.4	22.8	3.8	0.3	<1	8	19.6
1041805	Drill Core	2.36	0.039	9.5	24	0.89	192	0.260	6.05	3.307	0.83	1.8	8.8	30	3.9	18.9	3.5	0.3	<1	7	25.5
1041806	Drill Core	2.79	0.039	8.0	25	1.00	230	0.264	6.59	3.604	0.70	0.4	8.8	28	4.0	22.7	3.7	0.3	<1	7	28.5
1041807	Drill Core	2.74	0.041	7.1	26	1.04	285	0.256	6.15	3.516	0.78	0.6	10.1	25	3.2	17.7	3.2	0.2	1	7	25.7
1041808	Drill Core	2.48	0.043	5.7	26	1.04	408	0.266	6.35	3.206	1.18	0.5	8.2	18	1.9	13.3	3.3	0.3	1	7	27.3
1041809	Drill Core	3.18	0.041	7.1	23	0.98	361	0.267	6.28	3.093	0.98	1.0	8.9	25	2.9	19.0	3.7	0.3	<1	8	24.6
1041810	Drill Core	2.50	0.042	6.4	26	1.04	471	0.252	6.47	3.204	1.32	0.8	7.0	17	1.7	9.7	2.9	0.2	<1	7	22.1
1041811	Drill Core	2.28	0.042	6.3	29	1.09	427	0.280	6.30	3.309	1.12	1.2	9.0	19	2.2	11.4	3.1	0.3	1	7	25.1
1041812	Drill Core	2.48	0.045	5.8	24	0.99	389	0.263	6.26	3.032	1.19	0.8	8.4	18	2.1	12.0	3.2	0.3	1	7	20.9
1041813	Drill Core	2.49	0.045	5.9	26	1.14	476	0.280	6.55	3.119	1.33	0.8	10.1	16	1.5	10.3	2.9	0.3	1	7	22.8
1041814	Drill Core	2.26	0.046	6.6	27	1.15	651	0.265	6.16	2.871	1.93	0.6	9.0	18	1.1	9.7	2.9	0.2	<1	7	21.4
1041815	Drill Core	2.30	0.042	6.7	25	1.05	513	0.254	6.47	2.903	1.67	0.8	9.0	17	1.0	9.4	3.0	0.3	<1	7	20.4
1041816	Drill Core	2.13	0.042	4.7	23	1.06	318	0.259	6.27	3.067	0.97	0.5	7.0	13	1.1	8.7	2.9	0.2	<1	7	23.2

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 4 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041787	Drill Core	<0.1	67.6	0.4
1041788	Drill Core	0.1	67.0	0.3
1041789	Drill Core	0.1	82.1	0.4
1041790	Drill Core	0.2	63.5	0.3
1041791	Drill Core	<0.1	56.3	0.4
1041792	Drill Core	0.2	135.8	0.4
1041793	Drill Core	<0.1	62.7	0.4
1041794	Drill Core	<0.1	65.8	0.3
1041795	Drill Core	<0.1	84.5	0.5
1041796	Drill Core	<0.1	78.5	0.4
1041797	Drill Core	<0.1	53.8	0.5
1041798	Drill Core	<0.1	43.1	0.5
1041799	Drill Core	0.3	38.9	0.4
1041800	Rock Pulp	2.5	124.2	0.8
1041801	Drill Core	<0.1	21.6	0.5
1041802	Drill Core	0.3	24.7	0.5
1041803	Drill Core	<0.1	17.6	0.5
1041804	Drill Core	<0.1	12.1	0.5
1041805	Drill Core	<0.1	31.2	0.4
1041806	Drill Core	<0.1	26.9	0.5
1041807	Drill Core	<0.1	23.8	0.5
1041808	Drill Core	<0.1	34.5	0.4
1041809	Drill Core	<0.1	44.8	0.4
1041810	Drill Core	<0.1	44.4	0.3
1041811	Drill Core	0.1	34.5	0.4
1041812	Drill Core	<0.1	52.2	0.5
1041813	Drill Core	<0.1	43.5	0.5
1041814	Drill Core	<0.1	59.8	0.4
1041815	Drill Core	<0.1	53.4	0.5
1041816	Drill Core	<0.1	40.2	0.4



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 5 of 5 Part 1

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
1041817	Drill Core	8.13	0.019	5.8	315.6	5.6	24	<0.1	19.5	8.1	190	1.88	6	1.7	<0.1	7.1	300	0.2	0.9	<0.1	72
1041818	Drill Core	8.51	0.007	8.9	192.0	6.7	30	<0.1	20.0	8.8	239	2.30	5	1.9	<0.1	6.5	372	<0.1	0.8	<0.1	78
1041819	Drill Core	2.39	0.008	6.1	137.6	8.0	33	<0.1	19.4	9.6	284	2.48	4	2.6	<0.1	7.0	390	<0.1	0.5	<0.1	80
1041820	Drill Core	2.82	<0.005	5.1	95.0	8.0	34	<0.1	19.8	9.6	295	2.57	4	2.8	<0.1	6.9	379	<0.1	0.4	<0.1	81
1041821	Drill Core	5.23	<0.005	2.8	50.8	7.8	31	<0.1	17.9	9.2	300	2.36	5	2.2	<0.1	6.4	395	<0.1	0.4	<0.1	76
1041822	Drill Core	8.84	0.007	3.8	148.0	6.3	25	0.1	17.4	9.2	214	2.22	5	1.7	<0.1	5.6	400	<0.1	0.3	<0.1	76
1041823	Drill Core	7.90	0.015	3.6	252.6	6.3	30	<0.1	19.2	8.5	230	2.31	5	1.5	<0.1	6.1	413	<0.1	0.3	<0.1	81
1041824	Drill Core	5.34	0.010	3.6	174.3	6.5	29	0.1	17.5	8.8	228	2.25	5	2.0	<0.1	6.8	387	<0.1	0.4	<0.1	75
1041825	Drill Core	5.55	<0.005	4.0	136.5	6.2	27	<0.1	18.5	9.3	218	2.12	6	1.9	<0.1	7.5	511	<0.1	0.6	<0.1	74
1041826	Drill Core	5.42	0.011	5.0	133.9	4.6	24	<0.1	17.2	7.7	250	1.92	6	2.1	<0.1	7.0	275	0.2	1.8	<0.1	71
1041827	Drill Core	5.72	0.011	2.2	120.3	6.7	30	<0.1	16.2	8.5	414	2.02	7	1.9	<0.1	8.4	508	0.3	1.3	<0.1	65
1041828	Drill Core	9.11	0.017	12.3	191.4	7.4	33	<0.1	19.2	9.4	303	2.31	6	2.9	<0.1	6.5	458	<0.1	0.8	0.1	76
1041829	Drill Core	2.86	0.026	2.1	305.7	6.5	34	0.1	18.6	8.9	262	2.21	5	1.7	<0.1	6.6	433	<0.1	0.3	0.2	75
1041830	Drill Core	5.58	0.016	1.5	117.6	7.0	32	<0.1	18.5	9.1	287	2.65	5	1.8	<0.1	6.9	495	<0.1	0.3	0.1	74
1041831	Drill Core	5.73	0.014	1.6	97.1	8.4	32	<0.1	15.9	9.2	304	2.60	4	1.6	<0.1	6.4	469	<0.1	0.3	<0.1	66
1041832	Drill Core	5.32	0.013	1.6	80.8	8.0	38	0.1	17.4	9.0	348	2.83	4	2.1	<0.1	7.9	452	<0.1	0.3	<0.1	86



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 5 of 5 Part 2

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
1041817	Drill Core	2.43	0.047	4.8	25	0.94	343	0.259	6.56	2.506	1.56	1.4	6.8	13	0.9	6.9	2.8	0.2	<1	7	20.7
1041818	Drill Core	2.43	0.045	6.5	26	1.07	499	0.253	6.60	2.627	1.76	0.7	9.6	16	1.1	8.0	2.7	0.2	1	7	24.3
1041819	Drill Core	2.39	0.041	6.8	26	1.17	667	0.271	6.43	2.592	2.16	0.8	10.0	19	1.3	9.4	2.6	0.3	<1	7	25.1
1041820	Drill Core	2.46	0.045	7.8	26	1.15	657	0.262	6.72	2.654	2.17	0.8	11.1	21	1.2	9.9	2.9	0.2	<1	7	23.6
1041821	Drill Core	2.25	0.042	7.2	24	1.03	644	0.255	6.35	2.651	2.23	0.7	9.4	18	1.0	8.5	2.8	0.2	<1	7	20.1
1041822	Drill Core	2.23	0.038	5.0	25	1.06	498	0.257	6.09	2.850	1.54	0.6	7.6	13	1.2	7.8	2.5	0.2	1	7	21.4
1041823	Drill Core	2.14	0.046	5.9	25	1.10	586	0.266	6.17	2.767	1.77	0.7	7.2	15	0.9	8.5	2.7	0.3	<1	7	22.3
1041824	Drill Core	2.12	0.043	5.8	24	1.08	576	0.249	6.36	2.742	1.79	0.5	7.5	15	1.2	7.6	2.6	0.2	<1	7	23.0
1041825	Drill Core	2.31	0.051	6.5	24	1.12	495	0.264	6.70	2.820	1.66	0.6	7.1	17	1.1	9.2	2.9	0.2	1	7	24.0
1041826	Drill Core	1.86	0.045	4.4	23	1.05	438	0.248	7.00	2.510	1.81	1.1	6.6	12	1.1	6.1	2.7	0.2	1	7	21.1
1041827	Drill Core	4.22	0.040	7.7	21	1.14	711	0.222	6.13	2.221	1.75	1.0	8.0	22	0.9	11.4	2.7	0.2	1	7	19.9
1041828	Drill Core	2.61	0.072	7.2	28	1.04	605	0.259	6.42	2.853	1.70	1.1	9.5	20	1.2	10.2	2.8	0.2	<1	7	21.6
1041829	Drill Core	2.43	0.048	7.1	24	1.11	502	0.281	6.47	3.122	1.39	0.6	9.3	19	1.5	10.0	3.1	0.2	1	7	21.3
1041830	Drill Core	2.57	0.041	7.6	29	1.28	471	0.291	6.93	3.233	1.13	0.5	8.7	19	1.4	9.4	3.1	0.2	<1	8	22.2
1041831	Drill Core	2.40	0.035	6.6	27	1.12	520	0.274	6.86	3.082	1.16	0.4	8.0	16	1.0	7.0	3.1	0.3	1	7	20.6
1041832	Drill Core	2.41	0.044	7.6	27	1.10	631	0.257	6.79	3.069	1.27	0.6	9.6	19	1.3	10.4	3.0	0.2	1	7	19.0



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko
Report Date: December 07, 2011

Page: 5 of 5 Part 3

CERTIFICATE OF ANALYSIS

VAN11005906.1

Method	1EX	1EX	1EX	
Analyte	S	Rb	Hf	
Unit	%	ppm	ppm	
MDL	0.1	0.1	0.1	
1041817	Drill Core	<0.1	73.3	0.3
1041818	Drill Core	<0.1	63.9	0.4
1041819	Drill Core	<0.1	68.7	0.5
1041820	Drill Core	<0.1	67.6	0.5
1041821	Drill Core	<0.1	55.5	0.4
1041822	Drill Core	<0.1	49.0	0.4
1041823	Drill Core	<0.1	55.0	0.4
1041824	Drill Core	<0.1	59.8	0.4
1041825	Drill Core	<0.1	67.4	0.3
1041826	Drill Core	<0.1	84.7	0.3
1041827	Drill Core	<0.1	79.6	0.4
1041828	Drill Core	<0.1	56.7	0.6
1041829	Drill Core	<0.1	49.3	0.4
1041830	Drill Core	<0.1	38.3	0.3
1041831	Drill Core	<0.1	33.3	0.4
1041832	Drill Core	<0.1	36.7	0.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 07, 2011

Page: 1 of 3 Part 1

QUALITY CONTROL REPORT

VAN11005906.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1	
Pulp Duplicates																					
1041730	Drill Core	2.23	0.280	3.4	851.1	7.2	31	0.5	23.4	10.6	247	2.50	11	7.2	<0.1	7.8	377	<0.1	0.4	0.1	103
REP 1041730	QC			3.1	841.7	7.1	30	0.4	21.7	10.1	242	2.47	11	7.5	<0.1	7.9	369	0.1	0.4	<0.1	104
REP 1041773	QC			0.8	185.5	6.8	28	<0.1	20.3	9.8	208	2.46	7	1.6	<0.1	8.3	383	<0.1	0.4	<0.1	100
1041801	Drill Core	3.63	0.032	4.0	600.3	5.8	26	0.1	13.4	7.6	231	1.50	5	2.0	<0.1	6.7	407	0.2	0.6	0.1	55
REP 1041801	QC		0.034																		
1041820	Drill Core	2.82	<0.005	5.1	95.0	8.0	34	<0.1	19.8	9.6	295	2.57	4	2.8	<0.1	6.9	379	<0.1	0.4	<0.1	81
REP 1041820	QC			4.4	96.0	7.6	34	<0.1	19.5	9.5	293	2.57	5	2.6	<0.1	6.0	367	<0.1	0.4	<0.1	83
Core Reject Duplicates																					
1041738	Drill Core	4.85	0.015	3.9	268.8	8.0	42	0.1	26.5	13.3	398	3.22	8	3.2	<0.1	8.7	382	<0.1	0.6	0.4	117
DUP 1041738	QC		0.011	4.0	253.4	8.2	41	0.1	27.4	13.7	383	3.07	9	3.1	<0.1	8.7	391	<0.1	0.6	0.5	113
1041773	Drill Core	8.12	0.012	1.0	189.4	6.3	29	0.1	20.8	10.6	212	2.53	9	1.6	<0.1	8.8	401	<0.1	0.4	<0.1	104
DUP 1041773	QC		0.014	0.8	218.4	7.2	26	0.1	20.3	9.7	205	2.48	8	1.6	<0.1	8.2	369	<0.1	0.4	0.1	98
1041808	Drill Core	5.51	0.009	3.4	189.7	6.8	29	<0.1	16.6	8.0	240	1.92	6	1.9	<0.1	5.9	398	<0.1	0.3	<0.1	69
DUP 1041808	QC		0.013	2.7	216.0	7.1	32	0.1	15.9	8.0	243	1.98	4	2.1	<0.1	7.4	428	<0.1	0.4	<0.1	71
Reference Materials																					
STD OREAS24P	Standard			1.1	48.9	2.8	111	<0.1	138.0	43.5	1054	7.30	4	0.6	<0.1	2.8	379	0.2	0.1	<0.1	159
STD OREAS24P	Standard			1.3	47.2	2.7	113	0.2	138.7	44.5	1076	7.41	3	0.5	<0.1	2.9	397	<0.1	<0.1	<0.1	160
STD OREAS24P	Standard			1.5	48.6	2.8	116	<0.1	144.7	45.2	1121	7.49	2	0.7	<0.1	3.0	383	0.2	0.1	<0.1	153
STD OREAS24P	Standard			1.7	46.9	2.9	109	<0.1	135.8	44.3	1070	7.35	4	0.7	<0.1	2.8	402	<0.1	<0.1	<0.1	154
STD OREAS24P	Standard			1.8	56.6	2.9	112	<0.1	138.3	44.1	1099	7.17	3	0.7	<0.1	2.8	387	0.3	<0.1	<0.1	156
STD OREAS45C	Standard			1.9	610.6	23.8	84	0.4	320.4	96.6	1120	17.67	11	2.1	<0.1	10.2	32	0.2	0.8	0.3	265
STD OREAS45C	Standard			2.6	631.7	24.6	82	0.4	329.4	103.0	1140	18.12	12	2.1	<0.1	10.8	37	0.2	1.1	0.2	274
STD OREAS45C	Standard			2.1	606.6	25.7	81	0.3	327.1	102.4	1159	17.90	11	2.4	<0.1	11.0	42	0.2	0.9	0.2	268
STD OREAS45C	Standard			2.5	604.2	23.9	79	0.3	336.0	98.9	1103	18.14	12	2.3	<0.1	10.4	39	0.2	0.8	0.3	269
STD OREAS45C	Standard			2.2	629.7	26.5	90	0.5	352.7	103.5	1201	17.46	12	2.3	<0.1	11.0	40	0.4	0.6	0.3	279
STD OXH82	Standard		1.287																		
STD OXH82	Standard		1.332																		
STD OXH82	Standard		1.323																		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko
 Report Date: December 07, 2011

Page: 1 of 3 Part 2

QUALITY CONTROL REPORT

VAN11005906.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1	
Pulp Duplicates																					
1041730	Drill Core	1.71	0.051	14.1	41	1.33	588	0.362	7.30	2.951	2.00	0.8	7.9	33	2.2	14.5	3.3	0.2	<1	10	24.7
REP 1041730	QC	1.72	0.051	14.1	39	1.32	584	0.365	7.12	3.009	1.97	0.8	7.8	31	2.1	14.6	3.2	0.2	<1	10	24.1
REP 1041773	QC	2.01	0.056	6.5	29	1.13	362	0.293	6.98	3.090	1.27	0.4	10.9	18	1.9	10.9	3.3	0.3	<1	9	21.5
1041801	Drill Core	2.74	0.017	10.1	23	1.16	211	0.259	6.61	3.532	0.61	0.8	9.8	31	4.0	22.8	3.7	0.3	<1	9	23.2
REP 1041801	QC																				
1041820	Drill Core	2.46	0.045	7.8	26	1.15	657	0.262	6.72	2.654	2.17	0.8	11.1	21	1.2	9.9	2.9	0.2	<1	7	23.6
REP 1041820	QC	2.46	0.044	6.5	27	1.11	635	0.266	6.39	2.633	2.16	0.8	10.5	18	1.3	9.0	2.9	0.2	<1	7	24.6
Core Reject Duplicates																					
1041738	Drill Core	2.52	0.052	10.9	47	1.57	592	0.381	7.31	2.899	1.98	0.9	8.0	29	2.0	14.8	3.4	0.3	1	12	25.8
DUP 1041738	QC	2.47	0.052	10.4	46	1.56	582	0.382	7.23	2.970	1.97	0.9	8.4	28	1.9	15.3	3.5	0.3	1	11	25.8
1041773	Drill Core	2.07	0.053	6.5	31	1.17	376	0.307	7.29	3.210	1.35	0.6	10.6	18	1.8	11.3	3.3	0.3	1	9	20.6
DUP 1041773	QC	1.96	0.058	6.5	30	1.11	369	0.291	6.86	3.027	1.28	0.5	10.0	18	1.9	11.3	3.3	0.3	<1	9	19.8
1041808	Drill Core	2.48	0.043	5.7	26	1.04	408	0.266	6.35	3.206	1.18	0.5	8.2	18	1.9	13.3	3.3	0.3	1	7	27.3
DUP 1041808	QC	2.50	0.047	7.2	24	1.12	436	0.269	6.79	3.205	1.28	0.6	8.9	22	2.0	14.9	3.3	0.3	<1	8	30.6
Reference Materials																					
STD OREAS24P	Standard	5.45	0.137	17.9	187	4.00	265	1.056	7.45	2.358	0.64	0.4	132.5	37	1.6	20.6	18.7	1.1	<1	19	7.1
STD OREAS24P	Standard	5.49	0.126	17.8	190	4.04	271	1.044	7.50	2.332	0.62	0.4	127.9	36	1.7	19.5	18.3	1.1	2	20	6.7
STD OREAS24P	Standard	5.70	0.140	17.9	195	4.02	284	1.047	7.75	2.527	0.68	0.5	138.4	37	1.5	24.2	20.1	1.1	1	20	7.9
STD OREAS24P	Standard	5.90	0.129	19.1	203	4.09	273	1.057	7.64	2.541	0.64	0.5	132.7	40	1.4	21.5	18.9	1.1	<1	20	7.4
STD OREAS24P	Standard	5.78	0.132	18.1	204	3.99	287	1.025	7.61	2.377	0.65	0.4	129.3	36	1.5	21.4	18.5	1.1	<1	20	8.0
STD OREAS45C	Standard	0.47	0.049	23.6	925	0.26	257	1.166	7.03	0.108	0.33	1.1	161.6	49	2.5	11.5	22.1	1.4	<1	58	14.9
STD OREAS45C	Standard	0.48	0.055	25.2	936	0.27	282	1.207	7.19	0.123	0.35	1.1	170.5	52	2.9	11.5	22.4	1.4	<1	61	16.7
STD OREAS45C	Standard	0.48	0.049	24.7	850	0.26	278	1.212	7.28	0.108	0.35	1.1	165.5	51	2.9	13.9	23.0	1.5	<1	59	15.9
STD OREAS45C	Standard	0.46	0.052	24.9	918	0.27	269	1.216	7.31	0.109	0.33	1.2	165.9	52	3.0	11.4	22.6	1.4	<1	60	15.9
STD OREAS45C	Standard	0.49	0.053	26.4	942	0.26	307	1.224	7.55	0.104	0.36	1.0	168.6	55	3.2	13.1	22.0	1.5	<1	61	16.7
STD OXH82	Standard																				
STD OXH82	Standard																				
STD OXH82	Standard																				

This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only.



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 07, 2011

Page: 1 of 3 **Part** 3

QUALITY CONTROL REPORT

VAN11005906.1

Method	1EX	1EX	1EX
Analyte	S	Rb	Hf
Unit	%	ppm	ppm
MDL	0.1	0.1	0.1
Pulp Duplicates			
1041730	Drill Core	<0.1	78.0 0.4
REP 1041730	QC	<0.1	80.1 0.3
REP 1041773	QC	<0.1	70.0 0.5
1041801	Drill Core	<0.1	21.6 0.5
REP 1041801	QC		
1041820	Drill Core	<0.1	67.6 0.5
REP 1041820	QC	<0.1	57.5 0.5
Core Reject Duplicates			
1041738	Drill Core	<0.1	67.6 0.4
DUP 1041738	QC	<0.1	70.8 0.4
1041773	Drill Core	<0.1	77.6 0.6
DUP 1041773	QC	<0.1	73.7 0.4
1041808	Drill Core	<0.1	34.5 0.4
DUP 1041808	QC	<0.1	44.5 0.5
Reference Materials			
STD OREAS24P	Standard	<0.1	24.8 3.5
STD OREAS24P	Standard	<0.1	27.7 3.1
STD OREAS24P	Standard	<0.1	20.5 3.5
STD OREAS24P	Standard	<0.1	23.1 3.1
STD OREAS24P	Standard	<0.1	21.0 3.3
STD OREAS45C	Standard	<0.1	24.2 4.3
STD OREAS45C	Standard	<0.1	26.8 4.2
STD OREAS45C	Standard	<0.1	21.3 4.4
STD OREAS45C	Standard	<0.1	23.9 4.3
STD OREAS45C	Standard	<0.1	25.3 4.5
STD OXH82	Standard		
STD OXH82	Standard		
STD OXH82	Standard		



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 07, 2011

Page: 3 of 3 Part 1

QUALITY CONTROL REPORT

VAN11005906.1

		WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
		Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
		kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
		0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
BLK	Blank			<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
Prep Wash																					
G1	Prep Blank	<0.01	<0.005	0.3	1.8	19.5	52	<0.1	3.5	4.6	711	2.25	<1	2.9	<0.1	8.8	695	<0.1	0.1	0.2	47
G1	Prep Blank	<0.01	<0.005	0.3	1.6	20.3	48	<0.1	3.1	4.4	710	2.26	<1	2.8	<0.1	9.1	684	<0.1	<0.1	0.2	47



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 07, 2011

Page: 3 of 3 Part 2

QUALITY CONTROL REPORT

VAN11005906.1

		1EX Ca %	1EX P %	1EX La ppm	1EX Cr ppm	1EX Mg %	1EX Ba ppm	1EX Ti %	1EX Al %	1EX Na %	1EX K %	1EX W ppm	1EX Zr ppm	1EX Ce ppm	1EX Sn ppm	1EX Y ppm	1EX Nb ppm	1EX Ta ppm	1EX Be ppm	1EX Sc ppm	1EX Li ppm	
		0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	0.1
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	0.010	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<1	<1	<0.1	
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<1	<1	<0.1	
BLK	Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1	<1	<1	<0.1	
Prep Wash																						
G1	Prep Blank	2.21	0.080	25.4	4	0.60	1129	0.273	6.78	2.738	2.11	0.2	10.8	56	1.4	15.7	24.2	1.5	3	4	34.6	
G1	Prep Blank	2.35	0.084	26.6	4	0.63	1027	0.276	7.17	2.772	2.97	<0.1	11.2	59	1.6	16.5	25.2	1.5	3	5	34.5	



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: Taseko

Report Date: December 07, 2011

Page: 3 of 3 Part 3

QUALITY CONTROL REPORT

VAN11005906.1

		1EX S %	1EX Rb ppm	1EX Hf ppm
		0.1	0.1	0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
BLK	Blank	<0.1	<0.1	<0.1
Prep Wash				
G1	Prep Blank	<0.1	71.0	0.6
G1	Prep Blank	<0.1	102.1	0.7



Acme Analytical Laboratories (Vancouver) Ltd.
1020 Cordova St. East Vancouver BC V6A 4A3 Canada

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Submitted By: Mathius Westphal
Receiving Lab: Canada-Vancouver
Received: November 23, 2011
Report Date: December 12, 2011
Page: 1 of 2

CERTIFICATE OF ANALYSIS

VAN11006481.1

CLIENT JOB INFORMATION

Project: GRANITE CREEK
Shipment ID:
P.O. Number
Number of Samples: 5

SAMPLE PREPARATION AND ANALYTICAL PROCEDURES

Method Code	Number of Samples	Code Description	Test Wgt (g)	Report Status	Lab
R200-250	5	Crush, split and pulverize 250 g rock to 200 mesh			VAN
G601	5	Fire Assay fusion Au by ICP-ES	30	Completed	VAN
1EX	5	4 Acid digestion ICP-MS analysis	0.25	Completed	VAN

SAMPLE DISPOSAL

DISP-PLP Dispose of Pulp After 90 days
DISP-RJT Dispose of Reject After 90 days

ADDITIONAL COMMENTS

Acme does not accept responsibility for samples left at the laboratory after 90 days without prior written instructions for sample storage or return.

Invoice To: Ranex Exploration
Box 4200
Smithers BC V0J 2N0
Canada

CC: Tim Johnson



This report supersedes all previous preliminary and final reports with this file number dated prior to the date on this certificate. Signature indicates final approval; preliminary reports are unsigned and should be used for reference only. All results are considered the confidential property of the client. Acme assumes the liabilities for actual cost of analysis only. Results apply to samples as submitted. ** asterisk indicates that an analytical result could not be provided due to unusually high levels of interference from other elements.



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: GRANITE CREEK
 Report Date: December 12, 2011

Page: 2 of 2 Part 1

CERTIFICATE OF ANALYSIS

VAN11006481.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	0.1	
318515	Rock	1.08	0.117	1.1	42.4	492.7	105	3.5	5.7	0.6	283	1.29	58	1.3	<0.1	12.2	10	0.4	2.1	0.2	6
318517	Rock	1.19	0.052	26.8	74.7	708.7	1143	10.9	2.8	1.3	318	0.52	25	11.6	<0.1	13.9	66	3.2	4.2	0.4	5
318516	Rock	0.90	1.222	1.9	239.6	2798	3188	14.1	3.2	1.8	415	2.42	5884	1.1	1.2	7.2	9	28.4	21.0	4.5	7
318514	Rock	0.62	1.153	31.6	657.4	4357	696	8.4	16.5	8.9	841	3.29	122	5.0	0.4	2.8	143	6.1	245.4	6.8	28
318513	Rock	0.86	<0.005	9.6	17.1	18.0	108	0.1	9.6	1.9	274	0.56	28	0.9	<0.1	9.6	35	0.3	1.2	<0.1	30



Acme Analytical Laboratories (Vancouver) Ltd.
 1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: GRANITE CREEK
 Report Date: December 12, 2011

Page: 2 of 2 Part 2

CERTIFICATE OF ANALYSIS

VAN11006481.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	1	
318515	Rock	0.04	0.008	11.3	6	0.33	442	0.065	6.49	0.080	3.82	1.2	51.4	25	1.2	7.2	8.4	0.7	2	2	13.4
318517	Rock	0.06	0.007	6.8	<1	0.08	525	0.057	5.83	2.533	3.81	4.8	41.9	18	0.8	4.9	8.5	0.6	<1	2	12.6
318516	Rock	0.03	0.004	8.7	6	0.20	96	0.035	3.84	0.038	2.17	1.5	28.7	19	1.6	4.4	4.8	0.4	2	1	25.1
318514	Rock	10.49	0.005	21.3	8	2.24	2530	0.034	1.64	0.037	0.67	2.2	2.5	46	4.1	17.5	0.4	<0.1	<1	3	29.0
318513	Rock	1.44	0.031	15.5	12	0.68	633	0.044	6.09	0.117	2.69	2.2	9.6	29	1.8	6.6	0.4	<0.1	<1	6	18.5



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: GRANITE CREEK
Report Date: December 12, 2011

Page: 2 of 2 Part 3

CERTIFICATE OF ANALYSIS

VAN11006481.1

	Method	1EX	1EX	1EX
	Analyte	S	Rb	Hf
	Unit	%	ppm	ppm
	MDL	0.1	0.1	0.1
318515	Rock	<0.1	189.2	2.5
318517	Rock	0.1	140.8	2.2
318516	Rock	0.8	116.6	1.5
318514	Rock	0.1	31.4	<0.1
318513	Rock	<0.1	83.7	0.4



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: GRANITE CREEK
 Report Date: December 12, 2011

Page: 1 of 1 Part 1

QUALITY CONTROL REPORT

VAN11006481.1

Method	WGHT	G6	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX
Analyte	Wgt	Au	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V
Unit	kg	gm/t	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MDL	0.01	0.005	0.1	0.1	0.1	1	0.1	0.1	0.2	1	0.01	1	0.1	0.1	0.1	1	0.1	0.1	0.1	1
Pulp Duplicates																				
REP G1	QC		0.2	3.7	20.0	53	<0.1	6.7	4.8	803	2.26	1	2.6	<0.1	7.8	725	<0.1	<0.1	0.1	52
Reference Materials																				
STD OREAS24P	Standard		1.7	54.2	3.4	123	<0.1	146.5	46.9	1150	8.10	3	0.7	<0.1	3.2	405	0.2	<0.1	<0.1	181
STD OREAS45C	Standard		2.4	623.3	27.8	87	0.3	344.4	106.0	1146	19.51	11	2.4	<0.1	11.1	41	0.3	1.0	0.3	277
STD OXH82	Standard	1.301																		
STD OXK79	Standard	3.646																		
STD OXH82 Expected		1.278																		
STD OXK79 Expected		3.532																		
STD OREAS24P Expected			1.5	52	2.9	119	0.06	141	44	1100	7.53	1.2	0.75		2.85	403	0.15	0.09		158
STD OREAS45C Expected			2.26	620	24	83	0.28	333	104	1160	18.33	10.1	2.4	0.045	10.2	36.4	0.15	0.79	0.21	270
BLK	Blank	<0.005																		
BLK	Blank	<0.005																		
BLK	Blank		<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.2	<1	<0.01	<1	<0.1	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<1
Prep Wash																				
G1	Prep Blank	<0.01	<0.005																	
G1	Prep Blank		0.2	3.5	19.3	50	<0.1	6.2	4.7	776	2.17	1	2.6	<0.1	6.9	712	<0.1	<0.1	<0.1	51



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada
 Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
 Box 4200
 Smithers BC V0J 2N0 Canada

Project: GRANITE CREEK
 Report Date: December 12, 2011

Page: 1 of 1 Part 2

QUALITY CONTROL REPORT

VAN11006481.1

Method	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	1EX	
Analyte	Ca	P	La	Cr	Mg	Ba	Ti	Al	Na	K	W	Zr	Ce	Sn	Y	Nb	Ta	Be	Sc	Li	
Unit	%	%	ppm	ppm	%	ppm	%	%	%	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
MDL	0.01	0.001	0.1	1	0.01	1	0.001	0.01	0.001	0.01	0.1	0.1	1	0.1	0.1	0.1	0.1	1	1	0.1	
Pulp Duplicates																					
REP G1 QC	2.37	0.079	23.6	8	0.63	984	0.251	7.42	2.940	3.08	0.1	13.5	51	1.5	15.4	26.0	1.4	3	5	34.3	
Reference Materials																					
STD OREAS24P Standard	5.91	0.140	20.8	213	4.42	299	1.124	8.18	2.649	0.67	0.4	145.0	41	1.8	25.3	22.3	1.2	1	21	9.0	
STD OREAS45C Standard	0.47	0.055	27.9	954	0.25	289	1.180	7.37	0.110	0.34	1.2	172.8	54	2.9	14.0	24.1	1.5	1	59	16.1	
STD OXH82 Standard																					
STD OXK79 Standard																					
STD OXH82 Expected																					
STD OXK79 Expected																					
STD OREAS24P Expected	5.83	0.136	17.4	196	4.13	285	1.1	7.66	2.34	0.7	0.5	141	37.6	1.6	21.3	21	1.04		20	8.7	
STD OREAS45C Expected	0.482	0.051	26.2	962	0.25	270	1.1313	7.59	0.097	0.36	1.06	169.7	54	2.9	12.9	23.05	1.43		59.03	15.69	
BLK Blank																					
BLK Blank																					
BLK Blank	<0.01	<0.001	<0.1	<1	<0.01	<1	<0.001	<0.01	<0.001	<0.01	<0.1	<0.1	<1	<0.1	<0.1	<0.1	<0.1	<1	<1	<0.1	
Prep Wash																					
G1 Prep Blank																					
G1 Prep Blank	2.37	0.084	19.5	9	0.60	902	0.240	7.50	2.874	3.01	<0.1	11.7	44	1.3	15.0	25.7	1.4	3	5	32.8	



Acme Analytical Laboratories (Vancouver) Ltd.

1020 Cordova St. East Vancouver BC V6A 4A3 Canada

Phone (604) 253-3158 Fax (604) 253-1716

www.acmelab.com

Client: **Ranex Exploration**
Box 4200
Smithers BC V0J 2N0 Canada

Project: GRANITE CREEK

Report Date: December 12, 2011

Page: 1 of 1 Part 3

QUALITY CONTROL REPORT

VAN11006481.1

Method	1EX	1EX	1EX
Analyte	S	Rb	Hf
Unit	%	ppm	ppm
MDL	0.1	0.1	0.1
Pulp Duplicates			
REP G1	QC	<0.1	111.8 0.7
Reference Materials			
STD OREAS24P	Standard	<0.1	23.7 3.9
STD OREAS45C	Standard	<0.1	25.4 4.6
STD OXH82	Standard		
STD OXK79	Standard		
STD OXH82 Expected			
STD OXK79 Expected			
STD OREAS24P Expected		22.4	3.6
STD OREAS45C Expected	0.021	24	4.27
BLK	Blank		
BLK	Blank		
BLK	Blank	<0.1	<0.1 <0.1
Prep Wash			
G1	Prep Blank		
G1	Prep Blank	<0.1	103.8 0.6

APPENDIX III

Drill
Logs

GC11-74	Depth [m]	
	0 to 11.37	Overburden
rock type	11.37 to 52.1	Biotite-granodiorite fsp xtals <5mm, bt pods <8mm, +/-hbl disseminated cpy pods w/ bt <5mm, pyrite <1mm, cpy>>py non magnetic
	52.2 to 52.95	Mafic dike w/ dark gray green matrix some fsp xtals <1mm px xtals <0.05mm magnetic
	52.95 to 62.66	Biotite-granodiorite
	62.66 to 64.17	Mafic dike w/ dark gray green matrix, see above
	64.17 to 68.65	Biotite-granodiorite
	68.65 to 70.3	Mafic dike w/ dark gray green matrix, see above
	70.3 to 72	Biotite-granodiorite magnetic - pyrrhotite
	72 to 81.9	Biotite-granodiorite w/ intercalated pinkish granodiorite w/ hbl +/-py-pyrrhotite transition is not sharp the latter is barren, some qtz-py veins <1mm at 45 tca
	81.9 to 82.75	Mafic dike w/ dark gray green matrix, see above
	82.75 to 106.15	Biotite-granodiorite w/ intercalated pinkish granodiorite
	106.15 to 107.3	dike w/ dark gray matrix and fsp xtals <3mm
	107.3 to 115.2	granodiorite w/ bt+hbl, pyrrhotite and py, no cpy
	115.2 to 116	dark gray dike in brecciated granodiorite
	116 to 116.35	granodiorite w/ bt, pyrrhotite and py, no cpy
	116.35 to 117	dark gray dike, fg matrix
	117 to 117.4	granodiorite w/ bt, pyrrhotite and py, no cpy
	117.4 to 119.4	Mafic dike w/ dark gray green matrix, px <0.05mm
	119.4 to 122.2	gray-green dike w/ fg matrix, lots of fsp laths <3mm
	122.2 to 136.6	granodiorite w/ bt, pyrrhotite and py, no cpy
	136.6 to 131.12	gray-green dike w/ fg matrix, lots of fsp laths <3mm
	131.12 to 145.4	granodiorite w/ bt, pyrrhotite and py, few cpy
	145.4 to 204	granodiorite w/ bt and hbl, pyrrhotite and some py in bt pods bt < 5mm, hbl <8mm, isomrph fsp <6mm
	EOH	

52.2 to 52.95	dike, magnetic, no mineralization visible
52.95 to 72	disseminated py <1mm disseminated cpy <5mm patches w/bt, cpy>>py
72 to 86	disseminated cpy <5mm patches w/bt and py, cpy>>py, increased values at 81.8 and 84.8m qtz-bt-py-cpy veins <1mm at 30 to 45 tca in barren granodiorite at 74.3, 76.5m
86 to 91.2	no visible mineralization
91.2 to 106.15	some cpy in bt pods at 91.2, 91.5, 96.3, 102.7, 103.3m cpy<1cm w/ bt rim and vuggy qtz at 97m (photo)
106.15 to 107.3	no visible mineralization
107.3 to 115.2	cpy in bt pod at 113.8m
115.2 to 137.8	no visible mineralization
137.8 to 145.4	cpy in bt pod at 137.8, 143.7m py-Mo at 143.4m
145.4 to 159	no visible mineralization
159 to 160	disseminated py <1mm, cpy<1mm in vein w/bt at 45 tca at 159.7m
160 to 204	no visible mineralization
EOH	

GC11-75	Depth [m]	
	0 to 8	Overburden
rock type	8 to 14.1	Granodiorite
	14.1 to 55	fine to medium grained, fsp <1mm, bt <2mm, barren Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <8mm, hbl laths <5mm disseminated cpy pods w/ bt <5mm, pyrite <1mm, cpy>>py non magnetic
	55 to 70	Biotite-granodiorite, medium to fine grained fsp xtals <5mm, bt pods <4mm, hbl laths <8mm disseminated py+/-cpy pods w/ bt, pyrite <2mm, cpy<py non magnetic
	70 to 81	Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <8mm, hbl laths <5mm disseminated py/cpy pods w/ bt <5mm, cpy=py non magnetic
	81 to 90.2	Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <8mm, hbl laths <5mm disseminated cpy pods w/ bt <5mm, cpy>>py non magnetic
	90.2 to 101	Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <5mm, hbl laths <8mm disseminated cpy pods w/ bt <1mm, cpy>>py non magnetic decrease of cpy grade and grain size increase of hbl/bt ratio
	101 to 115	Biotite-Hornblende-granodiorite, medium grained fsp xtals <5mm, bt pods <5mm, hbl laths <8mm disseminated cpy pods w/ bt <1mm, cpy>py magnetic spots, magnetite in hbl pods slight increase of py, decrease of cpy/py ratio
	115 to 155.5	Hornblende-Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <5mm, hbl laths <8mm some magnetic spots, magnetite in hbl pods some cpy in bt, no py
	155.5 to 177	Hornblende-Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <5mm, hbl laths <8mm no py, no cpy magnetic, magnetite in hbl pods
	EOH	

GC11-75	Depth [m]	
Mineralization	8 to 11.9	no visible mineralization
	11.9 to 12	dry py-cpy vein <0.05 mm at 45 tca
	12 to 14.1	no visible mineralization
	14.1 to 55	disseminated py <1mm disseminated cpy <5mm patches w/bt, cpy>>py cpy-bt vein <3mm at 45 tca at 29.7m (photos at 12, 13, 14.1, 14.3, 29.7m) cpy-hbl-qtz vein <3mm at 30 tca at 40m, vuggy qtz cpy-hbl-qtz vein <1mm at 30 tca at 40m cpy-hbl-qtz vein <1mm at 45 tca at 40.5m dry cpy vein<0.05mm at 30 tca at 44m Mo flake <2mm at 45.1m (photos)
	55 to 70	disseminated py+/-cpy pods w/ bt, pyrite <2mm, cpy<py cpy-hbl-qtz vein <3mm at 10 tca w/ vuggy qtz from 62 to 62.7m (photos)
	70 to 81	disseminated py/cpy pods w/ bt <5mm, cpy=py cpy pod <1cm w/ py rim and cpy <3mm w/ py rim at 70.05m (photo)
	81 to 90.2	disseminated cpy pods w/ bt <5mm, cpy>>py cpy-hbl-qtz vein <0.05mm at 15 tca at 81.2m (photo)
	90.2 to 101	disseminated cpy pods w/ bt <1mm, cpy>>py decrease of cpy grade and grain size
	101 to 115	disseminated cpy pods w/ bt <1mm, cpy>py slight increase of py, decrease of cpy/py ratio
	115 to 126.5	no visible mineralization, no py some cpy 'remnants' in bt pods at 126.6, 143.5, 143.9, 152.6, 154.8,
	126.5 to 155.1	155.05m cpy w/ malachite sprinkles in bt at 144.3, 145.4m
	155.1 to 177	no visible mineralization, no py
	EOH	

GC11-76	Depth [m]	
	0 to 4.54	Overburden
rock type	4.54 to 108	Hornblende-Biotite-Granodiorite
		zoned fsp xtals <1cm, bt pods <3mm, hbl <6mm, qtz interstitial magnetic, magnetite
	EOH	

GC11-76	Depth [m]	
Mineralization	4.54 to 33.7	no visible mineralization
	33.7 to 34.7	cc-cpy veining <1.5cm at 30 to subparallel tca (photos)
	34.7 to 35.9	no visible mineralization
	35.9 to 36	cpy <2mm in bt pod
	36 to 49.6	no visible mineralization
	49.6 to 49.7	cpy flakes on dry vein surface w/ cc
	49.7 to 69.95	no visible mineralization
	69.95 to 98.5	py in bt pods at 69.95, 74.2, 77.3, 79.5, 83.8 to 84.2, 92.4, 92.7 to 93, 93.5, 98.5m
	98.5 to 108	no visible mineralization
	EOH	

GC11-77	Depth [m]	
	0 to 5.85	Overburden
rock type	5.85 to 117.8	Biotite-Granodiorite, medium grained fsp xtals <5mm, bt <3mm, interstitial qtz and fsp magnetic
	117.8 to 146.6	Transition to a hbl-bt granodiorite w/ no sharp boundary, but a recognizable change in mineralogy and amount of mafics including the appearance of hbl xtals <1cm Hornblende-Biotite-Granodiorite fsp xtals <5mm, hbl<1cm, bt <3mm, interstitial qtz and fsp magnetic
	146.6 to 178	Biotite-Granodiorite, medium grained fsp xtals <5mm, bt <3mm, interstitial qtz and fsp magnetic
	178 to 204.8	Hornblende-Biotite-Granodiorite fsp xtals <5mm, hbl<1cm, bt <3mm, interstitial qtz and fsp magnetic
	204.8 to 206	pink fg aplite w/ bt
	206 to 338.6	Hornblende-Biotite-Granodiorite fsp xtals <5mm, hbl<1cm, bt <3mm, interstitial qtz and fsp magnetic
	338.6 to 338.65	pink fg aplite w/ bt at 80 tca
	338.65 to 399	Hornblende-Biotite-Granodiorite fsp xtals <5mm, hbl<1cm, bt <3mm, interstitial qtz and fsp magnetic
	EOH	
GC11-77	Depth [m]	
Mineralization	5.85 to 399	no visible mineralization py <1mm at 13.05, 13.7m qtz-py-hbl <1mm at 90 tca at 154.7m py pods <1cm at 299.3m in qtz vein <1cm at 90 tca w/pinking alt <10cm py vein <0.5mm, irregular shape, wurm like over 2cm at 326.9m
	EOH	

31.2 to 50	Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <5mm, some hbl lats <3mm medium to low magnetic
50 to 84	Biotite-granodiorite, fine grained fsp xtals <4mm, bt pods <3mm low magnetic
84 to 116.6	Biotite-granodiorite, fine grained medium to high magnetic
116.6 to 123.3	Biotite-granodiorite, fine grained low to medium magnetic
123.3 to 171.75	Hornblende-Biotite-granodiorite, medium grained fsp xtals <5mm, bt pods <5mm, hbl lats <1cm medium to high magnetic
171.75 to 177.3	fg dike, purple on top and bottom, greenish in the middle part fsp laths <1.5mm, flow pattern, irregular bleached spots contact at 30 tca, not magnetic
177.3 to 184.1	Hornblende-Biotite-granodiorite, medium grained
184.1 to 184.75	aplite dike w/ hem specs, at 70 tca, not magnetic
184.75 to 192	Hornblende-Biotite-granodiorite, medium grained EOH


GC11-78	Depth [m]	
Mineralization	0 to 33.7	no visible mineralization
	33.7 to 50	qtz-cpy <1mm subparallel tca from 33.7 to 35.5 qtz-cpy-Mo <0.5mm subparallel tca at 41.4m cpy pods<2mm in qtz vein at 45 tca at 41.4m qtz-cpy vein <1mm at 15 tca at 42.5m qtz-cpy vein <1mm at 15 tca w/ 1.5mm pods of cpy at 47.7m
	50 to 66.4	no visible mineralization
	66.4 to 84	qtz-cpy vein <3mm at 15 tca from 66.4 to 67.6m dry cpy vein subparallel tca at 72m cc-Mo vein <2mm at 30 tca at 75m qtz-py <1.5cm subparallel tca from 75 to 75.5m
	84 to 104.6	qtz-cpy <0.5mm subparallel tca from 78.7 to 80, 82.9 to 83.7m qtz-cpy <0.5 mm at 45 tca at 78.3, 82.4m cpy pod <2mm in subparallel qtz vein at 87.5m qtz-cpy vein <1mm from 89 to 90m qtz-cpy vein <3mm at 15 tca at 94.1m dry cpy vein <0.1mm subparallel tca from 94 to 95m
	104.6 to 117	no visible mineralization
	117 to 123	qtz-cpy veins <1mm at 45 and 15 tca
	123 to 159	no visible mineralization
	159 to 165	sph w/qtz at 159.3m possibly galena w/qtz at 160.4m
	165 to 192	cc-qtz-cpy veins<3mm at 162.2, 163.1, 163.3, 163.7, 164.3, 164.5m no visible mineralization
	EOH	

GC11-79	Depth [m]	
	0 to 15	Overburden, boulders
rock type	15 to 39.7	Biotite-granodiorite, fine to medium grained fsp xtals <5mm, bt pods <3mm, some hbl lats <2mm high magnetic
	39.7 to 79.5	Biotite-granodiorite, medium grained fsp xtals <6mm, bt pods <5mm, some hbl lats <3mm medium to low magnetic some high #s at 54m - 31, 66m - 39, 68m - 76, 69m - 27, 70m - 32 contact to above at 20 tca
	79.5 to 92	Biotite-granodiorite, fine to medium grained fsp xtals <4mm, bt pods <5mm, some hbl lats <2mm medium magnetic
	92 to 113	Biotite-granodiorite, fine to medium grained fsp xtals <4mm, bt pods <5mm, some hbl lats <2mm low magnetic
	113 to 121	Biotite-granodiorite, fine to medium grained fsp xtals <4mm, bt pods <5mm, some hbl lats <2mm high magnetic
	121 to 181.5	Biotite-granodiorite, medium grained fsp xtals <8mm, bt pods <6mm, some hbl lats <2mm low to medium magnetic w/ some high #s 129m - 31, 133m - 35, 139m - 47, 156m - 34,
	181.5 to 199	Biotite-granodiorite, medium grained fsp xtals <8mm, bt pods <6mm, some hbl lats <2mm medium to high magnetic
	199 to 210	BiotiteHornblende-granodiorite, medium grained fsp xtals <8mm, bt pods <6mm, some hbl lats <10mm high magnetic, increased mafic content magnetic high at 209m of 208 (!) (photos) concentric circles of magnetite (!)
	EOH	

GC11-79	Depth [m]	
Mineralization	0 to 17	no visible mineralization
	17 to 34	dry py veins <0.1mm at 45 tca at 25.9, 33.3, 33.35m
		dry cpy veins <0.1mm at 30 to 45 tca at 17.1, 20, 21.4, 21.8, 24.9, 26, 26.2, 27.2, 29.1, 32.3, 32.4m
		dry cpy vein <0.1mm parallel tca at 33.7m
	34 to 45	no visible mineralization
	45 to 88.5	cpy in bt pods <3mm at 45.3, 45.6, 55.8 to 56.3m
		qtz-cpy vein <1cm at 30 tca at 50.3, 58.95m
		dry cpy veins <0.1mm at 30 to 45 tca at 52.8, 57.4, 57.95, 58.85, 60.4
		qtz-py <3cm at 71.4m
		dry cpy veins <0.1mm at 30 to 45 tca at 76.5, 77.7, 80.7m
		qtz-cpy vein <2mm at 30 tca at 80.3m
		qtz-py-cpy vein <2cm at 45 tca at 88.4m
	88.5 to 99	no visible mineralization
	99 to 103	qtz-cpy <1mm at 30 tca at 99.05m
		strong silicification w/ diss Mo from 99.5 to 100.5m
		and diss cpy/py from 101 to 103m
	103 to 112.2	qtz-cpy <1mm at 30 to 45 tca at 110.7, 118m
		qtz-py <1mm at 30 to 45 tca at 110, 110.8, 112.1
	112.2 to 121.5	no visible mineralization
	121.5 to 140	qtz-hbl-cpy <1mm at 10 tca at 125.7m
		qtz-cc-hbl <2cm in alt zone at 126.4m
		qtz-hbl-cpy <3cm at 45 tca at 142.35m (photo)
		cpy in bt pods <3mm at 121.5, 125.8, 130.5 to 131, 136, m
	140 to 159.05	diss. cpy in bt pods
	159.05 to 181	no visible mineralization
	181 to 205.7	cpy in bt pod at 181.3, 193.05m
		qtz-cpy <0.5cm at 30 tca at 189.5, 193m
		qtz-cpy <1mm at 15 tca at 191.3m
		qtz-cpy <2mm at 45 tca at 203.5m
		py in bt pods at 195.6, 195.8, 197.2, 203.5, 203.6, 205.7m
	205.7 to 210	no visible mineralization
	EOH	

APPENDIX IV

Drill
Cross Sections




<p>Au</p> <p>80.0 mm/unit</p> <p>Au unit: g/T</p> <ul style="list-style-type: none"> 0 - 0.1 0.1 - 0.2 0.2 - 0.3 0.3 - 1 	<p>Cu</p> <p>0.005 mm/unit</p> <p>Cu unit: ppm</p> <ul style="list-style-type: none"> 0 - 64.7 64.7 - 148 148 - 442.3 442.3 - 6000
--	--

HoleID

EOH

mm given at scale of 1:500

Granitecreekgold Ltd.	
<p>Date: 2013-06-11</p> <p>Author: Qimin</p> <p>Office:</p> <p>Drawing:</p> <p>Scale: 1:500</p> <p>Projection: Non-Earth (meters)</p>	<p>Taseko Cross Section Map</p> <p>Drill Hole GC11-74</p> <p>Drill Hole GC11-75</p>



Hole ID

Mo

0.08 mm/unit


Mo unit: ppm

- 0 - 1.4
- 1.4 - 3.2
- 3.2 - 8.9
- 8.9 - 3000

EOH

mm given at scale of 1:500

Granicreekgold Ltd.	
Taseko Cross Section Map Drill Hole GC11-74 Drill Hole GC11-75	
Date: 2013-06-11	
Author: Qimin	
Office:	
Drawing:	
Scale: 1:500	Projection: Non-Earth (meters)





- | | |
|---|---|
| <p>Au
80.0 mm/unit</p> <p>Au unit: g/T</p> <ul style="list-style-type: none"> 0 - 0.1 0.1 - 0.2 0.2 - 0.3 0.3 - 1 | <p>Cu
0.005 mm/unit</p> <p>Cu unit: ppm</p> <ul style="list-style-type: none"> 0 - 64.7 64.7 - 148 148 - 442.3 442.3 - 6000 |
|---|---|

HoleID
|
EOH

mm given at scale of 1:500

Granitecreekgold Ltd.	
Date: 2013-06-11	Taseko Cross Section Map
Author: Qimin	Drill Hole GC11-76
Office:	Drill Hole GC11-77
Drawing:	
Scale: 1:500	Projection: Non-Earth (meters)






Au	Cu
80.0 mm/unit	0.005 mm/unit
Au unit: g/T	Cu unit: ppm
■ 0 - 0.1	■ 0 - 64.7
■ 0.1 - 0.2	■ 64.7 - 148
■ 0.2 - 0.3	■ 148 - 442.3
■ 0.3 - 1	■ 442.3 - 6000

HoleID
EOH

mm given at scale of 1:500

Granitecreekgold Ltd.	
Taseko Cross Section Map	
Drill Hole GC11-78	
Drill Hole GC11-79	
Date: 2013-06-11	
Author: Qimin	
Office:	
Drawing:	
Scale: 1:500	Projection: Non-Earth (meters)



Granitecreekgold Ltd.	
Taseko Cross Section Map Drill Hole GC11-78 Drill Hole GC11-79	
Date: 2013-06-11	
Author: Qimin	
Office:	
Drawing:	
Scale: 1:500	Projection: Non-Earth (meters)