



BC Geological Survey
Assessment Report
38607



Ministry of Energy, Mines & Petroleum Resources
Mining & Minerals Division
BC Geological Survey

Assessment Report
Title Page and Summary

TYPE OF REPORT [type of survey(s)]:

TOTAL COST: \$2,467

AUTHOR(S): D. Cremonese, P.Eng.

SIGNATURE(S):

NOTICE OF WORK PERMIT NUMBER(S)/DATE(S):

YEAR OF WORK: 2019

STATEMENT OF WORK - CASH PAYMENTS EVENT NUMBER(S)/DATE(S): 5751230

PROPERTY NAME: Harry

CLAIM NAME(S) (on which the work was done): 508823

COMMODITIES SOUGHT: Au, Ag

MINERAL INVENTORY MINFILE NUMBER(S), IF KNOWN:

MINING DIVISION: Skeena

NTS/BCGS: 104B020

LATITUDE: 57 ° 37 ' " LONGITUDE: 130 ° 34 ' " (at centre of work)

OWNER(S):

1) Teuton Resources Corp. 2)

MAILING ADDRESS:

2130 Crescent Road

Victoria, BC V8S 2H3

OPERATOR(S) [who paid for the work]:

1) As above 2)

MAILING ADDRESS:

PROPERTY GEOLOGY KEYWORDS (lithology, age, stratigraphy, structure, alteration, mineralization, size and attitude):

Stewart Complex, Triassic-Jurassic, Mylonites, Betty Creek Formation, Mudstones, Greywackes, Mount Dilworth Formation,

Unuk River Formation, andesite volcanics

REFERENCES TO PREVIOUS ASSESSMENT WORK AND ASSESSMENT REPORT NUMBERS:

28014, 28689, 30770, 31328, 32083

| TYPE OF WORK IN THIS REPORT | EXTENT OF WORK (IN METRIC UNITS) | ON WHICH CLAIMS | PROJECT COSTS APPORTIONED (Incl. support) |
|--|----------------------------------|--------------------|---|
| GEOLOGICAL (scale, area) | | | |
| Ground, mapping | | | |
| Photo interpretation | | | |
| GEOPHYSICAL (line-kilometres) | | | |
| Ground | | | |
| Magnetic | | | |
| Electromagnetic | | | |
| Induced Polarization | | | |
| Radiometric | | | |
| Seismic | | | |
| Other | | | |
| Airborne | | | |
| GEOCHEMICAL (number of samples analysed for...) | | | |
| Soil | | | |
| Silt | | | |
| Rock 7 Gold 30 Element ICP | | 508823 | \$2,467 |
| Other | | | |
| DRILLING (total metres; number of holes, size) | | | |
| Core | | | |
| Non-core | | | |
| RELATED TECHNICAL | | | |
| Sampling/assaying | | | |
| Petrographic | | | |
| Mineralographic | | | |
| Metallurgic | | | |
| PROSPECTING (scale, area) | | | |
| PREPARATORY / PHYSICAL | | | |
| Line/grid (kilometres) | | | |
| Topographic/Photogrammetric (scale, area) | | | |
| Legal surveys (scale, area) | | | |
| Road, local access (kilometres)/trail | | | |
| Trench (metres) | | | |
| Underground dev. (metres) | | | |
| Other | | | |
| | | TOTAL COST: | \$2,467 |

ASSESSMENT REPORT
ON
GEOCHEMICAL WORK
ON THE FOLLOWING CLAIMS

Tenure # 508823

Harry Property

STATEMENTS OF WORK # 5751230

Located

30 KM NORTH-NORTHWEST OF
STEWART, BRITISH COLUMBIA
SKEENA MINING DIVISION

56 degrees 10 minutes latitude
130 degrees 03 minutes longitude

MAPSHEETS 104B020

PROJECT PERIOD: July 31 to September 20, 2019

ON BEHALF OF
TEUTON RESOURCES CORP.
VANCOUVER, B.C.

REPORT BY

D. Cremonese, P. Eng.
2130 Crescent Road.
Victoria, BC V8S 2H3.

Date: Nov. 18, 2019

TABLE OF CONTENTS

| | Page |
|--|-------------|
| 1. INTRODUCTION | |
| A. Property, Location, Access and Physiography | 1 |
| B. Status of Property | 1 |
| C. History | 1 |
| D. References | 3 |
| E. Summary of Work Done | 4 |
| 2. TECHNICAL DATA AND INTERPRETATION | 4 |
| A. Geology & Mineralization | 4 |
| B. Rock Geochemistry | 5 |
| a. Introduction | 5 |
| b. Treatment of Data | 5 |
| c. Sample Descriptions | 6 |
| C. Discussion | 7 |
| D. Field Procedure and Laboratory Technique | 7 |
| E. Conclusions | 8 |
| APPENDICES | |
| 1 Work Cost Statement | |
| 2 Certificate of Qualification | |
| 3 GPS Sample Locations | |
| 4 Assay Certificates | |
| ILLUSTRATIONS | |
| Fig. 1 Location Map | Report Body |
| Fig. 2 Claims Map | Report Body |
| Fig. 3 Regional Geology Map | Report Body |
| Fig. 4 Prospective Corridor | Report Body |
| Fig. 5 Detailed Sampling Locations—Au Geochemistry | Report Body |
| Fig. 6 Detailed Sampling Locations—As Geochemistry | Report Body |

1. INTRODUCTION

A. Property, Location, Access and Physiography

The property is located about 30 km northwest of Stewart, British Columbia. Access is by truck up the old Granduc Mining Road which commences on the American side of the border at Hyder, Alaska (about 2km from Stewart), and then proceeds north before entering Canada again just before the Premier minesite. Most of the interesting portions of the claims lie between the Granduc road and the Salmon Glacier (to the west). In places the precursor Granduc road, which lies sub-parallel to the newer road but at lower elevation near the ice, provides an alternative method of traversing the claims area. Because this road is now washed out in several places, a helicopter is necessary to access some of the steeper portions of the property.

Topography in the area of interest between the road and the Salmon Glacier is generally very rugged, with several places too steep to access without ropes. Elevations vary from 800 to 1,100m. Vegetation in the area is generally sparse, with much of it featuring barren rock or glacial debris, however in some places scrub hemlock and balsam occur in patches, interspersed with shrubs, mountain grasses and heather.

Climate is severe during the winter months with abundant snowfall. Depending upon local weather conditions, ground comes open for fieldwork generally from early June onward.

B. Status of Property

The property is comprised of two claims as summarized below:

| Tenure # | Present Anniversary Date |
|----------|--------------------------|
| 508822 | Nov. 5, 2020 |
| 508823 | Nov. 5, 2020 |

Claim locations are shown on Fig. 2. The claims are owned by Teuton Resources Corp. of Vancouver.

C. History

After the 1919 discovery and subsequent exploitation of the famous Premier mine, located a few km south of the Harry property, the upper portions of the Salmon Glacier region were intensively prospected. At that time, much less rock exposure was available for sampling, because glaciers and permanent icefields covered far greater areas than they do today. This work disclosed a fair number of new showings in the upper Salmon Glacier area, mostly gold or silver bearing veins, some of which were high-graded on a small scale (the Outland Silver Bar prospect being an example). A

little further north, in the Summit Lake area, gold-pyrrhotite veins at the Scottie Gold property saw limited production in the 1980's.

As for the property area itself, in the northern sections along Troy ridge, well-known Stewart prospector Harry Swan (whom the author had the pleasure of meeting many times during the 1980's) maintained a property for many years. This property featured a rustic cabin, built by Mr. Swan, with majestic views of the surrounding mountains.

About 12 years ago the Silver Butte area about three km south-southeast of the Harry claims became prominent due to the discovery by Pinnacle Mines and Mountain Boy Resources of gold-silver bearing shears in a zone 300m wide that has been traced for 1.6 km. Outstanding drill intersections were obtained including Hole 36 which assayed 11.35 g/t gold over 17.8m and Hole #52 grading a remarkable 34.05 g/t gold over 15.25m. This property has been explored intermittently during the past years and was eventually acquired by Ascot Resources to add to its gold holdings in the Premier and Dilworth areas.

The impetus for staking the Harry property arose from the memory of a trip the author made in the early 1980's to a spot near the center of the property, accompanied by Mr. Nick Benkovich (a well-known Stewart prospector who went by the handle "Bonus Nick"). Mr. Benkovich had a small fraction (the "Harry Fraction") surrounded by claims owned by third parties. The author sampled a shear zone on this fraction over a 10m width, located on a steep slope that required careful climbing to access from the old Granduc road. From memory it was in silicified volcanics and mineralized with pyrite and minor galena. The original assay certificate for this sample has been misplaced, but the author remembers it being close to 0.10 oz/ton gold over the 10m sampled interval. Exact location of the sample site, however, has not subsequently been identified.

In 2004, Teuton carried out a small rock geochem survey over the subject claims with generally positive results. This was followed up in 2006 and 2008 with a further rock geochem survey and some geological mapping. The 2008 work established a line of anomalous gold and arsenic values near the eastern border of the property. Results of this work are on file with the government in the assessment report database.

Geochemical programs were run along the eastern edge of the Salmon Glacier in both 2008 and 2009 disclosing a large number of anomalous to highly anomalous gold and arsenic values. In 2010, four holes totalling 487.07 meters were drilled testing a silicified, sercite-altered, pyritic gossan close to the eastern boundary of Tenure 508823. Best intersection was 9.15m of 0.72g/t gold in a hole which had to be discontinued when it encountered underground workings. A talus fine, surface sampling program was also undertaken which defined a long section of anomalous gold values with peaks up to 965ppm gold.

D. References

- ALLDRICK, D.J.(1984): Geological Setting of the Precious Metals Deposits in the Stewart Area, Paper 84-1, Geological Fieldwork 1983", B.C.M.E.M.P.R.
- ALLDRICK, D.J.(1985): "Stratigraphy and Petrology of the Stewart Mining Camp (104B/1E)", p. 316, Paper 85-1, Geological Fieldwork 1984, B.C.M.E.M.P.R.
- ASCOT RESOURCES WEBSITE; <https://ascotgold.com/>
- EMPR ASSESMENT REPORT INDEX; Report #15752, 1986 Diamond Drill Program, Silver Butte Property.
- EMPR MAPPLACE; http://webmap.em.gov.bc.ca/mapplace/minpot/new_xmap.cfm
- EMPR MINFILE MASTER REPORT: 104B30 Outland Silver Bar; 104B34 Scottie Gold
- CREMONESE, D. AND MASTALERZ, K (2005): Assessment Report on Geochemical Work on Tenure #s 508822 and 508823, on file with BCEMPR, Report #28,014.
- CREMONESE, D. AND MASTALERZ, K (2006): Assessment Report on Geological and Geochemical Work on Tenure #s 508822 and 508823, on file with BCEMPR, Report #28,689.
- CREMONESE, D. (2009): Assessment Report on Geochemical Work on the Harry Property; on file with BCEMPR, Report #30770.
- CREMONESE, D. (2010): Assessment Report on Geochemical Work on the Harry Property; on file with BCEMPR, Report #31328.
- CREMONESE, D. (2011): Assessment Report on Geochemical and Diamond Drilling, Harry Property; on file with BCEMPR, Report #32083.
- GROVE, E.W. (1971): Bulletin 58, Geology and Mineral Deposits of the Stewart Area. B.C.M.E.M.P.R.
- GROVE, E.W. (1982): Unuk River, Salmon River, Anyox Map Areas. Ministry of Energy, Mines and Petroleum Resources, B.C.
- GROVE, E.W. (1987): Geology and Mineral Deposits of the Unuk River-Salmon River-Anyox Area, Bulletin 63, BCMEMPR

E. Summary of Work Done.

The 2019 work on the Harry property was part of a larger, summer program involving exploration of several Teuton properties located in the Stewart region. This field work spanned the period from July 31 to September 20, 2019.

The author made a half day visit to the property by helicopter on August 12, 2019. A short geochemical traverse was undertaken in an attempt to identify the area of the Harry showing which the author had visited in the early 1980's with then owner Nick Benkovich. Seven rock samples were taken along contour.

Samples were prepared and analyzed for gold content/ICP at the MSALabs facility in Langley, BC.

2. TECHNICAL DATA AND INTERPRETATION

A. Geology and Mineralization

The property lies along the western edge of a broad, NNW trending belt of Triassic and Jurassic volcanic and sedimentary rocks termed by Grove (1971) as the "Stewart Complex". This belt is bounded to the west by the Coast Crystalline Belt (mainly granodiorites) and to the east by a thick series of sedimentary rocks known as the Bowser Assemblage (Middle Jurassic to Upper Jurassic). The geology of the property and surrounding area is shown in this report in Fig. 3.

Locally, the Harry property is underlain by a succession of Lower to Upper Jurassic sedimentary and volcanogenic rocks of the Hazelton Group. The strata strike generally from NNW to SSE and dip at variable angles westward. The property area is located entirely on the western limb of a relatively narrow (ca. 5-7 km) but complex, NNW-SSE trending synclinal feature (Mt. Dilworth Syncline; Grove 1971) which parallels the prominent McTagg Anticlinorium located ca. 10 km westward and which locally exposes a broad belt of an older, folded succession of the Stuhini Group (Triassic). The western limb of the synclinal feature forms a zone of intense tectonic deformation with numerous faults of varying geometry and orientation. This zone of, probably a regional thrust character, is overprinted locally by numerous effects caused by cataclastic deformation and mylonitization. The area is host to several important mineral occurrences starting from the Premier mine (south), through Scottie Gold, East Gold and the Sulphurets area, up to the Treaty Creek showings. Most of the faults are parallel or sub-parallel to the main structural trend in the area, however, there are some steep faults which cross cut the main structural trend (Grove 1971).

The predominant part of the Harry property is underlain by coarse-grained and poorly sorted sedimentary rocks of mixed composition with fragments predominantly of volcanic provenance interfingering with greenish volcanic/volcaniclastic rocks of andesitic composition of the Unuk River Formation (J1-HU; Fig. 3). Finer-grained end members--siltstones, tuffaceous sediments--are less common. A high proportion of the rocks of this unit are represented by cataclasites and mylonites derived from the pre-existing volcanics and sediments, which underwent strong

tectonic deformation. Eastward, these strata grade(?) into variably colored sandstones, conglomerates and breccias also of volcanic provenance of the Betty Creek Formation (J2/3-HB). This succession is relatively thin and overprinted locally by strong tectonic deformation. Its upper contact with a younger succession appears to have a character of a NNW-SSE trending fault or thrust. This succession is composed predominantly of dark gray mudstones to greywackes with minor conglomerates, chert and limestones and is here assigned to the Mount Dilworth Formation (J2/3-HD). A narrow belt of these rocks is exposed in the very northeastern corner of the property along the southeastern shoreline of Summit Lake (Fig. 3). These fine-grained sedimentary rocks interfinger with felsic volcanics and volcanic breccias further southeastward in the Long Lake area. The lithostratigraphic position of the youngest strata exposed at the NE tip of the property (turbiditic sediments J2/3-Hs) has not been yet defined precisely, but they apparently correspond to Salmon River Formation. E. Grove (1971) has mapped several thin, subvertical Tertiary dykes along the eastern slope of the Salmon Glacier valley. The dykes cross cut older stratigraphic units and strike roughly W-E on the Harry Property.

The Harry property lies within what has been termed a “prospective corridor” (cf. Ascot Resources website: References) for finding gold deposits of the type presently established between the Premier, Silver Coin and Dilworth properties of Ascot Resources.. This corridor is shown in Fig. 4.

B. Rock Geochemistry

a. Introduction

Seven rock geochemical samples (samples Harry 1 to 7) were taken in 2019 along a steep, sericitized and pyritized gossanous area near the eastern boundary of Tenure 508823. The samples lay along a 100m stretch with positions located by a handheld GPS unit. The southern end of the sample traverse lies close to a small adit which had not previously been discerned on the property.

b. Treatment of Data

Locations for the rock geochemical samples and their corresponding gold values (in ppb) are presented in this report on Fig. 5; arsenic values (in ppm) on Fig. 6.

As in other small-scale surveys, a statistical treatment according to standard methods was not deemed practical. In lieu of such treatment, the author has simply chosen anomalous levels by reference to several rock geochemical programs conducted over other properties in the Stewart region over the past ten years. On this basis, anomalous levels are indicated below:

| <u>Element</u> | <u>Anomalous Above*</u> |
|----------------|-------------------------|
| Gold | 100 ppb |
| Arsenic | 140 ppm |

*Anomalous ranges will vary greatly according to rock type. For this reason, defining anomalous levels for any particular property based on regional averages is somewhat arbitrary

c. Sample Descriptions

Sample descriptions follow. Where any values for gold or arsenic are anomalous, the complete set of values has been included below the description with the anomalous values highlighted in bold. Values for gold can be seen in Fig. 5 and values for arsenic in Fig. 6.

| | |
|---------|--|
| Harry-1 | Sub-crop. Grab. Highly silicified, limonite alteration, ash tuff, moderate pyrite, less than 1% galena.. |
| | Au - 777 ppb As - 471 ppm |
| Harry-2 | Grab in place. Andesitic lapilli tuff, limonite staining, pyrite about 5%, trace galena. |
| | Au - 1008 ppb As - 292 ppm |
| Harry-3 | Sub-crop. Grab. Heavy pyrite, silicified. Limonite alteration. Same rock type. |
| | Au - 307 ppb As - 402 ppm |
| Harry-4 | Sub-crop. Grab. Same description as 3, above. |
| | Au - 261 ppb As - 558 ppm |
| Harry-5 | Grab in place. Andesite tuff. Weaker limonite alteration, pyrite about 3% |
| | Au - 114 ppb As - 227 ppm |
| Harry-6 | Grab in place. Limonite alteration. Pyrite about 2%. Silicified andesite,. |

Au - 955 ppb
As - 281 ppm

Harry-7 Grab in place. Andesite tuff. Pyrite about 3%. Limonite alteration, weak.

Au - 163 ppb
As - 214 ppm

C. Discussion

Samples were taken along contour of a steep gossanous slope looking west above the Salmon Glacier. All of the samples taken during the program were anomalous in both gold and arsenic with peak values of 1008ppb gold and 558ppm arsenic.

D. Field Procedure and Laboratory Analysis

Analysis of rock specimens collected during the 2009 program was carried out at the MSALabs facility in Langley BC (an ISO 9001:2015 certified and ISO 17025:2017 accredited laboratory)

Rock samples are logged into the tracking system and dried prior to sample preparation. The dried samples are crushed to 70% passing 2mm and split to create homogeneous subsamples. The subsamples are then pulverized to 85% passing 75micron. Preparation blanks are inserted with every workorder that requires crushing and/or pulverizing. Barren material is crushed, pulverized and analyzed along with the samples. Preparation duplicates are split after the crushing stage and are denoted by 'PD' following the sample name. Once split, they are pulverized and analyzed along with the samples following the regular procedure.

Prepared samples are weighed and digested under heat using a mixture of hydrochloric and nitric acids (termed "aqua regia"). Upon completion of digestion, samples are made up to volume with deionized water and analyzed by ICP-ES (Inductively Coupled Plasma) once the solutions have settled.

Gold assays: The prepared samples are weighed, mixed with flux, and fused to produce a lead button. The lead button is subsequently cupelled to remove the lead to yield a doré bead containing only the precious metals. The doré beads are digested using a combination of hydrochloric and nitric acids and the final solutions are analyzed by AAS (atomic absorption spectroscopy) or ICP-ES. Any samples reporting gold concentrations greater than 10ppm are re-analyzed by fire assay fusion with gravimetric finish

E. Conclusions


The 2019 rock geochemical sampling program over part of the Harry property tentatively identified a gold anomalous area which could be the site of the original "Harry" showing first viewed by the author in the early 1980s. All samples were gold anomalous ranging between 114 and 1008 ppb gold. Values in arsenic were also uniformly anomalous.

The author recommends that a grid be put in and sampled uphill and along contour of samples Harry 1 and 2 to define the extent of the anomalous zone. Success of this program could lead to a decision to drill.

Respectfully submitted,



D. Cremonese, P.Eng.
November 18, 2019



HARRY PROPERTY

ALASKA

PREMIER MINE

37A

56°N

Hyder
Stewart



GENERAL LOCATION MAP

HARRY PROPERTY

ALASKA

Fort St. John

Stewart

Terrace

Kitimat

Prince Rupert

Bella Coola

Quesnel

Williams Lake

Kamloops

Kelowna

Nelson

Cransbrook

Victoria

Vancouver

U.S.A.

LEGEND

— Road

● Town / City



0 300 km


TEUTON RESOURCES CORP. (TWO:TSXV)

HARRY PROPERTY
2019 ASSESSMENT REPORT

NTS Nos. 104B.020 SKEENA MINING DIVISION

LOCATION MAP





GEOLOGY LEGEND

Middle to Upper Jurassic
 muJHs Hazelton Group: Sediments
 muJHM Hazelton Group: Mount Dilworth Fm: Calc-alkaline Volcanics

Lower Jurassic
 IJHB Hazelton Group: Betty Creek Formation: Volcaniclastic rocks
 IJHU Hazelton Group: Unuk River Formation: Andesitic Volcanics

Early Jurassic
 EJTCS Texas Creek Plutonic Suite: Granodioritic intrusive

— Fault

LEGEND

— Gravel Road
 — Rough Road
 — Glacier
 — Creek

TEUTON RESOURCES CORP. (TUO:TSXV)

**HARRY PROPERTY
 2019 ASSESSMENT REPORT**

NTS Nos. 104B.020 SKEENA MINING DIVISION

GEOLOGY MAP

Source: Modified BCGS Map

Date: Sept. 2019

Figure: 3

PROSPECTIVE
CORRIDOR

HARRY
PROPERTY



Martha Ellen

Big Missouri/Province

Unicorn

ALASKA

BRITISH
COLUMBIA

Indian

Leslie Flat

Sebakwe

Power/Hope

Northern Lights

Premier

Ascot Resources

Prospect

Resource

Advanced Prospect




Harry-Prospective-corridor-v2
NAD 83
Sept 16 2019
Last updated: Nov 19 2019
Created by: NB

0 1 2 4 Kilometers
1:100,000

HWY 37A

434500

Sample Au (ppb)





| Sample ID | Au Concentration (ppb) |
|-----------|------------------------|
| Harry 01 | 777 |
| Harry 02 | 1008 |
| Harry 03 | 307 |
| Harry 04 | 261 |
| Harry 05 | 114 |
| Harry 06 | 955 |
| Harry 07 | 163 |

6225000

6225000

HARRY CLAIM AREA
OUTSIDE OF CLAIM



434500

TEUTON RESOURCES CORP. (TUO:TSXV)

Figure 5


TEU-2019-Harry-fig5
NAD 83
Oct 30 2019
Last updated: Nov 01 2019
Created by: NB

- Access Road
- Mineral Claim Boundary

HARRY PROPERTY
DETAILED SAMPLE LOCATIONS

434500

Sample As (ppm)





| Sample ID | As Concentration (ppm) |
|-----------|------------------------|
| Harry 01 | 583 |
| Harry 02 | 292 |
| Harry 03 | 402 |
| Harry 04 | 588 |
| Harry 05 | 227 |
| Harry 06 | 281 |
| Harry 07 | 214 |

6225000

6225000

HARRY CLAIM AREA
OUTSIDE OF CLAIM



434500

TEUTON RESOURCES CORP. (TUO:TSXV)

Figure 6

TEU-2019-Harry-fig6
NAD 83
Nov 01 2019
Last updated: Nov 01 2019
Created by: NB

- Access Road
- Mineral Claim Boundary

**HARRY PROPERTY
DETAILED SAMPLE LOCATIONS**

APPENDIX 2 – CERTIFICATE OF QUALIFICATION

I, Dino M. Cremonese, do hereby certify that:

1. I am a mineral property consultant with an office at 2130 Crescent Road, Victoria, BC.
2. I am a graduate of the University of British Columbia (B.A.Sc. in metallurgical engineering, 1972, and L.L.B., 1979).
3. I am a Professional Engineer registered with the Association of Professional Engineers of the Province of British Columbia as a resident member, #13876.
4. I have practised my profession since 1979.
5. This report is based upon work carried out on the Harry property, Skeena Mining Division in August of 2019.
6. I am a principal of Teuton Resources Corp., owner of the Harry property: this report was prepared solely for satisfying assessment work requirements in accordance with government regulations.

Dated at Vancouver, B.C. this 18th day of November, 2019.



D. Cremonese, P.Eng.

APPENDIX 3**GPS READINGS FOR SAMPLES**

| Sample | Latitude | Longitude |
|---------|----------|-------------|
| Harry 1 | 56.16471 | -130.054165 |
| Harry 2 | 56.16455 | -130.054263 |
| Harry 3 | 56.16438 | -130.054308 |
| Harry 4 | 56.16428 | -130.054347 |
| Harry 5 | 56.16412 | -130.054408 |
| Harry 6 | 56.16387 | -130.054486 |
| Harry 7 | 56.16378 | -130.054402 |

APPENDIX 4

ASSAY CERTIFICATES



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Number of Samples: 139
 Report Version: Final

| |
|------------------|
| COMMENTS: |
|------------------|

Test results reported relate to the tested samples only on an "as received" basis. Unless otherwise stated above, sufficient sample was received for the methods requested and all samples were received in acceptable condition. Analytical results in unsigned reports marked "provisional" are subject to change, pending final QC review and approval. The customer has not provided any information that can affect the validity of the test results. Please refer to MSALABS' Schedule of Services and Fees for our complete Terms and Conditions. Preliminary results are applicable when a portion of samples in a job is 100% completed and reported or 1 of a number of methods on the same job have been completed 100%. Results cannot change, but additional results or results for additional methods can be added.

| SAMPLE PREPARATION | |
|--------------------|--|
| METHOD CODE | DESCRIPTION |
| PRP-910 | Dry, Crush to 70% passing 2mm, Split 250g, Pulverize to 85% passing 75µm |
| | |

| ANALYTICAL METHODS | |
|--------------------|---|
| METHOD CODE | DESCRIPTION |
| FAS-111 | Au, Fire Assay, 30g fusion, AAS, Trace Level |
| FAS-415 | Au, Fire Assay, 30g fusion, Gravimetric |
| ICP-130 | Multi-Element, 0.5g, 3:1 Aqua Regia, ICP-AES, Trace Level |

Signature:

Yvette Hsi, BSc.
 Laboratory Manager
 MSALABS



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units LOR | FAS-111 Au ppm 0.005 | FAS-415 Au ppm 0.05 | ICP-130 Ag ppm 0.2 | ICP-130 Al % 0.01 | ICP-130 As ppm 2 | ICP-130 B ppm 10 | ICP-130 Ba ppm 10 | ICP-130 Be ppm 0.5 | ICP-130 Bi ppm 2 | ICP-130 Ca % 0.01 | ICP-130 Cd ppm 0.5 |
|---------------|-------------|---------------------|--------------------------|----------------------|---------------------|--------------------|-------------------|------------------|------------------|-------------------|--------------------|------------------|-------------------|--------------------|
| Granite Blank | QC-P-BK | -- | | <0.005 | | <0.2 | 0.86 | <2 | <10 | 61 | <0.5 | 3 | 0.63 | <0.5 |
| Granite Blank | QC-P-BK | -- | | <0.005 | | <0.2 | 0.81 | <2 | <10 | 56 | <0.5 | <2 | 0.62 | <0.5 |
| H428801 | Core | 1.34 | | <0.005 | | 1.2 | 0.78 | 37 | <10 | 76 | <0.5 | <2 | 0.91 | 7.5 |
| H428802 | Core | 2.53 | | <0.005 | | 1.0 | 0.77 | 19 | <10 | 121 | <0.5 | <2 | 2.90 | 7.7 |
| H428803 | Core | 3.66 | | <0.005 | | 2.5 | 0.85 | 24 | <10 | 103 | <0.5 | <2 | 1.38 | 17.6 |
| H428804 | Core | 4.89 | | <0.005 | | 2.4 | 0.53 | 16 | <10 | 99 | <0.5 | <2 | 2.68 | 7.9 |
| H428805 | Core | 4.03 | | <0.005 | | 0.4 | 0.66 | 7 | <10 | 112 | <0.5 | <2 | 1.53 | 1.3 |
| H428806 | Core | 3.70 | | <0.005 | | 2.8 | 0.49 | 38 | <10 | 90 | <0.5 | <2 | 2.84 | 37.2 |
| H428807 | Core | 4.22 | | 0.008 | | 2.5 | 0.60 | 35 | <10 | 89 | <0.5 | <2 | 1.82 | 8.9 |
| H428808 | Core | 1.04 | | <0.005 | | 2.9 | 0.60 | 61 | <10 | 69 | <0.5 | <2 | 3.29 | 12.4 |
| H428809 | Core | 3.71 | | <0.005 | | 1.1 | 0.44 | 47 | <10 | 100 | <0.5 | <2 | 6.88 | 7.1 |
| H428810 | Core | 0.38 | | <0.005 | | <0.2 | 0.77 | <2 | <10 | 317 | <0.5 | 4 | 0.40 | <0.5 |
| H428811 | Core | 4.90 | | <0.005 | | 0.9 | 0.47 | 42 | <10 | 94 | <0.5 | <2 | 3.88 | 9.2 |
| H428812 | Core | 3.56 | | <0.005 | | 1.1 | 0.44 | 42 | <10 | 99 | <0.5 | <2 | 3.60 | 11.4 |
| H428813 | Core | 1.23 | | 0.008 | | 0.4 | 1.57 | 7 | <10 | 106 | <0.5 | <2 | 2.85 | <0.5 |
| H428814 | Core | 3.21 | | <0.005 | | 0.4 | 2.90 | 22 | <10 | 79 | 0.6 | <2 | 8.51 | 2.2 |
| H428815 | Core | 1.93 | | <0.005 | | 0.3 | 1.54 | <2 | <10 | 99 | 0.5 | <2 | 7.71 | <0.5 |
| H428816 | Core | 0.98 | | <0.005 | | 0.2 | 1.61 | 10 | <10 | 85 | <0.5 | <2 | 9.75 | 0.8 |
| H428817 | Core | 0.47 | | <0.005 | | 0.4 | 1.99 | <2 | <10 | 138 | 0.8 | <2 | 7.04 | <0.5 |
| H428818 | Core | 1.05 | | <0.005 | | <0.2 | 2.62 | 13 | <10 | 103 | 0.6 | <2 | 8.59 | <0.5 |
| H428819 | Core | 2.40 | | <0.005 | | <0.2 | 3.22 | 13 | <10 | 77 | 0.8 | <2 | 8.88 | 0.6 |
| H428820 | Pulp | 0.15 | | 1.656 | | 15.8 | 2.47 | 24 | 13 | <10 | <0.5 | <2 | 0.63 | 14.4 |
| H428821 | Core | 2.66 | | <0.005 | | <0.2 | 3.52 | 6 | 10 | 73 | 0.8 | <2 | 6.96 | <0.5 |
| H428822 | Core | 2.37 | | <0.005 | | <0.2 | 3.32 | 3 | <10 | 92 | 0.8 | <2 | 4.52 | <0.5 |
| H428823 | Core | 2.51 | | <0.005 | | <0.2 | 3.42 | 11 | 11 | 101 | 0.7 | <2 | 6.21 | <0.5 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units LOR | FAS-111 Au ppm 0.005 | FAS-415 Au ppm 0.05 | ICP-130 Ag ppm 0.2 | ICP-130 Al % 0.01 | ICP-130 As ppm 2 | ICP-130 B ppm 10 | ICP-130 Ba ppm 10 | ICP-130 Be ppm 0.5 | ICP-130 Bi ppm 2 | ICP-130 Ca % 0.01 | ICP-130 Cd ppm 0.5 |
|-----------|-------------|---------------------|--------------------------|----------------------|---------------------|--------------------|-------------------|------------------|------------------|-------------------|--------------------|------------------|-------------------|--------------------|
| H428824 | Core | 2.60 | | 0.007 | | 1.6 | 0.53 | 15 | <10 | 99 | <0.5 | 2 | 3.90 | 13.1 |
| H428825 | Core | 2.36 | | <0.005 | | 0.6 | 0.86 | 3 | <10 | 94 | <0.5 | <2 | 3.61 | <0.5 |
| H428826 | Core | 2.45 | | <0.005 | | 0.6 | 2.14 | 4 | <10 | 75 | <0.5 | <2 | 6.35 | <0.5 |
| H428827 | Core | 2.49 | | <0.005 | | 0.5 | 2.36 | 3 | <10 | 82 | <0.5 | <2 | 3.64 | <0.5 |
| H428828 | Core | 2.48 | | <0.005 | | 0.5 | 2.17 | 5 | <10 | 82 | <0.5 | <2 | 3.57 | <0.5 |
| H428829 | Core | 2.14 | | <0.005 | | 0.4 | 2.29 | 3 | <10 | 80 | <0.5 | <2 | 3.53 | <0.5 |
| H428830 | Core | 0.26 | | <0.005 | | <0.2 | 0.74 | <2 | <10 | 293 | <0.5 | <2 | 0.37 | <0.5 |
| H428831 | Core | 2.39 | | 0.006 | | 0.4 | 2.29 | 6 | <10 | 85 | <0.5 | <2 | 2.98 | <0.5 |
| H428832 | Core | 2.40 | | <0.005 | | 0.4 | 2.23 | 8 | 12 | 111 | <0.5 | <2 | 4.11 | <0.5 |
| H428832PD | QC-PD | -- | | <0.005 | | 0.4 | 2.28 | 5 | <10 | 112 | <0.5 | <2 | 4.04 | <0.5 |
| H428833 | Core | 2.22 | | <0.005 | | 0.4 | 2.65 | 6 | 13 | 91 | <0.5 | <2 | 3.46 | <0.5 |
| H428834 | Core | 2.47 | | 0.005 | | 0.4 | 2.30 | 5 | <10 | 87 | <0.5 | <2 | 4.09 | <0.5 |
| H428835 | Core | 2.54 | | 0.006 | | 0.3 | 2.46 | 4 | 13 | 96 | <0.5 | <2 | 4.37 | <0.5 |
| H428836 | Core | 2.28 | | <0.005 | | <0.2 | 3.25 | 8 | <10 | 61 | <0.5 | 2 | 2.64 | <0.5 |
| H428837 | Core | 2.42 | | <0.005 | | <0.2 | 3.28 | 3 | <10 | 55 | <0.5 | <2 | 3.71 | <0.5 |
| H428838 | Core | 2.33 | | <0.005 | | <0.2 | 2.94 | <2 | <10 | 52 | <0.5 | <2 | 3.73 | <0.5 |
| H428839 | Core | 2.44 | | <0.005 | | <0.2 | 2.87 | <2 | <10 | 66 | <0.5 | <2 | 2.70 | <0.5 |
| H428840 | Pulp | 0.15 | | 1.666 | | 15.8 | 2.78 | 19 | 15 | 20 | <0.5 | <2 | 0.61 | 14.5 |
| H428841 | Core | 2.41 | | 0.005 | | 0.2 | 2.86 | 3 | <10 | 78 | <0.5 | <2 | 3.77 | <0.5 |
| H428842 | Core | 2.31 | | <0.005 | | 0.2 | 2.79 | 2 | <10 | 45 | <0.5 | <2 | 3.47 | <0.5 |
| H428843 | Core | 2.39 | | <0.005 | | <0.2 | 2.85 | <2 | <10 | 37 | <0.5 | <2 | 3.14 | <0.5 |
| H428844 | Core | 2.52 | | <0.005 | | 0.2 | 2.72 | <2 | <10 | 61 | <0.5 | <2 | 3.71 | <0.5 |
| H428845 | Core | 2.06 | | 0.009 | | 0.4 | 2.54 | 3 | <10 | 68 | <0.5 | <2 | 4.14 | <0.5 |
| H428846 | Core | 2.11 | | 0.005 | | 0.3 | 2.66 | <2 | <10 | 68 | <0.5 | <2 | 3.85 | <0.5 |
| H428847 | Core | 2.34 | | 0.008 | | 0.5 | 1.18 | 8 | <10 | 90 | 0.5 | <2 | 4.67 | 0.7 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units LOR | FAS-111 Au ppm 0.005 | FAS-415 Au ppm 0.05 | ICP-130 Ag ppm 0.2 | ICP-130 Al % 0.01 | ICP-130 As ppm 2 | ICP-130 B ppm 10 | ICP-130 Ba ppm 10 | ICP-130 Be ppm 0.5 | ICP-130 Bi ppm 2 | ICP-130 Ca % 0.01 | ICP-130 Cd ppm 0.5 |
|-----------|-------------|---------------------|--------------------------|----------------------|---------------------|--------------------|-------------------|------------------|------------------|-------------------|--------------------|------------------|-------------------|--------------------|
| H428848 | Core | 2.46 | | 0.005 | | 0.4 | 2.69 | <2 | <10 | 61 | <0.5 | <2 | 2.72 | <0.5 |
| H428849 | Core | 2.32 | | <0.005 | | 0.3 | 1.62 | 6 | <10 | 100 | 0.5 | <2 | 4.19 | 0.8 |
| H428850 | Core | 0.18 | | <0.005 | | <0.2 | 0.90 | <2 | <10 | 296 | <0.5 | <2 | 0.36 | <0.5 |
| H428701 | Core | 0.81 | | 0.008 | | 0.4 | 1.37 | 13 | <10 | 83 | 0.6 | <2 | 2.24 | <0.5 |
| H428702 | Core | 3.54 | | <0.005 | | <0.2 | 3.58 | 30 | <10 | 79 | 0.6 | 2 | 6.34 | <0.5 |
| H428703 | Core | 4.13 | | <0.005 | | 0.2 | 2.64 | 7 | <10 | 118 | 0.7 | 2 | 7.16 | <0.5 |
| H428704 | Core | 1.40 | | <0.005 | | 0.2 | 2.85 | <2 | <10 | 150 | 0.8 | <2 | 7.48 | <0.5 |
| H428705 | Core | 1.23 | | <0.005 | | <0.2 | 3.46 | <2 | <10 | 99 | 0.7 | <2 | 5.47 | <0.5 |
| H428706 | Core | 1.69 | | <0.005 | | <0.2 | 2.40 | <2 | 13 | 148 | 0.8 | <2 | 9.04 | 0.9 |
| H428707 | Core | 2.09 | | <0.005 | | <0.2 | 2.85 | 4 | 11 | 91 | 0.8 | <2 | 11.11 | 0.7 |
| H428708 | Core | 2.47 | | <0.005 | | <0.2 | 3.01 | <2 | <10 | 99 | 0.8 | <2 | 7.75 | <0.5 |
| H428709 | Core | 2.69 | | <0.005 | | <0.2 | 2.93 | <2 | <10 | 101 | 0.8 | <2 | 7.02 | <0.5 |
| H428710 | Core | 0.34 | | <0.005 | | <0.2 | 0.85 | <2 | 24 | 331 | <0.5 | <2 | 0.36 | <0.5 |
| H428711 | Core | 1.19 | | <0.005 | | 0.3 | 1.40 | 18 | <10 | 88 | 0.6 | <2 | 8.26 | 0.6 |
| H428712 | Core | 1.53 | | <0.005 | | <0.2 | 2.31 | 2 | <10 | 95 | <0.5 | <2 | 3.49 | <0.5 |
| H428713 | Core | 2.24 | | <0.005 | | <0.2 | 2.33 | <2 | 12 | 104 | <0.5 | <2 | 4.78 | <0.5 |
| H428714 | Core | 4.70 | | <0.005 | | <0.2 | 2.62 | 6 | <10 | 78 | <0.5 | <2 | 4.30 | <0.5 |
| H428715 | Core | 7.89 | | <0.005 | | 0.3 | 2.28 | 6 | <10 | 76 | <0.5 | <2 | 3.13 | <0.5 |
| H428715PD | QC-PD | -- | | 0.008 | | <0.2 | 2.29 | 9 | <10 | 87 | <0.5 | <2 | 3.08 | <0.5 |
| H428716 | Core | 2.36 | | <0.005 | | <0.2 | 2.81 | <2 | <10 | 120 | <0.5 | <2 | 2.12 | <0.5 |
| H428717 | Core | 2.51 | | <0.005 | | <0.2 | 1.88 | 3 | <10 | 120 | <0.5 | <2 | 2.94 | <0.5 |
| H428718 | Core | 2.74 | | 0.021 | | 0.4 | 0.17 | 7 | <10 | 154 | <0.5 | <2 | 4.38 | <0.5 |
| H428719 | Core | 2.16 | | 0.026 | | 0.7 | 0.37 | 13 | <10 | 206 | <0.5 | <2 | 5.23 | 0.6 |
| H428720 | Pulp | 0.15 | | 1.690 | | 15.8 | 2.51 | 19 | 26 | <10 | <0.5 | <2 | 0.64 | 14.7 |
| H428721 | Core | 2.87 | | 0.024 | | 0.8 | 0.22 | 5 | 13 | 79 | <0.5 | 2 | 8.89 | <0.5 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units LOR | FAS-111 Au ppm 0.005 | FAS-415 Au ppm 0.05 | ICP-130 Ag ppm 0.2 | ICP-130 Al % 0.01 | ICP-130 As ppm 2 | ICP-130 B ppm 10 | ICP-130 Ba ppm 10 | ICP-130 Be ppm 0.5 | ICP-130 Bi ppm 2 | ICP-130 Ca % 0.01 | ICP-130 Cd ppm 0.5 |
|-----------|-------------|---------------------|--------------------------|----------------------|---------------------|--------------------|-------------------|------------------|------------------|-------------------|--------------------|------------------|-------------------|--------------------|
| H428722 | Core | 1.61 | | 0.022 | | 0.4 | 0.64 | 18 | <10 | 170 | <0.5 | <2 | 4.79 | <0.5 |
| H428723 | Core | 2.07 | | <0.005 | | <0.2 | 1.39 | 17 | <10 | 213 | <0.5 | <2 | 3.43 | <0.5 |
| H428724 | Core | 2.58 | | <0.005 | | 0.3 | 1.93 | 16 | <10 | 147 | <0.5 | <2 | 4.27 | <0.5 |
| H428725 | Core | 2.44 | | 0.007 | | 0.2 | 1.55 | <2 | 14 | 291 | <0.5 | <2 | 4.50 | <0.5 |
| H428726 | Core | 2.30 | | <0.005 | | <0.2 | 1.23 | <2 | 12 | 375 | <0.5 | <2 | 4.58 | <0.5 |
| H428727 | Core | 2.41 | | <0.005 | | 0.3 | 1.29 | <2 | <10 | 213 | <0.5 | <2 | 4.99 | <0.5 |
| H428728 | Core | 2.51 | | 0.006 | | 0.3 | 1.05 | 7 | <10 | 259 | <0.5 | <2 | 7.27 | <0.5 |
| H428729 | Core | 2.90 | | 0.008 | | <0.2 | 0.97 | 6 | <10 | 822 | <0.5 | <2 | 6.04 | <0.5 |
| H428730 | Core | 0.36 | | <0.005 | | <0.2 | 0.97 | <2 | <10 | 383 | <0.5 | 3 | 0.43 | <0.5 |
| H428731 | Core | 0.49 | | 0.087 | | 1.2 | 0.96 | 344 | 16 | 65 | <0.5 | <2 | 8.34 | 1.4 |
| H428732 | Core | 1.70 | | <0.005 | | 0.3 | 1.16 | <2 | 12 | 222 | <0.5 | <2 | 5.44 | <0.5 |
| H428733 | Core | 2.43 | | <0.005 | | 0.3 | 0.98 | <2 | <10 | 228 | <0.5 | <2 | 5.29 | <0.5 |
| H428734 | Core | 2.89 | | 0.009 | | <0.2 | 1.04 | <2 | <10 | 254 | <0.5 | <2 | 5.91 | <0.5 |
| H428735 | Core | 2.65 | | 0.005 | | 0.3 | 1.66 | 5 | <10 | 172 | <0.5 | 2 | 5.61 | <0.5 |
| H428736 | Core | 2.58 | | <0.005 | | 0.3 | 2.26 | 14 | 12 | 137 | <0.5 | <2 | 6.37 | <0.5 |
| H428737 | Core | 2.47 | | 0.009 | | 0.4 | 2.04 | 22 | <10 | 158 | <0.5 | <2 | 5.40 | <0.5 |
| H428738 | Core | 1.79 | | <0.005 | | 0.3 | 0.67 | 26 | 14 | 189 | <0.5 | <2 | 6.89 | 0.7 |
| H428739 | Core | 3.04 | | <0.005 | | <0.2 | 1.17 | 3 | <10 | 142 | <0.5 | <2 | 3.58 | <0.5 |
| H428740 | Pulp | 0.15 | | 1.642 | | 15.6 | 2.49 | 18 | 14 | <10 | <0.5 | <2 | 0.64 | 13.8 |
| H428741 | Core | 2.26 | | <0.005 | | <0.2 | 1.06 | 6 | <10 | 148 | <0.5 | <2 | 4.87 | <0.5 |
| H428742 | Core | 3.24 | | <0.005 | | <0.2 | 1.11 | 5 | <10 | 121 | <0.5 | <2 | 3.78 | <0.5 |
| DNW 08 | Rock | 0.87 | | <0.005 | | 1.1 | 0.63 | 64 | 10 | 262 | <0.5 | <2 | <0.01 | <0.5 |
| DNW 09 | Rock | 0.93 | | <0.005 | | 0.2 | 0.94 | 115 | <10 | 244 | <0.5 | <2 | 0.05 | <0.5 |
| DNW 10 | Rock | 0.42 | | 0.071 | | 0.6 | 0.62 | 147 | 13 | 64 | <0.5 | <2 | <0.01 | <0.5 |
| DNW 11 | Rock | 0.58 | | <0.005 | | 0.8 | 0.75 | 10 | 11 | <10 | <0.5 | 4 | <0.01 | <0.5 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units LOR | FAS-111 Au ppm | FAS-415 Au ppm | ICP-130 Ag ppm | ICP-130 Al % | ICP-130 As ppm | ICP-130 B ppm | ICP-130 Ba ppm | ICP-130 Be ppm | ICP-130 Bi ppm | ICP-130 Ca % | ICP-130 Cd ppm |
|-----------|-------------|---------------------|--------------------------|----------------|----------------|----------------|--------------|----------------|---------------|----------------|----------------|----------------|--------------|----------------|
| DNW 12 | Rock | 1.35 | | <0.005 | | 0.4 | 0.71 | 9 | 16 | 10 | <0.5 | 3 | <0.01 | <0.5 |
| DNW 13 | Rock | 1.91 | | <0.005 | | 2.5 | 0.78 | 29 | 14 | <10 | <0.5 | 3 | 0.02 | 3.1 |
| DNW 14 | Rock | 1.18 | | 0.019 | | 2.2 | 0.58 | 39 | <10 | 87 | <0.5 | <2 | 0.25 | 2.1 |
| DNW 15 | Rock | 0.63 | | 0.007 | | 0.7 | 0.86 | 20 | <10 | 23 | <0.5 | <2 | 0.04 | <0.5 |
| DNW 16 | Rock | 0.44 | | <0.005 | | 0.6 | 0.65 | 24 | 16 | <10 | <0.5 | 2 | <0.01 | <0.5 |
| DNW 17 | Rock | 0.82 | | 0.036 | | 32.5 | 0.77 | 180 | 11 | 27 | <0.5 | <2 | <0.01 | 1.2 |
| DNW 18 | Rock | 0.24 | | 0.187 | | 84.3 | 0.13 | 477 | <10 | 18 | <0.5 | <2 | <0.01 | 5.4 |
| Harry 01 | Rock | 0.85 | | 0.777 | | 21.7 | 0.33 | 583 | <10 | 245 | <0.5 | <2 | <0.01 | 1.4 |
| Harry 02 | Rock | 0.81 | | 1.008 | | 3.9 | 0.57 | 292 | <10 | 303 | <0.5 | <2 | <0.01 | 0.6 |
| Harry 03 | Rock | 1.18 | | 0.307 | | 3.6 | 0.80 | 402 | <10 | 13 | <0.5 | <2 | 0.10 | 4.0 |
| Harry 04 | Rock | 2.42 | | 0.261 | | 3.3 | 0.71 | 588 | 10 | 12 | <0.5 | 3 | 0.20 | 4.8 |
| Harry 05 | Rock | 1.67 | | 0.114 | | 1.7 | 0.83 | 227 | <10 | 57 | <0.5 | <2 | 0.21 | 4.8 |
| Harry 06 | Rock | 0.59 | | 0.955 | | 3.5 | 1.26 | 281 | <10 | 146 | <0.5 | <2 | 0.25 | 1.0 |
| Harry 07 | Rock | 0.90 | | 0.163 | | 2.2 | 0.73 | 214 | <10 | 112 | <0.5 | <2 | <0.01 | <0.5 |
| M19-01 | Rock | 1.26 | | <0.005 | | <0.2 | 0.10 | 2 | <10 | 33 | <0.5 | <2 | 0.22 | <0.5 |
| 2729201 | Rock | 0.86 | | 0.008 | | 0.6 | 0.74 | 9 | <10 | 165 | <0.5 | <2 | 17.57 | 2.7 |
| 2729202 | Rock | 0.60 | | 0.013 | | 1.5 | 1.58 | 102 | <10 | 111 | 0.5 | <2 | 6.30 | 2.6 |
| 2729203 | Rock | 0.92 | | <0.005 | | 0.5 | 1.10 | 15 | <10 | 149 | 0.5 | <2 | 6.50 | 1.1 |
| 2729204 | Rock | 1.11 | | 0.005 | | 1.1 | 0.35 | 87 | <10 | 989 | <0.5 | <2 | 20.69 | 22.1 |
| 2729205 | Rock | 0.86 | | 0.800 | | 3.1 | 1.69 | 59 | <10 | 1154 | <0.5 | <2 | 0.39 | <0.5 |
| 2729206 | Rock | 0.91 | | 0.044 | | 10.9 | 0.73 | 40 | <10 | 11 | <0.5 | <2 | 2.57 | >2000 |
| 2729207 | Rock | 0.92 | | 7.749 | | 22.6 | 1.09 | 304 | <10 | 358 | <0.5 | 4 | 0.05 | 14.4 |
| 2729208 | Rock | 1.09 | | 4.175 | | 5.8 | 2.22 | 130 | <10 | 183 | <0.5 | 2 | 0.05 | 0.9 |
| 2729209 | Rock | 0.98 | | 0.061 | | 0.4 | 0.75 | 21 | <10 | 158 | <0.5 | <2 | 6.44 | 2.6 |
| 2729210 | Rock | 1.20 | | 0.700 | | 8.6 | 3.05 | 277 | <10 | 56 | <0.5 | <2 | 5.48 | 316.6 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units LOR | FAS-111 Au ppm | FAS-415 Au ppm | ICP-130 Ag ppm | ICP-130 Al % | ICP-130 As ppm | ICP-130 B ppm | ICP-130 Ba ppm | ICP-130 Be ppm | ICP-130 Bi ppm | ICP-130 Ca % | ICP-130 Cd ppm |
|-------------|-------------|---------------------|--------------------------|----------------|----------------|----------------|--------------|----------------|---------------|----------------|----------------|----------------|--------------|----------------|
| 2729211 | Rock | 1.01 | | 0.013 | | 0.2 | 0.39 | 9 | <10 | 246 | <0.5 | <2 | 9.17 | 4.3 |
| 2727251 | Rock | 1.05 | | 0.012 | | <0.2 | 0.23 | 3 | <10 | 556 | <0.5 | <2 | 16.68 | 1.9 |
| 2727252 | Rock | 0.80 | | 0.058 | | 1.8 | 0.86 | 327 | <10 | 171 | <0.5 | <2 | 18.11 | 16.4 |
| 2727253 | Rock | 0.75 | | 0.034 | | 8.2 | 0.37 | 11 | <10 | 29 | <0.5 | <2 | 19.55 | 878.1 |
| 2727254 | Rock | 0.96 | | 0.366 | | >100 | 0.98 | 3556 | <10 | 512 | <0.5 | <2 | 0.30 | 11.0 |
| 2727255 | Rock | 0.95 | | >10 | 11.20 | 24.1 | 1.83 | 225 | <10 | 317 | <0.5 | <2 | 0.07 | 4.0 |
| 2727256 | Rock | 1.56 | | >10 | 28.67 | 34.9 | 0.23 | 500 | 32 | 498 | <0.5 | 10 | <0.01 | 10.2 |
| 2727256PD | QC-PD | -- | | >10 | 28.87 | 37.8 | 0.24 | 546 | 29 | 443 | <0.5 | 6 | <0.01 | 9.8 |
| 2727257 | Rock | 1.39 | | 7.635 | | 18.9 | 1.24 | 238 | 19 | 2388 | <0.5 | <2 | 0.12 | 4.6 |
| 2727258 | Rock | 0.72 | | 6.089 | | 11.1 | 2.36 | 875 | 11 | 33 | <0.5 | 3 | 0.64 | 215.8 |
| 2727259 | Rock | 1.30 | | 0.083 | | 0.4 | 0.23 | 76 | <10 | 482 | <0.5 | <2 | 0.01 | 2.8 |
| 2727260 | Rock | 0.91 | | 0.088 | | 0.3 | 0.05 | 35 | <10 | 35 | <0.5 | <2 | <0.01 | <0.5 |
| 2727261 | Rock | 0.76 | | 0.008 | | <0.2 | 0.42 | 4 | <10 | 327 | <0.5 | <2 | 5.74 | <0.5 |
| 2727262 | Rock | 1.28 | | 0.008 | | <0.2 | 0.61 | 29 | <10 | 522 | <0.5 | <2 | 14.73 | <0.5 |
| 2727263 | Rock | 1.27 | | <0.005 | | <0.2 | 0.15 | <2 | <10 | 258 | <0.5 | <2 | 12.19 | <0.5 |
| 2727264 | Rock | 0.84 | | 0.036 | | 0.4 | 1.57 | 124 | 16 | 153 | <0.5 | <2 | 0.57 | <0.5 |
| 2727265 | Rock | 1.29 | | 0.029 | | 0.5 | 1.19 | 16 | 31 | 160 | <0.5 | <2 | 3.76 | <0.5 |
| 2727266 | Rock | 1.30 | | 0.088 | | 2.1 | 1.96 | 36 | 31 | 68 | <0.5 | <2 | 9.23 | <0.5 |
| 2727267 | Rock | 1.34 | | 0.068 | | 3.6 | 0.42 | 60 | 18 | 67 | <0.5 | <2 | 3.73 | <0.5 |
| DUP H428822 | | | | | | 0.2 | 3.35 | <2 | 15 | 90 | 0.8 | <2 | 4.62 | <0.5 |
| DUP H428843 | | | | | | <0.2 | 2.84 | 3 | <10 | 36 | <0.5 | <2 | 3.13 | <0.5 |
| DUP H428741 | | | | | | <0.2 | 1.03 | <2 | <10 | 144 | <0.5 | <2 | 4.77 | <0.5 |
| DUP H428806 | | | | <0.005 | | | | | | | | | | |
| DUP H428711 | | | | <0.005 | | | | | | | | | | |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | Sample Type | PWE-100 Rec. Wt. kg | Method Analyte Units | FAS-111 Au ppm | FAS-415 Au ppm | ICP-130 Ag ppm | ICP-130 Al % | ICP-130 As ppm | ICP-130 B ppm | ICP-130 Ba ppm | ICP-130 Be ppm | ICP-130 Bi ppm | ICP-130 Ca % | ICP-130 Cd ppm |
|---------------|-------------|---------------------|----------------------|----------------|----------------|----------------|--------------|----------------|---------------|----------------|----------------|----------------|--------------|----------------|
| DUP H428722 | | 0.01 | LOR | 0.005 | 0.05 | 0.2 | 0.01 | 2 | 10 | 10 | 0.5 | 2 | 0.01 | 0.5 |
| DUP 2727255 | | | | 0.022 | 10.90 | | | | | | | | | |
| STD BLANK | | | | | | <0.2 | <0.01 | <2 | <10 | <10 | <0.5 | <2 | <0.01 | <0.5 |
| STD BLANK | | | | | | <0.2 | <0.01 | <2 | <10 | <10 | <0.5 | <2 | <0.01 | <0.5 |
| STD BLANK | | | | | | <0.2 | <0.01 | <2 | <10 | <10 | <0.5 | <2 | <0.01 | <0.5 |
| STD BLANK | | | | <0.005 | | | | | | | | | | |
| STD BLANK | | | | <0.005 | | | | | | | | | | |
| STD BLANK | | | | <0.005 | | | | | | | | | | |
| STD BLANK | | | | | <0.05 | | | | | | | | | |
| STD OREAS 24b | | | | | | <0.2 | 3.20 | 9 | <10 | 149 | 1.6 | 4 | 0.46 | <0.5 |
| STD OREAS 601 | | | | | | 48.8 | 0.82 | 311 | <10 | 237 | 0.6 | 21 | 1.04 | 7.8 |
| STD OREAS 24b | | | | | | <0.2 | 3.09 | 7 | <10 | 143 | 1.5 | 4 | 0.45 | <0.5 |
| STD OxA131 | | | | 0.075 | | | | | | | | | | |
| STD OxD127 | | | | 0.445 | | | | | | | | | | |
| STD OxN155 | | | | 7.593 | | | | | | | | | | |
| STD OxD90 | | | | | 25.07 | | | | | | | | | |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|---------------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| Granite Blank | 4 | 83 | 6 | 1.75 | <10 | <1 | 0.09 | <10 | 0.47 | 456 | 4 | 0.10 | 4 | 390 |
| Granite Blank | 3 | 71 | 4 | 1.73 | <10 | <1 | 0.09 | <10 | 0.46 | 471 | 3 | 0.09 | 4 | 401 |
| H428801 | 7 | 43 | 44 | 3.19 | <10 | <1 | 0.19 | <10 | 0.46 | 278 | 7 | 0.04 | 21 | 598 |
| H428802 | 7 | 33 | 30 | 2.98 | <10 | <1 | 0.28 | <10 | 0.46 | 990 | 6 | 0.02 | 14 | 687 |
| H428803 | 6 | 41 | 43 | 2.59 | <10 | <1 | 0.25 | <10 | 0.36 | 313 | 11 | 0.02 | 22 | 590 |
| H428804 | 8 | 42 | 53 | 3.40 | <10 | <1 | 0.24 | <10 | 0.65 | 667 | 6 | 0.04 | 20 | 956 |
| H428805 | 3 | 40 | 18 | 1.80 | <10 | 1 | 0.30 | <10 | 0.50 | 357 | 3 | 0.02 | 6 | 439 |
| H428806 | 6 | 38 | 67 | 2.50 | <10 | <1 | 0.24 | <10 | 0.40 | 550 | 24 | 0.01 | 43 | 957 |
| H428807 | 9 | 54 | 62 | 3.63 | <10 | <1 | 0.30 | <10 | 0.44 | 416 | 10 | 0.01 | 28 | 1625 |
| H428808 | 9 | 48 | 56 | 4.54 | <10 | <1 | 0.33 | <10 | 0.48 | 439 | 15 | 0.02 | 37 | 3284 |
| H428809 | 6 | 28 | 51 | 3.43 | <10 | <1 | 0.28 | <10 | 0.58 | 811 | 32 | 0.03 | 57 | 765 |
| H428810 | 4 | 71 | 2 | 1.99 | <10 | <1 | 0.52 | <10 | 0.49 | 334 | 3 | 0.15 | 4 | 616 |
| H428811 | 7 | 22 | 53 | 3.31 | <10 | <1 | 0.31 | <10 | 0.53 | 598 | 20 | 0.03 | 57 | 909 |
| H428812 | 8 | 23 | 62 | 3.09 | <10 | <1 | 0.31 | <10 | 0.46 | 649 | 33 | 0.02 | 58 | 805 |
| H428813 | 11 | 22 | 43 | 3.04 | 10 | <1 | 0.28 | <10 | 1.19 | 829 | 1 | 0.04 | 26 | 954 |
| H428814 | 30 | 164 | 50 | 5.66 | 17 | <1 | 0.19 | <10 | 2.97 | 1165 | 17 | 0.01 | 183 | 3747 |
| H428815 | 17 | 32 | 64 | 4.45 | <10 | <1 | 0.30 | <10 | 2.02 | 885 | 3 | 0.02 | 33 | 1282 |
| H428816 | 37 | 73 | 44 | 6.53 | 14 | 1 | 0.26 | <10 | 3.08 | 1405 | 4 | 0.01 | 162 | 3153 |
| H428817 | 31 | 87 | 70 | 5.07 | 13 | <1 | 0.43 | <10 | 1.95 | 1079 | 4 | 0.02 | 152 | 3694 |
| H428818 | 26 | 93 | 43 | 5.52 | 17 | <1 | 0.27 | <10 | 3.83 | 1173 | <1 | 0.02 | 167 | 6151 |
| H428819 | 35 | 134 | 37 | 6.58 | 19 | <1 | 0.21 | 10 | 5.07 | 1135 | <1 | 0.01 | 225 | 4956 |
| H428820 | 77 | 96 | >10000 | 18.66 | 33 | <1 | 0.38 | <10 | 2.06 | 259 | 324 | 0.08 | 63 | 344 |
| H428821 | 41 | 142 | 46 | 7.62 | 21 | <1 | 0.20 | 11 | 4.70 | 1082 | <1 | 0.01 | 290 | 1786 |
| H428822 | 41 | 171 | 53 | 7.24 | 23 | <1 | 0.26 | 16 | 3.49 | 875 | <1 | 0.01 | 254 | 1303 |
| H428823 | 39 | 180 | 72 | 7.35 | 22 | <1 | 0.28 | 17 | 4.14 | 1050 | <1 | 0.01 | 285 | 2198 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|-----------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| | 1 | 1 | 1 | 0.01 | 10 | 1 | 0.01 | 10 | 0.01 | 5 | 1 | 0.01 | 1 | 10 |
| H428824 | 14 | 49 | 80 | 2.87 | <10 | <1 | 0.28 | <10 | 1.08 | 758 | 76 | 0.02 | 84 | 2776 |
| H428825 | 11 | 33 | 60 | 3.02 | <10 | <1 | 0.29 | <10 | 1.09 | 691 | 2 | 0.03 | 39 | 836 |
| H428826 | 13 | 33 | 74 | 4.47 | 12 | <1 | 0.25 | <10 | 1.51 | 744 | 1 | 0.03 | 27 | 1202 |
| H428827 | 14 | 33 | 94 | 4.71 | 13 | <1 | 0.27 | <10 | 1.49 | 630 | 2 | 0.03 | 28 | 1268 |
| H428828 | 15 | 32 | 107 | 4.54 | 12 | <1 | 0.25 | <10 | 1.37 | 607 | 2 | 0.03 | 31 | 1370 |
| H428829 | 13 | 32 | 95 | 4.55 | 13 | <1 | 0.26 | <10 | 1.45 | 660 | 2 | 0.03 | 30 | 1377 |
| H428830 | 4 | 55 | 2 | 1.93 | <10 | <1 | 0.50 | <10 | 0.48 | 319 | 2 | 0.14 | 4 | 577 |
| H428831 | 14 | 31 | 91 | 4.69 | 13 | 1 | 0.27 | <10 | 1.45 | 580 | 2 | 0.03 | 27 | 1388 |
| H428832 | 14 | 37 | 103 | 4.54 | 12 | <1 | 0.25 | <10 | 1.45 | 743 | 2 | 0.03 | 38 | 1394 |
| H428832PD | 14 | 40 | 103 | 4.54 | 11 | <1 | 0.28 | <10 | 1.46 | 736 | 2 | 0.03 | 38 | 1382 |
| H428833 | 15 | 41 | 96 | 4.65 | 11 | <1 | 0.27 | <10 | 1.66 | 655 | 2 | 0.04 | 38 | 1417 |
| H428834 | 14 | 30 | 85 | 4.27 | <10 | <1 | 0.28 | <10 | 1.40 | 747 | 2 | 0.03 | 30 | 1351 |
| H428835 | 14 | 28 | 89 | 4.52 | <10 | <1 | 0.27 | <10 | 1.55 | 877 | 4 | 0.04 | 22 | 1335 |
| H428836 | 15 | 20 | 50 | 5.53 | 15 | <1 | 0.15 | <10 | 2.44 | 989 | <1 | 0.06 | 7 | 1650 |
| H428837 | 16 | 19 | 58 | 5.68 | 15 | <1 | 0.12 | <10 | 2.52 | 1343 | <1 | 0.06 | 6 | 1448 |
| H428838 | 15 | 19 | 53 | 5.26 | 16 | <1 | 0.11 | <10 | 2.21 | 1306 | <1 | 0.07 | 5 | 1431 |
| H428839 | 12 | 20 | 46 | 5.08 | 13 | <1 | 0.14 | <10 | 2.34 | 1059 | <1 | 0.07 | 7 | 1424 |
| H428840 | 74 | 95 | >10000 | 18.17 | 28 | <1 | 0.41 | <10 | 2.23 | 254 | 297 | 0.09 | 57 | 331 |
| H428841 | 16 | 20 | 82 | 5.11 | 10 | <1 | 0.20 | <10 | 2.19 | 1253 | 1 | 0.04 | 13 | 1482 |
| H428842 | 13 | 15 | 43 | 4.84 | 12 | <1 | 0.13 | <10 | 1.85 | 1181 | <1 | 0.08 | 3 | 1328 |
| H428843 | 11 | 13 | 30 | 4.86 | 16 | <1 | 0.12 | <10 | 1.84 | 1001 | <1 | 0.07 | 3 | 1381 |
| H428844 | 15 | 19 | 63 | 5.15 | 13 | <1 | 0.24 | <10 | 1.64 | 776 | 1 | 0.04 | 13 | 1353 |
| H428845 | 14 | 25 | 99 | 4.44 | 11 | <1 | 0.29 | <10 | 1.40 | 748 | 1 | 0.03 | 20 | 1350 |
| H428846 | 15 | 28 | 99 | 4.75 | 11 | <1 | 0.31 | <10 | 1.39 | 637 | 1 | 0.03 | 23 | 1389 |
| H428847 | 14 | 20 | 76 | 3.44 | <10 | <1 | 0.38 | <10 | 1.86 | 1025 | 2 | 0.03 | 24 | 1228 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|-----------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| | 1 | 1 | 1 | 0.01 | 10 | 1 | 0.01 | 10 | 0.01 | 5 | 1 | 0.01 | 1 | 10 |
| H428848 | 14 | 32 | 74 | 5.38 | 12 | <1 | 0.27 | <10 | 1.77 | 602 | 2 | 0.03 | 35 | 1262 |
| H428849 | 15 | 23 | 73 | 4.48 | <10 | <1 | 0.32 | <10 | 2.00 | 1000 | 1 | 0.03 | 32 | 1177 |
| H428850 | 4 | 59 | 2 | 1.99 | <10 | <1 | 0.57 | <10 | 0.55 | 303 | 2 | 0.15 | 3 | 607 |
| H428701 | 24 | 21 | 98 | 3.01 | <10 | <1 | 0.35 | <10 | 1.26 | 521 | 2 | 0.02 | 45 | 1487 |
| H428702 | 45 | 174 | 57 | 7.70 | 19 | <1 | 0.23 | <10 | 4.83 | 1233 | <1 | 0.02 | 207 | 2851 |
| H428703 | 35 | 125 | 47 | 7.25 | 15 | <1 | 0.23 | <10 | 4.25 | 1148 | <1 | 0.02 | 171 | 2699 |
| H428704 | 29 | 61 | 40 | 7.13 | 15 | <1 | 0.27 | 14 | 3.70 | 1263 | <1 | 0.02 | 83 | 4383 |
| H428705 | 32 | 52 | 41 | 7.99 | 20 | <1 | 0.23 | 15 | 3.31 | 971 | <1 | 0.02 | 102 | 1614 |
| H428706 | 26 | 39 | 31 | 6.42 | 14 | <1 | 0.24 | 15 | 3.67 | 1512 | <1 | 0.02 | 81 | 2372 |
| H428707 | 26 | 54 | 35 | 6.62 | 17 | <1 | 0.18 | 10 | 2.81 | 1534 | <1 | 0.02 | 82 | 2280 |
| H428708 | 26 | 48 | 34 | 6.79 | 17 | <1 | 0.24 | 12 | 2.23 | 1462 | <1 | 0.02 | 95 | 1976 |
| H428709 | 25 | 82 | 32 | 7.66 | 18 | <1 | 0.23 | <10 | 3.27 | 1212 | <1 | 0.02 | 136 | 2395 |
| H428710 | 4 | 42 | 2 | 2.02 | <10 | <1 | 0.58 | <10 | 0.57 | 332 | 1 | 0.13 | 4 | 604 |
| H428711 | 23 | 73 | 35 | 5.56 | 11 | <1 | 0.28 | <10 | 4.32 | 1389 | <1 | 0.02 | 149 | 2390 |
| H428712 | 14 | 14 | 36 | 4.66 | <10 | 1 | 0.37 | <10 | 1.78 | 1011 | <1 | 0.03 | 16 | 1349 |
| H428713 | 12 | 13 | 41 | 4.32 | <10 | <1 | 0.47 | <10 | 1.43 | 1236 | <1 | 0.03 | 3 | 1355 |
| H428714 | 14 | 13 | 43 | 5.00 | 12 | <1 | 0.33 | <10 | 1.29 | 1049 | <1 | 0.05 | 4 | 1360 |
| H428715 | 14 | 19 | 36 | 4.70 | 10 | <1 | 0.24 | <10 | 1.35 | 1094 | <1 | 0.06 | 6 | 1473 |
| H428715PD | 13 | 18 | 37 | 4.62 | <10 | <1 | 0.27 | <10 | 1.33 | 1105 | <1 | 0.07 | 5 | 1456 |
| H428716 | 12 | 13 | 44 | 4.94 | 11 | <1 | 0.32 | <10 | 1.52 | 1151 | <1 | 0.06 | 4 | 1347 |
| H428717 | 11 | 12 | 49 | 3.90 | <10 | <1 | 0.31 | <10 | 1.14 | 1223 | <1 | 0.04 | 5 | 1375 |
| H428718 | 3 | 85 | 20 | 2.48 | <10 | <1 | 0.12 | <10 | 1.06 | 1270 | 3 | 0.02 | 8 | 368 |
| H428719 | 5 | 66 | 32 | 3.19 | <10 | <1 | 0.27 | <10 | 1.25 | 1397 | 2 | 0.02 | 10 | 969 |
| H428720 | 77 | 96 | >10000 | 18.80 | 34 | <1 | 0.38 | <10 | 2.07 | 259 | 249 | 0.09 | 62 | 340 |
| H428721 | 4 | 64 | 44 | 5.24 | <10 | <1 | 0.15 | <10 | 2.42 | 2641 | 2 | 0.02 | 10 | 471 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|-----------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| H428722 | 8 | 17 | 53 | 3.17 | <10 | <1 | 0.42 | <10 | 1.16 | 1234 | <1 | 0.03 | 8 | 1311 |
| H428723 | 11 | 12 | 68 | 3.52 | <10 | <1 | 0.31 | <10 | 1.89 | 1118 | <1 | 0.04 | 6 | 1469 |
| H428724 | 15 | 9 | 56 | 5.12 | 13 | <1 | 0.28 | <10 | 1.54 | 1298 | <1 | 0.05 | 3 | 1705 |
| H428725 | 11 | 15 | 58 | 4.06 | <10 | <1 | 0.51 | <10 | 1.12 | 1257 | <1 | 0.05 | 5 | 1438 |
| H428726 | 13 | 13 | 56 | 3.87 | <10 | <1 | 0.67 | <10 | 1.39 | 1197 | <1 | 0.04 | 2 | 1611 |
| H428727 | 11 | 12 | 66 | 4.22 | <10 | <1 | 0.56 | <10 | 0.90 | 1153 | <1 | 0.05 | 2 | 1727 |
| H428728 | 7 | 19 | 80 | 2.61 | <10 | <1 | 0.62 | <10 | 0.66 | 1510 | <1 | 0.05 | 3 | 1204 |
| H428729 | 8 | 18 | 66 | 2.82 | <10 | <1 | 0.64 | <10 | 0.61 | 1227 | <1 | 0.04 | 2 | 1256 |
| H428730 | 4 | 85 | 1 | 2.02 | <10 | <1 | 0.62 | <10 | 0.49 | 330 | <1 | 0.23 | 3 | 618 |
| H428731 | 32 | 27 | 298 | 8.01 | 12 | <1 | 0.51 | <10 | 0.55 | 1515 | 7 | 0.04 | 6 | 874 |
| H428732 | 9 | 17 | 66 | 4.43 | <10 | <1 | 0.65 | <10 | 0.69 | 1273 | <1 | 0.05 | 3 | 1449 |
| H428733 | 10 | 15 | 75 | 4.46 | <10 | <1 | 0.67 | <10 | 0.67 | 1308 | <1 | 0.05 | 1 | 1517 |
| H428734 | 11 | 16 | 61 | 4.17 | <10 | <1 | 0.71 | <10 | 0.58 | 1340 | <1 | 0.05 | 2 | 1583 |
| H428735 | 12 | 16 | 81 | 4.73 | 11 | <1 | 0.50 | <10 | 0.64 | 1171 | <1 | 0.06 | 4 | 1474 |
| H428736 | 13 | 15 | 57 | 5.09 | 12 | <1 | 0.43 | <10 | 0.70 | 1134 | <1 | 0.05 | 3 | 1470 |
| H428737 | 13 | 17 | 121 | 4.53 | 12 | <1 | 0.44 | <10 | 0.95 | 1178 | 2 | 0.04 | 10 | 1321 |
| H428738 | 7 | 50 | 47 | 2.34 | <10 | <1 | 0.40 | <10 | 1.67 | 2340 | 5 | 0.05 | 15 | 755 |
| H428739 | 5 | 61 | 18 | 2.34 | <10 | 1 | 0.34 | <10 | 0.78 | 1222 | <1 | 0.09 | 2 | 848 |
| H428740 | 76 | 97 | >10000 | 18.54 | 32 | <1 | 0.37 | <10 | 2.06 | 261 | 319 | 0.09 | 61 | 334 |
| H428741 | 5 | 51 | 6 | 2.45 | <10 | <1 | 0.38 | <10 | 1.18 | 1742 | <1 | 0.09 | 1 | 844 |
| H428742 | 4 | 49 | 25 | 1.92 | <10 | <1 | 0.34 | <10 | 0.74 | 1015 | 2 | 0.09 | 3 | 812 |
| DNW 08 | <1 | 39 | 35 | 6.42 | <10 | 2 | 0.63 | <10 | 0.01 | 5 | 24 | 0.02 | 1 | 2371 |
| DNW 09 | 3 | 139 | 4 | 2.19 | <10 | <1 | 0.48 | 10 | 0.10 | 313 | 2 | 0.02 | 4 | 198 |
| DNW 10 | <1 | 167 | 3 | 2.24 | <10 | <1 | 0.49 | <10 | 0.03 | 31 | 1 | 0.01 | 4 | 185 |
| DNW 11 | 26 | 28 | 41 | 15.20 | 20 | 4 | 0.41 | <10 | <0.01 | <5 | 14 | 0.03 | 11 | 136 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|-----------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| DNW 12 | 25 | 68 | 25 | 14.76 | 20 | 2 | 0.39 | <10 | <0.01 | 9 | 10 | 0.02 | 9 | 155 |
| DNW 13 | 66 | 81 | 28 | 11.05 | 15 | 5 | 0.45 | <10 | 0.02 | 13 | 4 | 0.02 | 25 | 178 |
| DNW 14 | 8 | 208 | 45 | 2.10 | <10 | <1 | 0.32 | <10 | 0.07 | 366 | 5 | 0.01 | 6 | 245 |
| DNW 15 | 19 | 78 | 8 | 3.46 | <10 | 1 | 0.50 | <10 | 0.02 | 20 | 3 | 0.03 | 9 | 489 |
| DNW 16 | 14 | 154 | 20 | 13.42 | 19 | <1 | 0.36 | <10 | 0.02 | 23 | <1 | 0.02 | 11 | 241 |
| DNW 17 | 26 | 110 | 4283 | 3.94 | <10 | <1 | 0.44 | <10 | 0.02 | 16 | 82 | 0.02 | 9 | 80 |
| DNW 18 | 91 | 335 | >10000 | 13.42 | 20 | 2 | 0.08 | <10 | <0.01 | 31 | 107 | <0.01 | 32 | 140 |
| Harry 01 | <1 | 336 | 49 | 4.29 | <10 | 3 | 0.50 | <10 | 0.03 | 42 | 4 | 0.01 | 6 | 262 |
| Harry 02 | <1 | 158 | 12 | 3.26 | <10 | <1 | 0.70 | <10 | 0.05 | 35 | 2 | 0.02 | 3 | 386 |
| Harry 03 | 6 | 292 | 58 | 10.11 | 17 | <1 | 0.47 | <10 | 0.20 | 202 | <1 | 0.01 | 8 | 326 |
| Harry 04 | 10 | 121 | 29 | 12.54 | 19 | <1 | 0.51 | <10 | 0.38 | 557 | <1 | 0.03 | 4 | 902 |
| Harry 05 | 9 | 145 | 15 | 4.37 | <10 | <1 | 0.49 | <10 | 0.21 | 222 | 1 | <0.01 | 4 | 980 |
| Harry 06 | 18 | 70 | 73 | 3.73 | <10 | <1 | 0.56 | <10 | 0.42 | 439 | 2 | <0.01 | 7 | 1118 |
| Harry 07 | 5 | 106 | 7 | 2.33 | <10 | <1 | 0.55 | <10 | 0.06 | 31 | 2 | <0.01 | 2 | 301 |
| M19-01 | 2 | 251 | 16 | 0.40 | <10 | <1 | 0.07 | <10 | 0.01 | 113 | 7 | 0.01 | 10 | 163 |
| 2729201 | 11 | 31 | 39 | 3.19 | <10 | <1 | 0.17 | <10 | 0.83 | 3002 | 1 | 0.02 | 11 | 504 |
| 2729202 | 11 | 45 | 69 | 4.97 | <10 | <1 | 0.30 | <10 | 0.82 | 1576 | 4 | 0.03 | 27 | 1335 |
| 2729203 | 10 | 82 | 63 | 2.85 | <10 | <1 | 0.25 | <10 | 0.58 | 1262 | 3 | 0.02 | 33 | 610 |
| 2729204 | 6 | 17 | 46 | 2.94 | <10 | <1 | 0.17 | <10 | 0.34 | 4769 | 4 | 0.03 | 12 | 635 |
| 2729205 | 4 | 38 | 313 | 8.65 | 19 | <1 | 0.21 | <10 | 0.59 | 293 | 2 | 0.04 | 4 | 791 |
| 2729206 | 49 | 21 | 99 | 3.84 | 10 | 48 | 0.28 | <10 | 0.31 | 2166 | <1 | 0.01 | 7 | 537 |
| 2729207 | 5 | 74 | 303 | 9.18 | 17 | <1 | 0.17 | 13 | 0.32 | 142 | 4 | 0.02 | 5 | 523 |
| 2729208 | 6 | 40 | 508 | 10.00 | 22 | <1 | 0.18 | <10 | 0.86 | 419 | 3 | 0.03 | 4 | 870 |
| 2729209 | 7 | 57 | 31 | 3.06 | <10 | <1 | 0.25 | <10 | 0.26 | 1821 | 3 | 0.02 | 6 | 733 |
| 2729210 | 40 | 31 | 273 | 11.98 | 22 | 12 | 0.13 | <10 | 1.09 | 3922 | 1 | 0.02 | 16 | 641 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|-------------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| 2729211 | 9 | 61 | 15 | 4.54 | <10 | <1 | 0.23 | 11 | 2.61 | 1840 | 1 | 0.02 | 4 | 502 |
| 2727251 | 3 | 41 | 4 | 3.63 | <10 | <1 | 0.14 | <10 | 1.58 | 2973 | 2 | 0.02 | <1 | 230 |
| 2727252 | 8 | 17 | 14 | 6.02 | <10 | <1 | 0.09 | <10 | 2.38 | 8468 | 56 | 0.01 | 10 | 305 |
| 2727253 | 10 | 11 | 151 | 4.67 | <10 | 20 | 0.12 | <10 | 1.07 | 10395 | 4 | 0.01 | 2 | 184 |
| 2727254 | <1 | 32 | 144 | 3.31 | <10 | <1 | 0.33 | 12 | 0.23 | 155 | 8 | 0.02 | 2 | 958 |
| 2727255 | 17 | 38 | 1133 | 13.02 | 24 | 1 | 0.24 | <10 | 0.68 | 294 | 5 | 0.02 | 7 | 681 |
| 2727256 | 23 | 14 | 887 | 43.73 | 58 | <1 | 0.02 | <10 | 0.01 | 311 | 1 | 0.01 | 7 | 57 |
| 2727256PD | 24 | 17 | 907 | 45.24 | 63 | <1 | 0.02 | <10 | 0.01 | 321 | <1 | 0.01 | 8 | 81 |
| 2727257 | 13 | 43 | 589 | 21.60 | 35 | <1 | 0.17 | <10 | 0.37 | 501 | 2 | <0.01 | 7 | 656 |
| 2727258 | 23 | 46 | 548 | 11.62 | 22 | 10 | 0.17 | <10 | 0.76 | 1320 | 4 | 0.01 | 5 | 570 |
| 2727259 | 2 | 203 | 25 | 0.97 | <10 | <1 | 0.08 | <10 | 0.04 | 36 | 6 | 0.01 | 9 | 60 |
| 2727260 | 2 | 190 | 7 | 0.52 | <10 | <1 | 0.02 | <10 | <0.01 | 20 | 5 | <0.01 | 8 | 42 |
| 2727261 | 11 | 21 | 3 | 3.92 | <10 | <1 | 0.20 | 15 | 1.16 | 951 | <1 | 0.06 | 3 | 1074 |
| 2727262 | 13 | 23 | 11 | 7.22 | 10 | <1 | 0.25 | <10 | 0.41 | 2293 | 2 | 0.03 | 2 | 1012 |
| 2727263 | 5 | 49 | 9 | 4.09 | <10 | <1 | 0.09 | 13 | 3.09 | 1555 | 1 | 0.01 | <1 | 164 |
| 2727264 | 17 | 43 | 28 | 6.00 | <10 | <1 | 0.27 | <10 | 0.62 | 738 | 24 | 0.02 | 5 | 1375 |
| 2727265 | 9 | 23 | 240 | 5.07 | <10 | <1 | 0.41 | <10 | 0.26 | 2197 | 2 | 0.03 | 4 | 2193 |
| 2727266 | 17 | 29 | 1376 | 13.60 | 13 | <1 | 0.23 | <10 | 1.35 | 6449 | <1 | 0.02 | 17 | 1063 |
| 2727267 | 16 | 42 | 610 | 3.54 | <10 | <1 | 0.22 | <10 | 0.44 | 1194 | 2 | 0.02 | 17 | 932 |
| DUP H428822 | 42 | 174 | 52 | 7.29 | 23 | <1 | 0.25 | 14 | 3.56 | 894 | <1 | 0.01 | 259 | 1330 |
| DUP H428843 | 11 | 13 | 29 | 4.83 | 14 | <1 | 0.12 | <10 | 1.84 | 997 | <1 | 0.07 | 2 | 1359 |
| DUP H428741 | 5 | 52 | 5 | 2.39 | <10 | <1 | 0.36 | <10 | 1.16 | 1706 | <1 | 0.09 | 1 | 789 |
| DUP H428806 | | | | | | | | | | | | | | |
| DUP H428711 | | | | | | | | | | | | | | |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| | ICP-130 Co ppm | ICP-130 Cr ppm | ICP-130 Cu ppm | ICP-130 Fe % | ICP-130 Ga ppm | ICP-130 Hg ppm | ICP-130 K % | ICP-130 La ppm | ICP-130 Mg % | ICP-130 Mn ppm | ICP-130 Mo ppm | ICP-130 Na % | ICP-130 Ni ppm | ICP-130 P ppm |
|---------------|----------------------|----------------------|----------------------|--------------------|----------------------|----------------------|-------------------|----------------------|--------------------|----------------------|----------------------|--------------------|----------------------|---------------------|
| Sample ID | 1 | 1 | 1 | 0.01 | 10 | 1 | 0.01 | 10 | 0.01 | 5 | 1 | 0.01 | 1 | 10 |
| DUP H428722 | | | | | | | | | | | | | | |
| DUP 2727255 | | | | | | | | | | | | | | |
| STD BLANK | <1 | <1 | <1 | <0.01 | <10 | <1 | <0.01 | <10 | <0.01 | <5 | <1 | <0.01 | <1 | <10 |
| STD BLANK | <1 | <1 | <1 | <0.01 | <10 | <1 | <0.01 | <10 | <0.01 | <5 | <1 | <0.01 | <1 | <10 |
| STD BLANK | <1 | <1 | <1 | <0.01 | <10 | <1 | <0.01 | <10 | <0.01 | <5 | <1 | <0.01 | <1 | <10 |
| STD BLANK | | | | | | | | | | | | | | |
| STD BLANK | | | | | | | | | | | | | | |
| STD BLANK | | | | | | | | | | | | | | |
| STD OREAS 24b | 14 | 107 | 37 | 4.01 | 16 | <1 | 1.17 | 16 | 1.38 | 340 | 3 | 0.11 | 57 | 626 |
| STD OREAS 601 | 5 | 45 | 1020 | 2.14 | <10 | <1 | 0.25 | 14 | 0.19 | 414 | 3 | 0.08 | 23 | 360 |
| STD OREAS 24b | 14 | 106 | 37 | 3.96 | 16 | <1 | 1.16 | 14 | 1.35 | 331 | 4 | 0.10 | 56 | 604 |
| STD OxA131 | | | | | | | | | | | | | | |
| STD OxD127 | | | | | | | | | | | | | | |
| STD OxA155 | | | | | | | | | | | | | | |
| STD OxA90 | | | | | | | | | | | | | | |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|---------------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| Granite Blank | <2 | 0.01 | 2 | 3 | 26 | <8 | 0.10 | <10 | 27 | <10 | 29 | <5 |
| Granite Blank | <2 | 0.02 | 2 | 3 | 25 | <8 | 0.10 | <10 | 24 | <10 | 28 | <5 |
| H428801 | 14 | 1.22 | 3 | 3 | 73 | <8 | <0.01 | <10 | 31 | <10 | 475 | <5 |
| H428802 | 7 | 0.66 | 3 | 3 | 167 | <8 | <0.01 | <10 | 13 | <10 | 369 | <5 |
| H428803 | 7 | 1.17 | 5 | 2 | 87 | <8 | <0.01 | <10 | 25 | <10 | 814 | <5 |
| H428804 | 7 | 1.29 | 3 | 4 | 168 | <8 | <0.01 | <10 | 21 | <10 | 415 | <5 |
| H428805 | 6 | 0.37 | 3 | <2 | 98 | <8 | <0.01 | <10 | 6 | <10 | 114 | <5 |
| H428806 | 5 | 1.68 | 11 | 3 | 150 | <8 | <0.01 | <10 | 38 | <10 | 1956 | <5 |
| H428807 | 11 | 2.21 | 10 | 4 | 176 | <8 | <0.01 | <10 | 23 | <10 | 542 | <5 |
| H428808 | 33 | 3.73 | 15 | 4 | 308 | <8 | <0.01 | <10 | 32 | <10 | 816 | <5 |
| H428809 | 8 | 2.65 | 9 | 4 | 499 | <8 | <0.01 | <10 | 23 | <10 | 608 | <5 |
| H428810 | <2 | 0.02 | <2 | 3 | 48 | <8 | 0.18 | <10 | 43 | <10 | 59 | <5 |
| H428811 | 5 | 2.47 | 8 | 4 | 220 | <8 | <0.01 | <10 | 24 | <10 | 846 | <5 |
| H428812 | 17 | 2.25 | 9 | 3 | 245 | <8 | <0.01 | <10 | 22 | <10 | 1035 | <5 |
| H428813 | <2 | 0.32 | <2 | 2 | 255 | <8 | <0.01 | <10 | 34 | <10 | 53 | <5 |
| H428814 | 11 | 0.84 | 4 | 5 | 580 | <8 | <0.01 | <10 | 64 | <10 | 153 | <5 |
| H428815 | 3 | 1.09 | 3 | 4 | 589 | <8 | <0.01 | <10 | 34 | <10 | 57 | <5 |
| H428816 | 11 | 2.59 | <2 | 4 | 561 | <8 | <0.01 | <10 | 28 | <10 | 94 | <5 |
| H428817 | <2 | 1.34 | 4 | 4 | 381 | <8 | 0.01 | <10 | 48 | <10 | 88 | <5 |
| H428818 | <2 | 0.32 | <2 | 4 | 519 | <8 | <0.01 | <10 | 36 | <10 | 79 | <5 |
| H428819 | <2 | 0.13 | <2 | 5 | 446 | <8 | <0.01 | <10 | 39 | <10 | 86 | <5 |
| H428820 | 4491 | >10 | 14 | 12 | 9 | <8 | 0.13 | <10 | 119 | 23 | 2468 | <5 |
| H428821 | <2 | 0.19 | 4 | 6 | 366 | <8 | 0.01 | <10 | 32 | <10 | 110 | <5 |
| H428822 | 3 | 0.32 | 4 | 5 | 232 | <8 | 0.01 | <10 | 26 | <10 | 124 | <5 |
| H428823 | 3 | 0.28 | 3 | 6 | 409 | <8 | 0.01 | <10 | 28 | <10 | 130 | <5 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|-----------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| H428824 | 17 | 1.60 | 9 | 2 | 290 | <8 | <0.01 | <10 | 132 | <10 | 636 | 6 |
| H428825 | <2 | 0.99 | 3 | 2 | 279 | <8 | <0.01 | <10 | 24 | <10 | 94 | <5 |
| H428826 | 3 | 0.59 | 6 | 3 | 783 | <8 | <0.01 | <10 | 36 | <10 | 76 | <5 |
| H428827 | 6 | 0.57 | 4 | 3 | 229 | <8 | <0.01 | <10 | 39 | <10 | 95 | <5 |
| H428828 | 9 | 0.74 | 2 | 3 | 315 | <8 | <0.01 | <10 | 37 | <10 | 88 | <5 |
| H428829 | 5 | 0.49 | <2 | 3 | 201 | <8 | <0.01 | <10 | 39 | <10 | 95 | <5 |
| H428830 | <2 | <0.01 | <2 | 2 | 42 | <8 | 0.18 | <10 | 42 | <10 | 52 | <5 |
| H428831 | 8 | 0.71 | <2 | 3 | 192 | <8 | <0.01 | <10 | 39 | <10 | 89 | <5 |
| H428832 | 7 | 0.78 | <2 | 3 | 242 | <8 | <0.01 | <10 | 39 | <10 | 94 | <5 |
| H428832PD | 9 | 0.75 | 3 | 3 | 237 | <8 | <0.01 | <10 | 41 | <10 | 95 | <5 |
| H428833 | 15 | 0.55 | <2 | 3 | 206 | <8 | <0.01 | <10 | 43 | <10 | 107 | <5 |
| H428834 | 13 | 0.70 | <2 | 3 | 223 | <8 | <0.01 | <10 | 34 | <10 | 102 | <5 |
| H428835 | 12 | 0.82 | 3 | 3 | 241 | <8 | <0.01 | <10 | 42 | <10 | 87 | <5 |
| H428836 | 9 | 0.45 | <2 | 7 | 192 | <8 | <0.01 | <10 | 105 | <10 | 84 | <5 |
| H428837 | 11 | 0.51 | <2 | 9 | 258 | <8 | <0.01 | <10 | 123 | <10 | 85 | <5 |
| H428838 | 5 | 0.50 | <2 | 10 | 216 | <8 | <0.01 | <10 | 120 | <10 | 77 | <5 |
| H428839 | 9 | 0.54 | 4 | 8 | 184 | <8 | <0.01 | <10 | 98 | <10 | 84 | <5 |
| H428840 | 4489 | >10 | 20 | 12 | 10 | 9 | 0.13 | <10 | 128 | 17 | 2457 | 6 |
| H428841 | 15 | 0.85 | 4 | 4 | 318 | <8 | <0.01 | <10 | 61 | <10 | 78 | <5 |
| H428842 | 7 | 0.30 | 4 | 7 | 253 | <8 | <0.01 | <10 | 98 | <10 | 75 | <5 |
| H428843 | 8 | 0.21 | <2 | 6 | 213 | <8 | <0.01 | <10 | 84 | <10 | 78 | <5 |
| H428844 | 9 | 0.74 | 2 | 4 | 215 | <8 | <0.01 | <10 | 54 | <10 | 90 | <5 |
| H428845 | 9 | 0.37 | 2 | 3 | 240 | <8 | <0.01 | <10 | 38 | <10 | 87 | <5 |
| H428846 | 12 | 0.43 | 3 | 3 | 197 | <8 | <0.01 | <10 | 41 | <10 | 93 | <5 |
| H428847 | 16 | 0.28 | <2 | 3 | 233 | <8 | <0.01 | <10 | 26 | <10 | 91 | <5 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|-----------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| | 2 | 0.01 | 2 | 2 | 1 | 8 | 0.01 | 10 | 1 | 10 | 1 | 5 |
| H428848 | 8 | 0.42 | <2 | 3 | 149 | <8 | <0.01 | <10 | 39 | <10 | 102 | <5 |
| H428849 | 9 | 0.36 | 3 | 3 | 247 | <8 | <0.01 | <10 | 27 | <10 | 102 | <5 |
| H428850 | 3 | <0.01 | 3 | 2 | 43 | <8 | 0.16 | <10 | 46 | <10 | 54 | <5 |
| H428701 | 10 | 0.33 | <2 | 3 | 153 | <8 | <0.01 | <10 | 20 | <10 | 86 | <5 |
| H428702 | 6 | 0.13 | <2 | 7 | 373 | <8 | 0.01 | <10 | 86 | <10 | 103 | 5 |
| H428703 | 6 | 0.18 | 6 | 7 | 517 | <8 | <0.01 | <10 | 69 | <10 | 97 | <5 |
| H428704 | 8 | 0.07 | 3 | 5 | 524 | <8 | 0.01 | <10 | 56 | <10 | 108 | 7 |
| H428705 | 8 | 0.08 | <2 | 4 | 392 | <8 | 0.01 | <10 | 55 | <10 | 119 | 8 |
| H428706 | 6 | 0.02 | 4 | 4 | 625 | <8 | <0.01 | <10 | 40 | <10 | 100 | 7 |
| H428707 | 8 | 0.04 | <2 | 4 | 608 | <8 | 0.01 | <10 | 41 | <10 | 96 | 7 |
| H428708 | 7 | 0.05 | <2 | 4 | 414 | <8 | 0.01 | <10 | 37 | <10 | 96 | 6 |
| H428709 | 10 | 0.07 | 2 | 6 | 521 | <8 | 0.01 | <10 | 45 | <10 | 99 | 5 |
| H428710 | 4 | <0.01 | <2 | 3 | 39 | <8 | 0.17 | <10 | 47 | <10 | 59 | <5 |
| H428711 | 7 | 0.08 | 4 | 5 | 582 | <8 | <0.01 | <10 | 50 | <10 | 68 | <5 |
| H428712 | 3 | 0.01 | 3 | 4 | 177 | <8 | <0.01 | <10 | 34 | <10 | 78 | <5 |
| H428713 | 8 | 0.03 | <2 | 5 | 244 | <8 | <0.01 | <10 | 32 | <10 | 70 | <5 |
| H428714 | 7 | 0.05 | <2 | 7 | 257 | <8 | <0.01 | <10 | 66 | <10 | 81 | <5 |
| H428715 | 5 | 0.08 | <2 | 7 | 216 | <8 | <0.01 | <10 | 74 | <10 | 74 | <5 |
| H428715PD | 4 | 0.10 | <2 | 7 | 210 | <8 | <0.01 | <10 | 70 | <10 | 74 | <5 |
| H428716 | 7 | 0.05 | <2 | 4 | 151 | <8 | <0.01 | <10 | 48 | <10 | 91 | <5 |
| H428717 | <2 | 0.09 | <2 | 3 | 224 | <8 | <0.01 | <10 | 35 | <10 | 70 | <5 |
| H428718 | 13 | 0.07 | <2 | <2 | 225 | <8 | <0.01 | <10 | 6 | <10 | 33 | <5 |
| H428719 | 28 | 0.13 | 4 | 3 | 309 | <8 | <0.01 | <10 | 9 | <10 | 95 | <5 |
| H428720 | 4549 | >10 | 12 | 12 | 11 | <8 | 0.13 | <10 | 120 | 16 | 2469 | <5 |
| H428721 | 3 | 0.05 | 5 | 3 | 448 | <8 | <0.01 | <10 | 9 | <10 | 44 | <5 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|-----------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| H428722 | <2 | 0.16 | <2 | 3 | 370 | <8 | <0.01 | <10 | 13 | <10 | 48 | <5 |
| H428723 | 13 | 0.02 | <2 | 3 | 281 | <8 | <0.01 | <10 | 21 | <10 | 69 | <5 |
| H428724 | 5 | 0.02 | <2 | 5 | 303 | <8 | 0.01 | <10 | 46 | <10 | 80 | <5 |
| H428725 | 2 | 0.07 | 3 | 5 | 310 | <8 | 0.01 | <10 | 36 | <10 | 68 | <5 |
| H428726 | <2 | 0.06 | 4 | 4 | 385 | <8 | 0.02 | <10 | 33 | <10 | 55 | <5 |
| H428727 | <2 | 0.13 | 3 | 3 | 298 | <8 | 0.02 | <10 | 31 | <10 | 66 | <5 |
| H428728 | 4 | 0.07 | 7 | 4 | 467 | <8 | <0.01 | <10 | 27 | <10 | 36 | <5 |
| H428729 | 3 | 0.16 | 3 | 3 | 399 | <8 | <0.01 | <10 | 23 | <10 | 35 | <5 |
| H428730 | <2 | <0.01 | <2 | 3 | 69 | <8 | 0.19 | <10 | 43 | <10 | 49 | <5 |
| H428731 | 153 | 6.75 | 9 | 3 | 518 | <8 | <0.01 | <10 | 26 | <10 | 41 | <5 |
| H428732 | 4 | 0.04 | 5 | 5 | 319 | <8 | 0.01 | <10 | 44 | <10 | 65 | <5 |
| H428733 | <2 | 0.04 | 3 | 6 | 297 | <8 | 0.02 | <10 | 51 | <10 | 35 | <5 |
| H428734 | 2 | 0.05 | 4 | 6 | 350 | <8 | 0.02 | <10 | 50 | <10 | 32 | <5 |
| H428735 | <2 | 0.12 | 3 | 7 | 340 | <8 | 0.04 | <10 | 56 | <10 | 71 | <5 |
| H428736 | <2 | 0.23 | 4 | 6 | 358 | <8 | 0.03 | <10 | 56 | <10 | 81 | <5 |
| H428737 | 10 | 0.19 | <2 | 3 | 342 | <8 | <0.01 | <10 | 37 | <10 | 88 | <5 |
| H428738 | 24 | 0.06 | 3 | <2 | 347 | <8 | <0.01 | <10 | 20 | <10 | 47 | 8 |
| H428739 | <2 | 0.11 | <2 | 2 | 233 | <8 | <0.01 | <10 | 23 | <10 | 44 | 9 |
| H428740 | 4495 | >10 | 12 | 12 | 11 | <8 | 0.14 | <10 | 120 | 19 | 2443 | 5 |
| H428741 | 5 | 0.13 | <2 | 2 | 376 | <8 | <0.01 | <10 | 31 | <10 | 45 | 9 |
| H428742 | <2 | 0.08 | <2 | <2 | 286 | <8 | <0.01 | <10 | 21 | <10 | 36 | 10 |
| DNW 08 | 32 | 0.61 | 8 | 3 | 155 | <8 | <0.01 | <10 | 67 | <10 | 17 | 7 |
| DNW 09 | 13 | 0.60 | 7 | <2 | 8 | <8 | <0.01 | <10 | 7 | <10 | 184 | 12 |
| DNW 10 | 9 | 2.11 | 4 | <2 | 17 | <8 | <0.01 | <10 | 4 | <10 | 12 | 7 |
| DNW 11 | 51 | >10 | 11 | <2 | 270 | <8 | <0.01 | <10 | 12 | <10 | 3 | 6 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|-----------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| DNW 12 | 68 | >10 | 9 | <2 | 1097 | <8 | <0.01 | <10 | 13 | <10 | 2 | 8 |
| DNW 13 | 85 | >10 | 10 | 6 | 18 | <8 | <0.01 | <10 | 22 | <10 | 121 | 11 |
| DNW 14 | 101 | 0.33 | 5 | <2 | 30 | <8 | 0.01 | <10 | 18 | <10 | 224 | 5 |
| DNW 15 | 14 | 3.73 | 5 | <2 | 34 | <8 | <0.01 | <10 | 16 | <10 | 2 | 11 |
| DNW 16 | 25 | >10 | 10 | <2 | 8 | <8 | <0.01 | <10 | 16 | <10 | 10 | 7 |
| DNW 17 | 15 | 4.35 | 45 | 3 | 5 | <8 | <0.01 | <10 | 19 | <10 | 32 | 18 |
| DNW 18 | 136 | >10 | 8 | 5 | 29 | <8 | <0.01 | <10 | 38 | <10 | 48 | 5 |
| Harry 01 | >10000 | 1.47 | 20 | <2 | 9 | <8 | <0.01 | <10 | 13 | 144 | 128 | <5 |
| Harry 02 | 1239 | 0.84 | 5 | <2 | 15 | <8 | <0.01 | <10 | 24 | <10 | 41 | <5 |
| Harry 03 | 745 | 9.02 | 10 | 3 | 9 | <8 | <0.01 | <10 | 36 | 139 | 354 | <5 |
| Harry 04 | 254 | >10 | 11 | 4 | 17 | <8 | <0.01 | <10 | 34 | <10 | 403 | 5 |
| Harry 05 | 389 | 3.31 | 4 | 3 | 11 | <8 | <0.01 | <10 | 30 | <10 | 643 | <5 |
| Harry 06 | 17 | 1.35 | 7 | 3 | 8 | <8 | <0.01 | <10 | 40 | <10 | 48 | <5 |
| Harry 07 | 48 | 1.77 | 5 | <2 | 4 | <8 | <0.01 | <10 | 15 | <10 | 16 | <5 |
| M19-01 | 5 | 0.02 | <2 | <2 | 9 | <8 | <0.01 | <10 | 4 | <10 | 16 | <5 |
| 2729201 | 23 | 0.45 | <2 | 5 | 1031 | <8 | <0.01 | <10 | 31 | <10 | 185 | <5 |
| 2729202 | 85 | 1.55 | 7 | 5 | 237 | <8 | <0.01 | <10 | 49 | <10 | 272 | <5 |
| 2729203 | 14 | 0.09 | 8 | 4 | 281 | <8 | <0.01 | <10 | 34 | <10 | 105 | <5 |
| 2729204 | 144 | 0.06 | <2 | 2 | 703 | <8 | <0.01 | <10 | 13 | <10 | 1114 | <5 |
| 2729205 | 92 | 0.23 | 4 | 3 | 136 | <8 | <0.01 | <10 | 68 | <10 | 76 | 8 |
| 2729206 | 103 | >10 | 4 | 2 | 67 | <8 | <0.01 | <10 | 19 | <10 | >10000 | <5 |
| 2729207 | 1173 | 0.51 | 35 | <2 | 7 | <8 | <0.01 | <10 | 39 | <10 | 1561 | 5 |
| 2729208 | 97 | 0.21 | 11 | 3 | 4 | <8 | <0.01 | <10 | 98 | <10 | 224 | 10 |
| 2729209 | 23 | 0.02 | 3 | 2 | 223 | <8 | <0.01 | <10 | 17 | <10 | 206 | <5 |
| 2729210 | 250 | 1.54 | <2 | 4 | 124 | <8 | 0.02 | 13 | 63 | <10 | >10000 | 8 |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| Sample ID | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|-------------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| | 2 | 0.01 | 2 | 2 | 1 | 8 | 0.01 | 10 | 1 | 10 | 1 | 5 |
| 2729211 | 14 | 0.02 | 4 | 4 | 453 | <8 | <0.01 | <10 | 21 | <10 | 341 | <5 |
| 2727251 | 11 | 0.06 | <2 | <2 | 789 | <8 | <0.01 | <10 | 8 | <10 | 128 | <5 |
| 2727252 | 126 | 0.30 | 4 | 4 | 859 | <8 | <0.01 | <10 | 50 | <10 | 1311 | <5 |
| 2727253 | 52 | 3.19 | 12 | 3 | 500 | <8 | <0.01 | 11 | 25 | <10 | >10000 | <5 |
| 2727254 | 1054 | 0.26 | 302 | 2 | 14 | <8 | <0.01 | <10 | 23 | <10 | 725 | 7 |
| 2727255 | 596 | 0.33 | 18 | 3 | 5 | <8 | <0.01 | <10 | 65 | <10 | 823 | 8 |
| 2727256 | 886 | 0.50 | 72 | <2 | 64 | <8 | <0.01 | <10 | 33 | 11 | 1118 | 10 |
| 2727256PD | 943 | 0.51 | 78 | <2 | 72 | <8 | <0.01 | <10 | 33 | <10 | 1128 | 9 |
| 2727257 | 208 | 0.14 | 56 | 2 | 76 | <8 | <0.01 | <10 | 72 | 10 | 116 | 9 |
| 2727258 | 883 | 1.99 | 11 | <2 | 117 | <8 | <0.01 | <10 | 48 | <10 | >10000 | 6 |
| 2727259 | 24 | 0.04 | <2 | <2 | 11 | <8 | <0.01 | <10 | 7 | <10 | 263 | <5 |
| 2727260 | 4 | <0.01 | <2 | <2 | 2 | <8 | <0.01 | <10 | 3 | <10 | 22 | <5 |
| 2727261 | <2 | 0.03 | <2 | 5 | 312 | <8 | <0.01 | <10 | 17 | <10 | 56 | 8 |
| 2727262 | 29 | 0.08 | <2 | 6 | 227 | <8 | <0.01 | <10 | 46 | <10 | 57 | <5 |
| 2727263 | 14 | <0.01 | <2 | <2 | 540 | <8 | <0.01 | <10 | 8 | <10 | 60 | <5 |
| 2727264 | 42 | 0.84 | 5 | 3 | 27 | <8 | <0.01 | <10 | 31 | <10 | 55 | 8 |
| 2727265 | 7 | 0.05 | <2 | 6 | 41 | <8 | <0.01 | <10 | 25 | <10 | 32 | <5 |
| 2727266 | 14 | 0.40 | 3 | 9 | 106 | <8 | <0.01 | 11 | 60 | <10 | 32 | 5 |
| 2727267 | 13 | 1.74 | 9 | <2 | 115 | <8 | <0.01 | <10 | 11 | <10 | 24 | <5 |
| DUP H428822 | <2 | 0.31 | 5 | 5 | 234 | <8 | 0.01 | <10 | 26 | <10 | 130 | <5 |
| DUP H428843 | 4 | 0.21 | <2 | 6 | 209 | <8 | <0.01 | <10 | 84 | <10 | 78 | <5 |
| DUP H428741 | <2 | 0.13 | <2 | 2 | 366 | <8 | <0.01 | <10 | 31 | <10 | 46 | 8 |
| DUP H428806 | | | | | | | | | | | | |
| DUP H428711 | | | | | | | | | | | | |

***Please refer to the cover page for comments regarding this test report. ***



MSALABS
 Unit 1, 20120 102nd Avenue
 Langley, BC V1M 4B4
 Phone: +1-604-888-0875

To: **Teuton Resources Corp**
2130 Crescent Road
Victoria, BC, V8S 2H3
Canada

| | |
|---------------------|-------------------|
| TEST REPORT: | YVR1910610 |
|---------------------|-------------------|

Project Name:
 Job Received Date: 11-Sep-2019
 Job Report Date: 18-Oct-2019
 Report Version: Final

| | ICP-130 Pb ppm | ICP-130 S % | ICP-130 Sb ppm | ICP-130 Sc ppm | ICP-130 Sr ppm | ICP-130 Th ppm | ICP-130 Ti % | ICP-130 Tl ppm | ICP-130 V ppm | ICP-130 W ppm | ICP-130 Zn ppm | ICP-130 Zr ppm |
|---------------|----------------------|-------------------|----------------------|----------------------|----------------------|----------------------|--------------------|----------------------|---------------------|---------------------|----------------------|----------------------|
| Sample ID | 2 | 0.01 | 2 | 2 | 1 | 8 | 0.01 | 10 | 1 | 10 | 1 | 5 |
| DUP H428722 | | | | | | | | | | | | |
| DUP 2727255 | | | | | | | | | | | | |
| STD BLANK | <2 | <0.01 | <2 | <2 | <1 | <8 | <0.01 | <10 | <1 | <10 | <1 | <5 |
| STD BLANK | <2 | <0.01 | <2 | <2 | <1 | <8 | <0.01 | <10 | <1 | <10 | <1 | <5 |
| STD BLANK | <2 | <0.01 | <2 | <2 | <1 | <8 | <0.01 | <10 | <1 | <10 | <1 | <5 |
| STD BLANK | | | | | | | | | | | | |
| STD BLANK | | | | | | | | | | | | |
| STD BLANK | | | | | | | | | | | | |
| STD OREAS 24b | 12 | 0.20 | 4 | 10 | 31 | 13 | 0.21 | <10 | 79 | <10 | 97 | 28 |
| STD OREAS 601 | 286 | 1.02 | 23 | <2 | 35 | <8 | 0.01 | <10 | 9 | <10 | 1351 | 24 |
| STD OREAS 24b | 9 | 0.20 | <2 | 10 | 30 | 10 | 0.20 | <10 | 78 | <10 | 97 | 25 |
| STD OxA131 | | | | | | | | | | | | |
| STD OxD127 | | | | | | | | | | | | |
| STD OxA155 | | | | | | | | | | | | |
| STD OxA90 | | | | | | | | | | | | |

***Please refer to the cover page for comments regarding this test report. ***